



Volume 22, No.21

State	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
AL	26	58.4	49.4	38,437	28	63.9	53.6	611,514
AR	12	90.0	75.7	39,276	29	95.1	86.8	1,190,650
AZ	9	82.8	69.6	19,911	10	81.1	57.5	198,101
CA	6	97.6	92.7	9,839	13	94.7	83.5	100,758
FL	4	33.3	28.6	5,925	4	41.8	39.5	75,148
GA	58	52.0	44.6	235,252	59	51.2	44.1	1,627,345
KS	3	30.3	16.8	12,808	3	33.1	20.3	94,889
LA	3	89.9	57.0	3,418	19	87.6	70.2	334,798
MO	14	92.5	82.7	46,321	20	94.4	84.2	575,871
MS	22	88.0	65.9	15,428	37	86.8	63.7	1,112,352
NC	31	91.1	79.7	35,580	33	92.5	82.2	477,424
NM	2	91.0	85.0	721	2	88.4	71.2	22,053
OK	12	72.2	52.6	33,428	12	80.1	66.2	315,833
SC	15	86.7	74.5	21,813	15	90.8	81.5	192,293
TN	11	86.1	63.2	18,362	21	90.4	73.4	580,916
TX	90	51.0	36.7	147,539	175	74.0	59.3	4,406,889
VA	4	93.2	83.7	13,744	4	94.2	86.0	92,674
United States	322	64.7	53.1	697,802	484	76.9	63.7	12,009,508
AMERICAN PIMA								
AZ	3			994	3			4,687
CA	11			24,538	14			282,563
NM*	-			-	-			-
TX	2			3,496	3			24,349
United States	17			32,201	21			324,705
United States all cotton	336			730,003	497			12,334,213

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 24, 2020

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	0.1	0.1	0.3	0.2	69.5	77.8	46.5	54.7	-	0.2	0.4	0.4
	3	0.2	0.2	0.5	0.3	3.9	3.9	10.2	9.3	-	0.2	0.4	0.4
	4	*	*	-	*	0.1	0.1	*	0.5	-	*	*	*
	5	*	*	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.3	0.4	0.8	0.5	73.5	81.7	56.7	64.4	-	0.4	0.8	0.8
31	1 - 2	4.3	2.6	2.0	1.7	14.6	6.6	19.1	20.0	0.3	1.3	3.0	2.6
	3	14.7	16.5	11.7	13.7	8.6	4.7	19.0	11.2	7.0	12.4	17.9	16.8
	4	4.4	8.3	5.0	6.7	1.8	1.0	2.5	1.5	4.0	5.5	4.9	5.9
	5	0.3	0.6	0.3	0.4	0.2	0.1	0.3	0.1	0.1	0.3	0.2	0.3
	6	*	*	-	*	*	*	-	-	-	*	*	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	23.6	27.9	19.0	22.5	25.3	12.4	41.0	32.8	11.4	19.6	26.0	25.7
41	1 - 2	2.8	1.4	1.1	0.6	0.4	0.2	0.1	0.4	0.1	0.3	2.0	1.3
	3	26.2	21.7	31.0	21.4	0.3	0.2	0.6	0.9	18.0	16.3	31.1	24.0
	4	27.0	27.1	34.9	39.7	0.2	0.2	0.7	0.5	39.3	34.8	25.9	26.4
	5	6.3	6.4	6.5	10.2	0.2	0.1	0.1	0.1	8.5	9.5	4.3	5.3
	6	0.6	0.5	0.3	0.5	0.1	*	*	*	0.5	0.7	0.3	0.3
	7	*	*	-	*	*	*	-	-	*	*	*	*
	8	-	*	-	*	*	*	-	-	-	-	-	*
Total	----	62.9	57.1	73.8	72.4	1.2	0.7	1.5	1.8	66.3	61.7	63.7	57.3
51	1 - 2	0.1	*	0.1	*	-	*	-	-	-	*	*	*
	3	0.7	0.5	1.1	0.3	-	*	-	*	2.0	1.2	0.9	0.7
	4	2.1	1.7	1.6	1.9	-	-	-	-	10.5	4.7	2.3	2.3
	5	1.5	1.2	1.5	1.2	-	-	-	-	3.6	2.1	0.9	1.3
	6	0.4	0.2	0.2	0.1	-	*	-	-	0.3	0.3	0.1	0.3
	7	*	*	*	*	-	*	-	-	*	*	*	*
	8	-	*	-	*	-	*	-	-	-	-	*	*
Total	----	4.8	3.7	4.5	3.6	-	*	-	*	16.4	8.4	4.2	4.6
61	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	*	*	-	*	-	-	-	-	*	*	*	*
	4	*	*	-	-	-	-	-	-	0.2	*	*	*
	5	*	*	-	-	-	-	-	-	0.2	*	*	*
	6	*	*	-	*	-	-	-	-	0.2	*	-	*
	7	*	*	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.1	*	-	*	-	-	-	-	0.6	0.1	*	*
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	*	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	-	-	-	-	-	-	-	-
12 & 22	1 - 2	-	*	-	*	*	3.8	0.2	0.1	-	-	*	*
	3	-	*	-	*	-	0.8	0.2	0.1	-	-	*	*
	4	-	*	-	-	-	0.1	*	*	-	-	-	*
	5	-	-	-	-	-	*	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	*	*	4.7	0.4	0.2	-	-	*	*
32	1 - 2	*	0.1	*	*	-	0.1	0.1	0.3	-	*	*	0.1
	3	0.3	0.6	0.2	0.1	-	0.1	0.1	0.2	0.4	0.2	0.2	0.4
	4	0.1	0.5	0.2	0.1	-	0.1	0.1	*	0.5	0.2	0.1	0.2
	5	0.1	0.1	*	*	*	*	0.1	*	-	*	*	*
	6	*	*	-	*	*	*	-	-	-	-	-	*
	7	-	-	-	-	*	*	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.6	1.2	0.4	0.2	*	0.4	0.4	0.5	0.9	0.4	0.3	0.7
42	1 - 2	0.1	0.1	-	*	-	*	-	*	*	*	*	0.1
	3	1.4	1.7	0.2	0.1	-	*	*	0.1	0.9	1.2	1.0	2.3
	4	2.0	3.2	0.8	0.4	-	-	*	*	0.8	2.0	1.4	3.3
	5	0.7	1.1	0.2	0.2	*	*	-	*	0.1	0.5	0.4	0.8
	6	0.1	0.1	*	*	*	*	-	-	-	*	*	0.1
	7	*	*	-	*	*	*	-	-	-	-	-	*
	8	-	-	-	-	*	*	-	-	-	-	-	-
Total	----	4.3	6.2	1.3	0.8	*	*	*	0.1	1.8	3.7	2.7	6.5

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 24, 2020

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	*	-	*	-	-	-	-	*	*	*	*
	3	0.3	0.3	-	*	-	-	-	*	0.3	0.9	0.2	0.4
	4	0.9	1.0	*	*	-	-	-	-	0.9	2.4	0.8	1.4
	5	0.7	0.7	*	*	-	-	-	-	0.6	1.0	0.4	1.0
	6	0.2	0.2	*	*	-	-	-	-	0.1	0.1	0.1	0.2
	7	*	*	*	*	*	*	-	-	-	*	*	*
	8	-	*	*	*	-	-	-	-	-	-	*	*
Total	----	2.1	2.3	0.1	0.1	*	*	-	*	1.8	4.3	1.5	3.0
62	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	*	*	-	*	-	-	-	-	-	*	*	*
	4	0.1	0.1	-	*	-	-	-	-	0.1	0.1	*	*
	5	0.1	0.1	-	-	-	-	-	-	0.2	0.1	*	*
	6	*	*	-	-	-	-	-	-	0.2	*	*	*
	7	-	*	-	-	-	-	-	-	-	*	-	*
	8	-	*	-	-	-	-	-	-	-	-	-	*
Total	----	0.2	0.2	-	*	-	-	-	-	0.6	0.3	*	0.1
13 & 23	1 - 2	-	-	-	-	-	0.1	-	*	-	-	-	*
	3	-	*	-	-	-	*	-	*	-	-	*	*
	4	-	*	-	-	-	*	-	-	-	-	-	*
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	-	-	0.1	-	*	-	-	*	*
33	1 - 2	*	*	-	-	-	*	-	*	-	-	*	*
	3	*	*	*	*	-	*	-	*	-	*	*	*
	4	*	*	*	*	-	*	*	*	-	*	*	*
	5	*	*	-	*	-	*	-	-	-	*	*	*
	6	*	*	-	-	-	-	-	-	-	-	-	*
	7	*	*	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.1	0.1	*	*	-	*	*	*	-	*	0.1	0.1
43	1 - 2	*	*	-	-	-	-	-	-	*	*	*	*
	3	0.2	0.1	*	*	-	-	-	-	0.1	0.2	0.2	0.2
	4	0.3	0.2	*	*	-	*	-	*	0.1	0.2	0.2	0.3
	5	0.1	0.1	*	*	-	*	-	-	*	*	*	0.1
	6	*	*	*	*	-	-	-	-	-	*	*	*
	7	*	*	-	*	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.6	0.4	0.1	0.1	-	*	-	*	0.2	0.5	0.5	0.6
53	1 - 2	-	*	-	*	-	-	-	-	-	*	-	*
	3	*	0.1	-	*	-	-	-	-	*	0.2	*	0.1
	4	0.1	0.1	-	*	-	-	-	-	0.1	0.2	0.1	0.2
	5	0.1	0.1	-	*	-	-	-	-	*	0.1	0.1	0.2
	6	*	*	-	-	-	-	-	-	-	*	*	*
	7	-	*	*	*	-	-	-	-	-	-	*	*
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	----	0.3	0.3	*	*	-	-	-	-	0.1	0.5	0.2	0.5
63	1 - 2	-	*	-	-	-	-	-	-	-	-	-	-
	3	-	*	-	-	-	-	-	-	-	-	*	*
	4	-	*	-	-	-	-	-	-	-	*	*	*
	5	*	*	-	*	-	-	-	-	-	*	*	*
	6	-	*	-	-	-	-	-	-	-	-	*	*
	7	-	*	-	-	-	-	-	-	-	*	*	*
	8	-	-	-	-	*	*	-	-	-	-	-	*
Total	----	*	0.1	-	*	*	*	-	-	-	*	*	0.1
24 - 54	1 - 8	0.1	*	-	*	*	*	-	-	-	*	*	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-	*	*
81 - 85	1 - 8	*	*	-	-	-	-	-	-	-	-	*	*
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	-	-	-	-	-	-	-	-	-	-	-
31		-	*	-	-	*	*	-	-	-	*	*	*
32		*	*	*	*	0.1	*	-	*	-	*	*	*
33		0.3	0.2	0.1	*	0.2	0.4	0.1	*	-	0.3	0.3	0.4
34		1.1	1.3	0.5	*	2.0	1.9	2.0	0.8	0.7	1.1	2.6	2.2
35		6.4	5.4	1.9	0.5	7.3	9.4	2.6	4.5	5.8	3.6	9.6	7.9
36		15.8	14.2	4.9	2.8	18.0	20.9	2.3	15.5	14.6	8.7	19.1	16.8
37		38.9	32.9	20.0	21.7	40.0	33.4	33.3	28.2	27.6	23.8	37.6	34.3
38		24.0	27.4	23.0	24.0	22.9	22.3	34.1	29.5	31.0	40.9	21.8	25.0
39		12.0	15.2	32.0	28.8	8.6	9.5	22.9	18.6	16.9	20.0	8.0	11.5
40 & Longer		1.4	3.4	17.6	22.3	1.0	2.3	2.8	2.7	3.4	1.6	1.0	1.9
Average Staple		37.19	37.39	38.33	38.48	37.03	37.01	37.75	37.48	37.47	37.65	36.93	37.13
Average Length		1.16	1.17	1.20	1.20	1.16	1.16	1.18	1.17	1.17	1.18	1.15	1.16

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 24, 2020

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	8.7	23.5	20.7	1.9	0.3	0.7	0.8	0.8	*	0.2	91.0	91.9
	3	9.7	16.4	11.6	3.7	0.4	0.4	0.5	1.0	0.2	0.3	1.5	2.1
	4	0.4	2.0	0.1	0.2	*	*	-	*	*	*	-	-
	5	-	0.1	-	*	-	-	-	*	-	*	-	-
	6	-	*	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	18.8	42.0	32.4	5.9	0.7	1.0	1.3	1.8	0.2	0.5	92.5	94.0
31	1 - 2	3.6	2.5	1.4	1.6	2.0	5.3	7.0	2.6	1.2	2.9	4.3	3.8
	3	21.9	16.1	20.4	18.6	21.0	17.7	19.9	17.6	13.3	18.7	0.3	1.3
	4	13.7	14.4	3.2	10.9	4.6	4.4	2.4	9.7	4.9	6.4	0.1	*
	5	2.5	3.3	-	0.5	0.4	0.2	*	0.8	0.2	0.3	-	-
	6	0.4	0.3	-	*	*	*	-	*	*	*	-	-
	7	*	*	-	-	-	-	-	*	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	42.0	36.6	25.0	31.7	27.9	27.7	29.4	30.8	19.5	28.3	4.7	5.1
41	1 - 2	-	*	0.1	0.4	1.9	2.0	5.0	1.0	1.9	1.9	-	*
	3	0.5	0.2	13.3	16.1	38.6	31.0	40.1	19.7	37.6	33.6	-	*
	4	3.5	1.9	12.5	29.6	24.3	29.2	18.5	31.9	29.5	25.1	-	-
	5	5.1	3.1	0.6	6.4	3.0	4.5	1.8	9.2	2.7	2.7	-	*
	6	2.8	1.6	*	0.3	0.1	0.1	0.2	0.6	0.1	0.1	-	-
	7	0.8	0.6	-	*	*	*	-	*	*	*	-	-
	8	0.4	0.2	-	-	-	-	-	-	-	-	-	-
Total	----	13.0	7.5	26.6	52.8	68.0	66.8	65.7	62.3	71.8	63.5	-	*
51	1 - 2	-	-	-	*	*	*	*	*	*	*	-	-
	3	-	*	-	0.2	0.8	0.8	0.1	0.2	1.0	0.9	-	-
	4	-	-	-	0.9	1.5	2.1	0.1	0.9	2.4	1.6	-	-
	5	-	*	-	0.3	0.5	1.0	0.3	0.7	0.4	0.3	-	-
	6	*	*	-	*	*	0.1	0.2	0.1	*	*	-	-
	7	0.3	0.1	-	*	*	*	*	*	-	*	-	-
	8	0.8	0.3	-	-	-	-	-	-	-	*	-	-
Total	----	1.2	0.4	-	1.4	2.7	3.9	0.6	1.9	3.9	2.9	-	-
61	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	*	-	-	-	-
	4	-	-	-	*	-	-	-	*	-	-	-	-
	5	-	-	-	*	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	-	-	-	*	-	-	-	-
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	-	-	-	-	-
12 & 22	1 - 2	2.0	0.7	0.3	*	*	*	-	*	*	*	-	0.4
	3	1.6	1.2	0.4	0.1	*	*	-	*	*	*	-	*
	4	0.1	0.2	0.1	*	*	*	-	*	-	*	-	-
	5	-	*	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	3.7	2.2	0.8	0.1	0.1	0.1	-	*	*	*	-	0.5
32	1 - 2	1.3	0.6	0.4	0.1	*	*	0.1	*	*	0.1	0.6	*
	3	5.5	3.0	5.4	0.9	0.2	0.1	1.5	0.3	0.3	0.6	0.1	*
	4	2.0	1.7	2.5	0.6	0.1	*	0.4	0.3	0.2	0.3	-	*
	5	0.3	0.8	-	0.1	*	*	*	*	*	*	-	-
	6	*	0.2	-	*	*	*	-	*	*	*	-	-
	7	-	*	-	*	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	9.1	6.2	8.4	1.7	0.3	0.2	2.0	0.7	0.5	1.0	0.7	0.1
42	1 - 2	-	-	-	0.1	-	*	-	*	*	0.1	-	-
	3	0.1	*	1.5	1.2	0.1	0.1	0.2	0.4	0.9	1.3	-	-
	4	0.1	0.1	2.2	2.9	0.1	0.1	0.2	1.1	1.7	1.6	-	-
	5	*	0.2	0.1	0.9	0.1	*	*	0.6	0.2	0.3	-	-
	6	*	0.1	-	0.1	*	*	-	0.1	*	*	-	-
	7	*	*	-	*	-	*	-	*	*	*	-	-
	8	-	*	-	-	-	-	-	-	*	*	-	-
Total	----	0.2	0.4	3.7	5.2	0.2	0.3	0.4	2.1	2.8	3.2	-	-

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 24, 2020

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	-	*	-	-	-	*	*	*	-	-
	3	-	-	-	0.1	*	*	-	*	0.2	0.1	-	-
	4	-	-	*	0.3	*	*	-	0.1	0.4	0.2	-	-
	5	-	-	-	0.1	*	*	*	0.1	0.1	0.1	-	-
	6	-	*	-	*	-	*	*	*	*	*	-	-
	7	-	-	-	*	-	*	-	*	-	-	-	-
	8	*	*	-	-	-	-	-	*	*	*	-	-
Total	----	*	*	*	0.5	*	*	*	0.2	0.7	0.4	-	-
62	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	*	-	-	-	-
	4	-	-	-	-	-	-	-	*	*	*	-	-
	5	-	-	-	*	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	*	*	*	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	-	-	-	*	*	*	-	-
13 & 23	1 - 2	0.3	0.1	-	-	-	-	-	-	-	*	-	0.1
	3	0.3	0.3	-	-	*	*	-	-	-	-	-	0.1
	4	-	0.1	-	-	*	*	-	-	-	-	-	-
	5	-	*	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.6	0.4	-	-	*	*	-	-	-	*	-	0.1
33	1 - 2	1.2	0.2	0.1	*	-	*	-	*	-	*	1.2	*
	3	3.4	1.2	1.5	0.1	-	*	0.2	*	0.1	0.1	0.8	0.1
	4	2.3	1.2	1.0	0.1	-	*	0.1	*	*	*	-	*
	5	0.8	0.4	-	*	-	*	*	*	*	*	-	-
	6	0.2	0.1	-	-	-	-	-	-	-	*	-	-
	7	*	*	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	7.8	3.1	2.6	0.2	-	*	0.3	*	0.1	0.1	2.1	0.2
43	1 - 2	*	*	-	*	-	*	-	*	-	*	-	-
	3	0.1	*	0.2	0.1	*	*	0.1	*	0.1	0.1	-	*
	4	0.2	0.1	0.2	0.2	*	*	0.1	*	0.3	0.1	-	*
	5	0.3	0.2	*	0.1	*	*	*	*	*	*	-	-
	6	0.4	0.2	-	*	-	*	-	*	*	*	-	-
	7	0.2	0.1	-	*	-	-	-	*	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-	-	-
Total	----	1.4	0.6	0.4	0.4	*	*	0.2	0.1	0.4	0.3	-	*
53	1 - 2	-	-	-	-	-	-	-	*	-	-	-	-
	3	-	-	-	*	-	-	-	*	-	*	-	-
	4	-	-	-	*	-	*	*	*	*	*	-	-
	5	-	*	-	*	-	*	-	*	-	*	-	-
	6	-	*	-	*	-	*	-	*	-	*	-	-
	7	-	*	-	-	-	-	-	*	-	-	-	-
	8	-	*	-	-	-	-	-	*	-	-	-	-
Total	----	-	*	-	0.1	-	*	*	*	*	*	-	-
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	*	-	-	-	-
	4	-	-	-	-	-	-	-	*	-	*	-	-
	5	-	-	-	-	-	-	-	*	-	*	-	-
	6	-	*	-	-	-	-	-	*	*	*	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	-	-	-	-	*	*	*	-	-
24 - 54 25 - 35 81 - 85	1 - 8	2.3	0.5	0.1	*	-	-	-	*	0.1	*	-	-
	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
	1 - 8	-	*	-	-	-	-	-	*	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		*	*	-	-	-	*	-	-	-	-	-	-
31		0.1	*	-	-	-	*	-	-	-	*	-	-
32		1.5	0.6	-	-	-	-	-	*	-	*	-	-
33		3.1	3.1	-	*	-	*	-	*	*	*	0.1	0.1
34		12.0	17.3	-	0.1	-	*	0.2	0.2	0.2	0.6	1.4	1.7
35		29.6	37.2	-	0.8	0.1	0.1	4.3	1.8	4.2	4.2	26.2	13.7
36		38.7	30.1	0.1	3.2	3.8	1.7	13.4	6.1	22.4	15.5	41.3	24.6
37		14.1	10.2	34.1	16.1	36.2	24.6	22.1	19.9	36.5	37.2	27.3	31.1
38		1.0	1.3	8.7	25.8	26.0	27.7	20.9	25.9	20.2	22.5	0.4	13.5
39		*	0.2	42.5	32.2	23.7	28.3	25.0	29.4	11.9	14.5	2.2	10.1
40 & Longer		*	*	14.7	21.7	10.3	17.6	14.2	16.6	4.5	5.5	1.0	5.2
Average Staple		35.47	35.30	38.42	38.54	38.02	38.37	37.92	38.26	37.26	37.43	36.13	36.92
Average Length		1.10	1.10	1.20	1.21	1.19	1.20	1.18	1.20	1.16	1.17	1.12	1.15

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 24, 2020

Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	38.7	53.8	0.9	0.5	0.5	2.8	34.7	42.1	-	*
	3	7.7	8.4	2.0	0.9	0.1	1.0	12.6	13.0	-	0.1
	4	0.3	0.2	0.2	*	-	*	0.9	1.2	-	*
	5	-	*	*	*	-	-	*	*	-	-
	6	-	-	-	*	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	46.7	62.5	3.0	1.5	0.6	3.8	48.3	56.4	-	0.1
31	1 - 2	12.2	8.8	0.7	1.7	12.8	16.1	4.1	3.0	1.0	1.5
	3	12.9	13.1	9.1	16.8	23.0	34.5	10.8	11.6	6.4	6.8
	4	3.8	3.7	5.4	8.3	4.2	6.8	7.2	5.5	0.9	1.2
	5	0.3	0.5	0.4	0.5	0.1	0.2	1.8	1.0	-	*
	6	*	*	-	*	-	*	0.2	0.2	-	*
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	29.3	26.1	15.6	27.3	40.1	57.6	24.2	21.4	8.2	9.6
41	1 - 2	0.2	0.1	0.4	0.5	3.1	2.2	0.2	0.5	4.0	5.4
	3	0.9	0.4	19.7	19.2	32.6	18.4	1.2	3.5	48.0	50.8
	4	0.8	0.7	34.4	33.0	21.0	14.1	1.3	2.7	24.9	23.4
	5	0.3	0.6	8.3	8.3	1.4	2.0	1.2	0.8	1.3	1.4
	6	0.1	0.2	0.4	0.5	*	0.1	0.8	0.3	-	*
	7	0.1	*	*	*	-	*	0.4	0.2	-	-
	8	*	*	-	-	-	-	0.2	0.1	-	-
Total	----	2.4	2.0	63.2	61.5	58.2	36.7	5.2	8.0	78.2	81.0
51	1 - 2	-	-	*	*	-	*	-	*	*	0.1
	3	-	-	0.8	0.3	*	*	*	0.2	2.8	2.2
	4	*	*	5.5	2.2	*	*	*	0.2	5.9	2.7
	5	*	*	3.9	1.7	-	*	*	0.1	1.0	0.4
	6	*	*	0.7	0.3	-	*	*	*	*	*
	7	*	*	*	*	-	*	*	*	-	*
	8	*	*	-	-	-	-	*	*	-	-
Total	----	*	*	10.9	4.5	*	0.1	0.1	0.4	9.8	5.4
61	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	*	-	-
	4	-	-	-	*	-	-	-	*	-	*
	5	-	-	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	-	-	-	*	-	-	-	*	-	*
71	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	*	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	*	-	-
12 & 22	1 - 2	5.6	2.3	-	*	0.1	*	4.9	3.4	-	*
	3	1.5	0.9	0.1	*	*	*	1.7	1.5	-	*
	4	0.1	0.1	*	*	-	*	0.2	0.2	-	*
	5	-	*	-	-	-	-	*	*	-	*
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	7.2	3.3	0.1	*	0.2	*	6.8	5.2	-	*
32	1 - 2	3.3	1.0	*	*	0.2	0.2	1.2	0.3	*	*
	3	2.7	1.6	0.2	0.3	0.3	0.8	2.3	1.1	0.5	0.5
	4	0.7	0.6	0.3	0.3	*	0.2	1.2	0.7	0.1	0.2
	5	0.2	0.1	*	*	*	*	0.3	0.2	*	*
	6	*	*	-	-	-	*	*	*	-	*
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	6.9	3.3	0.6	0.7	0.6	1.2	5.0	2.4	0.7	0.8
42	1 - 2	*	*	*	*	*	*	*	0.1	*	*
	3	0.1	*	0.9	0.7	*	0.2	0.4	0.7	0.6	1.1
	4	0.2	0.1	2.1	1.6	0.1	0.1	0.3	0.8	0.7	1.3
	5	0.1	0.1	0.9	0.7	*	*	0.2	0.3	0.2	0.2
	6	*	*	0.2	0.1	-	*	0.2	0.1	*	*
	7	*	*	*	*	-	*	0.1	*	-	-
	8	-	*	-	-	-	-	0.1	*	-	-
Total	----	0.4	0.3	4.1	3.2	0.1	0.4	1.2	2.1	1.6	2.6

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 24, 2020

Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	*	-	-	-	*	*	*	-	*
	3	-	*	*	*	-	*	*	0.3	0.1	0.1
	4	-	*	0.7	0.4	-	*	*	0.3	0.3	0.1
	5	-	*	0.9	0.4	-	*	*	0.2	0.1	*
	6	*	*	0.3	0.2	-	*	*	0.1	-	*
	7	-	*	*	*	-	-	*	*	-	-
	8	-	-	-	*	-	-	0.1	*	-	-
Total	----	*	*	2.0	1.0	-	*	0.1	0.9	0.4	0.2
62	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	-	-	-	*	*	-	-
	5	-	*	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	*	*	-	-	-	*	-	-
	8	*	*	-	-	-	-	-	*	-	-
Total	----	*	*	*	*	-	-	*	*	-	-
13 & 23	1 - 2	1.2	0.5	-	-	*	*	2.7	0.8	-	-
	3	0.5	0.2	-	-	*	*	0.8	0.3	-	-
	4	0.1	*	-	-	-	-	0.1	*	-	-
	5	-	*	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	1.8	0.8	-	-	*	*	3.6	1.2	-	-
33	1 - 2	1.3	0.4	-	*	*	*	1.1	0.2	-	*
	3	1.7	0.6	0.1	*	0.1	0.1	1.3	0.3	0.1	*
	4	0.7	0.2	0.1	*	*	*	0.7	0.1	0.1	*
	5	0.1	*	-	*	-	*	0.2	*	-	*
	6	*	*	-	*	-	-	*	*	-	-
	7	-	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	3.9	1.3	0.2	0.1	0.1	0.1	3.4	0.7	0.1	0.1
43	1 - 2	*	*	-	-	-	*	*	*	*	*
	3	0.1	*	*	*	*	*	*	0.1	0.4	0.1
	4	0.3	0.1	0.1	0.1	-	*	0.1	0.2	0.4	0.1
	5	0.2	*	0.1	0.1	-	*	0.1	0.1	0.1	*
	6	*	*	*	*	-	-	*	*	*	*
	7	*	*	*	*	-	-	*	*	-	-
	8	-	*	-	-	-	-	*	*	-	-
Total	----	0.6	0.1	0.2	0.2	*	*	0.3	0.4	0.9	0.2
53	1 - 2	-	*	-	-	-	*	-	*	-	-
	3	-	-	-	*	-	*	*	0.1	-	-
	4	-	-	*	*	-	*	*	0.1	*	*
	5	-	*	0.1	0.1	-	-	*	0.1	-	-
	6	-	*	*	*	-	-	*	0.1	-	-
	7	-	*	-	*	-	-	-	*	-	-
	8	-	*	-	-	-	-	*	*	-	-
Total	----	-	*	0.1	0.1	-	*	*	0.4	*	*
63	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	*	-	-	-	*	-	-
	5	-	-	-	-	-	-	-	*	-	*
	6	-	-	-	-	-	*	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	*	-	-	-	-	-	*	-	-
Total	----	-	*	-	*	-	*	-	*	-	*
24 - 54	1 - 8	0.9	0.3	-	*	*	*	1.8	0.4	0.1	*
25 - 35	1 - 8	-	*	-	-	-	-	*	*	-	-
81 - 85	1 - 8	-	*	-	-	-	-	*	*	-	-
STAPLE											
28 & Shorter		-	*	-	-	-	-	-	*	-	-
29		*	*	-	-	-	-	*	*	-	-
30		*	*	-	-	-	-	0.2	0.1	-	-
31		0.3	0.4	-	-	-	-	0.9	0.4	-	-
32		1.2	1.3	*	*	-	*	3.0	1.6	-	-
33		3.0	3.5	0.2	0.1	-	*	8.4	4.7	-	-
34		6.9	6.2	1.6	1.1	0.1	0.1	14.4	10.1	*	0.1
35		12.0	8.1	4.5	4.2	4.2	2.8	17.5	16.2	0.6	0.8
36		12.8	11.4	11.4	10.5	26.3	15.7	19.1	22.6	4.1	5.6
37		21.6	25.6	34.4	27.6	41.1	39.8	21.1	26.8	29.6	27.9
38		21.0	21.6	27.9	29.6	25.0	25.9	9.0	11.8	31.3	26.9
39		12.8	14.9	16.2	20.4	3.1	13.3	4.7	4.4	23.6	24.2
40 & Longer		8.4	7.0	3.8	6.4	0.3	2.3	1.5	1.4	10.8	14.5
Average Staple		36.96	37.04	37.46	37.67	36.97	37.38	35.69	36.10	38.08	38.14
Average Length		1.15	1.16	1.17	1.18	1.15	1.17	1.11	1.13	1.19	1.19

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 24, 2020

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	1.3	0.8	1.9	1.0	*	*	0.2	*	1.5	1.1	0.8	0.6
Bark - Level 2	-	*	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	*	*	0.1	0.1	*	0.1	0.1	0.4	*	*	*	*
Grass - Level 2	-	-	-	*	-	-	-	-	-	-	-	-
Prep - Level 1	0.1	*	-	*	-	*	-	*	-	*	*	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	31.8	23.9	0.9	0.1	1.7	3.5	-	*	62.5	52.5	43.8	40.8
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	*	*	*	*	-	-	-	-	-	-	*	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	*	-	-	*	*	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	-	*	-	-	-	*	*	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	0.1	*	*	*	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	*	-	-	-	-	-	-	-	-	*	*
23	*	*	-	*	0.1	*	-	-	-	*	*	*
24	0.1	0.1	*	*	0.1	*	-	*	-	*	0.1	0.1
25	0.2	0.1	*	*	0.2	0.2	-	*	*	0.1	0.8	0.4
26	1.3	0.6	*	0.1	0.3	0.6	-	0.1	0.9	0.7	3.0	1.7
27	5.1	2.6	0.5	0.4	2.0	2.7	*	0.5	4.4	2.5	7.8	5.6
28	13.3	9.8	3.0	2.3	5.1	9.2	0.2	1.6	12.1	9.5	17.2	14.0
29	25.5	24.7	13.0	10.9	12.3	14.7	3.6	7.3	24.0	27.0	26.2	25.1
30	29.3	30.7	31.6	28.2	16.7	19.5	11.2	15.8	25.7	32.5	23.4	26.1
31	15.8	19.4	28.5	30.9	22.3	19.9	8.9	18.9	19.4	18.3	12.8	15.7
32	6.9	8.0	13.5	16.3	18.7	14.0	3.1	12.6	9.0	6.4	5.6	7.0
33	1.9	2.8	6.7	7.2	9.5	8.3	8.3	8.5	3.2	2.3	2.1	2.9
34	0.5	0.9	2.6	3.0	5.5	5.7	17.3	6.8	1.0	0.7	0.7	1.0
35	0.2	0.3	0.5	0.7	3.3	3.1	8.0	9.1	0.2	0.1	0.2	0.4
36	0.1	0.1	*	0.1	2.6	1.5	15.9	10.3	0.1	*	0.1	0.1
37	*	*	*	*	1.1	0.5	19.0	6.4	-	*	*	*
38	*	*	*	*	0.2	0.1	3.8	1.6	-	*	*	*
39	-	*	-	-	*	*	0.2	0.2	-	*	*	*
40 & Above	-	*	-	-	*	*	0.4	0.3	-	-	-	*
Average	30.10	30.39	31.13	31.29	31.66	31.24	34.53	32.98	30.32	30.30	29.78	30.11
Mike												
2.4 & Below	*	*	-	*	-	*	-	-	-	-	-	-
2.5	*	*	-	*	-	*	-	-	-	-	*	*
2.6	0.1	*	-	*	-	*	-	-	-	-	*	*
2.7	0.1	*	-	*	-	*	-	*	-	-	*	*
2.8	0.1	*	-	*	-	*	-	*	-	-	*	*
2.9	0.2	*	*	*	-	*	-	*	-	*	*	*
3.0	0.5	0.1	-	*	*	*	*	*	-	*	*	*
3.1	0.2	0.1	0.1	*	0.1	*	0.2	0.1	0.1	*	*	*
3.2	0.3	0.1	0.2	0.1	0.1	0.1	0.1	*	0.5	0.1	*	*
3.3	0.3	0.2	0.2	0.1	0.1	0.1	0.4	0.1	0.4	0.1	0.1	0.1
3.4	0.6	0.4	0.4	0.2	0.1	0.1	0.9	0.4	0.6	0.2	0.1	0.1
3.5	0.9	0.6	0.7	0.4	0.2	0.2	1.4	0.7	0.6	0.4	0.3	0.2
3.6	1.5	1.0	1.0	0.8	0.2	0.3	2.7	1.6	1.5	1.0	0.6	0.4
3.7	2.2	1.6	1.1	1.3	0.5	0.4	4.5	3.7	3.6	1.8	0.9	0.7
3.8	3.4	2.5	2.3	2.1	0.9	0.6	4.1	4.8	4.5	3.5	1.7	1.2
3.9	4.8	3.7	3.8	3.6	1.4	0.9	10.1	7.6	5.9	5.3	2.9	2.2
4.0	5.3	4.8	4.8	5.2	2.0	1.4	12.5	7.4	7.4	8.6	4.3	3.5
4.1	6.7	6.4	5.8	7.8	4.3	2.4	18.9	8.7	8.4	10.5	5.8	5.4
4.2	7.5	7.7	7.2	10.7	6.3	4.0	11.1	9.2	9.6	12.4	7.6	7.9
4.3	10.7	9.1	9.7	12.8	7.5	5.9	12.6	9.5	12.4	13.3	10.3	10.8
4.4	10.5	10.5	11.4	14.1	9.0	8.7	10.2	9.6	9.3	12.4	13.3	13.3
4.5	10.9	11.2	11.3	13.9	12.4	11.8	5.5	9.5	7.6	10.5	13.7	13.9
4.6	9.3	11.0	11.8	11.0	16.1	13.9	2.8	8.3	9.3	8.5	12.7	12.9
4.7	7.6	9.6	10.8	7.3	11.4	13.5	0.9	6.2	8.4	5.0	10.3	10.4
4.8	6.7	7.4	7.8	4.4	7.1	11.1	0.2	4.5	6.3	3.0	7.1	7.6
4.9	4.1	5.1	4.7	2.4	5.7	9.0	0.1	4.0	2.7	1.6	4.3	4.6
5.0	2.3	3.1	2.3	1.1	4.4	6.1	0.4	2.3	0.7	1.0	2.2	2.6
5.1	1.8	1.8	1.4	0.5	3.9	4.6	-	1.1	0.2	0.5	1.0	1.2
5.2	0.9	1.1	0.7	0.2	2.9	2.7	0.1	0.5	-	0.2	0.4	0.4
5.3	0.3	0.5	0.3	0.1	2.2	1.2	-	0.1	0.1	0.1	0.3	0.2
5.4	0.2	0.2	0.2	*	1.2	0.8	-	*	0.1	0.1	0.2	0.1
5.5 & Above	*	0.1	*	*	-	0.2	-	*	-	0.1	0.1	0.1
Average	4.36	4.43	4.43	4.37	4.58	4.64	4.12	4.31	4.30	4.30	4.45	4.47

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 24, 2020

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	21.4	17.5	0.5	0.6	0.4	0.4	0.5	0.5	1.1	0.4	-	0.3
Bark - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	0.2	0.1	-	*	*	*	*	0.1	0.2	*	-	0.1
Grass - Level 2	-	-	-	-	-	-	-	*	-	-	-	-
Prep - Level 1	-	*	-	*	0.1	*	-	*	*	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	*	-	-	-	-
Seed Coat - Level 1	-	*	-	*	0.3	*	*	0.1	*	*	-	0.2
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	*	-	-	-	*	-	-	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	*	*	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	*	-	*	-	*	-	-	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	*	0.1	*	*	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	*	-	-	-	*	-	-	-	-	-	-
23	*	0.1	-	-	-	-	-	-	*	*	-	-
24	0.1	0.3	-	-	-	*	-	*	*	*	-	-
25	0.5	1.1	-	*	*	*	*	*	0.7	0.3	-	*
26	1.6	2.8	-	*	*	*	0.4	0.2	4.8	1.8	-	0.4
27	4.0	8.5	0.1	0.1	0.2	0.1	2.6	1.4	15.0	6.7	0.3	5.3
28	11.8	19.7	1.5	1.1	2.8	1.3	8.4	4.9	24.4	15.5	10.3	15.2
29	25.7	25.2	10.9	8.1	14.9	9.1	20.7	15.6	21.3	22.6	57.1	21.9
30	25.6	20.4	43.6	28.5	39.8	31.7	30.2	30.4	15.5	22.2	18.7	27.1
31	16.9	11.9	14.6	28.7	27.0	34.1	27.9	26.5	9.5	16.1	10.8	19.7
32	7.2	6.7	20.3	14.3	10.3	16.0	7.0	12.0	4.9	8.7	1.5	8.4
33	5.8	2.4	9.0	9.8	4.1	5.5	2.1	5.8	2.7	3.9	-	1.7
34	0.7	0.7	0.1	6.3	0.6	1.6	0.5	2.5	0.8	1.6	0.3	0.1
35	0.1	0.1	-	2.4	0.2	0.4	0.2	0.7	0.2	0.6	-	*
36	*	*	-	0.5	*	0.1	*	0.1	0.1	0.1	-	*
37	-	*	-	0.1	-	*	-	*	-	*	-	0.1
38	-	*	-	*	-	*	-	*	-	*	-	-
39	-	-	-	-	-	*	-	*	-	-	-	*
40 & Above	-	-	-	-	-	-	-	-	-	-	1.0	*
Average	30.27	29.72	31.09	31.62	30.86	31.25	30.50	30.96	29.39	30.18	29.95	30.19
Mike												
2.4 & Below	1.2	0.6	-	-	-	-	-	*	*	*	-	-
2.5	4.8	3.9	-	-	*	*	-	*	*	*	-	-
2.6	5.2	3.2	-	-	0.1	*	-	*	*	*	-	-
2.7	5.1	3.6	-	-	*	*	*	*	*	*	-	-
2.8	4.6	5.1	-	*	0.1	*	*	*	*	*	-	*
2.9	5.4	6.2	-	*	0.1	*	*	*	0.1	*	-	0.1
3.0	6.3	6.5	-	*	0.3	*	0.1	*	0.1	0.1	-	0.4
3.1	5.1	6.2	-	*	0.5	0.1	0.2	*	0.2	0.2	-	0.8
3.2	7.7	6.8	-	*	0.5	0.2	0.6	*	0.5	0.3	-	0.9
3.3	5.4	6.9	-	*	1.0	0.3	0.5	*	0.9	0.5	-	1.0
3.4	4.8	7.7	*	0.1	2.0	0.6	0.3	*	1.1	0.8	5.7	2.1
3.5	7.4	7.8	-	0.1	2.1	1.0	0.5	0.1	1.9	1.2	-	2.3
3.6	6.7	6.6	-	0.1	3.3	1.6	0.4	0.1	2.9	2.0	-	2.9
3.7	6.9	6.5	-	0.2	3.9	2.4	0.6	0.1	3.8	2.9	-	2.7
3.8	6.3	5.8	*	0.4	6.1	3.7	0.6	0.3	5.4	4.5	8.7	4.2
3.9	3.5	4.4	1.3	1.1	8.5	5.6	0.9	0.5	7.5	6.2	4.0	4.9
4.0	4.1	3.6	0.1	1.9	9.6	7.4	1.6	0.9	8.6	8.0	1.9	4.7
4.1	3.3	3.2	0.9	3.0	9.0	9.2	1.8	1.9	10.0	9.3	30.9	8.0
4.2	2.5	2.6	2.3	5.2	8.5	10.4	3.4	3.3	11.7	10.7	26.2	8.0
4.3	2.0	1.6	9.2	7.9	9.3	11.2	4.8	5.5	12.3	11.5	0.3	7.4
4.4	0.7	0.6	5.6	11.0	8.2	11.6	9.0	8.7	9.6	11.2	4.4	8.6
4.5	0.2	0.2	4.8	13.7	8.4	10.1	15.0	12.8	9.7	10.2	7.6	8.3
4.6	0.4	0.3	12.2	16.4	7.7	8.1	15.9	15.9	6.6	7.9	0.1	7.7
4.7	0.2	0.1	32.9	15.4	4.9	6.1	15.6	16.6	3.5	5.8	3.6	7.7
4.8	-	0.1	28.8	11.2	3.0	4.1	11.0	14.0	2.1	3.7	5.1	6.4
4.9	-	*	1.8	7.2	1.1	2.8	8.8	9.7	0.8	2.0	-	5.1
5.0	-	*	-	3.4	0.6	1.6	4.7	5.3	0.3	0.7	1.2	3.1
5.1	-	-	-	1.2	0.1	0.9	2.3	2.7	0.1	0.2	-	1.1
5.2	-	-	-	0.3	0.5	0.6	1.1	1.1	0.1	0.1	-	0.9
5.3	-	-	-	0.1	0.2	0.1	0.3	0.4	0.1	*	-	0.4
5.4	-	-	-	*	0.2	0.1	0.1	0.1	*	*	-	0.1
5.5 & Above	-	-	-	*	0.1	*	*	*	*	*	-	*
Average	3.34	3.36	4.63	4.56	4.17	4.30	4.58	4.63	4.18	4.26	4.16	4.30

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 24, 2020

Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter										
Bark - Level 1	12.6	7.3	2.1	1.3	0.5	0.2	17.3	5.7	1.3	0.6
Bark - Level 2	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	-	*	*	0.1	-	*	0.1	0.1	-	*
Grass - Level 2	-	-	-	-	-	-	-	*	-	-
Prep - Level 1	-	*	*	*	*	*	*	*	0.1	*
Prep - Level 2	-	-	-	-	-	-	-	*	-	-
Seed Coat - Level 1	*	*	2.2	0.4	0.1	*	0.1	0.1	-	-
Seed Coat - Level 2	-	*	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	-	-	*	*	*	-	*
Oil - Level 2	-	-	-	-	-	-	-	*	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	-	-	*	*	*	-	-
Other - Level 2	-	-	-	-	-	-	-	*	-	-
Plastic - Level 1	*	*	-	*	*	*	*	*	*	*
Plastic - Level 2	-	*	-	-	-	-	-	*	-	-
STRENGTH 1/ 22 & Below	-	*	-	-	-	-	0.2	*	-	-
23	-	*	*	*	-	-	0.3	0.1	-	*
24	*	0.1	0.1	*	-	*	0.5	0.3	*	*
25	0.3	0.4	1.1	0.4	-	*	1.5	0.9	0.3	0.2
26	1.0	1.1	4.7	2.0	*	0.1	3.4	2.2	2.2	1.4
27	3.2	3.4	13.7	7.0	1.1	0.5	7.6	5.2	15.1	7.3
28	7.1	8.2	24.7	17.8	9.1	4.8	13.9	10.5	32.4	19.2
29	14.9	14.7	29.1	27.5	34.3	21.7	18.3	17.1	24.4	26.3
30	19.3	18.1	17.6	24.5	36.4	36.8	19.0	20.5	15.3	22.1
31	17.8	18.5	6.7	12.8	15.0	24.3	15.0	18.1	7.0	14.5
32	16.6	15.8	1.7	5.2	3.1	8.4	9.4	12.5	2.7	5.7
33	11.2	10.9	0.4	1.8	0.8	2.6	5.9	7.6	0.6	2.4
34	6.8	5.7	0.1	0.6	*	0.6	3.3	3.4	0.1	0.6
35	1.6	2.1	*	0.2	*	0.1	1.3	1.2	*	0.2
36	0.2	0.7	*	*	-	*	0.3	0.4	-	*
37	*	0.2	-	*	-	*	0.1	0.1	-	*
38	*	*	-	-	-	*	*	*	-	-
39	*	*	-	-	-	-	*	*	-	-
40 & Above	*	*	-	-	-	-	*	*	-	-
Average	31.23	31.18	29.13	29.83	30.13	30.64	30.22	30.63	29.15	29.89
Mike										
2.4 & Below	0.2	*	-	-	-	*	1.9	0.2	-	-
2.5	0.5	0.1	-	-	-	*	3.9	0.7	-	-
2.6	0.3	0.1	-	-	-	*	2.4	0.8	-	-
2.7	0.2	0.1	-	*	-	*	2.0	0.9	-	-
2.8	0.4	0.2	-	*	-	*	2.5	1.0	-	-
2.9	0.9	0.3	-	*	-	*	2.6	1.2	-	*
3.0	0.7	0.6	-	*	*	*	2.8	1.4	*	*
3.1	1.0	0.9	-	*	0.1	0.1	3.0	1.6	0.2	0.1
3.2	1.3	1.4	0.1	*	0.1	0.1	3.3	1.8	0.1	0.1
3.3	3.1	2.3	0.1	0.1	0.1	0.2	3.5	2.1	0.4	0.3
3.4	4.3	3.2	0.4	0.3	*	0.3	3.7	2.4	0.7	0.5
3.5	5.3	4.0	0.6	0.5	0.3	0.5	3.7	2.8	1.1	0.9
3.6	5.3	4.7	1.2	1.0	0.4	0.8	4.3	3.3	1.9	1.6
3.7	6.8	5.3	2.5	2.2	0.8	1.5	5.3	4.0	4.6	2.7
3.8	8.0	6.6	5.8	3.9	1.5	2.2	5.8	4.9	6.0	4.1
3.9	8.2	7.5	6.5	5.7	2.0	2.9	5.9	5.8	6.8	5.1
4.0	7.9	8.8	8.0	7.7	5.5	4.3	6.8	6.8	8.2	7.9
4.1	8.2	9.6	9.9	9.6	7.4	5.7	6.4	7.6	10.2	8.8
4.2	7.9	9.8	10.5	11.1	8.3	7.7	5.7	8.1	10.2	11.4
4.3	8.0	8.9	10.7	12.5	8.1	9.2	5.6	8.4	13.9	13.1
4.4	5.3	7.5	12.3	12.9	7.2	10.1	4.8	8.1	13.1	13.4
4.5	4.4	5.9	10.9	10.7	6.7	10.6	4.1	7.5	9.3	11.5
4.6	3.5	4.7	8.7	8.4	7.1	10.6	3.6	6.4	5.5	8.0
4.7	3.0	3.0	5.3	5.7	9.7	9.8	2.8	4.8	3.2	5.4
4.8	2.4	2.0	3.3	3.5	11.6	8.8	1.9	3.2	2.1	2.9
4.9	1.6	1.2	1.3	2.0	10.6	6.5	1.0	2.0	1.4	1.2
5.0	0.9	0.8	1.0	1.2	6.2	3.9	0.5	1.1	0.8	0.4
5.1	0.3	0.4	0.6	0.5	3.0	2.3	0.2	0.6	0.2	0.2
5.2	*	0.2	0.1	0.2	1.8	1.2	0.1	0.2	*	0.1
5.3	-	0.1	0.1	0.1	1.2	0.4	*	0.1	*	*
5.4	-	*	*	*	0.4	0.1	-	*	*	*
5.5 & Above	-	*	*	*	*	*	*	*	-	-
Average	3.98	4.06	4.28	4.30	4.54	4.46	3.74	4.07	4.21	4.27

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 24, 2020

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	*	*	-	*	-	*	-	-	-	-	-	-
2.5 - 2.6	0.1	*	-	*	-	*	-	-	-	-	*	*
2.7 - 2.9	0.4	*	*	*	-	*	-	*	-	*	*	*
3.0 - 3.2	1.1	0.3	0.3	0.1	0.2	0.1	0.4	0.1	0.5	0.1	*	0.1
3.3 - 3.4	0.9	0.6	0.6	0.3	0.3	0.2	1.2	0.5	1.0	0.2	0.2	0.2
3.5 - 3.6	2.4	1.6	1.7	1.1	0.3	0.4	4.2	2.3	2.2	1.4	0.9	0.6
3.7 - 4.2	29.8	26.8	24.9	30.7	15.4	9.7	61.3	41.4	39.4	42.0	23.1	21.0
4.3 - 4.9	59.8	63.9	67.5	65.9	69.2	73.8	32.4	51.6	55.9	54.2	71.6	73.5
5.0 - 5.2	4.9	6.0	4.4	1.8	11.2	13.4	0.5	3.9	0.8	1.7	3.6	4.2
5.3 & Above	0.6	0.8	0.5	0.1	3.4	2.3	-	0.1	0.2	0.3	0.5	0.4
Average	4.36	4.43	4.43	4.37	4.58	4.64	4.12	4.31	4.30	4.30	4.45	4.47
Leaf												
1 - 2	7.4	4.3	3.5	2.5	84.5	88.6	66.0	75.5	0.4	1.9	5.5	4.5
3	44.1	41.8	44.7	35.9	12.7	9.7	30.1	21.7	28.7	32.8	51.9	45.3
4	37.1	42.3	42.7	48.9	2.2	1.4	3.5	2.6	56.3	50.3	35.7	40.2
5	9.8	10.4	8.6	12.0	0.4	0.3	0.4	0.1	13.3	13.7	6.3	9.0
6	1.5	1.1	0.5	0.7	0.1	*	*	*	1.2	1.2	0.5	1.0
7	0.1	0.1	0.1	*	*	*	-	-	0.1	0.1	*	0.1
8	-	*	*	*	*	*	-	-	-	-	*	*
Average	3.54	3.62	3.58	3.72	1.85	1.74	2.31	2.04	3.86	3.80	3.44	3.57
HVI Trash 1/												
00	-	*	-	-	0.1	*	-	0.1	-	-	-	*
01	0.5	0.3	0.1	0.1	52.4	59.3	22.3	39.7	-	0.1	0.4	0.3
02	9.0	5.7	4.6	3.1	34.7	31.2	49.2	38.5	1.0	3.3	8.3	6.7
03	21.0	18.1	17.1	12.7	8.8	6.2	18.8	14.1	9.8	13.3	24.2	20.7
04	24.2	25.3	25.1	22.2	2.5	1.8	6.1	4.8	22.0	23.8	27.2	26.0
05	19.6	21.8	22.4	23.5	0.8	0.8	2.4	1.8	26.3	24.1	19.5	20.8
06	12.2	14.0	15.0	18.0	0.3	0.3	0.8	0.7	20.1	17.3	10.9	12.8
07	6.8	7.7	8.5	10.7	0.1	0.2	0.3	0.2	11.6	9.7	5.4	6.8
08	3.4	3.8	4.1	5.5	0.1	0.1	0.2	0.1	5.1	4.7	2.5	3.3
09	1.7	1.8	1.8	2.5	*	0.1	0.1	*	2.3	2.2	1.0	1.5
10	0.8	0.8	0.7	1.0	*	*	-	*	1.2	0.9	0.4	0.7
11	0.4	0.4	0.3	0.4	*	*	-	*	0.3	0.4	0.2	0.3
12	0.2	0.2	0.1	0.2	*	*	-	*	0.2	0.2	0.1	0.1
13	0.1	0.1	0.1	0.1	*	*	-	*	0.1	0.1	*	0.1
14	*	*	*	*	-	*	-	-	*	*	*	*
15	*	*	*	*	-	*	-	-	-	*	*	*
16	*	*	*	*	-	-	-	-	-	*	*	*
17	-	*	*	*	-	-	-	-	-	-	*	*
18 & Above	*	*	-	*	*	*	-	-	-	*	*	*
Average	0.46	0.48	0.49	0.52	0.17	0.16	0.22	0.19	0.53	0.51	0.44	0.46
UNIFORMITY 2/												
74 & Below	-	-	-	-	-	-	-	-	-	-	-	-
75	*	*	-	*	-	-	-	-	-	-	*	*
76	0.1	*	-	*	0.2	*	*	*	*	*	*	*
77	0.4	0.2	0.1	*	0.4	0.3	*	0.1	0.4	0.2	0.2	0.3
78	1.6	1.3	0.7	0.4	2.1	2.3	0.8	0.8	1.6	1.1	1.5	1.6
79	7.7	6.9	4.2	2.1	12.9	11.2	4.8	7.5	6.2	5.7	7.2	7.3
80	24.9	26.5	15.3	12.0	27.8	28.6	24.7	29.6	18.9	29.8	24.2	23.7
81	40.2	40.0	30.7	35.6	35.0	37.2	40.3	33.4	30.6	43.2	36.6	36.7
82	21.8	20.5	31.8	35.4	18.4	16.8	7.6	10.1	26.6	15.2	22.8	22.8
83	3.0	4.0	15.1	12.7	3.0	3.2	9.6	13.0	13.2	4.1	6.4	6.5
84	0.3	0.4	2.1	1.6	0.2	0.4	11.7	5.3	2.3	0.6	1.0	1.0
85 & Above	*	*	0.1	0.1	-	*	0.5	0.2	0.2	*	0.1	0.1
Average	81.26	81.30	81.87	81.94	81.07	81.10	81.72	81.51	81.68	81.25	81.39	81.40
Tenderable 3/	58.4	63.9	90.0	95.1	82.8	81.1	97.6	94.7	33.3	41.8	52.0	51.2
SAMPLES CLASSED	38,437	611,514	39,276	1,190,650	19,911	198,101	9,839	100,758	5,925	75,148	235,252	1,627,345

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 24, 2020

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	1.2	0.6	-	-	-	-	-	*	*	*	-	-
2.5 - 2.6	10.0	7.1	-	-	0.1	*	-	*	*	*	-	-
2.7 - 2.9	15.1	14.9	-	*	0.2	*	*	*	0.2	0.1	-	0.1
3.0 - 3.2	19.1	19.5	-	*	1.3	0.3	0.8	0.1	0.8	0.5	-	2.1
3.3 - 3.4	10.2	14.6	*	0.1	3.0	1.0	0.8	0.1	2.0	1.3	5.7	3.1
3.5 - 3.6	14.1	14.4	-	0.2	5.4	2.6	0.9	0.1	4.8	3.2	-	5.3
3.7 - 4.2	26.8	26.1	4.6	11.8	45.7	38.7	8.8	7.0	47.0	41.6	71.8	32.6
4.3 - 4.9	3.5	2.8	95.3	82.7	42.6	54.0	80.1	83.1	44.7	52.3	21.2	51.2
5.0 - 5.2	-	*	-	5.0	1.2	3.1	8.1	9.1	0.5	1.0	1.2	5.1
5.3 & Above	-	-	-	0.2	0.5	0.2	0.4	0.5	0.1	*	-	0.6
Average	3.34	3.36	4.63	4.56	4.17	4.30	4.58	4.63	4.18	4.26	4.16	4.30
Leaf												
1 - 2	17.4	27.6	22.9	4.2	4.2	8.0	13.0	4.5	3.1	5.2	97.1	96.3
3	43.9	38.7	54.3	41.0	61.0	50.2	62.6	39.3	53.6	55.5	2.8	3.6
4	22.6	21.7	21.9	45.9	30.6	35.9	21.9	44.0	39.4	35.3	0.1	0.1
5	9.3	8.1	0.8	8.5	4.0	5.7	2.2	11.4	3.7	3.8	-	*
6	4.1	2.6	*	0.4	0.2	0.2	0.3	0.8	0.2	0.2	-	-
7	1.4	0.8	-	*	*	*	*	*	*	*	-	-
8	1.3	0.5	-	-	-	-	-	*	*	*	-	-
Average	3.47	3.20	3.00	3.60	3.35	3.40	3.14	3.65	3.44	3.38	1.51	1.55
HVI Trash 1/												
00	-	*	-	-	-	-	-	-	-	-	-	*
01	3.1	10.5	3.1	0.3	0.1	0.6	1.1	0.3	0.1	0.3	67.3	68.4
02	19.0	21.7	25.2	5.1	6.2	8.3	14.9	5.1	4.7	7.1	29.8	28.3
03	23.0	19.4	26.7	16.1	25.0	20.8	31.4	15.3	23.1	24.7	2.5	2.8
04	17.4	15.0	25.6	24.5	29.9	24.9	26.1	21.8	32.4	30.3	0.3	0.4
05	11.5	10.9	13.4	23.4	20.0	20.6	14.6	21.3	23.0	21.0	0.1	0.1
06	7.4	7.3	4.2	16.0	10.2	13.1	6.8	16.0	10.9	10.4	-	*
07	5.6	5.0	1.2	8.5	4.7	6.8	3.0	10.0	3.9	4.1	-	*
08	3.8	3.4	0.4	3.7	2.2	3.0	1.3	5.4	1.2	1.5	-	-
09	2.6	2.2	*	1.5	1.0	1.2	0.5	2.6	0.4	0.5	-	-
10	1.7	1.5	*	0.6	0.5	0.4	0.2	1.2	0.1	0.2	-	*
11	1.3	1.0	-	0.2	0.2	0.1	*	0.5	0.1	0.1	-	-
12	1.1	0.7	*	0.1	0.1	*	-	0.2	*	*	-	-
13	0.8	0.5	-	*	*	*	*	0.1	*	*	-	-
14	0.5	0.3	-	*	*	*	*	*	*	*	-	-
15	0.5	0.2	-	*	*	*	-	*	*	*	-	-
16	0.3	0.2	-	*	-	*	-	*	*	*	-	-
17	0.2	0.1	-	*	-	*	-	*	*	*	-	-
18 & Above	0.2	0.1	-	*	-	*	-	*	*	*	-	-
Average	0.46	0.41	0.34	0.48	0.44	0.45	0.38	0.51	0.43	0.42	0.14	0.14
UNIFORMITY 2/												
74 & Below	0.1	*	-	*	-	-	-	-	-	-	-	-
75	0.2	0.2	-	*	-	-	-	*	-	-	-	-
76	2.4	1.5	-	*	-	*	-	*	*	*	-	*
77	5.9	6.7	-	*	*	*	0.3	0.1	0.1	0.2	-	*
78	14.6	15.9	*	0.1	0.2	0.1	2.1	0.8	1.1	1.2	0.3	1.9
79	28.8	27.6	0.2	0.7	1.6	0.7	7.7	3.8	8.2	6.2	13.2	12.4
80	34.5	34.9	0.9	6.8	15.5	6.9	26.4	16.6	24.8	20.9	37.7	25.3
81	13.2	12.7	17.0	34.0	36.9	29.7	36.9	39.8	39.2	36.0	25.7	37.9
82	0.2	0.5	60.4	45.7	32.9	41.2	20.2	31.2	21.9	27.0	21.9	20.6
83	*	*	20.3	11.5	10.7	18.1	6.0	6.7	4.2	7.4	0.3	1.8
84	-	*	1.1	1.1	2.0	3.0	0.5	0.8	0.5	1.1	-	*
85 & Above	-	*	0.1	0.1	0.3	0.3	*	0.1	*	0.1	1.0	*
Average	79.71	79.72	82.48	82.08	81.87	82.24	81.30	81.65	81.32	81.53	80.90	81.14
Tenderable 3/	30.3	33.1	89.9	87.6	92.5	94.4	88.0	86.8	91.1	92.5	91.0	88.4
SAMPLES CLASSED	12,808	94,889	3,418	334,798	46,321	575,871	15,428	1,112,352	35,580	477,424	721	22,053

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 24, 2020

Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE										
2.4 & Below	0.2	*	-	-	-	*	1.9	0.2	-	-
2.5 - 2.6	0.8	0.1	-	-	-	*	6.3	1.5	-	-
2.7 - 2.9	1.5	0.6	-	*	-	0.1	7.1	3.1	-	*
3.0 - 3.2	3.0	2.9	0.1	0.1	0.2	0.3	9.1	4.9	0.3	0.2
3.3 - 3.4	7.4	5.5	0.6	0.4	0.1	0.5	7.2	4.5	1.1	0.8
3.5 - 3.6	10.6	8.6	1.8	1.6	0.7	1.3	8.1	6.2	3.0	2.5
3.7 - 4.2	47.1	47.7	43.2	40.2	25.3	24.4	35.8	37.2	46.0	40.2
4.3 - 4.9	28.3	33.0	52.6	55.8	61.0	65.5	23.8	40.4	48.6	55.5
5.0 - 5.2	1.2	1.4	1.7	1.9	11.0	7.4	0.8	1.9	1.0	0.7
5.3 & Above	-	0.1	0.1	0.1	1.6	0.5	*	0.1	*	*
Average	3.98	4.06	4.28	4.30	4.54	4.46	3.74	4.07	4.21	4.27
Leaf										
1 - 2	63.2	67.1	1.9	2.7	16.7	21.4	49.9	50.9	5.0	7.1
3	28.3	25.4	33.0	38.5	56.3	54.8	31.6	32.8	58.8	61.6
4	6.9	5.7	48.8	46.0	25.4	21.4	12.3	12.2	33.4	29.1
5	1.1	1.4	14.6	11.7	1.6	2.3	3.8	2.9	2.8	2.1
6	0.3	0.3	1.6	1.1	*	0.1	1.4	0.8	*	0.1
7	0.1	*	0.1	*	-	*	0.6	0.3	-	*
8	*	*	-	*	-	-	0.4	0.1	-	-
Average	2.32	2.17	3.81	3.70	3.11	3.04	2.62	2.53	3.34	3.26
HVI Trash 1/										
00	*	0.2	-	-	-	*	0.2	0.2	-	-
01	24.8	33.8	0.1	0.1	2.0	3.0	24.8	26.3	0.2	0.3
02	37.9	32.8	2.6	3.7	17.3	18.9	29.5	26.9	7.2	8.8
03	19.4	17.1	12.9	15.8	27.1	27.4	18.5	18.4	25.5	27.4
04	9.1	8.2	23.5	25.1	25.1	23.2	11.1	12.4	32.0	31.0
05	4.4	3.8	24.3	23.5	16.6	14.4	6.4	7.3	20.4	19.1
06	2.2	2.0	17.7	15.7	7.8	7.5	3.7	3.9	9.7	8.6
07	1.0	1.0	10.3	8.7	2.9	3.3	2.1	2.1	3.4	3.3
08	0.4	0.5	4.8	4.2	0.8	1.4	1.2	1.1	1.1	1.0
09	0.2	0.3	2.3	1.9	0.2	0.5	0.8	0.6	0.4	0.3
10	0.1	0.2	0.9	0.8	0.1	0.2	0.5	0.4	0.1	0.1
11	0.1	0.1	0.4	0.3	*	0.1	0.4	0.2	*	*
12	0.1	*	0.2	0.1	-	*	0.3	0.1	*	*
13	0.1	*	0.1	0.1	*	*	0.2	0.1	*	*
14	*	*	*	*	-	*	0.1	*	-	-
15	*	*	*	*	-	*	0.1	*	-	*
16	*	*	-	*	-	*	*	*	-	*
17	-	*	-	*	-	*	*	*	-	*
18 & Above	*	*	-	-	-	*	0.1	*	-	-
Average	0.25	0.23	0.51	0.49	0.38	0.37	0.29	0.28	0.42	0.41
UNIFORMITY 2/										
74 & Below	-	*	-	-	-	-	0.1	*	-	-
75	*	0.1	-	-	-	-	0.4	0.2	-	-
76	0.2	0.4	*	*	-	*	1.6	0.8	*	*
77	1.5	1.6	0.3	0.2	*	*	6.0	2.8	0.1	0.1
78	6.8	6.0	1.8	1.4	0.1	0.1	16.2	8.4	0.5	0.5
79	19.8	17.0	10.8	7.7	0.6	1.4	24.1	18.3	3.6	2.8
80	33.7	31.8	34.4	27.5	19.3	14.3	27.3	27.0	16.6	13.6
81	26.7	30.4	36.6	38.2	43.2	39.2	17.3	26.0	42.7	37.4
82	9.6	11.1	13.4	19.5	32.3	33.1	5.8	13.2	28.1	33.0
83	1.6	1.5	2.3	4.8	4.4	10.4	1.1	2.9	7.3	11.2
84	0.1	0.1	0.3	0.7	0.1	1.3	0.1	0.3	1.0	1.4
85 & Above	-	*	*	*	-	0.1	*	*	0.1	0.1
Average	80.58	80.67	81.02	81.29	81.65	81.86	79.94	80.59	81.67	81.84
Tenderable 3/	72.2	80.1	86.7	90.8	86.1	90.4	51.0	74.0	93.2	94.2
SAMPLES CLASSED	33,428	315,833	21,813	192,293	18,362	580,916	147,539	4,406,889	13,744	92,674

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 24, 2020

Color Grade	Leaf	Arizona		California		New Mexico		Texas	
		Week	Season	Week	Season	Week	Season	Week	Season
01	1	90.7	87.3	14.2	14.9	-	-	45.9	36.5
	2	7.1	5.2	11.0	7.0	-	-	10.5	12.2
	3	-	0.1	0.1	0.1	-	-	*	0.2
	4	-	-	-	-	-	-	-	*
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		97.9	92.6	25.4	22.0	-	-	56.4	49.0
02	1	2.0	7.0	16.2	29.0	-	-	23.1	22.8
	2	0.1	0.4	52.5	41.4	-	-	18.4	24.4
	3	-	-	2.7	2.0	-	-	0.2	1.8
	4	-	-	*	*	-	-	-	0.1
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		2.1	7.3	71.5	72.4	-	-	41.7	49.1
03	1	-	*	0.1	1.2	-	-	0.1	0.2
	2	-	-	2.2	3.6	-	-	1.5	1.2
	3	-	*	0.7	0.6	-	-	0.2	0.5
	4	-	-	*	*	-	-	-	0.1
	5	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	*	3.0	5.4	-	-	1.8	1.9
04	1	-	-	-	0.1	-	-	-	-
	2	-	-	*	0.1	-	-	*	*
	3	-	-	0.1	0.1	-	-	*	*
	4	-	*	*	*	-	-	-	-
	5	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	*	0.1	0.2	-	-	0.1	*
05	1	-	-	-	*	-	-	-	-
	2	-	-	-	*	-	-	-	-
	3	-	-	-	*	-	-	-	-
	4	-	-	-	*	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	-	*	-	-	-	-
06	1	-	-	-	*	-	-	-	-
	2	-	-	-	*	-	-	-	-
	3	-	-	-	*	-	-	-	-
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	-	*	-	-	-	-
07	1	-	-	-	-	-	-	-	-
	2	-	-	-	*	-	-	-	-
	3	-	-	-	*	-	-	-	-
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	-	*	-	-	-	-
STAPLE									
44 & Shorter		-	-	0.7	1.2	-	-	0.3	4.6
46		-	0.6	4.3	10.6	-	-	3.7	20.6
48		61.2	52.7	9.1	18.8	-	-	53.2	54.7
50		38.8	46.6	69.5	60.4	-	-	36.2	17.1
52 & Longer		-	0.1	16.4	8.9	-	-	6.6	3.0
Average Staple		48.78	48.93	49.93	49.31	-	-	48.90	47.86
Average Length		1.42	1.42	1.45	1.43	-	-	1.42	1.39
EXTRANEIOUS MATTER									
Bark		-	-	-	*	-	-	-	0.1
Grass		-	-	0.2	0.3	-	-	-	0.3
Spindle Twist		-	-	0.3	*	-	-	0.1	0.8
Preparation		-	-	-	*	-	-	0.1	0.2
All Other		-	-	*	*	-	-	0.1	0.1

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 24, 2020

Quality Designation	Arizona		California		New Mexico		Texas	
	Week	Season	Week	Season	Week	Season	Week	Season
MIKE								
2.4 & Below	-	-	-	-	-	-	-	*
2.5 - 2.6	-	-	-	*	-	-	-	*
2.7 - 2.9	-	-	0.1	*	-	-	0.1	0.9
3.0 - 3.2	-	-	0.2	0.1	-	-	0.9	3.8
3.3 - 3.4	-	-	0.6	0.4	-	-	3.1	4.4
3.5 - 3.6	0.1	0.1	1.0	2.2	-	-	6.0	6.6
3.7 - 4.2	89.9	80.5	29.4	34.3	-	-	59.9	55.6
4.3 - 4.9	10.0	19.4	68.7	62.9	-	-	30.0	28.7
5.0 - 5.2	-	-	*	*	-	-	-	-
5.3 & Above	-	-	*	*	-	-	-	-
Average	4.11	4.13	4.33	4.29	-	-	4.07	4.02
ALL RANGE MIKE								
2.4 & Below	-	-	-	-	-	-	-	*
2.5	-	-	-	-	-	-	-	-
2.6	-	-	-	*	-	-	-	*
2.7	-	-	-	*	-	-	-	0.1
2.8	-	-	0.1	*	-	-	-	0.2
2.9	-	-	-	*	-	-	0.1	0.5
3.0	-	-	*	*	-	-	0.1	0.7
3.1	-	-	0.1	*	-	-	0.2	1.2
3.2	-	-	0.1	*	-	-	0.6	1.9
3.3	-	-	0.2	0.1	-	-	1.2	2.1
3.4	-	-	0.4	0.3	-	-	1.9	2.3
3.5	-	-	0.6	0.9	-	-	2.5	2.8
3.6	0.1	0.1	0.4	1.3	-	-	3.5	3.8
3.7	-	0.5	1.7	2.0	-	-	3.7	4.5
3.8	1.6	1.1	2.1	2.9	-	-	5.3	4.8
3.9	13.2	8.6	2.6	4.8	-	-	8.5	9.1
4.0	10.9	17.6	6.0	6.2	-	-	13.0	11.1
4.1	32.9	31.0	6.9	7.4	-	-	17.2	14.1
4.2	31.4	21.7	10.2	11.0	-	-	12.3	12.0
4.3	9.9	15.6	13.9	15.6	-	-	10.5	10.8
4.4	-	1.7	18.6	17.7	-	-	15.0	11.9
4.5	0.1	1.5	17.2	14.1	-	-	4.1	4.7
4.6	-	0.6	11.5	9.4	-	-	0.5	1.4
4.7	-	*	5.2	4.5	-	-	-	*
4.8	-	-	1.9	1.4	-	-	-	-
4.9	-	-	0.3	0.2	-	-	-	-
5.0	-	-	*	*	-	-	-	-
5.1	-	-	*	*	-	-	-	-
5.2	-	-	*	*	-	-	-	-
5.3 & Above	-	-	*	*	-	-	-	-
Average	4.11	4.13	4.33	4.29	-	-	4.07	4.02
STRENGTH 1/ 36 & Below	-	-	*	0.2	-	-	0.2	3.8
37	-	*	0.2	1.9	-	-	0.4	3.4
38	-	-	1.1	4.7	-	-	0.6	4.0
39	-	*	3.1	4.7	-	-	1.2	4.5
40	0.4	0.9	1.4	2.3	-	-	1.8	7.5
41	5.8	3.9	1.8	2.6	-	-	9.8	11.1
42	6.3	7.6	7.1	7.0	-	-	19.6	14.4
43	22.7	24.8	14.8	16.0	-	-	23.3	15.7
44	38.2	42.0	21.3	22.6	-	-	20.2	16.5
45	9.7	14.7	25.1	21.1	-	-	15.1	12.3
46	16.2	5.5	15.8	11.4	-	-	5.7	5.1
47	0.2	0.4	5.6	4.0	-	-	1.2	1.3
48 & Above	0.4	0.2	2.7	1.5	-	-	1.0	0.4
Average	44.32	44.15	44.67	43.93	-	-	43.68	42.62
UNIFORMITY								
83 & Below	-	-	0.1	0.2	-	-	0.3	1.8
84	-	*	2.5	6.0	-	-	2.0	5.2
85	3.9	6.2	8.5	11.9	-	-	6.2	16.0
86	52.1	39.0	35.2	37.9	-	-	56.8	51.2
87	44.0	54.3	48.2	40.4	-	-	33.6	25.2
88 & Above	-	0.5	5.5	3.5	-	-	1.2	0.6
Average	86.88	86.94	86.91	86.67	-	-	86.69	86.39
Samples Classed	994	4,687	24,538	282,563	-	-	3,496	24,349

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.