



State	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
AL	6	57.4	49.7	1,901	29	86.0	73.6	977,044
AR	3	90.1	72.7	16,640	29	89.7	75.1	1,451,671
AZ	9	73.3	54.0	16,511	12	76.4	56.0	323,936
CA	2	4.40	4.10	1,560	17	86.9	75.5	183,145
FL*	-	-	-	-	4	82.9	65.9	158,776
GA	17	79.5	69.8	5,043	59	84.9	66.1	2,712,801
KS	3	35.7	15.9	17,218	3	53.1	33.3	209,336
LA	2	81.5	49.9	951	19	89.3	70.2	581,693
MO*	-	-	-	-	21	89.5	74.0	827,340
MS	5	65.8	48.7	972	38	88.4	65.9	1,536,875
NC	7	60.2	50.3	2,772	34	83.4	59.4	1,060,770
NM*	-	-	-	-	3	85.2	67.0	31,678
OK	6	90.0	73.9	10,827	12	77.8	60.2	503,174
SC	4	81.2	59.5	2,025	15	87.5	67.2	420,919
TN	-	-	-	-	22	89.4	71.1	938,993
TX	16	48.4	29.0	26,201	187	66.0	39.2	6,305,469
VA*	-	-	-	-	4	86.1	59.7	229,678
United States	84	65.0	47.2	108,669	508	79.0	57.7	18,453,298
AMERICAN PIMA								
AZ*	-			-	3			12,610
CA	6			21,567	17			575,425
NM*	-			-	-			-
TX*	-			-	3			15,020
United States	7			21,568	24			612,981
United States all cotton	90			130,237	520			19,066,279

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Feb 13, 2020

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	0.4	8.4	1.6	4.8	16.0	42.4	0.4	46.5	-	3.4	0.5	8.9
	3	0.2	8.9	2.0	4.3	2.6	4.6	-	5.0	-	3.0	2.3	6.5
	4	-	0.7	*	0.2	*	0.2	-	0.2	-	0.2	0.2	0.3
	5	-	*	-	*	-	*	-	*	-	-	-	*
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.6	18.0	3.6	9.3	18.7	47.3	0.4	51.7	-	6.5	3.0	15.7
31	1 - 2	0.1	2.2	2.4	3.4	10.1	9.5	0.8	13.7	-	1.5	0.2	3.6
	3	2.3	12.9	27.7	18.4	7.6	8.2	0.2	12.1	-	8.8	4.7	12.4
	4	0.4	5.6	8.0	8.3	0.9	1.6	-	1.6	-	3.5	2.4	4.2
	5	-	0.5	0.5	0.8	*	0.2	-	0.1	-	0.3	0.1	0.3
	6	-	*	*	*	-	*	-	*	-	*	*	*
	7	-	*	-	-	-	*	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	2.8	21.3	38.6	31.0	18.6	19.6	1.0	27.4	-	14.1	7.4	20.5
41	1 - 2	-	1.6	0.3	0.7	6.5	2.9	0.4	2.6	-	0.8	0.8	2.1
	3	13.3	16.5	17.3	12.8	12.7	7.2	4.0	8.4	-	16.7	18.4	18.1
	4	23.1	14.7	22.5	22.9	9.5	4.8	5.8	3.7	-	26.1	29.9	16.3
	5	5.5	3.3	7.3	12.2	3.4	1.5	3.5	0.5	-	5.7	4.3	3.4
	6	0.3	0.3	0.7	1.4	0.4	0.4	1.2	*	-	0.3	0.1	0.2
	7	-	*	*	*	*	0.1	-	*	-	*	-	*
	8	-	*	-	-	-	*	-	-	-	-	-	-
Total	----	42.2	36.5	48.1	50.1	32.5	16.9	14.9	15.2	-	49.6	53.3	40.2
51	1 - 2	0.8	0.7	*	0.1	1.0	0.7	-	0.1	-	0.4	1.3	0.9
	3	8.7	6.1	1.7	1.4	8.1	2.3	0.5	0.3	-	7.1	14.2	7.3
	4	5.2	5.6	3.9	3.6	7.4	2.4	1.5	0.2	-	11.4	10.4	6.0
	5	12.5	1.7	2.3	2.6	5.0	1.7	1.7	0.1	-	4.1	1.1	1.4
	6	22.9	0.5	0.3	0.4	1.3	0.8	0.6	0.1	-	0.3	*	0.1
	7	2.7	0.1	*	*	0.3	0.3	-	*	-	*	-	*
	8	-	*	-	*	0.2	0.1	-	*	-	-	-	*
Total	----	52.8	14.6	8.2	8.1	23.2	8.4	4.4	0.8	-	23.2	27.0	15.7
61	1 - 2	0.1	*	-	-	*	*	-	*	-	*	-	*
	3	0.2	0.1	-	*	*	*	0.6	*	-	0.1	0.2	0.1
	4	0.1	*	-	*	*	*	0.3	*	-	0.2	0.1	*
	5	-	*	-	*	-	*	-	-	-	0.1	*	*
	6	-	*	-	*	-	*	-	-	-	*	-	*
	7	-	*	-	-	-	*	-	-	-	-	-	*
	8	-	*	-	-	-	*	-	-	-	-	-	*
Total	----	0.3	0.1	-	*	*	0.1	0.8	*	-	0.4	0.3	0.2
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	*
	3	-	-	-	*	-	-	-	-	-	-	-	*
	4	-	*	-	-	-	*	-	-	-	-	-	*
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	*
	7	-	*	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	*	-	-	-	*	-	*
Total	----	-	*	-	*	-	*	-	-	-	*	-	*
12 & 22	1 - 2	0.1	0.2	-	*	0.4	1.2	-	0.1	-	*	0.2	0.4
	3	0.2	0.4	*	*	0.1	1.1	-	0.1	-	*	*	0.2
	4	-	0.1	-	*	-	0.2	-	*	-	*	-	*
	5	-	*	-	-	-	*	-	*	-	-	-	-
	6	-	-	-	-	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.3	0.7	*	0.1	0.5	2.5	-	0.2	-	0.1	0.2	0.6
32	1 - 2	-	0.1	*	*	1.1	0.5	0.1	0.3	-	*	0.1	0.3
	3	0.3	0.9	0.1	0.2	0.7	1.0	-	0.7	-	0.3	0.5	1.0
	4	0.1	0.6	0.2	0.2	0.1	0.5	0.3	0.3	-	0.2	0.4	0.3
	5	-	0.1	*	*	*	0.1	0.1	0.1	-	*	0.1	*
	6	-	*	*	*	-	*	-	*	-	*	-	*
	7	-	*	-	-	-	*	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.3	1.8	0.3	0.5	1.9	2.1	0.4	1.3	-	0.6	1.1	1.5
42	1 - 2	-	0.2	-	*	0.8	0.1	-	*	-	0.1	0.2	0.2
	3	0.2	1.7	0.2	0.2	0.8	0.6	1.7	0.5	-	0.8	1.6	1.4
	4	0.4	1.8	0.3	0.3	0.6	0.8	16.3	1.0	-	1.4	1.2	1.2
	5	-	0.6	0.3	0.1	0.2	0.4	14.4	0.4	-	0.5	0.4	0.2
	6	-	0.1	*	*	*	0.2	4.0	0.1	-	*	-	*
	7	-	*	*	*	-	*	0.3	*	-	*	-	*
	8	-	*	-	-	-	*	-	-	-	-	-	-
Total	----	0.6	4.3	0.8	0.7	2.4	2.1	36.7	2.0	-	2.7	3.3	3.0

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Feb 13, 2020

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	0.1	-	*	*	*	-	*	-	0.1	0.1	0.1
	3	0.1	0.8	-	*	0.1	0.1	0.8	0.1	-	0.7	0.8	0.9
	4	-	0.9	*	*	0.4	0.1	3.7	0.2	-	1.1	0.7	0.7
	5	-	0.2	0.1	*	0.3	0.1	10.6	0.3	-	0.5	0.1	0.2
	6	0.1	*	*	*	0.1	*	7.9	0.3	-	0.1	-	*
	7	-	*	-	-	0.1	*	2.6	0.1	-	*	-	*
	8	-	*	-	-	0.2	0.1	0.2	*	-	*	-	*
Total	----	0.1	2.1	0.1	0.1	1.2	0.4	25.8	1.1	-	2.4	1.7	2.0
62	1 - 2	-	*	-	*	-	-	-	-	-	*	-	*
	3	-	*	-	*	-	-	0.9	*	-	*	-	*
	4	-	*	-	*	-	*	1.2	*	-	0.1	-	*
	5	-	*	-	*	-	*	0.3	*	-	*	*	*
	6	-	*	-	*	-	*	-	-	-	*	-	*
	7	-	*	-	-	-	-	-	*	-	*	-	*
	8	-	*	-	-	*	*	-	*	-	*	-	*
Total	----	-	0.1	-	*	*	*	2.4	*	-	0.1	*	0.1
13 & 23	1 - 2	-	*	-	*	*	*	-	*	-	-	-	*
	3	-	*	-	*	*	*	-	*	-	-	-	*
	4	-	*	-	*	-	*	-	-	-	*	-	*
	5	-	*	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	*	*	0.1	-	*	-	*	-	*
33	1 - 2	-	*	-	*	0.2	0.1	-	*	-	-	*	*
	3	0.1	*	*	*	0.2	0.2	-	*	-	*	0.1	*
	4	-	*	*	*	*	*	-	*	-	*	0.1	*
	5	-	*	-	*	-	*	-	*	-	*	0.1	*
	6	-	*	-	-	-	*	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.1	0.1	*	*	0.4	0.3	-	*	-	*	0.3	0.1
43	1 - 2	-	*	-	*	*	*	-	*	-	-	0.1	*
	3	-	0.1	0.1	*	0.2	0.1	1.0	*	-	*	0.8	0.1
	4	-	0.2	*	0.1	0.2	0.1	3.1	*	-	0.1	0.6	0.1
	5	-	0.1	0.1	*	0.1	0.1	1.2	*	-	*	0.1	*
	6	-	*	*	*	*	*	0.6	*	-	*	-	*
	7	-	*	-	*	-	*	0.1	*	-	*	-	*
	8	-	*	-	-	-	*	-	-	-	-	-	-
Total	----	-	0.4	0.2	0.1	0.5	0.2	6.1	0.1	-	0.1	1.7	0.2
53	1 - 2	-	*	-	-	*	*	-	-	-	-	-	*
	3	-	*	-	*	*	*	-	*	-	*	0.2	*
	4	-	*	-	*	*	*	0.2	*	-	*	0.1	0.1
	5	-	*	-	*	*	*	2.1	*	-	*	-	*
	6	-	*	-	*	-	*	3.2	*	-	*	-	*
	7	-	*	-	*	*	*	1.1	*	-	-	-	*
	8	-	*	-	-	-	*	0.6	*	-	-	-	-
Total	----	-	0.1	-	*	*	*	7.2	0.1	-	0.1	0.3	0.1
63	1 - 2	-	*	-	-	-	-	-	-	-	-	-	*
	3	-	*	-	*	-	-	-	*	-	*	-	*
	4	-	*	-	*	-	*	-	-	-	*	-	*
	5	-	*	-	-	-	-	-	-	-	-	-	*
	6	-	*	-	-	-	-	-	-	-	*	-	*
	7	-	*	-	*	-	*	-	-	-	*	-	*
	8	-	*	-	-	-	*	-	-	-	*	-	*
Total	----	-	*	-	*	-	*	-	*	-	*	-	*
24 - 54	1 - 8	-	*	*	*	0.1	0.1	-	*	-	*	0.4	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	*	-	*	-	*	-	*	-	-	-	*
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	-	-	-	-	*	-	-	-	-	*	*
31		-	*	-	*	-	*	-	*	-	*	0.1	*
32		-	0.4	-	*	-	0.1	-	*	-	*	1.1	0.5
33		0.5	2.0	*	*	0.1	0.6	0.1	0.1	-	0.6	2.5	2.4
34		2.8	6.8	0.3	0.1	0.7	2.5	4.7	1.4	-	2.5	9.1	7.4
35		3.1	13.1	2.3	1.9	2.4	8.3	21.5	4.5	-	5.3	15.7	15.4
36		37.8	22.9	19.5	11.6	17.4	19.3	22.1	13.7	-	12.7	17.5	21.2
37		47.8	32.4	44.4	40.2	34.7	31.1	37.9	30.2	-	32.9	22.7	29.0
38		6.6	15.0	14.1	25.4	21.9	20.8	12.8	27.1	-	33.7	22.2	16.8
39		1.3	6.3	16.5	16.4	12.1	12.9	1.0	19.4	-	11.0	8.7	6.5
40 & Longer		0.1	1.1	2.8	4.4	10.7	4.5	-	3.8	-	1.1	0.4	0.8
Average Staple		36.55	36.51	37.31	37.56	37.55	37.15	36.35	37.50	-	37.25	36.49	36.46
Average Length		1.14	1.14	1.16	1.17	1.17	1.16	1.13	1.17	-	1.16	1.14	1.14

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Feb 13, 2020

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	3.5	17.9	9.9	15.2	-	2.7	9.8	13.6	3.6	4.6	-	38.0
	3	8.3	7.7	0.4	13.5	-	1.3	-	11.5	3.6	4.9	-	3.9
	4	0.7	0.4	-	0.7	-	*	-	1.3	0.2	0.3	-	*
	5	-	*	-	*	-	*	-	*	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	*	-	-	-	-
Total	----	12.5	25.9	10.3	29.5	-	4.0	9.8	26.4	7.4	9.8	-	41.9
31	1 - 2	1.1	3.0	0.4	2.4	-	5.8	3.7	2.9	2.3	3.6	-	14.0
	3	11.0	13.7	1.1	14.0	-	19.2	11.1	13.8	23.8	19.4	-	18.8
	4	12.7	9.6	0.6	6.5	-	7.1	0.6	7.3	5.3	8.5	-	3.3
	5	2.1	1.6	1.8	0.5	-	0.7	-	0.8	0.5	0.8	-	0.2
	6	0.1	0.1	-	*	-	*	-	*	-	*	-	-
	7	-	*	-	*	-	-	-	*	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-	-	-
Total	----	27.1	28.1	3.9	23.5	-	32.8	15.4	24.9	31.9	32.4	-	36.3
41	1 - 2	*	*	5.2	0.6	-	1.7	7.4	1.0	0.6	2.8	-	0.3
	3	0.1	0.2	23.4	9.5	-	18.0	10.8	11.1	13.0	25.6	-	1.9
	4	1.4	1.1	20.7	14.7	-	24.8	1.9	15.7	8.5	19.5	-	2.0
	5	1.5	1.6	12.6	4.7	-	11.0	-	5.5	0.8	3.2	-	0.7
	6	0.4	0.5	1.2	0.4	-	1.2	-	0.6	*	0.2	-	0.1
	7	*	0.1	-	*	-	*	-	*	-	*	-	-
	8	*	*	-	-	-	-	-	*	-	-	-	-
Total	----	3.5	3.5	63.1	29.9	-	56.7	20.1	33.9	23.0	51.2	-	4.9
51	1 - 2	-	-	0.5	0.1	-	0.1	5.9	0.2	0.9	0.1	-	*
	3	-	-	6.5	2.4	-	0.8	8.4	2.7	8.9	1.1	-	*
	4	-	*	3.9	5.9	-	2.6	2.3	5.5	5.9	1.8	-	*
	5	-	*	4.3	2.7	-	1.8	0.2	2.7	0.8	0.6	-	*
	6	-	*	1.1	0.4	-	0.4	-	0.5	-	0.1	-	*
	7	*	0.1	0.2	*	-	*	-	*	-	*	-	-
	8	0.2	0.1	-	*	-	*	-	*	-	*	-	-
Total	----	0.2	0.2	16.5	11.4	-	5.6	16.8	11.7	16.5	3.6	-	*
61	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	*	-	*	-	-	-	-
	4	-	-	-	0.1	-	*	-	*	-	*	-	-
	5	-	-	-	0.1	-	*	-	*	-	-	-	-
	6	-	-	-	*	-	*	-	*	-	-	-	-
	7	-	-	-	*	-	*	-	*	-	*	-	-
	8	-	-	-	-	-	*	-	*	-	*	-	-
Total	----	-	-	-	0.2	-	*	-	*	-	*	-	-
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	*	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	*	-	-	-	-
	8	-	-	-	-	-	*	-	-	-	-	-	-
Total	----	-	-	-	-	-	*	-	*	-	-	-	-
12 & 22	1 - 2	7.9	11.1	-	0.4	-	*	-	0.1	0.1	*	-	2.8
	3	9.9	4.4	-	0.5	-	*	-	0.2	1.0	0.1	-	1.9
	4	1.2	0.3	-	0.1	-	-	-	0.1	*	*	-	0.1
	5	*	*	-	*	-	-	-	*	-	*	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	19.1	15.8	-	1.0	-	*	-	0.4	1.2	0.1	-	4.7
32	1 - 2	0.5	0.3	-	0.1	-	*	0.2	0.1	0.2	0.1	-	1.1
	3	4.0	2.3	-	0.6	-	0.1	4.4	0.3	2.8	0.5	-	4.6
	4	8.0	3.6	0.2	0.3	-	0.1	0.6	0.3	1.3	0.3	-	1.8
	5	2.3	1.6	0.4	*	-	*	-	0.1	0.3	*	-	0.2
	6	0.1	0.2	0.1	*	-	*	-	*	-	*	-	*
	7	*	*	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	14.9	8.0	0.7	1.0	-	0.2	5.2	0.7	4.7	0.9	-	7.7
42	1 - 2	*	*	0.1	0.1	-	*	0.1	*	0.1	*	-	*
	3	0.4	0.1	0.4	0.8	-	0.1	7.6	0.3	5.8	0.6	-	0.2
	4	0.4	0.3	0.4	1.1	-	0.2	2.8	0.6	4.3	0.8	-	0.3
	5	0.8	1.0	1.8	0.4	-	0.1	0.2	0.4	-	0.2	-	0.4
	6	0.2	0.8	0.1	0.1	-	*	-	*	-	*	-	0.2
	7	*	0.3	-	*	-	*	-	*	-	*	-	0.1
	8	*	0.1	-	-	-	-	-	*	-	-	-	*
Total	----	1.8	2.4	2.8	2.4	-	0.4	10.7	1.3	10.1	1.6	-	1.1

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Feb 13, 2020

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	-	*	-	*	0.1	*	-	*	-	-
	3	-	-	0.6	0.2	-	*	4.3	0.1	0.3	*	-	*
	4	-	*	0.2	0.3	-	*	5.6	0.2	0.4	*	-	*
	5	-	*	0.5	0.2	-	*	2.4	0.1	*	*	-	0.1
	6	-	0.1	0.3	*	-	*	-	*	-	*	-	*
	7	0.1	0.1	-	*	-	*	-	*	-	*	-	-
	8	0.3	0.1	-	*	-	*	-	*	-	*	-	-
Total	----	0.4	0.3	1.7	0.7	-	0.1	12.3	0.4	0.8	0.1	-	0.1
62	1 - 2	-	-	-	-	-	-	-	*	-	-	-	-
	3	-	-	-	*	-	*	-	*	-	-	-	-
	4	-	*	-	*	-	*	0.2	*	-	*	-	-
	5	-	*	-	*	-	*	0.9	*	-	-	-	-
	6	-	-	-	*	-	*	0.1	*	-	*	-	-
	7	-	*	-	*	-	-	-	*	-	-	-	-
	8	-	-	-	-	-	*	-	-	-	-	-	-
Total	----	-	*	-	*	-	*	1.2	*	-	*	-	-
13 & 23	1 - 2	5.5	3.9	-	*	-	-	-	*	-	*	-	0.4
	3	5.2	2.3	-	*	-	-	-	*	0.5	*	-	0.2
	4	0.3	0.2	-	*	-	-	-	*	0.1	*	-	*
	5	*	*	-	-	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	*	-	-	-	-
Total	----	11.1	6.4	-	*	-	-	-	*	0.6	*	-	0.6
33	1 - 2	1.5	0.3	-	*	-	*	-	*	0.1	*	-	0.5
	3	3.2	1.0	-	0.1	-	*	2.0	*	1.3	0.1	-	1.2
	4	2.6	1.0	0.1	*	-	*	1.3	*	0.7	*	-	0.3
	5	0.7	0.6	-	*	-	*	-	*	0.2	*	-	*
	6	0.1	0.2	-	*	-	-	-	*	-	*	-	-
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	----	8.0	3.2	0.1	0.1	-	*	3.3	0.1	2.3	0.1	-	2.0
43	1 - 2	-	*	-	*	-	*	0.1	*	-	*	-	-
	3	-	*	-	0.1	-	*	1.3	*	0.2	0.1	-	*
	4	0.1	0.3	-	0.1	-	0.1	0.8	0.1	1.3	0.1	-	*
	5	0.2	0.6	0.3	*	-	*	0.1	*	0.1	*	-	0.1
	6	*	0.5	-	*	-	*	-	*	-	*	-	*
	7	-	0.3	-	-	-	-	-	*	-	-	-	*
	8	*	0.2	-	-	-	-	-	*	-	-	-	*
Total	----	0.3	1.9	0.3	0.3	-	0.1	2.4	0.1	1.6	0.2	-	0.2
53	1 - 2	-	-	-	-	-	-	-	*	-	*	-	-
	3	-	-	-	*	-	*	0.8	*	-	*	-	-
	4	-	0.1	0.1	*	-	*	1.1	*	*	*	-	-
	5	-	0.1	0.2	*	-	*	0.4	*	-	*	-	-
	6	-	0.3	0.1	*	-	*	-	*	-	*	-	-
	7	-	0.3	-	*	-	-	-	*	-	*	-	-
	8	0.1	0.3	-	-	-	-	-	*	-	*	-	*
Total	----	0.1	1.0	0.4	0.1	-	*	2.4	*	*	*	-	*
63	1 - 2	-	-	-	-	-	*	-	*	-	-	-	-
	3	-	-	-	-	-	*	-	*	-	-	-	-
	4	-	*	-	-	-	*	-	*	-	-	-	-
	5	-	*	-	-	-	*	-	*	-	*	-	-
	6	-	*	-	-	-	*	-	*	-	-	-	-
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	*	-	-	-	-	-	-
Total	----	-	*	-	-	-	*	-	*	-	*	-	-
24 - 54	1 - 8	1.0	2.2	0.1	*	-	*	0.4	*	*	*	-	0.4
25 - 35	1 - 8	-	*	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	0.9	-	*	-	*	-	*	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	*	-	-	-	-	-	-	-	-	-	-
30		-	*	-	-	-	-	-	-	-	-	-	-
31		*	*	-	-	-	*	-	-	-	*	-	-
32		*	0.1	-	*	-	*	-	*	-	0.1	-	-
33		0.9	0.7	-	*	-	*	-	*	0.1	0.4	-	*
34		4.7	4.8	-	0.3	-	0.3	0.2	0.7	0.5	2.6	-	0.3
35		15.6	20.2	-	1.7	-	3.1	5.5	3.6	5.8	10.8	-	3.1
36		40.4	39.0	13.9	8.2	-	15.3	21.1	11.9	21.7	27.3	-	12.7
37		31.1	29.7	28.6	22.3	-	44.0	27.0	27.9	42.5	33.7	-	35.8
38		6.2	4.7	5.3	30.8	-	21.5	39.0	33.9	24.8	16.7	-	26.3
39		1.1	0.5	19.3	26.1	-	11.5	7.0	19.5	4.3	7.2	-	17.2
40 & Longer		*	0.3	32.9	10.6	-	4.3	0.3	2.6	0.3	1.2	-	4.6
Average Staple		36.19	36.09	38.48	38.04	-	37.35	37.21	37.59	36.99	36.76	-	37.55
Average Length		1.13	1.12	1.20	1.19	-	1.17	1.16	1.18	1.15	1.15	-	1.17

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Feb 13, 2020

Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	46.2	41.6	0.8	6.1	-	4.1	8.8	26.3	-	11.7
	3	14.9	9.2	0.8	8.2	-	2.2	7.7	9.7	-	12.4
	4	1.0	0.2	*	0.5	-	0.2	0.8	0.7	-	0.6
	5	-	*	-	*	-	*	-	*	-	*
	6	-	-	-	*	-	-	-	*	-	*
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	62.1	51.1	1.7	14.8	-	6.5	17.3	36.7	-	24.8
31	1 - 2	3.6	7.3	11.0	5.2	-	5.8	5.7	4.5	-	5.3
	3	12.3	17.5	19.4	25.2	-	16.6	13.6	10.0	-	19.9
	4	9.8	5.5	7.6	9.2	-	5.6	4.9	3.5	-	6.0
	5	1.1	0.7	0.3	0.5	-	0.5	0.4	0.4	-	0.3
	6	*	*	-	*	-	*	-	*	-	*
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	26.8	31.0	38.3	40.2	-	28.5	24.5	18.5	-	31.6
41	1 - 2	0.2	0.1	4.2	2.1	-	3.8	0.4	0.6	-	6.4
	3	1.0	0.9	21.4	18.8	-	21.7	1.1	2.4	-	25.7
	4	1.9	2.0	9.7	13.1	-	21.4	1.6	1.8	-	6.5
	5	0.5	1.3	0.2	1.6	-	7.4	0.8	0.6	-	0.5
	6	*	0.5	-	0.1	-	0.9	0.3	0.2	-	*
	7	*	0.1	-	*	-	*	0.1	*	-	-
	8	-	*	-	-	-	*	*	*	-	-
Total	----	3.7	5.0	35.6	35.6	-	55.1	4.2	5.4	-	39.2
51	1 - 2	*	*	0.9	0.2	-	0.2	*	0.1	-	0.4
	3	*	*	1.6	1.7	-	1.8	0.1	0.3	-	1.6
	4	-	*	0.7	1.4	-	2.6	*	0.2	-	0.6
	5	*	*	-	0.3	-	1.3	*	0.1	-	0.1
	6	*	*	-	*	-	0.3	*	*	-	*
	7	*	*	-	*	-	*	*	*	-	-
	8	-	*	-	*	-	*	*	*	-	-
Total	----	0.1	0.1	3.2	3.5	-	6.1	0.2	0.7	-	2.5
61	1 - 2	-	-	-	*	-	*	-	*	-	-
	3	-	-	-	*	-	-	-	*	-	-
	4	-	-	-	*	-	*	-	*	-	*
	5	-	-	-	*	-	*	*	*	-	-
	6	-	-	-	*	-	-	-	*	-	-
	7	-	-	-	*	-	-	-	*	-	-
	8	-	*	-	*	-	-	-	*	-	-
Total	----	-	*	-	*	-	*	*	0.1	-	*
71	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	-	-	-	-	*	-	-
	5	-	-	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	*	-	-	-	*	-	-
Total	----	-	-	-	*	-	-	-	*	-	-
12 & 22	1 - 2	1.4	1.6	-	0.1	-	0.1	1.8	8.4	-	0.1
	3	0.2	1.3	0.4	0.2	-	0.1	4.5	5.2	-	0.1
	4	-	0.1	0.1	*	-	*	0.7	0.6	-	*
	5	-	*	-	-	-	*	*	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	1.6	3.0	0.6	0.4	-	0.2	7.1	14.2	-	0.2
32	1 - 2	0.9	0.5	0.5	0.3	-	0.3	2.7	2.6	-	0.1
	3	0.8	2.8	4.7	1.5	-	0.8	10.8	6.6	-	0.3
	4	0.1	1.6	5.3	0.7	-	0.3	5.7	3.0	-	0.1
	5	*	0.3	0.4	0.1	-	*	1.0	0.5	-	*
	6	-	*	-	*	-	*	*	0.1	-	*
	7	-	*	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	1.8	5.3	11.0	2.6	-	1.3	20.2	12.8	-	0.6
42	1 - 2	*	*	-	0.1	-	0.1	0.6	0.2	-	0.1
	3	0.1	0.3	1.4	1.0	-	0.8	2.3	1.0	-	0.6
	4	0.4	0.7	2.8	0.9	-	0.7	2.9	1.1	-	0.3
	5	0.1	0.7	0.7	0.2	-	0.2	1.5	0.6	-	*
	6	0.1	0.3	-	*	-	*	0.4	0.2	-	*
	7	*	0.1	-	-	-	*	0.1	0.1	-	-
	8	-	*	-	-	-	-	*	*	-	-
Total	----	0.7	2.1	4.9	2.3	-	1.8	7.7	3.1	-	1.0

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Feb 13, 2020

Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	*	*	-	*	-	*	0.4	*	-	*
	3	-	*	0.1	0.1	-	0.1	0.5	0.1	-	*
	4	-	*	0.1	0.1	-	0.1	0.1	0.1	-	*
	5	*	*	-	*	-	*	*	*	-	*
	6	0.2	*	-	*	-	*	*	*	-	*
	7	0.1	*	-	*	-	*	*	*	-	*
	8	0.1	*	-	*	-	-	*	*	-	*
Total	----	0.5	0.1	0.2	0.2	-	0.1	1.0	0.3	-	0.1
62	1 - 2	-	*	-	-	-	-	*	*	-	*
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	*	-	-	-	*	-	-
	5	-	-	-	*	-	-	-	*	-	-
	6	-	-	-	*	-	-	-	*	-	-
	7	-	-	-	*	-	-	-	*	-	*
	8	-	*	-	-	-	-	-	*	-	-
Total	----	-	*	-	*	-	-	*	*	-	*
13 & 23	1 - 2	0.2	0.1	-	*	-	-	0.7	1.2	-	-
	3	*	0.1	-	*	-	*	1.2	1.1	-	*
	4	-	*	-	*	-	-	0.4	0.1	-	-
	5	-	*	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	0.2	0.2	-	*	-	*	2.3	2.5	-	*
33	1 - 2	0.4	0.2	0.2	*	-	*	1.1	0.8	-	*
	3	0.4	0.6	0.4	0.1	-	0.1	2.8	2.0	-	*
	4	*	0.4	0.8	0.1	-	*	1.5	1.0	-	*
	5	-	0.1	0.1	*	-	*	0.3	0.2	-	*
	6	-	*	-	-	-	-	*	*	-	-
	7	-	*	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	0.8	1.3	1.6	0.2	-	0.1	5.7	4.0	-	0.1
43	1 - 2	-	*	-	*	-	*	0.5	0.1	-	*
	3	0.2	0.1	0.6	0.1	-	0.1	2.2	0.3	-	0.1
	4	0.2	0.2	1.8	0.1	-	0.1	2.1	0.3	-	*
	5	0.1	0.2	0.4	*	-	*	0.9	0.2	-	*
	6	*	0.1	*	*	-	*	0.2	0.1	-	-
	7	*	*	-	*	-	-	*	*	-	-
	8	-	*	-	-	-	-	-	*	-	-
Total	----	0.4	0.6	3.0	0.3	-	0.3	5.9	1.0	-	0.1
53	1 - 2	-	-	-	*	-	*	-	*	-	*
	3	-	*	-	*	-	*	*	*	-	*
	4	-	*	-	*	-	*	0.1	*	-	*
	5	*	*	-	*	-	*	*	*	-	-
	6	*	*	-	*	-	*	*	*	-	-
	7	*	*	-	-	-	-	-	*	-	-
	8	*	*	-	-	-	-	-	*	-	-
Total	----	0.1	0.1	-	*	-	*	0.1	0.1	-	*
63	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	-	*	*	-	-
	4	-	-	-	*	-	-	*	*	-	-
	5	-	-	-	*	-	-	-	*	-	-
	6	-	-	-	*	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	-	-	-	*	-	-	*	*	-	-
24 - 54	1 - 8	1.1	0.2	*	*	-	*	3.2	0.6	-	*
25 - 35	1 - 8	-	*	-	-	-	-	-	*	-	-
81 - 85	1 - 8	-	*	-	*	-	*	0.5	*	-	-
STAPLE											
28 & Shorter		-	*	-	-	-	-	-	*	-	-
29		-	*	-	-	-	-	-	*	-	-
30		-	*	-	-	-	-	-	0.2	-	-
31		*	0.2	-	*	-	-	0.3	1.2	-	-
32		0.8	1.3	*	0.3	-	*	2.7	3.8	-	*
33		2.5	4.8	0.8	1.7	-	*	8.5	8.6	-	0.1
34		5.8	9.3	4.5	5.8	-	1.0	16.8	15.0	-	1.2
35		5.3	13.1	14.3	13.1	-	11.8	20.9	20.2	-	4.9
36		10.1	16.3	26.4	20.1	-	36.3	18.5	19.6	-	16.7
37		22.4	23.8	38.2	37.4	-	37.9	14.5	19.0	-	39.7
38		22.2	16.0	13.8	17.1	-	10.4	6.2	8.2	-	23.2
39		17.5	10.3	1.8	4.0	-	2.4	6.9	3.2	-	11.5
40 & Longer		13.4	4.8	0.1	0.4	-	0.2	4.8	1.0	-	2.5
Average Staple		37.48	36.54	36.46	36.54	-	36.53	35.75	35.50	-	37.23
Average Length		1.17	1.14	1.14	1.14	-	1.14	1.11	1.11	-	1.16

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Feb 13, 2020

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	31.1	2.6	4.7	0.9	4.5	1.5	88.2	3.8	-	7.1	10.9	3.3
Bark - Level 2	-	*	-	*	-	-	-	*	-	-	-	*
Grass - Level 1	1.9	0.1	*	0.1	-	*	-	*	-	0.1	0.5	0.1
Grass - Level 2	-	*	*	*	-	-	-	-	-	-	-	*
Prep - Level 1	-	*	0.1	*	-	*	-	*	-	*	0.2	*
Prep - Level 2	-	*	-	-	-	-	-	-	-	-	-	*
Seed Coat - Level 1	-	*	*	*	-	0.9	-	*	-	0.1	0.1	*
Seed Coat - Level 2	-	*	-	-	-	-	-	-	-	-	-	*
Oil - Level 1	-	*	-	*	-	*	-	-	-	-	-	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	*
Spindle Twist - Level 1	-	-	-	-	-	*	-	*	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	*	*	-	0.1	-	*	-	*	-	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	0.1	*	*	*	*	0.1	0.1	*	-	*	-	*
Plastic - Level 2	-	-	-	*	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	*	-	*	-	*	-	-	-	-	-	*
23	-	*	-	*	-	*	-	-	-	*	0.1	*
24	-	*	*	*	-	*	-	*	-	*	0.2	0.2
25	0.3	0.4	0.3	*	*	0.2	-	*	-	0.1	1.3	0.9
26	0.6	1.8	0.6	0.3	0.1	0.5	-	*	-	0.8	4.1	3.4
27	9.2	7.7	2.3	1.4	0.4	1.7	0.5	0.3	-	3.6	11.0	8.5
28	57.0	21.1	12.8	6.4	2.2	5.0	1.8	0.6	-	12.3	16.1	15.4
29	19.8	29.7	33.3	19.7	6.7	12.3	16.9	3.0	-	25.5	23.2	21.7
30	8.5	21.4	31.4	30.1	16.3	21.1	37.8	11.7	-	29.4	23.3	22.2
31	3.6	10.8	15.8	23.9	27.3	21.1	26.2	16.8	-	16.5	12.7	14.7
32	0.6	4.6	3.2	11.9	19.2	15.5	13.7	16.9	-	7.1	6.0	7.6
33	0.3	1.7	0.2	4.4	12.2	11.0	1.6	12.0	-	3.4	1.5	3.5
34	0.1	0.6	*	1.5	8.8	6.6	0.7	6.4	-	1.0	0.5	1.3
35	-	0.2	*	0.4	4.4	3.2	0.6	9.1	-	0.3	0.1	0.4
36	-	0.1	-	0.1	1.6	1.3	0.1	11.6	-	0.1	*	0.1
37	-	*	-	*	0.6	0.5	0.1	8.4	-	*	-	*
38	-	*	-	*	0.2	0.1	-	2.4	-	-	-	*
39	-	*	-	*	0.1	*	-	0.5	-	-	-	-
40 & Above	-	-	-	-	*	*	-	0.3	-	-	-	-
Average	28.86	29.69	29.97	30.76	32.09	31.54	30.88	33.52	-	30.27	29.63	29.96
Mike												
2.4 & Below	-	-	-	-	-	*	0.1	*	-	-	-	-
2.5	-	*	-	-	-	*	0.1	*	-	*	-	*
2.6	-	*	-	-	-	*	1.0	*	-	*	-	*
2.7	-	*	-	-	-	*	1.7	0.1	-	*	-	*
2.8	-	*	-	*	-	*	3.5	0.1	-	*	-	*
2.9	-	*	-	*	*	*	4.6	0.2	-	*	-	*
3.0	-	*	-	*	*	0.1	5.1	0.3	-	*	-	*
3.1	-	*	-	*	0.2	0.1	11.7	0.6	-	*	-	*
3.2	-	*	-	*	0.2	0.2	8.8	0.6	-	*	-	*
3.3	-	0.1	-	*	0.4	0.2	10.6	0.6	-	*	-	*
3.4	-	0.2	-	*	0.9	0.4	14.5	0.8	-	*	-	0.1
3.5	0.1	0.5	-	0.1	1.5	0.5	7.1	1.1	-	*	*	0.1
3.6	0.2	0.9	-	0.3	1.7	0.9	11.9	1.5	-	*	0.2	0.2
3.7	1.1	1.7	-	0.6	1.5	1.3	6.3	1.5	-	*	*	0.3
3.8	4.3	2.8	0.4	1.2	2.0	1.8	5.4	1.9	-	0.1	0.8	0.6
3.9	13.1	4.3	1.1	2.0	2.4	2.1	1.7	2.8	-	0.4	1.0	1.1
4.0	11.3	6.0	1.3	3.3	2.7	2.7	2.8	4.9	-	1.0	2.1	1.9
4.1	10.7	7.6	1.0	5.1	3.7	3.5	0.8	7.5	-	2.0	5.1	3.2
4.2	6.5	9.2	2.4	7.6	4.7	4.6	0.1	9.4	-	3.6	5.7	5.6
4.3	9.1	10.6	6.6	10.1	7.1	6.0	0.4	10.2	-	6.9	7.7	8.8
4.4	9.4	11.8	12.1	11.8	10.5	8.3	0.9	12.0	-	13.3	13.9	12.4
4.5	17.3	12.3	16.3	13.5	11.6	10.5	-	11.3	-	18.7	21.6	14.9
4.6	11.8	11.0	21.4	13.5	10.4	12.0	1.0	10.8	-	18.4	19.8	15.3
4.7	1.9	8.9	18.2	10.9	9.0	11.0	0.1	8.0	-	15.1	11.0	13.1
4.8	2.3	5.7	11.6	8.1	7.8	9.6	-	5.3	-	9.9	4.6	9.7
4.9	0.4	3.4	4.7	5.2	6.1	7.4	-	2.9	-	5.5	2.9	6.3
5.0	0.8	1.7	1.9	3.1	4.3	5.9	-	1.6	-	2.7	1.5	3.4
5.1	-	0.7	0.8	1.8	3.6	4.1	-	1.1	-	1.6	1.1	1.7
5.2	-	0.3	0.2	1.0	3.6	2.7	-	1.1	-	0.5	0.4	0.6
5.3	-	0.1	0.1	0.5	2.0	1.8	-	0.7	-	0.1	0.2	0.2
5.4	-	*	*	0.2	0.7	1.1	-	0.5	-	*	0.1	0.1
5.5 & Above	-	*	-	0.1	1.4	1.0	-	0.7	-	*	0.1	*
Average	4.26	4.38	4.58	4.50	4.53	4.57	3.38	4.37	-	4.57	4.50	4.54

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Feb 13, 2020

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	34.0	22.0	1.8	1.3	-	0.4	0.7	1.1	0.6	2.3	-	1.8
Bark - Level 2	-	-	-	-	-	-	-	*	-	-	-	*
Grass - Level 1	-	*	-	0.1	-	*	-	0.1	-	0.3	-	*
Grass - Level 2	-	-	-	-	-	-	-	*	-	-	-	-
Prep - Level 1	-	*	-	*	-	*	0.4	*	0.1	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	*	-	*	-	*	1.1	*	-	*	-	*
Seed Coat - Level 2	-	-	-	-	-	-	-	*	-	-	-	-
Oil - Level 1	-	-	0.1	*	-	*	-	*	-	*	-	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	*	-	*	-	*	-	*	-	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	-	*	-	*	0.1	*	-	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	*	-	-	-	-
STRENGTH 1/ 22 & Below	-	0.1	-	-	-	*	-	*	-	-	-	-
23	-	0.1	-	-	-	*	-	*	-	*	-	-
24	-	0.3	-	*	-	*	-	*	-	*	-	*
25	0.1	1.0	-	*	-	*	-	0.1	0.2	0.2	-	0.1
26	0.8	2.2	-	0.2	-	0.2	0.8	0.5	0.8	0.7	-	0.6
27	1.3	3.4	-	0.8	-	1.8	5.6	2.1	2.7	1.9	-	2.8
28	7.4	6.1	0.2	5.2	-	8.6	17.0	6.2	12.0	5.0	-	14.2
29	21.1	19.0	7.2	18.8	-	25.2	33.6	15.7	20.9	13.1	-	21.4
30	23.8	25.2	32.8	26.2	-	34.2	30.7	29.1	16.3	24.1	-	24.5
31	14.2	19.1	19.7	20.2	-	19.9	10.1	27.0	26.8	24.3	-	20.5
32	15.4	12.0	15.2	14.6	-	7.0	2.0	12.4	16.8	17.0	-	11.4
33	12.0	7.2	9.0	8.6	-	2.2	0.3	5.2	2.7	9.1	-	4.1
34	3.2	3.4	8.6	3.6	-	0.6	-	1.4	0.5	3.4	-	0.4
35	0.6	0.7	4.8	1.3	-	0.2	-	0.2	0.3	0.9	-	0.1
36	0.1	0.1	2.2	0.3	-	*	-	*	-	0.2	-	*
37	*	*	0.2	0.1	-	*	-	*	-	0.1	-	*
38	*	*	-	*	-	*	-	*	-	*	-	*
39	-	-	-	-	-	*	-	*	-	-	-	-
40 & Above	-	-	-	-	-	-	-	-	-	-	-	-
Average	31.00	30.70	31.87	31.11	-	30.41	29.71	30.83	30.60	31.18	-	30.42
Mike												
2.4 & Below	-	*	-	-	-	-	-	-	-	-	-	-
2.5	*	0.2	-	-	-	-	-	-	-	*	-	-
2.6	0.2	0.2	-	-	-	-	-	-	-	*	-	-
2.7	0.9	0.5	-	-	-	-	-	-	-	*	-	-
2.8	0.7	0.7	-	-	-	-	-	*	-	*	-	*
2.9	1.3	1.0	-	-	-	-	-	*	-	*	-	0.2
3.0	1.9	2.2	-	*	-	*	-	*	-	*	-	0.1
3.1	3.6	3.2	-	*	-	*	-	*	-	*	-	0.2
3.2	5.8	4.0	-	*	-	*	-	*	*	*	-	0.2
3.3	8.5	5.0	-	*	-	*	-	*	-	*	-	0.4
3.4	8.9	5.7	-	*	-	0.1	-	*	*	*	-	1.0
3.5	9.5	6.8	-	*	-	0.1	-	*	1.1	0.1	-	2.0
3.6	9.7	7.4	-	0.1	-	0.2	-	0.1	2.7	0.2	-	2.6
3.7	8.0	6.9	-	0.2	-	0.4	1.1	0.2	6.4	0.3	-	4.6
3.8	7.4	6.9	0.4	0.5	-	0.9	3.5	0.5	1.4	0.6	-	5.7
3.9	5.6	7.3	2.5	1.0	-	1.7	5.7	1.0	3.3	1.1	-	6.6
4.0	4.8	6.8	7.3	1.4	-	2.9	6.0	1.9	2.5	1.5	-	7.5
4.1	5.3	6.6	5.4	2.6	-	4.8	1.5	2.8	2.3	2.3	-	7.9
4.2	3.5	5.5	1.6	4.2	-	7.6	1.2	4.3	7.3	3.6	-	8.8
4.3	2.9	4.7	3.8	7.5	-	9.8	4.6	6.6	6.8	5.4	-	8.9
4.4	2.3	4.5	4.1	11.2	-	12.0	9.1	9.9	6.0	8.3	-	9.8
4.5	1.9	3.8	5.4	15.8	-	12.9	9.9	13.2	8.7	11.2	-	8.7
4.6	2.4	2.9	14.1	16.8	-	12.5	14.9	15.6	13.2	14.1	-	8.2
4.7	1.1	2.3	13.1	16.2	-	11.3	19.7	15.7	6.5	15.1	-	5.5
4.8	1.5	1.9	20.1	11.0	-	8.6	12.3	12.8	2.9	13.5	-	3.8
4.9	1.3	1.3	12.9	6.1	-	6.0	5.8	8.1	3.8	10.5	-	2.0
5.0	0.2	0.8	4.5	3.0	-	3.9	3.3	4.1	2.5	6.5	-	1.4
5.1	0.7	0.6	0.6	1.3	-	2.4	1.1	1.9	3.9	3.3	-	1.5
5.2	0.2	0.1	0.2	0.5	-	1.2	0.3	0.8	9.6	1.5	-	1.4
5.3	*	0.1	0.5	0.2	-	0.4	-	0.4	6.2	0.6	-	0.6
5.4	*	*	0.5	0.1	-	0.1	-	0.1	2.8	0.3	-	0.3
5.5 & Above	-	*	2.9	*	-	*	-	*	*	0.2	-	*
Average	3.72	3.86	4.63	4.57	-	4.52	4.51	4.59	4.55	4.64	-	4.26

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Feb 13, 2020

Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter										
Bark - Level 1	3.9	8.5	0.3	1.6	-	0.3	21.1	9.2	-	0.6
Bark - Level 2	-	-	-	-	-	-	-	*	-	-
Grass - Level 1	-	*	-	0.3	-	*	*	0.1	-	0.1
Grass - Level 2	-	-	-	-	-	-	-	*	-	-
Prep - Level 1	-	*	-	*	-	*	-	*	-	*
Prep - Level 2	-	-	-	-	-	-	-	*	-	-
Seed Coat - Level 1	-	*	-	*	-	*	*	0.1	-	*
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	-	-	*	-	*	-	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	-	*	*	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	-	*	-	*	*	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	*	-	*	-	*	*	*	-	-
23	-	*	0.1	*	-	*	*	0.1	-	*
24	-	0.1	0.7	0.1	-	*	0.1	0.4	-	*
25	-	0.2	1.8	0.5	-	0.1	0.4	1.0	-	0.1
26	*	0.6	4.7	2.0	-	0.5	1.4	2.4	-	0.6
27	0.5	1.9	8.7	5.1	-	4.3	3.8	5.4	-	2.2
28	2.9	4.5	17.6	11.8	-	18.7	8.4	10.3	-	4.7
29	7.5	9.2	29.2	24.4	-	31.1	13.6	16.0	-	13.7
30	10.8	14.8	18.3	25.7	-	24.3	18.7	20.0	-	26.4
31	13.0	17.7	11.7	16.3	-	12.2	15.8	18.2	-	25.2
32	15.5	16.2	5.4	8.1	-	5.7	14.4	12.9	-	16.6
33	15.4	13.3	1.4	3.7	-	2.3	11.8	7.4	-	7.1
34	13.2	9.8	0.3	1.5	-	0.6	7.0	3.6	-	2.3
35	9.6	6.2	-	0.5	-	0.2	3.3	1.5	-	0.8
36	6.3	3.5	-	0.1	-	*	1.1	0.6	-	0.2
37	3.8	1.6	*	*	-	*	0.2	0.2	-	*
38	1.5	0.5	-	*	-	*	*	0.1	-	-
39	*	*	-	-	-	*	*	*	-	-
40 & Above	-	-	-	-	-	-	*	*	-	-
Average	32.98	32.14	29.50	30.24	-	29.95	31.28	30.68	-	31.07
Mike										
2.4 & Below	-	*	-	*	-	-	*	*	-	-
2.5	-	*	-	*	-	-	0.1	0.1	-	-
2.6	-	*	-	*	-	-	0.2	0.1	-	-
2.7	-	*	-	*	-	-	0.2	0.1	-	-
2.8	-	*	-	*	-	*	0.3	0.2	-	-
2.9	-	0.1	-	*	-	*	0.5	0.3	-	-
3.0	-	0.1	-	*	-	*	0.8	0.4	-	-
3.1	*	0.2	-	*	-	*	1.1	0.5	-	-
3.2	0.1	0.2	-	*	-	*	1.5	0.7	-	*
3.3	0.1	0.3	-	*	-	*	1.8	0.9	-	*
3.4	0.4	0.5	-	*	-	0.1	2.2	1.2	-	*
3.5	1.1	0.9	-	0.1	-	0.2	2.6	1.5	-	*
3.6	2.0	1.5	0.4	0.2	-	0.4	3.4	1.9	-	*
3.7	3.0	2.2	1.3	0.3	-	0.7	5.0	2.4	-	0.1
3.8	4.1	3.2	1.7	0.5	-	1.0	5.0	3.1	-	0.1
3.9	5.7	4.0	1.2	0.8	-	1.8	6.7	3.7	-	0.3
4.0	8.4	5.1	1.0	1.5	-	2.7	6.8	4.5	-	0.6
4.1	9.5	6.0	1.9	2.9	-	3.8	7.4	5.5	-	1.2
4.2	8.6	7.1	4.7	5.2	-	5.6	7.4	6.6	-	2.3
4.3	8.6	8.0	11.3	8.4	-	8.2	7.8	7.7	-	4.1
4.4	9.2	9.1	12.1	11.3	-	11.1	6.8	8.9	-	7.1
4.5	8.6	9.7	13.3	13.8	-	13.5	6.6	9.4	-	11.6
4.6	7.1	9.6	14.7	14.9	-	14.3	6.8	9.4	-	16.1
4.7	9.1	9.1	14.8	14.1	-	12.9	5.3	9.0	-	17.8
4.8	6.4	7.6	12.6	11.3	-	10.2	4.3	7.7	-	15.7
4.9	5.0	5.9	4.3	7.3	-	6.7	3.6	5.8	-	10.8
5.0	2.2	4.3	3.6	3.9	-	3.8	2.5	4.0	-	6.6
5.1	0.6	2.7	0.6	1.7	-	1.9	1.9	2.4	-	3.1
5.2	0.1	1.5	0.2	0.8	-	0.7	0.9	1.2	-	1.3
5.3	*	0.7	*	0.5	-	0.2	0.4	0.6	-	0.6
5.4	*	0.2	-	0.3	-	*	0.2	0.2	-	0.3
5.5 & Above	*	0.1	-	0.1	-	*	*	0.1	-	0.1
Average	4.32	4.43	4.53	4.57	-	4.53	4.18	4.38	-	4.68

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Feb 13, 2020

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	-	-	-	-	*	0.1	*	-	-	-	-
2.5 - 2.6	-	*	-	-	-	*	1.0	*	-	*	-	*
2.7 - 2.9	-	*	-	*	*	0.1	9.7	0.4	-	*	-	*
3.0 - 3.2	-	0.1	-	*	0.4	0.4	25.6	1.5	-	*	-	*
3.3 - 3.4	-	0.3	-	0.1	1.3	0.6	25.1	1.3	-	*	-	0.1
3.5 - 3.6	0.2	1.3	-	0.4	3.1	1.4	19.0	2.6	-	0.1	0.3	0.4
3.7 - 4.2	46.8	31.7	6.2	19.8	16.9	16.0	17.1	28.0	-	7.2	14.8	12.8
4.3 - 4.9	52.1	63.7	90.8	73.1	62.6	64.9	2.4	60.6	-	87.8	81.6	80.5
5.0 - 5.2	0.8	2.8	2.9	5.9	11.5	12.7	-	3.8	-	4.8	3.0	5.8
5.3 & Above	-	0.2	0.1	0.7	4.1	3.9	-	1.8	-	0.1	0.4	0.4
Average	4.26	4.38	4.58	4.50	4.53	4.57	3.38	4.37	-	4.57	4.50	4.54
Leaf												
1 - 2	1.4	13.5	4.3	9.1	36.2	57.5	1.7	63.4	-	6.2	3.5	16.5
3	25.5	48.4	49.0	37.5	33.1	25.4	9.7	27.1	-	37.6	43.9	48.2
4	29.2	30.5	34.9	35.7	19.1	10.9	32.3	7.3	-	44.3	46.2	29.3
5	17.9	6.5	10.6	15.9	9.0	4.1	33.9	1.5	-	11.2	6.2	5.6
6	23.3	1.0	1.1	1.9	1.8	1.5	17.5	0.5	-	0.7	0.1	0.4
7	2.7	0.1	*	*	0.4	0.5	4.1	0.2	-	*	-	*
8	-	*	-	*	0.4	0.2	0.8	*	-	*	-	*
Average	4.44	3.33	3.55	3.64	3.02	2.50	4.71	2.29	-	3.62	3.55	3.24
HVI Trash 1/												
00	-	*	-	*	*	*	-	0.1	-	-	-	*
01	0.1	2.7	0.2	1.3	12.9	30.6	0.4	33.5	-	1.0	0.2	3.7
02	3.0	15.0	6.8	9.6	26.8	30.2	1.4	33.4	-	7.5	5.7	17.0
03	13.1	24.6	22.1	16.6	19.1	15.1	4.1	16.6	-	16.7	19.1	24.3
04	13.5	23.3	24.9	18.4	13.8	9.1	8.4	7.7	-	22.7	28.4	22.1
05	13.5	16.1	17.8	17.1	10.2	5.6	13.8	4.1	-	21.4	24.0	15.4
06	8.7	9.2	12.5	14.1	7.2	3.6	15.7	2.1	-	14.9	12.6	9.0
07	7.1	4.7	7.7	10.2	4.4	2.2	14.2	1.0	-	8.4	6.4	4.6
08	6.0	2.3	4.3	6.4	2.6	1.3	12.4	0.6	-	4.1	2.6	2.2
09	8.2	1.1	2.1	3.4	1.4	0.8	10.1	0.3	-	1.9	0.7	1.0
10	8.4	0.6	1.1	1.6	0.6	0.5	7.1	0.2	-	0.8	0.3	0.4
11	8.5	0.3	0.5	0.7	0.3	0.3	4.8	0.2	-	0.4	0.1	0.2
12	4.6	0.1	0.1	0.3	0.2	0.2	2.4	0.1	-	0.1	-	0.1
13	3.2	0.1	0.1	0.1	0.1	0.1	2.2	0.1	-	0.1	-	*
14	1.1	*	-	*	0.1	0.1	1.2	*	-	*	-	*
15	0.9	*	-	*	0.1	0.1	1.0	*	-	*	-	*
16	0.2	*	*	*	0.1	*	0.3	*	-	*	-	*
17	-	*	-	*	*	*	0.1	*	-	*	-	*
18 & Above	-	*	*	*	*	0.1	0.5	*	-	*	-	*
Average	0.70	0.41	0.47	0.50	0.36	0.27	0.73	0.24	-	0.48	0.45	0.40
UNIFORMITY 2/												
74 & Below	-	-	-	-	-	-	-	-	-	-	-	-
75	-	*	-	*	-	*	0.2	*	-	-	-	*
76	0.1	*	-	*	*	*	0.5	*	-	*	-	*
77	0.1	0.2	0.1	0.1	*	0.2	10.7	0.4	-	*	-	0.1
78	0.5	2.2	0.5	0.4	0.6	1.7	43.1	1.5	-	0.3	0.3	1.0
79	5.8	11.4	3.4	2.3	4.7	8.1	33.5	4.1	-	2.0	2.5	5.2
80	22.4	30.7	30.6	12.7	19.3	22.9	6.8	17.9	-	13.6	14.1	19.1
81	62.8	35.4	48.0	35.5	42.1	35.7	2.8	29.4	-	41.8	32.9	37.0
82	7.6	16.2	15.2	35.1	26.6	24.8	2.4	21.8	-	32.4	34.3	28.1
83	0.7	3.4	1.9	12.4	6.2	6.0	-	14.1	-	8.3	14.3	8.2
84	-	0.4	0.2	1.5	0.4	0.6	-	10.4	-	1.5	1.7	1.2
85 & Above	-	*	0.1	0.1	*	0.1	-	0.4	-	0.1	*	0.1
Average	81.14	81.08	81.25	81.91	81.56	81.39	78.94	81.96	-	81.81	81.93	81.61
Tenderable 3/	57.4	86.0	90.1	89.7	73.3	76.4	4.40	86.9	-	82.9	79.5	84.9
SAMPLES CLASSED	1,901	977,044	16,640	1,451,671	16,511	323,936	1,560	183,145	-	158,776	5,043	2,712,801

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Feb 13, 2020

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	*	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	0.2	0.4	-	-	-	-	-	-	-	*	-	-
2.7 - 2.9	2.9	2.2	-	-	-	-	-	*	-	*	-	0.2
3.0 - 3.2	11.3	9.3	-	*	-	*	-	*	*	*	-	0.5
3.3 - 3.4	17.3	10.7	-	*	-	0.1	-	*	*	*	-	1.4
3.5 - 3.6	19.1	14.2	-	0.2	-	0.4	-	0.1	3.8	0.2	-	4.6
3.7 - 4.2	34.6	40.1	17.1	9.9	-	18.4	19.0	10.7	23.2	9.4	-	41.2
4.3 - 4.9	13.4	21.4	73.5	84.7	-	73.1	76.2	81.7	47.9	78.0	-	46.9
5.0 - 5.2	1.2	1.5	5.4	4.9	-	7.5	4.7	6.9	16.0	11.3	-	4.3
5.3 & Above	*	0.1	4.0	0.3	-	0.5	-	0.5	9.0	1.1	-	0.9
Average	3.72	3.86	4.63	4.57	-	4.52	4.51	4.59	4.55	4.64	-	4.26
Leaf												
1 - 2	20.2	36.7	16.1	18.9	-	10.3	27.3	17.9	8.0	11.2	-	57.0
3	42.9	31.9	32.5	41.7	-	39.6	50.8	40.1	61.2	52.3	-	32.8
4	27.5	17.2	26.4	29.8	-	34.8	17.6	31.1	28.1	31.4	-	8.0
5	7.7	7.9	22.0	8.5	-	13.7	4.2	9.6	2.7	4.8	-	1.7
6	0.9	3.2	2.8	1.0	-	1.5	0.1	1.2	*	0.3	-	0.4
7	0.2	1.7	0.2	*	-	*	-	0.1	-	*	-	0.1
8	0.6	1.3	-	*	-	*	-	*	-	*	-	*
Average	3.29	3.15	3.60	3.30	-	3.56	2.95	3.35	3.26	3.30	-	2.42
HVI Trash 1/												
00	-	-	-	-	-	*	-	*	-	-	-	*
01	2.8	12.3	4.9	4.0	-	1.4	8.0	4.4	0.3	1.4	-	20.6
02	23.5	28.2	10.0	19.1	-	9.7	20.6	16.6	9.7	12.2	-	35.1
03	22.0	17.3	15.2	20.1	-	17.3	25.7	19.3	27.8	25.1	-	21.7
04	16.9	11.9	16.0	17.9	-	18.9	21.9	18.2	29.5	25.8	-	11.1
05	12.7	8.5	13.0	14.7	-	17.2	10.9	15.2	17.1	17.9	-	5.6
06	9.0	5.8	10.1	10.4	-	13.8	5.9	11.1	9.4	9.9	-	2.7
07	5.8	4.1	10.7	6.5	-	9.7	3.4	7.1	3.5	4.6	-	1.4
08	3.1	2.8	8.7	3.7	-	6.0	2.3	4.1	1.8	2.0	-	0.7
09	1.8	2.1	6.1	1.9	-	3.3	1.2	2.2	0.5	0.8	-	0.4
10	1.0	1.6	2.8	1.0	-	1.6	0.1	1.0	0.2	0.3	-	0.2
11	0.4	1.2	1.5	0.5	-	0.7	-	0.5	0.1	0.1	-	0.1
12	0.2	1.0	0.4	0.2	-	0.3	-	0.2	-	*	-	0.1
13	0.1	0.7	0.1	0.1	-	0.1	-	0.1	*	*	-	*
14	0.1	0.6	0.1	*	-	*	-	*	-	*	-	*
15	0.1	0.5	0.2	*	-	*	-	*	-	*	-	*
16	0.1	0.4	-	*	-	*	-	*	-	*	-	-
17	0.1	0.3	-	*	-	*	-	*	-	*	-	*
18 & Above	0.4	0.9	-	*	-	*	-	*	-	*	-	*
Average	0.41	0.41	0.52	0.42	-	0.49	0.36	0.43	0.41	0.41	-	0.27
UNIFORMITY 2/												
74 & Below	*	*	-	-	-	-	-	-	-	-	-	-
75	*	*	-	-	-	-	-	*	-	*	-	-
76	0.1	0.2	-	-	-	*	-	*	-	*	-	-
77	0.7	0.8	-	*	-	*	0.1	0.1	-	0.1	-	*
78	4.7	3.5	-	0.3	-	0.1	1.6	0.9	0.4	0.6	-	0.1
79	20.9	16.3	0.3	2.0	-	0.9	11.3	4.7	3.6	4.4	-	1.3
80	31.3	36.9	9.7	13.6	-	7.2	32.7	20.7	17.2	19.8	-	10.5
81	37.3	35.6	34.1	36.8	-	26.9	37.1	44.6	33.2	38.0	-	29.3
82	4.7	6.4	38.9	33.5	-	42.2	15.8	24.7	41.0	29.2	-	45.7
83	0.2	0.3	13.5	11.7	-	20.1	1.1	4.0	4.2	6.9	-	12.6
84	*	*	3.4	1.9	-	2.4	0.1	0.4	0.4	0.8	-	0.4
85 & Above	-	*	0.2	0.3	-	0.2	-	*	-	0.1	-	*
Average	80.59	80.68	82.12	81.90	-	82.26	81.04	81.46	81.71	81.60	-	82.03
Tenderable 3/	35.7	53.1	81.5	89.3	-	89.5	65.8	88.4	60.2	83.4	-	85.2
SAMPLES CLASSED	17,218	209,336	951	581,693	-	827,340	972	1,536,875	2,772	1,060,770	-	31,678

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Feb 13, 2020

Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE										
2.4 & Below	-	*	-	*	-	-	*	*	-	-
2.5 - 2.6	-	*	-	*	-	-	0.2	0.2	-	-
2.7 - 2.9	-	0.1	-	*	-	*	1.0	0.6	-	-
3.0 - 3.2	0.1	0.5	-	*	-	0.1	3.4	1.5	-	*
3.3 - 3.4	0.5	0.9	-	*	-	0.1	4.0	2.1	-	*
3.5 - 3.6	3.1	2.4	0.4	0.2	-	0.6	6.0	3.4	-	*
3.7 - 4.2	39.4	27.7	11.9	11.1	-	15.5	38.2	25.8	-	4.6
4.3 - 4.9	54.0	59.0	83.2	81.1	-	77.1	41.2	57.8	-	83.3
5.0 - 5.2	2.9	8.5	4.4	6.4	-	6.4	5.2	7.6	-	11.1
5.3 & Above	*	0.9	*	1.0	-	0.2	0.6	0.9	-	1.0
Average	4.32	4.43	4.53	4.57	-	4.53	4.18	4.38	-	4.68
Leaf										
1 - 2	53.0	51.4	17.7	14.2	-	14.3	23.7	44.9	-	24.0
3	30.0	32.8	51.1	56.9	-	44.1	48.5	39.0	-	60.8
4	13.5	10.8	29.0	26.0	-	30.9	21.4	12.6	-	14.2
5	2.6	3.4	2.2	2.7	-	9.5	5.2	2.7	-	0.9
6	0.7	1.1	*	0.1	-	1.2	1.0	0.6	-	*
7	0.2	0.4	-	*	-	*	0.2	0.2	-	*
8	0.1	0.2	-	*	-	*	0.1	*	-	*
Average	2.56	2.58	3.16	3.17	-	3.39	3.11	2.67	-	2.91
HVI Trash 1/										
00	-	*	-	*	-	*	-	*	-	-
01	22.7	23.1	1.0	1.6	-	2.3	3.8	16.9	-	3.0
02	33.6	31.8	16.3	15.4	-	13.3	23.7	32.0	-	23.1
03	19.3	19.8	23.9	28.6	-	20.8	26.8	22.9	-	33.2
04	11.6	10.7	26.6	25.6	-	20.2	19.6	13.4	-	23.1
05	6.6	5.9	17.3	15.6	-	16.2	12.1	7.2	-	11.0
06	2.5	3.4	8.9	7.7	-	11.4	6.6	3.7	-	4.3
07	1.5	2.0	3.8	3.3	-	7.3	3.6	1.8	-	1.5
08	0.7	1.2	1.6	1.3	-	4.2	2.0	0.9	-	0.5
09	0.5	0.7	0.6	0.5	-	2.2	0.8	0.5	-	0.2
10	0.2	0.5	-	0.2	-	1.1	0.5	0.3	-	0.1
11	0.2	0.3	*	0.1	-	0.6	0.3	0.2	-	*
12	0.2	0.2	-	*	-	0.3	0.1	0.1	-	*
13	0.1	0.1	*	*	-	0.1	0.1	*	-	*
14	0.1	0.1	-	*	-	*	*	*	-	*
15	*	0.1	-	*	-	*	*	*	-	*
16	*	*	-	*	-	*	*	*	-	*
17	*	*	-	*	-	*	*	*	-	-
18 & Above	*	0.1	-	*	-	*	*	*	-	-
Average	0.27	0.29	0.40	0.39	-	0.45	0.37	0.29	-	0.34
UNIFORMITY 2/										
74 & Below	-	*	-	-	-	-	*	*	-	-
75	*	*	-	*	-	-	0.1	0.1	-	*
76	0.2	0.2	-	*	-	*	0.8	0.6	-	*
77	1.1	1.0	0.1	0.2	-	0.1	3.6	2.7	-	0.1
78	5.0	3.8	1.3	1.4	-	0.5	10.4	8.3	-	0.2
79	12.9	12.4	4.6	7.7	-	5.1	20.6	19.7	-	1.3
80	25.9	28.3	18.7	30.5	-	22.4	30.8	30.3	-	9.2
81	29.5	33.2	42.8	40.3	-	36.5	23.8	25.5	-	36.1
82	19.0	16.8	26.5	16.4	-	26.9	7.9	10.6	-	39.1
83	5.7	3.7	5.5	3.1	-	7.8	1.8	1.9	-	11.9
84	0.7	0.5	0.4	0.3	-	0.7	0.2	0.2	-	1.9
85 & Above	*	0.1	*	*	-	0.1	-	*	-	0.2
Average	81.06	81.02	81.50	81.17	-	81.55	80.35	80.51	-	82.02
Tenderable 3/	90.0	77.8	81.2	87.5	-	89.4	48.4	66.0	-	86.1
SAMPLES CLASSED	10,827	503,174	2,025	420,919	-	938,993	26,201	6,305,469	-	229,678

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Feb 13, 2020

Color Grade	Leaf	Arizona		California		New Mexico		Texas	
		Week	Season	Week	Season	Week	Season	Week	Season
01	1	-	53.4	30.4	28.1	-	-	-	11.5
	2	-	7.4	12.5	8.6	-	-	-	15.5
	3	-	1.0	*	*	-	-	-	0.3
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	61.9	43.0	36.8	-	-	-	27.4
02	1	-	20.7	17.4	29.1	-	-	-	14.7
	2	-	11.8	37.8	31.0	-	-	-	43.7
	3	-	2.9	1.1	0.9	-	-	-	5.2
	4	-	0.8	-	*	-	-	-	0.1
	5	-	*	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	36.2	56.3	61.0	-	-	-	63.6
03	1	-	0.2	0.1	0.3	-	-	-	1.0
	2	-	0.8	0.5	1.4	-	-	-	5.2
	3	-	0.7	0.1	0.4	-	-	-	1.8
	4	-	0.1	*	*	-	-	-	0.1
	5	-	*	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	1.8	0.7	2.1	-	-	-	8.2
04	1	-	*	*	*	-	-	-	-
	2	-	*	*	0.1	-	-	-	0.2
	3	-	0.1	*	*	-	-	-	0.4
	4	-	*	*	*	-	-	-	0.1
	5	-	-	-	*	-	-	-	*
	6	-	-	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-
Total -----		-	0.1	*	0.1	-	-	-	0.7
05	1	-	-	-	-	-	-	-	-
	2	-	-	-	*	-	-	-	*
	3	-	*	-	*	-	-	-	0.1
	4	-	*	-	*	-	-	-	*
	5	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	*	-	-	-	-
Total -----		-	*	-	*	-	-	-	0.1
06	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	-	*	-	-	-	-
07	1	-	-	-	-	-	-	-	-
	2	-	-	-	*	-	-	-	-
	3	-	-	-	*	-	-	-	-
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	-	*	-	-	-	-
STAPLE									
44 & Shorter		-	0.5	*	0.6	-	-	-	0.9
46		-	11.9	10.4	6.5	-	-	-	10.2
48		-	65.0	28.4	24.8	-	-	-	62.0
50		-	22.4	58.9	63.7	-	-	-	20.7
52 & Longer		-	0.1	2.3	4.3	-	-	-	6.1
Average Staple		-	48.19	49.06	49.29	-	-	-	48.42
Average Length		-	1.40	1.42	1.43	-	-	-	1.41
EXTRANEIOUS MATTER									
Bark		-	*	-	*	-	-	-	1.2
Grass		-	-	*	0.1	-	-	-	0.8
Spindle Twist		-	*	*	0.2	-	-	-	0.2
Preparation		-	-	-	*	-	-	-	-
All Other		-	0.1	*	*	-	-	-	0.1

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Feb 13, 2020

Quality Designation	Arizona		California		New Mexico		Texas	
	Week	Season	Week	Season	Week	Season	Week	Season
MIKE								
2.4 & Below	-	-	-	*	-	-	-	-
2.5 - 2.6	-	-	-	*	-	-	-	-
2.7 - 2.9	-	*	0.2	0.1	-	-	-	*
3.0 - 3.2	-	1.3	0.4	0.5	-	-	-	1.2
3.3 - 3.4	-	8.9	0.1	0.9	-	-	-	2.0
3.5 - 3.6	-	18.8	1.8	2.3	-	-	-	6.6
3.7 - 4.2	-	67.4	40.7	58.0	-	-	-	72.8
4.3 - 4.9	-	3.6	56.8	38.0	-	-	-	17.4
5.0 - 5.2	-	-	0.1	*	-	-	-	-
5.3 & Above	-	-	*	*	-	-	-	-
Average	-	3.79	4.24	4.14	-	-	-	3.97
ALL RANGE MIKE								
2.4 & Below	-	-	-	*	-	-	-	-
2.5	-	-	-	*	-	-	-	-
2.6	-	-	-	*	-	-	-	-
2.7	-	-	*	*	-	-	-	-
2.8	-	-	*	*	-	-	-	-
2.9	-	*	0.1	0.1	-	-	-	*
3.0	-	*	0.2	0.1	-	-	-	*
3.1	-	0.5	0.1	0.2	-	-	-	0.4
3.2	-	0.8	0.1	0.2	-	-	-	0.8
3.3	-	3.0	*	0.3	-	-	-	0.8
3.4	-	5.9	*	0.6	-	-	-	1.2
3.5	-	7.5	0.3	0.8	-	-	-	2.0
3.6	-	11.4	1.5	1.5	-	-	-	4.6
3.7	-	12.5	4.0	2.9	-	-	-	9.9
3.8	-	15.6	4.2	5.8	-	-	-	15.6
3.9	-	16.9	5.5	9.1	-	-	-	14.1
4.0	-	10.5	8.0	12.0	-	-	-	13.2
4.1	-	8.3	9.7	13.6	-	-	-	11.8
4.2	-	3.7	9.3	14.7	-	-	-	8.2
4.3	-	2.6	13.9	14.9	-	-	-	7.6
4.4	-	0.6	16.1	12.5	-	-	-	6.1
4.5	-	0.3	17.4	7.0	-	-	-	3.0
4.6	-	*	7.0	2.6	-	-	-	0.7
4.7	-	-	1.9	0.8	-	-	-	*
4.8	-	-	0.4	0.2	-	-	-	*
4.9	-	-	0.1	*	-	-	-	*
5.0	-	-	*	*	-	-	-	-
5.1	-	-	*	*	-	-	-	-
5.2	-	-	*	*	-	-	-	-
5.3 & Above	-	-	*	*	-	-	-	-
Average	-	3.79	4.24	4.14	-	-	-	3.97
STRENGTH 1/ 36 & Below	-	*	0.5	0.1	-	-	-	0.2
37	-	*	1.3	0.3	-	-	-	1.5
38	-	0.1	7.1	1.4	-	-	-	1.4
39	-	0.5	6.4	3.3	-	-	-	2.0
40	-	2.1	3.8	3.3	-	-	-	2.5
41	-	7.8	8.6	2.9	-	-	-	9.9
42	-	15.8	13.6	5.0	-	-	-	13.3
43	-	26.9	19.8	10.3	-	-	-	16.6
44	-	25.4	19.1	18.5	-	-	-	21.5
45	-	14.9	13.5	25.1	-	-	-	17.8
46	-	4.9	5.0	18.3	-	-	-	10.1
47	-	0.9	1.0	8.2	-	-	-	2.4
48 & Above	-	0.5	0.3	3.2	-	-	-	0.8
Average	-	43.82	42.97	44.75	-	-	-	43.79
UNIFORMITY								
83 & Below	-	0.9	0.3	0.4	-	-	-	0.7
84	-	8.4	5.0	4.8	-	-	-	3.0
85	-	39.4	19.9	15.4	-	-	-	22.4
86	-	48.1	51.7	54.3	-	-	-	62.0
87	-	3.1	20.9	23.5	-	-	-	11.6
88 & Above	-	0.1	2.3	1.7	-	-	-	0.4
Average	-	85.89	86.41	86.46	-	-	-	86.27
Samples Classed	-	12,610	21,567	575,425	-	-	-	15,020

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.