



Volume 20, No.22

State	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
AL	25	62.7	49.5	33,738	29	63.9	52.8	652,208
AR	10	79.2	56.8	22,806	28	71.4	52.4	1,141,954
AZ	14	72.0	47.4	24,807	14	73.6	50.2	183,773
CA	6	90.0	82.3	6,727	15	90.7	76.0	127,984
FL	3	56.5	50.4	2,259	4	61.7	51.1	61,000
GA	59	61.3	49.0	71,287	59	78.6	64.9	1,454,551
KS	3	40.6	35.7	4,390	3	52.7	42.8	44,441
LA	9	32.5	11.3	2,870	19	56.9	31.8	396,917
MO	12	69.9	47.2	22,834	21	68.6	48.5	734,844
MS	30	66.0	42.4	31,238	38	76.2	48.8	1,257,282
NC	21	78.7	62.5	16,435	33	76.2	58.2	666,870
NM	2	75.6	63.6	2,893	2	90.0	77.3	21,015
OK	12	83.8	71.4	26,156	12	83.5	70.8	252,088
SC	13	72.2	48.4	7,476	16	80.4	66.3	284,628
TN	13	54.8	27.2	10,983	22	46.5	28.5	755,502
TX	144	68.5	53.2	315,590	188	67.1	49.8	4,784,819
VA	4	81.2	48.4	3,295	4	81.5	56.1	167,206
United States	380	68.4	52.1	605,784	507	69.6	51.5	12,987,082
AMERICAN PIMA								
AZ	2			768	4			15,574
CA	15			28,155	17			423,745
NM*	-			-	-			-
TX*	-			-	-			-
United States	19			31,812	23			463,388
United States all cotton	397			637,596	521			13,450,470

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 27 2018

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	*	0.3	-	0.2	8.1	12.0	42.0	57.7	-	-	0.1	1.1
	3	0.1	0.5	-	0.2	2.8	4.5	12.4	11.9	-	*	0.1	2.2
	4	*	*	-	*	0.1	0.3	0.3	0.1	-	-	*	0.2
	5	-	*	-	-	-	*	-	*	-	-	-	*
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.1	0.8	-	0.4	10.9	16.9	54.6	69.7	-	*	0.1	3.5
31	1 - 2	0.9	1.6	*	0.5	14.3	11.3	14.1	10.2	2.0	0.3	0.7	3.6
	3	6.1	13.3	1.0	4.4	17.3	13.3	23.4	13.2	16.2	5.7	4.5	23.7
	4	4.0	6.8	1.3	3.1	4.6	2.5	5.2	2.0	2.9	3.3	2.0	11.6
	5	0.4	0.5	0.1	0.4	0.5	0.2	0.6	0.2	*	0.1	0.1	0.7
	6	*	*	-	*	*	*	0.1	*	-	-	-	*
	7	-	-	-	-	-	*	*	*	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	11.5	22.1	2.5	8.4	36.8	27.3	43.4	25.7	21.2	9.4	7.3	39.7
41	1 - 2	0.9	1.0	0.3	0.6	5.2	6.5	0.2	0.1	0.6	0.5	2.7	1.2
	3	14.5	15.6	12.6	15.6	21.2	21.1	0.3	0.3	13.9	16.8	24.4	16.3
	4	28.9	23.3	37.5	30.5	11.8	9.9	0.1	0.1	16.9	34.2	25.5	20.1
	5	10.8	7.8	13.0	11.1	2.4	1.7	0.1	*	1.7	6.4	5.3	4.0
	6	1.2	1.0	0.4	1.0	0.5	0.2	*	*	-	0.2	0.3	0.2
	7	0.1	*	*	*	0.1	*	-	*	-	-	*	*
	8	-	-	-	*	-	-	-	-	-	-	-	*
Total	----	56.4	48.7	63.7	58.8	41.1	39.4	0.8	0.6	33.1	58.0	58.2	41.8
51	1 - 2	0.3	*	*	0.1	0.1	0.2	-	-	-	*	0.2	*
	3	1.5	0.6	1.2	1.7	1.6	2.0	-	*	3.2	1.6	2.7	0.7
	4	3.8	1.5	10.2	6.3	1.6	2.2	-	-	11.2	5.9	4.9	1.6
	5	3.2	1.5	11.7	5.3	0.5	0.7	-	-	2.8	3.5	2.6	0.8
	6	0.7	0.6	1.6	0.8	0.2	0.1	-	-	-	0.3	0.5	0.1
	7	0.1	0.1	0.1	*	*	*	-	-	-	*	*	*
	8	*	*	*	*	-	*	-	-	-	*	-	*
Total	----	9.5	4.3	24.9	14.1	4.0	5.2	-	*	17.2	11.4	10.9	3.2
61	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	*	-	-	-	*	-	-	-	*	-	*
	4	-	*	-	*	-	-	-	-	-	*	*	*
	5	-	*	-	*	-	-	-	-	-	*	-	*
	6	-	*	-	*	-	-	-	-	-	-	-	*
	7	-	*	-	*	-	-	-	-	-	*	*	*
	8	-	*	-	-	-	*	-	-	-	*	-	-
Total	----	-	*	-	*	-	*	-	-	-	0.1	*	*
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	*
	4	*	*	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	*
Total	----	*	*	-	-	-	-	-	-	-	-	-	*
12 & 22	1 - 2	*	*	-	*	*	1.8	0.1	0.6	-	*	*	0.1
	3	-	*	-	*	*	0.9	0.3	0.5	-	-	0.1	0.1
	4	*	*	-	*	-	0.3	*	*	-	-	*	*
	5	-	-	-	-	-	*	-	-	-	-	-	*
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	-	*	*	3.0	0.4	1.2	-	*	0.1	0.1
32	1 - 2	0.1	0.1	-	*	0.1	0.2	0.1	0.5	-	*	0.1	0.3
	3	1.6	1.6	*	0.3	0.5	1.0	0.4	1.8	0.8	0.2	1.0	2.1
	4	1.1	1.3	*	0.2	0.3	0.4	0.1	0.3	0.3	0.2	0.6	1.1
	5	0.2	0.2	*	*	*	0.2	-	*	-	*	*	0.1
	6	*	*	-	*	-	*	-	-	-	*	*	*
	7	-	*	-	-	-	*	-	-	-	-	-	-
	8	-	-	-	-	-	*	-	-	-	-	-	-
Total	----	2.9	3.3	0.1	0.6	0.9	1.8	0.6	2.6	1.1	0.4	1.7	3.5
42	1 - 2	0.1	0.2	*	0.1	0.1	0.2	-	*	*	0.1	0.3	0.1
	3	3.0	4.5	0.8	3.9	1.6	1.6	*	0.1	2.6	2.6	4.9	1.9
	4	5.8	8.1	2.7	7.4	1.8	1.8	0.1	*	5.2	4.7	6.8	3.0
	5	2.5	2.9	1.5	2.2	0.7	0.5	0.1	*	0.8	1.3	1.6	0.8
	6	0.6	0.4	0.1	0.2	0.2	0.1	-	*	-	0.1	0.1	*
	7	*	*	*	*	0.1	*	-	-	-	-	*	*
	8	-	*	-	-	-	*	-	-	-	-	-	-
Total	----	12.1	16.1	5.1	13.7	4.4	4.2	0.2	0.1	8.6	8.7	13.6	5.7

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 27 2018

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	*	*	*	*	*	*	-	*	-	*	*	*
	3	0.7	0.3	0.1	0.3	0.1	0.2	-	-	1.5	1.2	0.5	0.1
	4	1.2	0.9	0.7	1.3	0.2	0.7	-	-	10.5	5.2	1.5	0.4
	5	1.1	0.7	1.0	1.1	0.4	0.3	-	-	4.6	3.0	0.9	0.2
	6	0.4	0.2	0.4	0.2	0.2	0.1	-	-	0.2	0.4	0.4	0.1
	7	*	*	0.2	*	0.1	*	-	-	-	*	*	*
	8	-	*	0.1	*	-	*	-	-	-	*	-	*
Total	----	3.4	2.1	2.4	2.9	1.1	1.3	-	*	16.8	9.9	3.3	0.8
62	1 - 2	-	-	-	-	-	*	-	-	-	-	-	-
	3	*	*	-	*	-	*	-	-	-	*	-	*
	4	*	*	-	*	*	*	-	-	0.1	0.1	*	*
	5	*	*	-	*	-	*	-	-	0.3	0.1	*	*
	6	*	*	-	*	-	-	-	-	-	*	*	*
	7	-	*	-	-	-	-	-	-	-	-	-	*
	8	-	*	-	-	-	*	-	-	-	-	-	-
Total	----	*	*	-	*	*	*	-	-	0.4	0.2	*	*
13 & 23	1 - 2	-	*	-	*	*	0.1	-	*	-	-	-	*
	3	*	*	-	*	*	0.1	-	*	-	-	*	*
	4	-	-	-	*	-	*	-	-	-	-	-	*
	5	-	-	-	-	-	*	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	-	*	*	0.2	-	*	-	-	*	*
33	1 - 2	*	*	-	-	-	*	-	*	-	*	*	0.1
	3	0.2	0.1	-	*	-	*	-	*	-	*	0.2	0.3
	4	0.3	0.1	*	*	*	0.1	-	*	-	*	0.1	0.1
	5	*	*	-	*	*	0.1	*	*	-	-	*	*
	6	*	*	-	-	-	*	-	-	-	-	-	*
	7	-	*	-	-	-	*	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.5	0.2	*	*	*	0.2	*	*	-	*	0.3	0.5
43	1 - 2	*	*	-	*	-	-	-	-	-	*	*	*
	3	0.4	0.3	0.1	0.2	-	*	-	*	0.1	0.3	1.0	0.3
	4	0.9	0.8	0.5	0.5	0.1	0.1	-	*	0.6	0.5	1.5	0.4
	5	0.6	0.4	0.2	0.2	0.2	0.1	-	-	0.3	0.1	0.6	0.1
	6	0.2	0.1	*	*	0.2	0.1	-	-	-	*	*	*
	7	*	*	-	*	0.1	*	-	-	-	-	*	*
	8	-	-	-	-	-	*	-	-	-	-	-	-
Total	----	2.1	1.6	0.8	0.8	0.6	0.3	-	*	0.9	0.9	3.2	0.9
53	1 - 2	*	*	-	*	-	-	-	-	-	-	-	*
	3	0.1	0.1	*	*	-	*	-	*	0.1	0.1	0.1	*
	4	0.3	0.2	0.1	0.1	-	*	-	-	0.1	0.4	0.3	0.1
	5	0.2	0.1	0.1	0.1	*	*	-	-	0.2	0.4	0.3	*
	6	0.1	*	*	*	*	*	-	-	*	0.1	0.1	*
	7	*	*	*	*	-	*	-	-	-	*	*	*
	8	*	*	*	*	-	*	-	-	-	-	*	*
Total	----	0.8	0.4	0.3	0.3	*	*	-	*	0.5	0.9	0.7	0.1
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	*	*	*	-	-	-	-	-	*	*	*
	4	*	*	-	*	-	-	-	-	-	*	*	*
	5	*	*	-	*	-	-	-	-	-	*	*	*
	6	*	*	*	*	-	-	-	-	-	-	-	*
	7	-	*	-	-	-	-	-	-	-	-	-	*
	8	-	*	*	*	-	-	-	-	-	-	-	-
Total	----	*	*	*	*	-	-	-	-	-	*	*	*
24 - 54	1 - 8	0.4	0.1	*	*	*	0.1	-	*	0.1	*	0.5	0.1
25 - 35	1 - 8	-	*	-	*	-	-	-	-	-	-	-	*
81 - 85	1 - 8	0.1	*	*	*	*	*	-	-	-	*	*	*
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	*	-	-	-	-	-	-	-	-	*	*
31		-	*	-	-	-	-	-	*	-	-	*	*
32		*	*	-	*	*	*	-	*	-	*	0.1	0.1
33		0.6	0.5	0.1	*	0.3	0.2	-	0.1	-	0.1	1.9	1.1
34		3.2	3.1	*	0.4	3.1	2.4	-	0.1	3.5	0.9	8.6	5.7
35		12.5	10.8	0.8	2.9	8.0	8.2	0.8	2.1	1.5	3.3	15.7	14.0
36		26.6	21.7	6.7	11.7	15.2	19.2	7.0	7.5	12.8	12.2	18.2	18.7
37		40.2	37.3	35.6	36.8	28.0	30.1	27.0	25.5	33.3	35.4	28.2	28.7
38		13.2	20.0	31.3	26.8	20.7	18.1	23.3	24.2	38.5	33.5	19.8	22.4
39		3.1	5.8	17.6	15.5	13.2	13.1	20.0	21.4	10.2	14.3	6.6	8.3
40 & Longer		0.5	0.7	7.9	5.8	11.4	8.7	21.9	19.1	0.2	0.3	1.1	1.1
Average Staple		36.57	36.79	37.82	37.57	37.45	37.30	38.23	38.15	37.34	37.41	36.53	36.74
Average Length		1.14	1.15	1.18	1.17	1.17	1.16	1.19	1.19	1.17	1.17	1.14	1.15

1/ Below Grade Color. 2/ Below Grade Leaf. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE													
For The Week Ending Dec 27 2018													
Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	3.0	2.7	-	0.7	-	0.7	*	0.5	0.5	0.1	16.1	14.0
	3	0.8	3.3	-	1.2	-	0.7	0.1	0.9	0.5	0.2	8.7	6.2
	4	0.1	0.2	-	0.1	-	*	*	0.1	*	*	0.3	0.1
	5	-	*	-	*	-	*	-	*	-	*	0.1	*
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	4.0	6.2	-	1.9	-	1.5	0.1	1.4	1.0	0.3	25.3	20.3
31	1 - 2	3.2	6.8	0.5	2.9	0.5	0.8	0.6	1.9	1.9	1.7	9.1	18.1
	3	11.6	21.1	4.7	16.6	6.5	6.6	9.1	14.3	8.3	13.8	16.9	23.5
	4	6.0	7.3	1.0	6.7	0.6	3.1	4.5	7.2	5.0	7.4	7.8	3.5
	5	0.5	1.0	-	0.4	0.1	0.3	0.2	0.5	0.9	0.8	3.0	0.5
	6	-	*	-	*	-	*	-	*	*	*	0.8	0.1
	7	-	-	-	-	-	-	-	-	-	-	*	*
	8	-	-	-	-	-	-	-	-	-	*	-	-
Total	----	21.4	36.2	6.2	26.6	7.7	10.9	14.4	23.8	16.1	23.7	37.6	45.7
41	1 - 2	-	0.6	1.8	1.8	1.2	0.8	1.7	1.2	1.7	1.6	2.6	2.4
	3	2.0	6.4	22.5	18.4	34.6	21.4	21.3	16.9	24.7	23.9	16.8	17.4
	4	12.0	12.5	24.9	19.6	31.5	33.9	30.0	30.9	29.6	24.2	10.3	9.7
	5	17.2	7.6	1.6	4.4	3.9	8.8	7.1	10.1	8.0	5.3	2.1	2.5
	6	2.9	1.4	-	0.3	0.1	0.4	0.3	0.7	1.0	0.4	2.9	0.6
	7	0.1	0.1	-	*	-	*	-	*	0.1	*	1.4	0.2
	8	-	-	-	-	-	-	-	*	-	*	-	-
Total	----	34.2	28.5	50.8	44.5	71.3	65.3	60.3	59.8	65.0	55.4	36.1	32.8
51	1 - 2	-	-	*	0.2	*	*	*	*	0.2	0.1	-	-
	3	0.1	*	2.3	1.5	1.7	0.7	1.4	0.4	2.6	1.4	*	*
	4	3.4	1.2	5.7	1.7	5.1	3.8	3.3	1.6	3.0	2.0	0.1	0.3
	5	7.3	1.9	1.3	0.6	1.6	2.9	2.0	1.6	1.0	1.0	0.1	0.2
	6	7.2	1.1	*	0.1	0.1	0.3	0.4	0.3	0.1	0.2	0.1	*
	7	3.8	0.4	-	*	*	*	*	*	*	*	0.1	*
	8	1.1	0.1	-	*	-	-	-	*	-	*	-	-
Total	----	22.9	4.8	9.4	4.1	8.5	7.8	7.1	3.9	7.0	4.6	0.4	0.5
61	1 - 2	-	-	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	*	-	*	-	*	-	*	-	-
	4	-	-	-	*	-	*	-	*	-	*	-	-
	5	-	-	-	*	*	*	-	*	-	*	-	-
	6	-	-	-	*	-	*	-	*	-	-	-	-
	7	*	*	-	-	-	*	-	*	-	*	-	-
	8	*	*	-	*	-	-	-	-	-	-	-	-
Total	----	0.1	*	-	*	*	*	-	*	-	*	-	-
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	-	-	-	-	-
12 & 22	1 - 2	-	0.2	-	*	-	*	-	*	-	*	-	*
	3	0.1	0.8	-	*	-	*	*	*	*	*	-	*
	4	0.1	0.4	-	*	-	*	*	*	*	*	-	-
	5	-	*	-	-	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.2	1.4	-	0.1	-	*	*	*	*	*	-	*
32	1 - 2	*	0.2	0.1	0.2	*	*	*	0.1	0.1	0.1	-	-
	3	0.2	1.5	1.1	1.2	0.7	0.4	0.7	0.5	0.7	0.8	-	*
	4	0.4	2.3	0.5	0.6	0.1	0.2	1.1	0.5	0.3	0.5	-	0.1
	5	*	0.8	-	*	*	*	0.2	0.1	0.1	*	0.1	*
	6	*	*	-	*	-	-	-	*	*	*	0.1	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.6	4.9	1.7	2.1	0.8	0.7	2.0	1.0	1.2	1.5	0.2	0.1
42	1 - 2	-	-	0.6	0.4	*	0.1	0.1	0.1	0.4	0.4	-	*
	3	0.1	*	6.6	4.5	2.6	3.6	1.9	1.4	2.6	4.9	-	0.2
	4	2.1	1.1	2.7	5.6	5.4	6.3	4.9	3.6	2.8	4.4	-	0.1
	5	5.3	1.6	0.3	1.3	0.7	1.6	2.6	2.0	0.8	0.8	0.2	*
	6	1.5	0.4	-	*	*	0.1	0.3	0.2	0.1	0.1	0.1	*
	7	0.1	*	-	*	-	-	*	*	*	*	-	-
	8	-	*	-	-	-	-	-	-	-	*	-	-
Total	----	9.0	3.1	10.1	11.8	8.8	11.8	9.8	7.3	6.6	10.5	0.3	0.4

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 27 2018

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	0.3	0.2	-	*	-	*	-	0.1	-	-
	3	-	-	3.7	1.6	0.1	0.1	0.4	0.1	0.2	0.9	-	*
	4	0.6	0.5	7.8	2.4	0.5	0.7	1.2	0.5	0.4	1.2	-	-
	5	3.7	1.5	3.2	0.9	0.2	0.6	1.0	0.8	0.3	0.4	-	-
	6	2.1	0.5	0.1	0.1	*	0.1	0.2	0.2	*	0.1	-	-
	7	0.3	*	-	*	-	*	*	*	-	*	0.1	*
	8	0.3	*	-	-	-	*	-	-	-	*	-	-
Total	----	6.9	2.5	15.2	5.2	0.8	1.5	2.9	1.6	0.9	2.8	0.1	*
62	1 - 2	-	-	-	*	-	-	-	*	-	*	-	-
	3	-	-	0.1	*	-	*	-	*	-	*	-	-
	4	-	-	0.1	*	-	*	-	*	-	*	-	-
	5	-	-	-	*	*	*	*	*	-	*	-	-
	6	*	*	-	*	-	-	*	*	-	*	-	-
	7	-	-	-	*	-	-	-	*	-	-	-	-
	8	*	*	-	-	-	*	-	-	-	*	-	-
Total	----	*	*	0.2	0.1	*	*	*	*	-	0.1	-	-
13 & 23	1 - 2	-	*	-	*	-	*	-	-	-	*	-	*
	3	-	0.7	-	-	-	-	-	-	-	*	-	*
	4	-	0.8	-	-	-	-	-	-	-	*	-	-
	5	-	*	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	1.5	-	*	-	*	-	-	-	*	-	0.1
33	1 - 2	-	0.1	-	*	-	*	*	*	-	*	-	*
	3	*	0.7	0.1	0.1	0.1	*	0.1	*	0.1	*	-	*
	4	0.2	1.8	0.1	*	0.1	*	0.2	*	0.1	*	-	-
	5	0.1	0.8	-	*	-	*	0.1	*	*	*	-	-
	6	-	0.1	-	-	-	-	*	*	-	*	-	-
	7	-	*	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.3	3.5	0.1	0.1	0.1	*	0.3	0.1	0.1	0.1	-	0.1
43	1 - 2	-	-	0.1	0.1	-	*	*	*	0.1	*	-	-
	3	-	*	1.0	0.5	0.2	0.1	0.4	0.1	0.6	0.2	-	*
	4	*	0.1	1.3	0.8	1.0	0.3	0.7	0.3	0.7	0.3	-	*
	5	*	0.2	0.3	0.3	0.3	0.1	0.4	0.2	0.2	0.1	-	-
	6	*	0.1	-	*	*	*	0.1	*	*	*	-	-
	7	-	*	-	-	-	*	*	*	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	*	-	-
Total	----	0.1	0.5	2.8	1.6	1.5	0.5	1.7	0.7	1.6	0.6	-	*
53	1 - 2	-	-	0.2	*	-	-	*	*	-	*	-	-
	3	-	-	1.4	0.3	*	*	0.1	*	*	0.1	-	-
	4	-	*	1.1	0.6	0.2	*	0.4	0.1	0.1	0.1	-	-
	5	-	*	0.3	0.4	0.1	*	0.3	0.1	*	*	-	*
	6	-	*	0.1	*	*	*	0.1	*	*	*	-	-
	7	-	*	-	*	-	*	*	*	*	*	-	-
	8	-	-	-	-	-	-	-	*	-	-	-	-
Total	----	-	*	3.1	1.4	0.3	0.1	0.9	0.3	0.2	0.2	-	*
63	1 - 2	-	-	-	*	-	-	-	*	-	*	-	-
	3	-	-	0.1	0.1	-	-	-	*	-	*	-	-
	4	-	-	0.1	0.1	-	*	*	*	-	*	-	-
	5	-	-	-	0.1	-	-	-	*	-	*	-	-
	6	-	*	-	*	-	-	*	*	-	*	-	-
	7	-	-	-	*	-	-	-	*	-	-	-	-
	8	-	-	-	-	-	-	-	*	-	-	-	-
Total	----	-	*	0.2	0.3	-	*	*	*	-	*	-	-
24 - 54	1 - 8	0.2	5.2	0.2	0.2	0.2	*	0.3	0.1	0.1	*	-	*
25 - 35	1 - 8	-	0.7	-	*	-	-	-	*	-	-	-	-
81 - 85	1 - 8	-	0.8	-	*	-	*	*	*	*	*	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	*	-	-
30		-	-	-	*	-	-	-	-	-	*	-	-
31		-	*	-	*	-	*	*	*	-	*	-	-
32		0.1	*	-	*	-	*	*	*	*	*	-	-
33		1.6	0.5	0.1	0.3	-	*	0.3	0.3	2.0	0.9	-	0.4
34		1.8	2.5	1.3	2.7	0.5	0.3	2.8	2.4	9.9	5.5	0.9	0.9
35		17.5	20.0	7.1	9.9	7.4	2.9	9.3	7.9	19.0	18.1	7.8	4.6
36		45.6	38.6	36.9	17.9	15.7	11.3	19.9	15.3	21.5	26.2	11.2	10.3
37		32.8	33.6	28.9	27.0	47.4	41.6	32.5	29.3	36.0	28.2	31.2	29.3
38		0.6	3.7	13.3	21.7	15.6	28.0	20.0	27.0	10.4	16.3	23.9	22.6
39		-	0.3	11.8	14.7	8.2	11.7	12.9	14.9	1.1	4.5	10.6	15.8
40 & Longer		-	0.8	0.7	5.8	5.3	4.3	2.3	2.9	0.1	0.4	14.4	16.2
Average Staple		36.08	36.18	36.84	37.21	37.16	37.47	37.05	37.26	36.16	36.44	37.59	37.83
Average Length		1.12	1.13	1.15	1.16	1.16	1.17	1.16	1.16	1.13	1.14	1.17	1.18

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 27 2018

Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	2.2	1.2	0.1	0.1	-	0.8	6.8	8.7	-	0.1
	3	1.2	1.7	*	0.4	-	0.7	6.8	6.6	-	0.2
	4	0.2	0.2	-	*	-	*	0.9	0.6	-	*
	5	*	*	-	*	-	-	*	*	-	-
	6	-	*	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	*	-	-
	Total	----	3.7	3.1	0.1	0.6	-	1.6	14.4	15.9	-
31	1 - 2	12.6	7.4	0.9	1.3	1.9	1.7	13.1	8.1	1.8	3.9
	3	28.3	26.2	3.3	11.0	0.6	5.5	27.2	20.5	13.3	23.4
	4	6.4	7.0	1.0	8.2	0.1	1.5	9.7	8.4	4.2	4.8
	5	0.6	0.4	0.2	0.7	*	0.1	1.7	1.2	0.4	0.1
	6	0.1	*	-	*	-	*	0.1	0.1	-	*
	7	-	*	-	-	-	-	*	*	-	-
	8	-	*	-	-	-	-	-	*	-	-
	Total	----	48.0	41.1	5.4	21.2	2.6	8.9	51.9	38.3	19.7
41	1 - 2	2.6	2.5	1.6	1.8	8.6	4.0	1.4	1.6	1.1	2.9
	3	24.1	22.4	14.4	18.2	31.3	21.8	6.2	8.8	31.7	34.8
	4	13.1	16.9	29.7	27.6	20.4	15.4	5.8	9.0	29.7	14.0
	5	3.2	3.9	13.3	7.9	3.4	2.4	3.2	3.8	4.1	0.6
	6	0.5	0.5	1.3	0.4	0.1	0.1	0.9	0.9	0.1	*
	7	*	0.1	*	*	-	-	0.2	0.2	-	-
	8	-	*	-	*	-	-	*	*	-	-
	Total	----	43.5	46.1	60.3	56.0	63.7	43.7	17.7	24.2	66.7
51	1 - 2	*	*	0.3	0.3	0.2	0.1	0.2	0.2	-	*
	3	0.1	0.2	3.6	1.9	5.8	2.3	0.5	0.8	0.4	0.5
	4	0.5	0.4	6.3	2.9	8.1	3.9	0.3	0.6	1.2	0.4
	5	0.5	0.6	5.0	2.0	2.7	1.5	0.1	0.3	0.2	*
	6	0.1	0.2	1.2	0.3	0.3	0.1	*	0.1	0.1	*
	7	-	*	0.1	*	*	*	*	0.1	*	*
	8	-	*	-	-	-	-	*	*	-	-
	Total	----	1.2	1.5	16.5	7.4	17.1	8.0	1.1	2.1	1.9
61	1 - 2	-	-	-	*	-	-	*	*	-	-
	3	-	-	*	*	-	-	*	*	-	-
	4	-	-	-	*	0.1	*	*	*	-	*
	5	-	-	*	*	0.1	*	*	*	-	-
	6	-	-	0.1	*	-	-	-	*	-	-
	7	-	-	*	*	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	*
	Total	----	-	-	0.1	*	0.3	*	0.1	0.1	-
71	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	-	-	-	-	*	-	-
	5	-	-	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	-	-	-	-	-	-	-	*	-
12 & 22	1 - 2	-	0.1	*	*	-	0.1	0.4	1.7	-	*
	3	0.1	0.2	*	0.1	-	0.1	0.8	1.8	-	*
	4	0.1	*	*	*	-	*	0.2	0.4	-	*
	5	*	*	-	*	-	*	*	*	-	*
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
	Total	----	0.2	0.3	0.1	0.1	-	0.1	1.5	3.9	-
32	1 - 2	*	0.1	0.2	0.2	0.9	0.6	0.9	0.7	0.2	0.2
	3	0.1	1.0	1.2	1.3	0.6	1.7	3.0	2.5	1.3	1.4
	4	0.4	0.7	0.4	0.7	0.2	0.6	1.7	1.7	0.4	0.4
	5	0.3	0.2	0.1	0.1	-	*	0.6	0.4	0.1	*
	6	0.1	*	-	*	-	*	0.1	*	-	*
	7	*	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
	Total	----	1.1	2.0	1.8	2.3	1.7	3.0	6.3	5.2	2.0
42	1 - 2	*	0.2	0.1	0.6	1.4	1.8	0.2	0.3	0.4	0.5
	3	0.4	1.3	1.5	3.3	5.0	14.0	0.8	1.6	3.4	6.4
	4	0.5	1.3	3.6	3.3	2.8	10.4	0.8	1.7	3.4	3.4
	5	0.2	0.5	1.7	1.0	0.6	1.6	0.4	0.6	0.7	0.2
	6	0.1	0.1	0.2	0.1	0.1	0.1	0.1	0.1	-	*
	7	*	*	-	*	-	-	*	*	-	-
	8	*	*	-	-	-	-	*	*	-	-
	Total	----	1.2	3.5	7.1	8.2	9.8	27.8	2.3	4.4	7.9

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE											
For The Week Ending Dec 27 2018											
Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	*	*	0.2	0.1	-	*	0.1	0.1	-	*
	3	0.1	0.1	1.6	0.9	0.2	0.8	0.5	0.7	-	0.7
	4	0.1	0.2	1.7	1.0	0.3	2.1	0.5	0.9	0.2	0.3
	5	0.1	0.2	1.4	0.5	0.3	1.0	0.2	0.4	0.2	*
	6	*	0.1	0.9	0.1	0.1	0.1	*	0.1	0.1	*
	7	-	*	0.3	*	-	*	*	*	-	-
	8	-	*	-	-	-	-	*	*	-	-
Total	----	0.4	0.5	6.0	2.6	1.0	4.0	1.3	2.1	0.5	1.0
62	1 - 2	-	-	-	*	-	-	*	*	-	-
	3	-	*	0.1	*	-	*	0.1	0.1	-	-
	4	-	*	*	*	*	*	0.3	0.2	-	-
	5	-	-	*	*	-	*	0.1	0.1	-	-
	6	-	*	0.1	*	-	*	*	*	-	-
	7	-	*	*	*	-	*	-	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	-	*	0.2	0.1	*	*	0.6	0.5	-	-
13 & 23	1 - 2	-	*	-	*	-	*	*	0.1	-	*
	3	-	*	-	*	-	*	0.1	0.2	-	*
	4	*	*	-	*	-	-	0.1	0.1	-	-
	5	-	*	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	-	*	-	*	0.2	0.5	-	*
33	1 - 2	-	*	*	*	0.1	*	*	*	-	*
	3	-	0.2	0.1	0.1	0.2	0.1	0.3	0.3	*	*
	4	*	0.2	0.1	0.1	*	*	0.5	0.3	0.1	*
	5	0.1	*	*	*	-	*	0.2	0.1	-	*
	6	*	*	-	*	-	*	*	*	-	-
	7	*	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	0.1	0.5	0.2	0.2	0.3	0.1	1.2	0.7	0.1	0.1
43	1 - 2	-	*	-	*	0.2	0.1	*	*	-	*
	3	0.1	0.1	0.1	0.3	1.6	1.0	0.1	0.2	0.2	0.2
	4	0.1	0.2	0.4	0.5	0.6	0.8	0.2	0.3	0.7	0.2
	5	*	0.2	0.3	0.2	0.2	0.1	0.2	0.1	0.2	*
	6	*	0.1	0.1	*	*	*	0.1	*	-	*
	7	*	*	*	*	*	*	*	*	-	-
	8	-	*	-	-	-	-	*	*	-	-
Total	----	0.2	0.6	0.9	1.1	2.6	2.1	0.6	0.7	1.0	0.4
53	1 - 2	*	*	-	*	-	*	*	*	-	*
	3	0.1	0.1	0.2	0.1	0.1	0.1	*	0.1	-	*
	4	*	0.1	0.3	0.1	0.1	0.2	0.1	0.3	-	*
	5	*	*	0.3	0.1	0.1	0.1	0.1	0.2	-	*
	6	-	*	0.2	*	0.1	*	*	0.1	-	*
	7	-	*	0.1	*	*	*	*	*	-	-
	8	-	*	-	-	*	*	-	*	-	-
Total	----	0.1	0.2	1.0	0.3	0.5	0.5	0.4	0.7	-	*
63	1 - 2	-	-	-	-	-	-	*	*	-	-
	3	-	*	-	-	-	*	*	0.1	-	-
	4	-	*	-	*	-	*	0.1	0.2	-	-
	5	-	*	-	*	-	*	0.1	0.2	-	-
	6	-	-	-	-	-	*	*	0.1	-	-
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	-	*	-	*	-	*	0.3	0.5	-	-
24 - 54	1 - 8	0.4	0.4	0.1	*	0.4	0.1	0.1	0.2	0.2	*
25 - 35	1 - 8	-	*	-	-	-	-	-	*	-	-
81 - 85	1 - 8	-	0.1	*	*	0.1	*	0.1	0.1	*	*
STAPLE											
28 & Shorter		-	-	-	-	-	-	*	*	-	-
29		-	-	-	-	-	-	*	*	-	-
30		-	*	-	-	-	-	*	0.1	-	-
31		*	*	-	*	-	*	0.1	0.3	-	-
32		0.2	0.6	0.3	0.1	-	*	0.6	1.1	-	*
33		2.7	2.4	3.5	1.7	*	0.1	2.7	3.4	1.8	0.7
34		6.9	6.5	10.2	5.8	1.3	1.4	10.5	9.8	11.8	9.4
35		14.9	12.2	16.4	11.5	14.4	12.6	24.3	19.7	32.6	26.3
36		24.4	22.4	20.7	16.9	48.3	35.5	24.9	25.2	18.6	29.6
37		28.2	30.2	32.1	30.6	30.0	38.6	25.0	25.0	26.1	22.4
38		15.0	16.2	14.9	24.9	5.6	9.1	8.5	10.3	6.7	9.6
39		6.7	7.8	1.7	7.5	0.4	2.2	2.7	4.3	2.2	1.9
40 & Longer		1.0	1.6	0.2	0.9	*	0.4	0.6	0.9	0.2	0.1
Average Staple		36.44	36.57	36.19	36.78	36.25	36.49	35.96	36.06	35.85	36.00
Average Length		1.14	1.14	1.13	1.15	1.13	1.14	1.12	1.12	1.12	1.12

1/ Below Grade Color. 2/ Below Grade Leaf. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 27 2018

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	17.3	11.2	4.8	1.5	2.5	1.1	0.4	0.1	26.3	22.2	19.2	11.6
Bark - Level 2	-	*	-	-	-	-	-	-	-	*	-	*
Grass - Level 1	*	0.1	0.2	0.2	*	*	0.2	0.1	-	*	*	0.1
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	0.1	0.1	0.9	0.1	*	*	-	*	-	*	0.1	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	0.2	0.2	0.2	*	1.9	1.7	-	-	0.1	0.3	1.1	0.2
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	*	*	-	-	-	-	-	-	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	*	-	-	*	*	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	-	-	-	-	-	-	-	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	*	-	*	-	-	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	-	-	*	-	-	-	-	-	-	*	*
23	-	*	*	*	-	-	-	-	-	*	*	*
24	0.2	0.2	0.1	*	-	*	-	-	-	0.3	0.4	0.3
25	0.9	0.9	0.2	0.2	*	*	-	-	0.1	1.4	2.5	2.0
26	4.1	3.9	0.4	1.3	0.3	0.2	-	*	1.6	6.1	8.5	7.5
27	15.1	14.5	4.8	5.0	1.9	1.5	*	*	17.2	19.8	15.0	15.8
28	26.6	29.3	15.5	17.5	5.7	6.6	*	0.3	22.8	37.1	21.5	24.2
29	27.5	29.0	32.0	30.5	14.0	15.2	0.9	1.7	28.1	23.1	23.1	24.4
30	15.7	14.6	25.7	24.3	17.7	22.1	6.3	3.7	28.2	9.5	16.3	15.5
31	6.5	5.4	14.6	13.0	17.2	21.7	13.2	7.1	1.8	2.3	7.7	6.7
32	2.1	1.6	5.4	6.0	17.4	17.0	9.1	13.8	0.2	0.3	3.1	2.4
33	0.8	0.4	1.0	1.7	12.6	9.1	11.4	17.0	-	*	1.1	0.8
34	0.4	0.1	0.1	0.4	9.8	4.3	17.6	11.8	-	*	0.4	0.2
35	0.1	*	*	0.1	2.8	1.5	14.3	11.1	-	*	0.2	0.1
36	*	*	*	*	0.5	0.4	7.4	15.6	-	-	*	*
37	*	*	-	-	0.1	0.2	9.7	12.8	-	-	*	*
38	-	-	-	-	*	0.1	7.6	4.2	-	-	*	*
39	-	-	-	-	*	*	1.7	0.5	-	-	*	*
40 & Above	-	-	-	-	*	*	0.9	0.3	-	-	-	*
Average	29.12	29.03	29.93	29.91	31.60	31.24	34.50	34.56	29.14	28.58	29.04	28.98
Mike												
2.4 & Below	-	-	-	-	*	*	-	-	-	-	-	-
2.5	-	*	-	*	0.1	*	-	*	-	-	-	*
2.6	-	*	-	-	0.1	*	0.3	*	-	-	-	*
2.7	-	*	-	*	0.1	*	0.5	0.1	-	-	-	*
2.8	-	*	-	*	*	*	*	0.1	-	-	*	*
2.9	*	*	-	*	*	*	0.2	0.1	-	-	*	*
3.0	*	*	-	*	*	0.1	0.2	0.1	-	*	*	*
3.1	*	*	-	*	0.1	0.1	0.2	0.3	-	-	0.2	0.1
3.2	*	0.1	-	*	0.1	0.1	1.0	0.6	-	-	0.2	0.2
3.3	0.2	0.2	-	*	0.2	0.2	3.2	0.9	-	*	0.4	0.5
3.4	0.3	0.4	0.1	*	0.3	0.3	3.4	1.2	-	*	0.6	0.8
3.5	0.9	0.7	0.1	0.1	0.5	0.4	1.9	1.3	-	0.1	0.9	1.3
3.6	1.8	1.2	0.2	0.1	0.6	0.5	1.3	1.8	-	0.2	1.4	1.7
3.7	2.4	2.2	0.4	0.2	0.9	0.8	1.3	2.5	-	0.5	2.4	2.5
3.8	2.9	3.2	0.4	0.4	1.3	1.2	1.6	2.6	0.1	1.0	3.1	3.8
3.9	3.8	4.1	1.1	0.8	1.6	1.7	2.9	3.6	1.1	1.6	4.5	6.1
4.0	4.2	5.9	1.4	1.6	2.2	2.3	4.2	4.4	1.6	3.8	6.1	8.8
4.1	5.9	7.2	3.2	2.9	2.9	3.6	7.6	6.3	4.2	5.7	9.2	11.7
4.2	9.6	9.0	5.4	4.8	4.3	4.5	9.6	8.1	6.0	8.3	12.6	14.2
4.3	10.4	10.6	8.4	6.9	4.1	5.6	6.9	9.7	9.6	11.8	13.6	14.1
4.4	10.5	10.9	11.1	10.0	6.4	7.0	12.9	11.5	11.4	12.6	12.6	12.2
4.5	11.7	10.9	13.7	12.5	9.2	8.7	14.2	11.2	17.9	15.5	11.1	9.1
4.6	10.2	9.7	15.4	13.9	10.0	10.6	13.9	11.2	14.8	14.2	8.4	5.9
4.7	9.7	8.1	16.0	13.3	12.4	12.5	8.6	8.1	16.8	10.7	5.6	3.5
4.8	6.8	6.0	9.8	11.5	13.3	11.8	2.5	6.0	7.8	7.1	3.6	1.9
4.9	4.6	4.1	6.7	8.2	11.2	9.8	1.3	3.1	4.4	4.7	2.1	0.9
5.0	2.0	2.7	3.0	5.5	7.5	7.8	0.2	1.8	3.5	1.6	0.9	0.3
5.1	1.0	1.5	1.8	3.4	5.0	5.6	-	1.2	0.7	0.4	0.3	0.1
5.2	0.8	0.8	0.7	2.0	2.5	2.9	-	1.2	-	0.1	*	*
5.3	0.2	0.3	0.6	1.0	0.7	1.2	-	0.6	-	*	*	*
5.4	0.1	0.1	0.3	0.5	0.1	0.4	-	0.2	-	-	*	*
5.5 & Above	*	*	0.1	0.3	2.0	0.4	-	0.2	-	-	*	*
Average	4.40	4.38	4.56	4.61	4.63	4.62	4.26	4.36	4.53	4.46	4.29	4.22

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 27 2018

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	47.7	27.2	6.9	2.5	0.4	0.7	2.4	1.0	3.8	2.1	2.7	1.0
Bark - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	-	*	0.2	0.1	*	0.1	0.1	0.2	0.3	0.1	-	-
Grass - Level 2	-	-	-	-	-	-	-	*	-	-	-	-
Prep - Level 1	-	-	-	*	-	*	0.8	0.5	*	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	0.1	2.0	0.1	-	*	0.6	0.1	-	-	-	-
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	*	-	*	-	*	-	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	*	-	-	-	*	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	-	*	-	*	-	-	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	-	*	*	*	*	*	*	*	-	*	*	*
Plastic - Level 2	-	-	-	-	-	-	*	*	-	-	-	-
STRENGTH 1/ 22 & Below	*	*	-	*	-	*	*	*	*	*	-	-
23	0.1	*	-	*	*	*	0.1	*	0.1	*	-	-
24	0.3	0.2	-	*	0.1	*	0.3	0.1	0.9	0.1	-	-
25	0.4	0.9	-	0.1	0.3	0.2	0.4	0.4	2.5	0.9	0.1	*
26	0.3	2.3	0.1	0.7	2.6	1.1	2.5	1.6	5.5	3.1	0.2	0.1
27	3.9	8.0	2.8	3.1	10.1	5.9	8.6	5.1	13.4	7.3	1.7	1.8
28	40.9	26.9	7.2	10.0	32.4	18.1	17.3	14.0	17.5	15.2	12.3	11.3
29	32.3	29.3	33.0	26.3	32.7	28.5	25.3	28.7	23.0	23.3	38.7	24.9
30	13.8	17.2	32.2	28.5	10.1	23.6	25.8	28.0	18.6	21.8	30.6	31.9
31	2.0	11.0	20.1	17.3	5.5	12.4	13.5	14.1	10.5	14.5	11.4	21.8
32	5.4	4.0	4.1	8.9	3.9	6.3	4.6	5.4	5.1	8.2	2.7	6.5
33	0.5	0.2	0.4	3.5	1.6	2.9	1.4	1.9	1.9	3.9	2.2	1.6
34	*	*	0.1	1.1	0.6	0.8	0.2	0.4	0.7	1.4	0.1	0.1
35	-	*	-	0.3	*	0.1	*	0.1	0.1	0.2	-	*
36	-	-	*	0.1	*	*	-	*	*	*	-	*
37	-	-	-	*	-	*	-	*	*	*	-	-
38	-	-	-	*	-	-	-	-	-	*	-	*
39	-	-	-	-	-	*	-	-	-	-	-	-
40 & Above	-	-	-	-	-	-	-	-	-	-	-	-
Average	29.29	29.43	30.21	30.38	29.25	29.95	29.73	29.97	29.36	30.01	29.98	30.33
Mike												
2.4 & Below	*	*	-	-	-	-	-	-	-	*	0.1	*
2.5	*	0.2	-	*	-	-	-	-	-	-	*	*
2.6	0.2	0.4	-	-	-	-	-	-	-	-	1.0	0.1
2.7	0.1	0.6	-	-	-	*	-	-	-	*	1.0	0.1
2.8	0.2	0.9	-	-	-	-	-	-	-	*	1.8	0.4
2.9	0.1	0.7	-	-	-	-	-	*	-	*	1.8	0.4
3.0	-	1.1	-	*	-	*	-	*	-	*	4.3	0.9
3.1	*	2.0	-	*	-	*	*	*	-	*	2.1	0.5
3.2	0.2	2.7	-	*	-	*	-	*	*	*	1.1	0.5
3.3	0.4	4.4	-	*	-	*	*	*	*	0.1	2.1	0.9
3.4	1.1	5.8	-	*	*	*	*	*	0.1	0.1	2.4	2.1
3.5	3.8	6.0	-	*	*	*	0.1	*	0.3	0.2	4.8	2.9
3.6	6.0	7.6	-	*	*	0.1	0.3	0.1	0.5	0.3	4.1	4.8
3.7	16.9	10.0	-	*	0.1	0.2	0.2	0.2	0.9	0.5	5.8	3.8
3.8	14.6	9.3	-	0.1	*	0.4	0.5	0.4	1.9	0.8	7.3	6.9
3.9	13.7	9.0	-	0.3	0.4	0.7	0.9	0.7	2.7	1.4	3.9	7.7
4.0	12.8	7.8	-	0.5	1.6	1.1	2.1	1.1	3.5	2.1	6.6	8.3
4.1	5.9	7.4	-	1.1	2.9	2.2	2.3	1.9	4.6	3.2	7.6	6.6
4.2	4.9	6.9	-	1.9	4.2	4.0	4.0	3.0	5.2	4.8	4.7	8.4
4.3	4.1	6.3	-	2.7	8.9	6.1	5.6	4.4	6.8	6.9	5.5	8.9
4.4	2.2	4.5	4.0	3.6	6.9	8.2	5.9	6.4	10.0	9.7	10.3	8.7
4.5	4.2	3.2	4.1	6.3	7.6	10.5	8.8	9.1	12.8	13.0	6.0	7.1
4.6	8.1	2.1	4.0	9.6	10.0	11.7	11.1	13.2	15.5	15.1	2.7	6.0
4.7	0.6	0.6	14.0	13.7	10.3	12.3	12.4	16.1	14.1	14.3	3.6	5.8
4.8	*	0.3	17.7	16.4	12.5	11.3	13.5	16.2	9.0	11.1	0.9	3.6
4.9	*	0.1	16.9	15.7	11.6	10.0	12.4	13.1	5.3	7.3	2.2	1.8
5.0	-	0.1	20.1	12.9	7.8	7.6	10.7	7.5	3.8	4.5	1.6	1.2
5.1	-	*	12.5	8.2	6.1	5.7	5.9	3.6	2.0	2.5	0.9	0.9
5.2	-	-	4.4	4.6	4.1	4.1	2.3	1.6	0.9	1.3	1.3	0.4
5.3	-	-	1.7	1.9	2.9	2.5	0.7	0.8	0.2	0.5	0.9	0.1
5.4	-	-	0.4	0.5	1.8	1.0	0.1	0.3	0.1	0.2	1.5	0.2
5.5 & Above	-	-	0.2	0.2	0.4	0.4	*	*	*	*	*	*
Average	3.96	3.83	4.87	4.79	4.70	4.69	4.67	4.68	4.51	4.57	4.00	4.16

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 27 2018

Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter										
Bark - Level 1	5.7	4.5	5.1	4.1	2.0	0.4	8.8	6.4	0.5	0.3
Bark - Level 2	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	-	*	0.2	0.1	-	*	*	0.2	-	*
Grass - Level 2	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	*	*	*	*	*	*	*	-	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	*	-	*	0.1	*	0.6	1.2	-	-
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	-	-	*	*	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	*	-	-	*	*	-	-
Other - Level 2	-	-	-	-	-	-	-	*	-	-
Plastic - Level 1	*	*	-	*	-	*	*	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	*	0.1	*	-	*	*	0.1	-	-
23	*	*	0.9	0.1	-	*	0.1	0.3	0.2	*
24	*	0.1	2.7	0.5	0.1	*	0.3	0.6	2.3	0.3
25	0.2	0.2	8.8	2.9	0.8	0.3	1.0	1.2	6.2	2.1
26	0.9	0.8	13.6	7.2	4.3	2.6	2.5	2.6	11.8	5.5
27	5.3	4.0	22.4	12.8	16.5	11.5	5.8	5.7	13.2	12.2
28	11.7	9.9	22.0	21.0	25.4	25.5	12.5	12.1	21.1	23.6
29	22.0	20.0	14.4	25.6	20.4	27.3	18.4	18.3	22.9	26.2
30	24.7	24.4	7.0	18.0	10.5	17.2	21.4	20.5	11.0	16.0
31	17.6	17.9	4.6	7.6	12.2	9.4	19.0	18.1	7.7	8.7
32	11.6	13.0	2.8	2.8	7.2	4.2	11.8	11.8	2.9	3.5
33	5.0	6.9	0.7	1.1	1.7	1.5	5.1	5.7	0.6	1.3
34	0.8	2.1	*	0.3	0.6	0.3	1.5	2.1	0.1	0.4
35	0.1	0.5	0.1	*	0.1	0.1	0.3	0.6	*	0.1
36	*	0.1	*	*	0.1	*	0.1	0.2	-	*
37	*	*	-	*	*	*	*	*	-	-
38	-	*	-	-	-	-	*	*	-	-
39	-	-	-	-	-	-	*	*	-	-
40 & Above	-	-	-	-	-	-	-	*	-	-
Average	30.39	30.65	28.10	29.10	29.37	29.44	30.32	30.34	28.63	29.22
Mike										
2.4 & Below	*	*	-	-	-	-	0.2	0.1	-	-
2.5	*	*	-	-	-	-	0.6	0.1	-	-
2.6	-	*	-	*	-	-	0.7	0.2	-	-
2.7	-	*	-	-	-	-	0.7	0.2	-	-
2.8	*	*	-	-	-	-	0.8	0.2	-	-
2.9	0.1	0.1	-	*	-	-	0.9	0.3	-	-
3.0	0.2	0.1	-	*	-	*	1.4	0.5	-	-
3.1	0.3	0.1	-	*	-	*	1.7	0.7	-	-
3.2	0.4	0.2	-	*	-	*	2.0	0.9	-	-
3.3	0.9	0.3	-	*	-	*	2.5	1.3	-	*
3.4	0.9	0.5	-	0.1	-	*	3.0	1.6	-	-
3.5	1.2	0.7	-	0.2	*	0.1	3.6	2.1	0.1	*
3.6	1.4	1.0	*	0.4	0.1	0.1	4.2	2.6	0.3	*
3.7	2.4	1.7	0.1	0.8	0.1	0.2	5.1	3.1	*	0.1
3.8	3.6	2.9	0.5	1.5	0.1	0.3	5.6	3.7	0.4	0.1
3.9	4.4	4.0	1.2	2.9	*	0.5	6.1	4.4	0.5	0.2
4.0	5.7	5.8	5.1	5.5	0.1	1.0	6.4	5.1	1.9	0.3
4.1	7.7	7.7	7.3	9.2	0.2	1.7	6.7	5.7	2.2	0.6
4.2	7.1	8.5	8.7	12.5	0.2	2.4	7.0	6.4	5.5	1.7
4.3	7.9	9.4	14.5	14.7	0.7	3.6	6.9	7.0	8.5	3.6
4.4	7.6	10.4	13.3	15.2	5.6	5.5	6.3	7.4	8.0	7.2
4.5	11.3	11.4	15.3	12.6	7.1	7.8	5.7	7.9	10.0	14.0
4.6	11.5	10.2	11.8	9.6	9.4	9.9	5.5	7.9	12.4	20.2
4.7	9.7	8.3	9.4	6.7	12.9	11.5	5.0	7.5	17.1	20.4
4.8	5.4	6.5	6.8	4.2	14.7	12.9	3.8	6.5	16.6	15.6
4.9	4.0	4.4	3.2	2.0	14.7	12.3	2.7	5.3	7.1	8.9
5.0	2.9	2.7	1.8	1.1	14.8	11.0	1.8	3.9	4.3	4.2
5.1	1.4	1.6	0.9	0.5	11.0	8.5	1.3	2.9	3.0	1.9
5.2	1.1	0.9	0.1	0.2	6.1	5.5	0.8	1.9	1.7	0.7
5.3	0.6	0.4	*	*	1.8	3.2	0.4	1.3	0.4	0.2
5.4	0.3	0.2	-	*	0.3	1.5	0.2	0.8	0.1	*
5.5 & Above	*	0.1	-	*	0.1	0.3	0.1	0.5	-	*
Average	4.37	4.39	4.44	4.37	4.83	4.77	4.07	4.34	4.61	4.66

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 27 2018

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	-	-	-	*	*	-	-	-	-	-	-
2.5 - 2.6	-	*	-	*	0.2	*	0.3	0.1	-	-	-	*
2.7 - 2.9	*	*	-	*	0.1	0.1	0.8	0.3	-	-	*	*
3.0 - 3.2	*	0.1	-	0.1	0.2	0.3	1.4	1.0	-	*	0.4	0.4
3.3 - 3.4	0.5	0.7	0.1	0.1	0.4	0.5	6.6	2.1	-	*	1.0	1.3
3.5 - 3.6	2.7	1.9	0.3	0.2	1.2	0.9	3.2	3.0	-	0.4	2.4	3.1
3.7 - 4.2	28.8	31.6	11.8	10.8	13.1	14.0	27.1	27.5	13.0	20.9	37.9	47.0
4.3 - 4.9	63.8	60.3	81.2	76.2	66.7	66.1	60.4	60.8	82.7	76.6	57.1	47.7
5.0 - 5.2	3.9	5.0	5.6	10.9	15.1	16.3	0.2	4.2	4.2	2.1	1.2	0.5
5.3 & Above	0.3	0.4	0.9	1.8	2.9	1.9	-	0.9	-	*	*	*
Average	4.40	4.38	4.56	4.61	4.63	4.62	4.26	4.36	4.53	4.46	4.29	4.22
Leaf												
1 - 2	2.4	3.2	0.4	1.4	27.9	32.3	56.5	69.2	2.7	0.9	4.1	6.5
3	28.2	36.9	16.0	26.7	45.0	44.8	36.8	27.9	38.3	28.6	39.4	47.6
4	46.6	43.2	52.9	49.4	20.5	18.3	5.8	2.6	47.9	54.6	43.6	38.6
5	19.2	14.2	27.6	20.3	4.8	3.8	0.8	0.3	11.0	14.8	11.5	6.9
6	3.4	2.3	2.6	2.1	1.4	0.6	0.1	*	0.2	1.1	1.4	0.4
7	0.3	0.2	0.3	*	0.4	0.2	*	*	-	*	0.1	*
8	*	*	0.2	*	-	0.1	-	-	-	*	*	*
Average	3.94	3.76	4.18	3.95	3.05	2.93	2.44	2.19	3.68	3.87	3.67	3.47
HVI Trash 1/												
00	-	-	-	-	-	*	-	*	-	-	-	-
01	0.1	0.2	*	0.1	6.5	9.3	18.9	30.5	0.1	*	0.2	0.5
02	3.9	5.0	0.6	2.3	26.0	28.1	42.1	43.1	4.6	1.6	5.4	8.4
03	13.0	17.4	5.3	10.7	26.0	26.5	23.7	19.0	16.5	11.3	17.1	21.8
04	21.2	24.2	14.9	20.0	19.1	17.1	9.6	5.3	24.0	25.3	23.4	25.7
05	21.2	20.8	22.8	22.4	10.7	9.5	3.6	1.5	24.7	26.8	21.5	20.2
06	16.1	14.1	22.2	18.6	5.5	4.7	1.1	0.5	16.6	18.3	14.9	12.3
07	11.0	8.6	16.2	12.5	2.7	2.3	0.5	0.1	8.5	9.5	8.6	6.3
08	6.5	4.8	9.5	7.1	1.4	1.1	0.4	0.1	2.7	4.3	4.4	2.8
09	3.5	2.5	4.9	3.6	0.9	0.6	0.1	*	1.5	1.9	2.2	1.2
10	1.7	1.3	1.9	1.6	0.5	0.3	*	*	0.5	0.7	1.1	0.5
11	0.9	0.6	0.8	0.7	0.3	0.2	*	*	0.1	0.2	0.6	0.2
12	0.4	0.3	0.4	0.3	0.1	0.1	-	-	*	0.1	0.4	0.1
13	0.2	0.1	0.2	0.1	0.1	0.1	-	*	-	*	0.1	*
14	0.1	0.1	0.1	*	*	*	-	-	-	*	0.1	*
15	*	*	*	*	0.1	*	-	-	-	-	*	*
16	*	*	*	*	*	*	-	-	-	-	*	*
17	*	*	*	*	*	*	-	-	-	-	*	*
18 & Above	*	*	*	*	-	*	-	-	-	*	*	*
Average	0.53	0.49	0.60	0.55	0.35	0.33	0.24	0.21	0.48	0.51	0.49	0.45
UNIFORMITY 2/												
74 & Below	-	-	-	-	-	-	-	*	-	-	-	-
75	-	*	-	-	*	*	*	*	-	-	*	*
76	*	*	*	*	0.1	*	*	*	*	*	*	*
77	0.3	0.3	0.1	0.1	0.3	0.1	*	0.1	0.1	0.2	0.3	0.2
78	2.5	2.0	0.6	0.5	1.2	1.0	0.1	0.7	0.4	0.9	2.0	1.8
79	11.9	10.1	4.1	3.0	6.1	6.2	0.8	1.9	6.2	13.0	9.4	9.7
80	33.4	33.4	17.4	15.5	18.8	21.0	7.1	6.4	49.8	54.7	28.2	31.7
81	36.6	38.1	38.9	35.3	32.6	37.9	36.1	22.9	38.2	28.5	37.1	37.3
82	12.3	13.6	30.4	32.6	30.1	26.5	26.5	27.1	5.0	2.5	18.1	15.7
83	2.6	2.2	7.8	12.2	9.5	6.3	16.8	16.3	0.2	0.3	4.3	3.3
84	0.3	0.3	0.7	0.8	1.2	0.8	8.9	20.8	-	*	0.6	0.4
85 & Above	*	*	*	*	0.2	0.1	3.6	3.9	-	-	0.1	*
Average	80.98	81.03	81.65	81.81	81.62	81.50	82.39	82.70	80.88	80.64	81.20	81.11
Tenderables	62.7	63.9	79.2	71.4	72.0	73.6	90.0	90.7	56.5	61.7	61.3	78.6
SAMPLES CLASSED	33,738	652,208	22,806	1,141,954	24,807	183,773	6,727	127,984	2,259	61,000	71,287	1,454,551

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on New York No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 27 2018

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	*	*	-	-	-	-	-	-	-	*	0.1	*
2.5 - 2.6	0.2	0.6	-	*	-	-	-	-	-	-	1.0	0.1
2.7 - 2.9	0.3	2.1	-	-	-	*	-	*	-	*	4.7	0.9
3.0 - 3.2	0.2	5.7	-	*	-	*	*	*	*	*	7.4	1.9
3.3 - 3.4	1.5	10.2	-	*	*	*	0.1	*	0.1	0.2	4.5	3.0
3.5 - 3.6	9.8	13.7	-	*	*	0.1	0.4	0.1	0.8	0.5	8.9	7.7
3.7 - 4.2	68.7	50.4	-	3.9	9.2	8.5	10.0	7.4	18.8	12.9	35.9	41.7
4.3 - 4.9	19.2	17.2	60.6	67.9	67.7	70.1	69.7	78.6	73.3	77.5	31.2	41.8
5.0 - 5.2	-	0.1	37.0	25.6	18.0	17.4	18.9	12.7	6.6	8.3	3.8	2.5
5.3 & Above	-	-	2.3	2.5	5.1	3.9	0.9	1.1	0.3	0.7	2.4	0.3
Average	3.96	3.83	4.87	4.79	4.70	4.69	4.67	4.68	4.51	4.57	4.00	4.16
Leaf												
1 - 2	6.3	10.6	3.6	6.5	1.8	2.5	2.6	3.7	4.8	4.1	27.8	34.6
3	15.0	35.6	43.6	46.0	46.5	33.7	35.6	34.7	40.3	46.3	42.4	47.4
4	25.0	31.5	45.4	38.4	44.6	48.4	46.4	44.8	42.0	40.2	18.6	13.8
5	34.2	17.5	7.2	8.5	6.9	14.4	13.9	15.3	11.5	8.6	5.7	3.2
6	13.7	4.1	0.2	0.5	0.2	0.9	1.4	1.5	1.3	0.7	3.9	0.8
7	4.3	0.6	-	*	*	*	0.1	0.1	0.1	*	1.6	0.2
8	1.5	0.2	-	*	-	*	*	*	*	*	-	-
Average	4.53	3.71	3.57	3.50	3.57	3.78	3.76	3.76	3.65	3.56	3.18	2.86
HVI Trash 1/												
00	-	-	-	-	-	-	-	-	-	-	-	-
01	1.3	1.6	0.2	0.6	*	0.1	0.1	0.2	0.3	0.2	3.9	5.9
02	6.7	11.4	4.6	9.1	3.1	3.1	4.3	5.5	6.1	5.8	25.5	29.8
03	6.5	17.8	16.5	22.1	19.1	12.5	15.8	16.5	17.7	20.1	25.8	29.6
04	7.7	16.6	27.4	24.9	29.9	21.1	23.4	22.6	24.0	26.4	16.6	16.9
05	9.1	13.8	23.7	19.6	24.0	23.0	22.8	21.4	20.9	21.1	9.9	8.6
06	10.8	11.9	14.4	12.1	13.5	18.5	15.8	15.7	13.9	13.2	6.3	4.7
07	12.8	9.2	7.8	6.4	6.5	11.6	9.4	9.4	8.4	7.0	3.6	2.2
08	12.6	6.8	3.7	3.0	2.5	5.8	4.7	4.9	4.2	3.4	2.4	1.1
09	10.1	4.5	1.2	1.3	0.9	2.6	2.2	2.2	2.3	1.6	2.0	0.6
10	6.9	2.7	0.4	0.5	0.2	1.0	0.9	0.9	1.1	0.7	1.1	0.3
11	4.5	1.6	*	0.2	0.1	0.4	0.4	0.4	0.5	0.3	1.5	0.3
12	3.6	1.0	0.1	0.1	*	0.1	0.2	0.1	0.3	0.1	0.6	0.1
13	2.3	0.5	-	*	*	*	0.1	0.1	0.1	*	0.5	0.1
14	1.5	0.3	-	*	*	*	*	*	0.1	*	0.1	*
15	1.2	0.2	-	*	*	*	*	*	*	*	0.1	*
16	0.6	0.1	-	-	-	*	-	*	*	*	*	*
17	1.0	0.1	-	-	-	*	*	*	-	*	-	-
18 & Above	0.9	0.1	-	-	-	*	-	*	*	*	-	-
Average	0.73	0.52	0.47	0.45	0.46	0.52	0.50	0.49	0.49	0.47	0.39	0.33
UNIFORMITY 2/												
74 & Below	-	*	0.1	*	-	-	*	*	*	*	-	-
75	-	*	-	*	-	-	*	*	*	*	-	-
76	0.2	0.2	-	0.1	*	*	0.1	*	0.2	0.1	-	-
77	0.9	1.0	0.3	0.6	*	*	0.3	0.3	1.3	0.7	*	*
78	2.9	3.1	2.1	3.3	0.1	0.1	3.1	2.1	6.0	3.6	0.1	0.2
79	8.3	16.6	14.9	12.7	1.7	0.8	13.2	9.2	20.4	15.5	0.4	1.5
80	45.9	45.6	32.9	30.2	16.9	6.7	31.4	30.0	33.8	33.2	7.3	6.0
81	35.8	28.3	41.1	34.4	41.6	26.1	34.7	38.3	29.1	32.1	37.7	24.7
82	5.0	4.7	7.8	14.4	29.2	41.1	14.5	16.9	7.7	12.4	34.7	45.8
83	0.3	0.4	0.7	3.5	9.5	22.3	2.4	2.9	1.3	2.0	19.2	21.0
84	0.1	*	0.1	0.6	0.8	2.7	0.2	0.3	0.2	0.2	0.6	0.7
85 & Above	0.5	0.1	-	0.1	*	0.1	-	*	*	*	*	0.1
Average	80.76	80.58	80.85	81.00	81.76	82.30	80.96	81.13	80.57	80.84	82.13	82.25
Tenderables	40.6	52.7	32.5	56.9	69.9	68.6	66.0	76.2	78.7	76.2	75.6	90.0
SAMPLES CLASSED	4,390	44,441	2,870	396,917	22,834	734,844	31,238	1,257,282	16,435	666,870	2893	21015

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on New York No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 27 2018

Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE										
2.4 & Below	*	*	-	-	-	-	0.2	0.1	-	-
2.5 - 2.6	*	*	-	*	-	-	1.2	0.3	-	-
2.7 - 2.9	0.1	0.1	-	*	-	-	2.4	0.8	-	-
3.0 - 3.2	0.9	0.4	-	*	-	*	5.1	2.1	-	-
3.3 - 3.4	1.7	0.8	-	0.1	-	*	5.5	2.9	-	*
3.5 - 3.6	2.6	1.7	*	0.5	0.1	0.2	7.8	4.7	0.3	*
3.7 - 4.2	31.0	30.5	22.8	32.5	0.7	6.2	37.0	28.4	10.5	2.9
4.3 - 4.9	57.4	60.5	74.3	65.1	65.0	63.6	36.0	49.5	79.7	90.0
5.0 - 5.2	5.5	5.2	2.8	1.7	31.9	25.0	4.0	8.7	9.0	6.8
5.3 & Above	0.8	0.6	*	0.1	2.2	5.0	0.7	2.6	0.5	0.3
Average	4.37	4.39	4.44	4.37	4.83	4.77	4.07	4.34	4.61	4.66
Leaf										
1 - 2	17.5	11.6	3.4	4.5	13.2	9.3	23.2	21.4	3.4	7.7
3	54.9	53.7	26.2	37.6	45.4	48.2	46.5	44.3	50.3	67.7
4	21.5	27.3	43.5	44.5	33.0	35.2	21.3	24.7	40.1	23.6
5	5.0	6.2	22.4	12.4	7.6	6.9	7.1	7.5	5.9	1.0
6	1.0	1.1	4.0	1.0	0.7	0.4	1.6	1.6	0.2	*
7	0.1	0.2	0.6	*	0.1	*	0.3	0.4	*	*
8	*	*	-	*	*	*	*	0.1	-	*
Average	3.17	3.32	3.99	3.68	3.37	3.41	3.17	3.23	3.49	3.18
HVI Trash 1/										
00	-	-	-	-	-	-	-	*	-	-
01	1.8	1.0	0.2	0.3	1.8	0.8	4.2	4.4	0.1	0.3
02	19.3	12.9	4.0	5.6	11.9	10.1	23.8	19.9	4.6	10.4
03	30.8	26.0	11.2	16.1	20.8	22.0	26.8	24.0	21.6	32.3
04	21.8	24.4	18.1	23.4	23.2	24.5	18.3	19.3	27.5	31.7
05	12.4	16.4	21.0	22.4	18.3	19.2	11.0	13.1	21.9	16.5
06	6.5	9.2	17.7	15.6	11.4	11.9	6.5	8.1	14.0	6.0
07	3.6	4.9	13.0	8.9	6.3	6.4	3.9	4.8	6.7	1.9
08	1.9	2.5	7.0	4.4	3.3	3.0	2.3	2.8	2.5	0.6
09	1.0	1.3	4.2	1.9	1.8	1.3	1.3	1.6	0.6	0.2
10	0.5	0.7	2.0	0.8	0.6	0.5	0.8	0.9	0.3	*
11	0.2	0.3	0.9	0.3	0.2	0.2	0.5	0.5	0.1	*
12	0.1	0.2	0.4	0.1	0.2	0.1	0.3	0.3	*	*
13	0.1	0.1	0.2	0.1	0.1	*	0.1	0.2	-	*
14	*	0.1	0.1	*	0.1	*	0.1	0.1	-	*
15	*	*	*	*	-	*	*	0.1	-	*
16	-	*	-	*	-	*	*	*	-	*
17	*	*	*	*	*	*	*	*	*	*
18 & Above	*	*	-	*	0.1	*	*	*	-	-
Average	0.38	0.42	0.55	0.49	0.44	0.44	0.38	0.40	0.46	0.38
UNIFORMITY 2/										
74 & Below	*	*	*	*	-	-	*	*	-	*
75	*	*	*	*	-	-	0.2	0.2	-	*
76	0.1	0.1	0.3	0.2	-	*	0.6	0.6	*	0.1
77	1.0	0.7	1.8	1.0	*	0.1	1.9	1.7	0.1	0.5
78	5.8	3.3	12.4	5.8	0.8	0.6	6.2	4.8	3.4	3.2
79	19.2	13.4	29.3	22.2	6.7	5.3	17.7	13.5	17.8	18.7
80	39.3	33.3	37.9	39.2	31.6	21.1	30.2	27.0	40.9	40.9
81	28.7	33.6	13.9	24.4	31.0	35.1	28.9	29.7	27.1	27.8
82	5.5	13.0	3.8	6.2	23.6	28.9	11.9	17.2	9.9	7.7
83	0.3	2.3	0.5	1.0	5.5	8.0	2.1	4.7	0.8	1.0
84	*	0.3	*	0.1	0.7	0.8	0.2	0.6	-	0.1
85 & Above	*	0.1	-	*	*	*	*	*	-	*
Average	80.51	80.90	80.07	80.47	81.33	81.59	80.66	80.94	80.69	80.65
Tenderables	83.8	83.5	72.2	80.4	54.8	46.5	68.5	67.1	81.2	81.5
SAMPLES CLASSED	26,156	252,088	7,476	284,628	10,983	755,502	315,590	4,784,819	3,295	167,206

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on New York No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 27 2018

Color Grade	Leaf	Arizona		California		New Mexico		Texas	
		Week	Season	Week	Season	Week	Season	Week	Season
01	1	0.7	3.4	15.6	21.1	-	-	-	-
	2	0.4	15.2	29.7	23.5	-	-	-	-
	3	-	1.6	0.7	0.4	-	-	-	-
	4	-	*	-	*	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		1.0	20.2	45.9	44.9	-	-	-	-
02	1	15.6	11.4	3.4	5.8	-	-	-	-
	2	35.5	22.0	42.3	38.5	-	-	-	-
	3	0.7	1.7	5.8	7.6	-	-	-	-
	4	-	*	0.1	0.1	-	-	-	-
	5	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		51.8	35.1	51.5	52.0	-	-	-	-
03	1	1.4	1.9	*	*	-	-	-	-
	2	28.3	23.5	1.2	1.3	-	-	-	-
	3	8.6	7.7	1.0	1.4	-	-	-	-
	4	0.3	0.3	0.2	0.2	-	-	-	-
	5	-	-	*	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		38.5	33.4	2.4	2.9	-	-	-	-
04	1	-	*	*	*	-	-	-	-
	2	5.1	4.8	*	*	-	-	-	-
	3	3.4	4.9	0.1	0.1	-	-	-	-
	4	-	0.3	*	*	-	-	-	-
	5	-	-	-	*	-	-	-	-
	6	-	*	-	*	-	-	-	-
	7	-	*	-	-	-	-	-	-
Total -----		8.5	10.0	0.1	0.1	-	-	-	-
05	1	-	-	-	-	-	-	-	-
	2	0.1	0.3	-	*	-	-	-	-
	3	-	0.9	*	*	-	-	-	-
	4	-	0.1	*	*	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		0.1	1.3	*	*	-	-	-	-
06	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	*	-	*	-	-	-	-
	4	-	-	-	*	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	*	-	*	-	-	-	-
07	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-
	4	-	-	-	*	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	-	*	-	-	-	-
STAPLE									
44 & Shorter		-	0.1	0.1	0.2	-	-	-	-
46		0.3	20.2	3.7	4.2	-	-	-	-
48		40.1	29.7	24.7	34.5	-	-	-	-
50		51.6	47.3	60.8	54.7	-	-	-	-
52 & Longer		8.1	2.7	10.7	6.4	-	-	-	-
Average Staple		49.35	48.65	49.56	49.26	-	-	-	-
Average Length		1.44	1.42	1.44	1.43	-	-	-	-
EXTRANEIOUS MATTER									
Bark		-	-	*	*	-	-	-	-
Grass		-	0.2	*	0.2	-	-	-	-
Spindle Twist		-	-	0.1	*	-	-	-	-
Preperation		-	*	*	*	-	-	-	-
All Other		-	0.1	0.1	*	-	-	-	-

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 27 2018

Quality Designation	Arizona		California		New Mexico		Texas	
	Week	Season	Week	Season	Week	Season	Week	Season
MIKE								
2.4 & Below	-	-	*	*	-	-	-	-
2.5 - 2.6	-	-	0.6	0.1	-	-	-	-
2.7 - 2.9	-	-	1.0	0.2	-	-	-	-
3.0 - 3.2	-	*	0.7	0.5	-	-	-	-
3.3 - 3.4	-	0.3	1.2	1.1	-	-	-	-
3.5 - 3.6	6.1	1.8	3.2	3.8	-	-	-	-
3.7 - 4.2	78.4	78.7	48.6	51.9	-	-	-	-
4.3 - 4.9	15.5	19.1	44.8	42.4	-	-	-	-
5.0 - 5.2	-	-	*	*	-	-	-	-
5.3 & Above	-	-	*	*	-	-	-	-
Average	4.05	4.05	4.15	4.15	-	-	-	-
ALL RANGE MIKE								
2.4 & Below	-	-	*	*	-	-	-	-
2.5	-	-	0.3	*	-	-	-	-
2.6	-	-	0.3	*	-	-	-	-
2.7	-	-	0.4	*	-	-	-	-
2.8	-	-	0.3	0.1	-	-	-	-
2.9	-	-	0.3	0.1	-	-	-	-
3.0	-	-	0.3	0.1	-	-	-	-
3.1	-	-	0.2	0.1	-	-	-	-
3.2	-	*	0.2	0.3	-	-	-	-
3.3	-	0.1	0.4	0.4	-	-	-	-
3.4	-	0.3	0.8	0.7	-	-	-	-
3.5	0.3	0.2	0.9	1.4	-	-	-	-
3.6	5.9	1.7	2.3	2.3	-	-	-	-
3.7	10.3	4.4	4.0	3.4	-	-	-	-
3.8	2.7	8.6	4.7	5.3	-	-	-	-
3.9	7.6	17.3	6.2	7.7	-	-	-	-
4.0	7.9	19.0	7.4	9.9	-	-	-	-
4.1	33.7	16.3	10.5	11.5	-	-	-	-
4.2	16.1	13.1	15.8	14.1	-	-	-	-
4.3	11.6	11.0	17.7	15.7	-	-	-	-
4.4	2.6	5.0	14.0	13.6	-	-	-	-
4.5	1.3	2.4	7.9	8.2	-	-	-	-
4.6	-	0.6	3.7	3.6	-	-	-	-
4.7	-	0.1	1.2	1.1	-	-	-	-
4.8	-	*	0.2	0.3	-	-	-	-
4.9	-	*	*	*	-	-	-	-
5.0	-	-	*	*	-	-	-	-
5.1	-	-	*	*	-	-	-	-
5.2	-	-	-	*	-	-	-	-
5.3 & Above	-	-	*	*	-	-	-	-
Average	4.05	4.05	4.15	4.15	-	-	-	-
STRENGTH 1/ 36 & Below	0.1	0.1	1.2	0.3	-	-	-	-
37	-	0.1	0.5	0.6	-	-	-	-
38	0.1	1.1	1.6	2.0	-	-	-	-
39	1.8	6.6	2.2	3.6	-	-	-	-
40	3.3	8.9	2.3	3.6	-	-	-	-
41	3.9	6.5	4.0	4.2	-	-	-	-
42	9.6	11.5	10.5	9.3	-	-	-	-
43	27.0	27.0	17.3	17.2	-	-	-	-
44	21.6	24.3	24.8	24.5	-	-	-	-
45	27.1	10.7	20.2	20.8	-	-	-	-
46	3.9	2.4	9.4	9.3	-	-	-	-
47	1.4	0.5	3.9	3.2	-	-	-	-
48 & Above	0.1	0.2	2.2	1.4	-	-	-	-
Average	44.01	43.18	44.10	44.00	-	-	-	-
UNIFORMITY								
83 & Below	-	0.1	2.3	0.9	-	-	-	-
84	0.4	2.6	6.2	5.4	-	-	-	-
85	21.6	28.1	23.0	21.4	-	-	-	-
86	38.2	49.1	50.5	53.9	-	-	-	-
87	39.7	20.0	16.8	16.9	-	-	-	-
88 & Above	0.1	0.2	1.2	1.5	-	-	-	-
Average	86.60	86.29	86.22	86.30	-	-	-	-
Samples Classed	768	15,574	28,155	423,745	-	-	-	-