



State	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
AL	27	92.2	84.6	65,401	27	92.6	82.0	504,923
AR	29	92.2	78.1	144,539	29	87.1	72.0	1,009,097
AZ	9	72.9	44.4	18,311	9	80.4	55.7	78,684
CA	3	99.8	88.0	2,852	8	85.9	66.8	32,630
FL	4	92.5	85.6	13,154	4	93.8	85.3	67,630
GA	59	94.7	85.2	227,428	59	93.6	83.1	1,358,507
KS	3	67.7	48.9	12,788	3	73.3	51.5	65,575
LA	9	68.4	44.8	9,004	18	64.2	38.9	343,324
MO	18	96.9	89.6	58,903	18	97.4	89.2	404,391
MS	32	81.9	62.6	85,020	36	78.0	56.4	960,883
NC	34	85.2	68.3	119,818	34	85.3	68.8	648,672
NM	2	84.0	63.1	2,930	3	89.3	71.5	9,684
OK	11	71.3	54.7	19,772	11	78.8	61.4	68,665
SC	13	88.0	76.7	40,702	13	89.5	78.4	215,431
TN	19	86.4	73.1	74,377	19	88.7	73.5	473,158
TX	101	60.4	47.0	236,077	149	73.5	57.0	2,052,031
VA	4	97.7	92.3	25,271	4	96.4	89.6	127,137
United States	377	83.4	70.4	1,156,347	444	83.7	68.4	8,420,422
AMERICAN PIMA								
AZ	2			2,114	3			7,008
CA	12			26,626	13			175,152
NM*	-			-	2			12,037
TX	2			2,850	2			9,449
United States	17			34,399	20			203,646
United States all cotton	392			1,190,746	461			8,624,068

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 01, 2022

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	5.7	11.9	52.0	44.0	29.4	37.1	33.4	65.1	0.4	5.3	4.5	7.4
	3	8.1	13.0	11.6	8.8	4.2	8.4	6.3	15.0	1.2	3.0	3.4	4.9
	4	0.8	1.0	0.2	0.1	0.1	0.3	-	0.6	0.1	0.2	0.3	0.3
	5	*	*	-	*	-	*	-	*	-	-	*	*
	6	-	*	-	-	-	-	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	14.7	25.9	63.8	53.0	33.7	45.8	39.7	80.7	1.7	8.6	8.3	12.5
31	1 - 2	3.3	6.5	11.6	16.3	25.5	17.0	36.4	8.8	1.6	5.7	8.4	13.4
	3	24.3	32.3	17.0	21.8	24.3	18.2	12.5	5.4	12.7	25.5	26.9	35.0
	4	12.4	13.6	3.0	3.6	5.2	3.1	0.3	0.6	6.7	11.5	9.3	9.5
	5	1.2	1.3	0.4	0.3	0.2	0.2	-	0.1	0.9	1.3	0.8	0.7
	6	*	*	*	*	-	*	-	-	*	*	*	*
	7	-	*	-	*	-	-	-	-	-	-	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	41.2	53.8	32.0	42.0	55.2	38.5	49.2	14.9	21.9	43.9	45.5	58.6
41	1 - 2	0.9	0.6	0.1	0.3	0.4	0.5	0.4	0.1	2.5	2.0	2.8	1.9
	3	15.6	7.1	1.6	2.1	2.8	2.6	1.8	0.3	30.3	20.9	19.7	13.1
	4	19.7	8.3	1.7	1.6	3.7	2.4	1.1	0.1	34.5	18.1	14.9	8.8
	5	4.5	2.1	0.3	0.4	0.9	0.6	0.2	*	7.0	3.6	2.9	1.7
	6	0.6	0.2	*	0.1	*	*	-	-	0.3	0.2	0.2	0.1
	7	0.3	*	-	*	-	*	-	-	*	*	*	*
	8	0.1	*	-	-	-	-	-	-	-	-	-	-
Total	----	41.7	18.3	3.8	4.5	7.8	6.1	3.5	0.5	74.6	44.9	40.6	25.7
51	1 - 2	*	*	*	*	-	-	-	-	*	*	0.1	*
	3	0.2	0.1	*	*	-	*	-	-	0.3	0.2	1.7	0.5
	4	0.6	0.2	*	*	-	-	*	*	0.6	0.2	1.9	0.5
	5	0.2	0.1	*	*	-	-	-	-	0.4	0.1	0.6	0.2
	6	*	*	*	*	-	-	-	-	*	*	0.1	*
	7	*	*	-	*	-	-	-	-	-	-	*	*
	8	*	*	-	-	-	-	-	-	-	-	-	-
Total	----	1.1	0.4	*	*	-	*	*	*	1.3	0.5	4.6	1.2
61	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	*
	4	-	*	-	-	-	-	-	-	-	-	*	*
	5	-	-	-	-	-	-	-	-	-	-	*	*
	6	-	-	-	-	-	-	-	-	-	-	*	*
	7	-	-	*	*	-	-	-	-	-	-	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	*	*	-	-	-	-	-	-	*	*
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	-	-	-	-	-
12 & 22	1 - 2	*	*	*	*	0.2	4.2	2.1	1.4	-	*	*	*
	3	*	*	*	*	0.2	2.1	3.8	1.4	-	*	*	*
	4	*	*	-	*	-	0.3	-	*	-	*	*	*
	5	-	*	-	-	-	*	-	-	-	-	*	*
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.1	*	*	0.1	0.3	6.6	5.9	2.9	-	*	*	*
32	1 - 2	*	0.1	*	0.1	1.8	0.6	0.3	0.1	*	*	*	*
	3	0.1	0.4	0.1	0.1	0.5	0.9	1.2	0.6	*	0.3	0.1	0.2
	4	0.2	0.3	*	*	0.1	0.8	*	0.2	*	0.2	0.1	0.1
	5	*	*	*	*	-	0.3	-	-	*	*	*	*
	6	*	*	-	*	-	*	-	-	-	*	-	*
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.3	0.8	0.2	0.2	2.4	2.5	1.5	0.9	*	0.6	0.2	0.4
42	1 - 2	*	*	*	*	0.2	*	-	*	-	*	*	*
	3	0.2	0.2	*	*	0.1	0.1	0.1	*	0.1	0.5	0.2	0.6
	4	0.3	0.3	*	0.1	0.1	0.1	0.1	*	0.3	0.7	0.3	0.5
	5	0.1	0.1	*	*	*	0.1	-	*	*	0.1	0.1	0.1
	6	*	*	*	*	*	*	-	-	-	*	*	*
	7	*	*	*	*	-	-	-	-	-	-	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.7	0.7	0.1	0.2	0.5	0.3	0.2	0.1	0.4	1.4	0.6	1.2

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 01, 2022

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	*	-	*	-	-	-	-	-	-	*	*
	3	*	*	-	*	-	-	-	-	*	*	*	0.1
	4	*	*	*	*	-	-	-	*	*	*	0.1	0.2
	5	*	*	*	*	-	-	-	-	-	*	0.1	0.1
	6	-	*	-	*	-	-	-	-	-	-	*	*
	7	-	*	*	*	-	-	-	-	-	-	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total		----	* 0.1	* *		- -		- *		* *		0.2 0.3	
62	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	*
	4	-	-	-	-	-	-	-	-	-	-	*	*
	5	-	-	-	-	-	-	-	-	-	-	-	*
	6	-	-	-	-	-	-	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total		----	- -	- -		- -		- -		- -		* *	
13 & 23	1 - 2	-	-	*	*	-	0.1	-	*	-	-	-	-
	3	*	*	-	-	-	*	-	-	-	-	*	*
	4	-	-	-	-	-	*	-	-	-	-	-	*
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total		----	* *	* *		- 0.1		- *		- -		* *	
33	1 - 2	-	*	*	*	-	*	-	*	-	*	*	*
	3	*	*	*	*	-	*	-	*	-	*	*	*
	4	*	*	*	*	-	-	-	-	-	*	*	*
	5	*	*	-	*	-	*	-	-	-	-	*	*
	6	*	*	-	-	-	-	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total		----	* *	* *		- *		- *		- *		* *	
43	1 - 2	-	-	-	*	-	-	-	-	-	-	-	-
	3	*	*	*	*	-	*	-	-	-	*	*	*
	4	*	*	*	*	*	*	-	-	-	-	*	*
	5	*	*	*	*	*	*	-	-	*	*	*	*
	6	-	*	-	-	-	-	-	-	-	-	*	*
	7	-	-	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total		----	0.1 *	* *		* *		- -		* *		* *	
53	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	*	-	-	-	*
	4	*	*	-	*	-	-	-	*	-	*	*	*
	5	-	*	-	-	-	-	-	-	-	*	-	*
	6	-	*	-	-	-	-	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total		----	* *	- *		- -		- *		- *		* *	
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total		----	- -	- -		- -		- -		- -		- -	
24 - 54 25 - 35 81 - 85	1 - 8	*	*	-	*	-	*	-	-	-	-	-	-
	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	-	-	-	-	-	-	-	-	-	-	*
31		*	*	-	-	-	-	-	-	*	*	*	*
32		*	0.1	*	*	-	-	-	-	0.2	0.1	*	0.1
33		0.4	0.6	*	*	*	*	-	*	1.1	1.2	0.5	1.3
34		4.0	4.4	0.3	0.3	0.8	1.3	-	3.3	6.0	7.2	4.2	6.6
35		10.4	11.5	6.6	4.0	4.8	7.6	5.6	14.0	12.9	17.4	12.8	14.9
36		18.8	17.9	22.0	16.9	14.0	22.2	26.0	19.3	21.6	27.7	21.5	23.2
37		32.1	32.3	31.2	30.5	45.1	41.3	9.9	25.8	27.7	26.9	37.9	34.9
38		24.5	20.8	20.7	24.6	25.2	20.4	22.3	23.8	18.1	13.4	16.3	14.0
39		8.4	9.2	13.0	16.2	7.5	5.9	24.2	10.7	9.2	5.0	5.5	4.2
40 & Longer		1.4	3.2	6.3	7.5	2.7	1.2	12.1	3.0	3.2	1.1	1.4	0.7
Average Staple		36.92	36.93	37.31	37.55	37.23	36.94	37.70	36.97	36.75	36.38	36.70	36.46
Average Length		1.15	1.15	1.16	1.17	1.16	1.15	1.18	1.15	1.15	1.13	1.15	1.14

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE													
For The Week Ending Dec 01, 2022													
Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	45.1	45.8	9.1	4.1	74.1	78.2	25.4	21.4	0.6	1.9	39.7	26.7
	3	22.8	26.6	5.2	2.6	5.7	6.4	9.9	9.0	1.1	2.4	1.6	3.6
	4	2.9	2.2	0.1	0.1	0.1	0.1	0.3	0.2	0.2	0.2	-	*
	5	0.1	*	-	*	-	*	*	*	*	*	-	-
	6	-	-	-	-	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	70.9	74.6	14.3	6.8	79.9	84.7	35.6	30.7	1.8	4.6	41.3	30.3
31	1 - 2	0.2	0.3	6.2	7.8	9.4	8.6	9.7	12.7	2.2	3.4	21.5	23.2
	3	4.0	1.6	21.2	25.2	8.5	5.6	27.9	33.6	20.3	29.0	6.9	23.1
	4	5.1	2.0	5.4	4.5	1.1	0.6	6.9	7.8	12.1	17.8	1.3	1.9
	5	2.0	0.6	0.1	0.1	*	*	0.3	0.5	1.0	1.6	*	0.1
	6	0.3	0.1	*	*	-	-	*	*	*	*	-	-
	7	*	*	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	11.5	4.6	33.0	37.6	19.1	14.9	44.9	54.7	35.7	51.9	29.8	48.3
41	1 - 2	-	-	2.0	1.7	0.1	0.1	0.7	0.5	1.0	0.4	0.4	1.2
	3	*	*	23.6	22.0	0.5	0.2	6.5	5.5	21.6	12.1	8.1	8.8
	4	0.1	*	8.4	16.1	0.2	0.1	6.3	5.3	29.1	20.5	12.6	6.8
	5	0.7	0.2	1.5	2.2	*	*	1.2	1.1	6.4	6.5	5.1	2.1
	6	0.3	0.1	0.4	0.1	-	*	0.1	0.1	0.4	0.6	1.7	0.5
	7	-	-	0.1	*	-	*	*	*	*	*	*	*
	8	-	-	-	*	-	-	-	-	-	-	-	-
Total	----	1.1	0.3	35.9	42.2	0.8	0.4	14.9	12.4	58.6	40.1	27.9	19.4
51	1 - 2	-	-	*	*	-	*	*	*	*	*	-	-
	3	-	-	5.6	1.0	-	*	0.4	0.1	0.3	0.1	-	0.2
	4	-	-	6.8	2.0	-	*	0.5	0.2	0.9	0.3	*	*
	5	-	-	0.7	0.6	-	*	0.1	0.1	0.6	0.2	*	*
	6	-	-	0.1	*	-	-	*	*	0.1	*	0.3	0.1
	7	-	-	*	*	-	-	*	*	*	*	-	-
	8	-	-	-	-	-	-	-	*	-	-	-	-
Total	----	-	-	13.2	3.7	-	*	1.1	0.5	1.9	0.6	0.4	0.3
61	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	*	-	*	-	-
	4	-	-	-	*	-	-	-	*	-	-	-	-
	5	-	-	-	*	-	-	-	*	*	*	-	-
	6	-	-	-	*	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	-	-	-	*	*	*	-	-
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	-	-	-	-	-
12 & 22	1 - 2	7.0	7.9	*	*	0.1	*	0.1	*	-	*	0.6	0.3
	3	4.4	7.9	*	*	*	*	*	*	*	*	*	*
	4	1.4	1.2	-	-	-	-	-	*	*	*	-	-
	5	0.2	0.1	-	-	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	13.1	17.1	0.1	*	0.1	*	0.1	*	*	*	0.6	0.3
32	1 - 2	0.1	*	-	*	*	*	0.2	*	*	*	-	0.1
	3	1.3	0.5	0.1	0.1	0.1	*	0.4	0.1	0.2	0.7	-	0.6
	4	1.0	0.7	*	*	*	*	0.1	0.1	0.4	0.5	-	0.2
	5	0.5	0.4	-	*	-	*	*	*	0.1	0.1	-	-
	6	0.1	*	-	-	-	-	-	*	*	*	-	-
	7	*	*	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	3.0	1.7	0.1	0.2	0.1	*	0.7	0.2	0.7	1.3	-	0.9
42	1 - 2	-	-	*	0.2	-	*	*	*	*	*	-	*
	3	*	*	1.6	2.4	-	*	0.7	0.3	0.2	0.3	-	0.1
	4	*	*	0.9	1.7	-	*	1.3	0.5	0.5	0.7	-	0.3
	5	0.1	*	*	0.2	-	*	0.3	0.2	0.3	0.3	-	0.1
	6	*	*	-	*	-	-	*	*	0.1	*	-	-
	7	-	*	-	*	-	-	*	*	*	*	-	-
	8	*	*	-	*	-	-	-	-	-	-	-	-
Total	----	0.1	0.1	2.6	4.5	-	*	2.3	0.9	1.0	1.3	-	0.5

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 01, 2022

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	-	0.1	-	*	*	*	-	-	-	-
	3	-	-	0.2	1.7	-	*	*	*	*	*	-	-
	4	-	-	0.1	2.1	-	*	0.1	0.2	*	*	-	-
	5	-	-	*	0.4	-	*	0.1	0.2	*	*	-	-
	6	-	-	-	*	-	-	*	0.1	*	*	-	-
	7	-	-	-	*	-	-	*	*	*	*	-	-
	8	-	-	-	*	-	-	-	-	-	-	-	-
Total	----	-	-	0.3	4.3	-	*	0.3	0.5	0.1	*	-	-
62	1 - 2	-	-	-	*	-	-	-	-	-	-	-	-
	3	-	-	-	0.1	-	-	-	*	-	-	-	-
	4	-	-	-	0.1	-	-	-	*	-	*	-	-
	5	-	-	-	*	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	*	-	*	-	-
	7	-	-	-	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	0.2	-	-	-	*	*	*	-	-
13 & 23	1 - 2	0.1	0.1	-	-	*	*	-	-	-	-	-	-
	3	0.1	0.8	-	-	-	-	-	*	*	*	-	-
	4	-	0.3	-	-	-	-	-	-	-	*	-	-
	5	-	*	-	-	-	-	-	-	-	-	-	-
	6	-	*	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.2	1.2	-	-	*	*	-	*	*	*	-	-
33	1 - 2	*	*	-	-	*	*	*	*	-	*	-	-
	3	0.1	0.1	-	*	*	*	*	*	*	*	-	-
	4	*	0.2	-	*	-	*	*	*	*	*	-	-
	5	-	*	-	*	-	-	-	*	*	*	-	-
	6	-	*	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.1	0.3	-	*	*	*	*	*	0.1	*	-	-
43	1 - 2	-	-	-	*	-	-	-	*	-	-	-	-
	3	-	-	0.2	*	*	*	*	*	*	*	-	-
	4	-	*	0.2	*	-	-	*	*	*	*	-	-
	5	-	*	-	*	-	-	*	*	*	*	-	-
	6	-	*	*	*	-	-	*	*	*	*	-	-
	7	-	*	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	0.4	0.1	*	*	0.1	*	0.1	0.1	-	-
53	1 - 2	-	-	-	*	-	-	-	-	-	-	-	-
	3	-	-	-	0.1	-	-	*	*	-	-	-	-
	4	-	-	-	0.2	-	-	*	*	*	*	-	-
	5	-	-	*	*	-	-	*	*	*	*	-	-
	6	-	-	-	*	-	-	*	*	*	*	-	-
	7	-	-	-	-	-	-	*	*	-	-	-	-
	8	-	-	-	*	-	-	-	-	-	-	-	-
Total	----	-	-	*	0.3	-	-	*	*	*	*	-	-
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	*	-	-	-	-
	4	-	-	-	0.1	-	-	-	*	-	-	-	-
	5	-	-	-	*	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	*	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	0.1	-	-	-	*	*	*	-	-
24 - 54	1 - 8	-	0.1	*	*	-	-	*	*	*	*	-	-
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	-	-	*	-	-	-	-	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	*	-	-	-	-	-	-	-	-	-	-
30		*	0.1	-	-	-	-	-	-	-	*	-	-
31		0.5	0.8	-	*	-	*	-	*	-	*	-	-
32		3.5	4.3	*	0.2	*	*	*	*	*	*	-	-
33		12.0	14.3	*	1.3	*	*	0.2	0.1	0.2	0.3	*	*
34		16.2	19.7	3.0	4.4	0.5	0.3	1.2	1.2	1.3	2.2	5.6	2.4
35		20.4	22.6	8.9	9.6	4.7	3.3	5.5	4.7	7.2	9.0	6.2	7.4
36		27.5	23.4	11.9	16.9	16.7	15.0	11.5	9.9	20.6	23.7	11.8	7.5
37		16.4	13.6	19.8	25.4	31.4	30.0	28.6	28.8	40.6	40.1	28.8	18.4
38		3.3	1.2	21.8	19.1	26.7	26.1	23.3	25.5	20.6	17.3	11.6	25.4
39		0.2	0.1	25.9	17.0	16.3	19.1	18.3	19.2	7.5	6.0	15.1	15.0
40 & Longer		*	*	8.7	6.3	3.6	6.1	11.3	10.5	2.0	1.3	20.9	24.0
Average Staple		35.18	34.89	37.61	37.18	37.43	37.61	37.69	37.74	37.02	36.84	37.70	38.11
Average Length		1.10	1.09	1.18	1.16	1.17	1.18	1.18	1.18	1.16	1.15	1.18	1.19

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 01, 2022

Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	7.6	20.3	1.4	1.2	22.8	46.8	25.7	31.8	0.6	1.5
	3	5.3	9.8	3.8	2.8	8.7	12.4	18.7	10.4	1.4	2.3
	4	0.3	0.5	0.7	0.3	0.3	0.4	2.8	1.1	0.1	0.1
	5	-	*	*	*	*	*	0.1	0.1	-	-
	6	-	-	-	-	-	*	*	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	13.1	30.6	5.9	4.3	31.7	59.7	47.2	43.4	2.0	3.9
31	1 - 2	13.9	12.3	2.1	2.5	12.0	12.6	8.9	7.5	6.0	5.4
	3	35.3	28.1	18.1	25.3	25.5	17.7	21.7	13.7	50.6	50.7
	4	16.3	9.6	14.9	18.7	3.3	3.2	10.3	4.6	13.4	18.2
	5	1.4	0.6	2.9	2.9	0.1	0.2	3.0	1.1	0.2	0.8
	6	*	*	0.1	0.1	*	*	0.6	0.2	*	*
	7	-	-	-	*	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	67.0	50.6	38.1	49.5	40.9	33.7	44.5	27.0	70.2	75.1
41	1 - 2	0.9	0.7	0.5	0.2	1.9	0.4	0.1	1.7	1.3	0.4
	3	6.5	5.2	11.6	8.0	9.2	2.1	0.8	5.8	14.9	8.4
	4	5.5	3.6	24.1	22.7	6.2	1.5	1.6	2.8	10.4	9.4
	5	2.0	1.4	10.3	9.9	0.9	0.3	1.5	0.8	0.5	1.7
	6	0.6	0.3	1.2	1.0	0.1	*	0.9	0.3	*	0.1
	7	0.1	*	*	*	*	*	0.4	0.1	-	*
	8	-	-	-	-	-	-	0.1	*	-	-
Total	----	15.6	11.2	47.7	41.8	18.3	4.3	5.4	11.4	27.1	19.9
51	1 - 2	-	-	*	*	*	*	*	0.3	-	-
	3	-	*	1.5	0.3	*	*	0.1	1.5	0.1	*
	4	-	-	2.9	0.9	*	*	*	0.7	0.2	0.1
	5	*	*	1.7	0.8	*	*	*	0.1	0.1	*
	6	0.1	*	0.4	0.2	*	*	*	*	-	-
	7	*	*	*	*	*	*	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	0.1	0.1	6.5	2.1	0.1	*	0.2	2.6	0.3	0.2
61	1 - 2	-	-	-	-	-	-	*	*	-	-
	3	-	-	*	*	*	*	*	0.1	-	-
	4	-	-	-	-	-	-	*	*	-	-
	5	-	-	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	*	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	-	-	*	*	*	*	*	0.1	-	-
71	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	-	-	-	-	*	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	-	-	-	-	-	-	-	*	-	-
12 & 22	1 - 2	0.9	2.1	*	*	0.2	0.1	0.4	3.1	*	*
	3	0.4	1.2	*	*	0.1	*	0.6	1.4	-	*
	4	0.1	0.1	*	*	*	*	0.2	0.3	-	*
	5	-	*	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	1.3	3.4	*	*	0.2	0.1	1.2	4.7	*	*
32	1 - 2	1.1	0.7	*	*	0.9	0.2	0.1	0.9	*	*
	3	0.6	0.8	0.1	0.2	2.5	0.6	0.4	1.3	0.2	0.4
	4	0.4	0.5	0.2	0.4	0.4	0.2	0.3	0.4	0.1	0.2
	5	0.1	0.1	0.1	0.1	*	*	0.1	0.1	*	*
	6	-	-	*	*	*	*	*	*	-	-
	7	-	-	-	*	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	2.2	2.1	0.4	0.8	3.9	1.0	0.9	2.7	0.3	0.6
42	1 - 2	*	*	*	*	0.1	*	*	0.5	-	*
	3	0.1	*	0.1	0.1	0.9	0.2	*	1.8	*	0.1
	4	0.1	0.1	0.5	0.7	1.8	0.3	0.1	1.1	*	0.1
	5	*	*	0.2	0.4	0.6	0.1	0.1	0.2	*	*
	6	*	*	0.1	*	*	*	*	*	-	*
	7	*	*	-	*	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	0.2	0.2	0.9	1.2	3.4	0.7	0.3	3.7	0.1	0.3

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 01, 2022

Quality Designation	Leaf	OKLAHOMA <i>Week Season</i>		SOUTH CAROLINA <i>Week Season</i>		TENNESSEE <i>Week Season</i>		TEXAS <i>Week Season</i>		VIRGINIA <i>Week Season</i>	
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	-	-	-	*	-	0.2	-	-
	3	-	-	*	*	*	*	*	1.1	*	*
	4	-	-	0.1	0.1	*	*	0.1	0.8	-	*
	5	-	-	0.1	0.1	*	*	*	0.2	*	*
	6	-	-	*	*	*	*	*	*	-	-
	7	-	-	-	*	*	*	*	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
<i>Total</i>	----	-	-	<i>0.2</i>	<i>0.2</i>	<i>*</i>	<i>*</i>	<i>0.1</i>	<i>2.3</i>	<i>*</i>	<i>*</i>
62	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	-	-	0.1	-	-
	4	-	-	-	-	-	-	*	0.1	-	-
	5	-	-	-	*	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
<i>Total</i>	----	-	-	-	<i>*</i>	-	-	<i>*</i>	<i>0.2</i>	-	-
13 & 23	1 - 2	*	0.4	-	-	*	*	*	0.2	-	*
	3	0.1	0.5	-	-	*	*	*	0.1	-	*
	4	*	0.1	-	-	*	*	*	*	-	-
	5	-	-	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
<i>Total</i>	----	<i>0.1</i>	<i>1.0</i>	-	-	<i>*</i>	<i>*</i>	<i>*</i>	<i>0.4</i>	-	<i>*</i>
33	1 - 2	*	0.1	*	*	0.1	*	*	0.1	-	-
	3	0.1	0.2	*	*	0.3	0.1	0.1	0.2	*	*
	4	0.1	0.2	*	*	0.1	*	*	0.1	*	*
	5	*	0.1	*	*	*	*	*	*	*	*
	6	-	*	*	*	-	-	*	*	-	-
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
<i>Total</i>	----	<i>0.2</i>	<i>0.5</i>	<i>0.1</i>	<i>*</i>	<i>0.6</i>	<i>0.1</i>	<i>0.1</i>	<i>0.4</i>	<i>*</i>	<i>*</i>
43	1 - 2	-	-	-	-	*	*	*	*	-	-
	3	*	*	*	*	0.3	*	*	0.2	-	-
	4	*	*	*	*	0.3	0.1	*	0.2	*	*
	5	*	*	*	*	0.2	*	*	0.1	-	*
	6	*	*	*	*	*	*	*	*	-	-
	7	-	*	-	*	*	*	*	*	-	-
	8	*	*	-	-	-	-	-	*	-	-
<i>Total</i>	----	<i>*</i>	<i>0.1</i>	<i>0.1</i>	<i>0.1</i>	<i>0.8</i>	<i>0.2</i>	<i>*</i>	<i>0.5</i>	<i>*</i>	<i>*</i>
53	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	*	-	-	-	*	*	0.1	-	-
	4	-	-	-	-	-	-	*	0.2	-	-
	5	-	-	-	*	*	*	*	0.1	-	-
	6	-	*	*	*	*	*	*	*	-	-
	7	-	-	*	*	-	-	-	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
<i>Total</i>	----	-	<i>*</i>	<i>*</i>	<i>*</i>	<i>*</i>	<i>*</i>	<i>*</i>	<i>0.4</i>	-	-
63	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	-	*	*	-	-
	4	-	-	-	-	-	-	*	*	-	-
	5	-	-	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
<i>Total</i>	----	-	-	-	-	-	-	<i>*</i>	<i>0.1</i>	-	-
24 - 54	1 - 8	*	0.2	-	*	*	*	*	*	-	-
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	*	-	-	-	-	-	*	-	-
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	*	-	-
29		-	-	-	-	-	-	*	*	-	-
30		-	*	-	-	-	-	*	0.1	-	-
31		-	*	-	-	-	-	0.1	0.6	-	-
32		*	0.2	0.1	*	-	*	0.4	1.9	-	*
33		0.6	1.9	0.3	0.3	*	*	1.3	5.2	*	0.2
34		1.7	4.5	1.7	1.7	0.3	0.3	3.7	11.6	0.3	1.4
35		4.7	6.8	4.5	7.5	2.9	3.0	8.7	18.2	4.1	7.4
36		9.7	9.9	12.8	17.2	13.6	11.9	18.8	21.6	18.9	21.1
37		26.8	27.9	28.6	35.0	44.8	39.0	33.3	24.0	47.0	43.5
38		17.1	19.6	23.4	20.7	28.1	29.3	19.5	10.5	22.4	19.7
39		20.3	17.4	19.0	13.0	8.4	13.5	9.8	4.6	6.2	5.9
40 & Longer		19.1	11.8	9.5	4.6	1.8	2.9	4.3	1.7	1.2	0.8
<i>Average Staple</i>		<i>37.97</i>	<i>37.49</i>	<i>37.62</i>	<i>37.22</i>	<i>37.30</i>	<i>37.47</i>	<i>36.97</i>	<i>35.97</i>	<i>37.11</i>	<i>36.93</i>
<i>Average Length</i>		<i>1.19</i>	<i>1.17</i>	<i>1.18</i>	<i>1.16</i>	<i>1.17</i>	<i>1.17</i>	<i>1.15</i>	<i>1.12</i>	<i>1.16</i>	<i>1.15</i>

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 01, 2022

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	1.3	0.5	0.2	0.2	*	*	-	*	1.1	0.5	0.6	0.3
Bark - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	0.1	0.1	0.1	0.1	-	*	*	0.2	0.3	0.2	0.1	0.1
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	-	*	*	-	-	-	-	-	-	*	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	0.1	0.2	*	*	3.4	2.0	-	*	*	0.3	0.1	0.3
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	*	*	*	*	-	-	-	-	-	-	*	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	*	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	*	*	-	*	-	-	-	-	*	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	0.1	-	*	*	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	*	*	*	*	-	-	-	-	-	-	-	*
23	*	*	*	*	-	-	-	-	-	*	*	*
24	*	*	*	*	-	-	-	-	*	*	*	*
25	*	*	*	*	-	*	-	-	0.1	0.2	0.1	0.2
26	0.1	0.2	*	*	0.2	0.2	-	0.1	0.5	0.7	0.5	1.0
27	1.0	1.6	0.8	0.4	0.9	1.8	*	1.5	1.4	2.7	2.6	4.3
28	4.1	6.1	8.1	4.1	2.6	7.2	1.1	5.9	4.4	7.4	9.7	12.1
29	17.2	17.7	24.2	16.8	4.8	14.7	5.8	9.0	10.2	15.3	21.0	23.1
30	29.0	28.4	32.6	30.3	8.8	18.0	14.2	10.5	23.9	23.4	26.3	26.4
31	26.2	25.5	20.5	29.3	17.8	21.1	6.7	7.0	25.1	19.2	21.4	18.6
32	13.9	13.5	8.9	13.3	22.5	17.7	4.0	7.7	17.3	15.4	11.6	9.2
33	5.7	5.3	3.6	4.1	21.1	11.2	2.8	12.9	12.0	10.2	4.7	3.6
34	2.0	1.3	0.9	1.2	9.7	4.4	2.0	13.0	3.9	3.7	1.5	1.1
35	0.6	0.3	0.2	0.4	4.5	1.7	9.9	9.5	0.9	1.3	0.4	0.3
36	0.1	0.1	0.1	0.1	4.6	1.4	24.5	9.5	0.3	0.5	0.1	0.1
37	*	*	*	*	1.7	0.4	16.8	9.2	0.1	0.2	*	*
38	*	*	-	-	0.7	0.2	11.0	3.7	*	*	*	*
39	-	-	-	-	0.1	*	0.4	0.2	-	-	-	-
40 & Above	-	-	-	-	*	*	0.9	0.3	-	-	-	-
Average	30.99	30.85	30.56	30.94	32.64	31.39	34.79	33.36	31.37	31.08	30.62	30.34
Mike												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	*
2.5	-	*	-	-	-	-	-	-	-	-	-	*
2.6	*	*	-	-	-	-	-	-	*	*	-	*
2.7	*	*	*	*	-	-	-	-	-	-	*	*
2.8	*	*	-	*	-	-	-	*	-	-	*	*
2.9	*	*	*	*	*	*	-	*	-	-	*	*
3.0	0.1	*	*	*	0.1	*	-	*	*	*	*	*
3.1	0.1	0.1	*	*	0.1	0.1	-	0.1	0.1	*	*	*
3.2	0.2	0.2	*	*	0.2	0.1	-	0.2	0.3	0.1	0.1	0.1
3.3	0.6	0.3	0.1	0.1	0.3	0.1	-	0.3	0.5	0.2	0.3	0.2
3.4	0.8	0.5	0.2	0.2	0.4	0.1	-	0.7	0.9	0.4	0.7	0.3
3.5	1.7	0.8	0.6	0.3	0.8	0.3	0.1	0.8	0.9	0.6	0.9	0.4
3.6	2.6	1.4	1.2	0.6	1.2	0.4	-	1.6	1.7	0.7	1.6	0.8
3.7	3.6	2.3	1.7	0.9	0.7	0.7	2.1	2.1	1.9	1.2	2.5	1.3
3.8	5.3	4.1	2.6	1.7	0.9	0.7	7.2	2.8	3.1	2.2	3.1	2.0
3.9	7.0	5.5	4.1	2.8	1.9	1.1	7.6	3.9	3.6	4.1	4.4	3.1
4.0	8.9	7.4	5.9	4.3	2.6	1.8	10.0	5.2	4.5	6.1	5.6	4.7
4.1	10.7	8.7	7.4	6.1	2.6	2.3	3.9	6.5	8.4	8.6	7.9	6.7
4.2	11.9	10.2	9.5	8.1	2.4	3.4	3.3	7.5	13.5	11.0	10.2	9.2
4.3	12.2	10.7	10.2	9.5	3.0	6.2	4.6	7.8	15.9	11.9	10.9	11.7
4.4	10.9	10.3	9.9	10.1	7.5	9.0	11.4	8.8	13.5	12.3	13.0	13.5
4.5	7.4	9.5	9.9	9.9	7.3	11.1	14.1	10.3	10.6	12.2	12.5	13.8
4.6	5.5	8.3	9.5	10.2	8.5	12.8	14.9	8.2	8.7	11.0	10.5	11.7
4.7	3.7	6.9	8.0	9.0	10.6	13.7	16.7	7.6	4.8	8.2	7.2	8.5
4.8	2.4	5.2	7.2	7.8	12.5	11.4	3.7	7.4	3.0	4.8	4.0	5.3
4.9	1.2	3.3	4.9	6.4	13.9	8.7	0.6	5.8	0.9	1.9	2.2	3.1
5.0	0.8	2.0	3.1	4.7	10.1	6.0	-	2.4	0.9	1.1	1.3	1.7
5.1	1.0	1.1	2.0	3.3	6.3	4.4	-	3.6	0.8	0.8	0.6	0.9
5.2	0.8	0.7	1.2	2.1	2.3	2.7	-	2.9	0.6	0.4	0.2	0.4
5.3	0.1	0.3	0.4	1.1	2.5	2.0	-	2.0	0.7	0.3	0.1	0.2
5.4	0.2	0.1	0.2	0.6	0.7	0.6	-	1.0	0.3	0.1	*	0.1
5.5 & Above	0.1	0.2	0.1	0.4	0.6	0.2	-	0.3	*	*	*	*
Average	4.22	4.33	4.41	4.51	4.66	4.63	4.35	4.45	4.31	4.36	4.33	4.40

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 01, 2022

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	14.1	8.9	2.4	0.5	*	0.1	0.7	0.4	0.7	0.4	0.3	0.2
Bark - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	0.1	*	0.4	0.3	0.1	*	0.1	0.2	0.2	0.2	-	*
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	0.5	-	*	*	*	*	*	-	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	*	*	*	0.4	*	*	*	0.1	*	*	-	*
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	-	-	-	-	*	-	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	*	-	*	-	*	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	*	*	*	*	*	-	-
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	0.1	*	*	*	*	-	*	-	-	-	-
23	-	0.1	-	*	*	*	*	*	-	-	-	-
24	*	0.3	-	*	*	*	*	*	*	*	-	-
25	0.1	0.8	0.2	0.1	*	*	*	*	*	*	-	-
26	0.3	2.3	1.3	0.7	*	*	*	0.1	0.1	0.2	*	*
27	2.7	4.3	1.3	2.0	1.0	0.5	0.2	0.6	0.4	1.0	0.1	2.0
28	11.6	12.1	2.8	5.6	9.9	4.1	2.5	3.1	2.2	5.0	8.0	8.9
29	19.1	20.2	21.3	14.4	33.9	20.1	12.1	12.3	11.7	17.0	15.2	17.3
30	22.9	22.3	21.9	24.3	35.9	40.2	36.0	31.6	26.4	28.8	26.2	28.2
31	17.4	17.9	32.3	27.2	13.3	25.1	31.5	32.1	28.4	26.0	24.3	18.9
32	16.7	12.1	14.9	16.9	4.0	7.3	11.0	14.0	17.4	14.0	20.0	15.9
33	6.8	5.7	3.6	6.5	1.4	1.9	4.2	4.2	8.8	5.8	5.9	6.9
34	1.9	1.6	0.2	1.7	0.5	0.6	1.8	1.4	3.6	1.8	0.1	1.0
35	0.4	0.2	0.1	0.3	0.1	0.2	0.6	0.4	0.9	0.4	*	0.9
36	0.1	*	*	*	*	*	0.1	0.1	0.2	*	-	-
37	*	*	-	*	-	-	*	*	*	*	-	-
38	-	-	-	*	-	-	-	-	-	-	-	-
39	-	-	-	-	-	-	-	-	-	-	-	-
40 & Above	-	-	-	-	-	-	-	-	-	-	-	-
Average	30.75	30.38	30.83	30.99	30.16	30.64	31.04	31.05	31.37	30.96	30.96	30.85
Mike												
2.4 & Below	*	*	-	-	-	-	-	-	-	-	-	-
2.5	0.1	0.1	-	-	-	-	-	*	-	-	-	-
2.6	0.2	0.5	-	-	*	*	-	*	-	-	0.1	*
2.7	0.5	0.6	-	*	-	-	-	*	-	-	0.1	*
2.8	2.4	1.0	-	-	*	*	-	*	-	-	*	*
2.9	0.7	0.9	-	*	0.1	*	*	*	*	*	0.1	0.5
3.0	1.1	1.3	-	-	0.1	0.1	0.1	*	*	*	0.2	0.3
3.1	2.7	1.9	0.3	*	0.3	0.1	0.1	*	*	*	0.2	0.3
3.2	2.5	2.2	1.1	*	0.3	0.1	0.1	*	0.1	*	0.4	1.2
3.3	4.7	2.6	0.2	*	0.2	0.2	0.2	0.1	0.2	0.1	4.5	2.3
3.4	3.8	2.2	*	*	0.3	0.4	0.3	0.1	0.2	0.1	4.0	2.0
3.5	4.2	3.3	*	*	0.4	0.7	0.5	0.1	0.4	0.2	7.7	3.7
3.6	4.0	3.4	*	0.1	0.8	1.2	0.7	0.2	0.5	0.3	7.8	4.6
3.7	1.8	4.1	*	0.1	1.6	2.1	1.1	0.4	0.9	0.5	12.2	7.8
3.8	2.6	5.3	0.3	0.2	2.6	3.0	1.1	0.7	1.7	0.9	9.4	10.4
3.9	6.1	6.4	1.4	0.4	4.3	4.5	2.1	1.2	2.3	1.6	2.3	10.5
4.0	6.4	6.3	2.2	0.8	5.9	6.1	2.6	1.7	3.7	2.9	5.3	7.3
4.1	6.7	8.1	2.2	1.1	10.3	8.8	4.2	2.6	5.6	4.6	6.3	8.8
4.2	7.3	9.2	3.1	1.9	13.8	10.8	4.6	3.6	7.5	6.8	4.6	4.5
4.3	9.4	9.7	5.8	2.9	13.1	12.3	6.9	5.6	8.8	9.0	1.9	3.6
4.4	11.1	9.8	8.6	4.5	12.9	12.7	8.2	7.7	9.4	10.3	2.4	3.6
4.5	9.6	8.7	9.2	7.1	10.6	11.9	10.4	10.0	10.5	11.8	6.8	4.8
4.6	7.4	6.6	8.3	10.1	8.5	10.0	11.8	11.8	10.4	11.3	5.9	4.6
4.7	3.9	3.4	8.3	12.5	6.5	7.2	11.8	12.1	9.6	11.0	6.8	6.2
4.8	0.8	1.6	9.8	14.4	4.3	4.0	10.3	11.4	9.0	9.4	3.2	6.4
4.9	*	0.6	14.1	14.2	1.6	2.2	8.5	10.2	7.4	7.4	2.8	3.5
5.0	*	0.2	11.7	13.0	0.9	0.9	5.7	7.9	4.7	5.0	1.0	1.1
5.1	-	*	7.5	8.3	0.4	0.4	4.2	5.7	2.9	3.0	0.6	0.5
5.2	*	*	2.1	4.0	0.2	0.1	2.6	3.8	1.9	1.9	0.8	0.6
5.3	-	-	2.1	2.0	0.1	0.1	1.4	1.9	1.1	1.0	2.4	0.7
5.4	-	-	0.6	1.1	*	*	0.6	0.8	0.6	0.6	*	*
5.5 & Above	-	-	1.2	1.1	*	*	0.3	0.5	0.4	0.2	-	-
Average	4.01	4.05	4.68	4.79	4.31	4.33	4.58	4.67	4.52	4.55	4.06	4.11

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 01, 2022

Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter										
Bark - Level 1	10.6	7.1	1.8	1.0	0.8	0.3	21.9	7.1	0.1	0.2
Bark - Level 2	-	-	-	-	-	-	*	*	-	-
Grass - Level 1	*	*	0.1	0.4	0.1	0.1	*	0.9	*	*
Grass - Level 2	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	-	-	*	*	*	*	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	*	*	*	*	*	0.1	0.1	-	-
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	-	-	*	*	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	-	-	-	*	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	*	*	0.1	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	*	-	-	*	*	*	0.4	-	-
23	-	*	-	-	*	*	*	0.5	-	-
24	-	*	*	*	*	*	0.1	1.0	-	-
25	*	0.1	*	0.1	*	*	0.4	1.7	*	*
26	0.1	0.7	0.3	0.6	0.1	0.1	1.3	3.2	*	*
27	0.8	1.7	1.5	3.0	1.3	0.5	3.9	6.4	0.3	0.4
28	2.6	4.0	6.2	11.1	10.4	4.4	8.3	11.8	1.8	4.0
29	7.0	9.1	17.4	25.8	35.0	20.4	14.0	17.0	9.8	18.2
30	13.8	13.6	32.6	29.6	33.9	38.4	18.8	18.7	28.3	34.1
31	18.2	16.5	22.5	17.2	14.0	25.9	19.3	15.9	33.6	25.9
32	20.2	17.4	12.0	8.2	3.9	8.0	15.6	11.3	16.3	11.3
33	15.0	17.4	5.9	3.3	1.1	1.8	9.8	6.8	7.3	4.5
34	14.5	14.4	1.4	0.9	0.1	0.3	5.3	3.5	2.1	1.3
35	6.2	4.2	0.2	0.2	*	*	2.3	1.3	0.4	0.2
36	1.3	0.8	*	*	*	*	0.7	0.4	0.1	*
37	0.1	0.1	-	-	-	-	0.2	0.1	-	-
38	*	*	-	-	-	-	*	*	-	-
39	-	*	-	-	-	-	*	*	-	-
40 & Above	-	-	-	-	-	-	-	*	-	-
Average	32.31	32.07	30.81	30.34	30.12	30.63	31.13	30.34	31.30	30.86
Mike										
2.4 & Below	-	*	-	-	-	-	*	*	-	-
2.5	0.3	0.2	-	-	-	-	0.1	*	-	-
2.6	0.5	0.4	-	-	*	*	0.2	0.1	-	-
2.7	0.5	0.3	-	-	*	*	0.5	0.1	-	-
2.8	0.4	0.3	-	-	*	*	1.1	0.3	-	-
2.9	0.5	0.4	*	*	0.1	*	1.7	0.4	-	-
3.0	0.6	0.5	0.1	*	0.2	*	2.1	0.6	*	*
3.1	1.8	0.9	0.3	0.1	0.6	0.2	2.7	0.9	*	*
3.2	2.8	1.3	0.3	0.1	0.8	0.2	3.3	1.1	*	*
3.3	6.2	3.0	0.6	0.2	1.0	0.3	4.1	1.4	*	0.1
3.4	6.0	4.4	0.6	0.2	1.3	0.5	4.9	1.7	0.2	0.2
3.5	7.1	4.7	1.1	0.3	2.0	0.9	5.2	2.0	0.3	0.4
3.6	8.4	7.0	1.3	0.6	2.5	1.4	5.6	2.4	0.6	0.6
3.7	8.5	7.0	2.5	1.2	4.1	2.2	6.1	2.8	1.2	1.3
3.8	7.7	7.4	3.5	1.8	4.8	2.9	6.0	3.5	2.5	2.7
3.9	6.9	6.9	4.4	2.9	6.7	4.0	5.9	4.5	4.3	5.0
4.0	7.0	8.5	5.6	4.2	6.7	5.0	5.9	5.8	8.9	7.7
4.1	6.9	7.9	9.1	6.3	7.5	6.1	5.9	7.5	11.5	10.9
4.2	6.2	7.4	9.3	8.5	9.5	7.6	5.8	9.4	14.1	14.0
4.3	6.3	7.4	10.2	11.0	9.6	9.2	5.8	10.1	13.5	14.4
4.4	5.9	6.2	10.3	12.9	9.5	10.3	5.4	9.6	12.9	12.5
4.5	5.4	6.3	9.7	12.6	9.9	10.4	5.0	8.8	11.2	9.7
4.6	1.6	3.7	9.6	11.3	7.0	9.3	4.3	8.1	8.7	7.5
4.7	1.0	3.1	6.9	9.1	5.3	8.4	3.8	6.6	4.1	4.7
4.8	0.7	1.5	4.9	6.5	3.9	6.8	3.0	4.8	3.0	3.5
4.9	0.4	1.7	4.0	4.3	3.0	5.6	2.1	3.1	1.2	2.2
5.0	0.1	1.0	2.0	2.6	2.0	3.8	1.4	1.9	1.0	1.3
5.1	*	0.5	2.2	1.7	1.0	2.4	0.9	1.1	0.3	0.6
5.2	0.1	0.1	0.8	1.0	0.6	1.4	0.6	0.6	0.1	0.2
5.3	*	*	0.3	0.4	0.4	0.6	0.3	0.3	0.1	0.1
5.4	*	*	0.2	0.1	0.2	0.2	0.2	0.2	0.2	0.3
5.5 & Above	*	*	*	*	0.1	*	0.2	0.2	*	0.1
Average	3.85	4.00	4.35	4.44	4.25	4.42	3.96	4.25	4.30	4.31

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 01, 2022

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	*
2.5 - 2.6	*	*	-	-	-	-	-	-	*	*	-	*
2.7 - 2.9	0.1	*	*	*	*	*	-	*	-	-	*	*
3.0 - 3.2	0.4	0.3	0.1	*	0.4	0.2	-	0.3	0.4	0.1	0.1	0.1
3.3 - 3.4	1.5	0.8	0.3	0.2	0.8	0.2	-	1.1	1.4	0.5	1.0	0.5
3.5 - 3.6	4.2	2.2	1.8	0.9	1.9	0.7	0.1	2.4	2.6	1.3	2.6	1.2
3.7 - 4.2	47.4	38.2	31.2	23.8	11.1	10.0	34.0	28.0	35.0	33.3	33.7	27.2
4.3 - 4.9	43.4	54.2	59.7	62.9	63.4	72.9	65.9	56.0	57.4	62.2	60.3	67.8
5.0 - 5.2	2.6	3.8	6.3	10.1	18.7	13.1	-	8.9	2.3	2.2	2.1	3.1
5.3 & Above	0.5	0.6	0.7	2.1	3.8	2.9	-	3.3	1.0	0.3	0.1	0.2
Average	4.22	4.33	4.41	4.51	4.66	4.63	4.35	4.45	4.31	4.36	4.33	4.40
Leaf												
1 - 2	9.9	19.1	63.8	60.7	57.4	59.5	72.5	75.6	4.5	13.1	16.0	22.8
3	48.6	53.0	30.4	33.0	32.1	32.2	25.7	22.6	44.6	50.5	52.2	54.4
4	34.1	23.7	5.0	5.5	9.3	7.0	1.5	1.6	42.2	30.9	26.9	19.9
5	6.1	3.7	0.7	0.8	1.1	1.3	0.2	0.1	8.3	5.2	4.5	2.7
6	0.7	0.3	*	0.1	*	0.1	-	-	0.4	0.3	0.4	0.2
7	0.3	0.1	*	*	-	*	-	-	*	*	*	*
8	0.1	*	-	-	-	-	-	-	-	-	-	-
Average	3.40	3.12	2.33	2.37	2.43	2.40	2.15	1.98	3.55	3.28	3.21	3.02
HVI Trash 1/												
00	-	*	-	*	-	*	-	0.1	-	*	-	*
01	1.2	3.4	23.3	22.9	24.7	23.4	33.9	43.0	0.3	3.3	2.8	4.7
02	12.4	21.8	43.8	41.7	37.4	42.9	42.1	35.6	7.6	15.6	18.8	26.0
03	24.3	29.0	19.4	20.6	19.5	19.4	18.1	14.8	19.8	25.5	27.8	30.3
04	25.0	21.8	7.6	8.6	9.6	7.8	4.0	4.6	24.5	23.8	23.2	20.1
05	17.9	12.8	3.3	3.5	4.9	3.5	0.9	1.2	20.7	16.2	14.2	10.5
06	10.4	6.4	1.5	1.5	2.3	1.7	0.6	0.4	14.0	8.8	7.4	4.9
07	4.9	2.8	0.7	0.6	1.0	0.9	0.3	0.1	7.6	4.2	3.4	2.1
08	2.0	1.1	0.3	0.3	0.3	0.4	0.1	*	3.6	1.6	1.4	0.8
09	0.9	0.5	0.1	0.1	0.1	0.1	-	*	1.3	0.6	0.6	0.3
10	0.5	0.2	*	0.1	*	*	-	-	0.4	0.2	0.2	0.1
11	0.2	0.1	*	*	*	*	-	-	0.2	0.1	0.1	0.1
12	0.1	*	*	*	*	*	-	-	0.1	*	0.1	*
13	*	*	*	*	*	*	-	-	*	*	*	*
14	*	*	*	*	-	-	-	-	-	*	*	*
15	*	*	*	*	-	*	-	-	*	*	*	*
16	*	*	*	*	-	-	-	-	-	*	*	*
17	*	*	-	*	-	-	-	-	*	*	*	*
18 & Above	*	*	*	*	-	-	-	-	-	-	*	*
Average	0.42	0.36	0.23	0.24	0.25	0.24	0.20	0.19	0.46	0.39	0.38	0.34
UNIFORMITY 2/												
74 & Below	-	*	-	-	-	-	-	-	-	*	-	*
75	-	*	-	-	-	-	-	-	-	*	*	*
76	*	*	*	*	-	*	-	*	*	*	*	0.1
77	0.1	0.2	0.1	*	0.1	0.2	-	0.1	0.1	0.2	0.3	0.7
78	1.0	1.3	0.4	0.2	1.6	2.1	0.9	1.5	1.3	1.7	1.9	3.6
79	6.2	8.2	7.1	3.1	7.4	10.5	19.5	13.1	5.4	9.8	8.8	14.3
80	22.2	25.0	24.8	16.3	22.0	31.2	13.7	21.7	24.3	29.6	26.3	29.9
81	40.4	35.9	26.9	27.3	39.2	38.3	1.2	34.1	37.8	33.7	33.7	30.7
82	25.1	22.9	25.0	29.4	27.1	16.5	8.5	12.0	24.4	18.3	20.4	15.6
83	4.5	5.8	12.5	19.0	2.3	1.2	45.0	10.9	5.9	6.0	7.1	4.5
84	0.4	0.6	2.9	4.2	0.3	0.1	11.1	6.5	0.8	0.6	1.3	0.7
85 & Above	*	*	0.4	0.5	*	*	0.2	0.1	*	*	0.1	0.1
Average	81.43	81.35	81.65	82.04	81.35	81.05	82.17	81.46	81.45	81.22	81.33	80.99
Tenderable 3/	92.2	92.6	92.2	87.1	72.9	80.4	99.8	85.9	92.5	93.8	94.7	93.6
SAMPLES CLASSED	65,401	504,923	144,539	1,009,097	18,311	78,684	2,852	32,630	13,154	67,630	227,428	1,358,507

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 01, 2022

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	*	*	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	0.3	0.6	-	-	*	*	-	*	-	-	0.1	*
2.7 - 2.9	3.6	2.4	-	*	0.1	*	*	*	*	*	0.3	0.6
3.0 - 3.2	6.3	5.4	1.4	*	0.7	0.3	0.2	0.1	0.1	*	0.7	1.9
3.3 - 3.4	8.5	4.8	0.2	*	0.5	0.6	0.4	0.1	0.4	0.2	8.6	4.3
3.5 - 3.6	8.1	6.7	*	0.1	1.2	1.9	1.2	0.4	0.9	0.5	15.6	8.3
3.7 - 4.2	30.9	39.4	9.2	4.5	38.5	35.3	15.6	10.2	21.7	17.5	40.1	49.2
4.3 - 4.9	42.2	40.4	64.0	65.7	57.4	60.4	67.9	68.7	65.2	70.2	29.8	32.7
5.0 - 5.2	*	0.2	21.3	25.4	1.5	1.5	12.4	17.4	9.5	9.9	2.4	2.2
5.3 & Above	-	-	3.8	4.3	0.1	0.1	2.3	3.1	2.1	1.8	2.4	0.7
Average	4.01	4.05	4.68	4.79	4.31	4.33	4.58	4.67	4.52	4.55	4.06	4.11
Leaf												
1 - 2	52.4	54.2	17.4	14.1	83.7	86.9	36.2	34.7	3.8	5.8	62.2	51.5
3	32.7	37.7	57.8	55.2	14.8	12.2	46.0	48.8	43.7	44.7	16.6	36.4
4	10.5	6.5	21.8	26.8	1.4	0.8	15.6	14.3	43.2	40.1	14.0	9.3
5	3.6	1.3	2.4	3.7	*	*	2.0	2.0	8.6	8.7	5.2	2.2
6	0.7	0.2	0.5	0.2	-	*	0.2	0.2	0.6	0.7	2.0	0.6
7	*	*	0.1	*	-	*	*	*	0.1	0.1	*	*
8	*	*	-	*	-	-	-	*	-	-	-	-
Average	2.63	2.51	3.11	3.20	1.90	1.83	2.81	2.82	3.59	3.54	2.52	2.56
HVI Trash 1/												
00	-	-	-	*	*	0.1	*	*	*	*	-	-
01	15.6	15.7	2.0	1.9	46.7	51.4	10.0	8.6	0.2	0.6	28.0	16.3
02	41.4	45.3	20.9	19.0	38.1	37.0	32.0	32.4	5.4	7.1	33.1	35.7
03	19.5	22.5	31.9	31.2	9.8	8.3	26.6	28.2	18.5	18.7	10.2	23.8
04	10.0	9.0	24.4	24.3	3.6	2.2	16.4	16.4	25.3	24.1	9.0	12.1
05	5.9	4.0	11.6	13.5	1.3	0.7	8.6	8.0	22.3	20.9	7.5	6.0
06	3.0	1.7	4.9	6.1	0.4	0.2	3.8	3.6	14.7	13.9	4.8	3.0
07	1.8	0.8	2.1	2.5	0.1	0.1	1.6	1.6	7.7	7.8	2.8	1.4
08	1.2	0.5	0.9	1.0	*	*	0.6	0.7	3.6	3.8	2.0	0.8
09	0.7	0.3	0.5	0.4	*	*	0.3	0.3	1.4	1.7	1.4	0.5
10	0.5	0.1	0.4	0.1	*	*	0.1	0.1	0.6	0.8	0.8	0.3
11	0.2	0.1	0.2	0.1	-	*	0.1	*	0.2	0.3	0.3	0.1
12	0.1	*	0.1	*	-	*	*	*	0.1	0.1	-	-
13	*	*	*	*	-	-	*	*	*	*	0.1	*
14	-	*	*	*	-	-	*	*	*	*	-	-
15	*	*	*	*	-	-	*	*	*	*	-	-
16	-	-	*	*	-	-	*	*	-	*	-	-
17	-	-	-	*	-	-	*	*	-	*	-	-
18 & Above	-	-	-	*	-	-	*	*	*	*	-	-
Average	0.28	0.26	0.36	0.37	0.18	0.16	0.31	0.31	0.47	0.47	0.29	0.28
UNIFORMITY 2/												
74 & Below	*	*	-	-	-	-	-	-	-	-	-	-
75	*	*	-	*	-	-	-	*	-	-	-	-
76	0.1	0.4	*	*	*	*	*	*	*	*	-	-
77	0.8	3.0	*	0.2	*	0.1	*	*	*	*	*	*
78	10.9	12.3	0.1	1.4	0.6	0.4	0.2	0.3	0.2	0.3	0.4	0.2
79	37.9	31.9	4.1	5.2	6.8	4.6	2.4	1.9	1.4	2.2	11.0	4.8
80	34.4	34.3	10.0	17.9	27.9	19.1	12.7	9.8	8.7	10.2	28.2	24.7
81	14.0	14.9	44.2	34.8	35.3	31.4	30.9	28.4	25.2	26.1	30.4	46.5
82	1.6	3.0	32.1	30.0	21.4	29.4	37.0	37.0	35.9	35.8	27.4	21.1
83	0.3	0.2	7.2	9.3	7.1	12.7	15.2	19.0	23.4	21.3	2.4	2.6
84	-	*	2.2	1.0	0.9	2.2	1.4	3.3	4.7	3.6	0.1	0.1
85 & Above	-	-	0.1	0.1	0.1	0.2	0.1	0.2	0.5	0.3	*	*
Average	80.02	80.00	81.79	81.63	81.40	81.77	81.98	82.16	82.31	82.20	81.24	81.38
Tenderable 3/	67.7	73.3	68.4	64.2	96.9	97.4	81.9	78.0	85.2	85.3	84.0	89.3
SAMPLES CLASSED	12,788	65,575	9,004	343,324	58,903	404,391	85,020	960,883	119,818	648,672	2,930	9,684

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 01, 2022

Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE										
2.4 & Below	-	*	-	-	-	-	*	*	-	-
2.5 - 2.6	0.8	0.5	-	-	*	*	0.3	0.1	-	-
2.7 - 2.9	1.3	1.1	*	*	0.1	*	3.2	0.9	-	-
3.0 - 3.2	5.2	2.7	0.8	0.2	1.5	0.4	8.2	2.7	*	*
3.3 - 3.4	12.2	7.3	1.3	0.4	2.3	0.9	8.9	3.2	0.2	0.2
3.5 - 3.6	15.5	11.7	2.3	0.9	4.4	2.4	10.8	4.4	1.0	1.1
3.7 - 4.2	43.2	45.1	34.4	25.0	39.3	27.8	35.5	33.5	42.5	41.6
4.3 - 4.9	21.4	29.8	55.6	67.6	48.2	60.0	29.3	51.1	54.5	54.5
5.0 - 5.2	0.3	1.6	5.0	5.3	3.6	7.5	2.8	3.5	1.4	2.1
5.3 & Above	0.1	*	0.5	0.6	0.6	0.9	0.8	0.6	0.3	0.5
Average	3.85	4.00	4.35	4.44	4.25	4.42	3.96	4.25	4.30	4.31
Leaf										
1 - 2	24.4	36.6	4.1	3.8	37.9	60.2	35.1	46.2	7.9	7.3
3	48.4	45.9	35.3	36.8	47.5	33.3	42.3	37.8	67.2	61.9
4	22.7	14.7	43.4	43.8	12.3	5.8	15.5	12.4	24.1	28.1
5	3.6	2.3	15.3	14.1	2.0	0.7	4.9	2.8	0.9	2.7
6	0.8	0.4	1.8	1.4	0.2	0.1	1.5	0.6	*	0.1
7	0.1	0.1	0.1	0.1	*	*	0.5	0.1	-	*
8	*	*	-	-	-	-	0.1	*	-	-
Average	3.05	2.76	3.76	3.73	2.75	2.33	2.93	2.63	3.18	3.26
HVI Trash 1/										
00	-	*	-	-	*	*	*	0.1	-	-
01	5.3	12.4	0.4	0.2	9.7	24.1	9.0	16.6	0.2	0.4
02	19.2	25.0	5.4	5.1	30.2	36.6	29.9	30.4	9.5	8.8
03	23.9	24.6	14.6	15.5	28.2	21.6	25.2	22.8	30.7	27.2
04	21.1	17.7	21.8	21.5	16.2	10.2	15.2	14.0	32.1	30.2
05	14.1	10.3	20.6	20.8	8.3	4.4	8.6	7.7	18.1	18.8
06	8.4	5.2	16.0	16.0	4.2	1.9	4.8	4.0	6.6	8.8
07	3.8	2.3	10.3	10.3	1.9	0.8	2.8	2.0	2.1	3.7
08	1.7	1.2	5.8	5.7	0.8	0.3	1.8	1.1	0.5	1.4
09	0.9	0.6	2.8	2.8	0.3	0.1	1.1	0.6	0.1	0.4
10	0.6	0.3	1.4	1.2	0.1	0.1	0.6	0.3	*	0.1
11	0.4	0.2	0.6	0.5	0.1	*	0.4	0.2	*	0.1
12	0.2	0.1	0.3	0.2	*	*	0.2	0.1	-	*
13	0.1	0.1	0.1	0.1	*	*	0.1	0.1	*	*
14	0.1	0.1	*	*	*	*	0.1	*	-	*
15	0.1	*	*	*	*	*	*	*	-	-
16	0.1	*	*	*	*	*	*	*	-	-
17	*	*	*	*	*	*	*	*	-	-
18 & Above	*	*	-	*	*	*	*	*	-	-
Average	0.39	0.33	0.51	0.51	0.31	0.25	0.34	0.30	0.39	0.41
UNIFORMITY 2/										
74 & Below	-	-	-	-	-	-	*	*	-	-
75	*	*	*	*	-	-	0.1	0.1	-	-
76	0.1	0.1	*	*	*	*	0.4	0.5	-	-
77	0.8	1.0	0.1	0.1	0.1	*	2.1	1.8	*	*
78	4.6	4.2	1.0	0.9	0.5	0.3	7.2	5.2	0.1	0.1
79	14.3	13.7	4.9	5.2	5.4	3.2	18.8	14.1	0.4	0.7
80	24.1	23.8	14.3	18.8	20.4	15.1	29.6	29.3	4.6	6.8
81	30.9	28.8	36.5	36.2	41.9	32.5	26.8	32.2	20.1	24.9
82	21.9	24.5	30.9	26.9	27.8	34.2	11.9	14.0	41.1	37.7
83	3.1	3.8	10.2	10.0	3.7	13.3	2.7	2.5	28.6	25.7
84	0.1	0.1	1.8	1.7	0.2	1.3	0.4	0.2	4.7	3.9
85 & Above	*	*	0.2	0.2	*	*	*	*	0.4	0.3
Average	81.04	81.09	81.75	81.65	81.48	81.87	80.64	80.82	82.53	82.38
Tenderable 3/	71.3	78.8	88.0	89.5	86.4	88.7	60.4	73.5	97.7	96.4
SAMPLES CLASSED	19,772	68,665	40,702	215,431	74,377	473,158	236,077	2,052,031	25,271	127,137

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 01, 2022

Color Grade	Leaf	Arizona		California		New Mexico		Texas	
		Week	Season	Week	Season	Week	Season	Week	Season
01	1	49.0	34.8	31.7	40.5	-	2.5	3.1	4.1
	2	10.0	14.7	15.0	19.1	-	7.9	5.3	4.2
	3	-	2.8	0.1	0.1	-	0.1	-	-
	4	-	0.1	-	*	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		58.9	52.4	46.8	59.7	-	10.5	8.3	8.3
02	1	27.3	28.0	12.7	10.8	-	3.9	17.7	16.5
	2	13.2	17.4	30.5	25.1	-	59.1	48.5	52.8
	3	0.4	1.2	4.0	1.9	-	13.5	6.0	5.4
	4	-	0.2	0.1	*	-	0.3	0.1	0.1
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		41.0	46.7	47.3	37.8	-	76.8	72.4	74.8
03	1	*	*	0.1	*	-	*	1.2	1.3
	2	-	0.3	2.6	1.2	-	3.7	9.9	10.1
	3	*	0.2	2.9	1.0	-	6.8	7.3	4.5
	4	-	0.1	0.3	0.1	-	1.6	0.9	0.3
	5	-	-	-	-	-	0.1	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		0.1	0.6	5.8	2.3	-	12.3	19.2	16.2
04	1	-	-	*	*	-	-	-	-
	2	-	*	-	*	-	0.1	*	0.5
	3	-	0.1	*	0.1	-	0.1	*	0.2
	4	-	0.1	*	*	-	0.1	*	*
	5	-	-	-	*	-	0.1	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	0.2	0.1	0.1	-	0.4	0.1	0.7
05	1	-	-	-	-	-	-	-	-
	2	-	-	*	*	-	-	-	*
	3	-	-	-	*	-	-	-	*
	4	-	*	*	*	-	*	-	-
	5	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	*	*	*	-	*	-	*
06	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	-	-	-	-	-	-
07	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	-	-	-	-	-	-
STAPLE									
44 & Shorter		-	0.7	0.5	0.9	-	*	2.0	0.6
46		0.3	1.9	17.8	13.7	-	4.3	15.7	12.8
48		52.6	48.5	43.4	54.4	-	61.7	65.3	60.0
50		46.4	45.9	35.6	29.3	-	32.3	16.9	26.5
52 & Longer		0.8	3.0	2.7	1.7	-	1.6	*	0.1
Average Staple		48.95	48.97	48.45	48.34	-	48.62	47.95	48.25
Average Length		1.42	1.42	1.41	1.41	-	1.42	1.40	1.40
EXTRANEIOUS MATTER									
Bark		-	*	-	*	-	0.1	-	-
Grass		-	-	0.8	0.2	-	0.4	*	0.5
Spindle Twist		-	0.1	0.1	0.1	-	*	0.1	0.1
Preparation		-	-	*	*	-	-	-	0.1
All Other		-	-	*	*	-	-	*	*

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 01, 2022

Quality Designation	Arizona		California		New Mexico		Texas	
	Week	Season	Week	Season	Week	Season	Week	Season
MIKE								
2.4 & Below	-	-	-	-	-	-	-	-
2.5 - 2.6	-	-	-	-	-	-	-	-
2.7 - 2.9	-	-	0.2	*	-	*	0.9	0.3
3.0 - 3.2	-	-	0.3	0.4	-	3.6	4.0	1.5
3.3 - 3.4	-	*	0.3	0.9	-	6.7	2.4	3.2
3.5 - 3.6	-	0.4	3.9	4.2	-	11.1	10.5	6.8
3.7 - 4.2	92.5	83.6	78.1	81.2	-	69.5	70.9	78.1
4.3 - 4.9	7.5	16.0	17.2	13.3	-	9.0	11.4	10.1
5.0 - 5.2	-	-	-	-	-	-	-	-
5.3 & Above	-	-	-	-	-	-	-	-
Average	4.07	4.09	4.05	4.01	-	3.87	3.91	3.94
ALL RANGE MIKE								
2.4 & Below	-	-	-	-	-	-	-	-
2.5	-	-	-	-	-	-	-	-
2.6	-	-	-	-	-	-	-	-
2.7	-	-	-	-	-	-	-	-
2.8	-	-	*	*	-	-	-	*
2.9	-	-	0.2	*	-	*	0.9	0.3
3.0	-	-	0.2	0.1	-	*	2.4	0.7
3.1	-	-	0.1	0.1	-	1.1	0.8	0.3
3.2	-	-	*	0.2	-	2.5	0.8	0.5
3.3	-	-	*	0.3	-	4.8	0.8	1.7
3.4	-	*	0.3	0.6	-	1.9	1.5	1.5
3.5	-	*	1.1	1.1	-	4.1	0.9	2.1
3.6	-	0.4	2.7	3.1	-	7.0	9.6	4.7
3.7	1.4	2.5	4.0	6.3	-	9.9	5.0	7.0
3.8	3.2	4.4	7.6	10.3	-	10.1	10.6	12.5
3.9	13.0	11.5	11.3	14.7	-	15.1	18.7	18.6
4.0	27.2	20.9	17.1	18.5	-	16.3	18.5	17.4
4.1	27.1	19.5	17.3	17.3	-	10.5	13.2	13.2
4.2	20.7	24.8	20.8	14.1	-	7.5	4.8	9.5
4.3	7.3	11.4	12.7	8.5	-	5.1	6.4	4.2
4.4	0.1	3.4	4.2	3.5	-	2.9	2.5	2.3
4.5	*	1.0	0.2	1.0	-	1.0	0.3	2.8
4.6	-	0.2	*	0.3	-	*	0.7	0.4
4.7	-	-	*	*	-	-	0.4	0.1
4.8	-	-	-	*	-	-	1.2	0.3
4.9	-	-	-	*	-	-	-	*
5.0	-	-	-	-	-	-	-	-
5.1	-	-	-	-	-	-	-	-
5.2	-	-	-	-	-	-	-	-
5.3 & Above	-	-	-	-	-	-	-	-
Average	4.07	4.09	4.05	4.01	-	3.87	3.91	3.94
STRENGTH 1/								
36 & Below	-	0.8	0.3	0.2	-	8.7	4.6	2.3
37	-	0.3	1.0	1.6	-	7.8	5.1	3.5
38	-	0.3	3.9	5.0	-	2.6	11.2	10.7
39	0.1	5.0	8.6	5.8	-	1.1	31.0	15.7
40	0.2	3.3	2.5	2.0	-	3.1	13.6	13.0
41	1.8	3.8	1.6	2.9	-	8.1	4.2	8.6
42	13.7	16.9	4.1	6.5	-	14.4	8.4	16.5
43	34.8	28.5	9.2	12.6	-	18.5	11.2	14.4
44	22.5	21.6	15.8	17.2	-	17.0	8.4	11.3
45	15.7	11.6	19.6	19.8	-	11.8	1.8	3.1
46	6.2	4.6	15.0	14.2	-	4.6	0.2	0.6
47	3.8	2.5	11.3	8.7	-	2.0	0.3	0.2
48 & Above	1.3	0.8	7.1	3.5	-	0.3	*	0.2
Average	44.25	43.55	44.51	44.20	-	42.44	40.55	41.41
UNIFORMITY								
83 & Below	-	*	0.4	0.2	-	0.1	1.0	0.4
84	0.2	0.2	5.9	4.6	-	2.0	12.5	4.1
85	6.7	6.7	22.4	17.4	-	20.5	27.7	24.4
86	56.2	48.7	45.4	49.0	-	57.0	55.2	51.4
87	36.5	42.4	23.4	27.0	-	20.1	3.5	19.4
88 & Above	0.4	2.0	2.4	1.9	-	0.3	0.1	0.4
Average	86.74	86.83	86.38	86.49	-	86.42	85.86	86.30
Samples Classed	2,114	7,008	26,626	175,152	-	12,037	2,850	9,449

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.