



State	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
AL	7	70.8	40.3	1,852	23	80.2	66.8	621,374
AR	6	87.4	58.4	29,142	26	85.1	66.4	1,870,825
AZ	7	85.4	68.8	14,808	9	89.3	73.9	190,626
CA	2	96.5	83.5	6,871	11	88.3	73.5	70,622
FL	2	43.1	38.7	845	4	71.0	50.3	106,115
GA	29	78.7	60.9	14,985	55	78.8	59.9	1,824,278
KS	3	6.60	6.30	3,162	3	48.8	31.5	167,168
LA	-	-	-	-	15	77.3	55.2	329,898
MO	4	81.9	56.7	12,310	19	91.2	77.8	880,276
MS*	-	-	-	-	33	77.9	56.2	1,149,588
NC	3	82.4	66.5	516	31	92.1	79.0	786,429
NM*	-	-	-	-	5	89.2	77.6	21,979
OK	5	32.6	25.9	2,816	11	75.7	62.3	163,516
SC	7	88.4	73.8	4,553	11	87.1	70.0	322,192
TN	-	-	-	-	18	86.4	78.1	535,228
TX	52	67.0	54.6	58,381	154	75.7	57.1	3,997,711
VA*	-	-	-	-	4	97.1	86.2	214,888
United States	131	75.3	57.9	151,276	432	80.9	63.5	13,252,713
AMERICAN PIMA								
AZ	2			2,450	2			12,583
CA	3			10,729	11			298,782
NM*	-			-	3			21,831
TX	2			3,677	3			37,155
United States	8			16,973	20			370,351
United States all cotton	138			168,249	441			13,623,068

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 23, 2025

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	-	2.3	5.6	1.7	68.4	79.9	90.7	75.0	-	0.8	0.3	2.0
	3	-	1.7	5.8	1.3	3.3	6.0	1.6	8.5	-	0.4	0.5	1.1
	4	-	0.1	0.2	*	*	0.1	-	1.0	-	*	*	*
	5	-	*	-	*	-	*	-	*	-	-	-	*
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	4.1	11.6	3.0	71.7	85.9	92.3	84.5	-	1.3	0.8	3.2
31	1 - 2	1.5	5.7	14.3	5.4	14.6	6.5	7.4	6.5	-	3.2	2.2	6.4
	3	1.2	22.3	47.2	19.2	10.3	4.4	0.2	1.8	0.4	18.4	5.5	19.5
	4	-	5.0	12.1	4.8	1.9	0.8	-	1.1	-	4.8	0.5	3.1
	5	-	0.2	0.7	0.2	0.3	0.1	-	0.3	-	0.1	-	0.1
	6	-	*	*	*	*	*	-	*	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	2.6	33.2	74.3	29.6	27.1	11.9	7.5	9.7	0.4	26.6	8.2	29.1
41	1 - 2	7.3	1.9	1.3	2.8	0.1	*	0.1	0.4	-	0.9	4.9	2.3
	3	22.3	21.0	6.0	30.2	0.2	*	-	*	9.2	16.6	28.1	23.9
	4	1.6	15.7	3.9	19.6	0.6	0.1	-	*	5.0	19.0	10.2	14.5
	5	-	2.3	0.7	3.0	0.4	0.1	-	*	0.2	3.1	0.7	1.7
	6	-	0.1	0.1	0.3	*	*	-	*	0.1	0.1	-	0.1
	7	-	*	*	*	-	*	-	-	-	*	-	*
	8	-	*	-	-	-	*	-	-	-	-	-	*
Total	----	31.2	41.1	12.0	56.0	1.2	0.3	0.1	0.4	14.6	39.7	43.8	42.4
51	1 - 2	3.0	0.3	*	0.1	-	-	-	*	-	0.1	2.5	0.6
	3	35.4	3.5	1.2	1.9	-	-	-	*	29.2	5.3	21.4	6.9
	4	15.5	3.2	0.4	2.0	-	*	-	-	39.1	11.0	14.4	6.6
	5	3.1	0.9	*	0.7	-	*	-	-	6.6	3.2	1.9	1.6
	6	1.3	0.2	*	0.2	-	*	-	-	0.5	0.3	0.1	0.2
	7	0.2	*	-	*	-	*	-	-	0.1	*	*	*
	8	-	*	-	-	-	-	-	-	-	-	-	*
Total	----	58.5	8.1	1.7	4.9	-	*	-	*	75.5	19.9	40.4	15.9
61	1 - 2	-	*	-	-	-	-	-	*	-	-	-	*
	3	0.5	*	-	*	-	-	-	*	-	*	-	*
	4	2.6	*	-	*	-	-	-	-	-	0.2	-	*
	5	1.3	*	-	*	-	-	-	-	0.1	0.1	*	*
	6	0.1	*	-	*	-	-	-	-	1.2	*	0.1	*
	7	-	*	-	*	-	-	-	-	0.6	*	*	*
	8	-	*	-	-	-	-	-	-	-	-	-	*
Total	----	4.5	*	-	*	-	-	-	*	1.9	0.4	0.1	*
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	*	-	-	-	-	-	-	-	-	-	-
	6	-	*	-	*	-	-	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	*	-	-
Total	----	-	*	-	*	-	-	-	-	-	*	-	*
12 & 22	1 - 2	-	*	-	*	-	1.1	-	2.3	-	*	-	*
	3	-	*	*	*	-	0.4	*	1.3	-	*	*	*
	4	-	*	*	*	-	*	-	0.3	-	-	*	*
	5	-	-	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	0.1	*	*	-	1.5	*	3.9	-	*	*	*
32	1 - 2	0.1	0.1	-	*	-	*	*	0.1	-	*	-	0.1
	3	0.4	1.1	0.1	0.2	-	*	-	0.2	-	0.5	0.1	0.5
	4	-	0.4	0.2	0.1	-	*	-	0.3	-	0.3	*	0.2
	5	-	*	*	*	-	*	-	0.2	-	*	-	*
	6	-	*	-	*	-	*	-	*	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	*
Total	----	0.5	1.7	0.3	0.3	-	0.2	*	0.8	-	0.8	0.2	0.8
42	1 - 2	0.1	0.3	*	0.1	*	*	-	*	-	*	*	0.1
	3	0.2	3.7	*	2.7	-	*	-	*	-	1.1	1.1	2.3
	4	0.1	4.1	*	2.0	-	*	-	*	0.1	2.4	1.4	2.4
	5	-	1.1	-	0.2	-	*	-	*	-	0.6	0.2	0.4
	6	-	0.1	-	*	-	*	-	-	-	*	-	*
	7	-	*	-	*	-	-	-	-	-	*	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.3	9.3	0.1	5.0	*	*	-	*	0.1	4.1	2.7	5.2

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 23, 2025

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	*	-	*	-	-	-	*	-	*	*	*
	3	0.1	0.5	*	0.5	-	-	-	0.1	1.5	0.9	0.6	0.6
	4	0.8	0.9	*	0.6	-	-	-	*	4.9	3.5	2.1	1.5
	5	0.6	0.4	-	0.1	-	-	-	-	0.8	1.5	0.5	0.6
	6	0.5	0.1	-	*	-	-	-	-	0.1	0.2	0.1	0.1
	7	0.2	*	-	-	-	-	-	-	-	*	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	*
Total		----	2.12.0	*1.2		-	-	-0.1		7.36.1		3.32.7	
62	1 - 2	-	-	-	*	-	-	-	*	-	-	-	*
	3	-	*	-	*	-	-	-	*	-	*	*	*
	4	-	*	-	*	-	-	-	-	0.1	0.1	-	*
	5	0.1	*	-	*	-	-	-	-	-	0.1	*	*
	6	-	*	-	*	-	-	-	-	-	*	*	*
	7	-	*	-	-	-	-	-	-	-	*	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	*
Total		----	0.1*	-*		-	-	-*		0.10.3		**	
13 & 23	1 - 2	-	-	-	-	-	0.1	-	*	-	*	-	*
	3	-	*	-	-	-	*	-	0.1	-	*	*	*
	4	-	-	-	-	-	*	-	0.1	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total		----	-*	-	-	-	0.1	-	0.2	-	*	**	*
33	1 - 2	-	*	-	-	-	*	-	*	-	*	-	*
	3	-	*	*	*	-	*	-	*	-	*	-	*
	4	-	*	*	*	-	*	-	0.1	-	*	-	*
	5	-	*	-	-	-	*	-	0.1	-	-	-	*
	6	-	-	-	-	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	*	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total		----	-*	**	*	-	*	-	0.2	-	*	-	*
43	1 - 2	-	*	-	*	-	-	-	*	-	*	-	*
	3	-	0.1	-	*	-	*	-	*	-	*	0.2	0.1
	4	0.1	0.2	*	*	-	*	-	-	-	0.1	0.2	0.1
	5	-	0.1	*	*	-	*	-	-	-	*	-	*
	6	-	*	-	*	-	*	-	-	-	*	-	*
	7	-	-	-	-	-	*	-	*	-	-	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total		----	0.10.4	*0.1		-	*	-	*	-	0.2	0.30.3	
53	1 - 2	-	-	-	*	-	-	-	-	-	-	-	*
	3	-	*	-	*	-	-	-	*	-	0.1	*	*
	4	0.1	*	-	*	-	-	-	-	0.1	0.4	*	0.1
	5	0.1	*	-	*	-	-	-	-	-	0.1	*	0.1
	6	-	*	-	*	-	-	-	-	-	*	-	*
	7	-	*	-	-	-	-	-	-	-	-	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total		----	0.10.1	-*		-	-	-	*	0.10.6		0.10.2	
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	*	-	-	-	-	-	-	-	*	-	*
	5	-	*	-	-	-	-	-	-	-	*	-	*
	6	-	*	-	-	-	-	-	-	-	*	-	*
	7	-	*	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total		----	-*	-	-	-	-	-	-	-	*	-	*
24 - 54	1 - 8	-	*	-	*	-	*	-	*	-	0.1	-	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	-	-	-	-	-	-	-	-	*	-	*
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	-	-	-	-	-	-	-	-	-	-	*
31		0.1	*	-	*	-	*	-	-	-	-	-	*
32		0.3	0.2	-	*	-	*	*	*	-	*	0.1	0.1
33		7.8	2.0	*	0.1	*	0.1	0.3	*	-	0.3	1.2	0.8
34		34.4	7.8	0.3	0.9	*	0.5	0.8	0.4	2.5	3.6	9.6	5.2
35		32.8	16.9	1.9	7.2	0.6	2.4	4.2	3.1	7.9	11.8	24.2	17.2
36		12.9	26.3	14.3	23.3	4.3	9.2	17.0	16.0	3.3	22.4	33.3	29.7
37		6.7	34.4	65.8	57.8	20.3	35.2	52.1	39.9	13.6	32.8	23.2	33.8
38		4.9	9.6	16.0	9.8	35.3	29.1	23.3	18.5	55.4	19.3	7.2	10.4
39		0.2	2.3	1.8	0.9	31.3	17.0	2.2	11.7	17.0	8.0	1.1	2.6
40 & Longer		-	0.4	*	*	8.1	6.5	*	10.3	0.2	1.7	0.1	0.3
Average Staple		34.91	36.23	37.01	36.71	38.19	37.68	36.99	37.52	37.64	36.83	35.93	36.33
Average Length		1.09	1.13	1.15	1.14	1.19	1.18	1.16	1.17	1.18	1.15	1.12	1.13

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE													
For The Week Ending Jan 23, 2025													
Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	-	14.8	-	12.0	5.0	2.8	-	1.7	1.0	0.6	-	62.5
	3	-	15.2	-	5.6	1.8	1.1	-	1.2	3.1	0.5	-	10.4
	4	-	1.4	-	0.2	-	*	-	*	0.6	*	-	0.6
	5	-	*	-	*	-	-	-	*	-	*	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	31.4	-	17.8	6.8	3.9	-	2.9	4.7	1.0	-	73.5
31	1 - 2	-	0.9	-	7.6	19.3	14.7	-	4.3	1.2	4.7	-	7.1
	3	-	5.9	-	25.3	25.1	31.2	-	19.4	13.2	18.6	-	8.8
	4	-	3.7	-	6.6	0.9	3.9	-	7.1	2.9	6.3	-	4.7
	5	-	0.7	-	0.3	*	0.1	-	0.4	0.2	0.5	-	1.4
	6	-	*	-	*	-	*	-	*	-	*	-	0.1
	7	-	*	-	*	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	*	-	-
Total	----	-	11.1	-	39.8	45.3	49.9	-	31.2	17.4	30.2	-	22.1
41	1 - 2	0.1	*	-	0.4	1.6	5.0	-	0.9	5.2	2.4	-	0.2
	3	3.8	0.5	-	13.3	22.0	26.7	-	19.0	23.1	27.4	-	1.0
	4	6.4	1.3	-	19.0	11.0	9.2	-	25.4	27.3	26.8	-	1.1
	5	1.0	0.6	-	4.4	0.6	0.6	-	6.2	7.9	5.7	-	0.5
	6	*	0.1	-	0.2	-	*	-	0.5	1.6	0.5	-	0.1
	7	-	*	-	*	-	-	-	*	0.2	0.1	-	-
	8	-	*	-	*	-	-	-	-	-	*	-	-
Total	----	11.4	2.6	-	37.3	35.2	41.5	-	52.0	65.3	63.0	-	2.9
51	1 - 2	-	*	-	0.1	0.1	*	-	*	-	*	-	-
	3	-	0.4	-	0.5	1.4	0.4	-	0.9	2.3	0.7	-	*
	4	*	1.1	-	0.9	0.7	0.3	-	2.8	6.4	1.9	-	0.1
	5	0.2	1.2	-	0.3	0.1	0.1	-	1.4	1.0	1.2	-	0.1
	6	0.3	0.5	-	*	-	*	-	0.2	1.2	0.3	-	*
	7	0.1	0.2	-	*	-	-	-	*	-	0.1	-	-
	8	-	0.1	-	*	-	-	-	-	-	*	-	-
Total	----	0.6	3.4	-	1.8	2.3	0.8	-	5.3	10.9	4.2	-	0.3
61	1 - 2	-	-	-	-	-	*	-	*	-	-	-	-
	3	-	-	-	*	*	*	-	*	-	-	-	-
	4	-	-	-	*	*	*	-	*	-	-	-	-
	5	-	-	-	-	*	*	-	*	-	*	-	-
	6	-	-	-	*	0.2	*	-	*	-	*	-	-
	7	-	*	-	-	0.1	*	-	*	-	*	-	-
	8	-	*	-	-	-	-	-	-	-	*	-	-
Total	----	-	*	-	*	0.3	*	-	*	-	*	-	-
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	*	-	-	-	-
	5	-	-	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	*	-	-
Total	----	-	-	-	-	-	-	-	*	-	*	-	-
12 & 22	1 - 2	-	4.2	-	*	-	*	-	*	-	*	-	0.2
	3	-	6.0	-	0.1	*	*	-	*	-	*	-	0.5
	4	-	1.0	-	*	-	*	-	*	-	*	-	0.1
	5	-	*	-	*	-	-	-	*	-	*	-	*
	6	-	*	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	11.2	-	0.1	*	*	-	0.1	-	*	-	0.8
32	1 - 2	-	0.1	-	*	0.1	*	-	0.1	-	*	-	-
	3	-	1.6	-	0.4	2.2	0.3	-	0.3	0.4	0.1	-	0.1
	4	*	1.5	-	0.2	1.1	0.1	-	0.2	0.4	0.1	-	0.1
	5	-	0.4	-	*	*	*	-	*	-	*	-	*
	6	-	0.1	-	*	-	-	-	*	-	*	-	-
	7	-	*	-	-	-	-	-	-	-	*	-	-
	8	-	*	-	-	-	-	-	-	-	*	-	-
Total	----	*	3.8	-	0.6	3.3	0.4	-	0.6	0.8	0.3	-	0.1
42	1 - 2	*	*	-	*	0.1	0.2	-	0.1	-	*	-	*
	3	5.9	1.3	-	0.7	3.1	2.0	-	1.8	-	0.2	-	*
	4	15.7	3.2	-	1.0	2.3	0.9	-	2.7	-	0.4	-	*
	5	6.2	1.6	-	0.4	0.3	0.1	-	0.8	-	0.1	-	*
	6	0.4	0.3	-	*	-	*	-	0.1	0.2	*	-	-
	7	*	0.1	-	*	-	-	-	*	-	*	-	-
	8	-	*	-	*	-	-	-	-	-	*	-	-
Total	----	28.3	6.6	-	2.1	5.8	3.1	-	5.6	0.2	0.9	-	0.1

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 23, 2025

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	*	-	*	-	*	-	*	-	-	-	-
	3	0.2	0.6	-	0.1	0.1	0.2	-	0.3	-	*	-	0.1
	4	1.7	2.7	-	0.2	0.2	0.1	-	1.1	-	0.1	-	0.1
	5	7.2	4.8	-	0.1	*	*	-	0.6	-	0.1	-	*
	6	7.7	3.0	-	*	-	*	-	0.1	-	*	-	-
	7	4.3	1.3	-	*	-	-	-	*	0.2	*	-	-
	8	0.9	0.4	-	*	-	-	-	-	-	*	-	-
Total		----	22.012.7	-	0.4	0.4	0.3	-	2.1	0.2	0.2	-	0.1
62	1 - 2	-	-	-	-	-	-	-	*	-	-	-	-
	3	-	-	-	*	-	*	-	*	-	-	-	-
	4	-	*	-	-	-	*	-	*	-	-	-	-
	5	-	*	-	*	-	*	-	*	-	-	-	-
	6	-	*	-	*	0.1	*	-	*	-	*	-	-
	7	*	*	-	-	0.1	*	-	*	-	*	-	-
	8	0.2	0.1	-	-	-	-	-	-	-	*	-	-
Total		----	0.30.1	-	*	0.2	*	-	*	-	*	-	-
13 & 23	1 - 2	-	0.1	-	*	-	*	-	-	-	-	-	*
	3	-	0.2	-	*	-	*	-	*	-	*	-	*
	4	-	0.1	-	*	-	-	-	*	-	-	-	-
	5	-	*	-	-	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total		----	-0.4	-	*	-	*	-	*	-	*	-	*
33	1 - 2	-	*	-	*	-	*	-	*	-	*	-	*
	3	-	0.1	-	*	*	*	-	*	-	*	-	*
	4	-	0.2	-	*	*	*	-	*	0.2	*	-	-
	5	-	0.1	-	*	-	*	-	*	0.2	*	-	-
	6	-	*	-	-	-	-	-	-	-	*	-	-
	7	-	*	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	*	-	-
Total		----	-0.4	-	0.1	*	*	-	*	0.4	*	-	*
43	1 - 2	-	*	-	*	-	*	-	*	-	*	-	-
	3	0.3	0.4	-	*	0.1	*	-	*	-	*	-	-
	4	1.7	1.0	-	*	0.1	*	-	*	0.2	*	-	-
	5	1.6	0.6	-	*	0.1	*	-	*	-	*	-	*
	6	0.2	0.1	-	*	-	*	-	*	-	*	-	-
	7	-	*	-	*	-	-	-	-	-	*	-	-
	8	-	*	-	-	-	-	-	-	-	*	-	-
Total		----	3.82.1	-	*	0.3	0.1	-	0.1	0.2	0.1	-	*
53	1 - 2	-	*	-	-	-	-	-	*	-	-	-	-
	3	0.5	0.3	-	*	-	*	-	*	-	*	-	-
	4	5.5	2.3	-	*	-	*	-	*	-	*	-	-
	5	6.0	4.3	-	*	-	*	-	*	-	*	-	-
	6	9.2	3.4	-	*	-	*	-	*	-	*	-	-
	7	7.5	1.6	-	-	-	-	-	*	-	*	-	-
	8	1.9	0.4	-	*	-	-	-	-	-	*	-	-
Total		----	30.612.2	-	*	-	*	-	0.1	-	*	-	-
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	*	-	-	-	-	-	*	-	-	-	-
	5	-	*	-	-	-	-	-	*	-	-	-	-
	6	0.3	0.1	-	-	-	-	-	*	-	-	-	-
	7	0.3	*	-	-	-	-	-	*	-	-	-	-
	8	0.6	0.1	-	-	-	-	-	-	-	-	-	-
Total		----	1.20.2	-	-	-	-	-	*	-	-	-	-
24 - 54	1 - 8	1.6	1.7	-	*	-	*	-	*	-	*	-	-
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	0.2	0.1	-	-	-	-	-	-	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	*	-	-	-	-	-	-	-	-	-	-
30		-	*	-	-	-	-	-	-	-	-	-	-
31		-	0.3	-	-	-	-	-	*	-	-	-	-
32		-	1.3	-	*	*	*	-	*	-	-	-	*
33		0.4	4.6	-	0.1	*	0.1	-	0.3	-	0.2	-	0.1
34		18.0	13.2	-	0.7	0.2	1.0	-	2.9	0.4	4.3	-	1.3
35		5.0	21.6	-	7.4	2.3	7.5	-	14.1	3.5	19.2	-	7.5
36		26.8	24.3	-	22.6	23.1	25.3	-	28.9	23.6	39.9	-	21.5
37		36.9	27.4	-	40.3	69.1	56.0	-	41.0	50.4	31.5	-	35.3
38		12.2	6.8	-	18.4	5.1	9.5	-	10.4	12.0	4.2	-	23.1
39		0.7	0.5	-	8.2	0.1	0.6	-	2.1	8.7	0.6	-	7.8
40 & Longer		-	*	-	2.3	*	*	-	0.2	1.4	0.1	-	3.3
Average Staple		36.21	35.74	-	37.02	36.77	36.67	-	36.48	37.02	36.14	-	37.12
Average Length		1.13	1.11	-	1.16	1.14	1.14	-	1.14	1.16	1.13	-	1.16

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE											
For The Week Ending Jan 23, 2025											
Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	11.9	48.5	1.1	1.0	-	3.5	11.0	24.8	-	0.3
	3	2.1	9.0	1.2	1.1	-	1.9	5.3	8.4	-	0.4
	4	*	0.2	-	0.1	-	*	0.4	0.6	-	*
	5	-	*	-	-	-	*	*	*	-	*
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	14.0	57.6	2.4	2.2	-	5.5	16.7	33.8	-	0.8
31	1 - 2	0.3	1.6	1.3	3.9	-	13.0	9.1	4.1	-	7.6
	3	0.4	2.4	11.4	22.7	-	22.5	24.0	16.1	-	27.8
	4	-	0.4	0.8	9.0	-	3.2	9.8	7.2	-	5.9
	5	-	*	-	0.5	-	0.1	1.8	1.0	-	0.3
	6	-	-	-	*	-	*	0.1	0.1	-	*
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	0.7	4.3	13.6	36.1	-	38.9	44.9	28.5	-	41.7
41	1 - 2	1.5	1.0	2.8	0.9	-	8.0	0.8	0.4	-	4.7
	3	8.9	8.3	15.7	17.5	-	24.1	4.6	6.1	-	31.5
	4	5.5	2.9	12.5	22.4	-	6.9	7.8	7.5	-	17.2
	5	1.1	0.5	2.2	5.1	-	0.5	5.1	2.8	-	2.4
	6	*	0.1	0.1	0.3	-	*	2.5	1.1	-	0.1
	7	-	-	-	*	-	-	1.0	0.5	-	*
	8	-	-	-	*	-	-	0.2	0.2	-	*
Total	----	17.1	12.8	33.4	46.2	-	39.5	22.0	18.6	-	56.0
51	1 - 2	-	*	1.7	0.1	-	0.4	*	*	-	*
	3	0.3	0.2	16.7	3.7	-	2.1	*	0.3	-	0.3
	4	0.3	0.2	27.1	7.2	-	0.8	0.1	0.6	-	0.3
	5	1.1	0.2	3.8	2.0	-	0.1	0.2	0.3	-	0.1
	6	0.4	*	0.2	0.2	-	*	0.3	0.1	-	*
	7	0.1	*	*	*	-	-	0.4	0.1	-	*
	8	0.1	*	-	*	-	-	0.5	0.2	-	-
Total	----	2.2	0.7	49.5	13.2	-	3.4	1.4	1.6	-	0.7
61	1 - 2	-	-	-	-	-	*	-	-	-	-
	3	-	-	-	*	-	*	-	*	-	-
	4	-	-	-	*	-	*	-	*	-	-
	5	-	-	-	*	-	*	-	*	-	-
	6	-	-	-	*	-	-	-	*	-	-
	7	-	-	-	*	-	-	-	*	-	-
	8	-	-	-	*	-	-	*	*	-	-
Total	----	-	-	-	*	-	*	*	*	-	-
71	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	-	-	-	-	*	-	-
	5	-	-	-	-	-	-	-	*	-	-
	6	-	-	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	-	-	-	*	-	-
12 & 22	1 - 2	0.9	3.4	-	*	-	*	0.6	3.8	-	*
	3	1.8	1.7	-	*	-	*	0.7	2.2	-	*
	4	0.1	0.2	-	*	-	*	0.1	0.3	-	*
	5	-	*	-	-	-	*	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	2.9	5.3	-	*	-	*	1.4	6.3	-	*
32	1 - 2	1.7	0.8	-	*	-	0.2	0.7	0.5	-	*
	3	1.5	1.2	0.1	0.1	-	0.6	2.2	2.0	-	0.3
	4	0.2	0.3	0.1	0.1	-	0.1	1.2	1.2	-	0.1
	5	-	*	-	*	-	*	0.3	0.3	-	*
	6	-	*	-	*	-	*	*	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	3.4	2.4	0.1	0.3	-	0.9	4.5	4.2	-	0.4
42	1 - 2	4.2	1.0	-	*	-	1.9	*	*	-	*
	3	19.9	6.2	0.1	0.2	-	6.3	0.7	1.0	-	0.1
	4	15.9	4.3	0.4	0.6	-	1.5	1.6	1.9	-	0.1
	5	5.8	0.9	0.1	0.3	-	0.1	1.3	0.8	-	*
	6	0.2	0.1	*	*	-	*	0.3	0.2	-	*
	7	-	*	-	*	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	46.1	12.5	0.5	1.1	-	9.8	4.1	3.9	-	0.3

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE											
For The Week Ending Jan 23, 2025											
Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	*	-	*	-	0.2	*	*	-	*
	3	0.4	0.1	0.1	0.1	-	0.9	0.1	0.1	-	*
	4	1.2	0.4	0.2	0.5	-	0.6	0.5	0.4	-	*
	5	3.3	0.4	0.1	0.3	-	0.1	0.9	0.4	-	*
	6	2.0	0.2	-	*	-	*	0.7	0.1	-	-
	7	1.1	*	-	*	-	-	0.3	*	-	-
	8	0.5	*	-	-	-	-	0.1	*	-	-
Total	----	8.5	1.1	0.5	0.9	-	1.8	2.6	1.0	-	*
62	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	*	-	*	-	*	-	*	-	-
	4	-	-	-	*	-	*	-	*	-	-
	5	-	-	-	*	-	*	-	*	-	-
	6	-	-	-	*	-	-	-	*	-	-
	7	-	-	-	*	-	-	-	*	-	-
	8	-	-	-	-	-	-	*	*	-	*
Total	----	-	*	-	*	-	*	*	*	-	*
13 & 23	1 - 2	0.1	0.2	-	*	-	-	*	0.2	-	*
	3	0.2	0.2	-	*	-	-	0.1	0.2	-	*
	4	*	*	-	*	-	-	0.1	*	-	*
	5	-	-	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	0.4	0.5	-	*	-	-	0.2	0.5	-	*
33	1 - 2	-	0.2	-	-	-	*	*	0.1	-	*
	3	0.3	0.4	-	*	-	*	0.3	0.3	-	0.1
	4	0.4	0.1	-	*	-	*	0.5	0.2	-	*
	5	0.1	*	-	*	-	-	0.2	*	-	*
	6	*	*	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	0.8	0.7	-	*	-	*	1.1	0.7	-	0.1
43	1 - 2	-	0.1	-	*	-	*	-	*	-	*
	3	0.1	0.6	-	*	-	0.1	*	0.1	-	*
	4	1.4	0.4	-	*	-	*	0.3	0.2	-	*
	5	0.1	0.1	-	*	-	*	0.4	0.1	-	*
	6	-	*	-	*	-	-	0.1	*	-	*
	7	-	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	1.6	1.3	-	0.1	-	0.1	0.8	0.4	-	*
53	1 - 2	-	*	-	-	-	-	-	*	-	-
	3	0.1	*	*	*	-	-	*	*	-	-
	4	0.6	0.1	-	*	-	*	0.1	0.1	-	-
	5	1.1	0.1	*	*	-	-	0.1	0.1	-	-
	6	0.3	0.1	*	*	-	-	*	0.1	-	-
	7	-	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	2.1	0.2	0.1	*	-	*	0.3	0.3	-	-
63	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	-	-	-	-	*	-	-
	5	*	*	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	*	*	-	-	-	-	*	*	-	-
24 - 54	1 - 8	0.1	0.5	-	*	-	*	0.1	0.2	-	*
25 - 35	1 - 8	-	-	-	-	-	-	-	*	-	-
81 - 85	1 - 8	-	*	-	-	-	-	*	*	-	-
STAPLE											
28 & Shorter		-	*	-	-	-	-	-	*	-	-
29		-	0.1	-	-	-	-	*	*	-	-
30		-	0.2	-	-	-	-	0.3	0.1	-	-
31		-	0.7	-	-	-	*	1.3	0.6	-	-
32		*	1.4	-	-	-	*	2.6	2.1	-	-
33		0.9	3.3	2.2	0.2	-	0.2	9.3	5.4	-	0.2
34		10.0	9.0	8.4	2.6	-	2.0	17.2	12.3	-	2.8
35		30.2	18.3	16.0	14.6	-	13.2	23.2	19.7	-	16.2
36		19.0	24.8	27.3	33.4	-	35.5	22.8	21.8	-	45.9
37		28.6	25.4	34.3	37.0	-	42.3	18.2	24.4	-	32.8
38		10.7	10.9	10.0	9.5	-	6.0	3.2	9.6	-	1.9
39		0.6	5.3	1.7	2.3	-	0.8	1.6	3.4	-	0.2
40 & Longer		*	0.6	*	0.4	-	0.1	0.3	0.5	-	*
Average Staple		35.99	36.08	36.20	36.44	-	36.39	35.26	35.83	-	36.15
Average Length		1.12	1.13	1.13	1.14	-	1.13	1.10	1.12	-	1.13

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 23, 2025

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	1.3	0.3	*	0.1	*	0.1	-	0.1	1.4	0.9	0.7	1.1
Bark - Level 2	-	-	-	*	-	-	-	-	-	-	-	-
Grass - Level 1	0.9	0.1	*	*	*	0.1	0.1	0.2	0.5	0.1	0.4	0.1
Grass - Level 2	-	*	-	-	-	-	-	-	-	-	-	*
Prep - Level 1	-	*	-	*	-	*	-	-	-	*	-	*
Prep - Level 2	-	-	-	*	-	-	-	-	-	-	-	*
Seed Coat - Level 1	7.5	1.3	1.4	0.3	0.1	0.1	-	-	49.0	5.6	10.1	2.7
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	*	-	*	-	-	-	-	-	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	-	-	-	-	-	-	-	-	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	-	*	*	*	*	*	*	*	-	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	-	-	-	-	-	-	-	-	-	-	-
23	-	*	-	-	-	-	-	-	-	-	-	*
24	-	*	*	*	*	*	*	*	-	*	*	*
25	0.2	0.1	*	*	*	0.1	0.5	0.1	-	*	0.1	0.1
26	1.8	0.8	0.3	0.2	0.5	0.2	0.5	0.1	-	0.1	3.0	0.5
27	7.7	4.0	1.3	2.7	2.1	0.9	0.8	0.7	-	0.7	11.1	2.8
28	24.2	14.3	10.9	21.0	5.4	3.5	4.1	3.1	5.9	3.0	19.4	10.2
29	55.8	28.5	35.2	40.5	4.0	7.2	11.9	10.2	8.0	12.1	28.1	23.3
30	9.2	26.5	27.1	23.8	8.3	13.7	26.0	22.1	13.7	24.5	18.9	28.0
31	1.0	16.1	15.5	8.8	21.2	20.6	32.1	25.3	54.7	25.5	12.0	19.8
32	0.1	6.7	7.2	2.3	22.1	19.8	16.2	11.0	16.3	18.5	5.3	9.8
33	-	2.1	2.1	0.5	16.7	14.4	2.3	6.6	0.6	7.6	1.6	3.9
34	-	0.6	0.3	0.1	8.9	10.3	5.0	7.3	0.7	5.1	0.4	1.3
35	-	0.1	*	*	8.7	5.8	0.5	5.1	-	2.3	0.1	0.3
36	-	*	*	*	1.9	2.3	*	4.6	-	0.5	-	0.1
37	-	*	-	*	0.1	0.6	-	2.4	-	0.1	-	*
38	-	*	-	-	*	0.3	-	0.9	-	*	-	*
39	-	-	-	-	-	0.1	-	0.2	-	*	-	*
40 & Above	-	*	-	-	*	*	-	*	-	-	-	*
Average	29.07	30.11	30.21	29.69	32.29	32.22	31.12	32.01	31.20	31.46	29.61	30.49
Mike												
2.4 & Below	-	-	-	-	*	*	-	-	-	-	-	*
2.5	-	-	-	*	*	*	-	*	-	-	-	-
2.6	-	-	-	*	*	*	-	*	-	-	-	*
2.7	-	*	-	*	*	*	-	0.1	-	-	-	*
2.8	-	*	-	*	0.1	*	-	*	-	-	-	*
2.9	-	*	-	*	*	*	-	*	-	-	-	*
3.0	-	*	-	*	0.6	0.1	-	0.2	-	-	-	*
3.1	-	*	-	*	0.7	0.2	-	0.4	0.1	*	-	*
3.2	-	0.1	-	*	0.8	0.3	*	0.5	-	*	0.1	*
3.3	-	0.1	*	*	1.5	0.5	0.6	0.8	-	*	0.1	*
3.4	-	0.2	-	0.1	1.6	0.6	0.7	1.5	0.1	*	0.2	*
3.5	0.1	0.4	*	0.1	1.5	0.7	2.6	1.6	0.2	*	0.2	0.1
3.6	0.9	0.7	*	0.2	2.0	1.1	8.2	3.0	0.2	0.1	0.5	0.1
3.7	1.7	1.4	*	0.4	3.7	1.8	9.9	4.4	5.0	0.2	0.6	0.3
3.8	1.8	2.4	0.1	0.7	5.1	3.2	14.9	6.8	1.5	0.4	0.7	0.6
3.9	3.5	3.7	1.7	1.4	8.4	4.6	20.1	9.3	3.0	0.7	1.6	1.0
4.0	2.4	5.3	1.6	2.4	5.7	5.3	15.0	10.9	0.5	0.8	3.1	1.8
4.1	0.2	7.5	2.6	3.6	8.4	7.2	11.8	10.7	2.2	1.8	4.8	3.2
4.2	4.6	9.5	4.3	5.2	8.0	8.7	7.4	9.1	11.5	3.1	7.0	5.1
4.3	9.1	10.2	5.5	7.5	7.7	9.3	3.1	7.5	10.4	4.5	9.2	7.5
4.4	3.9	10.8	9.7	9.9	6.2	10.7	0.8	6.1	6.7	8.3	10.3	10.3
4.5	7.8	10.2	8.1	12.5	5.6	8.9	0.9	5.0	15.6	10.9	9.1	12.5
4.6	11.3	10.1	12.1	14.6	5.0	8.1	*	4.1	12.2	14.6	11.1	13.6
4.7	6.4	9.0	13.8	14.3	5.1	7.6	0.7	4.2	17.4	15.7	16.3	13.5
4.8	23.3	7.1	16.5	11.3	8.2	7.2	0.9	3.6	2.8	12.7	10.4	11.4
4.9	7.2	5.1	13.0	7.7	4.9	5.5	0.3	3.4	1.7	10.2	7.0	8.3
5.0	4.5	3.1	7.5	4.4	3.3	3.2	0.2	2.5	2.5	7.8	3.9	5.4
5.1	3.2	1.8	2.3	2.2	1.8	2.1	0.7	2.1	3.6	4.3	2.8	3.0
5.2	-	0.9	0.7	0.9	1.3	1.2	1.1	1.2	1.2	2.5	0.7	1.3
5.3	2.7	0.4	0.3	0.3	1.6	1.1	*	0.9	1.5	1.0	0.2	0.6
5.4	5.4	0.1	0.1	0.1	0.8	0.6	*	*	-	0.2	-	0.2
5.5 & Above	-	*	*	*	0.1	0.3	-	*	-	0.1	-	0.1
Average	4.63	4.43	4.64	4.57	4.29	4.41	3.95	4.21	4.47	4.67	4.53	4.59

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 23, 2025

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	77.0	24.5	-	*	0.1	*	-	0.2	3.7	2.6	-	3.2
Bark - Level 2	-	-	-	*	-	-	-	*	-	-	-	-
Grass - Level 1	-	0.1	-	0.1	-	*	-	*	-	0.2	-	0.6
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	*	-	-	*	*	-	*	-	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	0.1	-	0.2	0.3	*	-	0.9	-	*	-	-
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	-	-	*	-	*	-	-	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	*	-	-	-	*	-	*	-	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	-	*	-	*	-	*	-	*	0.2	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	*	*	-	-	-	-	-	-	-	-	-	-
23	-	*	-	-	-	-	-	-	-	-	-	-
24	-	0.1	-	*	-	*	-	*	-	*	-	-
25	-	0.2	-	*	-	*	-	0.1	0.6	0.2	-	*
26	0.2	0.7	-	*	*	0.1	-	0.5	2.7	2.5	-	0.1
27	1.8	2.2	-	0.3	2.0	1.8	-	3.3	15.5	17.0	-	1.5
28	19.9	5.3	-	3.4	24.4	17.0	-	14.8	29.7	36.5	-	6.9
29	13.5	10.1	-	19.2	43.4	40.5	-	31.4	24.4	27.2	-	18.4
30	22.0	18.2	-	33.3	24.0	27.6	-	29.7	21.3	11.6	-	21.6
31	18.1	21.3	-	28.9	5.5	9.4	-	14.2	5.2	3.9	-	23.4
32	16.1	19.1	-	10.4	0.7	2.8	-	4.5	0.4	1.0	-	14.4
33	5.6	14.6	-	3.0	*	0.6	-	1.3	0.2	0.2	-	7.8
34	2.0	6.2	-	1.1	-	0.1	-	0.4	-	*	-	4.3
35	0.7	1.3	-	0.3	-	*	-	0.1	-	*	-	1.1
36	0.1	0.4	-	*	-	*	-	*	-	-	-	0.3
37	*	0.1	-	*	-	*	-	*	-	-	-	*
38	-	*	-	*	-	-	-	-	-	-	-	*
39	-	*	-	-	-	-	-	-	-	-	-	-
40 & Above	-	*	-	-	-	-	-	-	-	-	-	*
Average	30.63	31.51	-	30.82	29.55	29.82	-	30.01	29.07	28.90	-	31.08
Mike												
2.4 & Below	-	*	-	-	-	-	-	*	-	-	-	-
2.5	-	0.1	-	-	-	-	-	*	-	*	-	-
2.6	0.1	0.1	-	-	-	-	-	*	-	*	-	-
2.7	0.4	0.2	-	*	-	*	-	*	-	*	-	*
2.8	0.7	0.4	-	*	-	*	-	*	-	*	-	0.1
2.9	0.8	0.7	-	*	-	*	-	*	1.0	*	-	0.1
3.0	0.7	1.1	-	*	-	*	-	*	1.7	*	-	0.2
3.1	0.4	1.9	-	*	-	*	-	*	2.1	*	-	0.2
3.2	0.6	2.0	-	*	-	0.1	-	*	1.7	0.1	-	0.9
3.3	0.9	2.5	-	0.1	-	0.1	-	*	1.9	0.2	-	1.4
3.4	2.8	2.1	-	0.1	*	0.2	-	*	2.5	0.3	-	1.6
3.5	3.1	3.6	-	0.1	*	0.3	-	0.1	3.9	0.4	-	2.1
3.6	3.4	4.9	-	0.2	0.1	0.5	-	0.1	2.1	0.7	-	2.5
3.7	7.4	5.6	-	0.2	0.3	0.9	-	0.3	3.5	1.0	-	5.3
3.8	10.0	7.1	-	0.4	0.8	1.6	-	0.6	5.2	1.7	-	6.0
3.9	13.6	8.2	-	0.9	0.8	2.4	-	0.9	8.5	2.8	-	6.7
4.0	16.9	7.8	-	1.6	2.7	3.5	-	1.7	7.6	4.5	-	7.1
4.1	9.8	8.7	-	2.4	3.2	5.0	-	2.7	8.7	6.7	-	7.1
4.2	9.3	8.7	-	4.2	4.7	7.4	-	4.1	7.8	8.6	-	9.3
4.3	6.3	8.1	-	6.5	7.3	10.1	-	6.4	6.8	11.1	-	7.6
4.4	7.9	7.1	-	8.7	10.6	12.3	-	8.6	4.1	13.2	-	6.9
4.5	2.1	5.5	-	9.3	11.3	13.5	-	10.8	12.6	14.0	-	8.4
4.6	0.7	3.8	-	10.4	10.5	13.4	-	13.3	5.4	12.7	-	8.2
4.7	1.7	3.2	-	12.3	11.8	10.7	-	14.1	2.3	9.7	-	7.4
4.8	0.3	2.4	-	12.9	14.3	8.0	-	12.7	5.0	6.3	-	3.5
4.9	*	2.0	-	9.2	11.3	4.9	-	9.8	2.5	3.4	-	3.3
5.0	-	1.3	-	6.6	7.8	2.9	-	7.0	2.9	1.6	-	2.9
5.1	-	0.6	-	5.2	2.5	1.2	-	3.8	-	0.6	-	0.7
5.2	-	0.1	-	3.6	0.2	0.6	-	1.8	-	0.2	-	0.5
5.3	-	*	-	2.8	*	0.2	-	0.8	-	*	-	0.1
5.4	-	*	-	1.4	*	0.1	-	0.3	-	*	-	0.1
5.5 & Above	-	-	-	0.8	-	*	-	0.1	-	*	-	*
Average	3.96	4.04	-	4.67	4.60	4.47	-	4.63	4.12	4.41	-	4.24

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE										
For The Week Ending Jan 23, 2025										
Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter										
Bark - Level 1	33.3	3.6	3.5	3.2	-	*	15.1	5.3	-	1.3
Bark - Level 2	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	-	*	-	0.3	-	*	0.2	0.6	-	*
Grass - Level 2	-	-	-	-	-	-	-	*	-	-
Prep - Level 1	-	*	-	*	-	-	-	*	-	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	*	*	0.6	0.2	-	*	*	0.1	-	*
Seed Coat - Level 2	-	-	-	-	-	-	-	*	-	-
Oil - Level 1	-	*	-	-	-	-	*	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	-	-	-	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	-	*	0.1	*	-	*	*	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/										
22 & Below	-	0.1	-	-	-	-	0.1	0.1	-	-
23	*	0.2	-	-	-	-	0.2	0.2	-	-
24	0.4	0.4	-	-	-	*	0.6	0.4	-	-
25	3.3	0.8	0.2	0.1	-	0.1	1.1	1.0	-	0.5
26	2.0	1.8	2.0	0.7	-	1.0	2.4	2.3	-	7.2
27	12.1	4.2	13.3	4.2	-	8.2	6.6	5.2	-	28.5
28	22.6	7.8	23.3	15.1	-	30.0	13.7	10.2	-	39.2
29	17.4	12.0	25.8	27.4	-	36.1	18.5	16.0	-	18.4
30	15.1	13.5	17.8	26.2	-	18.4	20.0	20.1	-	5.3
31	10.0	12.9	10.6	15.5	-	4.7	16.8	19.0	-	0.9
32	14.3	15.8	4.9	7.5	-	1.1	11.7	12.6	-	0.1
33	2.8	17.4	1.9	2.6	-	0.3	5.4	6.9	-	*
34	-	9.4	0.2	0.6	-	*	1.9	3.5	-	*
35	-	2.9	*	0.1	-	*	0.7	1.6	-	*
36	-	0.7	-	*	-	*	0.2	0.6	-	-
37	-	0.2	-	-	-	-	*	0.2	-	-
38	-	*	-	-	-	-	*	*	-	-
39	-	*	-	-	-	-	-	*	-	-
40 & Above	-	-	-	-	-	-	*	*	-	-
Average	29.69	31.45	29.50	30.13	-	29.27	30.28	30.66	-	28.33
Mike										
2.4 & Below	-	*	-	-	-	-	*	*	-	-
2.5	-	*	-	-	-	-	0.1	*	-	-
2.6	-	*	-	-	-	-	0.1	0.1	-	-
2.7	-	*	-	-	-	*	0.3	0.1	-	*
2.8	-	*	-	*	-	*	0.4	0.2	-	*
2.9	-	*	-	*	-	*	0.7	0.3	-	*
3.0	-	0.1	-	*	-	*	0.6	0.4	-	0.1
3.1	-	0.2	-	*	-	*	0.8	0.6	-	*
3.2	-	0.3	-	*	-	0.1	1.4	0.9	-	0.1
3.3	-	0.5	-	*	-	0.2	1.7	1.1	-	0.2
3.4	-	0.8	*	*	-	0.3	2.3	1.4	-	0.5
3.5	-	1.0	0.1	0.1	-	0.4	3.6	1.8	-	0.8
3.6	*	2.4	0.1	0.2	-	0.7	4.0	2.3	-	1.5
3.7	1.3	3.2	0.4	0.3	-	1.3	4.2	2.9	-	3.0
3.8	2.2	4.0	0.4	0.8	-	2.4	4.7	3.6	-	5.2
3.9	1.5	6.1	0.8	1.2	-	3.8	5.8	4.4	-	7.4
4.0	3.3	7.6	1.6	2.4	-	5.9	6.6	5.3	-	9.3
4.1	10.4	9.0	2.2	4.0	-	8.5	6.5	6.4	-	11.0
4.2	15.4	10.2	4.9	7.0	-	11.0	8.5	7.6	-	13.5
4.3	13.4	10.7	9.6	10.3	-	13.0	7.6	8.9	-	15.7
4.4	15.3	10.7	16.0	12.7	-	13.5	9.8	9.7	-	13.9
4.5	7.8	10.0	17.2	13.2	-	12.6	9.6	9.6	-	9.7
4.6	7.9	7.8	17.2	13.3	-	11.0	8.0	9.0	-	4.7
4.7	7.4	6.1	12.5	11.1	-	7.6	5.3	8.0	-	2.2
4.8	7.2	3.6	7.0	9.4	-	4.5	3.6	6.4	-	0.8
4.9	4.0	2.6	3.7	6.6	-	1.9	1.9	4.2	-	0.2
5.0	2.3	1.7	2.8	4.0	-	0.8	1.2	2.4	-	*
5.1	0.6	0.8	2.2	2.0	-	0.3	0.6	1.2	-	-
5.2	-	0.3	1.3	0.8	-	0.1	0.2	0.6	-	*
5.3	-	0.1	*	0.3	-	*	*	0.3	-	-
5.4	-	*	-	*	-	*	*	0.1	-	-
5.5 & Above	-	*	-	*	-	*	-	*	-	-
Average	4.39	4.27	4.53	4.53	-	4.35	4.16	4.30	-	4.20

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE												
For The Week Ending Jan 23, 2025												
Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	-	-	-	*	*	-	-	-	-	-	*
2.5 - 2.6	-	-	-	*	*	*	-	*	-	-	-	*
2.7 - 2.9	-	*	-	*	0.2	*	-	0.1	-	-	-	*
3.0 - 3.2	-	0.1	-	*	2.1	0.5	*	1.1	0.1	*	0.1	*
3.3 - 3.4	-	0.3	*	0.1	3.2	1.1	1.4	2.3	0.1	*	0.3	0.1
3.5 - 3.6	0.9	1.1	*	0.3	3.5	1.8	10.8	4.6	0.5	0.1	0.7	0.2
3.7 - 4.2	14.2	29.7	10.3	13.6	39.3	30.8	79.2	51.2	23.7	7.0	17.9	12.1
4.3 - 4.9	69.0	62.4	78.8	77.8	42.8	57.2	6.6	33.9	66.9	76.9	73.4	77.2
5.0 - 5.2	7.8	5.8	10.5	7.5	6.4	6.5	2.0	5.9	7.2	14.6	7.4	9.7
5.3 & Above	8.1	0.6	0.4	0.5	2.6	2.0	*	0.9	1.5	1.3	0.2	0.8
Average	4.63	4.43	4.64	4.57	4.29	4.41	3.95	4.21	4.47	4.67	4.53	4.59
Leaf												
1 - 2	11.9	10.6	21.2	10.1	83.1	87.6	98.2	84.3	-	5.2	9.9	11.6
3	60.0	54.0	60.3	56.0	13.8	10.9	1.8	12.1	40.4	43.4	57.5	55.0
4	20.7	29.7	16.8	29.1	2.5	1.1	-	2.8	49.2	41.8	28.9	28.6
5	5.1	5.2	1.5	4.3	0.6	0.3	-	0.6	7.8	8.9	3.3	4.4
6	1.8	0.5	0.1	0.6	*	*	-	0.1	1.9	0.7	0.3	0.3
7	0.4	*	*	*	-	*	-	*	0.7	*	0.1	*
8	-	*	-	-	-	*	-	-	-	*	-	*
Average	3.26	3.31	2.99	3.29	1.83	1.76	1.58	1.89	3.73	3.57	3.27	3.27
HVI Trash 1/												
00	-	-	-	-	0.1	0.2	*	0.1	-	-	-	-
01	1.0	1.0	2.2	0.9	55.8	56.8	68.9	49.5	-	0.4	0.7	1.1
02	19.8	14.3	24.9	13.6	32.3	33.7	29.4	36.2	0.6	7.0	13.8	14.2
03	35.9	28.5	35.4	28.8	8.0	6.8	1.7	8.2	11.0	19.8	29.7	28.0
04	21.7	25.6	22.4	25.9	2.2	1.6	*	2.7	30.7	25.6	27.1	25.5
05	10.3	15.7	9.6	15.9	1.0	0.5	*	1.6	29.5	21.3	16.3	16.0
06	4.9	8.1	3.5	8.1	0.3	0.2	-	0.9	14.6	13.4	7.2	8.2
07	2.5	3.7	1.3	3.8	0.2	0.1	-	0.4	7.8	7.0	3.1	3.9
08	1.2	1.6	0.4	1.7	*	0.1	-	0.2	2.6	3.2	1.3	1.7
09	1.1	0.7	0.2	0.8	-	*	-	0.1	1.5	1.4	0.3	0.8
10	0.8	0.3	*	0.3	-	*	-	0.1	1.1	0.5	0.2	0.3
11	0.4	0.2	*	0.2	-	*	-	0.1	0.2	0.2	0.1	0.1
12	0.3	0.1	-	0.1	-	*	-	*	0.4	0.1	0.1	0.1
13	0.1	*	*	*	-	*	-	*	0.1	*	0.1	*
14	0.1	*	-	*	-	*	-	*	-	*	*	*
15	0.1	*	-	*	-	*	-	*	-	*	-	*
16	0.1	*	-	*	-	*	-	-	-	*	*	*
17	-	*	-	*	-	*	-	-	-	*	*	*
18 & Above	-	*	-	*	-	-	-	-	-	*	*	*
Average	0.37	0.40	0.33	0.40	0.16	0.16	0.13	0.18	0.50	0.46	0.39	0.40
UNIFORMITY 2/												
74 & Below	-	-	-	-	-	-	-	-	-	-	-	-
75	-	*	-	-	-	*	-	*	-	-	-	*
76	0.1	*	-	*	*	*	*	*	-	*	-	*
77	0.1	0.2	*	*	0.3	0.1	0.3	*	-	*	*	0.1
78	2.9	1.2	0.3	0.2	1.0	0.5	1.3	0.5	-	0.1	0.5	0.5
79	3.7	7.1	1.9	1.8	6.4	3.0	12.6	6.5	0.2	1.5	4.2	2.9
80	37.6	22.1	10.2	13.2	20.4	18.9	61.3	37.2	0.8	11.5	22.1	13.9
81	21.8	36.3	29.6	32.0	38.9	40.3	18.2	26.2	24.0	32.1	37.6	31.9
82	31.8	25.8	38.5	37.4	28.4	30.2	4.4	15.7	49.1	34.3	22.8	30.6
83	2.0	6.6	15.8	13.6	4.3	6.4	1.8	7.8	24.6	16.0	11.1	15.8
84	-	0.6	3.6	1.6	0.2	0.5	-	5.3	1.1	4.2	1.5	4.0
85 & Above	-	*	0.2	0.2	-	*	-	0.8	0.1	0.4	0.1	0.4
Average	81.28	81.45	82.11	81.97	81.44	81.63	80.59	81.43	82.40	82.11	81.62	82.00
Tenderable 3/	70.8	80.2	87.4	85.1	85.4	89.3	96.5	88.3	43.1	71.0	78.7	78.8
SAMPLES CLASSED	1,852	621,374	29,142	1,870,825	14,808	190,626	6,871	70,622	845	106,115	14,985	1,824,278

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 23, 2025

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	*	-	-	-	-	-	*	-	-	-	-
2.5 - 2.6	0.1	0.2	-	-	-	-	-	*	-	*	-	-
2.7 - 2.9	2.0	1.4	-	*	-	*	-	*	1.0	*	-	0.2
3.0 - 3.2	1.7	5.0	-	0.1	-	0.1	-	*	5.6	0.2	-	1.3
3.3 - 3.4	3.7	4.6	-	0.2	*	0.3	-	0.1	4.5	0.5	-	3.0
3.5 - 3.6	6.5	8.5	-	0.2	0.1	0.8	-	0.2	6.0	1.1	-	4.6
3.7 - 4.2	67.0	46.1	-	9.8	12.4	20.9	-	10.3	41.3	25.2	-	41.4
4.3 - 4.9	19.0	32.1	-	69.4	77.0	72.9	-	75.6	38.8	70.5	-	45.3
5.0 - 5.2	-	2.0	-	15.4	10.4	4.7	-	12.7	2.9	2.4	-	4.1
5.3 & Above	-	*	-	4.9	0.1	0.3	-	1.1	-	*	-	0.2
Average	3.96	4.04	-	4.67	4.60	4.47	-	4.63	4.12	4.41	-	4.24
Leaf												
1 - 2	0.1	20.2	-	20.2	26.2	22.7	-	7.3	7.4	7.8	-	70.0
3	10.8	32.5	-	45.9	55.9	61.9	-	43.0	42.1	47.7	-	20.8
4	31.2	19.9	-	28.0	16.4	14.5	-	39.4	38.0	35.8	-	6.8
5	22.5	14.7	-	5.5	1.1	0.9	-	9.5	9.3	7.7	-	2.1
6	19.0	8.0	-	0.4	0.3	*	-	0.8	2.9	0.9	-	0.3
7	12.7	3.4	-	*	0.2	*	-	*	0.4	0.2	-	-
8	3.7	1.2	-	*	-	-	-	-	-	0.1	-	-
Average	5.03	3.70	-	3.19	2.93	2.93	-	3.53	3.59	3.47	-	2.12
HVI Trash 1/												
00	-	-	-	-	-	-	-	*	-	-	-	0.2
01	-	6.4	-	4.1	3.5	2.8	-	0.8	0.6	0.6	-	40.3
02	0.3	18.4	-	19.3	29.2	26.0	-	9.0	9.9	9.7	-	31.3
03	2.8	18.4	-	23.8	31.9	35.0	-	20.7	19.8	22.5	-	13.2
04	9.4	12.2	-	21.3	19.5	21.3	-	24.4	19.2	24.9	-	6.4
05	14.5	8.8	-	15.1	9.6	9.5	-	19.9	18.0	19.1	-	3.8
06	12.4	7.2	-	8.7	3.8	3.5	-	12.7	14.3	11.7	-	2.4
07	10.7	6.4	-	4.5	1.4	1.2	-	6.8	9.3	6.2	-	1.2
08	8.3	5.2	-	1.9	0.5	0.4	-	3.2	2.9	2.9	-	0.6
09	7.6	4.4	-	0.8	0.2	0.1	-	1.3	2.7	1.4	-	0.3
10	6.8	3.5	-	0.3	0.1	0.1	-	0.5	1.7	0.6	-	0.2
11	6.2	2.6	-	0.1	0.1	*	-	0.2	1.2	0.3	-	0.1
12	5.0	2.0	-	*	0.1	*	-	0.1	0.2	0.1	-	*
13	4.3	1.4	-	*	0.1	*	-	*	-	0.1	-	*
14	4.0	1.1	-	*	*	*	-	*	-	*	-	-
15	3.1	0.7	-	*	*	*	-	*	0.2	*	-	-
16	2.1	0.5	-	*	-	-	-	*	-	*	-	-
17	1.1	0.3	-	*	-	-	-	*	-	*	-	-
18 & Above	1.5	0.5	-	*	-	-	-	*	-	*	-	-
Average	0.84	0.51	-	0.39	0.33	0.33	-	0.45	0.48	0.44	-	0.22
UNIFORMITY 2/												
74 & Below	*	*	-	-	-	-	-	-	-	-	-	-
75	0.1	0.1	-	*	-	-	-	*	-	-	-	-
76	0.2	0.3	-	*	-	*	-	*	-	-	-	*
77	1.1	1.5	-	*	-	*	-	0.1	-	*	-	0.2
78	4.8	7.0	-	0.1	0.1	0.2	-	0.5	-	0.3	-	0.8
79	25.8	20.3	-	1.8	0.2	1.9	-	3.6	4.7	3.2	-	8.7
80	28.8	31.6	-	13.8	3.1	10.6	-	19.8	22.5	18.5	-	24.1
81	30.8	30.1	-	33.8	29.4	32.0	-	37.6	36.6	37.3	-	36.9
82	7.7	8.6	-	33.9	44.2	40.6	-	27.7	25.6	30.8	-	25.1
83	0.5	0.5	-	14.2	21.7	13.6	-	9.4	10.3	9.2	-	3.6
84	-	*	-	2.2	1.3	0.9	-	1.1	0.4	0.7	-	0.6
85 & Above	-	-	-	0.2	0.1	0.1	-	0.2	-	*	-	*
Average	80.56	80.53	-	81.97	82.32	82.00	-	81.67	81.58	81.70	-	81.34
Tenderable 3/	6.60	48.8	-	77.3	81.9	91.2	-	77.9	82.4	92.1	-	89.2
SAMPLES CLASSED	3,162	167,168	-	329,898	12,310	880,276	-	1,149,588	516	786,429	-	21,979

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE										
For The Week Ending Jan 23, 2025										
Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE										
2.4 & Below	-	*	-	-	-	-	*	*	-	-
2.5 - 2.6	-	*	-	-	-	-	0.2	0.1	-	-
2.7 - 2.9	-	0.1	-	*	-	*	1.4	0.6	-	*
3.0 - 3.2	-	0.6	-	*	-	0.2	2.8	2.0	-	0.2
3.3 - 3.4	-	1.3	*	0.1	-	0.5	4.0	2.5	-	0.7
3.5 - 3.6	*	3.4	0.2	0.3	-	1.1	7.5	4.1	-	2.3
3.7 - 4.2	34.1	40.1	10.3	15.8	-	33.0	36.2	30.3	-	49.4
4.3 - 4.9	63.0	51.6	83.2	76.7	-	64.0	45.8	55.8	-	47.3
5.0 - 5.2	2.9	2.8	6.3	6.9	-	1.3	2.0	4.2	-	*
5.3 & Above	-	0.1	*	0.3	-	*	*	0.5	-	-
Average	4.39	4.27	4.53	4.53	-	4.35	4.16	4.30	-	4.20
Leaf										
1 - 2	20.6	56.9	6.9	5.9	-	27.3	22.2	34.1	-	12.7
3	36.2	30.6	45.4	45.5	-	58.5	38.1	37.0	-	60.6
4	25.7	9.6	41.1	39.9	-	13.2	22.7	20.2	-	23.7
5	12.7	2.3	6.2	8.2	-	1.0	10.3	5.9	-	2.8
6	3.1	0.5	0.4	0.6	-	*	4.1	1.7	-	0.2
7	1.2	0.1	*	*	-	-	1.8	0.7	-	*
8	0.6	*	-	*	-	-	0.8	0.4	-	*
Average	3.45	2.40	3.48	3.52	-	2.87	3.42	2.99	-	3.17
HVI Trash 1/										
00	-	0.2	-	-	-	-	*	0.1	-	-
01	5.4	28.4	0.5	0.4	-	4.6	7.3	15.0	-	0.7
02	17.2	30.7	10.1	7.9	-	28.8	20.9	22.3	-	14.6
03	18.0	17.1	21.7	21.4	-	33.7	21.6	19.6	-	31.3
04	16.3	10.5	23.3	25.7	-	19.6	15.5	16.0	-	26.1
05	11.5	6.0	21.2	20.5	-	8.4	10.8	10.8	-	15.0
06	9.1	3.1	12.7	12.9	-	3.2	7.3	6.5	-	7.3
07	7.7	1.6	6.7	6.4	-	1.1	5.1	3.8	-	3.2
08	6.2	1.0	2.0	2.8	-	0.4	3.4	2.1	-	1.2
09	2.8	0.6	1.0	1.2	-	0.2	2.3	1.3	-	0.4
10	2.1	0.3	0.3	0.4	-	0.1	1.7	0.8	-	0.2
11	0.9	0.2	0.2	0.2	-	*	1.2	0.5	-	0.1
12	1.0	0.1	*	0.1	-	*	0.8	0.4	-	*
13	0.9	0.1	*	*	-	*	0.7	0.3	-	*
14	0.4	*	-	*	-	*	0.4	0.2	-	*
15	0.3	*	-	*	-	*	0.3	0.1	-	*
16	*	*	-	*	-	-	0.2	0.1	-	*
17	*	*	-	*	-	-	0.1	0.1	-	*
18 & Above	0.1	*	-	*	-	-	0.1	0.1	-	*
Average	0.47	0.27	0.44	0.45	-	0.32	0.43	0.36	-	0.39
UNIFORMITY 2/										
74 & Below	-	*	-	-	-	-	0.1	0.1	-	-
75	-	0.1	-	-	-	-	0.3	0.2	-	-
76	0.2	0.5	-	-	-	*	1.1	0.8	-	-
77	0.9	1.6	-	*	-	0.1	4.1	2.8	-	*
78	2.8	4.7	0.7	0.2	-	0.5	13.6	7.8	-	0.4
79	23.4	12.6	6.9	1.8	-	4.2	24.2	16.3	-	3.4
80	45.7	20.0	35.7	15.3	-	18.6	29.9	26.0	-	22.3
81	19.0	27.4	34.3	37.5	-	38.8	18.9	27.3	-	36.5
82	7.9	24.2	20.1	34.2	-	30.6	6.1	14.7	-	28.8
83	0.1	8.2	2.2	10.4	-	6.8	1.5	3.5	-	8.0
84	-	0.6	0.1	0.7	-	0.3	0.2	0.4	-	0.7
85 & Above	-	*	-	*	-	*	*	*	-	*
Average	80.45	81.18	81.19	81.83	-	81.61	80.11	80.69	-	81.62
Tenderable 3/	32.6	75.7	88.4	87.1	-	86.4	67.0	75.7	-	97.1
SAMPLES CLASSED	2,816	163,516	4,553	322,192	-	535,228	58,381	3,997,711	-	214,888

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE									
For The Week Ending Jan 23, 2025									
Color Grade	Leaf	Arizona		California		New Mexico		Texas	
		Week	Season	Week	Season	Week	Season	Week	Season
01	1	79.0	76.0	10.6	15.7	-	21.8	8.2	13.2
	2	11.1	6.2	12.6	14.4	-	23.2	15.6	23.5
	3	0.1	*	0.1	0.3	-	2.1	1.5	4.4
	4	-	-	-	*	-	*	0.1	0.8
	5	-	-	-	-	-	-	-	*
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		90.2	82.3	23.3	30.3	-	47.1	25.3	41.9
02	1	7.6	15.1	13.0	16.1	-	12.2	11.3	11.7
	2	2.2	2.4	56.4	43.5	-	26.9	46.0	32.5
	3	-	*	3.0	4.0	-	9.4	6.6	6.0
	4	-	-	*	0.1	-	1.1	0.1	2.5
	5	-	-	-	-	-	*	-	0.3
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		9.8	17.6	72.3	63.6	-	49.6	64.0	53.0
03	1	*	*	0.1	0.3	-	0.1	0.5	0.2
	2	-	0.1	2.8	3.1	-	0.7	6.3	2.2
	3	-	*	1.2	1.7	-	1.8	3.4	1.8
	4	-	*	*	0.2	-	0.6	0.1	0.5
	5	-	-	-	*	-	0.1	-	0.1
	6	-	-	-	*	-	-	-	*
	7	-	-	-	*	-	-	-	-
Total -----		*	0.1	4.1	5.4	-	3.3	10.3	4.8
04	1	-	-	-	*	-	-	-	*
	2	-	*	0.1	0.1	-	*	0.1	*
	3	-	-	0.1	0.2	-	*	0.3	0.1
	4	-	-	-	0.1	-	*	-	0.1
	5	-	-	-	*	-	-	-	*
	6	-	-	-	*	-	-	-	*
	7	-	-	-	*	-	-	-	-
Total -----		-	*	0.2	0.5	-	*	0.4	0.3
05	1	-	-	-	*	-	-	-	-
	2	-	*	*	*	-	-	-	-
	3	-	-	0.1	0.1	-	-	-	*
	4	-	-	-	0.1	-	-	-	-
	5	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	*	-	-	-	*
Total -----		-	*	0.1	0.2	-	-	-	*
06	1	-	-	-	-	-	-	-	-
	2	-	-	-	*	-	-	-	-
	3	-	-	-	*	-	-	-	-
	4	-	-	-	*	-	-	-	-
	5	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	*	-	-	-	-
Total -----		-	-	-	*	-	-	-	-
07	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-
	5	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	*	-	-	-	-
Total -----		-	-	-	*	-	-	-	-
STAPLE									
44 & Shorter		-	*	-	0.2	-	1.3	8.1	11.4
46		0.5	2.4	*	4.1	-	14.8	12.7	33.5
48		51.3	55.7	12.7	19.1	-	66.7	68.8	48.7
50		47.6	40.6	63.9	55.5	-	16.2	10.4	6.1
52 & Longer		0.7	1.3	23.4	21.1	-	0.9	0.1	0.2
Average Staple		48.97	48.81	50.21	49.86	-	48.01	47.54	46.99
Average Length		1.42	1.42	1.46	1.45	-	1.39	1.39	1.37
EXTRANEIOUS MATTER									
Bark		-	-	-	*	-	0.2	-	0.1
Grass		-	-	-	0.1	-	1.3	0.4	0.3
Spindle Twist		-	-	0.1	0.9	-	-	-	0.3
Preparation		-	-	-	*	-	-	-	*
All Other		-	*	*	*	-	*	0.2	0.2

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE For The Week Ending Jan 23, 2025								
Quality Designation	Arizona		California		New Mexico		Texas	
	Week	Season	Week	Season	Week	Season	Week	Season
MIKE								
2.4 & Below	-	-	*	*	-	-	-	*
2.5 - 2.6	-	*	0.2	*	-	*	-	*
2.7 - 2.9	*	0.1	0.7	0.5	-	0.2	0.1	0.2
3.0 - 3.2	0.5	0.7	0.5	1.9	-	6.0	0.1	1.1
3.3 - 3.4	1.9	0.9	1.5	5.7	-	10.1	0.2	3.3
3.5 - 3.6	12.2	6.2	20.3	19.7	-	19.0	3.5	10.0
3.7 - 4.2	85.3	91.0	76.2	71.6	-	61.0	87.1	79.2
4.3 - 4.9	0.1	1.2	0.6	0.6	-	3.6	9.1	6.3
5.0 - 5.2	-	-	*	*	-	-	-	*
5.3 & Above	-	-	-	*	-	-	-	-
Average	3.84	3.89	3.78	3.76	-	3.75	4.02	3.90
ALL RANGE MIKE								
2.4 & Below	-	-	*	*	-	-	-	*
2.5	-	-	*	*	-	-	-	-
2.6	-	*	0.1	*	-	*	-	*
2.7	*	*	0.2	0.1	-	0.1	*	0.1
2.8	-	*	0.2	0.1	-	0.1	-	*
2.9	-	*	0.3	0.2	-	0.1	*	0.1
3.0	-	*	0.2	0.4	-	0.3	-	0.2
3.1	-	0.1	0.1	0.6	-	1.6	*	0.4
3.2	0.5	0.6	0.1	0.9	-	4.2	0.1	0.5
3.3	0.2	0.4	0.2	1.9	-	3.7	*	1.2
3.4	1.6	0.5	1.3	3.8	-	6.4	0.1	2.1
3.5	5.0	2.1	6.4	7.5	-	7.7	0.2	3.4
3.6	7.2	4.0	13.9	12.2	-	11.2	3.2	6.5
3.7	7.7	6.6	19.7	17.1	-	11.8	7.8	10.5
3.8	17.9	18.4	21.1	19.0	-	14.0	6.6	14.1
3.9	34.0	29.1	16.9	16.8	-	13.3	15.1	15.1
4.0	20.6	25.0	11.4	10.8	-	11.5	22.1	15.4
4.1	3.8	10.0	5.4	6.0	-	6.5	18.5	13.6
4.2	1.3	1.9	1.7	2.0	-	3.9	17.1	10.5
4.3	0.1	0.4	0.5	0.5	-	3.3	6.3	4.8
4.4	-	0.7	0.1	0.1	-	0.3	1.9	1.3
4.5	-	0.1	*	*	-	*	0.3	0.1
4.6	-	-	-	*	-	*	0.2	*
4.7	-	*	*	*	-	-	0.2	*
4.8	-	-	-	*	-	-	0.1	*
4.9	-	-	-	*	-	*	*	*
5.0	-	-	-	*	-	-	-	-
5.1	-	-	*	*	-	-	-	*
5.2	-	-	-	-	-	-	-	-
5.3 & Above	-	-	-	*	-	-	-	*
Average	3.84	3.89	3.78	3.76	-	3.75	4.02	3.90
STRENGTH 1/								
36 & Below	-	0.1	0.3	0.7	-	17.3	2.5	16.7
37	-	*	0.2	2.1	-	13.6	4.3	13.3
38	*	*	0.4	4.2	-	4.3	6.3	13.6
39	*	0.1	1.5	4.3	-	1.7	1.2	2.6
40	0.9	0.5	4.7	3.9	-	1.2	0.5	1.0
41	4.2	3.7	12.4	6.6	-	4.1	6.4	2.5
42	15.7	13.6	20.6	12.7	-	11.1	10.8	5.4
43	27.7	32.4	22.2	19.5	-	14.1	23.8	11.1
44	27.3	25.2	16.7	21.1	-	13.7	18.8	15.3
45	11.2	15.1	12.5	15.8	-	13.3	20.0	11.7
46	9.2	6.8	6.3	6.6	-	4.1	4.6	4.6
47	3.5	2.2	1.9	1.8	-	1.4	0.6	1.7
48 & Above	0.2	0.2	0.3	0.5	-	0.2	0.2	0.4
Average	44.11	44.07	43.44	43.34	-	41.47	43.06	40.99
UNIFORMITY								
83 & Below	-	0.1	0.6	0.6	-	0.3	1.7	7.2
84	0.1	0.7	2.3	5.4	-	12.2	11.5	21.9
85	4.0	11.9	19.7	21.9	-	41.2	17.5	29.3
86	61.1	57.5	48.0	55.0	-	40.7	57.5	37.6
87	32.3	29.0	23.5	15.8	-	5.3	11.8	4.0
88 & Above	2.4	0.8	5.9	1.4	-	0.3	0.1	0.1
Average	86.77	86.61	86.55	86.29	-	85.85	86.10	85.52
Samples Classed	2,450	12,583	10,729	298,782	-	21,831	3,677	37,155

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
 * Less than 0.05 percent.