



Volume 21, No.24

State	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
AL	15	78.5	69.0	29,706	29	86.4	74.0	922,738
AR	12	76.6	58.9	35,575	28	90.0	75.8	1,383,271
AZ	11	68.7	46.6	22,458	12	79.8	59.5	221,512
CA	7	90.9	81.9	19,598	15	88.4	76.7	153,328
FL	4	77.3	63.2	3,387	4	83.1	65.4	148,081
GA	53	82.8	67.0	96,710	59	85.2	66.1	2,565,544
KS	3	74.1	49.8	16,040	3	55.6	37.3	122,061
LA	8	79.8	58.6	12,224	19	89.5	70.5	567,744
MO	11	91.2	71.9	32,760	21	89.4	73.9	784,323
MS	23	88.6	69.1	33,553	38	88.4	66.0	1,493,173
NC	21	86.6	69.2	21,604	34	83.3	59.0	1,020,674
NM	2	81.2	48.9	3,159	2	86.1	69.3	26,761
OK	11	65.5	47.4	35,198	12	79.1	61.6	398,472
SC	10	89.6	73.5	13,755	15	87.4	67.1	401,980
TN	11	81.6	56.6	16,336	22	89.5	71.0	929,816
TX	102	46.5	24.4	197,524	187	66.4	39.4	6,070,468
VA	4	93.7	83.3	4,958	4	85.8	59.3	204,471
United States	308	69.7	50.7	594,545	504	79.5	57.9	17,414,417
AMERICAN PIMA								
AZ	2			1,501	3			9,135
CA	13			36,329	17			443,008
NM*	-			-	-			-
TX*	-			-	3			14,572
United States	17			39,009	24			476,391
United States all cotton	322			633,554	519			17,890,808

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 09, 2020

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	1.2	8.8	0.9	4.9	23.5	54.5	33.3	53.3	-	3.6	2.7	9.3
	3	0.9	9.3	1.6	4.4	2.3	5.7	3.8	5.7	-	3.1	1.7	6.7
	4	*	0.8	0.1	0.2	0.2	0.3	*	0.2	-	0.2	0.1	0.3
	5	-	*	-	*	*	*	-	*	-	-	-	*
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	2.1	18.8	2.6	9.5	26.0	60.6	37.1	59.3	-	6.8	4.4	16.3
31	1 - 2	2.1	2.3	0.5	3.4	13.4	10.2	10.3	14.7	0.2	1.4	1.1	3.8
	3	10.5	13.1	10.0	18.3	7.9	8.1	8.7	12.3	3.1	8.8	7.2	12.7
	4	3.3	5.7	6.9	8.4	1.5	1.7	0.7	1.7	1.4	3.4	4.5	4.2
	5	0.2	0.5	0.8	0.8	0.2	0.2	*	0.1	0.2	0.3	0.4	0.3
	6	-	*	*	*	*	*	-	*	-	*	*	*
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	16.0	21.6	18.3	31.0	23.0	20.2	19.8	28.8	4.8	13.9	13.2	21.0
41	1 - 2	2.5	1.6	0.5	0.7	5.7	1.8	6.8	1.4	4.6	0.8	2.7	2.1
	3	25.1	16.1	15.5	12.8	12.7	3.8	21.8	4.8	37.3	17.2	24.8	17.9
	4	17.0	14.3	23.4	23.1	7.0	2.2	7.3	2.2	23.5	25.9	21.5	16.1
	5	2.4	3.2	16.2	12.5	2.0	0.6	0.9	0.3	4.6	5.2	5.1	3.3
	6	0.3	0.3	3.0	1.4	0.4	0.1	*	*	0.1	0.2	0.4	0.2
	7	*	*	*	*	0.1	*	-	*	-	*	*	*
	8	*	*	-	-	*	*	-	-	-	-	-	-
Total	----	47.3	35.7	58.6	50.5	27.8	8.6	36.9	8.7	70.2	49.3	54.5	39.5
51	1 - 2	1.4	0.6	0.2	0.1	0.5	0.3	0.3	*	1.1	0.4	0.8	0.9
	3	8.2	6.0	2.5	1.3	2.2	0.8	0.9	0.1	3.6	7.4	8.8	7.2
	4	7.3	5.6	8.0	3.4	5.1	0.8	0.3	0.1	2.9	11.5	7.8	5.9
	5	2.4	1.5	6.3	2.4	2.9	0.6	0.2	*	2.5	3.8	1.7	1.4
	6	0.3	0.3	1.4	0.4	0.7	0.4	0.1	*	0.7	0.3	0.1	0.1
	7	*	*	-	*	0.2	0.2	*	*	-	*	*	*
	8	-	*	-	*	*	*	-	-	-	-	-	*
Total	----	19.6	14.1	18.3	7.6	11.6	3.0	1.7	0.3	10.8	23.4	19.2	15.5
61	1 - 2	*	*	-	-	-	*	*	*	-	*	*	*
	3	*	0.1	-	*	-	*	*	*	-	0.1	0.1	0.1
	4	*	*	-	*	*	*	-	*	-	0.2	*	*
	5	*	*	-	*	-	*	-	-	-	0.1	*	*
	6	-	*	-	*	*	*	-	-	-	*	-	*
	7	-	*	-	-	*	*	-	-	-	-	-	*
	8	-	*	-	-	*	*	-	-	-	-	-	*
Total	----	0.1	0.1	-	*	0.1	*	*	*	-	0.5	0.1	0.2
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	*
	3	-	-	-	*	-	-	-	-	-	-	-	*
	4	-	*	-	-	-	-	-	-	-	-	-	*
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	*
	7	-	*	-	-	-	-	-	-	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	*	-	*
Total	----	-	*	-	*	-	-	-	-	-	*	-	*
12 & 22	1 - 2	0.1	0.2	-	*	0.7	1.6	0.2	0.1	-	*	0.1	0.4
	3	0.1	0.4	*	*	0.3	1.6	*	0.1	-	*	0.1	0.2
	4	*	0.1	-	*	*	0.3	-	*	-	*	*	*
	5	-	*	-	-	-	*	-	*	-	-	-	-
	6	-	-	-	-	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.1	0.7	*	0.1	1.0	3.5	0.2	0.2	-	0.1	0.1	0.6
32	1 - 2	0.1	0.1	-	*	0.8	0.4	0.5	0.3	-	0.1	0.1	0.3
	3	0.5	0.9	0.1	0.2	2.2	1.0	0.6	0.6	0.1	0.3	0.4	1.0
	4	0.7	0.7	0.3	0.2	0.8	0.6	0.2	0.3	0.2	0.2	0.2	0.3
	5	0.2	0.1	*	*	0.1	0.2	*	0.1	0.1	*	*	*
	6	*	*	-	*	-	*	-	*	*	*	*	*
	7	-	*	-	-	-	*	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	1.6	1.8	0.5	0.4	3.9	2.2	1.3	1.2	0.5	0.6	0.7	1.6
42	1 - 2	0.2	0.2	-	*	0.1	*	*	*	0.1	0.1	0.2	0.2
	3	3.0	1.7	0.3	0.2	1.8	0.4	0.9	0.4	4.8	0.8	1.9	1.4
	4	3.5	1.8	0.5	0.3	1.8	0.4	1.5	0.7	3.3	1.3	1.6	1.1
	5	0.8	0.6	0.3	0.1	0.5	0.2	0.3	0.1	1.4	0.4	0.3	0.2
	6	*	0.1	0.1	*	0.1	0.1	*	*	0.4	*	*	*
	7	-	*	-	-	*	*	-	-	*	*	*	*
	8	-	*	-	-	*	*	-	-	-	-	-	-
Total	----	7.5	4.3	1.2	0.6	4.4	1.2	2.7	1.3	10.0	2.7	4.0	2.9

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 09, 2020

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	0.1	0.1	-	*	-	-	-	-	0.1	0.1	0.1	0.1
	3	1.2	0.9	*	*	0.1	0.1	*	*	0.8	0.8	0.9	0.9
	4	1.4	1.0	*	*	0.3	0.1	0.1	0.1	0.5	1.1	0.8	0.7
	5	0.3	0.2	0.1	*	0.2	*	0.1	0.1	*	0.5	0.3	0.2
	6	*	*	0.1	*	0.1	*	*	*	0.1	0.1	0.1	*
	7	-	*	-	-	*	*	-	*	-	*	*	*
	8	-	*	-	-	*	*	-	-	-	*	-	*
Total	----	3.0	2.2	0.2	0.1	0.8	0.2	0.2	0.2	1.4	2.5	2.2	2.0
62	1 - 2	-	*	-	*	-	-	-	-	-	*	*	*
	3	-	*	-	*	-	-	-	*	-	*	*	*
	4	*	*	-	*	-	-	-	-	-	0.1	*	*
	5	*	*	-	*	-	-	-	-	-	*	*	*
	6	-	*	-	*	*	*	-	-	*	*	*	*
	7	-	*	-	-	-	-	-	-	-	*	*	*
	8	-	*	-	-	-	*	-	-	-	*	*	*
Total	----	*	0.1	-	*	*	*	-	*	*	0.1	0.1	0.1
13 & 23	1 - 2	-	*	-	*	*	0.1	-	*	-	-	-	*
	3	*	*	-	*	*	*	-	*	-	-	*	*
	4	-	*	-	*	-	*	-	-	-	*	*	*
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	-	*	0.1	0.1	-	*	-	*	*	*
33	1 - 2	*	*	-	*	0.1	0.1	*	*	-	-	*	*
	3	0.1	*	*	*	0.3	0.1	*	*	-	*	*	*
	4	0.1	*	*	*	0.1	*	-	*	*	*	*	*
	5	0.1	*	*	*	*	*	-	-	-	-	*	*
	6	*	*	-	-	-	-	-	-	-	-	*	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.2	0.1	*	*	0.6	0.2	0.1	*	*	*	0.1	*
43	1 - 2	*	*	*	*	*	*	-	*	-	-	*	*
	3	0.5	0.1	*	*	0.1	*	*	*	0.9	*	0.4	0.1
	4	0.8	0.2	0.1	0.1	0.4	0.1	*	*	0.7	*	0.4	0.1
	5	0.4	0.1	0.1	*	0.1	*	-	*	0.2	*	0.1	*
	6	0.1	*	*	*	*	*	-	-	-	*	*	*
	7	*	*	-	*	*	*	-	-	-	-	-	*
	8	-	*	-	-	-	*	-	-	-	-	-	-
Total	----	1.8	0.4	0.2	0.1	0.6	0.1	*	*	1.7	0.1	0.9	0.2
53	1 - 2	-	*	-	-	-	-	-	-	-	-	*	*
	3	0.1	*	-	*	*	*	-	-	0.1	*	0.1	*
	4	0.2	*	*	*	*	*	-	*	0.2	*	0.2	0.1
	5	0.1	*	*	*	*	*	-	-	*	*	0.1	*
	6	*	*	*	*	*	*	-	-	0.1	*	*	*
	7	-	*	-	*	*	*	-	-	-	-	-	*
	8	-	*	-	-	-	*	-	-	-	-	-	-
Total	----	0.4	0.1	*	*	0.1	*	-	*	0.4	0.1	0.4	0.1
63	1 - 2	-	*	-	-	-	-	-	-	-	-	-	*
	3	-	*	-	*	-	-	-	-	*	*	*	*
	4	-	*	-	*	-	*	-	-	0.1	*	-	*
	5	-	*	-	-	-	-	-	-	-	-	-	*
	6	-	*	-	-	-	-	-	-	-	*	-	*
	7	-	*	-	*	-	-	-	-	-	*	-	*
	8	-	*	-	-	-	-	-	-	-	*	-	*
Total	----	-	*	-	*	-	*	-	-	0.1	*	*	*
24 - 54	1 - 8	0.2	*	-	*	0.2	*	-	*	*	*	0.1	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	*	*	-	-	-	-	-	-	-	-	*	*
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	-	-	-	-	-	-	-	-	-	*	*
31		*	*	-	*	-	-	-	-	-	*	0.1	*
32		0.3	0.5	-	*	0.2	*	-	-	-	*	0.4	0.4
33		1.9	2.1	-	*	1.3	0.6	*	0.1	0.6	0.7	2.6	2.3
34		7.4	6.8	0.1	0.1	2.6	2.5	0.2	1.1	3.2	2.7	7.7	7.4
35		10.8	13.1	2.0	1.8	6.7	8.2	4.3	3.5	10.2	5.2	18.0	15.3
36		19.8	22.8	16.1	11.3	20.6	19.3	12.9	11.9	15.1	12.1	23.6	21.1
37		32.3	32.5	41.8	40.2	35.2	31.3	20.3	31.2	39.2	32.5	24.8	29.2
38		19.0	14.9	20.5	25.7	19.6	21.3	24.7	28.0	25.7	34.4	15.4	16.9
39		7.5	6.3	12.8	16.4	10.1	12.8	32.5	20.0	5.8	11.3	6.8	6.5
40 & Longer		1.0	1.1	6.8	4.5	3.7	3.9	5.1	4.2	0.2	1.2	0.5	0.8
Average Staple		36.64	36.51	37.47	37.57	37.04	37.14	37.83	37.58	36.90	37.27	36.34	36.47
Average Length		1.14	1.14	1.17	1.17	1.16	1.16	1.18	1.17	1.15	1.16	1.13	1.14

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 09, 2020

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	30.0	21.1	3.8	15.6	0.6	2.8	19.7	13.5	1.7	4.6	25.8	44.4
	3	5.7	7.0	4.1	13.8	0.6	1.3	10.4	11.6	2.1	4.9	2.8	4.4
	4	0.3	0.3	0.1	0.8	*	*	1.4	1.3	0.1	0.3	*	*
	5	*	*	-	*	-	*	0.1	*	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	*	-	-	-	-
Total	----	36.0	28.4	8.0	30.1	1.2	4.1	31.5	26.5	3.9	9.9	28.6	48.8
31	1 - 2	3.0	3.7	0.4	2.4	2.8	5.4	3.9	2.6	3.2	3.7	14.6	14.1
	3	16.7	13.8	6.5	14.3	14.6	19.3	10.6	13.7	16.6	19.5	15.6	15.8
	4	11.9	9.2	4.7	6.6	4.9	7.2	4.7	7.5	4.1	8.6	1.0	1.9
	5	2.5	1.6	0.4	0.5	0.4	0.7	0.4	0.8	0.2	0.8	0.2	0.1
	6	*	0.1	-	*	*	*	*	*	-	*	-	-
	7	-	*	-	*	-	-	-	*	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-	-	-
Total	----	34.2	28.3	12.0	23.9	22.8	32.6	19.7	24.6	24.0	32.6	31.4	31.9
41	1 - 2	-	*	0.4	0.5	2.9	1.6	1.9	1.0	6.2	2.7	0.3	0.3
	3	*	0.1	15.0	9.2	27.8	17.9	11.3	11.0	42.1	25.3	0.3	2.1
	4	0.6	1.0	25.9	14.3	27.2	25.1	13.1	16.0	15.9	19.6	0.5	1.9
	5	1.9	1.5	5.9	4.6	7.4	11.2	4.0	5.6	1.2	3.2	0.3	0.6
	6	0.2	0.5	0.2	0.4	1.1	1.2	0.2	0.6	*	0.2	-	0.1
	7	0.2	0.2	-	*	-	*	*	*	-	*	-	-
	8	0.2	*	-	-	-	-	-	*	-	-	-	-
Total	----	3.2	3.4	47.5	29.1	66.4	57.0	30.6	34.1	65.4	51.0	1.4	5.1
51	1 - 2	-	-	0.2	0.1	*	0.1	0.4	0.2	0.1	0.1	-	-
	3	-	-	3.8	2.3	0.8	0.7	3.9	2.7	1.4	1.1	-	*
	4	-	*	12.0	5.8	4.5	2.5	6.0	5.6	1.0	1.8	-	*
	5	-	0.1	3.2	2.6	2.4	1.8	3.0	2.7	0.2	0.6	-	*
	6	-	*	0.2	0.4	0.4	0.3	0.3	0.5	*	0.1	-	*
	7	0.2	0.1	-	*	-	*	*	*	-	*	-	-
	8	0.5	0.1	-	*	-	-	-	*	-	*	-	-
Total	----	0.6	0.3	19.4	11.2	8.1	5.4	13.6	11.8	2.7	3.6	-	*
61	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	*	-	*	-	-	-	-
	4	-	-	-	0.1	-	*	*	*	-	*	-	-
	5	-	-	-	0.1	-	*	*	*	-	-	-	-
	6	-	-	-	*	-	*	-	*	-	-	-	-
	7	-	-	-	*	-	-	-	*	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	*	-	-
Total	----	-	-	-	0.2	-	*	*	*	-	*	-	-
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	*	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	*	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	*	-	-	-	-
12 & 22	1 - 2	14.1	10.1	0.1	0.4	-	*	0.3	0.1	*	*	5.0	3.2
	3	3.3	2.9	0.5	0.5	-	*	0.4	0.2	*	0.1	6.4	2.0
	4	*	0.1	*	0.1	-	-	0.1	0.1	-	*	*	0.1
	5	-	*	-	*	-	-	-	*	-	*	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	17.4	13.1	0.6	1.0	-	*	0.7	0.4	0.1	0.1	11.4	5.2
32	1 - 2	0.1	0.3	*	0.1	*	*	0.1	0.1	0.1	0.1	3.4	1.0
	3	0.8	1.7	0.3	0.6	0.1	0.1	0.4	0.3	0.6	0.5	10.6	3.0
	4	1.9	2.6	0.3	0.3	0.1	0.1	0.3	0.3	0.4	0.3	3.5	1.2
	5	0.6	1.3	*	*	*	*	*	0.1	*	*	0.4	0.1
	6	*	0.2	-	*	-	*	-	*	-	*	-	-
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	3.4	6.1	0.7	1.0	0.2	0.2	0.8	0.7	1.0	0.9	17.9	5.4
42	1 - 2	-	*	0.1	0.1	*	*	0.1	*	*	*	-	*
	3	*	*	2.8	0.8	0.1	0.1	0.6	0.2	0.9	0.5	-	0.2
	4	0.1	0.3	3.4	1.0	0.4	0.1	1.0	0.6	0.9	0.7	0.4	0.2
	5	0.4	1.2	1.1	0.4	0.2	0.1	0.4	0.4	0.1	0.2	0.7	0.2
	6	0.2	1.0	0.1	0.1	*	*	0.1	*	-	*	0.3	0.1
	7	*	0.3	-	*	-	-	*	*	-	*	0.1	*
	8	*	0.1	-	-	-	-	-	*	-	-	-	*
Total	----	0.7	3.0	7.6	2.3	0.8	0.3	2.1	1.3	2.0	1.5	1.4	0.8

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 09, 2020

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	*	*	-	*	-	*	-	*	-	-
	3	-	-	1.5	0.2	*	*	*	*	*	*	-	*
	4	-	*	0.8	0.3	*	*	0.2	0.2	*	*	-	*
	5	-	0.1	0.1	0.1	*	*	0.1	0.1	-	*	-	0.1
	6	-	0.1	*	*	-	*	*	*	-	*	-	*
	7	*	0.1	-	*	-	-	-	*	-	*	-	-
	8	*	0.1	-	*	-	-	*	*	-	*	-	-
Total	----	*	0.4	2.5	0.7	*	*	0.3	0.3	0.1	0.1	-	0.1
62	1 - 2	-	-	-	-	-	-	-	*	-	-	-	-
	3	-	-	-	*	-	*	-	*	-	-	-	-
	4	-	*	-	*	-	*	-	*	-	*	-	-
	5	-	*	-	*	-	*	*	*	-	-	-	-
	6	-	-	-	*	-	*	*	*	-	*	-	-
	7	-	*	-	*	-	-	*	*	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	*	-	*	*	*	-	*	-	-
13 & 23	1 - 2	1.5	3.2	-	*	-	-	-	*	*	*	0.5	0.4
	3	1.0	1.6	*	*	-	-	*	*	-	*	0.5	0.2
	4	0.1	0.1	-	*	-	-	*	*	-	-	*	*
	5	-	*	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	*	-	-	-	-
Total	----	2.7	4.9	*	*	-	-	*	*	*	*	1.0	0.7
33	1 - 2	*	0.1	*	*	-	*	*	*	*	*	1.0	0.5
	3	0.3	0.6	0.1	*	*	*	0.1	*	0.2	*	4.1	1.0
	4	0.3	0.6	0.1	*	*	*	0.1	*	0.2	*	1.3	0.3
	5	-	0.6	-	*	*	*	*	*	*	*	-	*
	6	*	0.2	-	*	-	-	*	*	-	*	-	-
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	----	0.5	2.2	0.1	0.1	0.1	*	0.2	*	0.4	0.1	6.4	1.8
43	1 - 2	-	*	*	*	-	*	*	*	*	*	-	-
	3	*	0.1	0.3	0.1	0.1	*	0.1	*	0.2	*	-	*
	4	*	0.4	0.7	0.1	0.2	0.1	0.1	*	0.2	0.1	0.1	*
	5	-	0.9	0.2	*	0.1	*	0.1	*	*	*	-	*
	6	*	0.9	*	*	-	*	*	*	-	*	-	-
	7	*	0.4	-	-	-	-	-	*	-	-	-	-
	8	*	0.4	-	-	-	-	-	*	-	-	-	-
Total	----	0.1	3.1	1.3	0.3	0.4	0.1	0.3	0.1	0.4	0.1	0.1	*
53	1 - 2	-	-	-	-	-	-	-	*	-	*	-	-
	3	-	-	0.1	*	-	*	*	*	-	*	-	-
	4	-	0.1	0.1	*	*	*	*	*	*	*	-	-
	5	-	0.2	*	*	*	*	*	*	*	*	-	-
	6	-	0.4	-	*	-	*	*	*	-	*	-	-
	7	*	0.6	-	-	-	-	-	*	-	*	-	-
	8	0.1	0.4	-	-	-	-	-	*	-	*	-	-
Total	----	0.1	1.8	0.2	*	*	*	0.1	*	*	*	-	-
63	1 - 2	-	-	-	-	-	*	-	*	-	-	-	-
	3	-	-	-	-	-	*	-	*	-	-	-	-
	4	-	*	-	-	-	*	-	*	-	-	-	-
	5	-	*	-	-	-	*	-	*	-	*	-	-
	6	-	*	-	-	-	*	-	*	-	-	-	-
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	-	-	*	-	*	-	*	-	-
24 - 54	1 - 8	1.0	3.4	0.1	*	*	*	0.1	*	*	*	0.3	0.2
25 - 35	1 - 8	-	*	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	1.6	*	*	-	-	-	*	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	*	-	-	-	-	-	-	-	-	-	-
30		-	*	-	-	-	-	-	-	-	-	-	-
31		-	*	-	-	-	*	-	-	-	*	-	-
32		-	0.1	*	*	-	*	-	*	0.1	0.1	-	-
33		0.5	0.8	*	*	-	*	*	*	1.1	0.4	-	*
34		1.5	5.5	3.3	0.2	*	0.3	0.9	0.6	5.2	2.5	0.1	0.4
35		14.3	21.3	7.3	1.7	2.0	3.2	6.4	3.5	13.4	10.8	1.5	3.5
36		42.7	39.1	6.2	8.3	10.2	15.5	20.8	11.7	25.6	27.3	12.8	13.2
37		33.4	29.2	21.3	22.5	44.9	43.5	35.0	27.6	29.8	33.7	33.4	32.7
38		5.0	3.3	20.3	31.0	26.7	21.6	24.6	34.2	15.3	16.8	34.5	27.1
39		0.5	0.4	23.5	26.2	12.0	11.5	10.7	19.7	8.6	7.3	14.8	18.4
40 & Longer		2.1	0.4	18.0	10.0	4.1	4.4	1.6	2.6	1.0	1.1	3.0	4.8
Average Staple		36.35	36.04	37.92	38.03	37.49	37.35	37.15	37.61	36.63	36.76	37.57	37.58
Average Length		1.13	1.12	1.18	1.19	1.17	1.17	1.16	1.18	1.14	1.15	1.17	1.17

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 09, 2020

Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	27.0	45.2	2.9	6.3	1.6	4.1	9.5	26.9	0.5	12.2
	3	7.0	9.1	5.0	8.5	0.6	2.2	5.1	9.7	0.3	13.4
	4	0.2	0.2	0.2	0.5	0.7	0.2	0.6	0.6	-	0.6
	5	-	*	-	*	0.1	*	*	*	-	*
	6	-	-	-	*	-	-	*	*	-	*
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	34.1	54.5	8.1	15.3	2.9	6.5	15.2	37.2	0.7	26.3
31	1 - 2	6.6	7.3	3.1	5.1	4.7	5.8	7.0	4.4	2.2	5.2
	3	22.0	16.6	17.3	25.5	11.3	16.6	13.2	9.9	5.1	21.0
	4	5.5	5.3	6.0	9.3	2.4	5.6	4.2	3.5	1.0	6.4
	5	0.6	0.7	0.5	0.5	0.3	0.5	0.7	0.4	*	0.4
	6	*	*	*	*	*	*	0.1	*	-	*
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	34.6	29.9	27.0	40.4	18.8	28.6	25.2	18.2	8.2	33.0
41	1 - 2	0.1	*	3.9	2.0	2.7	3.8	0.8	0.6	8.1	5.2
	3	2.2	0.5	28.1	18.5	22.9	21.8	3.3	2.4	53.5	24.4
	4	4.4	1.4	19.7	12.9	21.1	21.2	3.2	1.7	16.0	6.7
	5	2.0	1.1	1.8	1.5	5.3	7.3	1.4	0.5	1.3	0.5
	6	0.7	0.5	0.1	0.1	0.1	0.9	0.3	0.1	-	*
	7	0.1	0.2	-	*	-	*	0.1	*	-	-
	8	*	*	-	-	-	*	*	*	-	-
Total	----	9.6	3.8	53.5	35.0	52.1	55.1	9.1	5.4	78.9	36.8
51	1 - 2	-	*	0.6	0.1	0.3	0.2	*	0.1	0.7	0.2
	3	*	*	3.1	1.7	3.7	1.8	0.1	0.3	6.1	1.2
	4	0.1	*	0.7	1.4	8.8	2.5	0.1	0.2	3.6	0.5
	5	*	*	0.2	0.3	4.0	1.3	0.1	0.1	0.5	*
	6	0.1	*	*	*	0.3	0.3	*	*	-	*
	7	0.1	*	*	*	-	*	*	*	-	-
	8	*	*	-	*	-	*	*	*	-	-
Total	----	0.3	0.1	4.7	3.5	17.1	6.1	0.4	0.7	10.9	1.9
61	1 - 2	-	-	-	*	-	*	-	*	-	-
	3	-	-	-	*	-	-	-	*	-	-
	4	-	-	-	*	-	*	-	*	-	-
	5	-	-	-	*	-	*	-	*	-	-
	6	-	-	-	*	-	-	-	*	-	-
	7	-	-	*	*	-	-	-	*	-	-
	8	-	*	-	*	-	-	-	*	-	-
Total	----	-	*	*	*	-	*	-	0.1	-	-
71	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	-	-	-	-	*	-	-
	5	-	-	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	*	-	-	-	*	-	-
Total	----	-	-	-	*	-	-	*	*	-	-
12 & 22	1 - 2	1.6	1.7	*	0.1	0.2	0.1	3.0	8.6	-	0.1
	3	0.7	1.5	0.2	0.2	0.1	0.1	3.0	5.3	-	0.1
	4	*	0.1	*	*	0.3	*	0.4	0.6	-	*
	5	-	*	-	-	*	*	*	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	2.3	3.3	0.2	0.4	0.5	0.2	6.5	14.5	-	0.2
32	1 - 2	0.9	0.5	0.2	0.3	0.2	0.3	4.6	2.6	-	0.1
	3	4.4	2.5	1.1	1.5	0.5	0.8	11.9	6.5	0.1	0.3
	4	2.7	1.6	0.6	0.7	0.4	0.3	5.0	3.0	*	0.1
	5	0.4	0.3	0.1	0.1	0.1	*	0.8	0.5	-	*
	6	*	*	-	*	-	*	0.1	0.1	-	*
	7	-	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	8.4	4.9	2.0	2.5	1.2	1.3	22.3	12.7	0.1	0.5
42	1 - 2	-	*	0.2	0.1	0.1	0.1	0.4	0.2	-	0.1
	3	0.7	0.2	1.8	1.0	0.8	0.8	2.0	0.9	0.4	0.6
	4	2.1	0.5	1.0	0.9	2.1	0.7	2.5	1.1	0.2	0.3
	5	1.5	0.5	0.1	0.2	1.3	0.2	1.5	0.6	-	*
	6	0.6	0.3	0.1	*	0.1	*	0.5	0.2	-	*
	7	0.1	0.1	-	-	-	*	0.1	0.1	-	-
	8	0.1	*	-	-	-	-	*	*	-	-
Total	----	5.0	1.5	3.3	2.2	4.3	1.8	7.1	3.0	0.7	1.1

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE											
For The Week Ending Jan 09, 2020											
Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	0.1	*	-	*	*	*	-	*
	3	-	*	0.3	0.1	0.1	0.1	0.1	0.1	-	*
	4	-	*	0.1	0.1	0.3	0.1	0.1	0.1	*	*
	5	-	*	0.1	*	0.3	*	*	*	-	*
	6	*	*	*	*	*	*	*	*	-	*
	7	*	*	0.1	*	-	*	*	*	-	-
	8	0.1	*	0.1	*	-	-	0.1	*	-	*
	Total	----	0.1	0.1	0.7	0.2	0.7	0.1	0.3	0.3	*
62	1 - 2	-	*	-	-	-	-	-	*	-	*
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	*	-	-	-	*	-	-
	5	-	-	-	*	-	-	-	*	-	-
	6	-	-	-	*	-	-	-	*	-	-
	7	-	-	-	*	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
	Total	----	-	*	-	*	-	-	-	*	-
13 & 23	1 - 2	*	0.1	-	*	-	-	0.7	1.3	-	-
	3	*	0.1	-	*	-	*	0.6	1.1	-	*
	4	-	*	-	*	-	-	0.1	0.1	-	-
	5	-	*	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	0.1	0.2	-	*	-	*	1.3	2.5	-
33	1 - 2	0.2	0.1	*	*	*	*	1.5	0.8	-	*
	3	1.5	0.5	0.1	0.1	0.1	0.1	3.9	2.0	*	*
	4	0.8	0.4	*	*	*	*	1.8	1.0	-	*
	5	0.2	0.1	*	*	*	*	0.4	0.2	-	*
	6	-	*	-	-	-	-	*	*	-	-
	7	-	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	2.7	1.1	0.2	0.2	0.2	0.1	7.6	3.9	*
43	1 - 2	*	*	-	*	*	*	0.4	0.1	-	*
	3	0.4	*	0.1	0.1	0.2	0.1	1.0	0.3	0.2	0.1
	4	0.9	0.1	0.1	0.1	1.0	0.1	0.9	0.3	0.1	*
	5	0.7	0.2	*	*	0.3	*	0.6	0.2	*	*
	6	0.3	0.1	*	*	0.1	*	0.3	0.1	-	-
	7	*	*	*	*	-	-	0.1	*	-	-
	8	*	*	-	-	-	-	*	*	-	-
	Total	----	2.4	0.4	0.3	0.2	1.6	0.3	3.3	0.9	0.4
53	1 - 2	-	-	*	*	-	*	-	*	-	*
	3	-	*	-	*	*	*	*	*	-	*
	4	-	*	-	*	0.1	*	*	*	-	*
	5	*	*	-	*	*	*	*	*	-	-
	6	0.1	*	*	*	*	*	*	*	-	-
	7	*	*	-	-	-	-	*	*	-	-
	8	*	*	-	-	-	-	*	*	-	-
	Total	----	0.1	*	*	*	0.1	*	0.1	*	-
63	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	*	-	-	-	*	-	-
	5	-	-	-	*	-	-	-	*	-	-
	6	-	-	-	*	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
	Total	----	-	-	-	*	-	-	-	*	-
24 - 54	1 - 8	0.2	0.1	*	*	0.4	*	1.4	0.6	*	*
25 - 35	1 - 8	-	*	-	-	-	-	*	*	-	-
81 - 85	1 - 8	*	*	-	*	-	*	0.1	*	-	-
STAPLE											
28 & Shorter		-	*	-	-	-	-	-	*	-	-
29		-	*	-	-	-	-	*	*	-	-
30		0.2	*	-	-	-	-	0.3	0.2	-	-
31		0.6	0.2	0.2	*	-	-	1.8	1.2	-	-
32		0.8	1.2	0.9	0.3	-	*	6.2	3.8	-	*
33		7.4	4.8	2.6	1.8	-	*	11.3	8.6	0.1	0.1
34		11.2	9.1	6.0	5.9	0.3	1.0	19.0	15.0	0.2	0.7
35		17.7	13.4	13.6	13.1	8.2	11.9	21.5	20.2	1.4	4.7
36		17.0	16.5	23.6	20.1	31.7	36.5	17.1	19.6	21.2	16.7
37		19.4	24.3	38.4	37.4	40.6	37.7	13.9	19.1	38.3	39.0
38		13.0	16.3	12.5	17.0	15.2	10.4	5.5	8.2	32.5	23.6
39		9.3	9.9	2.0	4.0	3.7	2.4	2.6	3.2	5.9	12.4
40 & Longer		3.3	4.2	0.3	0.4	0.3	0.2	0.9	0.9	0.4	2.8
Average Staple		36.17	36.52	36.33	36.53	36.75	36.52	35.08	35.50	37.21	37.28
Average Length		1.13	1.14	1.13	1.14	1.15	1.14	1.09	1.11	1.16	1.16

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 09, 2020

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	6.0	2.2	2.6	0.8	2.5	0.8	3.6	1.3	9.7	6.5	5.5	3.1
Bark - Level 2	-	*	-	*	-	-	-	-	-	-	-	*
Grass - Level 1	*	0.1	0.4	0.1	-	*	*	*	-	0.1	*	0.1
Grass - Level 2	-	*	-	-	-	-	-	-	-	-	-	*
Prep - Level 1	*	*	-	*	-	*	-	*	-	*	0.1	*
Prep - Level 2	-	*	-	-	-	-	-	-	-	-	*	*
Seed Coat - Level 1	*	*	-	*	*	1.1	-	*	-	*	*	*
Seed Coat - Level 2	-	*	-	-	-	-	-	-	-	-	-	*
Oil - Level 1	-	*	-	*	*	*	-	-	-	-	*	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	*
Spindle Twist - Level 1	-	-	-	-	*	*	-	*	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	-	0.1	-	*	-	*	-	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	*	*	*	-	*	*	*
Plastic - Level 2	-	-	-	*	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	*	-	*	-	-	-	-	-	-	-	*
23	*	*	-	*	*	*	-	-	-	*	0.1	*
24	0.1	*	*	*	0.1	*	-	-	*	*	0.3	0.2
25	0.4	0.4	0.1	*	0.7	0.2	-	*	0.1	0.1	1.5	0.9
26	3.0	1.8	0.6	0.2	1.5	0.5	-	*	1.0	0.8	4.5	3.3
27	13.2	7.5	3.2	1.2	2.9	1.9	*	0.4	3.9	3.5	9.9	8.4
28	24.3	20.7	10.3	5.9	4.6	5.6	0.1	0.6	19.7	11.9	16.8	15.4
29	28.2	29.8	22.6	19.0	10.2	13.3	0.9	2.9	34.0	24.8	21.3	21.7
30	16.6	21.6	26.5	30.2	15.6	23.2	8.0	10.5	23.6	29.8	20.2	22.3
31	7.6	10.9	18.4	24.5	21.1	21.5	16.5	15.4	9.5	16.8	14.1	14.8
32	3.5	4.7	9.4	12.4	18.9	15.1	16.5	16.4	5.1	7.3	7.1	7.7
33	1.7	1.7	5.9	4.5	12.9	9.7	14.6	11.3	2.1	3.5	3.1	3.5
34	0.7	0.6	2.4	1.6	7.2	5.2	6.9	6.3	0.7	1.0	0.9	1.3
35	0.4	0.2	0.7	0.4	2.8	2.4	9.6	9.9	0.1	0.3	0.2	0.4
36	0.2	0.1	0.1	0.1	0.7	1.0	13.4	13.0	0.1	0.1	0.1	0.1
37	0.1	*	*	*	0.4	0.3	8.2	9.6	-	*	*	*
38	-	*	-	*	0.3	0.1	3.3	2.7	-	-	-	*
39	-	*	-	*	0.2	*	1.6	0.6	-	-	-	-
40 & Above	-	-	-	-	0.1	*	0.3	0.3	-	-	-	-
Average	29.40	29.71	30.58	30.81	31.58	31.34	33.96	33.72	29.84	30.30	29.76	29.98
Mike												
2.4 & Below	-	-	-	-	0.1	*	-	-	-	-	-	-
2.5	-	*	-	-	0.4	*	-	*	-	*	*	*
2.6	-	*	-	-	0.1	*	-	-	*	*	*	*
2.7	-	*	-	-	*	*	-	*	*	*	*	*
2.8	*	*	-	*	*	*	0.1	*	0.1	*	*	*
2.9	-	*	-	*	0.1	*	-	0.1	*	*	*	*
3.0	*	*	-	*	0.1	*	0.1	0.2	*	*	*	*
3.1	*	*	-	*	0.1	0.1	0.3	0.4	0.1	*	*	*
3.2	*	*	-	*	0.3	0.1	0.1	0.4	*	*	*	*
3.3	-	0.1	-	*	0.3	0.2	0.6	0.4	0.2	*	*	*
3.4	0.1	0.2	*	*	0.4	0.2	1.2	0.6	*	*	0.1	0.1
3.5	0.3	0.4	0.2	0.1	0.5	0.4	1.3	0.9	0.2	*	0.1	0.1
3.6	0.3	0.9	0.2	0.3	1.0	0.7	1.3	1.5	0.1	*	0.2	0.2
3.7	0.8	1.8	0.4	0.6	1.1	1.1	1.1	1.5	0.2	*	0.3	0.3
3.8	1.9	2.8	1.4	1.2	1.5	1.8	1.6	2.1	0.8	0.1	0.8	0.6
3.9	3.3	4.2	3.0	2.0	1.9	1.9	2.4	3.0	1.5	0.4	1.7	1.0
4.0	5.4	5.9	4.4	3.4	3.1	2.7	5.7	5.2	1.8	0.7	3.0	1.8
4.1	8.9	7.6	6.2	5.1	4.6	3.7	7.6	7.6	2.6	1.6	4.5	3.1
4.2	10.6	9.3	8.8	7.8	5.3	4.8	10.1	8.9	2.7	3.1	7.3	5.5
4.3	13.4	10.5	11.1	10.3	5.4	6.3	10.3	9.5	9.5	6.4	10.9	8.7
4.4	15.2	11.8	9.9	11.9	7.2	8.9	16.0	11.5	11.6	13.1	13.9	12.3
4.5	12.7	12.2	8.3	13.6	7.3	10.9	14.7	11.4	18.2	18.4	15.2	14.9
4.6	8.8	11.0	8.2	13.4	9.5	12.5	13.6	11.3	20.8	18.7	14.0	15.4
4.7	8.2	9.0	7.1	10.7	9.5	11.5	6.0	8.4	15.6	15.8	10.9	13.2
4.8	5.2	5.7	7.2	7.9	10.1	9.6	4.4	5.4	10.2	10.6	8.1	9.8
4.9	2.3	3.4	8.2	5.1	8.8	7.0	1.0	3.1	3.5	5.9	4.7	6.4
5.0	1.5	1.8	7.8	3.1	7.6	5.5	0.6	1.8	0.4	2.9	2.5	3.5
5.1	0.8	0.8	4.9	1.7	4.8	4.0	0.1	1.3	-	1.7	1.1	1.8
5.2	0.3	0.3	1.9	1.0	3.3	2.5	-	1.3	-	0.5	0.4	0.6
5.3	0.1	0.1	0.5	0.5	2.5	1.8	*	0.8	-	0.1	0.1	0.3
5.4	*	*	0.2	0.2	1.5	1.1	-	0.6	-	*	*	0.1
5.5 & Above	*	*	*	0.1	1.4	0.6	-	0.8	-	*	*	*
Average	4.38	4.38	4.52	4.49	4.59	4.57	4.33	4.39	4.51	4.59	4.49	4.55

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 09, 2020

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	16.1	22.2	1.5	1.2	0.3	0.3	2.3	1.1	0.8	2.3	0.4	2.0
Bark - Level 2	-	-	-	-	-	-	-	*	-	-	-	*
Grass - Level 1	-	*	0.1	0.1	*	*	*	0.1	*	0.3	-	*
Grass - Level 2	-	-	-	-	-	-	-	*	-	-	-	-
Prep - Level 1	-	*	-	*	-	*	*	*	-	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	*	-	*	-	*	-	*	-	*	-	*
Seed Coat - Level 2	-	-	-	-	-	-	-	*	-	-	-	-
Oil - Level 1	-	-	-	*	-	*	-	*	-	*	-	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	*	-	*	*	*	-	*	-	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	*	0.1	*	-	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	*	-	-	-	-
STRENGTH 1/ 22 & Below	-	0.1	-	-	-	*	-	*	-	-	-	-
23	-	0.2	-	-	-	*	-	*	*	*	-	-
24	-	0.6	*	*	*	*	*	*	0.1	*	-	*
25	*	1.6	0.4	*	-	*	0.3	0.1	0.6	0.1	-	*
26	*	3.6	1.0	0.2	*	0.2	1.8	0.5	1.8	0.7	1.3	0.2
27	0.6	5.1	0.8	0.9	0.4	1.8	5.0	2.0	5.2	1.9	8.1	2.0
28	3.4	6.4	0.8	5.3	5.6	8.4	14.0	5.9	9.7	4.9	30.2	11.2
29	14.7	16.7	9.2	19.0	25.9	24.3	25.1	15.2	17.6	13.1	31.5	19.9
30	25.8	23.6	24.1	26.4	38.8	34.5	24.9	29.3	24.0	23.9	15.9	25.5
31	26.3	20.1	30.1	20.2	18.2	20.4	16.6	27.4	24.3	24.3	9.8	23.1
32	15.3	11.7	21.3	14.4	5.7	7.2	9.7	12.6	11.1	17.1	3.2	13.1
33	7.2	5.7	6.3	8.5	3.8	2.2	2.1	5.3	3.9	9.2	*	4.4
34	5.0	3.5	3.8	3.5	1.1	0.7	0.3	1.5	1.2	3.5	0.1	0.4
35	1.3	0.9	1.4	1.2	0.4	0.2	0.1	0.2	0.3	0.9	-	*
36	0.2	0.2	0.8	0.3	*	*	*	*	0.1	0.2	-	*
37	0.1	*	*	0.1	*	*	-	*	*	0.1	-	*
38	*	*	*	*	-	*	-	*	-	*	-	*
39	-	-	-	-	-	*	-	*	-	-	-	-
40 & Above	-	-	-	-	-	-	-	-	-	-	-	-
Average	31.29	30.53	31.47	31.09	30.54	30.43	30.12	30.86	30.46	31.19	29.40	30.61
Mike												
2.4 & Below	-	*	-	-	-	-	-	-	-	-	-	-
2.5	-	0.2	-	-	-	-	-	-	-	*	-	-
2.6	0.4	0.2	-	-	-	-	-	-	-	*	-	-
2.7	0.2	0.5	-	-	-	-	-	-	-	*	-	-
2.8	*	0.5	-	-	-	-	-	*	-	*	-	*
2.9	0.8	0.9	-	-	-	-	-	*	-	*	-	0.2
3.0	1.6	1.9	-	*	-	*	-	*	-	*	-	0.2
3.1	0.8	3.1	-	*	*	*	-	*	-	*	-	0.1
3.2	1.0	3.3	-	*	*	*	-	*	*	*	-	0.2
3.3	2.7	3.8	-	*	*	*	*	*	*	*	*	0.3
3.4	3.4	4.4	-	*	0.1	0.1	*	*	*	*	0.8	0.6
3.5	6.0	5.2	0.1	*	0.2	0.1	*	*	0.2	0.1	1.2	1.9
3.6	9.5	6.2	0.3	0.1	0.3	0.2	0.2	0.1	0.5	0.1	4.4	2.4
3.7	8.7	6.2	0.4	0.2	0.5	0.4	0.3	0.2	0.6	0.3	4.8	4.3
3.8	7.7	6.4	0.5	0.5	1.6	0.9	0.7	0.5	0.5	0.5	7.4	5.3
3.9	9.6	8.2	0.1	1.0	1.9	1.7	0.8	1.0	1.2	1.0	7.9	6.2
4.0	8.0	7.5	1.4	1.4	2.6	3.0	1.5	1.9	1.9	1.4	11.1	7.3
4.1	7.0	7.3	1.7	2.5	4.6	4.8	1.6	2.9	3.3	2.2	10.4	7.5
4.2	9.8	6.8	4.9	4.3	7.0	7.6	4.4	4.3	5.4	3.4	5.4	8.5
4.3	7.8	5.6	9.6	7.6	9.7	9.8	7.1	6.6	9.2	5.3	5.9	8.7
4.4	5.0	4.9	10.3	11.3	9.7	11.9	11.1	9.9	10.1	8.2	7.6	10.7
4.5	3.5	4.6	12.5	15.9	13.1	12.9	14.0	13.1	13.5	11.2	8.6	9.3
4.6	2.1	3.7	16.6	16.7	13.2	12.4	17.4	15.5	15.1	14.2	7.3	8.9
4.7	2.1	3.0	14.1	16.1	11.6	11.2	18.7	15.6	13.6	15.2	6.3	6.0
4.8	0.9	2.3	10.2	11.0	10.3	8.6	11.0	12.8	8.8	13.7	2.9	3.7
4.9	1.0	1.5	10.4	6.1	7.9	6.1	5.3	8.1	6.6	10.7	3.0	2.1
5.0	0.3	0.9	3.2	3.0	3.3	4.0	3.4	4.1	4.8	6.6	1.3	1.4
5.1	*	0.5	3.2	1.4	1.5	2.5	1.6	1.9	2.5	3.4	0.8	1.8
5.2	*	0.1	0.3	0.5	0.5	1.2	0.7	0.9	0.8	1.5	0.9	1.5
5.3	-	0.1	*	0.2	0.3	0.4	0.1	0.4	0.7	0.6	1.0	0.7
5.4	-	*	*	0.1	0.1	0.1	*	0.1	0.1	0.3	1.1	0.3
5.5 & Above	-	*	0.1	*	-	*	-	*	0.5	0.2	-	*
Average	3.93	3.93	4.59	4.57	4.52	4.52	4.57	4.59	4.56	4.64	4.25	4.29

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 09, 2020

Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter										
Bark - Level 1	16.6	7.2	1.0	1.6	0.4	0.3	21.7	8.8	2.4	0.7
Bark - Level 2	-	-	-	-	-	-	-	*	-	-
Grass - Level 1	-	*	0.9	0.3	-	*	*	0.1	0.1	0.1
Grass - Level 2	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	*	-	*	-	*	*	*	-	*
Prep - Level 2	-	-	-	-	-	-	-	*	-	-
Seed Coat - Level 1	*	*	-	*	-	*	*	0.1	-	*
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	*	*	-	-	-	*	-	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	*	*	-	*	*	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	0.1	*	*	*	-	*	*	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	*	-	*	-	*	*	*	-	-
23	*	*	*	*	-	*	*	0.1	-	-
24	0.1	0.1	0.2	0.1	*	*	0.2	0.4	*	*
25	0.4	0.2	1.0	0.5	0.3	*	0.5	1.0	0.1	*
26	0.9	0.6	2.9	2.0	2.1	0.5	1.9	2.5	0.1	0.4
27	2.6	1.8	6.3	5.0	11.0	4.2	4.9	5.5	1.5	1.5
28	4.9	4.4	21.8	11.7	25.6	18.6	9.3	10.4	3.2	4.2
29	8.9	8.9	33.2	24.3	29.4	31.2	15.0	16.1	20.2	13.5
30	13.6	15.1	19.8	25.9	17.4	24.4	18.6	20.0	34.4	26.6
31	13.4	18.1	9.3	16.4	8.8	12.3	18.8	18.2	30.0	25.7
32	15.5	16.5	3.6	8.1	2.9	5.7	14.1	12.8	7.7	17.4
33	14.7	13.6	1.5	3.7	1.5	2.3	8.3	7.3	2.1	7.3
34	11.4	9.9	0.4	1.5	0.6	0.6	4.5	3.5	0.6	2.4
35	6.3	6.0	0.1	0.5	0.3	0.2	2.1	1.5	0.1	0.8
36	4.0	3.2	*	0.1	*	*	1.0	0.6	*	0.2
37	2.3	1.2	-	*	*	*	0.5	0.2	-	*
38	0.8	0.3	-	*	-	*	0.2	0.1	-	-
39	*	*	-	-	-	*	*	*	-	-
40 & Above	-	-	-	-	-	-	*	*	-	-
Average	32.24	32.10	29.55	30.25	29.45	29.95	30.97	30.66	30.66	31.15
Mike										
2.4 & Below	-	-	-	*	-	-	0.1	*	-	-
2.5	*	*	*	*	-	-	0.2	0.1	-	-
2.6	0.1	*	-	*	-	-	0.3	0.1	-	-
2.7	0.1	*	-	*	-	-	0.3	0.1	-	-
2.8	0.3	*	-	*	-	*	0.4	0.2	-	-
2.9	0.2	*	-	*	-	*	0.5	0.3	-	-
3.0	0.2	0.1	-	*	*	*	0.6	0.3	-	-
3.1	0.2	0.2	-	*	0.1	*	0.7	0.5	-	-
3.2	0.3	0.3	*	*	0.2	*	0.9	0.7	-	*
3.3	0.3	0.3	*	*	0.2	*	1.1	0.9	-	*
3.4	0.4	0.4	0.1	*	0.7	0.1	1.4	1.2	-	*
3.5	1.2	0.8	0.2	0.1	0.9	0.2	1.9	1.5	-	*
3.6	1.7	1.4	0.4	0.1	1.7	0.4	2.5	1.9	-	*
3.7	3.1	2.2	0.7	0.3	2.8	0.7	3.0	2.4	*	0.1
3.8	3.1	3.1	1.1	0.4	3.8	1.0	3.5	3.0	0.5	0.1
3.9	3.4	4.0	2.3	0.7	4.5	1.8	4.2	3.7	0.6	0.3
4.0	4.4	4.9	2.6	1.4	5.7	2.6	4.9	4.5	1.0	0.6
4.1	5.8	5.9	5.9	2.9	6.0	3.7	5.5	5.5	3.4	1.3
4.2	6.4	6.9	8.2	5.0	6.4	5.5	6.1	6.6	4.8	2.2
4.3	8.1	8.2	11.4	8.3	5.4	8.1	6.9	7.7	9.8	4.1
4.4	8.6	9.3	14.1	11.3	7.3	11.1	7.5	8.9	15.5	7.0
4.5	9.3	9.8	14.8	13.9	8.7	13.6	7.7	9.5	16.4	11.5
4.6	8.1	9.7	11.0	15.0	10.6	14.4	7.8	9.5	22.3	15.9
4.7	8.3	9.2	10.5	14.3	7.6	13.0	7.7	9.1	12.8	18.0
4.8	7.3	7.5	8.4	11.5	8.7	10.3	6.8	7.7	6.2	15.5
4.9	6.9	5.9	4.7	7.4	9.9	6.8	6.0	5.8	3.8	11.2
5.0	5.7	4.4	1.4	3.9	6.3	3.8	4.8	4.0	2.6	6.8
5.1	3.6	2.7	0.9	1.8	1.9	1.9	3.1	2.4	0.1	3.1
5.2	2.1	1.7	0.6	0.8	0.5	0.7	1.9	1.2	*	1.4
5.3	0.5	0.8	0.5	0.5	0.2	0.2	1.0	0.6	-	0.6
5.4	0.1	0.2	0.2	0.3	*	*	0.4	0.2	-	0.3
5.5 & Above	*	0.1	*	0.1	*	*	0.2	0.1	-	0.1
Average	4.43	4.44	4.47	4.58	4.43	4.53	4.34	4.39	4.52	4.68

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 09, 2020

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	-	-	-	0.1	*	-	-	-	-	-	-
2.5 - 2.6	-	*	-	-	0.5	*	-	*	*	*	*	*
2.7 - 2.9	*	*	-	*	0.1	*	0.1	0.2	0.1	*	*	*
3.0 - 3.2	*	0.1	-	*	0.6	0.3	0.5	1.0	0.1	*	0.1	*
3.3 - 3.4	0.1	0.3	*	0.1	0.7	0.4	1.7	1.0	0.2	*	0.1	0.1
3.5 - 3.6	0.6	1.3	0.4	0.4	1.5	1.1	2.5	2.5	0.3	*	0.2	0.3
3.7 - 4.2	30.9	31.7	24.3	20.1	17.5	16.1	28.5	28.4	9.5	5.9	17.6	12.4
4.3 - 4.9	65.8	63.6	59.9	72.9	57.8	66.7	66.0	60.6	89.3	88.8	77.9	80.7
5.0 - 5.2	2.5	2.9	14.6	5.8	15.7	12.0	0.7	4.3	0.4	5.1	3.9	5.9
5.3 & Above	0.1	0.2	0.8	0.7	5.5	3.4	*	2.2	-	0.1	0.1	0.4
Average	4.38	4.38	4.52	4.49	4.59	4.57	4.33	4.39	4.51	4.59	4.49	4.55
Leaf												
1 - 2	7.7	13.9	2.0	9.2	45.0	69.1	51.5	69.9	6.1	6.4	7.7	17.1
3	50.1	48.6	30.3	37.3	30.1	21.7	36.8	24.0	50.8	38.6	46.3	48.4
4	34.4	30.3	39.4	35.7	17.1	6.4	10.1	5.4	32.8	44.1	37.2	28.8
5	7.0	6.3	23.8	15.9	6.1	1.9	1.5	0.7	9.0	10.2	8.1	5.4
6	0.8	0.8	4.6	1.8	1.3	0.6	0.1	*	1.3	0.7	0.6	0.4
7	0.1	0.1	*	*	0.3	0.2	*	*	*	*	*	*
8	*	*	-	*	0.1	0.1	-	-	-	*	*	*
Average	3.43	3.31	3.99	3.64	2.80	2.20	2.53	2.13	3.48	3.60	3.47	3.22
HVI Trash 1/												
00	-	*	-	*	-	*	-	0.1	-	-	-	*
01	1.1	2.8	0.1	1.4	19.0	39.2	20.2	38.3	0.9	1.1	1.4	3.8
02	9.8	15.3	2.7	9.7	28.7	33.6	36.2	34.9	7.8	7.7	9.5	17.5
03	25.0	24.8	11.2	16.5	17.9	13.2	21.9	15.0	25.3	17.0	22.1	24.5
04	26.7	23.2	17.5	18.3	12.9	6.3	11.2	6.3	24.0	23.2	25.0	22.0
05	18.2	15.9	17.6	17.0	8.6	3.2	6.0	3.0	16.9	21.5	18.7	15.2
06	9.9	9.1	16.0	14.2	5.6	1.8	2.7	1.5	11.9	14.6	11.8	8.8
07	4.8	4.7	13.0	10.3	3.3	1.0	1.1	0.6	6.4	8.0	6.2	4.5
08	2.2	2.2	9.9	6.4	1.9	0.6	0.4	0.2	3.5	3.8	3.1	2.1
09	1.1	1.0	6.3	3.4	0.9	0.4	0.2	0.1	1.8	1.7	1.3	0.9
10	0.6	0.5	3.5	1.6	0.5	0.2	0.1	*	0.8	0.8	0.5	0.4
11	0.3	0.2	1.5	0.7	0.3	0.2	*	*	0.4	0.3	0.2	0.2
12	0.2	0.1	0.6	0.3	0.2	0.1	*	*	0.2	0.1	0.1	0.1
13	0.1	*	0.2	0.1	0.1	0.1	-	*	*	*	*	*
14	*	*	*	*	*	*	*	*	*	*	*	*
15	*	*	*	*	*	*	-	*	-	*	*	*
16	*	*	*	*	*	*	-	-	-	*	*	*
17	*	*	-	*	*	*	-	-	-	*	-	*
18 & Above	*	*	-	*	*	*	-	-	-	*	*	*
Average	0.43	0.40	0.58	0.50	0.32	0.22	0.26	0.21	0.45	0.47	0.44	0.39
UNIFORMITY 2/												
74 & Below	-	-	-	-	-	-	-	-	-	-	-	-
75	-	*	-	*	-	*	-	-	-	-	-	*
76	*	*	*	*	*	*	-	*	-	*	*	*
77	0.3	0.2	*	0.1	0.1	0.2	*	*	-	*	0.1	0.1
78	2.3	2.2	0.4	0.4	1.6	1.8	0.1	0.4	0.4	0.3	1.0	0.9
79	9.5	11.3	2.3	2.3	7.9	8.6	2.9	2.6	3.5	2.0	5.5	5.2
80	27.9	30.6	11.8	12.3	29.0	22.4	24.3	14.3	11.9	13.3	18.2	19.1
81	40.7	35.4	31.6	35.4	34.8	35.6	28.9	30.2	50.8	41.4	35.0	37.2
82	16.0	16.4	37.4	35.4	21.5	25.2	10.0	24.4	26.4	32.7	29.8	27.9
83	2.8	3.4	14.2	12.6	4.3	5.4	18.3	15.9	6.3	8.6	8.9	8.1
84	0.5	0.4	2.2	1.5	0.8	0.7	15.0	11.6	0.7	1.6	1.4	1.2
85 & Above	0.1	*	0.1	0.1	*	0.2	0.4	0.4	-	0.1	0.1	0.1
Average	81.13	81.09	82.01	81.92	81.28	81.38	82.08	82.17	81.65	81.82	81.64	81.60
Tenderable 3/	78.5	86.4	76.6	90.0	68.7	79.8	90.9	88.4	77.3	83.1	82.8	85.2
SAMPLES CLASSED	29,706	922,738	35,575	1,383,271	22,458	221,512	19,598	153,328	3,387	148,081	96,710	2,565,544

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 09, 2020

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	*	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	0.4	0.4	-	-	-	-	-	-	-	*	-	-
2.7 - 2.9	1.0	1.9	-	-	-	-	-	*	-	*	-	0.2
3.0 - 3.2	3.4	8.3	-	*	*	*	-	*	*	*	-	0.5
3.3 - 3.4	6.1	8.2	-	*	0.1	0.1	*	*	0.1	*	0.8	0.9
3.5 - 3.6	15.5	11.4	0.4	0.2	0.5	0.3	0.3	0.1	0.7	0.2	5.6	4.2
3.7 - 4.2	51.0	42.4	9.0	9.8	18.2	18.4	9.4	10.8	12.8	8.8	46.9	39.0
4.3 - 4.9	22.4	25.6	83.7	84.7	75.5	73.0	84.6	81.6	76.9	78.4	41.7	49.4
5.0 - 5.2	0.3	1.6	6.7	4.9	5.3	7.6	5.6	6.9	8.2	11.5	2.9	4.7
5.3 & Above	-	0.2	0.2	0.3	0.3	0.5	0.2	0.5	1.4	1.0	2.1	1.1
Average	3.93	3.93	4.59	4.57	4.52	4.52	4.57	4.59	4.56	4.64	4.25	4.29
Leaf												
1 - 2	48.8	38.5	5.1	19.3	6.3	9.9	26.3	17.4	11.4	11.3	50.7	64.0
3	28.7	28.1	34.9	41.9	44.2	39.6	37.8	39.9	64.1	52.0	40.4	28.9
4	15.3	15.4	48.3	29.4	37.5	35.1	27.0	31.6	22.7	31.6	7.0	5.8
5	5.3	8.6	11.0	8.4	10.5	13.8	8.2	9.8	1.8	4.9	1.6	1.1
6	0.6	4.6	0.6	1.0	1.5	1.5	0.7	1.2	*	0.3	0.3	0.2
7	0.5	2.7	-	*	-	*	*	0.1	-	*	0.1	*
8	0.8	2.1	-	*	-	-	*	*	-	*	-	*
Average	2.79	3.24	3.67	3.29	3.57	3.57	3.17	3.36	3.15	3.31	2.53	2.29
HVI Trash 1/												
00	-	-	-	-	-	*	*	*	-	-	-	*
01	18.3	13.9	0.7	4.1	0.7	1.3	7.3	4.3	0.7	1.4	12.3	24.1
02	33.9	27.8	6.8	19.5	6.7	9.4	22.1	16.2	13.1	12.2	34.3	38.6
03	15.3	15.4	13.2	20.3	17.7	17.2	19.3	19.1	32.6	24.9	29.9	20.5
04	10.9	10.4	20.6	17.9	21.8	19.0	16.1	18.2	27.0	25.7	12.4	8.9
05	8.4	7.6	22.0	14.5	19.7	17.3	13.1	15.4	15.3	18.0	5.0	4.1
06	5.2	5.2	17.8	10.2	14.6	13.9	9.5	11.2	7.0	9.9	2.9	2.0
07	3.0	4.0	10.7	6.4	8.7	9.8	6.4	7.3	2.7	4.6	1.7	0.9
08	1.9	3.0	4.8	3.6	5.1	6.0	3.5	4.2	1.2	2.0	0.7	0.5
09	0.9	2.5	2.1	1.8	2.5	3.3	1.6	2.2	0.3	0.8	0.4	0.2
10	0.5	2.1	0.8	0.9	1.4	1.6	0.7	1.1	0.1	0.3	0.2	0.1
11	0.2	1.7	0.3	0.5	0.6	0.7	0.3	0.5	*	0.1	0.2	0.1
12	0.1	1.4	0.1	0.2	0.3	0.3	0.1	0.2	*	*	*	0.1
13	0.2	1.1	-	0.1	0.2	0.1	*	0.1	-	*	*	*
14	0.2	0.9	*	*	*	*	*	*	*	*	-	*
15	0.2	0.7	*	*	*	*	-	*	-	*	*	*
16	0.2	0.6	-	*	*	*	*	*	*	*	-	-
17	0.2	0.4	*	*	*	*	*	*	-	*	-	-
18 & Above	0.4	1.4	-	*	-	*	-	*	-	*	-	*
Average	0.32	0.44	0.50	0.42	0.49	0.49	0.40	0.44	0.38	0.41	0.29	0.25
UNIFORMITY 2/												
74 & Below	-	*	-	-	-	-	-	-	-	-	-	-
75	-	*	-	-	-	-	-	*	-	*	-	-
76	*	0.2	-	-	-	*	*	*	*	*	-	-
77	0.4	0.8	*	*	*	*	0.2	0.1	0.1	0.1	-	*
78	2.7	2.5	0.1	0.3	0.1	0.1	1.4	0.9	0.9	0.6	0.1	0.1
79	9.8	13.7	1.4	2.1	0.8	0.9	9.3	4.5	5.5	4.5	0.4	1.3
80	37.1	38.1	7.6	13.8	8.7	6.7	25.5	20.2	23.3	19.9	4.7	10.9
81	41.2	37.0	29.4	37.2	33.9	26.5	45.6	44.8	37.9	37.9	33.3	27.4
82	8.6	7.3	39.8	33.3	39.9	42.5	15.5	25.0	25.5	29.2	54.0	46.4
83	0.2	0.4	18.1	11.3	13.7	20.5	2.2	4.0	5.9	6.9	7.4	13.6
84	*	*	3.4	1.8	2.4	2.5	0.3	0.4	0.8	0.8	0.1	0.3
85 & Above	-	*	0.3	0.3	0.5	0.2	*	*	*	0.1	-	*
Average	80.88	80.76	82.21	81.88	82.11	82.28	81.16	81.47	81.47	81.59	82.11	82.05
Tenderable 3/	74.1	55.6	79.8	89.5	91.2	89.4	88.6	88.4	86.6	83.3	81.2	86.1
SAMPLES CLASSED	16,040	122,061	12,224	567,744	32,760	784,323	33,553	1,493,173	21,604	1,020,674	3,159	26,761

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 09, 2020

Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE										
2.4 & Below	-	-	-	*	-	-	0.1	*	-	-
2.5 - 2.6	0.1	*	*	*	-	-	0.6	0.1	-	-
2.7 - 2.9	0.7	0.1	-	*	-	*	1.2	0.6	-	-
3.0 - 3.2	0.7	0.5	*	*	0.3	0.1	2.2	1.5	-	*
3.3 - 3.4	0.7	0.7	0.1	*	0.9	0.1	2.5	2.0	-	*
3.5 - 3.6	2.8	2.2	0.6	0.2	2.5	0.6	4.5	3.3	-	*
3.7 - 4.2	26.3	26.9	20.8	10.7	29.2	15.3	27.2	25.7	10.5	4.5
4.3 - 4.9	56.6	59.6	74.9	81.5	58.2	77.2	50.4	58.1	86.8	83.1
5.0 - 5.2	11.4	8.8	2.9	6.5	8.6	6.4	9.7	7.6	2.7	11.4
5.3 & Above	0.7	1.1	0.7	1.0	0.2	0.2	1.6	0.9	-	1.0
Average	4.43	4.44	4.47	4.58	4.43	4.53	4.34	4.39	4.52	4.68
Leaf										
1 - 2	36.5	54.8	11.1	14.2	9.7	14.4	28.2	45.5	11.5	23.0
3	38.8	31.0	57.1	57.1	40.4	44.2	45.1	38.7	65.7	61.1
4	16.7	9.8	28.5	25.9	37.4	30.7	19.1	12.4	21.1	14.8
5	5.4	3.0	2.9	2.7	11.8	9.4	5.6	2.6	1.8	1.0
6	1.8	1.0	0.3	0.1	0.7	1.2	1.4	0.6	-	*
7	0.4	0.3	0.1	*	-	*	0.4	0.2	-	-
8	0.2	0.1	0.1	*	-	*	0.2	*	-	*
Average	2.92	2.50	3.25	3.17	3.53	3.38	3.05	2.65	3.13	2.93
HVI Trash 1/										
00	*	*	-	*	-	*	*	*	-	-
01	13.1	26.1	0.9	1.7	0.9	2.3	7.5	17.3	0.4	2.9
02	27.4	32.4	12.8	15.5	9.6	13.4	25.8	32.2	13.0	22.2
03	21.9	18.8	28.3	28.7	18.8	20.9	26.1	22.8	30.4	33.0
04	14.3	9.8	28.0	25.6	21.6	20.2	17.0	13.2	28.2	23.5
05	9.2	5.3	16.7	15.6	18.8	16.1	10.0	7.1	16.4	11.4
06	5.6	3.0	7.8	7.6	14.2	11.4	5.8	3.6	7.4	4.5
07	3.3	1.7	3.3	3.3	8.7	7.2	3.4	1.8	2.7	1.6
08	1.9	1.0	1.3	1.2	4.3	4.2	1.9	0.9	1.1	0.6
09	1.3	0.6	0.5	0.5	1.8	2.2	1.1	0.5	0.3	0.2
10	0.8	0.4	0.2	0.2	0.7	1.1	0.6	0.3	0.1	0.1
11	0.5	0.3	0.1	0.1	0.3	0.6	0.4	0.1	*	*
12	0.3	0.2	*	*	0.1	0.3	0.2	0.1	*	*
13	0.2	0.1	*	*	*	0.1	0.1	*	-	*
14	0.1	0.1	*	*	*	*	0.1	*	-	*
15	0.1	*	*	*	-	*	*	*	-	*
16	0.1	*	*	*	*	*	*	*	-	*
17	*	*	*	*	-	*	*	*	-	-
18 & Above	*	*	*	*	-	*	*	*	-	-
Average	0.34	0.27	0.40	0.39	0.47	0.45	0.36	0.29	0.39	0.34
UNIFORMITY 2/										
74 & Below	-	*	-	-	-	-	0.1	*	-	-
75	*	*	-	*	-	-	0.4	0.1	-	*
76	0.1	0.2	0.1	*	-	*	1.8	0.6	*	*
77	0.9	1.0	0.5	0.3	*	0.1	5.9	2.6	*	0.1
78	5.0	3.8	1.9	1.5	0.8	0.5	14.2	8.2	0.2	0.2
79	17.4	12.3	10.4	7.8	7.2	5.1	25.2	19.7	0.4	1.3
80	35.0	28.1	42.1	30.7	26.5	22.5	28.8	30.3	11.0	8.9
81	27.5	33.6	35.1	40.3	38.7	36.5	16.9	25.6	41.2	34.9
82	11.0	17.0	8.3	16.1	22.5	26.8	5.8	10.7	42.4	39.4
83	2.7	3.4	1.5	3.0	4.2	7.9	0.9	1.9	4.6	13.0
84	0.4	0.4	0.1	0.3	0.1	0.7	0.1	0.2	0.2	2.1
85 & Above	*	0.1	*	*	*	0.1	*	*	*	0.2
Average	80.74	81.01	80.85	81.16	81.33	81.55	79.96	80.51	81.84	82.05
Tenderable 3/	65.5	79.1	89.6	87.4	81.6	89.5	46.5	66.4	93.7	85.8
SAMPLES CLASSED	35,198	398,472	13,755	401,980	16,336	929,816	197,524	6,070,468	4,958	204,471

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 09, 2020

Color Grade	Leaf	Arizona		California		New Mexico		Texas	
		Week	Season	Week	Season	Week	Season	Week	Season
01	1	70.8	57.2	29.9	26.9	-	-	-	11.0
	2	6.3	6.8	6.7	7.9	-	-	-	15.3
	3	-	1.4	*	*	-	-	-	0.3
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		77.1	65.4	36.6	34.8	-	-	-	26.6
02	1	11.6	22.4	30.3	30.7	-	-	-	15.0
	2	9.9	7.8	29.1	31.2	-	-	-	44.4
	3	0.1	2.3	0.7	0.9	-	-	-	5.3
	4	-	1.0	-	*	-	-	-	0.1
	5	-	*	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		21.6	33.7	60.1	62.8	-	-	-	64.7
03	1	0.1	0.1	0.5	0.3	-	-	-	1.0
	2	1.0	0.5	1.9	1.5	-	-	-	5.2
	3	0.1	0.1	0.7	0.5	-	-	-	1.8
	4	-	0.1	*	*	-	-	-	0.1
	5	-	*	*	*	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		1.3	0.9	3.1	2.3	-	-	-	8.2
04	1	-	*	*	*	-	-	-	-
	2	-	-	0.1	0.1	-	-	-	0.1
	3	-	*	0.1	*	-	-	-	0.3
	4	-	0.1	*	*	-	-	-	0.1
	5	-	-	-	*	-	-	-	*
	6	-	-	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-
Total -----		-	0.1	0.2	0.1	-	-	-	0.4
05	1	-	-	-	-	-	-	-	-
	2	-	-	*	*	-	-	-	*
	3	-	-	*	*	-	-	-	*
	4	-	-	*	*	-	-	-	-
	5	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	*	-	-	-	-
Total -----		-	-	*	*	-	-	-	0.1
06	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	-	-	-	-	-	-
07	1	-	-	-	-	-	-	-	-
	2	-	-	-	*	-	-	-	-
	3	-	-	-	*	-	-	-	-
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	-	*	-	-	-	-
STAPLE									
44 & Shorter		-	0.7	-	0.5	-	-	-	0.8
46		0.7	15.2	0.6	6.6	-	-	-	9.7
48		61.8	60.9	25.9	25.2	-	-	-	63.3
50		37.5	23.2	70.7	63.0	-	-	-	20.8
52 & Longer		-	0.1	2.8	4.7	-	-	-	5.5
Average Staple		48.74	48.13	49.51	49.30	-	-	-	48.40
Average Length		1.42	1.40	1.44	1.43	-	-	-	1.41
EXTRANEIOUS MATTER									
Bark		-	-	*	*	-	-	-	1.1
Grass		-	-	*	0.1	-	-	-	0.9
Spindle Twist		-	*	0.6	0.2	-	-	-	0.1
Preparation		-	-	-	*	-	-	-	-
All Other		-	*	*	*	-	-	-	0.1

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 09, 2020

Quality Designation	Arizona		California		New Mexico		Texas	
	Week	Season	Week	Season	Week	Season	Week	Season
MIKE								
2.4 & Below	-	-	*	*	-	-	-	-
2.5 - 2.6	-	-	*	*	-	-	-	-
2.7 - 2.9	-	*	0.2	0.1	-	-	-	*
3.0 - 3.2	0.1	1.4	1.2	0.4	-	-	-	0.9
3.3 - 3.4	12.6	9.9	2.0	0.9	-	-	-	1.9
3.5 - 3.6	24.8	19.2	2.3	2.4	-	-	-	6.5
3.7 - 4.2	49.5	65.2	51.1	59.8	-	-	-	73.0
4.3 - 4.9	13.1	4.4	43.1	36.4	-	-	-	17.7
5.0 - 5.2	-	-	*	*	-	-	-	-
5.3 & Above	-	-	*	*	-	-	-	-
Average	3.85	3.78	4.16	4.14	-	-	-	3.97
ALL RANGE MIKE								
2.4 & Below	-	-	*	*	-	-	-	-
2.5	-	-	*	*	-	-	-	-
2.6	-	-	-	*	-	-	-	-
2.7	-	-	0.1	*	-	-	-	-
2.8	-	-	0.1	*	-	-	-	-
2.9	-	*	0.1	*	-	-	-	*
3.0	-	*	0.3	0.1	-	-	-	*
3.1	-	0.7	0.5	0.1	-	-	-	0.4
3.2	0.1	0.7	0.4	0.2	-	-	-	0.4
3.3	2.9	3.3	0.7	0.3	-	-	-	0.7
3.4	9.7	6.6	1.3	0.6	-	-	-	1.2
3.5	11.1	7.7	1.3	0.8	-	-	-	1.9
3.6	13.7	11.5	1.0	1.6	-	-	-	4.6
3.7	4.8	13.0	2.2	3.0	-	-	-	10.1
3.8	9.7	15.2	2.8	6.1	-	-	-	15.8
3.9	8.0	16.9	4.7	9.6	-	-	-	14.4
4.0	4.7	9.1	8.3	12.3	-	-	-	13.1
4.1	12.8	7.9	14.3	13.8	-	-	-	11.7
4.2	9.6	3.1	18.7	14.9	-	-	-	7.9
4.3	7.7	3.1	20.5	14.5	-	-	-	7.7
4.4	4.3	0.8	14.4	12.3	-	-	-	6.1
4.5	1.0	0.5	6.2	6.4	-	-	-	3.1
4.6	0.1	*	1.5	2.3	-	-	-	0.8
4.7	-	-	0.4	0.7	-	-	-	*
4.8	-	-	0.1	0.2	-	-	-	*
4.9	-	-	*	*	-	-	-	*
5.0	-	-	*	*	-	-	-	-
5.1	-	-	*	*	-	-	-	-
5.2	-	-	-	*	-	-	-	-
5.3 & Above	-	-	*	*	-	-	-	-
Average	3.85	3.78	4.16	4.14	-	-	-	3.97
STRENGTH 1/ 36 & Below	-	*	0.2	0.1	-	-	-	0.2
37	-	0.1	0.2	0.1	-	-	-	1.1
38	-	0.1	0.3	1.2	-	-	-	1.4
39	0.1	0.5	0.5	3.2	-	-	-	1.8
40	0.3	2.0	1.1	3.4	-	-	-	2.3
41	3.9	8.5	2.3	2.6	-	-	-	9.9
42	9.7	15.9	3.7	4.5	-	-	-	13.1
43	15.4	25.0	7.5	9.4	-	-	-	16.7
44	39.7	26.4	14.6	18.0	-	-	-	21.5
45	23.0	15.0	28.8	25.7	-	-	-	18.4
46	7.1	4.9	25.0	19.4	-	-	-	10.4
47	0.4	1.0	11.4	9.0	-	-	-	2.5
48 & Above	0.4	0.5	4.5	3.5	-	-	-	0.8
Average	44.37	43.82	45.43	44.88	-	-	-	43.85
UNIFORMITY								
83 & Below	0.2	1.1	0.4	0.3	-	-	-	0.7
84	5.5	9.4	2.3	4.9	-	-	-	2.6
85	33.9	37.9	14.8	15.6	-	-	-	22.3
86	57.6	47.8	62.2	54.7	-	-	-	62.7
87	2.7	3.7	19.2	23.0	-	-	-	11.4
88 & Above	0.1	0.1	1.2	1.5	-	-	-	0.4
Average	86.05	85.89	86.48	86.45	-	-	-	86.28
Samples Classed	1,501	9,135	36,329	443,008	-	-	-	14,572

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.