



Volume 20, No.19

State	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
AL	29	63.2	51.3	61,899	29	63.7	52.6	511,273
AR	24	72.5	49.0	86,273	28	70.8	52.2	1,023,794
AZ	12	72.9	49.7	25,259	12	74.8	51.1	102,364
CA	9	97.1	81.4	12,730	14	90.1	74.4	91,311
FL	3	55.8	46.4	7,996	4	64.0	52.7	45,269
GA	58	72.1	62.1	148,342	58	82.3	67.7	1,113,498
KS	3	49.2	31.2	4,959	3	54.5	46.5	23,723
LA	15	50.1	25.3	24,015	19	57.8	32.3	362,722
MO	19	76.6	52.9	60,157	21	68.0	48.2	633,567
MS	37	71.5	43.5	120,389	38	77.1	49.6	1,077,235
NC	33	77.7	59.0	74,539	33	75.4	57.7	562,849
NM	2	88.5	71.0	4,441	2	93.0	79.4	11,977
OK	10	81.9	68.6	38,053	10	81.9	68.8	150,969
SC	16	80.9	60.2	31,169	16	80.5	68.3	226,595
TN	22	60.6	36.0	63,696	22	44.9	28.0	678,986
TX	157	74.1	59.9	574,546	181	65.9	47.7	3,554,173
VA	4	81.9	53.0	19,920	4	79.7	55.3	134,683
United States	453	72.8	55.5	1,358,383	494	69.2	50.7	10,304,988
AMERICAN PIMA								
AZ	2			2,263	4			11,456
CA	16			49,874	17			315,637
NM*	-			-	-			-
TX*	-			-	-			-
United States	20			56,478	23			339,575
United States all cotton	470			1,414,861	509			10,644,563

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE													
For The Week Ending Dec 06 2018													
Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	0.2	0.3	0.2	0.2	5.0	14.7	46.4	57.9	-	-	0.4	1.4
	3	0.2	0.6	0.4	0.3	1.0	6.2	6.5	12.7	-	*	0.7	2.8
	4	*	*	*	*	0.1	0.6	0.1	0.1	-	-	0.1	0.3
	5	-	*	-	-	*	*	-	*	-	-	*	*
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.4	0.9	0.6	0.4	6.1	21.5	53.0	70.7	-	*	1.2	4.5
31	1 - 2	1.5	1.6	0.2	0.5	16.2	8.1	15.9	9.3	0.1	0.2	1.5	4.4
	3	7.2	14.9	2.5	4.6	15.5	9.8	23.1	12.7	5.9	5.7	11.4	29.1
	4	3.9	7.6	1.5	3.3	1.9	1.5	2.2	1.9	4.2	3.3	5.4	14.4
	5	0.3	0.6	0.1	0.4	0.1	0.1	*	0.2	0.2	0.1	0.3	0.9
	6	*	*	-	*	*	*	-	*	-	-	*	*
	7	-	-	-	-	*	*	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	12.9	24.8	4.2	8.8	33.8	19.6	41.2	24.1	10.4	9.3	18.6	48.8
41	1 - 2	1.4	0.9	1.2	0.6	13.3	7.0	0.1	*	0.4	0.4	1.5	0.9
	3	19.4	14.9	22.0	15.3	26.0	21.7	1.5	0.3	14.0	16.1	22.8	12.9
	4	27.5	21.8	28.7	30.2	8.6	8.8	0.2	0.1	31.5	37.0	31.3	17.4
	5	10.5	7.0	6.9	11.3	1.1	1.1	-	*	5.5	6.7	6.7	3.6
	6	1.8	0.8	0.4	1.0	0.1	0.1	-	*	0.1	0.1	0.3	0.1
	7	0.1	*	*	*	*	*	-	*	-	-	*	*
	8	-	-	-	*	-	-	-	-	-	-	*	*
Total	----	60.7	45.5	59.1	58.5	49.2	38.8	1.9	0.4	51.4	60.4	62.6	35.0
51	1 - 2	*	*	0.2	*	0.2	0.3	-	-	*	*	0.1	*
	3	1.2	0.4	5.3	1.4	1.5	2.8	*	*	1.5	1.4	1.4	0.4
	4	3.2	1.2	10.2	5.9	1.8	3.0	-	-	8.8	5.4	3.2	0.9
	5	2.9	1.2	3.9	5.0	0.6	0.9	-	-	4.8	3.5	1.8	0.5
	6	1.3	0.5	0.4	0.8	0.2	0.1	-	-	0.2	0.3	0.3	0.1
	7	0.3	0.1	*	*	0.1	*	-	-	-	*	*	*
	8	*	*	-	-	0.1	*	-	-	-	*	*	*
Total	----	8.9	3.3	20.1	13.1	4.4	7.2	*	*	15.3	10.6	6.7	1.8
61	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	*	-	-	*	*	-	*
	4	*	*	-	*	-	-	-	-	0.1	0.1	-	-
	5	*	*	*	*	-	-	-	-	*	*	-	*
	6	-	*	-	*	-	-	-	-	-	-	-	*
	7	-	*	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	*	*	-	-	-	*	*	*
Total	----	*	*	*	*	*	*	-	-	0.1	0.1	*	*
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	*
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	*	*
Total	----	-	-	-	-	-	-	-	-	-	-	*	*
12 & 22	1 - 2	*	*	-	*	0.6	3.1	0.4	0.8	-	*	*	0.1
	3	*	*	*	*	0.8	1.5	0.4	0.6	-	-	*	0.1
	4	*	*	-	*	*	0.5	*	*	-	-	*	*
	5	-	-	-	-	-	0.1	-	-	-	-	-	*
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	*	*	1.4	5.2	0.8	1.4	-	*	0.1	0.2
32	1 - 2	0.2	0.1	*	*	0.4	0.1	0.4	0.6	-	*	0.2	0.3
	3	1.0	1.7	0.1	0.4	1.0	0.9	2.1	2.3	0.1	0.1	1.4	2.4
	4	0.7	1.5	0.1	0.2	0.2	0.4	0.3	0.4	0.1	0.1	0.8	1.2
	5	0.1	0.2	-	*	*	0.3	*	*	*	*	0.1	0.1
	6	*	*	-	*	-	0.1	-	-	-	-	-	*
	7	-	*	-	-	-	*	-	-	-	-	-	-
	8	-	-	-	-	-	*	-	-	-	-	-	-
Total	----	2.0	3.6	0.2	0.6	1.5	1.9	2.8	3.2	0.2	0.3	2.5	4.0
42	1 - 2	0.2	0.2	0.1	0.1	0.1	0.2	*	*	*	0.1	0.1	0.1
	3	2.9	4.9	2.5	4.2	1.1	1.3	0.2	0.1	2.0	2.1	1.6	1.3
	4	4.3	9.1	5.7	7.8	1.0	1.6	0.1	*	5.5	4.0	3.2	2.3
	5	2.0	3.1	2.1	2.3	0.1	0.3	*	*	1.6	1.0	0.9	0.6
	6	0.4	0.4	0.2	0.2	-	0.1	-	-	*	*	0.1	*
	7	*	*	*	*	-	0.1	-	-	-	-	*	*
	8	-	*	-	-	-	*	-	-	-	-	-	-
Total	----	9.8	17.7	10.5	14.5	2.2	3.5	0.3	0.1	9.1	7.3	5.9	4.3

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 06 2018

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	*	*	*	*	*	*	-	*	*	*	*	*
	3	0.4	0.3	0.7	0.3	0.1	0.2	-	-	0.7	1.3	0.1	*
	4	1.0	0.8	1.7	1.3	0.2	1.0	-	-	5.8	5.2	0.5	0.2
	5	0.9	0.6	1.1	1.1	0.1	0.4	-	-	4.2	3.2	0.3	0.1
	6	0.2	0.2	0.1	0.2	*	*	-	-	0.2	0.5	0.1	*
	7	0.1	*	*	*	*	*	-	-	-	*	*	*
	8	*	*	-	-	*	*	-	-	-	*	-	*
Total	----	2.6	1.9	3.6	2.9	0.4	1.7	-	*	10.9	10.2	1.0	0.3
62	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	*	-	*	-	*	-	-	-	*	-	*
	4	*	*	-	*	-	-	-	-	*	0.1	*	*
	5	*	*	*	*	*	*	-	-	0.1	0.1	-	*
	6	-	*	-	*	-	-	-	-	*	*	-	*
	7	*	*	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	*	*	*	-	-	-	-	-	-
Total	----	*	*	*	*	*	*	-	-	0.1	0.2	*	*
13 & 23	1 - 2	*	*	-	*	*	0.1	-	*	-	-	*	*
	3	-	*	-	*	0.1	0.1	-	*	-	-	*	*
	4	-	-	-	*	0.1	0.1	-	-	-	-	-	*
	5	-	-	-	-	*	*	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	-	*	0.3	0.2	-	*	-	-	*	*
33	1 - 2	*	*	-	-	-	*	-	-	-	-	*	0.1
	3	0.3	0.1	*	*	0.1	*	-	*	-	*	0.2	0.3
	4	0.1	0.1	*	*	0.1	0.1	-	*	*	*	0.1	0.1
	5	*	*	*	*	*	0.1	-	-	-	-	*	*
	6	-	*	-	-	-	*	-	-	-	-	*	*
	7	-	*	-	-	-	*	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.4	0.2	0.1	*	0.1	0.2	-	*	*	*	0.4	0.5
43	1 - 2	*	*	*	*	-	-	-	-	-	-	*	*
	3	0.4	0.3	0.2	0.2	0.1	*	-	*	0.1	0.2	0.2	0.1
	4	0.6	0.8	0.5	0.4	0.1	0.1	-	*	0.9	0.4	0.4	0.2
	5	0.4	0.4	0.2	0.2	*	0.1	-	-	0.3	0.1	0.2	0.1
	6	0.1	0.1	*	*	*	*	-	-	*	*	*	*
	7	*	*	-	-	-	*	-	-	-	-	*	*
	8	-	-	-	-	-	*	-	-	-	-	-	-
Total	----	1.4	1.5	0.9	0.8	0.2	0.2	-	*	1.3	0.6	0.8	0.5
53	1 - 2	-	*	-	*	-	-	-	-	-	-	-	-
	3	0.1	0.1	*	*	-	*	-	-	0.1	*	*	*
	4	0.3	0.1	0.2	0.1	*	*	-	-	0.6	0.4	0.1	*
	5	0.1	0.1	0.2	0.1	-	*	-	-	0.4	0.4	0.1	*
	6	*	*	*	*	-	*	-	-	0.1	0.1	*	*
	7	*	*	-	*	-	*	-	-	-	*	*	*
	8	-	*	-	-	-	*	-	-	-	-	-	-
Total	----	0.6	0.4	0.5	0.3	*	*	-	-	1.2	0.9	0.2	*
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	*	-	-	-	-	-	-	-	*	-	-
	4	-	*	*	*	-	-	-	-	-	*	*	*
	5	-	*	-	*	-	-	-	-	*	*	-	-
	6	-	*	-	*	-	-	-	-	-	-	-	*
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	*	*	-	-	-	-	*	*	*	*
24 - 54	1 - 8	0.2	0.1	0.1	*	0.2	0.1	-	*	0.1	*	0.1	0.1
25 - 35	1 - 8	-	*	-	-	-	-	-	-	-	-	*	*
81 - 85	1 - 8	*	*	*	*	-	-	-	-	-	*	*	*
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		*	*	-	-	-	-	-	-	-	-	-	-
31		*	*	-	-	-	-	-	*	-	-	*	*
32		*	*	-	*	-	*	-	*	-	*	0.1	0.1
33		0.5	0.4	*	*	0.1	0.1	-	0.2	-	*	0.9	0.9
34		3.5	3.0	0.8	0.4	3.5	2.2	*	0.2	0.9	0.5	5.2	5.2
35		11.5	10.5	5.5	2.9	8.6	8.3	0.8	2.0	3.9	2.8	13.3	13.5
36		21.5	21.1	13.6	11.7	18.3	21.8	11.8	7.2	11.0	10.2	19.1	18.7
37		36.8	37.0	37.2	36.9	27.3	33.2	38.1	26.5	27.4	34.6	28.2	28.7
38		20.0	20.9	21.1	26.9	19.1	17.4	12.8	24.7	40.8	35.8	23.1	23.2
39		5.6	6.2	16.0	15.5	14.0	11.3	19.3	21.6	15.9	15.7	8.8	8.6
40 & Longer		0.6	0.8	5.8	5.8	9.2	5.8	17.2	17.6	0.2	0.4	1.3	1.1
Average Staple		36.76	36.83	37.44	37.57	37.30	37.13	37.91	38.12	37.52	37.51	36.79	36.78
Average Length		1.15	1.15	1.17	1.17	1.16	1.16	1.18	1.19	1.17	1.17	1.15	1.15

1/ Below Grade Color. 2/ Below Grade Leaf. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 06 2018

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	4.5	2.6	*	0.7	*	0.8	0.1	0.5	*	0.1	12.8	11.8
	3	8.5	3.4	*	1.3	*	0.8	0.3	1.0	0.2	0.2	6.3	5.9
	4	0.4	0.4	*	0.1	-	*	*	0.1	*	*	-	0.1
	5	-	*	-	*	-	*	-	*	-	*	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	13.5	6.4	*	2.1	*	1.7	0.4	1.6	0.2	0.3	19.0	17.7
31	1 - 2	7.1	5.7	1.3	3.0	0.4	0.9	1.4	2.0	0.9	1.8	22.3	19.7
	3	18.3	23.3	5.2	17.3	5.3	6.9	9.9	15.0	10.0	14.4	24.3	27.6
	4	7.9	8.7	2.3	7.1	1.2	3.5	5.1	7.7	7.3	7.5	4.1	3.4
	5	2.7	1.2	0.2	0.4	*	0.4	0.3	0.5	1.0	0.8	0.2	0.1
	6	0.3	0.1	-	*	-	*	*	*	*	*	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	*	-	-
Total	----	36.2	39.0	8.9	27.8	7.0	11.6	16.7	25.2	19.4	24.5	50.9	50.9
41	1 - 2	0.2	0.3	3.1	1.8	1.1	0.8	1.9	1.0	1.9	1.6	2.6	2.1
	3	6.7	8.2	24.1	17.7	28.4	20.2	19.7	16.1	23.1	23.9	11.0	14.8
	4	14.3	11.5	19.6	19.5	35.4	33.7	30.7	30.9	28.1	23.5	10.9	9.6
	5	9.4	4.7	5.8	4.6	7.0	9.3	9.8	10.5	7.9	4.9	3.4	3.1
	6	1.4	0.6	0.5	0.3	0.3	0.4	0.6	0.7	0.8	0.3	0.4	0.4
	7	*	*	*	*	*	*	*	*	-	*	-	*
	8	-	-	-	-	-	-	-	*	-	*	-	-
Total	----	31.8	25.3	53.2	43.9	72.1	64.5	62.7	59.2	61.8	54.2	28.3	30.0
51	1 - 2	-	-	0.6	0.2	*	*	0.1	*	0.2	0.1	-	-
	3	*	*	2.2	1.2	1.6	0.5	0.8	0.3	2.4	1.2	*	*
	4	1.3	0.3	2.8	1.5	7.2	3.4	2.9	1.3	3.3	1.7	0.5	0.3
	5	0.9	0.2	0.8	0.5	4.1	2.7	2.7	1.5	1.3	0.7	0.3	0.2
	6	0.4	0.1	*	0.1	0.5	0.3	0.4	0.3	0.3	0.1	*	*
	7	*	*	-	*	*	*	*	*	*	*	-	-
	8	-	-	-	*	-	-	-	*	-	-	-	-
Total	----	2.7	0.6	6.6	3.4	13.5	6.9	6.9	3.4	7.5	3.7	0.9	0.5
61	1 - 2	-	-	-	-	-	-	-	-	-	*	-	-
	3	-	-	*	*	-	-	-	*	*	*	-	-
	4	-	-	-	*	-	*	-	-	*	*	-	-
	5	-	-	-	*	-	-	*	*	*	*	-	-
	6	-	-	-	*	-	*	*	*	-	-	-	-
	7	-	-	-	-	-	-	-	*	-	-	-	-
	8	-	-	-	*	-	-	-	-	-	-	-	-
Total	----	-	-	*	*	-	*	*	*	*	*	-	-
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	-	-	-	-	-
12 & 22	1 - 2	-	*	*	*	-	*	*	*	-	*	-	*
	3	0.6	1.2	-	*	-	*	*	*	*	*	-	*
	4	0.1	0.6	-	*	-	*	*	*	*	*	-	-
	5	-	*	-	-	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.6	2.0	*	0.1	-	*	*	*	*	*	-	*
32	1 - 2	-	*	0.4	0.2	*	*	*	0.1	0.1	0.1	-	-
	3	0.5	0.9	0.9	1.2	0.2	0.5	0.5	0.5	0.5	0.9	-	*
	4	2.4	2.3	0.4	0.7	0.1	0.2	0.5	0.4	0.5	0.5	-	0.1
	5	2.0	1.2	*	*	-	*	0.1	*	0.1	*	-	*
	6	*	0.1	-	*	-	-	-	*	*	*	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	4.9	4.4	1.6	2.1	0.3	0.7	1.1	1.0	1.2	1.5	-	0.2
42	1 - 2	-	-	0.8	0.4	*	0.1	0.1	0.1	0.2	0.4	0.1	*
	3	0.1	*	6.1	4.4	1.5	3.8	1.7	1.3	2.7	5.5	0.7	0.3
	4	2.7	0.7	6.2	5.7	3.7	6.7	4.1	3.5	2.8	4.9	0.1	0.1
	5	3.2	0.9	1.4	1.4	0.6	1.8	2.5	2.0	0.7	0.8	-	-
	6	0.6	0.2	0.1	0.1	*	0.1	0.2	0.2	*	*	-	-
	7	-	*	-	*	-	-	*	*	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	6.6	1.8	14.4	12.0	5.7	12.5	8.7	7.1	6.4	11.6	0.8	0.4

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 06 2018

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	0.2	0.2	-	*	*	*	*	0.1	-	-
	3	-	-	2.8	1.6	0.1	0.1	0.1	0.1	0.5	1.0	*	*
	4	0.1	*	4.2	2.3	0.4	0.7	0.6	0.5	1.0	1.4	-	-
	5	1.5	0.3	1.5	0.9	0.2	0.6	0.8	0.8	0.3	0.5	-	-
	6	0.6	0.1	0.1	0.1	*	0.1	0.2	0.2	*	0.1	-	-
	7	*	*	*	*	-	-	*	*	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	*	-	-
	Total	----	2.3	0.5	8.8	5.0	0.7	1.6	1.8	1.6	1.9	3.1	*
62	1 - 2	-	-	-	*	-	-	-	-	*	*	-	-
	3	-	-	*	*	-	-	*	*	*	*	-	-
	4	-	-	*	*	*	*	*	*	*	*	-	-
	5	-	-	*	*	-	-	-	*	*	*	-	-
	6	-	-	-	*	-	-	-	*	-	*	-	-
	7	-	-	-	*	-	-	*	*	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	*	-	-
	Total	----	-	-	0.1	0.1	*	*	*	*	0.1	0.1	-
13 & 23	1 - 2	*	*	-	*	-	-	-	-	-	*	-	0.1
	3	-	1.3	-	-	-	-	-	-	-	*	-	0.1
	4	-	1.5	-	-	-	-	-	-	-	-	-	-
	5	-	*	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
	Total	----	*	2.8	-	*	-	-	-	-	-	*	-
33	1 - 2	-	*	*	*	-	*	*	*	*	*	-	*
	3	0.1	0.7	0.2	0.1	*	*	0.1	*	*	*	-	0.1
	4	0.3	2.8	*	*	*	*	*	*	*	*	-	-
	5	0.3	1.2	*	*	-	*	*	*	*	*	-	-
	6	*	0.1	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
	Total	----	0.7	4.9	0.3	0.1	*	*	0.1	0.1	0.1	0.1	-
43	1 - 2	-	-	0.2	*	-	*	*	*	*	*	-	-
	3	-	*	0.9	0.4	0.2	0.1	0.2	0.1	0.3	0.2	-	*
	4	0.1	0.1	0.9	0.7	0.4	0.2	0.5	0.2	0.4	0.3	-	*
	5	*	0.2	0.4	0.3	0.1	0.1	0.4	0.2	0.2	0.1	-	-
	6	*	0.1	*	*	*	*	0.1	*	*	*	-	-
	7	-	-	-	-	*	*	*	*	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
	Total	----	0.2	0.4	2.4	1.5	0.6	0.4	1.2	0.5	0.9	0.6	-
53	1 - 2	-	-	0.2	*	-	-	*	*	-	*	-	-
	3	-	-	1.3	0.3	*	*	*	*	0.1	0.1	-	-
	4	-	*	1.2	0.6	*	*	0.1	0.1	0.2	0.1	-	-
	5	-	-	0.5	0.4	*	*	0.1	0.1	0.1	0.1	-	*
	6	-	*	0.1	*	*	*	0.1	*	*	*	-	-
	7	-	*	-	*	*	*	*	*	-	*	-	-
	8	-	-	-	-	-	-	*	*	-	-	-	-
	Total	----	-	*	3.2	1.4	0.1	0.1	0.3	0.2	0.3	0.2	-
63	1 - 2	-	-	*	*	-	-	-	*	-	*	-	-
	3	-	-	0.1	0.1	-	-	*	*	*	*	-	-
	4	-	-	0.2	0.1	-	*	-	*	*	*	-	-
	5	-	-	*	0.1	-	-	*	*	*	*	-	-
	6	-	-	*	*	-	-	*	*	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	*	-	-	-	-
	Total	----	-	-	0.3	0.3	-	*	*	*	*	*	-
24 - 54	1 - 8	0.5	9.1	0.2	0.1	*	*	0.1	*	0.1	*	-	*
25 - 35	1 - 8	-	1.4	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	1.5	*	*	-	-	*	*	*	*	-	-
STAPLE		-	-	-	-	-	-	-	-	-	-	-	-
28 & Shorter	-	-	-	-	-	-	-	-	-	*	-	-	
29	-	-	-	-	-	-	-	-	-	*	*	-	-
30	-	-	*	*	-	-	-	-	-	*	*	-	-
31	-	-	*	*	-	*	-	*	*	*	*	-	-
32	-	*	*	*	-	*	*	*	*	0.1	*	-	-
33	0.1	0.1	0.1	0.4	*	*	0.4	0.3	1.4	0.7	1.7	0.6	
34	1.3	1.4	1.7	2.8	0.8	0.3	2.8	2.4	5.7	5.2	2.8	1.1	
35	15.1	13.9	8.5	9.9	3.1	2.7	7.8	7.9	18.7	17.6	5.9	3.7	
36	52.9	36.7	20.3	17.7	10.8	11.1	16.3	14.8	27.7	26.6	8.4	9.2	
37	30.0	41.1	25.9	26.9	41.8	41.2	28.2	29.0	28.7	27.8	30.2	30.8	
38	0.4	4.8	24.0	21.9	26.0	28.7	25.9	27.3	14.3	16.8	20.1	20.7	
39	0.1	0.6	12.2	14.7	11.4	11.8	15.5	15.2	3.3	4.8	17.6	17.7	
40 & Longer	-	1.4	7.3	5.8	6.0	4.3	3.1	3.1	0.1	0.5	13.4	16.2	
Average Staple		36.13	36.41	37.28	37.22	37.49	37.48	37.25	37.28	36.33	36.48	37.67	37.87
Average Length		1.13	1.13	1.16	1.16	1.17	1.17	1.16	1.16	1.13	1.14	1.18	1.18

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 06 2018

Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	0.5	1.1	*	0.2	0.1	0.9	3.6	9.7	0.2	0.1
	3	0.6	2.3	0.3	0.4	*	0.7	4.7	6.7	0.6	0.3
	4	*	0.2	*	*	-	*	0.9	0.6	*	*
	5	-	*	-	*	-	-	*	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	1.1	3.6	0.4	0.6	0.1	1.7	9.3	17.0	0.9	0.3
31	1 - 2	7.2	5.4	0.9	1.3	1.4	1.8	9.4	6.8	3.5	4.2
	3	27.5	24.7	6.7	12.3	3.3	5.8	26.7	18.1	20.9	25.0
	4	6.1	7.3	4.3	9.3	0.6	1.6	11.6	7.5	5.3	5.0
	5	0.6	0.5	0.2	0.8	*	0.1	1.9	1.0	0.1	0.1
	6	*	*	-	*	-	*	0.1	0.1	-	*
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	41.4	37.8	12.0	23.7	5.4	9.3	49.8	33.5	29.7	34.3
41	1 - 2	2.5	2.4	2.3	1.8	5.6	3.6	1.4	1.7	2.6	3.0
	3	23.5	21.5	18.1	17.8	26.8	21.4	8.8	9.4	37.3	33.3
	4	19.6	18.0	30.8	27.3	17.5	15.0	10.5	9.6	14.8	11.9
	5	5.1	3.9	9.8	7.7	3.6	2.3	5.0	3.8	1.1	0.4
	6	0.6	0.5	0.6	0.4	0.2	0.1	1.3	0.8	*	*
	7	0.1	0.1	*	*	-	-	0.3	0.1	-	-
	8	*	*	-	*	-	-	*	*	-	-
Total	----	51.5	46.3	61.6	55.1	53.6	42.3	27.5	25.4	55.9	48.7
51	1 - 2	*	*	0.6	0.3	0.5	0.1	0.3	0.1	0.3	0.1
	3	0.1	0.2	2.3	1.6	7.7	1.9	1.2	0.8	0.5	0.4
	4	0.4	0.5	5.9	1.9	11.0	3.1	0.7	0.7	0.3	0.2
	5	0.6	0.7	5.2	1.4	4.6	1.3	0.2	0.3	0.1	*
	6	0.2	0.3	0.9	0.2	0.4	0.1	0.1	0.2	*	*
	7	*	0.1	-	*	-	*	0.1	0.1	-	-
	8	*	*	-	-	-	-	*	*	-	-
Total	----	1.5	1.7	14.8	5.4	24.2	6.5	2.6	2.3	1.1	0.7
61	1 - 2	-	-	-	-	-	-	*	*	-	-
	3	-	-	*	*	-	-	0.1	*	-	-
	4	-	-	*	*	*	*	*	*	-	*
	5	-	-	-	-	*	*	*	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	-	-	0.1	*	*	*	0.1	0.1	-	*
71	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	-	*	*	-	-
	4	-	-	-	-	-	-	*	*	-	-
	5	-	-	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	*	*	-	-
12 & 22	1 - 2	*	0.1	-	*	*	0.1	0.3	2.1	-	-
	3	0.1	0.3	*	0.1	*	0.1	0.5	2.2	-	-
	4	*	*	*	*	-	*	0.2	0.4	-	*
	5	-	-	-	-	-	*	*	*	-	*
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	0.2	0.5	*	0.1	*	0.1	1.0	4.8	-	*
32	1 - 2	*	0.2	0.1	0.3	0.3	0.6	0.3	0.7	0.2	0.2
	3	0.2	1.5	0.8	1.4	0.7	1.9	1.2	2.5	1.8	1.5
	4	0.1	1.0	0.5	0.7	0.2	0.7	1.1	1.7	0.4	0.4
	5	0.1	0.2	*	0.1	*	*	0.3	0.4	*	*
	6	*	*	-	*	-	*	*	*	*	*
	7	*	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	0.5	3.0	1.4	2.4	1.2	3.2	3.0	5.3	2.5	2.1
42	1 - 2	0.1	0.1	0.1	0.7	0.8	1.9	0.1	0.3	0.4	0.6
	3	0.8	1.5	1.5	3.6	6.0	15.0	0.7	2.0	4.4	7.4
	4	0.9	1.5	2.6	3.4	3.2	11.1	0.8	2.0	2.8	3.8
	5	0.4	0.7	1.0	1.0	0.6	1.7	0.4	0.7	0.4	0.2
	6	0.2	0.2	0.1	0.1	*	0.1	0.1	0.1	0.1	*
	7	*	*	*	*	-	-	*	*	-	-
	8	*	*	-	-	-	-	*	*	-	-
Total	----	2.4	4.0	5.3	8.7	10.7	29.7	2.1	5.2	8.1	12.1

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 06 2018

Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA		
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	
52	1 - 2	*	*	0.1	0.1	*	*	0.1	0.1	*	0.1	
	3	0.2	0.2	0.8	0.9	0.8	0.9	0.4	0.7	0.2	0.8	
	4	0.2	0.2	1.3	0.9	1.0	2.2	0.5	1.0	0.1	0.3	
	5	*	0.2	0.6	0.4	0.7	1.0	0.2	0.5	*	*	
	6	*	0.1	0.1	0.1	0.1	0.1	0.1	*	0.1	*	*
	7	-	*	-	*	-	*	*	*	*	-	-
	8	-	*	-	-	-	-	*	*	-	-	
Total	----	0.5	0.6	2.9	2.5	2.6	4.3	1.2	2.5	0.3	1.2	
62	1 - 2	-	-	-	*	-	-	*	*	-	-	
	3	-	*	*	*	*	*	0.2	0.1	-	-	
	4	-	*	*	*	0.1	*	0.2	0.2	-	-	
	5	-	-	*	*	*	*	0.1	0.1	-	-	
	6	-	-	*	*	-	*	*	*	-	-	
	7	-	-	-	-	-	*	*	*	-	-	
	8	-	-	-	-	-	-	*	*	-	-	
Total	----	-	*	0.1	*	0.1	*	0.6	0.4	-	-	
13 & 23	1 - 2	-	*	-	*	-	*	0.1	0.2	*	*	
	3	-	*	-	*	*	*	0.1	0.3	*	*	
	4	*	*	-	*	-	-	*	0.1	-	-	
	5	-	*	-	-	-	-	*	*	-	-	
	6	-	-	-	-	-	-	-	*	-	-	
	7	-	-	-	-	-	-	-	-	-	-	
	8	-	-	-	-	-	-	-	-	-	-	
Total	----	*	0.1	-	*	*	*	0.1	0.6	*	*	
33	1 - 2	-	*	*	*	*	*	*	*	*	*	
	3	0.1	0.3	0.1	0.1	0.1	0.1	0.1	0.3	0.1	*	
	4	0.1	0.3	0.1	0.1	*	*	0.2	0.2	0.1	*	
	5	*	0.1	*	*	-	*	*	0.1	-	*	
	6	*	*	-	*	-	*	*	*	-	-	
	7	*	*	-	-	-	-	*	*	-	-	
	8	-	-	-	-	-	-	*	*	-	-	
Total	----	0.2	0.7	0.2	0.2	0.1	0.1	0.3	0.6	0.2	0.1	
43	1 - 2	*	*	*	*	0.2	0.1	*	*	*	*	
	3	0.1	0.1	0.2	0.3	0.9	1.0	0.2	0.2	0.4	0.2	
	4	0.1	0.3	0.4	0.5	0.4	0.9	0.2	0.3	0.7	0.2	
	5	*	0.2	0.3	0.2	*	0.1	0.1	0.2	0.1	*	
	6	0.1	0.1	0.1	*	*	*	*	*	*	*	
	7	*	*	*	*	-	-	*	*	-	-	
	8	*	*	-	-	-	-	*	*	-	-	
Total	----	0.4	0.8	1.0	1.0	1.5	2.1	0.6	0.7	1.3	0.4	
53	1 - 2	*	*	-	*	*	*	*	*	-	*	
	3	0.1	0.1	*	*	0.1	0.1	0.1	0.2	*	*	
	4	*	*	0.1	0.1	0.2	0.2	0.2	0.3	*	*	
	5	*	*	*	0.1	0.1	0.1	0.2	0.2	*	*	
	6	-	*	*	*	*	*	*	0.1	-	-	
	7	*	*	-	-	-	*	*	*	-	-	
	8	*	*	-	-	-	-	*	*	-	-	
Total	----	0.2	0.2	0.2	0.3	0.4	0.5	0.5	0.9	*	0.1	
63	1 - 2	-	-	-	-	-	-	*	*	-	-	
	3	*	*	-	-	*	*	0.1	0.1	-	-	
	4	-	*	-	*	*	*	0.4	0.2	-	-	
	5	-	*	-	-	*	*	0.3	0.2	-	-	
	6	-	-	-	-	-	*	0.1	0.1	-	-	
	7	-	-	-	-	-	-	*	*	-	-	
	8	-	-	-	-	-	-	*	*	-	-	
Total	----	*	*	-	*	*	*	0.9	0.5	-	-	
24 - 54	1 - 8	0.2	0.5	*	*	0.2	0.1	0.2	0.2	*	*	
25 - 35	1 - 8	-	*	-	-	-	-	*	*	-	-	
81 - 85	1 - 8	*	0.1	*	*	-	*	0.3	0.1	-	-	
STAPLE												
28 & Shorter		-	-	-	-	-	-	*	*	-	-	
29		-	-	-	-	-	-	*	*	-	-	
30		*	*	-	-	-	-	*	0.1	-	-	
31		*	*	*	*	-	*	0.2	0.4	-	-	
32		0.6	0.5	0.3	0.1	*	*	0.7	1.2	*	*	
33		2.6	2.1	2.8	1.4	0.3	0.1	2.8	3.8	1.5	0.7	
34		5.6	6.6	6.8	5.0	2.3	1.3	9.9	9.9	13.2	8.7	
35		10.6	11.6	14.5	10.1	16.3	12.1	21.8	19.0	29.9	25.1	
36		21.2	21.0	20.5	16.2	33.4	35.0	26.8	25.0	22.2	30.6	
37		32.1	30.2	34.0	30.0	36.6	39.5	24.8	24.4	24.5	22.4	
38		17.7	16.9	17.6	27.5	9.1	9.2	9.1	10.7	7.2	10.3	
39		8.1	8.9	3.2	8.8	1.6	2.3	3.2	4.7	1.4	2.1	
40 & Longer		1.4	2.1	0.4	1.0	0.4	0.4	0.7	0.9	0.1	0.1	
Average Staple		36.66	36.65	36.43	36.91	36.39	36.52	36.02	36.06	35.82	36.05	
Average Length		1.14	1.14	1.14	1.15	1.13	1.14	1.12	1.12	1.12	1.12	

1/ Below Grade Color. 2/ Below Grade Leaf. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 06 2018

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	18.6	9.6	2.1	1.3	0.3	0.7	-	*	30.7	20.4	19.1	9.5
Bark - Level 2	-	*	-	-	-	-	-	-	*	*	*	*
Grass - Level 1	*	0.1	0.4	0.2	-	*	-	0.2	-	*	*	0.1
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	0.1	*	*	*	-	-	-	*	-	*	*	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	0.3	0.2	*	*	3.5	1.6	-	-	0.2	0.3	0.2	0.1
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	*	*	-	-	-	-	-	-	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	*	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	-	-	-	-	-	-	-	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	*	*	*	-	-	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	-	-	*	-	-	-	-	-	-	-	*
23	*	*	-	*	-	-	-	-	0.1	*	*	*
24	0.1	0.2	*	*	*	*	-	-	0.4	0.3	0.2	0.3
25	0.7	0.9	0.3	0.2	*	*	-	-	1.8	1.6	1.2	2.0
26	3.2	3.9	2.2	1.3	0.4	0.2	-	*	3.8	6.6	5.4	7.5
27	13.8	14.4	5.3	5.0	2.6	1.5	-	*	12.5	20.6	14.1	16.1
28	31.2	30.0	20.0	17.5	7.4	8.4	-	0.4	37.3	39.1	22.5	25.0
29	27.2	29.0	31.2	30.3	14.1	17.9	*	1.9	34.8	22.3	25.4	24.6
30	15.7	14.4	22.1	24.3	24.4	23.7	1.1	3.4	6.3	7.0	18.9	15.1
31	5.7	5.3	12.7	13.0	19.6	22.0	7.5	6.3	2.7	1.9	8.0	6.4
32	1.8	1.4	4.8	6.1	16.4	15.9	25.0	14.7	0.3	0.4	2.9	2.2
33	0.4	0.4	1.2	1.8	8.6	6.8	18.4	17.6	-	*	1.0	0.6
34	0.1	0.1	0.3	0.4	4.8	2.7	9.7	10.7	*	*	0.3	0.2
35	*	*	0.1	0.1	1.4	0.7	6.2	10.2	-	*	0.1	*
36	*	*	*	*	0.2	0.1	13.2	16.8	-	-	*	*
37	*	*	-	-	0.1	*	14.8	13.1	-	-	*	*
38	-	-	-	-	*	*	3.4	4.1	-	-	*	*
39	-	-	-	-	*	*	0.4	0.5	-	-	-	-
40 & Above	-	-	-	-	-	*	0.3	0.2	-	-	*	*
Average	29.08	29.01	29.75	29.91	31.12	30.95	34.44	34.57	28.74	28.49	29.22	28.94
Mike												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	-
2.5	*	*	-	-	-	*	-	-	-	-	*	*
2.6	*	*	-	-	*	*	-	*	-	-	*	*
2.7	*	*	*	*	0.1	*	-	0.1	-	-	-	*
2.8	*	*	*	*	0.1	*	-	0.1	-	-	*	*
2.9	*	*	*	*	0.1	*	-	0.1	-	-	*	*
3.0	*	*	*	*	0.1	0.1	-	0.2	-	*	0.1	*
3.1	*	*	0.1	*	0.1	*	0.1	0.4	-	-	0.1	0.1
3.2	0.1	0.1	0.1	*	0.2	0.1	0.1	0.6	-	-	0.2	0.2
3.3	0.2	0.2	0.1	*	0.2	0.1	0.4	0.9	*	*	0.5	0.5
3.4	0.5	0.4	0.1	*	0.2	0.3	1.1	1.3	*	*	0.9	0.9
3.5	0.9	0.6	0.1	0.1	0.2	0.4	0.3	1.3	0.1	0.1	1.3	1.4
3.6	1.2	1.0	0.1	0.1	0.1	0.6	0.2	2.0	0.2	0.2	1.5	1.9
3.7	2.7	2.0	0.3	0.2	0.3	0.9	0.7	2.4	0.2	0.4	2.2	2.6
3.8	3.5	2.9	0.6	0.4	0.7	1.3	0.7	2.5	1.3	0.9	2.7	4.1
3.9	5.6	3.9	0.9	0.8	1.0	2.0	0.4	3.6	1.9	1.2	5.0	6.4
4.0	7.0	5.9	1.8	1.6	2.3	2.5	2.2	4.3	5.6	2.9	8.3	9.1
4.1	7.8	7.2	2.2	2.8	3.7	4.4	4.5	6.3	7.3	5.8	11.8	12.0
4.2	9.8	8.9	3.7	4.8	3.7	5.0	7.4	8.2	9.4	9.2	14.7	14.3
4.3	10.7	10.6	5.8	6.9	6.1	6.2	13.2	10.1	11.4	13.1	14.7	14.0
4.4	9.6	11.0	7.9	10.0	7.3	7.1	16.7	11.5	9.8	13.5	13.8	11.9
4.5	9.5	10.9	10.4	12.5	9.7	8.1	14.6	10.7	15.3	15.3	10.0	8.7
4.6	7.6	9.8	13.8	13.8	10.0	10.2	13.8	10.7	18.3	13.5	6.3	5.5
4.7	7.6	8.0	14.1	13.2	11.5	12.3	10.0	7.7	9.2	10.0	3.3	3.3
4.8	6.7	6.2	14.5	11.5	11.1	11.2	9.3	6.0	5.5	6.9	1.5	1.7
4.9	4.0	4.3	10.5	8.3	11.0	9.3	3.6	3.3	3.7	5.0	0.7	0.8
5.0	2.5	2.8	6.3	5.5	8.9	8.2	0.4	2.1	0.9	1.5	0.2	0.3
5.1	1.5	1.6	3.2	3.4	6.5	5.7	0.1	1.4	*	0.4	0.1	0.1
5.2	0.7	0.9	2.0	2.0	3.3	2.6	-	1.3	-	0.1	*	*
5.3	0.2	0.4	1.0	1.1	1.2	1.0	-	0.4	-	*	*	*
5.4	*	0.1	0.6	0.5	0.3	0.3	-	0.2	-	-	*	*
5.5 & Above	*	*	0.1	0.3	*	*	-	0.1	-	-	-	*
Average	4.35	4.39	4.64	4.62	4.64	4.60	4.45	4.35	4.43	4.46	4.23	4.21

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 06 2018

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	21.0	23.2	3.4	2.2	1.0	0.7	2.0	0.9	2.9	1.9	1.2	0.6
Bark - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	0.1	0.1	0.1	0.1	*	0.1	0.1	0.2	*	0.1	-	-
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	-	-	*	*	*	0.7	0.5	*	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	0.1	*	0.1	*	*	0.3	0.1	-	-	-	-
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	*	-	*	-	*	-	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	*	-	-	*	*	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	*	*	-	*	*	*	-	-	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	-	0.1	*	*	*	*	*	*	-	*	-	-
Plastic - Level 2	-	-	-	-	-	-	*	*	-	-	-	-
STRENGTH 1/ 22 & Below	*	*	-	*	-	*	-	*	-	-	-	-
23	*	*	*	*	-	*	*	*	0.1	*	-	-
24	0.1	0.2	*	*	*	*	0.1	0.1	0.2	0.1	-	-
25	0.1	1.4	0.5	0.1	0.4	0.2	0.7	0.4	1.0	0.7	-	-
26	0.1	3.1	1.3	0.7	1.2	1.1	2.4	1.6	3.6	2.8	*	*
27	5.6	7.5	3.6	3.1	5.7	5.6	5.6	4.8	8.0	6.7	2.9	1.3
28	17.4	22.7	14.2	10.0	20.3	17.3	15.6	13.5	15.8	14.7	23.6	13.0
29	33.9	35.5	34.9	25.7	30.6	28.0	30.2	28.5	21.1	23.6	21.6	24.2
30	23.6	16.9	29.7	28.3	20.6	24.6	28.2	28.4	19.2	22.2	33.6	31.6
31	12.0	8.3	10.2	17.5	11.0	12.8	12.1	14.6	15.0	14.9	15.6	23.1
32	6.6	4.1	3.9	9.2	5.5	6.4	3.9	5.6	9.6	8.5	2.6	6.4
33	0.4	0.2	1.6	3.7	3.5	3.1	1.0	2.0	4.3	4.1	0.1	0.3
34	0.1	*	0.1	1.2	1.0	0.8	0.2	0.4	1.8	1.4	*	*
35	*	*	*	0.3	0.2	0.1	*	0.1	0.3	0.2	-	*
36	-	-	*	0.1	*	*	*	*	*	*	-	-
37	-	-	-	*	*	*	-	*	*	*	-	-
38	-	-	-	*	-	-	-	-	-	*	-	-
39	-	-	-	-	-	*	-	-	-	-	-	-
40 & Above	-	-	-	-	-	-	-	-	-	-	-	-
Average	29.83	29.38	29.87	30.40	29.87	29.99	29.77	30.01	30.03	30.07	29.91	30.29
Mike												
2.4 & Below	-	*	-	-	-	-	-	-	-	-	-	-
2.5	0.5	0.2	-	*	-	-	-	-	-	-	-	-
2.6	0.3	0.7	-	-	-	-	-	-	-	-	-	-
2.7	0.5	0.9	-	-	*	*	-	-	-	*	-	-
2.8	0.7	1.2	-	-	-	-	-	-	*	*	0.2	0.1
2.9	0.1	1.0	-	-	-	-	-	*	*	*	0.3	0.1
3.0	1.0	1.3	-	*	*	*	*	*	*	*	0.7	0.4
3.1	6.6	2.6	*	*	*	*	-	*	*	*	0.3	0.2
3.2	5.3	2.9	-	*	*	*	-	*	*	*	0.5	0.3
3.3	6.7	6.6	-	*	*	*	*	*	0.1	0.1	1.7	0.7
3.4	7.7	7.7	-	*	0.1	*	*	*	0.1	0.1	3.1	1.3
3.5	10.0	6.8	-	*	0.1	*	0.1	*	0.2	0.2	3.5	2.7
3.6	10.8	6.7	-	*	0.2	0.1	0.1	0.1	0.3	0.3	7.7	4.9
3.7	7.8	10.8	*	0.1	0.3	0.2	0.2	0.2	0.7	0.4	2.9	3.0
3.8	8.2	9.7	*	0.1	0.7	0.4	0.4	0.4	1.3	0.7	5.1	7.3
3.9	5.5	7.5	0.2	0.3	1.1	0.8	0.5	0.7	1.6	1.3	7.1	8.4
4.0	4.2	7.5	0.1	0.5	1.2	1.1	0.6	1.1	2.6	2.0	9.7	10.3
4.1	3.6	7.8	0.2	1.1	2.9	2.1	1.4	1.9	4.1	3.2	5.8	6.5
4.2	4.3	4.5	0.9	2.0	5.1	4.0	2.7	3.0	5.7	4.8	8.7	10.0
4.3	3.1	5.4	2.3	2.8	7.1	6.0	4.5	4.4	7.1	6.9	7.6	9.2
4.4	7.8	4.9	4.7	3.6	8.4	8.3	6.6	6.5	8.9	9.6	10.0	7.9
4.5	1.9	1.9	6.2	6.2	9.9	10.6	8.3	9.2	12.0	13.2	7.1	6.9
4.6	2.6	1.0	7.1	9.6	11.4	11.6	13.4	13.4	12.6	15.1	2.8	5.8
4.7	0.7	0.2	11.7	13.8	11.2	12.3	15.5	16.2	13.3	14.4	5.0	5.1
4.8	-	*	19.0	16.5	12.0	11.2	15.5	16.4	10.7	11.3	5.2	4.8
4.9	-	*	19.2	15.8	11.3	10.0	14.0	13.1	8.3	7.4	1.9	1.8
5.0	*	*	14.8	12.6	7.8	7.6	8.0	7.1	5.0	4.6	1.5	1.0
5.1	*	*	7.0	8.0	4.6	5.7	4.2	3.3	2.8	2.5	1.6	1.3
5.2	-	-	4.2	4.4	2.4	4.1	1.9	1.6	1.8	1.3	-	*
5.3	-	-	2.1	1.9	1.3	2.5	1.5	0.8	0.7	0.5	-	-
5.4	-	-	0.2	0.4	0.5	1.1	0.4	0.3	0.1	0.2	-	-
5.5 & Above	-	-	*	0.2	0.2	0.4	0.1	*	*	*	-	-
Average	3.71	3.75	4.81	4.79	4.64	4.69	4.70	4.68	4.57	4.58	4.14	4.18

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE										
For The Week Ending Dec 06 2018										
Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter										
Bark - Level 1	3.7	4.2	4.7	4.3	0.7	0.3	7.4	5.8	0.3	0.3
Bark - Level 2	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	-	*	*	0.1	*	*	*	0.3	-	*
Grass - Level 2	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	*	-	*	*	*	*	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	*	-	*	*	*	1.6	1.3	-	-
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	*	*	-	-	*	*	*	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	*	-	-	*	*	-	-
Other - Level 2	-	-	-	-	-	-	-	*	-	-
Plastic - Level 1	*	*	*	*	*	*	*	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	*	*	-	-	-	*	0.1	0.2	-	-
23	*	*	0.2	0.1	*	*	0.4	0.3	0.2	*
24	0.1	0.1	1.0	0.3	0.1	*	0.6	0.7	0.9	0.3
25	0.3	0.2	4.2	2.2	0.6	0.2	1.0	1.3	3.3	2.1
26	0.6	0.7	9.1	6.1	5.2	2.4	2.2	2.7	6.8	5.2
27	3.3	3.7	14.1	11.7	16.3	11.0	5.5	5.9	17.5	12.1
28	9.4	9.9	23.2	20.5	28.1	25.3	11.4	12.3	24.5	23.8
29	16.9	19.6	20.3	27.2	21.2	27.9	17.2	18.5	20.6	26.7
30	22.0	23.7	15.2	19.5	13.7	17.6	19.9	20.4	13.7	16.3
31	20.2	17.8	7.7	8.0	9.1	9.5	18.8	17.6	8.4	8.6
32	16.8	13.0	3.3	2.9	4.0	4.1	13.3	11.3	2.5	3.3
33	7.7	7.4	1.4	1.2	1.6	1.5	6.5	5.7	1.0	1.2
34	2.1	2.9	0.3	0.3	0.2	0.3	2.3	2.2	0.5	0.4
35	0.5	0.7	*	*	*	0.1	0.6	0.7	0.1	*
36	*	0.1	*	*	*	*	0.2	0.2	-	*
37	*	*	-	*	-	*	*	*	-	-
38	*	*	-	-	-	-	*	*	-	-
39	-	-	-	-	-	-	*	*	-	-
40 & Above	-	-	-	-	-	-	-	*	-	-
Average	30.83	30.72	28.90	29.23	29.17	29.47	30.45	30.30	28.90	29.21
Mike										
2.4 & Below	-	*	-	-	-	-	*	*	-	-
2.5	*	*	-	-	-	-	0.1	*	-	-
2.6	*	*	*	*	-	-	0.2	*	-	-
2.7	-	*	-	-	-	-	0.2	0.1	-	-
2.8	*	*	-	-	-	-	0.3	0.1	-	-
2.9	0.1	0.1	-	*	-	-	0.4	0.2	-	-
3.0	*	0.1	-	-	*	*	0.6	0.3	-	-
3.1	*	0.1	-	*	-	*	0.8	0.4	-	-
3.2	0.1	0.2	-	*	*	*	1.2	0.6	-	-
3.3	0.5	0.3	*	*	*	*	1.7	0.8	-	*
3.4	0.9	0.4	0.1	0.1	*	*	2.5	1.2	-	-
3.5	1.1	0.5	0.1	0.2	0.1	*	3.2	1.6	*	*
3.6	1.2	0.7	0.3	0.4	0.2	0.1	3.9	2.0	0.2	*
3.7	2.1	1.3	0.6	0.9	0.4	0.2	4.5	2.5	0.3	0.1
3.8	3.3	2.3	1.6	1.7	0.6	0.3	5.3	3.1	0.3	0.1
3.9	3.3	3.4	2.5	3.2	0.9	0.5	6.1	3.8	0.3	0.1
4.0	4.6	5.5	4.6	6.0	1.3	1.0	6.7	4.5	0.6	0.2
4.1	8.0	7.9	8.2	9.7	2.3	1.7	7.2	5.3	0.6	0.5
4.2	8.6	8.9	10.2	13.0	2.9	2.5	7.6	6.1	1.3	1.6
4.3	10.3	9.4	14.2	15.0	4.1	3.7	7.8	7.0	2.7	3.3
4.4	9.4	10.9	14.9	14.9	5.7	5.4	7.5	7.7	6.0	7.3
4.5	10.5	11.8	13.5	12.1	8.8	7.8	7.2	8.5	13.5	14.1
4.6	8.5	10.1	10.7	9.1	9.3	10.0	6.5	8.7	18.8	20.6
4.7	7.2	8.2	7.5	6.3	11.4	11.6	5.7	8.4	19.9	20.5
4.8	6.6	6.8	5.1	4.0	12.9	12.8	5.0	7.4	14.6	15.6
4.9	4.6	4.9	3.2	1.8	12.2	12.1	3.4	6.1	12.0	8.7
5.0	3.3	3.0	1.7	1.0	11.5	11.1	2.1	4.7	5.1	4.4
5.1	2.4	1.7	0.8	0.4	7.7	8.6	1.3	3.5	2.6	2.0
5.2	2.3	1.1	0.2	0.1	4.6	5.6	0.6	2.4	0.9	0.7
5.3	0.8	0.4	0.2	0.1	2.2	3.1	0.3	1.6	0.3	0.2
5.4	0.2	0.1	-	*	0.8	1.5	0.1	1.0	0.1	*
5.5 & Above	*	0.1	-	*	0.2	0.4	*	0.7	*	*
Average	4.40	4.42	4.40	4.35	4.73	4.77	4.18	4.43	4.67	4.66

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 06 2018

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	*	*	-	-	*	*	-	*	-	-	*	*
2.7 - 2.9	*	*	*	*	0.2	0.1	-	0.3	-	-	*	*
3.0 - 3.2	0.1	0.1	0.2	*	0.4	0.2	0.2	1.2	-	*	0.4	0.4
3.3 - 3.4	0.7	0.6	0.1	0.1	0.4	0.4	1.6	2.2	*	*	1.4	1.4
3.5 - 3.6	2.1	1.7	0.1	0.2	0.3	1.0	0.5	3.3	0.3	0.3	2.8	3.3
3.7 - 4.2	36.4	30.9	9.4	10.7	11.6	16.1	15.9	27.3	25.7	20.3	44.8	48.5
4.3 - 4.9	55.7	60.8	76.9	76.2	66.8	64.4	81.2	60.1	73.1	77.3	50.2	46.0
5.0 - 5.2	4.8	5.3	11.5	11.0	18.7	16.5	0.6	4.9	0.9	2.0	0.3	0.4
5.3 & Above	0.2	0.5	1.7	1.8	1.6	1.3	-	0.7	-	*	*	*
Average	4.35	4.39	4.64	4.62	4.64	4.60	4.45	4.35	4.43	4.46	4.23	4.21
Leaf												
1 - 2	3.7	3.2	1.8	1.5	35.8	33.6	63.1	68.7	0.6	0.7	3.8	7.2
3	33.1	38.2	33.8	26.7	47.2	44.4	33.8	28.5	24.4	27.0	40.0	49.5
4	41.7	43.3	48.7	49.3	14.2	17.8	3.0	2.6	57.5	56.0	45.1	37.0
5	17.2	13.2	14.5	20.3	2.1	3.4	0.1	0.2	17.0	15.2	10.4	6.0
6	3.8	2.0	1.1	2.2	0.3	0.5	-	*	0.6	1.1	0.7	0.3
7	0.5	0.1	0.1	*	0.1	0.2	-	*	-	*	*	*
8	*	*	-	*	0.2	0.1	-	-	-	*	*	*
Average	3.86	3.73	3.79	3.95	2.82	2.89	2.26	2.18	3.93	3.89	3.64	3.43
HVI Trash 1/												
00	-	-	-	-	-	*	*	*	-	-	-	-
01	0.3	0.2	*	0.1	8.4	10.9	27.9	30.4	-	*	0.3	0.6
02	5.2	5.0	3.3	2.3	32.9	28.7	38.6	43.6	1.2	1.4	5.2	9.2
03	15.7	18.1	15.0	10.7	29.1	26.2	23.2	19.2	9.2	10.6	17.4	23.0
04	22.0	25.1	24.0	19.9	16.0	16.4	7.5	5.0	23.2	25.2	24.2	25.9
05	19.9	21.1	23.0	22.4	7.3	9.1	2.1	1.3	26.2	27.2	22.0	19.7
06	14.3	13.7	16.0	18.6	3.0	4.4	0.5	0.4	21.0	18.9	15.1	11.6
07	9.4	8.1	9.6	12.5	1.4	2.0	0.1	0.1	11.5	9.6	8.5	5.8
08	6.0	4.4	4.9	7.1	0.6	1.0	-	*	5.0	4.3	4.1	2.5
09	3.5	2.3	2.3	3.6	0.4	0.5	*	*	1.8	1.8	1.8	1.0
10	1.8	1.1	1.1	1.7	0.2	0.3	-	*	0.6	0.6	0.7	0.4
11	1.0	0.5	0.4	0.7	0.1	0.2	-	*	0.1	0.2	0.3	0.1
12	0.5	0.2	0.1	0.3	0.1	0.1	-	-	*	0.1	0.1	0.1
13	0.2	0.1	*	0.1	*	0.1	-	-	*	*	0.1	*
14	0.1	*	*	*	*	0.1	-	-	-	*	*	*
15	*	*	*	*	0.1	*	-	-	-	-	*	*
16	*	*	*	*	*	*	-	-	-	-	*	*
17	*	*	-	*	*	*	-	-	-	-	*	*
18 & Above	*	*	*	*	0.1	0.1	-	-	-	*	*	*
Average	0.52	0.49	0.50	0.55	0.31	0.32	0.22	0.20	0.52	0.51	0.48	0.44
UNIFORMITY 2/												
74 & Below	-	-	-	-	-	-	-	*	-	-	-	-
75	*	*	-	-	*	*	-	-	-	-	-	*
76	0.1	*	*	*	-	*	-	*	0.1	*	*	*
77	0.3	0.3	0.1	0.1	0.1	*	*	0.1	0.3	0.2	0.2	0.2
78	1.8	1.8	0.9	0.4	1.0	0.8	*	0.9	1.0	0.9	1.3	1.8
79	9.6	9.8	5.0	2.8	7.0	5.6	0.2	2.3	10.5	14.1	7.5	9.9
80	32.8	32.8	22.6	14.8	23.1	23.3	7.5	7.2	48.7	56.2	28.4	32.7
81	40.5	38.7	39.0	35.0	36.6	40.5	23.6	20.4	35.9	26.0	39.6	37.1
82	13.0	14.0	24.5	33.3	22.8	24.4	27.9	26.8	3.5	2.3	18.6	14.9
83	1.8	2.3	7.1	12.7	8.5	4.8	10.2	19.4	0.2	0.3	4.0	3.0
84	0.2	0.3	0.8	0.9	0.8	0.4	25.6	19.8	*	*	0.5	0.3
85 & Above	*	*	*	*	0.1	0.1	5.0	3.0	-	-	*	*
Average	81.04	81.05	81.51	81.84	81.48	81.43	82.81	82.67	80.75	80.60	81.25	81.08
Tenderables	63.2	63.7	72.5	70.8	72.9	74.8	97.1	90.1	55.8	64.0	72.1	82.3
SAMPLES CLASSED	61,899	511,273	86,273	1,023,794	25,259	102,364	12,730	91,311	7,996	45,269	148,342	1,113,498

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on New York No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 06 2018

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	*	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	0.8	0.9	-	*	-	-	-	-	-	-	-	-
2.7 - 2.9	1.3	3.1	-	-	*	*	-	*	*	*	0.5	0.2
3.0 - 3.2	12.9	6.8	*	*	*	*	*	*	*	*	1.4	0.9
3.3 - 3.4	14.4	14.4	-	*	0.1	*	*	*	0.1	0.2	4.8	2.0
3.5 - 3.6	20.8	13.5	-	*	0.4	0.1	0.2	0.1	0.5	0.5	11.2	7.5
3.7 - 4.2	33.7	47.8	1.4	4.1	11.5	8.5	5.9	7.4	16.0	12.4	39.3	45.5
4.3 - 4.9	16.0	13.4	70.4	68.4	71.3	70.0	77.8	79.3	72.9	77.8	39.7	41.6
5.0 - 5.2	*	*	26.0	25.0	14.8	17.4	14.1	12.1	9.7	8.4	3.1	2.2
5.3 & Above	-	-	2.3	2.5	1.9	3.9	2.0	1.1	0.8	0.7	-	-
Average	3.71	3.75	4.81	4.79	4.64	4.69	4.70	4.68	4.57	4.58	4.14	4.18
Leaf												
1 - 2	11.8	8.8	6.7	6.6	1.6	2.7	3.6	3.6	3.4	4.3	37.8	33.8
3	34.7	40.4	43.8	45.7	37.2	32.9	33.4	34.6	39.9	47.3	42.3	48.9
4	30.0	34.8	37.9	38.5	48.3	48.5	44.5	44.8	43.7	39.8	15.6	13.4
5	20.1	13.7	10.8	8.6	12.0	14.9	16.8	15.6	11.7	8.0	3.9	3.5
6	3.3	2.2	0.8	0.6	0.9	1.0	1.7	1.5	1.3	0.6	0.5	0.4
7	0.1	0.1	*	*	*	*	0.1	*	*	*	-	*
8	-	*	-	*	-	-	*	*	-	*	-	-
Average	3.69	3.60	3.55	3.51	3.74	3.79	3.80	3.77	3.68	3.53	2.85	2.85
HVI Trash 1/												
00	-	-	-	-	-	-	-	-	-	-	-	-
01	1.3	1.3	0.7	0.6	*	0.1	0.2	0.2	0.2	0.3	6.6	5.5
02	13.3	10.0	8.8	9.2	2.4	3.2	5.2	5.5	4.8	6.0	33.2	29.1
03	18.5	19.3	21.7	22.1	13.8	12.1	16.0	16.4	17.2	20.6	27.7	30.3
04	15.8	20.8	24.2	24.8	23.5	20.4	22.2	22.5	24.4	26.7	14.9	17.1
05	11.9	16.3	18.8	19.5	23.3	22.8	21.2	21.4	21.4	21.1	8.2	8.9
06	11.4	12.5	12.7	12.1	17.8	18.8	15.8	15.8	14.9	13.0	5.1	4.8
07	9.9	8.1	7.0	6.5	10.4	12.0	9.8	9.5	8.5	6.8	2.3	2.3
08	7.5	5.2	3.6	3.0	5.1	6.1	5.3	4.9	4.5	3.2	1.0	1.1
09	4.6	3.0	1.5	1.3	2.2	2.7	2.4	2.2	2.2	1.4	0.6	0.5
10	2.7	1.7	0.7	0.5	0.9	1.1	1.0	0.9	1.1	0.6	0.3	0.2
11	1.6	0.9	0.2	0.2	0.3	0.4	0.4	0.4	0.5	0.2	0.1	0.1
12	0.8	0.5	0.1	0.1	0.1	0.1	0.2	0.1	0.2	0.1	*	*
13	0.3	0.2	*	*	*	*	0.1	0.1	0.1	*	-	-
14	0.1	0.1	*	*	*	*	*	*	*	*	-	-
15	0.1	*	-	*	*	*	*	*	*	*	-	-
16	-	*	-	-	-	*	*	*	*	*	-	-
17	*	*	-	-	-	*	-	*	*	*	-	-
18 & Above	-	*	-	-	-	*	*	*	*	*	-	-
Average	0.51	0.48	0.45	0.45	0.51	0.53	0.50	0.49	0.49	0.46	0.32	0.33
UNIFORMITY 2/												
74 & Below	*	*	*	*	-	-	*	*	*	*	-	-
75	-	*	*	*	-	-	*	*	*	*	-	-
76	0.1	0.2	0.1	0.1	*	*	*	*	0.1	0.1	-	-
77	0.4	1.0	0.3	0.6	0.1	*	0.5	0.3	0.8	0.6	0.1	*
78	4.7	3.9	5.1	3.4	0.2	0.1	2.8	1.8	3.7	3.3	0.7	0.3
79	22.2	19.1	14.3	12.6	1.7	0.7	10.7	8.5	15.7	14.9	4.2	1.6
80	38.9	45.3	32.2	29.5	10.9	5.7	34.6	29.6	29.8	33.4	9.2	5.6
81	24.3	25.1	35.7	34.3	31.0	24.5	36.1	38.9	31.6	32.8	24.1	24.1
82	8.7	4.7	10.1	14.9	37.4	41.9	13.5	17.4	15.2	12.6	46.2	50.1
83	0.7	0.7	1.9	3.7	16.1	24.1	1.7	3.1	2.7	2.1	14.3	17.5
84	*	*	0.2	0.7	2.4	2.9	0.2	0.3	0.2	0.2	1.2	0.7
85 & Above	*	*	-	0.1	0.3	0.1	*	*	*	*	0.1	*
Average	80.57	80.51	80.81	81.01	82.07	82.37	80.96	81.16	80.90	80.87	82.01	82.21
Tenderables	49.2	54.5	50.1	57.8	76.6	68.0	71.5	77.1	77.7	75.4	88.5	93.0
SAMPLES CLASSED	4,959	23,723	24,015	362,722	60,157	633,567	120,389	1,077,235	74,539	562,849	4441	11977

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on New York No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 06 2018

Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE										
2.4 & Below	-	*	-	-	-	-	*	*	-	-
2.5 - 2.6	*	*	*	*	-	-	0.3	0.1	-	-
2.7 - 2.9	0.1	0.1	-	*	-	-	0.9	0.3	-	-
3.0 - 3.2	0.2	0.3	-	*	*	*	2.5	1.2	-	-
3.3 - 3.4	1.4	0.7	0.1	0.1	*	*	4.2	2.0	-	*
3.5 - 3.6	2.3	1.2	0.4	0.6	0.3	0.1	7.1	3.5	0.2	*
3.7 - 4.2	29.8	29.3	27.6	34.5	8.3	6.2	37.5	25.2	3.5	2.6
4.3 - 4.9	57.2	61.9	69.0	63.3	64.4	63.5	43.1	53.8	87.5	90.0
5.0 - 5.2	8.0	5.8	2.7	1.5	23.7	25.2	4.0	10.5	8.5	7.0
5.3 & Above	1.0	0.6	0.2	0.1	3.2	5.0	0.4	3.3	0.3	0.3
Average	4.40	4.42	4.40	4.35	4.73	4.77	4.18	4.43	4.67	4.66
Leaf										
1 - 2	10.3	9.5	4.1	4.8	8.9	9.1	15.6	21.8	7.3	8.3
3	53.7	52.8	30.8	38.5	46.5	48.8	44.9	43.6	66.3	69.0
4	27.6	29.5	46.1	44.3	34.3	35.0	27.7	25.2	24.4	21.9
5	7.0	6.7	17.1	11.6	9.7	6.7	9.1	7.5	1.8	0.8
6	1.2	1.2	1.9	0.8	0.7	0.4	2.1	1.5	0.1	*
7	0.2	0.2	*	*	-	*	0.5	0.3	-	-
8	*	*	-	*	-	-	0.1	0.1	-	-
Average	3.36	3.38	3.82	3.65	3.47	3.40	3.38	3.22	3.21	3.15
HVI Trash 1/										
00	-	-	-	-	-	-	*	*	-	-
01	0.6	0.6	0.3	0.3	0.6	0.7	2.3	4.8	0.3	0.4
02	12.5	10.3	5.0	5.9	10.6	10.0	17.0	19.3	10.0	11.3
03	26.8	23.9	13.7	16.4	22.6	22.2	24.3	23.3	31.3	33.4
04	24.6	24.9	21.3	23.7	22.4	24.8	20.3	19.3	31.6	31.6
05	16.3	18.0	22.2	22.4	17.2	19.3	14.2	13.4	16.5	15.7
06	9.1	10.6	16.8	15.4	11.4	11.8	9.1	8.5	6.6	5.4
07	4.7	5.6	10.3	8.7	7.4	6.2	5.5	5.0	2.4	1.6
08	2.6	2.9	5.5	4.2	4.2	2.9	3.1	2.8	0.8	0.5
09	1.3	1.5	2.8	1.8	2.1	1.3	1.8	1.6	0.3	0.1
10	0.7	0.8	1.3	0.8	1.0	0.5	1.0	0.9	0.1	*
11	0.3	0.4	0.5	0.3	0.4	0.2	0.6	0.5	*	*
12	0.2	0.2	0.2	0.1	0.2	0.1	0.3	0.3	*	*
13	0.1	0.1	0.1	*	*	*	0.2	0.2	-	*
14	0.1	0.1	*	*	*	*	0.1	0.1	*	*
15	*	*	*	*	*	*	0.1	0.1	-	*
16	*	*	-	*	-	*	*	*	*	*
17	*	*	-	*	-	*	*	*	-	-
18 & Above	*	*	*	*	-	*	*	*	-	-
Average	0.42	0.44	0.51	0.48	0.45	0.44	0.42	0.40	0.39	0.38
UNIFORMITY 2/										
74 & Below	*	*	-	*	-	-	*	*	*	*
75	*	*	*	*	-	-	0.2	0.2	*	*
76	0.1	0.1	0.2	0.1	*	*	0.5	0.6	0.1	0.1
77	0.7	0.5	1.4	0.8	0.2	0.1	2.0	1.7	0.6	0.5
78	3.0	2.3	6.9	4.9	1.3	0.5	5.9	4.3	3.9	2.9
79	13.4	11.5	25.1	20.3	10.5	4.9	16.8	12.0	20.9	18.0
80	30.1	30.4	35.3	39.8	29.0	19.8	32.2	25.5	42.3	40.9
81	35.6	35.0	22.5	26.1	31.8	35.7	28.9	30.2	25.0	28.6
82	14.5	16.3	7.2	6.8	20.5	29.9	11.1	19.1	6.3	8.0
83	2.3	3.4	1.3	1.0	5.9	8.3	2.1	5.6	0.8	1.0
84	0.2	0.5	0.1	0.1	0.8	0.8	0.2	0.7	0.1	0.1
85 & Above	*	0.1	-	*	*	*	*	*	*	*
Average	80.94	81.07	80.42	80.55	81.25	81.63	80.65	81.04	80.55	80.67
Tenderables	81.9	81.9	80.9	80.5	60.6	44.9	74.1	65.9	81.9	79.7
SAMPLES CLASSED	38,053	150,969	31,169	226,595	63,696	678,986	574,546	3,554,173	19,920	134,683

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on New York No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 06 2018

Color Grade	Leaf	Arizona		California		New Mexico		Texas	
		Week	Season	Week	Season	Week	Season	Week	Season
01	1	0.3	4.3	18.0	21.7	-	-	-	-
	2	0.2	20.5	22.6	22.4	-	-	-	-
	3	-	2.2	0.5	0.3	-	-	-	-
	4	-	*	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		0.5	27.0	41.1	44.4	-	-	-	-
02	1	17.4	7.8	5.1	6.3	-	-	-	-
	2	27.1	18.9	39.4	38.5	-	-	-	-
	3	1.5	1.9	10.7	7.8	-	-	-	-
	4	-	-	0.1	0.1	-	-	-	-
	5	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		46.0	28.5	55.3	52.6	-	-	-	-
03	1	3.3	2.2	*	*	-	-	-	-
	2	32.2	25.4	1.3	1.3	-	-	-	-
	3	7.1	7.7	1.9	1.4	-	-	-	-
	4	0.2	0.3	0.3	0.2	-	-	-	-
	5	-	-	*	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		42.8	35.6	3.5	2.9	-	-	-	-
04	1	-	*	-	*	-	-	-	-
	2	4.1	3.7	*	*	-	-	-	-
	3	3.6	3.9	*	*	-	-	-	-
	4	-	0.2	*	*	-	-	-	-
	5	-	-	*	*	-	-	-	-
	6	-	*	-	*	-	-	-	-
	7	-	0.1	-	-	-	-	-	-
Total -----		7.7	7.9	0.1	0.1	-	-	-	-
05	1	-	-	-	-	-	-	-	-
	2	0.7	0.2	-	*	-	-	-	-
	3	2.0	0.7	-	*	-	-	-	-
	4	0.2	0.1	-	*	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		2.9	1.0	-	*	-	-	-	-
06	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	*	*	-	*	-	-	-	-
	4	-	-	-	*	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		*	*	-	*	-	-	-	-
07	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-
	4	-	-	-	*	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	-	*	-	-	-	-
STAPLE									
44 & Shorter		-	0.1	0.1	0.2	-	-	-	-
46		*	27.4	4.1	4.5	-	-	-	-
48		30.4	28.2	32.6	36.7	-	-	-	-
50		68.9	43.5	55.1	53.5	-	-	-	-
52 & Longer		0.7	0.8	8.1	5.1	-	-	-	-
Average Staple		49.41	48.35	49.34	49.17	-	-	-	-
Average Length		1.43	1.41	1.43	1.43	-	-	-	-
EXTRANEIOUS MATTER									
Bark		-	-	-	*	-	-	-	-
Grass		-	0.2	-	0.2	-	-	-	-
Spindle Twist		-	-	0.1	*	-	-	-	-
Preperation		-	*	*	*	-	-	-	-
All Other		-	0.1	*	*	-	-	-	-

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 06 2018

Quality Designation	Arizona		California		New Mexico		Texas	
	Week	Season	Week	Season	Week	Season	Week	Season
MIKE								
2.4 & Below	-	-	*	*	-	-	-	-
2.5 - 2.6	-	-	*	*	-	-	-	-
2.7 - 2.9	-	-	0.3	0.1	-	-	-	-
3.0 - 3.2	-	0.1	0.9	0.3	-	-	-	-
3.3 - 3.4	-	0.3	1.8	0.9	-	-	-	-
3.5 - 3.6	3.0	1.3	6.3	3.6	-	-	-	-
3.7 - 4.2	69.5	78.1	54.1	52.0	-	-	-	-
4.3 - 4.9	27.5	20.2	36.7	43.1	-	-	-	-
5.0 - 5.2	-	-	*	*	-	-	-	-
5.3 & Above	-	-	-	-	-	-	-	-
Average	4.09	4.06	4.11	4.16	-	-	-	-
ALL RANGE MIKE								
2.4 & Below	-	-	*	*	-	-	-	-
2.5	-	-	*	*	-	-	-	-
2.6	-	-	-	*	-	-	-	-
2.7	-	-	*	*	-	-	-	-
2.8	-	-	0.1	*	-	-	-	-
2.9	-	-	0.1	*	-	-	-	-
3.0	-	-	0.2	0.1	-	-	-	-
3.1	-	-	0.2	0.1	-	-	-	-
3.2	-	0.1	0.4	0.2	-	-	-	-
3.3	-	0.1	0.5	0.3	-	-	-	-
3.4	-	0.3	1.3	0.6	-	-	-	-
3.5	-	0.1	2.8	1.3	-	-	-	-
3.6	3.0	1.2	3.6	2.2	-	-	-	-
3.7	4.4	3.3	5.1	3.4	-	-	-	-
3.8	7.2	9.2	6.1	5.5	-	-	-	-
3.9	12.2	17.4	7.8	7.7	-	-	-	-
4.0	14.1	20.9	10.1	10.1	-	-	-	-
4.1	14.2	15.3	11.1	11.2	-	-	-	-
4.2	17.5	11.9	13.8	14.1	-	-	-	-
4.3	19.7	11.8	12.9	15.9	-	-	-	-
4.4	6.6	4.5	11.3	14.0	-	-	-	-
4.5	1.2	2.9	7.4	8.4	-	-	-	-
4.6	-	0.8	3.2	3.5	-	-	-	-
4.7	-	0.2	1.3	1.0	-	-	-	-
4.8	-	*	0.4	0.2	-	-	-	-
4.9	-	*	0.1	*	-	-	-	-
5.0	-	-	*	*	-	-	-	-
5.1	-	-	-	-	-	-	-	-
5.2	-	-	*	*	-	-	-	-
5.3 & Above	-	-	-	-	-	-	-	-
Average	4.09	4.06	4.11	4.16	-	-	-	-
STRENGTH 1/ 36 & Below	-	0.1	*	0.2	-	-	-	-
37	-	0.2	0.3	0.5	-	-	-	-
38	*	1.4	3.8	2.2	-	-	-	-
39	0.1	8.8	5.9	4.0	-	-	-	-
40	0.4	11.8	4.2	4.0	-	-	-	-
41	4.5	7.7	4.8	4.2	-	-	-	-
42	19.1	11.0	9.7	8.9	-	-	-	-
43	35.0	25.4	16.9	17.1	-	-	-	-
44	28.0	22.1	21.4	24.6	-	-	-	-
45	11.4	8.5	19.9	20.4	-	-	-	-
46	1.1	2.5	8.7	9.2	-	-	-	-
47	0.3	0.5	2.9	3.2	-	-	-	-
48 & Above	0.1	0.2	1.4	1.4	-	-	-	-
Average	43.73	42.90	43.75	43.98	-	-	-	-
UNIFORMITY								
83 & Below	*	0.1	0.6	0.5	-	-	-	-
84	0.2	3.4	8.1	5.4	-	-	-	-
85	14.8	33.8	26.1	21.5	-	-	-	-
86	69.4	45.6	50.4	54.1	-	-	-	-
87	15.4	16.9	13.7	17.0	-	-	-	-
88 & Above	0.1	0.2	1.2	1.4	-	-	-	-
Average	86.45	86.20	86.17	86.31	-	-	-	-
Samples Classed	2,263	11,456	49,874	315,637	-	-	-	-