



State	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
AL	26	90.5	79.1	63,256	26	88.4	75.0	365,317
AR	27	79.5	56.2	146,726	28	79.2	55.9	1,035,144
AZ	8	92.9	78.1	14,492	8	87.6	62.5	51,558
CA	4	85.0	66.9	4,075	6	88.7	75.6	23,352
FL	4	70.6	42.1	8,912	4	73.6	48.0	53,620
GA	55	94.1	83.0	181,622	55	93.3	80.7	792,701
KS	3	57.6	43.5	14,764	3	48.7	28.8	49,787
LA	6	47.4	26.0	6,936	17	64.4	38.5	201,142
MO	19	92.9	75.2	66,273	19	91.4	72.9	464,905
MS	29	59.4	35.4	68,159	35	59.5	33.8	733,160
NC	32	62.6	39.8	84,688	32	62.5	39.9	406,900
NM	2	98.9	79.2	1,710	3	95.2	77.5	3,280
OK	11	79.4	62.5	20,539	11	82.9	62.8	78,619
SC	12	85.3	70.6	35,057	12	88.8	73.7	129,873
TN	18	97.6	90.4	69,505	18	97.6	90.0	432,568
TX	103	72.5	50.5	259,994	145	77.7	46.1	1,749,708
VA	4	85.5	67.1	20,031	4	88.6	70.3	70,031
United States	363	80.3	62.2	1,066,739	426	79.5	57.2	6,641,665
AMERICAN PIMA								
AZ*	-			-	-			-
CA	12			31,002	12			83,649
NM*	-			-	2			8,739
TX	3			2,494	3			5,638
United States	17			35,236	18			99,510
United States all cotton	377			1,101,975	440			6,741,175

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Nov 23, 2023

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	12.5	9.3	4.6	7.6	85.8	72.4	43.5	40.1	1.5	1.5	2.3	2.3
	3	11.1	8.9	1.8	2.9	5.0	5.9	14.9	15.4	2.7	1.6	2.5	1.7
	4	1.0	0.6	*	0.1	0.1	0.2	0.5	1.7	0.2	0.1	0.3	0.1
	5	*	*	-	*	-	*	-	*	-	-	*	*
	6	-	-	-	-	-	-	-	-	-	-	*	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	24.5	18.8	6.5	10.6	90.9	78.5	58.9	57.2	4.4	3.2	5.0	4.1
31	1 - 2	7.4	9.1	13.0	13.4	5.7	5.9	9.1	6.4	10.9	8.1	9.8	11.0
	3	33.7	36.9	36.3	38.9	2.7	3.1	19.9	15.1	36.6	32.8	39.5	38.0
	4	14.0	14.4	15.0	12.5	0.4	1.0	4.8	13.6	10.3	12.8	14.0	12.5
	5	1.6	1.5	1.6	1.0	0.1	0.1	0.3	3.1	1.2	1.3	1.4	1.1
	6	0.1	0.1	*	*	*	*	-	0.1	*	0.1	0.1	*
	7	*	*	-	*	-	-	-	-	-	*	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	56.7	62.0	66.0	65.8	8.9	10.2	34.0	38.3	58.9	55.2	64.8	62.7
41	1 - 2	0.7	0.7	0.3	0.4	*	0.1	0.1	*	1.9	0.9	0.8	1.0
	3	6.8	6.4	8.1	7.1	-	0.1	0.3	0.2	16.1	12.7	12.1	13.4
	4	6.8	6.9	13.1	11.4	*	*	0.1	1.1	11.7	13.6	12.3	12.4
	5	2.1	2.2	4.8	3.7	*	*	0.2	0.6	2.2	3.6	3.2	3.3
	6	0.3	0.3	0.6	0.4	-	-	0.1	0.2	0.2	0.5	0.4	0.4
	7	*	*	0.1	*	-	-	-	-	*	0.1	*	*
	8	-	*	-	-	-	-	-	-	-	*	*	*
Total	----	16.8	16.5	27.1	23.0	*	0.2	0.9	2.0	32.1	31.3	28.7	30.5
51	1 - 2	*	*	-	*	-	-	-	-	0.1	*	-	*
	3	0.1	*	*	*	-	-	-	-	0.9	0.2	*	*
	4	0.1	*	0.1	0.1	-	-	-	-	1.1	0.2	*	*
	5	0.1	*	0.1	0.1	-	-	-	-	0.4	0.1	*	*
	6	*	*	*	*	-	-	-	-	*	*	*	*
	7	-	-	*	*	-	-	-	-	*	*	-	*
	8	-	-	-	*	-	-	-	-	-	-	-	-
Total	----	0.3	0.1	0.2	0.2	-	-	-	-	2.5	0.5	0.1	0.1
61	1 - 2	-	*	-	*	-	-	-	-	-	-	-	-
	3	-	*	-	-	-	-	-	-	-	-	-	*
	4	*	*	-	*	-	-	-	-	-	-	-	*
	5	-	*	-	-	-	-	-	-	-	-	-	*
	6	-	-	-	*	-	-	-	-	-	-	-	*
	7	-	-	*	*	-	-	-	-	-	-	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	*	*	-	-	-	-	-	-	*	*
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	-	-	-	-	-
12 & 22	1 - 2	*	*	*	*	-	6.8	0.1	0.1	-	*	*	*
	3	*	*	*	*	-	2.2	0.4	0.2	-	*	*	*
	4	-	*	*	*	-	0.1	*	*	-	-	-	*
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	*	*	-	9.1	0.6	0.3	-	*	*	*
32	1 - 2	0.1	0.1	*	*	*	0.4	-	0.1	*	0.2	*	0.1
	3	0.4	0.6	*	0.1	*	0.9	0.5	0.3	0.2	2.1	0.3	0.5
	4	0.2	0.3	*	*	0.1	0.4	2.2	0.7	0.4	1.0	0.2	0.2
	5	*	*	*	*	*	0.1	2.0	0.5	*	0.1	*	*
	6	-	*	-	*	-	*	0.3	0.1	-	*	*	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.6	1.0	0.1	0.1	0.1	1.7	4.9	1.6	0.7	3.4	0.5	0.8
42	1 - 2	*	*	*	*	-	*	-	*	*	0.1	*	*
	3	0.4	0.5	*	0.1	-	*	-	*	0.5	2.7	0.3	0.6
	4	0.3	0.6	*	0.1	-	*	*	0.1	0.6	2.5	0.4	0.8
	5	0.1	0.3	*	0.1	-	*	0.1	0.2	0.2	0.6	0.1	0.2
	6	*	0.1	*	*	-	*	0.1	0.2	*	0.1	*	*
	7	*	*	-	*	-	-	-	-	-	*	*	*
	8	-	*	-	-	-	-	-	-	-	-	-	*
Total	----	0.9	1.5	0.1	0.2	-	0.1	0.3	0.4	1.3	6.1	0.9	1.7

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Nov 23, 2023

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	*	*	-	*	-	-	-	-	-	-	*	*
	3	*	*	-	*	-	-	-	-	*	*	*	*
	4	*	*	*	*	-	-	-	-	0.1	*	*	*
	5	*	*	*	*	-	-	-	-	*	*	*	*
	6	*	*	*	*	-	-	-	-	*	*	*	*
	7	-	*	-	*	-	-	-	-	-	*	-	*
	8	-	-	-	*	-	-	-	-	-	-	-	-
Total	----	0.1	*	*	*	-	-	-	-	0.1	0.1	*	*
62	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	*	-	-	-	-	-	-	-	-	-	*
	4	-	*	-	-	-	-	-	-	-	-	-	*
	5	-	*	-	-	-	-	-	-	-	-	-	*
	6	-	*	-	-	-	-	-	-	-	-	*	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	-	-	-	-	-	-	-	*	*
13 & 23	1 - 2	-	*	-	-	-	0.2	-	-	-	-	-	-
	3	-	-	-	-	-	*	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	-	-	0.2	-	-	-	-	-	-
33	1 - 2	-	*	-	*	*	*	-	*	-	-	*	*
	3	*	*	*	*	*	*	0.1	*	-	*	*	*
	4	*	*	*	*	*	*	0.2	*	-	*	*	*
	5	-	*	*	*	-	-	-	-	-	-	-	*
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	*	*	*	*	0.4	0.1	-	*	*	*
43	1 - 2	-	-	-	-	-	-	-	-	-	*	-	*
	3	*	*	*	*	-	-	-	-	*	0.1	*	*
	4	-	*	*	*	-	-	-	-	-	0.1	*	*
	5	-	*	*	*	-	-	0.1	*	-	*	*	*
	6	-	*	*	*	-	-	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	*	*	-	-	0.1	*	*	0.2	*	*
53	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	*	-	-	-	-	-	-	-	-	*	*
	4	-	-	-	-	-	-	-	-	-	-	*	*
	5	-	*	-	*	-	-	-	-	-	*	-	*
	6	-	-	-	-	-	-	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	*	-	-	-	-	-	*	*	*
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	*	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	*	*
	6	-	*	-	-	-	-	-	-	-	-	*	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	-	-	-	-	-	-	-	*	*
24 - 54 25 - 35 81 - 85	1 - 8	-	-	-	*	-	-	-	-	-	-	-	*
	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
	1 - 8	-	-	-	-	-	-	-	-	-	-	*	*
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	*	-	-	-	-	-	-	-	-	-	*
31		*	0.1	-	*	-	-	-	-	-	*	*	*
32		0.2	0.5	*	*	-	-	-	-	*	0.1	0.1	0.2
33		1.9	1.9	*	0.1	*	*	-	*	0.8	2.1	0.9	1.5
34		5.3	6.5	0.4	0.4	0.1	1.5	-	0.3	6.7	10.0	5.5	7.6
35		13.4	14.9	5.5	5.9	4.1	13.4	*	6.0	20.1	23.1	17.1	19.1
36		22.9	23.9	20.0	21.9	18.8	29.7	7.0	7.4	25.7	27.0	28.0	30.2
37		38.3	35.0	45.0	50.5	40.3	36.7	43.7	28.2	39.7	27.0	35.1	30.8
38		13.7	13.1	23.4	17.6	22.6	13.0	11.2	18.8	5.9	7.5	10.6	8.5
39		3.7	3.4	5.2	3.3	10.1	4.1	14.6	25.5	1.1	2.8	2.2	1.8
40 & Longer		0.6	0.7	0.6	0.3	4.1	1.5	23.5	13.7	0.1	0.4	0.6	0.3
Average Staple		36.48	36.38	37.03	36.90	37.28	36.64	38.06	37.91	36.19	36.02	36.34	36.15
Average Length		1.14	1.13	1.16	1.15	1.16	1.14	1.19	1.18	1.13	1.12	1.13	1.13

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE													
For The Week Ending Nov 23, 2023													
Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	15.4	8.5	4.5	3.3	4.9	9.5	7.1	5.3	4.3	3.7	88.9	89.8
	3	12.6	18.5	5.3	1.5	1.8	2.4	4.9	4.6	2.9	2.4	2.7	2.6
	4	3.6	5.4	0.2	*	0.1	0.1	0.1	0.2	0.1	0.1	0.1	*
	5	0.1	0.4	-	-	-	*	-	*	-	-	-	-
	6	-	*	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	31.7	32.8	10.0	4.9	6.8	11.9	12.2	10.0	7.3	6.2	91.8	92.4
31	1 - 2	1.3	0.5	3.6	7.8	24.6	21.3	9.4	9.3	11.7	10.8	6.3	4.9
	3	5.1	5.5	30.6	24.4	45.3	42.7	39.5	38.9	46.0	46.0	1.9	1.8
	4	9.6	10.3	11.9	6.9	7.0	7.8	11.0	12.3	14.5	15.1	-	0.2
	5	3.4	5.1	0.7	0.4	0.2	0.3	0.7	0.9	0.8	0.9	-	0.1
	6	0.2	0.9	-	*	-	*	*	*	*	*	-	-
	7	-	0.1	-	-	-	-	-	*	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	19.5	22.3	46.8	39.4	77.2	72.1	60.5	61.5	73.0	72.8	8.2	6.9
41	1 - 2	*	*	0.2	1.3	0.8	0.6	0.3	0.4	0.4	0.3	-	-
	3	0.7	0.2	11.5	16.0	8.5	8.0	7.1	8.2	6.8	6.8	-	-
	4	4.7	1.7	21.0	17.4	5.9	6.3	13.0	12.4	9.3	9.9	-	0.2
	5	6.8	2.9	3.7	4.4	0.7	1.0	5.4	4.5	2.6	2.7	-	0.2
	6	4.1	2.1	0.1	0.4	*	*	0.6	0.7	0.2	0.2	-	-
	7	0.5	0.5	-	*	-	*	*	*	*	*	-	-
	8	*	0.1	-	*	-	-	-	*	-	-	-	-
Total	----	16.9	7.4	36.6	39.4	16.0	15.9	26.5	26.3	19.4	19.9	-	0.3
51	1 - 2	-	-	-	*	-	*	-	*	*	*	-	-
	3	-	-	0.3	0.2	*	*	*	*	*	*	-	-
	4	-	-	1.4	0.5	*	*	*	*	*	*	-	-
	5	*	*	0.7	0.7	*	*	0.1	*	*	*	-	-
	6	0.1	*	0.2	0.1	-	*	*	*	-	*	-	-
	7	0.1	0.1	-	*	-	-	*	*	*	*	-	-
	8	0.1	0.3	-	-	-	-	-	*	-	-	-	-
Total	----	0.3	0.4	2.6	1.6	*	*	0.1	0.1	*	*	-	-
61	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	*	*	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	*	-	-	*	*	-	-	-	-
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	-	-	-	-	-
12 & 22	1 - 2	4.0	3.3	0.2	1.9	-	*	*	*	-	*	-	0.1
	3	5.6	11.5	0.2	0.8	-	-	*	*	-	*	-	-
	4	1.5	4.5	-	*	-	-	*	*	-	*	-	-
	5	0.1	0.2	-	-	-	-	-	*	-	-	-	-
	6	-	*	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	11.0	19.5	0.4	2.6	-	*	*	*	-	*	-	0.1
32	1 - 2	0.1	0.1	0.3	0.9	-	*	*	0.1	*	*	-	-
	3	1.3	1.2	0.9	2.7	*	*	0.1	0.6	0.1	0.4	-	-
	4	2.4	4.1	0.2	0.6	*	*	*	0.2	*	0.2	-	*
	5	0.8	2.7	-	*	-	*	*	*	*	*	-	-
	6	*	0.6	-	-	-	-	-	*	-	*	-	-
	7	-	0.1	-	*	-	-	-	*	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	----	4.6	8.6	1.3	4.3	*	*	0.2	1.0	0.1	0.6	-	*
42	1 - 2	-	-	0.1	0.4	-	*	*	*	-	*	-	-
	3	0.1	*	0.2	3.5	*	*	0.1	0.3	*	0.1	-	-
	4	1.2	0.5	0.7	2.3	*	*	0.1	0.5	0.1	0.2	-	-
	5	3.9	1.8	0.4	0.6	*	*	0.1	0.2	*	*	-	-
	6	4.5	2.3	0.1	0.1	-	-	*	*	-	*	-	-
	7	2.2	1.1	-	*	-	-	*	*	-	*	-	-
	8	0.2	0.1	-	-	-	-	-	*	-	-	-	-
Total	----	12.1	5.9	1.4	6.9	*	*	0.3	1.0	0.1	0.4	-	-

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Nov 23, 2023

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	-	*	-	-	-	-	-	-	-	-
	3	-	-	*	0.2	*	*	-	*	*	*	-	-
	4	-	-	0.2	0.3	-	-	*	*	*	*	-	-
	5	*	*	0.2	0.2	*	*	*	*	-	*	-	-
	6	0.3	0.1	*	0.1	*	*	-	*	-	*	-	-
	7	0.8	0.3	-	*	-	-	-	*	-	*	-	-
	8	0.4	0.2	-	-	-	-	-	*	-	-	-	-
Total	----	1.5	0.6	0.4	0.7	*	*	*	*	*	*	-	-
62	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	-	-	-
	4	-	-	-	*	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	-	-	-	-	-	-	-	-
13 & 23	1 - 2	0.6	0.2	-	*	-	-	-	-	*	*	-	-
	3	0.3	0.2	-	*	-	-	-	-	-	*	-	-
	4	0.1	0.2	-	-	-	-	-	*	-	*	-	-
	5	-	*	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	1.0	0.6	-	0.1	-	-	-	*	*	*	-	-
33	1 - 2	-	-	-	*	-	-	*	*	-	*	-	-
	3	0.1	0.1	-	*	-	-	0.1	*	*	*	-	*
	4	0.1	0.5	-	*	-	-	*	*	*	*	-	0.1
	5	0.1	0.5	-	-	-	-	*	*	-	-	-	-
	6	-	0.1	-	-	-	-	-	-	-	-	-	-
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.3	1.1	-	*	-	-	0.1	*	*	*	-	0.1
43	1 - 2	-	-	-	*	-	*	*	*	-	*	-	-
	3	*	*	*	*	*	*	*	*	*	*	-	-
	4	0.3	0.1	0.1	*	-	*	*	*	*	*	-	0.2
	5	0.7	0.3	0.1	*	-	*	*	*	-	*	-	-
	6	0.1	0.1	*	*	-	-	-	*	-	-	-	-
	7	*	0.1	-	-	-	-	-	*	-	-	-	-
	8	*	*	-	-	-	-	-	*	-	-	-	-
Total	----	1.1	0.6	0.3	0.1	*	*	*	*	*	*	-	0.2
53	1 - 2	-	-	-	-	-	*	-	-	-	-	-	-
	3	-	-	-	*	-	*	-	-	-	-	-	-
	4	-	-	*	*	-	-	-	*	-	*	-	-
	5	-	-	*	*	-	-	-	-	-	*	-	-
	6	-	*	-	*	-	-	-	-	-	*	-	-
	7	*	*	-	*	-	-	-	-	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	*	*	-	*	-	*	-	*	-	-
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	*	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	-	-	-	-	-	-	-	-
24 - 54 25 - 35 81 - 85	1 - 8	*	0.1	-	*	-	-	*	*	*	*	-	-
	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	0.1	-	-	-	-	-	-	*	*	-	-
31		0.7	0.5	*	*	-	-	-	*	*	*	-	-
32		2.1	1.9	0.4	0.1	-	*	*	0.1	0.3	0.2	-	-
33		6.4	4.3	2.3	1.2	*	*	0.3	0.6	1.9	2.4	-	-
34		14.4	11.0	1.5	5.6	*	0.1	2.3	4.4	9.5	10.8	0.1	*
35		21.0	20.1	0.3	15.0	3.9	2.7	9.9	13.1	24.5	23.9	2.5	5.1
36		21.8	23.5	11.3	27.3	16.8	16.3	20.1	25.5	33.5	32.2	11.5	14.6
37		20.6	25.4	49.9	31.6	43.2	48.9	39.6	37.0	26.4	25.6	25.7	24.5
38		8.2	9.7	25.2	13.0	26.7	25.4	17.9	14.1	3.6	4.1	22.9	24.7
39		4.6	3.6	8.3	5.4	8.4	5.5	7.7	4.4	0.3	0.7	12.7	15.4
40 & Longer		0.1	0.1	0.7	0.8	1.0	0.9	2.1	0.8	*	0.1	24.6	15.8
Average Staple		35.70	35.91	37.16	36.47	37.22	37.17	36.92	36.58	35.84	35.82	38.09	37.81
Average Length		1.11	1.12	1.16	1.14	1.16	1.16	1.15	1.14	1.12	1.12	1.19	1.18

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE											
For The Week Ending Nov 23, 2023											
Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	13.2	39.5	3.7	3.1	17.4	16.1	43.0	35.3	13.8	7.9
	3	5.0	6.3	4.6	2.9	7.8	5.1	11.8	15.6	10.2	5.9
	4	0.2	0.2	0.2	0.1	0.1	0.1	0.5	1.2	0.4	0.2
	5	-	*	*	*	*	*	*	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	18.4	46.0	8.6	6.2	25.4	21.3	55.3	52.1	24.4	14.0
31	1 - 2	12.6	7.7	5.0	5.4	19.5	28.2	7.6	4.3	20.2	20.5
	3	29.8	15.6	33.2	36.7	36.5	35.7	16.8	9.1	46.1	55.6
	4	8.8	3.5	18.7	18.5	7.2	5.9	5.5	2.9	6.8	6.3
	5	0.7	0.4	1.8	1.6	0.3	0.2	0.6	0.3	0.3	0.1
	6	*	*	*	*	-	*	*	*	-	-
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	51.9	27.2	58.8	62.3	63.5	70.0	30.5	16.6	73.5	82.6
41	1 - 2	1.1	0.6	0.3	0.2	0.7	0.6	0.1	0.3	0.2	0.2
	3	7.6	3.9	9.0	7.6	5.0	3.8	1.0	1.3	0.9	1.7
	4	5.4	2.0	17.3	16.5	4.0	3.3	1.6	1.0	0.7	1.0
	5	2.6	0.9	5.4	6.2	1.1	0.8	1.0	0.4	0.1	0.2
	6	0.6	0.2	0.5	0.6	0.1	0.1	0.4	0.1	-	*
	7	0.1	*	*	*	*	*	0.1	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	17.3	7.6	32.5	31.1	11.0	8.5	4.3	3.1	1.9	3.1
51	1 - 2	*	*	-	*	-	*	*	*	-	*
	3	0.1	*	*	*	*	*	*	0.2	*	*
	4	*	*	*	*	*	*	0.1	0.1	*	*
	5	*	*	*	*	*	*	0.1	*	-	*
	6	0.1	*	-	*	*	*	0.1	*	-	*
	7	*	*	-	*	-	-	*	*	-	-
	8	-	*	-	-	-	-	*	*	-	-
Total	----	0.2	0.1	*	*	*	*	0.4	0.4	*	*
61	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	-	-	-	*	*	-	-
	5	-	-	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	*	*	-	-
71	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	*	-	-
12 & 22	1 - 2	1.2	6.5	-	*	*	*	2.2	12.3	*	*
	3	0.8	3.1	*	*	*	*	1.5	6.5	*	*
	4	0.1	0.3	-	*	-	*	0.1	0.8	-	*
	5	*	*	-	-	-	-	*	0.1	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	2.1	9.9	*	*	*	*	3.8	19.7	*	*
32	1 - 2	1.5	1.0	-	*	*	*	0.5	0.7	-	*
	3	3.3	2.4	*	0.1	*	*	1.7	2.1	0.1	0.1
	4	2.1	1.5	*	0.1	*	*	0.8	1.1	*	0.1
	5	0.3	0.3	*	*	*	*	0.2	0.2	-	-
	6	*	*	-	*	-	-	*	*	-	-
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	7.1	5.2	*	0.2	0.1	0.1	3.2	4.1	0.1	0.2
42	1 - 2	*	*	-	-	*	*	*	0.1	*	*
	3	0.3	0.4	*	*	*	*	0.2	0.5	*	*
	4	0.7	0.3	*	0.1	*	*	0.4	0.5	-	*
	5	0.8	0.5	*	0.1	*	*	0.4	0.2	-	-
	6	0.2	0.1	*	*	-	-	0.3	0.1	-	-
	7	0.1	*	-	-	-	-	0.1	*	-	-
	8	*	*	-	-	-	-	0.1	*	-	-
Total	----	2.0	1.5	0.1	0.2	*	*	1.5	1.5	*	*

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE											
For The Week Ending Nov 23, 2023											
Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	*	*	-	-	-	-	-	*	-	-
	3	0.1	*	-	*	-	-	*	0.1	*	*
	4	-	-	*	*	-	*	0.1	0.1	-	-
	5	*	*	*	*	-	*	*	*	-	-
	6	*	*	-	*	*	*	*	*	-	-
	7	*	*	-	-	-	-	*	*	-	-
	8	*	*	-	-	-	-	0.1	*	-	-
Total	----	0.2	0.1	*	*	*	*	0.3	0.2	*	*
62	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	-	*	*	-	-
	4	-	-	-	*	-	-	-	*	-	-
	5	-	-	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	-	-	*	*	-	-
13 & 23	1 - 2	*	0.8	-	-	-	-	*	0.7	-	*
	3	0.1	0.7	-	-	-	-	0.1	0.6	*	*
	4	*	0.1	-	-	-	-	*	0.2	-	-
	5	*	*	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	0.2	1.6	-	-	-	-	0.1	1.4	*	*
33	1 - 2	*	0.1	-	-	*	*	*	*	-	-
	3	0.3	0.3	-	*	*	*	0.1	0.2	*	*
	4	0.2	0.3	-	*	*	*	0.1	0.2	-	*
	5	*	0.1	-	-	-	-	*	0.1	-	*
	6	-	*	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	0.5	0.8	-	*	*	*	0.2	0.5	*	0.1
43	1 - 2	-	*	-	-	-	-	*	*	-	-
	3	*	*	-	-	*	*	*	*	-	-
	4	*	*	-	*	*	*	*	*	-	-
	5	*	0.1	-	-	-	-	0.1	0.1	-	*
	6	*	*	-	*	-	-	0.1	*	-	*
	7	*	*	-	*	-	-	0.1	*	-	-
	8	*	*	-	-	-	-	*	*	-	-
Total	----	0.1	0.2	-	*	*	*	0.3	0.2	-	*
53	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	-	*	*	-	-
	4	-	-	-	-	-	-	*	*	-	-
	5	-	*	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	*	-	-	-	-	*	*	-	-
	8	-	*	-	-	-	-	*	*	-	-
Total	----	-	*	-	-	-	-	0.1	*	-	-
63	1 - 2	-	-	-	-	-	-	*	*	-	-
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	-	-	-	*	*	-	-
	5	-	-	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	-	-	-	-	-	-	*	*	-	-
24 - 54	1 - 8	0.1	0.1	-	*	-	-	0.1	*	-	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	*	-	-	-	-	*	*	-	-
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	*	*	-	-
30		*	*	-	-	-	-	0.1	0.1	-	-
31		0.2	0.4	-	-	-	-	0.4	0.3	*	*
32		3.2	2.0	*	*	-	*	1.5	1.7	0.1	*
33		5.3	4.3	0.4	0.4	*	*	4.4	5.8	0.8	1.1
34		8.4	7.0	2.6	3.2	0.1	0.3	11.3	15.6	5.8	5.6
35		10.9	11.4	12.9	13.0	1.4	2.9	18.3	23.8	21.0	21.9
36		15.7	20.1	28.5	27.0	14.6	17.5	23.2	22.7	41.7	42.2
37		31.0	34.2	37.7	39.9	57.8	57.8	24.6	18.9	25.0	25.3
38		17.8	14.3	11.5	12.4	21.4	18.2	9.8	7.2	4.6	3.4
39		5.9	5.0	5.6	3.6	4.3	3.2	4.6	3.0	0.8	0.4
40 & Longer		1.6	1.4	0.7	0.5	0.4	0.2	1.7	0.8	0.2	0.1
Average Staple		36.34	36.35	36.61	36.57	37.13	37.01	36.02	35.64	36.02	35.97
Average Length		1.13	1.13	1.14	1.14	1.16	1.16	1.12	1.11	1.12	1.12

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Nov 23, 2023

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	0.1	0.2	*	*	-	*	-	*	0.2	0.2	0.3	0.3
Bark - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	0.1	0.1	*	*	-	-	*	0.4	0.1	0.1	0.2	0.2
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	*	*	-	*	-	-	-	*	-	*	*	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	*	*	*	*	0.6	0.2	-	-	*	*	0.1	0.1
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	*	*	-	-	-	-	-	-	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	0.1	*	-	-	-	*	-	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	0.1	-	*	-	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	-	-	*	-	-	-	-	-	*	*	*
23	-	*	-	*	-	*	-	-	-	-	-	*
24	*	*	*	*	*	0.2	-	-	-	*	*	*
25	0.1	0.1	*	*	-	0.8	-	-	-	*	*	0.1
26	0.2	0.3	*	*	0.1	3.6	-	-	*	0.3	0.1	0.3
27	1.0	1.5	0.4	0.5	0.5	6.5	-	*	0.4	1.3	0.7	1.8
28	3.5	5.1	3.4	4.3	2.8	12.9	-	*	0.6	3.9	3.8	7.2
29	11.5	15.7	17.8	19.1	9.7	18.4	*	0.6	2.9	8.1	12.4	17.6
30	27.3	29.1	34.0	34.5	21.0	16.2	0.8	3.9	8.7	15.0	24.5	27.2
31	27.0	25.0	27.5	26.6	20.3	13.7	4.7	6.4	17.6	19.5	27.2	24.3
32	18.5	14.6	12.9	11.1	19.0	12.3	7.7	6.6	29.6	17.7	18.2	13.6
33	7.3	6.1	2.9	2.9	12.0	8.5	11.5	11.7	19.1	13.4	8.2	5.3
34	2.4	1.8	0.8	0.7	7.9	4.2	27.4	17.3	11.0	9.4	3.4	1.8
35	0.8	0.5	0.2	0.2	5.2	2.0	16.0	16.0	4.3	6.2	1.1	0.6
36	0.2	0.1	0.1	*	1.4	0.6	11.4	11.6	4.3	4.0	0.3	0.2
37	0.1	*	*	*	0.1	0.1	11.1	13.2	1.2	1.1	0.1	*
38	*	*	-	-	*	*	8.0	9.9	0.2	0.1	*	*
39	-	-	-	-	-	*	1.0	2.3	*	*	-	*
40 & Above	-	-	-	-	*	*	0.5	0.6	-	-	-	-
Average	31.24	30.97	30.86	30.77	31.89	30.57	35.14	35.16	32.74	32.19	31.33	30.85
Mike												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	-
2.5	-	-	-	*	-	-	-	-	-	-	-	*
2.6	-	-	*	*	*	*	-	-	-	-	-	*
2.7	-	*	*	*	0.1	*	-	-	-	-	-	*
2.8	-	-	*	*	0.1	*	-	-	-	-	*	*
2.9	-	*	*	*	0.1	*	-	-	-	-	*	*
3.0	*	*	*	*	0.3	0.1	-	-	-	-	*	*
3.1	0.1	*	*	*	0.6	0.3	-	-	-	-	*	*
3.2	0.4	0.1	*	*	0.5	0.3	-	*	-	*	*	*
3.3	0.2	0.1	*	*	0.5	0.4	*	*	-	-	*	*
3.4	0.4	0.2	*	*	0.6	0.5	0.7	0.2	-	*	0.1	*
3.5	0.6	0.3	0.1	*	1.2	0.8	0.1	0.2	-	0.1	0.2	0.1
3.6	1.0	0.5	0.1	0.1	1.3	1.0	1.2	0.5	*	0.1	0.3	0.3
3.7	1.9	1.0	0.2	0.1	2.3	1.4	1.2	1.7	-	0.2	0.7	0.6
3.8	3.2	1.9	0.2	0.2	3.3	2.4	2.5	3.3	0.1	0.4	1.5	1.3
3.9	6.1	3.4	0.4	0.3	1.9	2.7	5.3	4.2	0.2	0.6	2.7	2.5
4.0	8.5	5.1	1.0	0.7	3.1	4.1	8.1	6.0	0.9	1.2	4.5	4.2
4.1	8.8	7.1	2.2	1.5	4.7	5.7	5.8	5.0	1.8	2.3	7.2	6.5
4.2	8.6	8.3	3.5	2.8	9.1	7.8	6.2	8.2	3.0	3.7	10.3	9.2
4.3	9.9	10.5	4.5	4.8	8.0	9.3	8.1	11.7	4.1	4.9	11.8	11.4
4.4	10.1	10.9	7.9	8.1	10.0	10.6	9.0	11.9	6.1	6.8	12.7	13.0
4.5	10.5	10.7	10.5	11.0	12.2	11.4	11.4	11.8	7.7	8.6	12.5	13.0
4.6	7.2	9.9	13.1	13.1	14.0	11.7	6.4	7.8	9.3	11.0	11.6	12.1
4.7	5.9	8.8	12.9	13.7	10.2	8.8	8.8	6.6	10.7	14.2	9.2	9.8
4.8	5.5	7.4	13.1	12.9	7.1	6.0	7.6	5.7	13.2	14.4	6.5	7.4
4.9	4.2	5.3	10.5	10.6	5.1	5.3	8.4	6.7	15.6	12.2	4.6	4.9
5.0	3.4	3.7	8.2	7.9	2.8	3.7	4.6	6.1	16.1	9.4	2.1	2.2
5.1	1.7	2.4	6.0	5.6	0.4	1.6	3.3	1.9	4.6	4.7	1.3	1.0
5.2	0.8	1.1	3.3	3.5	*	1.9	1.3	0.5	1.5	2.6	0.3	0.3
5.3	0.4	0.7	1.2	1.7	0.3	1.5	-	0.1	2.3	1.3	0.1	0.1
5.4	0.1	0.3	0.7	0.9	0.1	0.6	-	-	2.4	1.0	*	*
5.5 & Above	0.1	0.2	0.3	0.6	*	0.2	-	-	0.5	0.5	*	*
Average	4.35	4.46	4.69	4.71	4.40	4.45	4.45	4.43	4.76	4.70	4.43	4.45

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Nov 23, 2023

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	8.4	13.1	-	0.1	*	*	*	*	1.1	0.7	-	0.2
Bark - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	0.6	2.4	-	*	0.2	0.1	*	*	0.3	0.3	-	-
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	-	-	*	-	*	-	-	-	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	*	-	*	-	*	*	*	*	*	-	1.6
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	*	-	*	*	*	*	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	-	-	*	*	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	-	*	*	*	*	*	*	*	-	-
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	-	-	-	-	-	-	*	-	-	-	-
23	*	*	-	-	-	*	-	*	-	-	-	-
24	*	*	-	*	*	*	*	*	*	*	-	-
25	0.1	0.1	-	*	*	*	*	*	*	*	0.1	*
26	1.4	0.7	-	0.6	0.1	0.1	*	0.2	0.1	0.1	0.1	*
27	2.6	1.7	*	2.1	0.9	0.8	0.4	1.1	0.7	0.7	-	1.2
28	4.6	3.5	1.2	4.7	8.0	6.8	2.6	4.0	4.3	4.0	2.7	4.5
29	10.5	6.6	4.8	10.6	28.6	27.1	8.7	13.0	17.5	13.8	15.7	23.3
30	13.6	11.8	8.3	22.7	38.2	40.0	25.3	25.4	27.6	25.5	21.4	24.2
31	19.9	18.7	28.5	29.2	18.2	19.4	30.5	29.1	25.3	27.6	13.5	9.5
32	22.1	23.2	31.8	19.3	4.4	4.7	21.2	17.1	15.0	17.3	27.5	19.1
33	14.3	16.9	19.3	7.6	1.3	0.9	7.8	7.0	7.2	7.8	17.1	13.7
34	7.3	11.4	5.0	1.9	0.2	0.2	2.7	2.4	1.8	2.5	2.0	3.4
35	3.3	4.8	0.7	0.8	0.1	0.1	0.5	0.6	0.5	0.6	-	0.6
36	0.2	0.4	0.3	0.3	*	*	0.2	0.1	0.1	0.1	-	*
37	0.1	0.1	0.1	*	*	*	*	*	*	*	-	*
38	-	-	-	*	-	-	-	-	-	-	-	0.5
39	-	*	-	-	-	-	-	-	-	-	-	-
40 & Above	-	-	-	-	-	-	-	-	-	-	-	-
Average	31.66	32.12	32.13	31.20	30.29	30.34	31.41	31.17	31.04	31.20	31.48	31.19
Mike												
2.4 & Below	*	*	-	-	-	-	-	-	-	-	-	-
2.5	*	*	-	-	-	-	-	-	-	*	-	-
2.6	0.1	*	-	-	-	-	*	*	-	*	-	-
2.7	0.1	0.5	-	-	-	-	-	*	*	*	-	-
2.8	0.4	1.4	-	-	-	-	-	*	*	*	-	-
2.9	2.2	2.3	-	-	-	-	*	*	*	*	-	-
3.0	1.8	3.5	-	*	-	-	*	*	*	*	-	-
3.1	2.5	5.3	-	*	*	*	-	*	*	*	-	-
3.2	2.6	6.4	-	*	*	*	*	*	*	*	-	-
3.3	2.9	5.4	*	*	*	*	*	*	*	*	-	0.1
3.4	6.5	7.6	*	*	*	*	*	0.1	*	*	0.9	1.4
3.5	7.3	8.3	*	*	*	*	*	0.1	0.1	0.1	1.5	0.8
3.6	7.4	7.2	-	*	0.1	0.1	0.1	0.1	0.2	0.1	0.1	1.0
3.7	9.8	8.7	*	0.1	0.1	0.2	0.2	0.1	0.3	0.2	0.1	2.9
3.8	11.0	9.2	-	0.2	0.4	0.4	0.1	0.2	0.6	0.4	1.7	4.6
3.9	11.4	8.6	*	0.5	1.1	0.9	0.3	0.4	0.7	0.7	0.1	3.3
4.0	9.1	7.4	0.1	1.0	2.2	1.8	0.9	0.6	1.8	1.3	3.3	8.0
4.1	5.9	5.8	0.4	2.0	4.4	3.0	1.5	1.0	2.0	1.9	4.1	8.0
4.2	5.9	4.7	0.3	3.4	6.5	4.8	2.5	1.7	2.8	2.7	7.1	8.1
4.3	4.8	3.6	1.6	5.0	8.3	7.9	2.8	2.7	3.5	3.5	12.9	10.7
4.4	2.2	2.0	2.6	6.4	10.3	11.4	3.7	3.9	4.5	4.6	4.6	4.1
4.5	3.5	1.3	4.2	8.1	11.7	13.7	6.4	5.9	6.2	6.7	4.9	3.7
4.6	1.1	0.4	8.9	10.9	14.8	15.2	8.5	8.2	8.4	8.4	16.0	8.5
4.7	0.6	0.2	12.2	12.1	15.7	13.8	8.9	10.1	9.8	10.3	24.6	17.3
4.8	0.6	0.2	8.7	12.6	11.2	11.2	10.7	12.2	11.5	11.2	15.1	12.2
4.9	0.3	0.1	11.1	9.9	6.3	7.3	13.4	13.8	11.5	11.5	2.9	3.8
5.0	*	*	15.2	8.9	4.2	4.6	12.4	12.4	11.4	11.7	0.1	1.2
5.1	*	*	10.0	6.4	1.6	2.2	10.0	9.8	8.8	9.5	-	0.4
5.2	-	-	7.5	4.8	0.8	1.0	7.8	7.3	7.2	7.2	-	-
5.3	-	-	7.7	3.3	0.2	0.4	5.2	4.6	4.6	4.3	-	-
5.4	-	-	5.7	2.4	*	0.1	2.9	2.7	2.3	2.1	-	-
5.5 & Above	-	-	3.7	2.1	*	*	1.6	2.1	1.6	1.5	-	-
Average	3.80	3.66	4.93	4.75	4.56	4.58	4.84	4.85	4.79	4.80	4.50	4.37

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Nov 23, 2023

Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter										
Bark - Level 1	4.3	4.0	4.9	2.5	*	*	6.6	3.3	*	0.1
Bark - Level 2	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	0.4	0.4	0.6	0.5	*	*	0.1	0.3	*	*
Grass - Level 2	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	-	-	-	-	-	*	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	-	-	*	-	-	*	0.4	-	-
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	-	-	-	*	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	*	-	-	*	*	-	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	*	*	0.1	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	0.1	0.1	-	-	-	-	*	0.3	-	-
23	0.2	0.3	-	-	-	*	*	0.4	-	-
24	1.0	0.8	-	*	*	*	0.1	0.9	-	*
25	2.0	1.5	*	*	*	*	0.4	1.8	*	*
26	2.2	2.1	0.1	*	*	0.1	1.5	3.6	0.1	0.1
27	3.5	3.5	0.3	0.2	0.7	1.5	3.5	6.5	1.6	1.4
28	7.1	5.8	1.6	1.6	4.3	10.3	7.6	10.2	13.5	10.9
29	10.8	9.0	10.7	10.1	23.5	31.1	12.6	13.9	31.1	31.6
30	11.8	11.7	35.1	30.6	39.7	37.0	16.7	15.9	30.1	31.5
31	9.1	11.1	29.6	32.9	26.3	16.0	18.2	15.0	18.8	17.8
32	10.2	11.3	13.8	15.8	4.9	3.4	16.5	12.6	4.1	5.1
33	15.9	16.6	7.3	7.1	0.4	0.6	11.1	9.4	0.6	1.1
34	18.1	18.1	1.4	1.4	0.1	0.1	6.4	5.5	0.1	0.3
35	7.1	7.0	0.2	0.3	*	*	3.6	2.7	*	0.1
36	0.8	0.8	*	0.1	-	*	1.4	1.0	*	*
37	0.2	0.2	-	*	-	-	0.3	0.2	-	-
38	*	*	-	-	-	-	*	*	-	-
39	-	-	-	-	-	-	*	*	-	-
40 & Above	-	-	-	-	-	-	*	*	-	-
Average	31.74	31.86	31.16	31.24	30.48	30.13	31.36	30.69	30.11	30.20
Mike										
2.4 & Below	-	-	-	-	-	-	*	*	-	-
2.5	-	*	-	-	-	-	*	*	-	-
2.6	*	*	-	-	-	-	0.1	0.1	-	-
2.7	*	*	-	-	-	-	0.1	0.1	-	-
2.8	*	*	-	*	-	-	0.1	0.1	-	-
2.9	0.2	0.1	-	*	-	-	0.1	0.2	-	-
3.0	0.2	0.3	-	*	*	*	0.2	0.2	*	*
3.1	0.2	0.3	*	*	*	*	0.3	0.3	-	-
3.2	0.3	0.5	0.1	*	0.1	*	0.5	0.5	*	*
3.3	0.6	0.8	0.1	0.1	0.1	0.1	0.8	0.8	*	*
3.4	1.5	1.4	0.1	0.1	0.3	0.2	0.9	1.0	0.1	0.1
3.5	2.2	1.7	0.1	0.2	0.9	0.4	1.2	1.2	0.3	0.2
3.6	1.7	1.6	0.3	0.3	1.5	0.7	1.6	1.6	0.5	0.3
3.7	2.2	2.2	0.7	0.5	2.4	1.3	2.0	2.1	1.3	0.8
3.8	2.9	3.0	1.6	1.1	3.2	2.0	2.5	2.7	1.6	1.1
3.9	4.7	4.6	1.9	1.8	3.7	2.9	3.0	3.4	1.9	2.0
4.0	5.8	7.0	2.9	3.5	6.3	4.7	3.3	4.4	3.1	3.1
4.1	9.2	8.1	6.1	5.2	9.7	7.2	4.2	5.7	4.7	5.1
4.2	10.2	9.4	7.7	7.7	11.2	10.3	5.3	7.2	5.8	6.7
4.3	11.0	11.2	9.8	10.2	12.5	14.6	6.1	8.6	6.9	8.1
4.4	10.3	9.8	11.8	11.3	13.2	16.0	7.5	9.5	7.7	9.7
4.5	8.9	10.5	11.6	11.6	11.6	13.9	8.9	9.9	11.2	10.9
4.6	6.7	8.2	11.9	12.1	9.7	10.4	9.5	9.7	11.9	12.3
4.7	6.2	6.3	9.3	11.5	6.9	7.1	9.7	8.8	11.2	10.9
4.8	4.6	5.4	7.9	9.1	4.1	4.4	9.2	7.3	10.4	10.3
4.9	4.7	3.5	7.3	6.5	0.9	2.0	7.9	5.4	7.1	7.3
5.0	3.6	2.4	4.1	4.0	0.7	1.3	5.4	3.6	6.5	5.3
5.1	1.2	1.0	2.9	2.1	0.5	0.5	3.5	2.4	4.7	2.9
5.2	0.5	0.5	1.5	0.9	0.2	0.1	2.4	1.4	1.6	1.3
5.3	0.3	0.3	0.4	0.2	0.1	*	1.6	0.8	1.0	0.8
5.4	*	*	0.1	*	*	*	0.9	0.4	0.1	0.4
5.5 & Above	-	*	*	*	*	*	1.2	0.5	0.3	0.3
Average	4.31	4.31	4.51	4.51	4.31	4.37	4.50	4.41	4.56	4.55

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Nov 23, 2023

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	-	-	*	*	*	*	-	-	-	-	-	*
2.7 - 2.9	-	*	*	*	0.2	0.1	-	-	-	-	*	*
3.0 - 3.2	0.5	0.1	0.1	*	1.4	0.7	-	*	-	*	*	*
3.3 - 3.4	0.6	0.2	0.1	*	1.1	0.9	0.7	0.2	-	*	0.1	0.1
3.5 - 3.6	1.6	0.8	0.2	0.1	2.5	1.8	1.3	0.7	*	0.2	0.4	0.4
3.7 - 4.2	37.2	26.8	7.5	5.6	24.4	24.1	29.1	28.3	6.0	8.3	26.8	24.4
4.3 - 4.9	53.4	63.5	72.5	74.1	66.5	63.1	59.7	62.2	66.6	72.0	68.9	71.5
5.0 - 5.2	5.9	7.3	17.4	17.0	3.3	7.1	9.2	8.5	22.3	16.6	3.6	3.5
5.3 & Above	0.7	1.2	2.2	3.1	0.4	2.3	-	0.1	5.1	2.8	0.1	0.1
Average	4.35	4.46	4.69	4.71	4.40	4.45	4.45	4.43	4.76	4.70	4.43	4.45
Leaf												
1 - 2	20.8	19.2	18.0	21.4	91.6	85.7	52.8	46.6	14.4	10.9	12.9	14.3
3	52.5	53.4	46.3	49.1	7.8	12.2	36.1	31.2	57.0	52.2	54.7	54.2
4	22.4	22.9	28.4	24.1	0.5	1.8	7.9	17.2	24.3	30.3	27.2	26.2
5	4.0	4.0	6.6	4.9	0.1	0.2	2.7	4.4	4.0	5.8	4.8	4.7
6	0.4	0.5	0.6	0.4	*	*	0.4	0.6	0.3	0.7	0.5	0.5
7	*	*	0.1	*	-	-	-	-	*	0.1	*	*
8	-	*	-	*	-	-	-	-	-	*	*	*
Average	3.10	3.12	3.25	3.13	1.68	1.82	2.49	2.68	3.19	3.33	3.25	3.23
HVI Trash 1/												
00	-	-	-	*	0.2	0.1	-	*	-	-	-	-
01	4.2	3.5	2.6	3.9	59.8	54.0	23.2	21.9	0.9	1.1	1.5	1.8
02	22.4	20.8	18.7	21.4	32.8	35.0	34.9	29.0	18.6	14.0	17.2	17.8
03	29.5	29.2	24.0	26.3	5.5	7.6	20.6	17.7	32.5	27.2	29.8	29.5
04	21.7	22.5	20.9	20.4	1.2	2.3	10.5	11.6	23.6	25.5	24.2	23.7
05	11.9	12.7	15.0	13.2	0.3	0.7	4.9	8.8	13.9	16.5	14.5	14.2
06	5.7	6.1	9.1	7.5	0.1	0.2	2.6	5.5	6.3	8.7	7.3	7.2
07	2.6	2.8	4.9	3.9	*	0.1	1.7	3.0	2.7	4.0	3.2	3.3
08	1.1	1.3	2.5	1.8	*	*	0.6	1.3	1.0	1.7	1.4	1.5
09	0.6	0.6	1.2	0.8	*	*	0.5	0.7	0.4	0.8	0.6	0.6
10	0.2	0.3	0.6	0.4	*	*	0.2	0.4	0.1	0.3	0.2	0.3
11	0.1	0.1	0.3	0.2	-	-	0.1	0.1	*	0.1	0.1	0.1
12	*	*	0.1	0.1	-	-	0.1	0.1	*	*	*	*
13	*	*	0.1	*	-	-	-	*	*	*	*	*
14	*	*	*	*	-	-	-	*	-	*	*	*
15	-	*	*	*	-	-	-	-	-	*	*	*
16	*	*	*	*	-	-	-	-	-	*	*	*
17	-	*	*	*	-	-	-	-	-	-	-	*
18 & Above	*	*	*	*	-	-	-	-	-	*	*	*
Average	0.35	0.36	0.40	0.37	0.15	0.16	0.26	0.30	0.37	0.40	0.38	0.38
UNIFORMITY 2/												
74 & Below	-	*	-	-	-	-	-	-	-	-	-	*
75	-	*	*	*	-	*	-	-	-	-	-	*
76	*	*	*	*	*	*	-	-	-	*	*	*
77	*	0.1	*	*	*	0.5	-	-	-	0.1	0.1	0.2
78	0.4	1.0	0.1	0.1	0.6	4.6	-	-	0.1	0.9	0.8	1.7
79	3.4	5.5	0.8	1.1	5.0	17.6	*	0.4	1.4	4.9	5.3	10.1
80	16.2	18.6	9.6	8.7	24.1	33.2	2.0	6.0	8.8	19.4	22.6	29.2
81	33.8	31.4	23.8	20.6	40.5	27.9	20.8	20.8	27.6	35.4	39.1	35.5
82	33.9	29.8	31.3	33.5	22.0	12.3	21.4	29.9	49.2	30.7	24.1	18.2
83	11.4	11.9	26.7	28.6	6.8	3.7	26.7	24.0	11.8	7.9	7.1	4.5
84	0.9	1.5	6.6	6.5	0.8	0.3	25.3	16.8	1.0	0.6	0.9	0.6
85 & Above	*	0.1	1.1	0.8	*	*	3.7	2.2	0.1	*	*	*
Average	81.81	81.70	82.42	82.47	81.47	80.82	83.10	82.75	82.09	81.61	81.50	81.19
Tenderable 3/	90.5	88.4	79.5	79.2	92.9	87.6	85.0	88.7	70.6	73.6	94.1	93.3
SAMPLES CLASSED	63,256	365,317	146,726	1,035,144	14,492	51,558	4,075	23,352	8,912	53,620	181,622	792,701

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Nov 23, 2023

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	*	*	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	0.1	0.1	-	-	-	-	*	*	-	*	-	-
2.7 - 2.9	2.6	4.1	-	-	-	-	*	*	*	*	-	-
3.0 - 3.2	6.9	15.3	-	*	*	*	*	0.1	0.1	*	-	-
3.3 - 3.4	9.4	12.9	*	*	*	*	*	0.1	0.1	0.1	0.9	1.5
3.5 - 3.6	14.7	15.4	*	0.1	0.1	0.1	0.1	0.2	0.3	0.2	1.6	1.8
3.7 - 4.2	53.1	44.3	0.9	7.1	14.7	11.1	5.5	4.0	8.3	7.2	16.3	34.9
4.3 - 4.9	13.1	7.8	49.2	65.0	78.3	80.4	54.4	56.9	55.4	56.3	81.1	60.2
5.0 - 5.2	*	*	32.7	20.1	6.6	7.8	30.2	29.4	27.4	28.3	0.1	1.6
5.3 & Above	-	-	17.2	7.8	0.3	0.6	9.7	9.4	8.5	7.9	-	-
Average	3.80	3.66	4.93	4.75	4.56	4.58	4.84	4.85	4.79	4.80	4.50	4.37
Leaf												
1 - 2	21.4	12.5	8.9	15.6	30.3	31.4	16.8	15.1	16.4	14.7	95.3	94.8
3	25.7	37.2	49.1	49.3	55.7	53.1	51.9	52.7	55.8	55.7	4.7	4.4
4	23.4	27.3	35.8	28.1	13.0	14.2	24.3	25.7	24.1	25.5	0.1	0.6
5	15.8	13.9	5.8	6.3	1.0	1.3	6.2	5.7	3.5	3.7	-	0.2
6	9.2	6.2	0.4	0.6	*	*	0.6	0.8	0.2	0.3	-	-
7	3.7	2.2	-	0.1	-	*	*	0.1	*	*	-	-
8	0.8	0.7	-	*	-	-	-	*	-	-	-	-
Average	3.76	3.72	3.40	3.27	2.83	2.83	3.21	3.24	3.15	3.19	1.54	1.57
HVI Trash 1/												
00	-	-	-	-	*	*	-	*	-	*	0.4	0.2
01	8.9	3.4	0.3	2.7	4.8	6.0	2.2	1.8	1.8	1.5	64.6	62.1
02	15.8	13.1	10.6	16.6	28.5	28.1	19.3	18.3	17.2	15.4	29.2	30.6
03	14.4	19.9	24.0	25.7	31.6	30.0	27.8	28.2	28.2	27.2	5.0	5.3
04	11.2	16.9	23.0	22.5	19.8	19.4	20.9	22.5	24.9	24.9	0.7	0.9
05	10.8	13.4	19.3	15.3	9.3	9.7	13.4	13.8	14.7	15.9	0.1	0.2
06	8.1	9.3	12.6	8.8	3.8	4.1	7.8	7.6	7.4	8.3	-	0.3
07	7.0	6.8	5.5	4.5	1.4	1.6	4.4	4.0	3.4	3.9	-	0.2
08	5.7	5.0	2.5	2.1	0.5	0.6	2.3	2.0	1.4	1.6	-	0.2
09	4.6	3.7	1.0	1.0	0.2	0.2	1.0	0.9	0.6	0.7	-	0.1
10	3.7	2.6	0.7	0.4	0.1	0.1	0.5	0.5	0.2	0.3	-	*
11	3.2	1.9	0.3	0.2	*	*	0.2	0.2	0.1	0.1	-	-
12	2.6	1.4	0.2	0.1	*	*	0.1	0.1	*	0.1	-	-
13	1.7	0.9	-	*	*	*	*	*	*	*	-	-
14	1.0	0.5	-	*	*	*	*	*	*	*	-	-
15	0.6	0.3	-	-	-	*	*	*	*	*	-	-
16	0.3	0.2	-	-	-	-	*	*	-	*	-	-
17	0.2	0.1	-	-	-	-	-	*	-	*	-	-
18 & Above	0.3	0.4	-	-	-	-	*	*	*	*	-	-
Average	0.53	0.50	0.44	0.40	0.32	0.32	0.39	0.39	0.38	0.40	0.14	0.15
UNIFORMITY 2/												
74 & Below	-	-	-	-	-	-	-	-	-	-	-	-
75	0.1	0.1	-	-	-	*	-	-	-	*	-	-
76	0.4	0.3	-	-	*	*	-	*	-	*	-	-
77	5.8	4.0	*	*	*	*	*	*	*	*	-	0.1
78	25.9	19.0	*	0.5	0.1	0.1	0.1	0.3	0.1	0.2	0.1	0.1
79	23.3	33.7	0.1	3.2	0.7	1.1	0.7	1.7	1.5	1.9	1.7	3.1
80	22.3	26.2	3.4	11.1	9.4	9.1	5.4	8.0	11.4	11.7	12.6	19.6
81	13.3	12.0	10.7	31.4	30.1	24.2	21.0	22.0	32.5	30.6	50.5	45.8
82	8.7	4.5	33.8	35.2	32.7	34.9	38.7	37.6	37.6	37.0	34.1	28.9
83	0.2	0.2	46.8	17.0	21.8	25.6	27.2	24.1	15.0	16.5	1.1	2.4
84	*	*	4.8	1.6	4.8	4.6	6.4	5.8	1.7	1.9	-	-
85 & Above	-	-	0.2	0.1	0.4	0.4	0.5	0.4	0.1	0.1	-	-
Average	79.83	79.81	82.82	82.00	82.26	82.34	82.52	82.37	82.03	82.05	81.68	81.52
Tenderable 3/	57.6	48.7	47.4	64.4	92.9	91.4	59.4	59.5	62.6	62.5	98.9	95.2
SAMPLES CLASSED	14,764	49,787	6,936	201,142	66,273	464,905	68,159	733,160	84,688	406,900	1,710	3,280

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE										
For The Week Ending Nov 23, 2023										
Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE										
2.4 & Below	-	-	-	-	-	-	*	*	-	-
2.5 - 2.6	*	*	-	-	-	-	0.1	0.1	-	-
2.7 - 2.9	0.3	0.1	-	*	-	-	0.3	0.4	-	-
3.0 - 3.2	0.7	1.0	0.1	*	0.1	0.1	1.1	1.1	*	*
3.3 - 3.4	2.1	2.2	0.2	0.2	0.4	0.2	1.6	1.7	0.1	0.1
3.5 - 3.6	3.9	3.3	0.5	0.5	2.4	1.1	2.8	2.8	0.8	0.5
3.7 - 4.2	35.0	34.3	20.9	19.8	36.5	28.3	20.1	25.5	18.3	19.0
4.3 - 4.9	52.4	54.9	69.6	72.2	59.0	68.3	58.8	59.2	66.5	69.5
5.0 - 5.2	5.3	3.8	8.4	7.0	1.4	1.9	11.4	7.4	12.8	9.5
5.3 & Above	0.3	0.3	0.4	0.3	0.1	*	3.7	1.8	1.4	1.5
Average	4.31	4.31	4.51	4.51	4.31	4.37	4.50	4.41	4.56	4.55
Leaf										
1 - 2	29.7	56.2	9.1	8.7	37.6	44.9	53.3	53.7	34.2	28.6
3	47.2	32.9	46.8	47.4	49.4	44.7	33.2	36.2	57.5	63.4
4	17.5	8.2	36.3	35.3	11.4	9.3	9.4	8.2	7.9	7.6
5	4.4	2.1	7.3	7.9	1.4	1.0	2.6	1.4	0.4	0.3
6	0.9	0.5	0.5	0.7	0.1	0.1	1.0	0.4	-	*
7	0.2	0.1	*	*	*	*	0.4	0.1	-	-
8	*	*	-	-	-	-	0.2	*	-	-
Average	2.98	2.43	3.43	3.44	2.73	2.61	2.56	2.48	2.74	2.79
HVI Trash 1/										
00	*	0.1	-	-	*	*	0.1	0.1	-	-
01	6.3	23.4	1.0	0.9	10.2	12.6	21.7	19.5	4.0	3.1
02	27.5	34.8	10.6	9.9	31.2	35.5	36.6	36.1	33.2	28.5
03	25.3	20.0	21.9	21.4	28.4	26.9	19.7	22.9	35.9	37.8
04	18.1	10.2	23.8	24.1	16.2	13.9	9.7	11.5	17.5	20.3
05	10.2	5.0	18.8	19.0	8.0	6.4	5.1	5.2	6.4	7.2
06	5.5	2.7	12.4	12.2	3.4	2.7	2.7	2.3	2.1	2.2
07	3.0	1.5	6.5	6.7	1.5	1.1	1.6	1.1	0.5	0.7
08	1.8	0.9	2.9	3.3	0.7	0.4	0.9	0.6	0.2	0.2
09	1.0	0.6	1.3	1.4	0.3	0.2	0.6	0.3	0.1	0.1
10	0.5	0.3	0.6	0.6	0.1	0.1	0.4	0.2	*	*
11	0.3	0.2	0.2	0.3	0.1	*	0.3	0.1	*	*
12	0.2	0.1	0.1	0.1	*	*	0.2	0.1	*	*
13	0.1	0.1	*	*	*	*	0.1	*	-	*
14	0.1	*	-	*	*	*	0.1	*	-	-
15	*	*	*	*	*	*	0.1	*	-	-
16	*	*	-	*	-	-	*	*	-	-
17	*	*	-	*	-	-	*	*	-	-
18 & Above	-	*	-	*	-	-	*	*	-	-
Average	0.35	0.27	0.44	0.45	0.30	0.28	0.27	0.27	0.30	0.31
UNIFORMITY 2/										
74 & Below	-	*	-	-	-	-	*	*	-	-
75	*	*	-	-	-	*	0.1	0.1	-	-
76	0.3	0.4	-	*	*	*	0.6	0.5	-	-
77	2.0	2.2	*	*	*	*	2.1	2.0	*	*
78	8.7	7.8	0.1	0.2	*	0.1	7.4	5.9	0.1	0.2
79	13.7	13.1	1.2	1.5	0.3	1.2	18.5	14.3	1.4	2.2
80	24.5	19.9	10.2	12.9	5.5	7.8	27.9	26.0	13.6	17.0
81	26.8	25.4	37.7	36.4	22.2	24.9	25.5	31.2	32.2	34.1
82	21.6	25.3	35.5	34.5	44.4	42.4	13.3	16.5	39.6	33.9
83	2.3	5.6	13.2	13.0	25.2	21.7	3.7	3.0	12.1	11.4
84	0.1	0.2	2.0	1.4	2.2	1.8	0.6	0.3	1.0	1.1
85 & Above	*	*	*	0.1	0.1	0.1	0.1	*	0.1	*
Average	80.84	81.02	82.00	81.93	82.41	82.26	80.68	80.85	81.95	81.84
Tenderable 3/	79.4	82.9	85.3	88.8	97.6	97.6	72.5	77.7	85.5	88.6
SAMPLES CLASSED	20,539	78,619	35,057	129,873	69,505	432,568	259,994	1,749,708	20,031	70,031

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Nov 23, 2023

Color Grade	Leaf	Arizona		California		New Mexico		Texas	
		Week	Season	Week	Season	Week	Season	Week	Season
01	1	-	-	2.8	6.7	-	35.8	16.4	17.6
	2	-	-	15.1	12.4	-	28.7	19.0	18.6
	3	-	-	1.0	0.5	-	0.7	0.2	0.5
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	18.9	19.6	-	65.2	35.5	36.7
02	1	-	-	5.2	9.5	-	9.9	12.0	12.7
	2	-	-	51.9	51.9	-	21.9	36.1	38.1
	3	-	-	14.2	10.0	-	2.2	8.4	7.1
	4	-	-	0.9	0.5	-	*	0.4	0.3
	5	-	-	*	*	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	72.3	71.9	-	34.0	57.0	58.1
03	1	-	-	0.1	0.2	-	*	0.1	0.1
	2	-	-	3.4	3.2	-	0.3	1.6	1.6
	3	-	-	3.8	3.7	-	0.4	4.3	2.6
	4	-	-	1.0	0.9	-	0.1	1.3	0.7
	5	-	-	0.1	*	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	8.3	8.0	-	0.8	7.4	5.0
04	1	-	-	-	-	-	-	-	-
	2	-	-	*	*	-	*	-	*
	3	-	-	0.2	0.2	-	-	0.1	0.1
	4	-	-	0.2	0.2	-	-	-	-
	5	-	-	*	*	-	-	-	-
	6	-	-	*	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	0.5	0.5	-	*	0.1	0.2
05	1	-	-	-	-	-	-	-	-
	2	-	-	-	*	-	-	-	-
	3	-	-	-	*	-	-	-	-
	4	-	-	*	*	-	-	-	-
	5	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	*	*	-	-	-	-
06	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-
	4	-	-	-	*	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	-	*	-	-	-	-
07	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	-	-	-	-	-	-
STAPLE									
44 & Shorter		-	-	0.2	0.6	-	1.7	7.1	8.8
46		-	-	9.5	8.9	-	10.9	26.2	35.8
48		-	-	31.9	34.4	-	68.7	51.4	40.6
50		-	-	46.9	48.5	-	18.2	15.2	14.8
52 & Longer		-	-	11.5	7.7	-	0.4	0.1	0.1
Average Staple		-	-	49.20	49.08	-	48.09	47.50	47.23
Average Length		-	-	1.43	1.43	-	1.40	1.38	1.37
EXTRANEIOUS MATTER									
Bark		-	-	*	*	-	-	-	-
Grass		-	-	0.4	0.2	-	-	-	-
Spindle Twist		-	-	0.2	0.2	-	-	0.1	*
Preparation		-	-	*	*	-	-	-	-
All Other		-	-	*	*	-	*	0.2	0.1

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE								
For The Week Ending Nov 23, 2023								
Quality Designation	Arizona		California		New Mexico		Texas	
	Week	Season	Week	Season	Week	Season	Week	Season
MIKE								
2.4 & Below	-	-	-	-	-	-	-	-
2.5 - 2.6	-	-	*	*	-	-	-	-
2.7 - 2.9	-	-	0.1	0.1	-	*	-	-
3.0 - 3.2	-	-	2.1	1.0	-	0.6	-	-
3.3 - 3.4	-	-	3.2	2.7	-	6.3	*	1.6
3.5 - 3.6	-	-	11.7	10.8	-	11.1	4.2	10.8
3.7 - 4.2	-	-	78.9	80.8	-	76.0	82.0	79.1
4.3 - 4.9	-	-	3.8	4.5	-	6.0	13.8	8.6
5.0 - 5.2	-	-	*	*	-	-	-	-
5.3 & Above	-	-	-	*	-	-	-	-
Average	-	-	3.87	3.89	-	3.88	3.96	3.91
ALL RANGE MIKE								
2.4 & Below	-	-	-	-	-	-	-	-
2.5	-	-	*	*	-	-	-	-
2.6	-	-	*	*	-	-	-	-
2.7	-	-	*	*	-	-	-	-
2.8	-	-	*	*	-	-	-	-
2.9	-	-	*	*	-	*	-	-
3.0	-	-	0.1	0.1	-	0.1	-	-
3.1	-	-	1.0	0.4	-	*	-	-
3.2	-	-	1.1	0.6	-	0.5	-	-
3.3	-	-	0.8	0.8	-	2.3	*	*
3.4	-	-	2.4	2.0	-	4.0	-	1.5
3.5	-	-	4.5	4.0	-	3.7	*	5.9
3.6	-	-	7.2	6.8	-	7.4	4.1	4.9
3.7	-	-	10.1	10.1	-	12.6	18.0	13.4
3.8	-	-	14.7	14.5	-	13.3	17.6	17.0
3.9	-	-	16.4	17.7	-	14.8	11.3	14.1
4.0	-	-	17.4	17.7	-	13.9	14.3	13.1
4.1	-	-	13.1	13.8	-	13.4	9.9	9.8
4.2	-	-	7.1	7.0	-	7.9	10.9	11.7
4.3	-	-	2.3	2.8	-	2.1	9.7	6.8
4.4	-	-	0.9	1.2	-	2.7	3.3	1.5
4.5	-	-	0.6	0.4	-	0.9	0.6	0.3
4.6	-	-	*	0.1	-	0.3	*	*
4.7	-	-	*	*	-	*	-	-
4.8	-	-	*	*	-	*	-	-
4.9	-	-	-	*	-	-	-	-
5.0	-	-	*	*	-	-	-	-
5.1	-	-	-	*	-	-	-	-
5.2	-	-	-	-	-	-	-	-
5.3 & Above	-	-	-	*	-	-	-	-
Average	-	-	3.87	3.89	-	3.88	3.96	3.91
STRENGTH 1/								
36 & Below	-	-	1.2	0.8	-	19.2	*	0.8
37	-	-	4.4	2.7	-	18.0	8.1	9.7
38	-	-	9.1	7.7	-	11.0	15.2	21.0
39	-	-	5.9	7.3	-	2.3	21.7	21.4
40	-	-	5.6	5.3	-	0.1	18.3	10.6
41	-	-	7.8	7.4	-	2.1	2.6	6.2
42	-	-	16.0	14.0	-	8.3	7.4	9.0
43	-	-	19.9	18.1	-	13.6	8.5	9.0
44	-	-	13.6	15.6	-	16.6	11.4	7.3
45	-	-	10.5	13.2	-	6.7	4.6	4.0
46	-	-	4.8	5.9	-	1.9	2.1	1.0
47	-	-	0.8	1.7	-	0.1	*	*
48 & Above	-	-	0.3	0.3	-	*	-	*
Average	-	-	42.45	42.78	-	40.59	40.93	40.55
UNIFORMITY								
83 & Below	-	-	0.2	0.2	-	0.1	-	0.1
84	-	-	2.8	4.0	-	5.8	3.3	7.6
85	-	-	24.9	21.3	-	42.3	32.4	42.1
86	-	-	39.9	49.8	-	32.5	45.7	38.4
87	-	-	31.0	24.0	-	19.2	18.5	11.8
88 & Above	-	-	1.2	0.8	-	0.1	*	*
Average	-	-	86.47	86.42	-	86.11	86.22	85.98
Samples Classed	-	-	31,002	83,649	-	8,739	2,494	5,638

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.