



Volume 21, No.19

State	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
AL	29	84.0	72.0	80,881	29	87.3	75.3	694,649
AR	26	87.6	71.2	118,671	28	91.4	78.4	1,037,874
AZ	10	78.4	59.5	15,807	11	81.3	59.6	116,495
CA	9	90.3	77.7	8,086	14	88.7	75.5	92,666
FL	4	78.7	63.0	14,397	4	82.2	67.1	100,617
GA	59	83.7	64.7	216,404	59	85.7	66.1	1,827,852
KS	2	57.2	30.7	13,412	3	46.3	32.2	57,136
LA	14	82.8	60.3	32,125	19	90.6	72.5	458,980
MO	21	87.5	69.5	69,757	21	89.2	74.3	529,824
MS	36	89.1	67.1	128,567	38	89.5	67.1	1,131,232
NC	34	84.7	64.6	100,759	34	82.5	56.9	804,639
NM	2	92.8	78.0	1,625	2	91.7	81.0	10,940
OK	12	80.4	64.2	37,913	12	85.3	68.2	216,022
SC	15	87.1	68.9	35,063	15	87.6	67.0	293,157
TN	22	88.1	68.5	92,685	22	90.6	72.8	696,832
TX	154	57.3	29.2	508,107	186	71.7	43.8	4,566,270
VA	4	86.2	58.0	24,048	4	84.9	56.1	155,161
United States	453	75.8	53.8	1,498,307	501	81.8	59.9	12,790,346
AMERICAN PIMA								
AZ	2			1,144	3			3,632
CA	17			39,919	17			268,181
NM*	-			-	-			-
TX	2			1,705	2			9,572
United States	22			44,725	23			285,795
United States all cotton	470			1,543,032	516			13,076,141

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 05, 2019

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	1.9	11.2	1.9	5.9	64.5	65.1	53.5	61.3	*	5.3	2.2	12.3
	3	2.1	11.9	2.4	5.4	6.0	7.4	3.9	7.5	0.1	4.4	1.1	9.0
	4	0.1	1.0	0.1	0.3	*	0.5	0.1	0.4	-	0.3	0.1	0.4
	5	-	*	-	*	-	*	-	*	-	-	*	*
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	4.0	24.1	4.4	11.6	70.5	73.1	57.5	69.2	0.1	10.0	3.4	21.7
31	1 - 2	0.9	2.7	1.8	4.0	15.5	8.9	29.5	15.6	0.7	2.0	1.6	4.7
	3	6.4	15.3	13.7	20.7	6.8	5.9	8.8	12.2	2.4	10.3	6.3	15.3
	4	2.5	6.5	5.8	9.4	0.3	1.5	0.8	1.7	1.1	3.4	2.5	4.5
	5	0.2	0.6	0.6	1.0	-	0.2	*	0.1	0.2	0.3	0.2	0.2
	6	*	*	*	*	-	*	-	*	-	*	*	*
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	10.0	25.2	21.8	35.2	22.6	16.5	39.2	29.6	4.4	16.0	10.5	24.8
41	1 - 2	1.7	1.4	0.8	0.7	4.0	0.6	0.2	0.1	1.5	0.6	2.5	1.8
	3	23.7	13.6	17.0	10.8	1.5	0.5	0.4	0.2	16.8	13.9	25.2	15.1
	4	20.5	12.3	28.8	21.8	*	0.3	0.4	0.2	34.0	22.8	22.4	13.5
	5	5.1	2.9	11.8	12.7	*	0.1	*	0.1	7.8	4.4	4.9	2.5
	6	0.4	0.3	1.5	1.4	-	*	-	*	0.2	0.2	0.3	0.1
	7	*	*	*	*	-	-	-	*	-	*	*	*
	8	*	*	-	-	-	-	-	-	-	-	-	*
Total	----	51.4	30.5	59.9	47.4	5.5	1.5	1.1	0.5	60.2	41.8	55.3	33.1
51	1 - 2	1.1	0.5	0.1	0.1	0.4	0.1	-	-	0.3	0.2	1.2	0.7
	3	10.9	4.5	2.3	0.7	0.4	0.1	-	-	6.4	6.9	11.1	5.7
	4	8.8	4.1	5.4	1.8	-	*	-	*	14.6	12.9	9.2	4.7
	5	2.4	1.2	3.6	1.7	-	*	-	-	6.0	4.4	2.2	1.1
	6	0.5	0.3	0.5	0.3	-	*	-	-	0.2	0.3	0.2	0.1
	7	*	*	-	*	-	-	-	-	-	*	*	*
	8	*	*	*	*	-	-	-	-	-	-	*	*
Total	----	23.7	10.6	11.8	4.6	0.7	0.1	-	*	27.4	24.8	24.0	12.3
61	1 - 2	*	*	-	-	*	*	-	-	*	*	*	*
	3	0.4	0.1	-	*	*	*	-	-	0.1	0.2	0.3	0.1
	4	0.2	*	*	*	-	-	-	-	0.2	0.3	0.1	*
	5	*	*	*	*	-	*	-	-	0.2	0.1	*	*
	6	*	*	*	*	-	-	-	-	-	*	*	*
	7	-	-	-	-	-	-	-	-	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	-	*	*
Total	----	0.6	0.1	*	*	*	*	-	-	0.5	0.6	0.4	0.1
71	1 - 2	-	-	-	-	-	-	-	-	-	-	*	*
	3	-	-	-	-	-	-	-	-	-	-	*	*
	4	-	-	-	-	-	-	-	-	-	-	*	*
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	*
Total	----	-	-	-	-	-	-	-	-	-	-	*	*
12 & 22	1 - 2	0.3	0.3	*	*	0.1	2.6	0.3	0.1	-	*	0.1	0.5
	3	0.3	0.4	*	*	*	2.7	0.4	0.1	-	0.1	0.1	0.3
	4	*	0.1	*	*	-	0.5	*	*	-	*	*	*
	5	-	*	-	-	-	*	-	*	-	-	-	-
	6	-	-	-	-	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.5	0.9	*	0.1	0.1	5.9	0.7	0.2	-	0.1	0.2	0.8
32	1 - 2	0.1	0.1	*	*	0.1	0.3	0.3	0.1	-	0.1	0.1	0.4
	3	0.5	1.0	0.3	0.3	0.2	0.8	1.0	0.2	-	0.3	0.2	1.3
	4	0.5	0.7	0.3	0.2	*	0.8	0.1	0.1	-	0.3	0.1	0.4
	5	0.1	0.1	*	*	-	0.3	-	0.1	*	*	*	*
	6	*	*	-	*	-	*	-	*	-	*	-	*
	7	-	*	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	1.2	2.0	0.7	0.5	0.4	2.1	1.4	0.5	*	0.7	0.4	2.0
42	1 - 2	0.1	0.2	*	*	*	*	*	*	0.2	0.1	0.2	0.2
	3	1.8	1.5	0.2	0.1	0.1	0.1	*	*	1.4	0.8	1.3	1.5
	4	2.1	1.6	0.5	0.2	0.1	0.2	*	*	2.3	1.3	1.2	1.2
	5	0.8	0.6	0.2	0.1	-	0.2	-	*	0.7	0.4	0.3	0.2
	6	0.1	0.1	*	*	-	0.1	-	-	*	*	*	*
	7	*	*	-	-	-	*	-	-	-	-	*	*
	8	*	*	-	-	-	*	-	-	-	-	-	-
Total	----	5.0	4.0	0.8	0.5	0.1	0.6	0.1	*	4.7	2.6	2.9	3.0

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 05, 2019

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	*	0.1	-	*	-	-	-	-	*	0.1	0.2	0.1
	3	1.1	0.8	*	*	-	*	-	-	1.0	0.9	1.1	0.9
	4	1.7	0.9	0.1	*	-	*	-	-	1.1	1.5	1.0	0.7
	5	0.3	0.2	*	*	-	*	-	-	0.5	0.6	0.2	0.2
	6	*	*	*	*	-	*	-	-	*	0.1	*	*
	7	*	*	-	-	-	-	-	-	-	*	-	*
	8	*	*	-	-	-	*	-	-	-	*	-	*
Total	----	3.1	2.1	0.1	*	-	*	-	-	2.6	3.1	2.6	1.9
62	1 - 2	*	*	-	*	-	-	-	-	*	*	*	*
	3	*	*	-	*	-	-	-	-	-	*	*	*
	4	*	*	-	*	-	-	-	-	-	0.1	*	*
	5	*	*	-	*	-	-	-	-	*	*	*	*
	6	*	*	-	*	-	-	-	-	-	*	*	*
	7	*	*	-	-	-	-	-	-	-	*	-	*
	8	-	*	-	-	-	-	-	-	-	*	-	*
Total	----	*	0.1	-	*	-	-	-	-	*	0.2	0.1	0.1
13 & 23	1 - 2	-	*	-	*	-	*	-	*	-	-	*	*
	3	*	*	*	*	-	*	-	-	-	-	*	*
	4	-	*	*	*	-	*	-	-	-	*	*	*
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	*	*	-	0.1	-	*	-	*	*	*
33	1 - 2	*	*	*	*	*	*	-	*	-	-	*	*
	3	*	*	0.1	*	*	*	-	-	-	*	*	*
	4	*	*	0.1	*	*	*	-	-	-	*	*	*
	5	*	*	*	*	-	*	-	-	-	-	-	*
	6	-	*	-	-	-	-	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.1	0.1	0.1	*	*	*	-	*	-	*	*	*
43	1 - 2	*	*	*	*	-	-	-	-	-	-	*	*
	3	*	0.1	*	*	*	*	-	*	-	*	0.1	*
	4	0.1	0.1	0.1	*	-	*	-	-	-	*	0.1	*
	5	0.1	*	*	*	-	*	-	-	*	*	*	*
	6	*	*	*	*	-	*	-	-	-	*	*	*
	7	-	*	-	-	-	*	-	-	-	-	-	*
	8	-	*	-	-	-	*	-	-	-	-	-	-
Total	----	0.3	0.2	0.2	0.1	*	*	-	*	*	*	0.2	0.1
53	1 - 2	-	*	-	-	-	-	-	-	-	-	*	*
	3	*	*	-	*	-	*	-	-	*	*	0.1	*
	4	*	*	*	*	-	-	-	-	*	*	0.1	*
	5	*	*	*	*	-	-	-	-	*	*	*	*
	6	-	*	-	*	-	*	-	-	*	*	*	*
	7	*	*	-	-	-	*	-	-	-	-	-	-
	8	-	*	-	-	-	*	-	-	-	-	-	-
Total	----	0.1	0.1	*	*	-	*	-	-	*	0.1	0.2	0.1
63	1 - 2	-	*	-	-	-	-	-	-	-	-	-	*
	3	-	*	-	*	-	-	-	-	-	-	-	*
	4	-	*	-	-	-	-	-	-	-	-	*	*
	5	-	*	-	-	-	-	-	-	-	-	*	*
	6	*	*	-	-	-	-	-	-	-	*	-	*
	7	*	*	-	*	-	-	-	-	-	*	-	-
	8	*	*	-	-	-	-	-	-	-	*	-	-
Total	----	*	*	-	*	-	-	-	-	-	*	*	*
24 - 54	1 - 8	*	*	*	*	-	*	-	-	-	*	*	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	*	-	-	-	-	-	-	-	-	*	*
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	-	-	-	-	-	-	-	-	-	*	*
31		*	*	-	*	-	-	-	-	-	-	*	*
32		0.4	0.5	*	*	*	*	-	-	*	*	0.3	0.4
33		2.3	2.1	-	*	0.2	0.6	*	*	1.1	0.7	1.9	2.4
34		6.1	6.7	*	0.1	2.0	2.5	2.2	1.2	1.6	2.3	6.2	7.3
35		13.6	13.1	1.2	1.8	5.7	8.1	9.3	2.9	5.0	3.9	14.0	15.0
36		24.7	22.8	7.9	11.2	11.1	21.5	19.4	12.2	12.1	10.4	20.4	20.8
37		33.2	32.7	34.9	40.7	33.3	33.5	30.9	35.3	29.3	34.8	29.1	30.4
38		13.3	14.6	27.6	25.2	24.7	21.0	20.9	27.2	33.2	35.6	18.7	17.2
39		5.3	6.3	20.3	16.5	17.4	10.7	14.0	17.9	16.0	11.3	8.1	5.7
40 & Longer		1.1	1.1	8.1	4.4	5.7	2.0	3.3	3.3	1.7	1.1	1.2	0.7
Average Staple		36.46	36.50	37.83	37.57	37.48	37.01	37.14	37.51	37.39	37.33	36.62	36.46
Average Length		1.14	1.14	1.18	1.17	1.17	1.16	1.16	1.17	1.17	1.17	1.14	1.14

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 05, 2019

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	20.3	18.8	8.9	18.0	0.7	3.8	4.8	15.6	1.1	5.6	41.2	63.1
	3	7.2	6.4	3.7	16.2	0.5	1.8	5.8	13.7	1.1	5.8	3.3	6.0
	4	0.2	0.2	0.2	0.9	*	*	0.6	1.6	*	0.4	-	*
	5	-	*	-	*	*	*	*	*	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	*	-	-	-	-
Total	----	27.7	25.4	12.8	35.1	1.3	5.6	11.2	31.0	2.2	11.8	44.5	69.1
31	1 - 2	5.0	3.0	1.6	2.7	3.1	6.3	1.6	2.8	3.4	3.9	19.3	13.1
	3	15.6	11.4	9.3	15.6	16.3	22.6	10.6	15.3	11.9	21.1	15.1	9.4
	4	9.7	8.1	2.8	7.3	5.4	8.8	6.9	8.4	2.9	9.8	0.7	0.7
	5	0.8	1.1	0.1	0.6	0.4	1.0	0.6	1.0	0.2	1.0	-	0.1
	6	*	0.1	*	*	*	*	*	*	*	*	-	-
	7	-	*	-	*	-	-	-	*	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-	-	-
Total	----	31.2	23.6	13.8	26.2	25.2	38.7	19.7	27.5	18.4	35.8	35.1	23.2
41	1 - 2	-	*	2.0	0.5	1.4	1.4	1.3	0.9	4.5	2.1	-	0.5
	3	0.3	0.2	16.3	7.7	19.8	14.4	14.3	9.6	38.1	21.4	2.6	2.2
	4	2.6	1.4	17.5	12.3	32.7	23.3	22.6	13.8	25.1	19.2	2.6	0.9
	5	2.1	1.8	4.6	4.3	12.2	11.5	8.7	5.3	3.1	3.4	0.6	0.1
	6	0.3	0.7	0.7	0.5	1.1	1.1	0.9	0.6	0.1	0.2	-	-
	7	*	0.3	*	*	*	*	*	*	-	*	-	-
	8	-	0.1	-	-	-	-	*	*	-	-	-	-
Total	----	5.3	4.5	41.2	25.3	67.2	51.7	47.8	30.2	71.0	46.3	5.8	3.6
51	1 - 2	-	-	0.2	*	0.1	*	0.2	0.1	0.1	*	-	-
	3	-	-	6.7	1.5	0.8	0.4	4.3	2.0	1.7	0.9	-	*
	4	-	*	12.5	4.0	2.3	1.4	8.9	4.2	2.9	1.8	-	*
	5	-	0.2	3.5	2.1	2.1	1.2	4.1	2.2	0.9	0.6	-	-
	6	-	0.1	0.3	0.4	0.3	0.3	0.9	0.5	0.1	0.1	-	-
	7	-	0.1	*	*	*	*	0.2	*	-	*	-	-
	8	-	0.2	*	*	-	-	*	*	*	*	-	-
Total	----	-	0.7	23.2	8.0	5.7	3.3	18.5	9.1	5.7	3.3	-	*
61	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	*	*	-	-	*	*	-	-	-	-
	4	-	-	0.1	0.1	-	-	*	*	-	-	-	-
	5	-	-	*	0.1	-	-	*	*	-	-	-	-
	6	-	-	*	*	-	-	*	*	-	-	-	-
	7	-	-	-	*	-	-	*	*	*	*	-	-
	8	-	-	-	-	-	-	*	*	*	*	-	-
Total	----	-	-	0.2	0.2	-	-	0.1	*	*	*	-	-
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	*	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	*	*	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	*	*	-	-	-	-
12 & 22	1 - 2	14.2	6.2	0.1	0.5	-	*	*	0.1	*	*	8.4	1.7
	3	3.2	1.3	0.2	0.6	*	*	0.1	0.2	*	0.1	1.0	0.3
	4	0.1	0.1	0.1	0.1	-	-	*	0.1	*	*	-	-
	5	*	*	-	*	-	-	-	*	-	*	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	17.5	7.6	0.4	1.1	*	*	0.2	0.4	*	0.1	9.4	2.0
32	1 - 2	0.3	0.2	0.1	0.2	-	*	*	0.1	0.1	0.1	0.6	0.1
	3	2.1	1.1	0.3	0.6	0.1	0.1	0.2	0.3	0.3	0.5	1.2	0.6
	4	2.7	2.3	0.2	0.3	*	*	0.3	0.3	0.1	0.4	0.6	0.4
	5	0.7	1.3	*	*	*	*	0.1	0.1	*	*	0.1	*
	6	*	0.2	-	*	*	*	*	*	-	*	-	-
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	5.9	5.2	0.6	1.1	0.1	0.2	0.6	0.7	0.5	0.9	2.4	1.2
42	1 - 2	-	-	0.1	0.1	*	*	*	*	0.1	*	-	*
	3	*	0.1	2.0	0.7	0.1	0.1	0.2	0.2	0.7	0.5	0.1	0.2
	4	0.1	0.6	1.8	0.9	0.2	0.1	0.5	0.4	0.7	0.7	-	*
	5	0.4	2.1	0.5	0.3	*	*	0.4	0.2	0.1	0.2	-	-
	6	0.3	1.7	*	0.1	*	*	0.1	*	*	*	-	-
	7	*	0.6	*	*	-	-	*	*	-	*	-	-
	8	*	0.2	-	-	-	-	-	-	-	-	-	-
Total	----	0.9	5.2	4.5	2.1	0.3	0.3	1.1	0.8	1.6	1.5	0.1	0.3

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 05, 2019

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	*	*	-	*	*	*	*	*	-	-
	3	-	-	0.9	0.1	*	*	0.1	*	*	*	-	-
	4	-	*	0.6	0.2	*	*	0.2	0.1	*	*	-	-
	5	*	0.2	0.2	0.1	*	*	0.1	0.1	*	*	-	-
	6	*	0.3	*	*	*	*	*	*	-	*	-	-
	7	*	0.2	*	*	-	-	*	*	-	-	-	-
	8	0.1	0.3	*	*	-	-	-	*	-	-	-	-
Total	----	0.1	0.9	1.8	0.5	*	*	0.4	0.2	0.1	0.1	-	-
62	1 - 2	-	-	-	-	-	-	-	*	-	-	-	-
	3	-	-	-	-	-	*	*	*	-	-	-	-
	4	-	*	-	*	-	*	*	*	-	*	-	-
	5	-	*	*	*	-	*	*	*	-	-	-	-
	6	-	-	*	*	-	*	-	*	*	*	-	-
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	*	*	-	*	*	*	*	*	-	-
13 & 23	1 - 2	7.0	2.5	*	*	-	-	*	*	-	-	1.3	0.2
	3	2.0	1.1	*	*	-	-	*	*	-	-	0.5	0.1
	4	0.2	0.1	-	*	-	-	-	*	-	-	-	-
	5	-	*	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	9.2	3.7	*	*	-	-	*	*	-	-	1.8	0.3
33	1 - 2	*	*	*	*	-	*	*	*	*	*	0.1	*
	3	0.5	0.5	0.1	*	*	*	*	*	0.1	*	0.9	0.2
	4	0.7	0.7	*	*	*	*	*	*	*	*	-	*
	5	0.4	1.1	*	*	*	*	*	*	-	*	-	-
	6	*	0.5	-	-	-	-	-	-	-	*	-	-
	7	-	0.1	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	----	1.7	2.9	0.2	0.1	*	*	*	*	0.1	0.1	1.0	0.2
43	1 - 2	-	*	*	*	-	*	*	*	*	*	-	-
	3	-	0.1	0.4	0.1	*	*	*	*	0.1	*	-	-
	4	*	0.9	0.5	0.1	0.1	*	*	*	0.1	*	-	-
	5	*	2.0	0.1	*	*	*	*	*	*	*	-	-
	6	-	1.9	*	*	-	*	*	*	*	*	-	-
	7	-	0.9	-	-	-	-	-	*	-	-	-	-
	8	-	0.8	-	-	-	-	-	-	-	-	-	-
Total	----	*	6.5	1.0	0.2	0.2	0.1	0.1	0.1	0.3	0.1	-	-
53	1 - 2	-	-	-	-	-	-	*	*	-	-	-	-
	3	-	-	*	*	*	*	*	*	*	*	-	-
	4	-	0.2	*	*	-	*	*	*	*	*	-	-
	5	-	0.4	*	*	*	*	*	*	*	*	-	-
	6	-	0.9	-	*	*	*	-	*	-	*	-	-
	7	-	1.3	-	-	-	-	-	-	-	-	-	-
	8	-	0.9	-	-	-	-	-	-	-	-	-	-
Total	----	-	3.8	0.1	*	*	*	0.1	*	*	*	-	-
63	1 - 2	-	-	-	-	-	*	-	*	-	-	-	-
	3	-	-	-	-	-	*	*	*	-	-	-	-
	4	-	*	-	-	-	*	-	*	-	-	-	-
	5	-	*	-	-	-	*	-	*	-	*	-	-
	6	-	*	-	-	-	*	-	*	-	-	-	-
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	----	-	0.1	-	-	-	*	*	*	-	*	-	-
24 - 54	1 - 8	0.6	6.5	0.2	*	*	*	*	*	*	*	-	-
25 - 35	1 - 8	-	*	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	3.4	*	*	-	-	-	*	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	*	-	-	-	-	-	-	-	-	-	-
30		-	*	-	-	-	-	-	-	-	-	-	-
31		-	*	-	-	-	*	-	-	*	*	-	-
32		*	*	-	-	-	*	-	*	0.1	0.1	-	-
33		0.7	0.6	0.1	*	*	*	*	*	0.4	0.4	-	-
34		5.1	7.2	0.2	0.1	0.2	0.4	0.5	0.6	2.6	2.4	1.4	0.2
35		28.4	25.9	2.7	1.2	1.8	3.9	2.6	3.2	10.9	10.5	20.8	4.9
36		32.6	38.6	12.9	8.4	13.0	16.7	11.9	11.0	26.0	27.5	3.5	7.9
37		30.9	26.0	23.8	23.0	42.5	43.3	25.6	26.6	35.6	33.8	23.4	29.4
38		2.2	1.4	33.6	31.6	23.2	20.8	32.6	35.0	16.0	16.6	23.3	31.2
39		0.1	0.2	18.8	26.6	13.9	11.0	23.0	21.1	7.2	7.5	20.7	21.3
40 & Longer		-	*	7.9	8.9	5.4	3.9	3.7	2.6	1.2	1.2	6.8	5.0
Average Staple		35.95	35.87	37.76	38.02	37.51	37.29	37.71	37.66	36.77	36.78	37.36	37.71
Average Length		1.12	1.12	1.18	1.19	1.17	1.16	1.18	1.18	1.15	1.15	1.17	1.18

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 05, 2019

Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	45.0	58.1	2.6	7.8	0.2	5.3	17.6	31.9	3.1	15.3
	3	12.6	9.5	2.5	10.6	0.2	2.9	7.3	11.0	1.6	17.2
	4	0.2	0.3	0.1	0.7	*	0.2	0.3	0.7	*	0.8
	5	*	*	-	*	-	*	*	*	-	*
	6	-	-	-	*	-	-	-	*	-	*
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	57.8	67.9	5.2	19.1	0.4	8.3	25.3	43.7	4.7	33.4
31	1 - 2	6.2	6.1	3.6	5.7	2.7	6.9	4.6	3.8	3.9	5.6
	3	16.0	11.8	23.8	28.1	8.3	19.7	11.0	8.8	11.2	23.5
	4	6.1	3.9	6.8	10.7	2.8	6.8	4.5	3.2	1.9	7.6
	5	1.0	0.6	0.2	0.7	0.3	0.7	0.5	0.4	*	0.4
	6	*	*	-	*	*	*	*	*	-	*
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	29.3	22.4	34.5	45.2	14.1	34.1	20.6	16.2	17.0	37.1
41	1 - 2	*	*	2.1	1.3	5.9	3.2	0.2	0.6	9.3	3.6
	3	0.1	0.1	25.8	13.6	31.0	18.3	1.1	2.4	46.9	18.1
	4	0.6	0.6	18.4	10.7	26.4	20.3	0.8	1.6	13.7	5.0
	5	1.2	0.6	1.7	1.6	8.9	7.5	0.6	0.4	1.2	0.5
	6	0.7	0.2	*	0.1	0.9	1.0	0.2	0.1	0.1	*
	7	0.6	0.1	-	-	*	*	0.1	*	-	-
	8	0.2	*	-	-	*	*	*	*	-	-
Total	----	3.5	1.6	48.0	27.2	73.1	50.3	3.0	5.0	71.1	27.2
51	1 - 2	*	*	0.2	0.1	0.4	0.1	*	0.1	0.1	0.1
	3	-	-	3.0	1.1	2.9	1.0	*	0.4	1.3	0.4
	4	-	*	2.8	1.0	4.0	1.6	*	0.3	1.1	0.2
	5	*	*	0.6	0.2	1.8	1.0	*	0.1	0.2	*
	6	*	*	0.1	*	0.3	0.3	*	*	-	*
	7	-	*	*	*	*	*	*	*	-	-
	8	*	*	*	*	*	*	*	*	-	-
Total	----	*	*	6.8	2.4	9.5	4.0	0.1	0.8	2.8	0.7
61	1 - 2	-	-	-	*	*	*	-	*	-	-
	3	-	-	-	*	-	-	-	*	-	-
	4	-	-	*	*	-	-	-	*	-	-
	5	-	-	-	*	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	*	*	-	-	-	*	-	-
Total	----	-	-	*	*	*	*	-	0.1	-	-
71	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	-	-	-	-	*	-	-
	5	-	-	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	-	-	-	-	-	-	-	*	-	-
12 & 22	1 - 2	2.0	1.6	*	0.2	*	0.1	8.1	10.0	*	0.1
	3	0.9	1.5	0.1	0.2	*	0.1	6.5	5.6	0.1	0.1
	4	*	0.1	*	*	*	*	0.6	0.6	*	*
	5	-	*	-	-	-	*	*	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	2.9	3.2	0.1	0.4	*	0.2	15.2	16.2	0.1	0.2
32	1 - 2	0.5	0.3	0.3	0.3	0.1	0.3	3.6	2.1	0.1	0.1
	3	1.8	1.6	1.2	1.6	0.6	0.8	10.7	4.9	0.7	0.3
	4	1.4	1.2	0.4	0.8	0.2	0.3	4.8	2.2	0.3	0.2
	5	0.4	0.3	*	0.1	*	*	0.8	0.4	*	*
	6	*	*	-	*	-	*	0.1	*	-	*
	7	*	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	4.1	3.4	1.9	2.9	0.9	1.4	20.0	9.7	1.0	0.5
42	1 - 2	*	*	0.1	0.1	0.1	0.1	0.1	0.2	0.2	*
	3	*	*	0.9	0.9	0.6	0.6	0.6	0.7	1.7	0.5
	4	0.1	0.1	0.9	0.9	0.5	0.5	0.7	0.7	0.9	0.3
	5	0.3	0.1	0.2	0.3	0.1	0.1	0.7	0.3	0.1	*
	6	0.2	0.1	*	*	*	*	0.4	0.1	*	*
	7	*	*	-	-	*	*	0.1	*	-	-
	8	*	*	-	-	-	-	*	*	-	-
Total	----	0.7	0.4	2.1	2.2	1.2	1.3	2.7	2.1	2.8	0.9

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE											
For The Week Ending Dec 05, 2019											
Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	*	*	*	*	*	*	-	*
	3	-	-	0.3	0.1	0.1	*	*	0.1	*	*
	4	-	*	0.2	0.1	0.1	*	*	0.2	*	*
	5	-	*	*	*	*	*	*	*	*	*
	6	*	*	*	*	*	*	*	*	*	*
	7	*	*	*	*	*	*	*	*	-	-
	8	*	*	-	-	-	-	*	*	-	-
Total	----	*	*	0.6	0.2	0.3	0.1	0.1	0.4	0.2	*
62	1 - 2	-	-	-	-	-	-	-	*	-	*
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	*	-	-	-	*	-	-
	5	-	-	-	*	-	-	-	*	-	-
	6	-	-	-	*	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	-	-	-	*	-	-	-	*	-	*
13 & 23	1 - 2	*	*	-	*	-	-	2.4	1.3	-	-
	3	*	0.1	*	*	*	*	2.2	1.0	-	*
	4	-	*	-	*	-	-	0.3	0.1	-	-
	5	-	*	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	*	0.1	*	*	*	*	4.8	2.4	-	*
33	1 - 2	0.3	0.1	0.1	*	*	*	1.2	0.6	*	*
	3	0.6	0.3	0.2	0.1	0.1	0.1	3.4	1.4	*	*
	4	0.2	0.3	0.1	*	*	*	1.5	0.6	*	*
	5	0.1	0.1	*	*	-	*	0.3	0.1	-	-
	6	*	*	-	-	-	-	*	*	-	-
	7	-	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	1.2	0.7	0.4	0.2	0.2	0.1	6.5	2.7	0.1	*
43	1 - 2	*	*	*	*	*	*	*	*	*	*
	3	*	*	0.2	0.1	0.1	0.1	0.2	0.1	0.1	*
	4	*	*	0.2	0.1	0.1	*	0.3	0.1	*	*
	5	0.1	*	0.1	*	*	*	0.2	0.1	*	*
	6	0.1	*	*	*	*	*	0.1	*	-	-
	7	*	*	-	-	-	-	0.1	*	-	-
	8	*	*	-	-	-	-	*	*	-	-
Total	----	0.2	0.1	0.4	0.2	0.3	0.2	0.9	0.4	0.1	*
53	1 - 2	-	-	-	*	-	-	*	*	*	*
	3	-	*	*	*	*	*	*	*	-	*
	4	-	-	*	*	*	*	*	*	*	*
	5	-	*	-	*	*	*	*	*	-	-
	6	*	*	-	*	-	-	*	*	-	-
	7	-	*	-	-	-	-	*	*	-	-
	8	-	*	-	-	-	-	*	*	-	-
Total	----	*	*	*	*	*	*	*	*	*	*
63	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	*	-	-	-	*	-	-
	5	-	-	-	*	-	-	-	*	-	-
	6	-	-	-	*	-	-	-	*	-	-
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	-	-	*	*	-	-
24 - 54	1 - 8	0.1	0.1	0.1	*	*	*	0.8	0.3	-	*
25 - 35	1 - 8	-	*	-	-	-	-	-	*	-	-
81 - 85	1 - 8	-	*	*	*	*	*	*	*	-	-
STAPLE											
28 & Shorter		-	*	-	-	-	-	-	*	-	-
29		-	*	-	-	-	-	*	*	-	-
30		*	*	-	-	-	-	0.1	0.2	-	-
31		0.3	0.3	*	*	-	-	1.0	1.1	-	-
32		1.0	1.2	0.1	0.2	-	*	3.6	3.5	-	*
33		4.5	4.8	1.2	1.6	*	*	9.1	7.8	*	0.1
34		10.5	9.2	4.3	5.7	0.5	1.1	17.7	14.2	0.6	0.8
35		12.0	12.9	11.5	13.1	7.7	12.5	23.0	20.0	5.8	4.9
36		12.7	17.3	22.1	20.4	35.5	37.2	19.2	19.9	16.8	16.3
37		23.9	25.0	37.9	38.2	41.4	36.4	16.6	20.4	43.5	38.8
38		17.1	17.0	18.9	16.7	11.4	9.9	6.4	8.8	20.9	23.3
39		11.0	9.2	3.6	3.8	3.3	2.6	2.5	3.2	9.7	12.6
40 & Longer		6.9	3.1	0.3	0.2	0.3	0.2	0.8	0.8	2.7	3.2
Average Staple		36.68	36.47	36.64	36.54	36.66	36.50	35.34	35.58	37.19	37.30
Average Length		1.15	1.14	1.14	1.14	1.14	1.14	1.10	1.11	1.16	1.16

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 05, 2019

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	2.0	1.8	1.0	0.7	0.6	0.1	0.9	0.1	7.0	7.1	3.2	2.8
Bark - Level 2	*	*	-	*	-	-	-	-	-	-	-	*
Grass - Level 1	*	0.1	0.1	0.1	-	*	-	0.1	*	0.2	*	0.1
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	*
Prep - Level 1	*	*	-	*	-	*	-	*	*	*	*	*
Prep - Level 2	-	*	-	-	-	-	-	-	-	-	-	*
Seed Coat - Level 1	*	*	*	*	1.3	1.4	-	*	*	*	*	*
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	*
Oil - Level 1	*	*	-	*	-	-	-	-	-	-	*	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	*	*
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	-	0.1	-	*	-	*	*	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	*	-	*	*	*	*	*
Plastic - Level 2	-	-	-	*	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	*	-	*	-	-	-	-	-	-	*	*
23	-	*	*	*	-	-	-	-	-	*	*	*
24	*	0.1	-	*	-	-	-	-	-	*	0.1	0.2
25	0.1	0.4	*	*	*	0.1	-	*	*	0.1	0.6	0.9
26	1.0	1.9	0.1	0.1	0.1	0.4	-	*	0.4	0.9	2.2	3.5
27	5.1	7.6	0.4	1.0	0.6	1.8	-	0.5	1.9	3.9	6.3	8.8
28	16.9	21.3	1.9	6.1	2.7	6.4	*	0.6	8.8	13.4	12.0	16.0
29	29.3	30.4	12.1	20.0	7.8	15.2	1.0	2.8	21.7	27.3	20.3	22.7
30	24.2	21.5	27.4	30.5	21.8	24.3	9.6	10.2	28.9	29.4	23.7	22.3
31	12.9	10.3	27.6	24.2	26.6	23.1	17.1	13.1	21.7	14.8	17.8	14.1
32	6.0	4.3	17.2	12.1	16.8	15.3	24.5	16.4	9.5	6.5	9.9	7.0
33	2.6	1.5	8.2	4.2	11.2	7.6	15.0	9.2	4.3	2.5	4.4	3.0
34	1.3	0.6	3.4	1.4	7.7	3.4	5.2	5.4	1.5	0.7	2.0	1.1
35	0.4	0.1	1.4	0.4	2.1	1.7	2.2	10.5	1.2	0.3	0.6	0.4
36	0.1	*	0.4	0.1	1.2	0.5	8.3	16.0	0.2	*	0.2	0.1
37	*	*	0.1	*	0.9	0.2	12.8	11.7	-	-	*	*
38	*	*	*	*	0.4	0.1	3.6	2.9	-	-	*	*
39	-	-	*	*	0.1	*	0.4	0.4	-	-	-	-
40 & Above	-	-	-	-	*	*	0.3	0.3	-	-	-	-
Average	30.02	29.66	31.38	30.78	31.82	31.12	33.60	33.94	30.65	30.15	30.32	29.89
Mike												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	-
2.5	*	*	-	-	-	-	*	*	-	*	*	*
2.6	*	*	-	-	-	-	-	-	-	*	*	*
2.7	*	*	-	-	-	-	-	*	-	-	*	*
2.8	-	*	-	*	-	-	-	*	-	*	*	*
2.9	*	*	*	*	*	*	-	0.1	-	*	*	*
3.0	*	*	-	*	0.1	*	0.1	0.2	-	*	*	*
3.1	*	*	*	*	0.2	*	0.4	0.3	-	-	*	*
3.2	0.1	*	*	*	0.2	0.1	0.1	0.3	-	-	*	*
3.3	0.2	0.1	*	*	0.3	0.1	0.1	0.4	*	*	*	*
3.4	0.3	0.2	*	*	0.4	0.1	0.1	0.5	*	*	*	0.1
3.5	0.4	0.4	0.1	0.1	1.0	0.3	0.8	1.0	*	*	0.1	0.1
3.6	0.9	0.9	0.3	0.2	0.7	0.5	0.3	1.6	*	*	0.1	0.2
3.7	1.7	1.8	0.8	0.6	0.8	1.0	0.8	1.8	-	*	0.2	0.3
3.8	3.0	2.8	1.5	1.2	1.5	1.8	1.3	2.5	0.1	0.1	0.6	0.6
3.9	4.0	4.3	2.2	2.0	2.5	1.9	2.7	3.2	*	0.3	1.0	1.0
4.0	5.6	6.0	3.6	3.4	3.3	2.5	4.1	4.9	0.2	0.9	1.4	1.7
4.1	7.1	7.8	5.2	5.2	4.4	3.3	6.9	7.4	0.7	1.7	2.4	3.0
4.2	10.3	9.7	8.2	7.9	3.3	4.1	12.6	8.2	1.8	3.1	4.5	5.3
4.3	10.1	11.1	8.7	10.5	5.5	6.2	9.7	8.5	6.7	6.5	7.6	8.5
4.4	10.8	12.0	11.0	12.2	8.5	9.6	11.0	9.5	16.9	14.3	10.5	12.1
4.5	12.1	12.1	13.2	14.0	10.9	10.9	10.3	10.3	20.6	20.4	14.4	15.0
4.6	10.9	10.8	12.4	13.8	10.6	12.8	13.4	10.8	18.8	19.5	16.4	15.8
4.7	9.0	8.6	10.1	10.8	10.2	12.1	7.2	9.0	14.3	14.6	15.0	13.4
4.8	6.5	5.2	8.6	7.7	9.1	9.9	5.5	6.1	8.4	8.6	11.1	10.0
4.9	3.3	3.2	6.0	4.7	8.3	7.0	4.6	4.0	4.3	4.8	7.0	6.3
5.0	2.0	1.6	3.7	2.6	7.2	6.4	1.3	2.5	4.0	3.0	4.2	3.5
5.1	1.2	0.7	2.3	1.4	3.9	4.1	1.7	1.8	2.4	1.8	2.4	1.8
5.2	0.4	0.3	1.3	0.9	2.6	2.1	3.5	1.9	0.6	0.4	0.7	0.6
5.3	0.1	0.1	0.8	0.4	2.6	1.3	1.1	1.2	*	0.1	0.2	0.2
5.4	*	*	0.3	0.1	1.6	1.0	0.1	0.7	*	*	0.1	0.1
5.5 & Above	-	*	0.1	*	0.4	0.6	-	1.0	-	*	*	0.1
Average	4.39	4.37	4.51	4.49	4.58	4.59	4.44	4.42	4.59	4.57	4.58	4.55

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 05, 2019

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	12.3	31.7	2.2	0.9	0.4	0.3	1.2	0.9	2.6	2.2	1.4	0.9
Bark - Level 2	-	-	-	-	-	-	-	*	-	-	-	-
Grass - Level 1	-	*	*	0.1	*	*	*	0.1	0.2	0.4	-	*
Grass - Level 2	-	-	-	-	-	-	-	*	-	-	-	-
Prep - Level 1	-	-	-	*	-	*	*	*	*	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	-	-	*	-	*	*	*	-	*	-	*
Seed Coat - Level 2	-	-	-	-	-	-	*	*	-	-	-	-
Oil - Level 1	-	-	-	*	*	*	*	*	-	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	*	*	-	*	*	*	*	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	*	*	*	*	*	-	-
Plastic - Level 2	-	-	-	-	-	-	*	*	-	-	-	-
STRENGTH 1/ 22 & Below	-	0.3	-	-	-	*	-	-	-	-	-	-
23	-	0.4	-	-	*	*	-	-	*	*	-	-
24	-	1.2	-	-	-	*	-	*	*	*	-	-
25	*	3.4	0.1	*	*	*	*	*	0.1	0.1	-	-
26	0.3	7.5	0.2	0.2	0.1	0.3	0.2	0.3	0.4	0.6	-	-
27	2.1	9.8	0.4	0.9	0.7	2.2	1.2	1.5	1.8	1.6	0.1	0.6
28	7.5	9.0	2.8	6.0	4.0	9.6	3.9	4.4	5.2	4.5	7.5	4.9
29	20.4	14.9	14.7	20.9	17.3	25.6	11.8	12.9	11.9	12.5	17.0	20.3
30	26.1	19.3	28.0	27.0	36.7	33.9	26.5	29.5	23.2	23.3	25.7	25.5
31	19.3	17.0	17.2	18.6	25.4	19.3	30.7	30.0	25.2	24.3	19.0	27.1
32	12.9	10.4	15.3	13.3	10.7	6.6	14.8	13.5	19.0	17.9	22.3	15.5
33	6.2	4.2	14.9	8.2	3.6	1.8	7.5	5.8	9.0	9.9	7.7	5.5
34	3.3	2.1	4.7	3.4	1.2	0.5	2.7	1.7	3.0	3.8	0.8	0.4
35	1.7	0.5	1.5	1.1	0.3	0.1	0.5	0.2	0.9	1.0	-	*
36	*	*	0.2	0.3	0.1	*	*	*	0.2	0.3	-	*
37	*	*	0.1	0.1	*	*	*	*	0.1	0.1	-	-
38	*	*	-	*	*	*	*	*	*	*	-	-
39	-	-	-	-	-	-	-	-	-	-	-	-
40 & Above	-	-	-	-	-	-	-	-	-	-	-	-
Average	30.88	29.85	31.42	31.00	30.82	30.33	31.17	31.00	31.23	31.27	31.01	30.91
Mike												
2.4 & Below	-	0.1	-	-	-	-	-	-	-	-	-	-
2.5	-	0.4	-	-	-	-	-	-	*	*	-	-
2.6	0.1	0.3	-	-	-	-	-	-	*	*	-	-
2.7	0.2	0.6	-	-	-	-	-	-	*	*	-	-
2.8	0.6	0.7	-	-	-	-	-	*	*	*	-	-
2.9	1.1	1.1	-	-	-	-	*	*	*	*	-	-
3.0	3.1	1.7	-	*	-	*	-	*	*	*	-	-
3.1	3.4	2.6	-	*	*	*	-	*	*	*	-	-
3.2	5.1	3.6	-	*	*	*	-	*	*	*	-	*
3.3	5.1	3.7	*	*	0.1	*	*	*	0.1	*	-	*
3.4	4.1	3.9	*	*	0.3	0.1	*	*	*	*	-	0.2
3.5	3.4	4.2	*	0.1	0.2	0.1	*	*	0.1	*	-	0.7
3.6	4.7	4.7	0.1	0.1	0.4	0.2	*	0.1	0.2	0.1	1.0	1.6
3.7	4.6	5.6	0.4	0.2	0.5	0.4	0.1	0.2	0.5	0.2	1.7	2.0
3.8	6.9	6.6	0.2	0.5	1.0	0.8	0.2	0.4	0.8	0.4	3.9	3.7
3.9	6.9	7.9	0.2	1.1	1.7	1.6	0.8	1.0	1.2	0.6	6.6	5.0
4.0	5.2	7.1	0.5	1.5	2.5	3.0	1.9	1.9	1.7	1.1	8.9	6.5
4.1	3.5	6.8	1.8	2.7	3.6	4.9	2.7	2.8	2.7	1.7	7.7	7.6
4.2	2.5	6.2	3.2	4.6	6.8	7.6	4.1	4.2	4.6	2.9	16.4	9.0
4.3	2.3	5.4	4.0	8.3	8.3	9.7	6.4	6.6	6.8	4.8	9.0	9.6
4.4	3.2	5.2	9.2	12.1	10.3	12.0	10.4	9.9	9.3	7.8	12.2	12.9
4.5	5.0	5.6	13.8	15.6	12.8	12.8	15.6	13.3	12.4	11.1	11.9	11.7
4.6	5.4	4.8	16.9	16.1	12.2	12.1	16.4	15.6	14.8	14.3	11.3	10.4
4.7	6.4	4.2	20.6	16.0	12.2	11.3	15.2	15.6	14.4	15.6	3.4	7.2
4.8	6.9	3.0	13.8	10.5	9.9	8.4	13.1	13.1	11.1	14.5	1.8	3.6
4.9	3.5	2.0	7.7	5.6	7.1	6.1	7.1	8.0	8.6	11.4	1.8	2.3
5.0	4.1	1.3	5.6	2.8	5.1	4.2	3.2	3.9	5.2	7.1	1.1	1.9
5.1	1.6	0.4	1.2	1.3	2.7	2.7	1.7	1.9	2.9	3.6	0.4	1.4
5.2	0.2	0.1	0.7	0.6	1.5	1.2	0.7	0.9	1.4	1.6	0.9	2.0
5.3	0.4	0.1	0.1	0.2	0.6	0.4	0.2	0.4	0.5	0.6	-	0.3
5.4	0.1	*	*	*	0.1	0.1	*	0.1	0.4	0.3	-	0.3
5.5 & Above	0.2	*	-	*	*	*	*	*	0.2	0.2	-	*
Average	4.03	3.97	4.63	4.56	4.55	4.52	4.58	4.59	4.60	4.66	4.30	4.36

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 05, 2019

Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter										
Bark - Level 1	6.4	3.9	2.6	1.5	0.3	0.3	12.7	5.6	0.6	0.6
Bark - Level 2	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	*	*	0.3	0.3	*	*	0.1	0.2	*	0.1
Grass - Level 2	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	-	-	*	-	*	*	*	-	*
Prep - Level 2	-	-	-	-	-	-	-	*	-	-
Seed Coat - Level 1	*	0.1	*	*	-	*	*	0.1	-	*
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	-	*	*	*	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	-	-	*	*	*	-	-
Other - Level 2	-	-	-	-	-	-	-	*	-	-
Plastic - Level 1	*	*	*	*	*	*	*	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	*	*	-	*	-	-	*	*	-	-
23	-	*	*	*	-	*	*	0.1	-	-
24	*	0.1	0.1	0.1	-	*	0.2	0.4	*	*
25	0.1	0.3	0.2	0.5	*	*	0.7	1.0	*	*
26	0.4	0.7	0.9	1.9	0.2	0.5	1.8	2.5	0.3	0.3
27	1.2	2.1	3.1	5.0	2.3	4.4	4.6	5.5	1.5	1.5
28	3.5	4.7	8.4	11.7	14.0	19.5	9.8	10.4	3.7	4.2
29	8.5	9.5	19.3	25.3	29.5	32.0	15.6	16.0	10.0	12.6
30	13.3	15.1	30.2	26.2	27.5	24.2	20.6	20.1	21.9	25.7
31	19.3	18.2	21.2	16.0	15.8	11.7	19.8	18.2	29.7	25.7
32	18.2	17.3	10.2	7.6	7.7	5.2	14.1	12.7	22.0	18.5
33	14.9	14.0	4.1	3.5	2.4	1.9	7.6	7.3	7.7	7.6
34	10.2	9.3	1.5	1.5	0.6	0.5	3.2	3.5	2.3	2.6
35	5.9	5.3	0.6	0.4	0.1	0.1	1.3	1.5	0.8	0.9
36	3.0	2.6	0.2	0.1	*	*	0.4	0.5	0.1	0.2
37	1.0	0.7	0.1	*	*	*	0.1	0.2	*	0.1
38	0.2	0.1	*	*	-	-	*	*	-	-
39	*	*	-	-	-	-	*	*	-	-
40 & Above	-	-	-	-	-	-	*	*	-	-
Average	32.21	31.94	30.60	30.22	30.21	29.89	30.78	30.64	31.32	31.20
Mike										
2.4 & Below	-	-	-	-	-	-	*	*	-	-
2.5	-	-	*	*	-	-	0.1	*	-	-
2.6	-	-	-	-	-	-	0.2	*	-	-
2.7	*	*	-	-	-	-	0.2	0.1	-	-
2.8	*	*	*	*	-	-	0.3	0.1	-	-
2.9	*	*	*	*	-	*	0.3	0.2	-	-
3.0	0.1	*	*	*	*	*	0.5	0.2	-	-
3.1	0.3	0.1	*	*	*	*	0.7	0.4	-	-
3.2	0.1	0.1	*	*	*	*	1.0	0.5	-	-
3.3	0.1	0.2	*	*	*	*	1.3	0.7	-	-
3.4	0.2	0.3	0.1	*	0.1	0.1	1.4	1.0	-	-
3.5	0.5	0.5	*	0.1	0.2	0.1	1.7	1.3	*	*
3.6	0.7	1.1	0.2	0.1	0.4	0.3	2.2	1.7	*	*
3.7	1.1	1.6	0.1	0.2	0.9	0.6	2.6	2.2	0.2	*
3.8	2.9	2.6	0.3	0.4	1.1	0.9	3.1	2.9	0.1	*
3.9	3.9	3.9	0.7	0.6	2.0	1.7	3.6	3.7	0.3	0.1
4.0	4.8	4.9	1.7	1.2	3.5	2.6	4.3	4.5	0.6	0.3
4.1	7.4	6.0	3.4	2.8	4.3	3.7	5.4	5.6	1.8	0.8
4.2	7.7	7.2	6.6	4.8	5.6	5.4	6.1	6.8	3.0	1.6
4.3	8.4	8.6	9.3	8.1	7.4	8.0	6.7	8.1	4.6	3.4
4.4	10.7	10.0	11.5	11.3	9.0	11.4	7.5	9.3	6.7	6.3
4.5	10.1	11.0	13.1	13.9	11.2	14.0	8.6	9.9	9.9	11.1
4.6	9.7	11.0	14.0	15.3	13.7	14.9	9.1	9.8	14.2	15.4
4.7	8.2	9.9	13.7	14.7	14.3	13.4	9.3	9.3	18.9	18.4
4.8	7.9	8.0	11.9	11.7	11.2	10.3	8.3	7.8	18.4	16.8
4.9	5.9	5.5	6.2	7.4	7.0	6.5	6.1	5.7	11.0	12.2
5.0	3.7	3.4	3.6	4.0	4.0	3.6	4.4	3.9	5.7	7.4
5.1	2.5	1.9	1.6	1.7	3.0	1.7	2.6	2.3	2.2	3.4
5.2	1.9	1.3	1.0	0.7	1.0	0.6	1.4	1.2	1.2	1.5
5.3	1.0	0.6	0.5	0.5	0.2	0.1	0.6	0.5	0.7	0.7
5.4	0.4	0.2	0.3	0.3	0.1	*	0.3	0.2	0.3	0.3
5.5 & Above	0.1	0.1	0.1	0.1	*	*	0.1	0.2	0.1	0.1
Average	4.46	4.45	4.56	4.58	4.54	4.53	4.37	4.40	4.67	4.70

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 05, 2019

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	*	*	-	-	-	-	*	*	-	*	*	*
2.7 - 2.9	*	*	*	*	*	*	-	0.1	-	*	*	*
3.0 - 3.2	0.2	0.1	*	*	0.5	0.1	0.6	0.8	-	*	*	*
3.3 - 3.4	0.4	0.3	*	0.1	0.7	0.2	0.3	0.9	*	*	0.1	0.1
3.5 - 3.6	1.3	1.4	0.4	0.3	1.8	0.9	1.1	2.6	*	*	0.2	0.4
3.7 - 4.2	31.7	32.4	21.3	20.3	15.8	14.6	28.5	28.1	2.8	6.1	10.1	12.1
4.3 - 4.9	62.7	63.1	69.9	73.8	63.0	68.6	61.7	58.3	90.0	88.7	82.0	81.1
5.0 - 5.2	3.6	2.5	7.3	4.9	13.6	12.6	6.5	6.2	7.1	5.1	7.2	6.0
5.3 & Above	0.1	0.2	1.1	0.5	4.6	2.9	1.2	2.9	*	0.1	0.3	0.4
Average	4.39	4.37	4.51	4.49	4.58	4.59	4.44	4.42	4.59	4.57	4.58	4.55
Leaf												
1 - 2	6.2	16.6	4.6	10.8	84.6	77.6	83.9	77.3	2.7	8.4	8.2	20.7
3	47.2	49.3	36.1	38.1	15.0	17.5	14.6	20.1	28.2	37.8	46.7	49.2
4	36.5	27.5	41.0	33.8	0.4	3.8	1.5	2.4	53.4	42.8	36.8	25.5
5	9.0	5.7	16.3	15.6	*	0.9	*	0.2	15.4	10.3	7.8	4.3
6	1.0	0.8	2.0	1.7	-	0.1	-	*	0.4	0.6	0.6	0.3
7	0.1	0.1	*	*	-	0.1	-	*	-	*	*	*
8	*	*	*	*	-	*	-	-	-	*	*	*
Average	3.52	3.24	3.75	3.59	1.86	1.99	1.86	1.97	3.83	3.57	3.45	3.13
HVI Trash 1/												
00	-	*	-	*	0.1	*	-	0.1	-	-	*	*
01	0.9	3.5	0.4	1.6	47.6	46.9	49.8	44.3	0.2	1.5	1.5	4.8
02	8.5	17.7	5.4	11.3	40.5	35.1	36.6	36.2	3.5	9.4	9.5	20.6
03	22.6	25.7	13.9	17.6	9.9	10.7	10.1	13.2	11.1	16.8	21.8	25.4
04	25.3	22.2	19.3	17.9	1.6	4.0	2.5	4.0	20.9	21.8	25.2	20.8
05	19.1	14.6	19.5	16.2	0.3	1.7	0.7	1.3	24.4	20.7	19.0	13.7
06	11.7	8.2	15.9	13.6	*	0.8	0.3	0.5	20.0	14.6	11.5	7.7
07	6.4	4.2	11.2	9.9	*	0.4	0.1	0.2	11.0	8.1	6.1	3.9
08	3.0	2.0	7.0	6.1	-	0.2	-	0.1	5.5	4.0	2.9	1.8
09	1.4	1.0	3.9	3.2	-	0.1	-	*	2.1	1.8	1.3	0.8
10	0.7	0.5	1.9	1.5	-	*	-	*	0.9	0.8	0.6	0.3
11	0.2	0.2	0.9	0.7	-	*	-	*	0.3	0.4	0.2	0.1
12	0.1	0.1	0.4	0.3	-	*	-	*	0.1	0.1	0.1	0.1
13	*	*	0.2	0.1	-	*	-	-	*	0.1	*	*
14	*	*	0.1	*	-	*	-	-	*	*	*	*
15	*	*	*	*	-	*	-	-	-	*	*	*
16	*	*	*	*	-	*	-	-	-	*	*	*
17	*	*	*	*	-	-	-	-	-	*	*	*
18 & Above	-	*	-	*	-	*	-	-	-	*	*	*
Average	0.45	0.39	0.53	0.49	0.17	0.18	0.17	0.18	0.52	0.47	0.44	0.37
UNIFORMITY 2/												
74 & Below	-	-	-	-	-	-	-	-	-	-	-	-
75	-	-	*	*	-	*	-	-	-	-	-	*
76	*	*	*	*	-	*	*	*	-	*	*	*
77	0.1	0.3	0.1	0.1	0.2	0.2	0.5	*	*	*	0.1	0.1
78	1.5	2.4	0.4	0.4	1.8	2.2	2.3	0.5	0.1	0.3	0.6	1.0
79	8.6	12.1	2.0	2.3	7.8	9.7	10.8	2.1	1.1	2.3	3.7	5.6
80	26.6	31.5	9.9	12.8	18.8	22.1	20.9	11.6	7.8	15.4	16.2	20.1
81	39.0	34.8	31.6	35.6	28.8	36.9	21.5	28.6	41.3	41.6	38.4	37.5
82	19.3	15.4	36.8	34.9	34.2	24.0	24.3	27.1	36.3	29.8	30.9	26.9
83	4.5	3.2	16.7	12.4	7.7	4.2	12.5	17.2	11.5	9.0	9.0	7.5
84	0.4	0.3	2.3	1.5	0.6	0.5	6.7	12.5	1.8	1.6	1.1	1.1
85 & Above	*	*	0.1	0.1	*	0.1	0.5	0.4	0.1	0.1	0.1	0.1
Average	81.26	81.04	82.07	81.91	81.55	81.30	81.63	82.28	82.00	81.77	81.71	81.55
Tenderable 3/	84.0	87.3	87.6	91.4	78.4	81.3	90.3	88.7	78.7	82.2	83.7	85.7
SAMPLES CLASSED	80,881	694,649	118,671	1,037,874	15,807	116,495	8,086	92,666	14,397	100,617	216,404	1,827,852

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 05, 2019

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	0.1	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	0.1	0.7	-	-	-	-	-	-	*	*	-	-
2.7 - 2.9	1.8	2.4	-	-	-	-	*	*	*	*	-	-
3.0 - 3.2	11.6	7.9	-	*	*	*	-	*	0.1	*	-	*
3.3 - 3.4	9.2	7.6	*	*	0.4	0.1	*	*	0.1	*	-	0.3
3.5 - 3.6	8.1	8.9	0.1	0.2	0.6	0.3	*	0.1	0.3	0.1	1.0	2.3
3.7 - 4.2	29.7	40.3	6.4	10.6	16.2	18.4	9.9	10.5	11.5	7.0	45.1	33.8
4.3 - 4.9	32.8	30.2	86.0	84.3	72.9	72.5	84.2	82.1	77.5	79.5	51.6	57.6
5.0 - 5.2	5.9	1.8	7.4	4.6	9.3	8.2	5.6	6.7	9.4	12.3	2.3	5.3
5.3 & Above	0.7	0.2	0.1	0.3	0.6	0.5	0.3	0.6	1.1	1.1	-	0.6
Average	4.03	3.97	4.63	4.56	4.55	4.52	4.58	4.59	4.60	4.66	4.30	4.36
Leaf												
1 - 2	47.0	30.7	13.3	22.0	5.4	11.6	8.0	19.6	9.3	11.7	70.7	78.7
3	31.2	22.3	40.0	43.2	37.6	39.5	35.6	41.3	53.9	50.4	24.7	19.1
4	16.5	16.0	36.5	26.1	40.8	33.7	40.2	28.9	32.1	32.3	3.9	2.0
5	4.5	12.6	9.1	7.6	14.8	13.8	14.0	8.8	4.4	5.2	0.7	0.2
6	0.6	8.6	1.0	1.0	1.4	1.4	1.9	1.2	0.2	0.3	-	-
7	0.1	5.3	0.1	*	*	*	0.2	0.1	*	*	-	-
8	0.1	4.5	*	*	-	-	*	*	*	*	-	-
Average	2.75	3.76	3.43	3.21	3.69	3.53	3.66	3.29	3.32	3.32	2.17	2.01
HVI Trash 1/												
00	-	-	-	-	-	*	-	*	-	-	-	-
01	16.3	11.3	4.4	4.7	0.4	1.6	1.4	5.0	0.8	1.6	27.6	34.4
02	33.8	21.5	10.9	22.1	5.6	10.6	8.1	18.2	10.9	12.4	43.3	43.9
03	17.2	11.8	16.9	21.6	14.1	18.0	14.4	20.4	26.0	24.1	17.2	14.8
04	12.0	8.9	20.0	17.2	18.5	18.6	18.7	18.1	27.1	25.2	7.0	4.7
05	9.0	7.0	17.9	13.1	19.2	16.6	18.9	14.2	18.6	18.2	2.6	1.5
06	5.2	5.4	13.3	9.0	16.6	13.4	15.2	10.1	9.9	10.3	1.3	0.4
07	2.9	5.1	8.4	5.6	12.1	9.6	10.4	6.5	4.3	4.9	0.7	0.2
08	1.7	4.3	4.2	3.2	7.0	5.9	6.3	3.8	1.6	2.1	0.2	*
09	0.8	4.0	2.1	1.7	3.6	3.2	3.5	2.0	0.6	0.8	0.1	*
10	0.5	3.7	1.1	0.9	1.7	1.5	1.8	1.0	0.2	0.3	-	-
11	0.2	3.2	0.5	0.4	0.7	0.6	0.8	0.5	*	0.1	-	-
12	0.1	2.8	0.2	0.2	0.3	0.3	0.3	0.2	*	*	-	-
13	0.1	2.3	*	0.1	0.1	0.1	0.1	0.1	*	*	-	-
14	0.1	1.9	*	*	*	*	*	*	*	*	-	-
15	*	1.5	*	*	*	*	*	*	-	*	-	-
16	-	1.2	*	*	*	*	*	*	*	*	-	-
17	*	0.9	*	*	-	*	*	*	*	*	-	-
18 & Above	*	3.1	*	*	-	*	*	*	*	*	-	-
Average	0.31	0.59	0.46	0.40	0.53	0.48	0.51	0.42	0.41	0.42	0.22	0.20
UNIFORMITY 2/												
74 & Below	*	*	-	-	-	-	-	-	-	-	-	-
75	0.1	*	-	-	-	-	*	*	*	*	-	-
76	1.0	0.3	-	-	*	*	*	*	*	*	-	-
77	1.4	0.7	*	*	*	*	0.1	0.1	0.1	0.1	-	-
78	2.4	1.7	0.2	0.3	0.1	0.2	1.0	0.7	0.7	0.6	0.1	0.2
79	13.5	12.2	1.1	2.1	0.3	0.8	4.8	4.0	4.9	4.4	5.2	1.4
80	32.1	35.8	9.0	14.3	2.9	5.8	20.1	19.2	22.0	19.4	21.7	5.3
81	40.2	39.9	36.3	37.9	19.1	25.6	44.1	45.3	38.9	37.4	17.4	20.9
82	8.6	8.7	41.3	32.6	46.6	43.2	25.4	26.1	26.6	29.9	28.1	52.4
83	0.6	0.6	10.7	10.9	27.2	21.5	4.0	4.2	6.1	7.2	25.5	19.2
84	0.1	0.1	1.2	1.7	3.5	2.7	0.4	0.4	0.7	0.8	1.8	0.5
85 & Above	*	*	0.1	0.2	0.3	0.2	*	*	*	0.1	0.1	0.1
Average	80.77	80.85	82.00	81.86	82.54	82.32	81.46	81.51	81.52	81.61	81.93	82.27
Tenderable 3/	57.2	46.3	82.8	90.6	87.5	89.2	89.1	89.5	84.7	82.5	92.8	91.7
SAMPLES CLASSED	13,412	57,136	32,125	458,980	69,757	529,824	128,567	1,131,232	100,759	804,639	1,625	10,940

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 05, 2019

Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE										
2.4 & Below	-	-	-	-	-	-	*	*	-	-
2.5 - 2.6	-	-	*	*	-	-	0.2	0.1	-	-
2.7 - 2.9	*	*	*	*	-	*	0.9	0.3	-	-
3.0 - 3.2	0.4	0.2	0.1	*	*	0.1	2.1	1.1	-	-
3.3 - 3.4	0.3	0.5	0.1	*	0.1	0.1	2.7	1.7	-	-
3.5 - 3.6	1.1	1.6	0.2	0.2	0.6	0.4	3.9	3.0	*	*
3.7 - 4.2	27.8	26.2	12.8	10.0	17.3	14.8	25.1	25.7	6.1	2.9
4.3 - 4.9	60.7	64.0	79.8	82.4	73.7	78.5	55.7	59.8	83.7	83.6
5.0 - 5.2	8.1	6.6	6.1	6.4	8.1	5.9	8.4	7.3	9.1	12.3
5.3 & Above	1.5	0.9	0.9	1.0	0.3	0.2	0.9	0.9	1.1	1.2
Average	4.46	4.45	4.56	4.58	4.54	4.53	4.37	4.40	4.67	4.70
Leaf										
1 - 2	54.0	66.2	9.1	15.6	9.4	16.0	38.3	50.6	16.7	24.7
3	31.9	24.8	57.9	56.4	44.0	43.5	43.4	36.7	63.6	60.2
4	8.9	6.6	29.8	25.0	34.2	29.9	13.9	10.4	18.0	14.1
5	3.2	1.7	2.9	2.8	11.1	9.3	3.2	1.9	1.5	1.0
6	1.1	0.5	0.2	0.1	1.3	1.3	0.9	0.3	0.1	*
7	0.7	0.2	*	*	*	*	0.3	0.1	-	-
8	0.2	0.1	*	*	*	*	*	*	-	-
Average	2.54	2.24	3.27	3.15	3.51	3.36	2.80	2.54	3.04	2.90
HVI Trash 1/										
00	*	0.1	-	*	-	*	*	*	-	-
01	23.4	36.0	0.7	2.0	0.6	2.8	12.3	20.2	1.3	3.4
02	34.2	33.8	11.2	16.7	9.5	14.6	31.7	34.0	16.6	23.7
03	20.3	15.1	28.0	28.7	19.6	21.0	25.6	21.8	32.3	33.0
04	9.7	6.9	28.5	24.6	20.8	19.5	14.8	12.0	27.3	22.7
05	4.8	3.6	17.7	14.9	17.8	15.5	7.6	6.2	13.6	10.6
06	2.8	1.9	8.4	7.5	12.6	11.0	3.7	3.0	5.6	4.2
07	1.6	1.0	3.3	3.4	8.4	7.1	1.9	1.4	2.1	1.5
08	1.0	0.6	1.3	1.3	5.1	4.1	1.0	0.7	0.8	0.6
09	0.7	0.3	0.6	0.6	2.8	2.2	0.5	0.3	0.2	0.2
10	0.5	0.2	0.2	0.2	1.5	1.1	0.3	0.2	0.1	0.1
11	0.4	0.2	0.1	0.1	0.7	0.6	0.2	0.1	*	*
12	0.2	0.1	*	*	0.3	0.3	0.1	*	*	*
13	0.2	0.1	*	*	0.2	0.1	0.1	*	-	*
14	0.1	*	*	*	0.1	0.1	*	*	-	*
15	0.1	*	*	*	*	*	*	*	*	*
16	*	*	*	*	*	*	*	*	-	*
17	*	*	-	*	*	*	*	*	-	-
18 & Above	*	*	*	*	*	*	*	*	-	-
Average	0.27	0.23	0.40	0.38	0.48	0.44	0.31	0.27	0.37	0.34
UNIFORMITY 2/										
74 & Below	*	*	-	-	-	-	*	*	-	-
75	*	0.1	*	*	-	-	0.1	0.1	-	-
76	0.2	0.3	*	0.1	*	*	0.7	0.5	*	*
77	0.7	1.4	0.2	0.3	*	0.1	2.8	2.3	*	0.1
78	3.5	4.5	1.0	1.6	0.3	0.5	9.1	7.3	0.2	0.2
79	9.6	12.3	5.6	8.4	3.0	5.2	23.1	18.3	1.2	1.3
80	27.2	26.5	29.3	31.8	16.9	22.6	33.4	30.0	8.0	9.2
81	35.7	33.2	41.5	40.4	36.6	36.2	22.1	27.2	32.6	34.2
82	18.8	18.2	18.8	14.9	31.4	26.6	7.2	11.9	43.7	38.9
83	3.9	3.1	3.3	2.3	10.9	8.0	1.2	2.1	12.5	13.5
84	0.4	0.3	0.3	0.2	0.7	0.8	0.1	0.2	1.6	2.4
85 & Above	*	0.1	*	*	*	0.1	*	*	0.1	0.2
Average	81.12	80.98	81.27	81.10	81.76	81.55	80.32	80.61	82.08	82.06
Tenderable 3/	80.4	85.3	87.1	87.6	88.1	90.6	57.3	71.7	86.2	84.9
SAMPLES CLASSED	37,913	216,022	35,063	293,157	92,685	696,832	508,107	4,566,270	24,048	155,161

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 05, 2019

Color Grade	Leaf	Arizona		California		New Mexico		Texas	
		Week	Season	Week	Season	Week	Season	Week	Season
01	1	69.1	44.9	23.8	25.2	-	-	8.6	9.1
	2	3.4	9.1	7.6	7.3	-	-	14.1	13.7
	3	-	3.5	*	*	-	-	0.6	0.2
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		72.5	57.5	31.4	32.6	-	-	23.4	23.1
02	1	23.6	23.9	29.8	32.1	-	-	26.3	17.9
	2	3.8	9.4	35.6	32.0	-	-	41.1	45.0
	3	-	5.7	1.2	1.0	-	-	5.7	3.9
	4	-	2.6	-	*	-	-	0.1	*
	5	-	0.1	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		27.4	41.5	66.6	65.2	-	-	73.2	66.9
03	1	-	0.1	0.2	0.3	-	-	0.6	1.5
	2	0.2	0.1	1.1	1.4	-	-	1.4	6.8
	3	-	0.2	0.6	0.5	-	-	1.3	1.6
	4	-	0.4	*	*	-	-	-	*
	5	-	*	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		0.2	0.8	1.9	2.2	-	-	3.3	9.9
04	1	-	-	*	*	-	-	-	-
	2	-	-	*	*	-	-	-	*
	3	-	*	*	*	-	-	-	0.1
	4	-	0.1	-	*	-	-	-	-
	5	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	0.2	*	0.1	-	-	-	0.1
05	1	-	-	-	-	-	-	-	-
	2	-	-	*	*	-	-	-	*
	3	-	-	*	*	-	-	0.1	0.1
	4	-	-	*	*	-	-	-	-
	5	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	*	-	-	-	-
Total -----		-	-	*	*	-	-	0.1	0.1
06	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	-	-	-	-	-	-
07	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	-	-	-	-	-	-
STAPLE									
44 & Shorter		-	1.0	0.5	0.5	-	-	0.1	1.2
46		0.8	21.2	10.4	8.2	-	-	2.1	9.1
48		86.6	58.5	22.5	27.5	-	-	57.2	64.5
50		12.3	19.2	60.2	59.3	-	-	39.2	22.0
52 & Longer		0.3	0.1	6.4	4.4	-	-	1.5	3.3
Average Staple		48.24	47.93	49.23	49.18	-	-	48.80	48.34
Average Length		1.41	1.40	1.43	1.43	-	-	1.42	1.40
EXTRANEIOUS MATTER									
Bark		-	-	0.2	*	-	-	-	0.7
Grass		-	-	0.1	*	-	-	-	0.1
Spindle Twist		-	-	*	*	-	-	0.2	*
Preparation		-	-	*	*	-	-	-	-
All Other		-	0.1	*	*	-	-	0.1	0.1

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 05, 2019

Quality Designation	Arizona		California		New Mexico		Texas	
	Week	Season	Week	Season	Week	Season	Week	Season
MIKE								
2.4 & Below	-	-	-	-	-	-	-	-
2.5 - 2.6	-	-	-	-	-	-	-	-
2.7 - 2.9	0.1	*	0.1	*	-	-	-	-
3.0 - 3.2	2.2	2.7	0.2	0.2	-	-	-	0.1
3.3 - 3.4	7.7	11.1	0.7	0.6	-	-	1.5	0.9
3.5 - 3.6	9.0	14.2	1.9	2.2	-	-	6.1	7.1
3.7 - 4.2	78.2	71.1	64.6	60.8	-	-	60.8	75.9
4.3 - 4.9	2.8	0.9	32.5	36.2	-	-	31.6	16.1
5.0 - 5.2	-	-	-	*	-	-	-	-
5.3 & Above	-	-	-	-	-	-	-	-
Average	3.81	3.75	4.12	4.14	-	-	4.06	3.97
ALL RANGE MIKE								
2.4 & Below	-	-	-	-	-	-	-	-
2.5	-	-	-	-	-	-	-	-
2.6	-	-	-	-	-	-	-	-
2.7	-	-	*	*	-	-	-	-
2.8	-	-	*	*	-	-	-	-
2.9	0.1	*	0.1	*	-	-	-	-
3.0	-	-	*	*	-	-	-	*
3.1	2.1	1.7	0.1	*	-	-	-	-
3.2	0.1	0.9	0.1	0.1	-	-	-	0.1
3.3	0.3	3.6	0.2	0.2	-	-	0.1	0.2
3.4	7.3	7.5	0.5	0.5	-	-	1.5	0.7
3.5	4.5	7.0	0.5	0.7	-	-	2.9	1.5
3.6	4.5	7.1	1.4	1.6	-	-	3.2	5.5
3.7	16.3	16.4	2.6	2.9	-	-	5.2	10.4
3.8	22.3	16.2	7.1	6.5	-	-	9.2	15.7
3.9	14.6	18.7	11.5	10.1	-	-	14.3	16.3
4.0	10.7	12.3	14.7	12.3	-	-	19.6	14.7
4.1	11.7	6.1	14.4	14.0	-	-	8.3	11.6
4.2	2.7	1.4	14.2	15.0	-	-	4.1	7.2
4.3	2.6	0.9	14.7	14.1	-	-	8.3	7.8
4.4	0.2	0.1	10.4	12.1	-	-	14.0	6.1
4.5	-	-	4.6	6.6	-	-	8.8	1.9
4.6	-	-	2.3	2.4	-	-	0.4	0.2
4.7	-	-	0.5	0.7	-	-	-	*
4.8	-	-	0.1	0.1	-	-	0.1	*
4.9	-	-	*	*	-	-	-	-
5.0	-	-	-	*	-	-	-	-
5.1	-	-	-	-	-	-	-	-
5.2	-	-	-	-	-	-	-	-
5.3 & Above	-	-	-	-	-	-	-	-
Average	3.81	3.75	4.12	4.14	-	-	4.06	3.97
STRENGTH 1/ 36 & Below	-	*	*	*	-	-	-	0.1
37	-	0.1	*	0.1	-	-	-	0.7
38	0.1	0.1	1.0	1.6	-	-	0.4	0.7
39	0.3	0.4	3.0	3.8	-	-	1.3	1.6
40	0.9	2.1	4.8	3.7	-	-	1.4	2.4
41	10.3	11.2	3.4	2.7	-	-	11.1	10.3
42	27.2	23.4	4.3	4.9	-	-	14.5	12.5
43	24.3	36.1	8.9	10.3	-	-	13.4	16.7
44	18.6	17.1	17.8	19.1	-	-	18.5	22.2
45	9.5	6.3	23.5	25.2	-	-	23.2	19.4
46	6.9	2.4	18.4	17.8	-	-	13.3	10.4
47	1.5	0.5	10.4	7.9	-	-	1.6	2.3
48 & Above	0.4	0.2	4.5	3.0	-	-	1.2	0.6
Average	43.61	43.32	44.87	44.70	-	-	44.11	43.92
UNIFORMITY								
83 & Below	0.8	0.4	0.6	0.3	-	-	0.2	0.8
84	4.9	5.5	6.7	5.1	-	-	0.7	1.5
85	52.8	41.1	16.8	15.6	-	-	11.1	22.8
86	37.8	48.3	53.7	53.5	-	-	67.2	61.7
87	3.4	4.5	20.7	24.0	-	-	20.4	12.8
88 & Above	0.3	0.1	1.5	1.5	-	-	0.5	0.4
Average	85.87	85.96	86.36	86.45	-	-	86.49	86.30
Samples Classed	1,144	3,632	39,919	268,181	-	-	1,705	9,572

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.