



Volume 21, No.28

State	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
AL	6	84.2	71.9	11,770	29	86.0	73.6	975,145
AR	3	82.1	53.6	9,359	29	89.7	75.1	1,435,031
AZ	11	67.9	51.0	19,434	12	76.6	56.1	307,425
CA*	-	-	-	-	17	87.6	76.1	181,585
FL	2	76.1	70.2	1,450	4	82.9	65.8	157,550
GA	22	80.2	62.3	11,053	59	84.9	66.1	2,707,768
KS	3	44.6	24.4	13,012	3	54.7	34.9	192,178
LA	4	92.7	81.1	2,668	19	89.3	70.3	580,742
MO	2	67.6	39.2	1,687	21	89.5	74.0	827,338
MS	11	86.4	50.1	5,247	38	88.4	65.9	1,535,904
NC	9	80.7	69.8	6,396	34	83.5	59.4	1,057,998
NM	-	-	-	-	3	85.4	67.2	31,309
OK	8	83.2	67.5	10,463	12	77.5	59.9	492,364
SC	6	91.0	68.2	2,425	15	87.5	67.2	418,894
TN	-	-	-	-	22	89.4	71.1	938,993
TX	19	50.3	28.8	19,250	187	66.0	39.2	6,279,311
VA*	-	-	-	-	4	86.2	59.7	225,227
United States	108	69.8	51.2	121,233	508	79.1	57.7	18,344,762
AMERICAN PIMA								
AZ*	-			-	3			12,610
CA	7			24,256	17			553,860
NM*	-			-	-			-
TX*	-			-	3			15,020
United States	8			24,265	24			591,415
United States all cotton	116			145,498	520			18,936,177

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Feb 06, 2020

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	3.7	8.4	0.6	4.8	14.5	43.9	-	46.9	-	3.4	7.9	8.9
	3	3.9	8.9	0.3	4.4	1.3	4.7	-	5.0	-	3.0	2.8	6.5
	4	0.1	0.7	-	0.2	*	0.2	-	0.2	-	0.2	0.1	0.3
	5	-	*	-	*	-	*	-	*	-	-	-	*
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	7.7	18.0	0.9	9.4	15.8	48.8	-	52.1	-	6.6	10.8	15.7
31	1 - 2	0.6	2.2	7.8	3.4	7.9	9.5	-	13.8	0.1	1.5	2.1	3.6
	3	6.7	12.9	35.1	18.3	9.7	8.3	-	12.2	3.7	8.9	8.9	12.4
	4	1.6	5.6	8.5	8.3	2.2	1.7	-	1.6	5.3	3.5	3.9	4.2
	5	0.3	0.5	0.4	0.8	*	0.2	-	0.1	0.3	0.3	0.4	0.3
	6	*	*	-	*	-	*	-	*	-	*	-	*
	7	-	*	-	-	-	*	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	9.2	21.3	51.8	30.9	19.8	19.6	-	27.7	9.4	14.1	15.3	20.6
41	1 - 2	0.7	1.6	0.3	0.7	4.4	2.7	-	2.6	-	0.8	1.5	2.1
	3	21.8	16.5	12.7	12.8	14.3	6.9	-	8.5	12.5	16.7	16.2	18.1
	4	24.6	14.7	20.8	22.9	12.3	4.6	-	3.7	37.1	26.0	16.4	16.3
	5	4.2	3.3	7.2	12.3	4.3	1.4	-	0.4	10.1	5.7	3.5	3.4
	6	0.1	0.3	0.1	1.4	0.8	0.4	-	*	0.2	0.3	0.1	0.2
	7	-	*	-	*	*	0.1	-	*	-	*	-	*
	8	-	*	-	-	-	*	-	-	-	-	-	-
Total	----	51.4	36.4	41.1	50.1	36.2	16.0	-	15.2	59.9	49.4	37.8	40.1
51	1 - 2	1.1	0.7	*	0.1	2.3	0.7	-	0.1	-	0.4	2.1	0.9
	3	7.2	6.1	0.4	1.4	4.7	2.0	-	0.3	0.4	7.1	12.5	7.3
	4	4.1	5.6	1.9	3.6	4.4	2.2	-	0.2	8.9	11.4	9.2	6.0
	5	7.4	1.7	1.1	2.6	3.6	1.5	-	0.1	8.8	4.1	3.0	1.4
	6	7.1	0.4	*	0.4	1.6	0.8	-	0.1	0.7	0.3	0.4	0.1
	7	-	*	*	*	0.4	0.3	-	*	-	*	*	*
	8	-	*	-	*	0.1	0.1	-	*	-	-	-	*
Total	----	26.9	14.5	3.5	8.1	17.1	7.6	-	0.8	18.8	23.3	27.2	15.7
61	1 - 2	-	*	-	-	0.1	*	-	*	-	*	0.1	*
	3	0.1	0.1	-	*	0.1	*	-	*	-	0.1	1.0	0.1
	4	*	*	-	*	*	*	-	*	-	0.2	0.1	*
	5	-	*	-	*	0.1	*	-	-	-	0.1	*	*
	6	-	*	-	*	0.1	*	-	-	-	*	-	*
	7	-	*	-	-	*	*	-	-	-	-	-	*
	8	-	*	-	-	*	*	-	-	-	-	-	*
Total	----	0.1	0.1	-	*	0.5	0.1	-	*	-	0.4	1.1	0.2
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	*
	3	-	-	-	*	-	-	-	-	-	-	-	*
	4	-	*	-	-	-	*	-	-	-	-	-	*
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	*
	7	-	*	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	*	-	-	-	*	-	*
Total	----	-	*	-	*	-	*	-	-	-	*	-	*
12 & 22	1 - 2	0.3	0.2	0.2	*	0.2	1.3	-	0.1	-	*	0.1	0.4
	3	0.3	0.4	0.1	*	*	1.2	-	0.1	-	*	0.1	0.2
	4	-	0.1	-	*	-	0.2	-	*	-	*	*	*
	5	-	*	-	-	-	*	-	*	-	-	-	-
	6	-	-	-	-	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.6	0.7	0.3	0.1	0.2	2.6	-	0.2	-	0.1	0.2	0.6
32	1 - 2	0.1	0.1	0.1	*	0.4	0.5	-	0.3	-	*	0.2	0.3
	3	1.4	0.9	0.8	0.2	0.6	1.0	-	0.7	0.1	0.3	0.2	1.0
	4	0.6	0.6	0.3	0.2	0.4	0.5	-	0.3	0.4	0.2	0.2	0.3
	5	*	0.1	*	*	*	0.1	-	0.1	-	*	*	*
	6	-	*	-	*	-	*	-	*	-	*	-	*
	7	-	*	-	-	-	*	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	2.2	1.8	1.2	0.5	1.4	2.1	-	1.3	0.6	0.6	0.6	1.5
42	1 - 2	-	0.2	-	*	0.1	0.1	-	*	-	0.1	0.3	0.2
	3	0.3	1.7	0.1	0.2	0.6	0.6	-	0.5	0.3	0.8	1.4	1.4
	4	0.8	1.8	0.3	0.3	1.9	0.8	-	0.8	4.7	1.4	0.6	1.2
	5	0.1	0.6	0.2	0.1	2.2	0.4	-	0.3	2.3	0.4	0.1	0.2
	6	-	0.1	-	*	0.6	0.2	-	0.1	0.1	*	-	*
	7	-	*	-	-	*	*	-	*	-	*	-	*
	8	-	*	-	-	*	*	-	-	-	-	-	-
Total	----	1.2	4.3	0.6	0.7	5.5	2.1	-	1.7	7.4	2.7	2.4	3.0

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Feb 06, 2020

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	0.1	0.1	-	*	-	*	-	*	-	0.1	0.2	0.1
	3	*	0.8	*	*	0.1	0.1	-	0.1	0.1	0.7	0.8	0.9
	4	0.1	0.9	*	*	0.3	0.1	-	0.2	0.9	1.1	0.6	0.7
	5	*	0.2	0.1	*	0.2	0.1	-	0.3	1.3	0.5	0.3	0.2
	6	-	*	*	*	0.1	*	-	0.2	0.2	0.1	*	*
	7	-	*	-	-	0.1	*	-	0.1	-	*	-	*
	8	-	*	-	-	0.7	0.1	-	*	-	*	-	*
Total	----	0.2	2.1	0.1	0.1	1.6	0.3	-	0.9	2.5	2.5	1.9	2.0
62	1 - 2	-	*	-	*	-	-	-	-	-	*	*	*
	3	*	*	-	*	-	-	-	*	-	*	*	*
	4	*	*	-	*	*	*	-	*	-	0.1	*	*
	5	-	*	*	*	*	*	-	*	-	*	*	*
	6	-	*	-	*	*	*	-	-	-	*	-	*
	7	-	*	-	-	-	-	-	*	-	*	-	*
	8	-	*	-	-	0.2	*	-	*	-	*	-	*
Total	----	*	0.1	*	*	0.2	*	-	*	-	0.1	0.1	0.1
13 & 23	1 - 2	*	*	-	*	*	*	-	*	-	-	*	*
	3	*	*	-	*	*	*	-	*	-	-	*	*
	4	-	*	-	*	-	*	-	-	-	*	-	*
	5	-	*	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	-	*	*	0.1	-	*	-	*	0.1	*
33	1 - 2	-	*	*	*	0.1	0.1	-	*	-	-	0.1	*
	3	0.1	*	0.2	*	0.1	0.2	-	*	-	*	0.3	*
	4	0.1	*	0.1	*	*	*	-	*	-	*	0.1	*
	5	*	*	*	*	-	*	-	*	-	*	-	*
	6	-	*	-	-	-	*	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.3	0.1	0.3	*	0.2	0.3	-	*	-	*	0.4	0.1
43	1 - 2	-	*	-	*	*	*	-	*	-	-	0.2	*
	3	0.1	0.1	*	*	0.1	0.1	-	*	0.1	*	0.8	0.1
	4	0.1	0.2	0.1	0.1	0.4	0.1	-	*	0.2	0.1	0.3	0.1
	5	*	0.1	*	*	0.5	*	-	*	0.3	*	0.1	*
	6	-	*	-	*	0.1	*	-	*	0.1	*	-	*
	7	-	*	-	*	*	*	-	-	-	*	-	*
	8	-	*	-	-	-	*	-	-	-	-	-	-
Total	----	0.1	0.4	0.1	0.1	1.2	0.2	-	*	0.6	0.1	1.3	0.2
53	1 - 2	0.1	*	-	-	-	-	-	-	-	-	*	*
	3	*	*	-	*	-	*	-	*	-	*	0.1	*
	4	*	*	-	*	*	*	-	*	0.2	*	0.2	0.1
	5	*	*	*	*	*	*	-	*	0.3	*	0.1	*
	6	-	*	-	*	0.1	*	-	*	0.3	*	*	*
	7	-	*	-	*	*	*	-	*	-	-	-	*
	8	-	*	-	-	-	*	-	*	-	-	-	-
Total	----	0.1	0.1	*	*	0.1	*	-	*	0.8	0.1	0.4	0.1
63	1 - 2	0.1	*	-	-	-	-	-	-	-	-	-	*
	3	-	*	-	*	-	-	-	*	-	*	-	*
	4	-	*	-	*	-	*	-	-	-	*	*	*
	5	-	*	-	-	-	-	-	-	-	-	-	*
	6	-	*	-	-	-	-	-	-	-	*	-	*
	7	-	*	-	*	*	*	-	-	-	*	-	*
	8	-	*	-	-	*	*	-	-	-	*	-	*
Total	----	0.1	*	-	*	*	*	-	*	-	*	*	*
24 - 54	1 - 8	*	*	*	*	0.1	0.1	-	*	-	*	0.3	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	*	*	*	-	*	-	*	-	-	*	*
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	-	-	-	-	*	-	-	-	-	-	*
31		-	*	-	*	-	*	-	*	-	*	0.1	*
32		0.2	0.4	-	*	0.1	0.1	-	*	-	*	1.1	0.5
33		0.8	2.0	-	*	0.6	0.6	-	0.1	0.1	0.6	6.3	2.4
34		1.3	6.8	0.2	0.1	1.6	2.6	-	1.3	1.1	2.5	12.7	7.4
35		5.2	13.1	6.2	1.9	10.8	8.6	-	4.3	3.4	5.3	19.3	15.4
36		33.2	22.9	31.5	11.5	22.2	19.4	-	13.6	31.0	12.6	20.4	21.2
37		42.0	32.4	44.0	40.1	31.1	30.9	-	30.1	32.3	32.9	19.3	29.0
38		11.1	15.0	12.8	25.5	21.3	20.8	-	27.2	30.7	33.8	14.2	16.8
39		5.7	6.3	5.1	16.4	8.9	12.9	-	19.5	1.4	11.0	6.1	6.5
40 & Longer		0.7	1.1	0.2	4.5	3.4	4.2	-	3.8	0.1	1.2	0.6	0.8
Average Staple		36.73	36.51	36.79	37.56	36.98	37.13	-	37.51	36.92	37.26	36.00	36.46
Average Length		1.14	1.14	1.15	1.17	1.15	1.16	-	1.17	1.15	1.16	1.12	1.14

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Feb 06, 2020

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	10.8	19.2	1.0	15.2	0.6	2.7	8.8	13.6	1.4	4.6	-	38.4
	3	9.7	7.6	0.6	13.5	0.2	1.3	3.0	11.5	1.7	4.9	-	4.0
	4	0.4	0.3	*	0.7	-	*	0.1	1.3	*	0.3	-	*
	5	-	*	-	*	-	*	-	*	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	*	-	-	-	-
Total	----	20.8	27.1	1.6	29.5	0.8	4.0	11.9	26.4	3.1	9.8	-	42.4
31	1 - 2	2.5	3.2	1.1	2.4	10.2	5.8	23.1	2.9	1.7	3.6	-	14.0
	3	10.5	13.9	5.1	14.1	11.7	19.2	22.7	13.8	22.8	19.4	-	18.5
	4	8.1	9.4	2.0	6.5	0.1	7.1	1.8	7.3	5.2	8.5	-	3.3
	5	1.1	1.6	0.1	0.5	-	0.7	-	0.8	*	0.8	-	0.2
	6	*	0.1	-	*	-	*	-	*	-	*	-	-
	7	-	*	-	*	-	-	-	*	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-	-	-
Total	----	22.2	28.2	8.3	23.5	21.9	32.8	47.6	24.9	29.7	32.4	-	36.0
41	1 - 2	-	*	1.5	0.6	7.2	1.7	2.6	1.0	2.4	2.8	-	0.3
	3	0.2	0.2	19.2	9.5	31.4	18.0	12.6	11.1	32.4	25.6	-	1.9
	4	2.2	1.1	30.8	14.7	7.1	24.8	8.4	15.7	12.2	19.5	-	2.0
	5	2.8	1.6	3.9	4.7	0.2	11.0	0.2	5.5	1.2	3.2	-	0.7
	6	0.5	0.5	*	0.4	-	1.2	-	0.6	0.1	0.2	-	0.1
	7	*	0.2	-	*	-	*	-	*	-	*	-	-
	8	-	*	-	-	-	-	-	*	-	-	-	-
Total	----	5.6	3.4	55.3	29.8	45.9	56.7	23.9	33.9	48.3	51.3	-	5.0
51	1 - 2	-	-	-	*	-	0.1	2.1	0.2	0.4	0.1	-	*
	3	-	-	7.1	2.4	3.9	0.8	7.2	2.7	4.0	1.1	-	*
	4	-	*	18.9	5.9	21.0	2.6	2.9	5.5	4.2	1.8	-	*
	5	*	*	3.9	2.7	3.6	1.8	0.6	2.7	0.2	0.6	-	*
	6	-	*	0.2	0.4	0.1	0.4	*	0.5	*	0.1	-	*
	7	-	0.1	-	*	-	*	-	*	-	*	-	-
	8	-	0.1	-	*	-	*	-	*	-	*	-	-
Total	----	*	0.2	30.0	11.4	28.5	5.6	12.8	11.7	8.8	3.6	-	*
61	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	*	-	*	-	-	-	-
	4	-	-	-	0.1	-	*	-	*	-	*	-	-
	5	-	-	-	0.1	-	*	-	*	-	-	-	-
	6	-	-	-	*	-	*	-	*	-	-	-	-
	7	-	-	-	*	-	*	-	*	-	*	-	-
	8	-	-	-	-	-	*	-	*	-	*	-	-
Total	----	-	-	-	0.2	-	*	-	*	-	*	-	-
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	*	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	*	-	-	-	-
	8	-	-	-	-	-	*	-	-	-	-	-	-
Total	----	-	-	-	-	-	*	-	*	-	-	-	-
12 & 22	1 - 2	12.6	11.4	-	0.4	-	*	-	0.1	0.1	*	-	2.8
	3	5.9	3.9	-	0.5	-	*	*	0.2	0.1	0.1	-	1.9
	4	0.2	0.2	-	0.1	-	-	-	0.1	*	*	-	0.1
	5	*	*	-	*	-	-	-	*	-	*	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	18.7	15.5	-	1.0	-	*	*	0.4	0.2	0.1	-	4.8
32	1 - 2	0.5	0.3	0.1	0.1	0.2	*	-	0.1	0.2	0.1	-	1.1
	3	3.2	2.1	0.6	0.6	0.3	0.1	0.4	0.3	1.6	0.5	-	4.5
	4	3.5	3.2	0.1	0.3	-	0.1	0.1	0.3	0.5	0.3	-	1.7
	5	2.2	1.5	-	*	-	*	*	0.1	*	*	-	0.2
	6	0.2	0.2	-	*	-	*	-	*	-	*	-	*
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	9.6	7.4	0.8	1.0	0.5	0.2	0.5	0.7	2.3	0.9	-	7.5
42	1 - 2	-	*	-	0.1	0.1	*	*	*	0.2	*	-	*
	3	*	*	0.4	0.8	0.1	0.1	0.1	0.2	3.1	0.6	-	0.2
	4	0.2	0.3	0.5	1.1	0.5	0.2	0.1	0.6	1.2	0.8	-	0.3
	5	1.2	1.0	0.1	0.4	0.3	0.1	0.1	0.4	0.1	0.2	-	0.3
	6	0.5	0.8	-	0.1	-	*	-	*	-	*	-	0.1
	7	0.1	0.3	-	*	-	*	-	*	-	*	-	0.1
	8	-	0.1	-	-	-	-	-	*	-	-	-	*
Total	----	2.1	2.5	1.0	2.4	1.0	0.4	0.4	1.3	4.6	1.5	-	1.0

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Feb 06, 2020

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	-	*	-	*	-	*	*	*	-	-
	3	-	-	0.1	0.2	0.2	*	0.3	0.1	0.5	*	-	*
	4	-	*	0.3	0.3	0.4	*	0.8	0.2	0.3	*	-	*
	5	-	*	0.1	0.1	0.1	*	*	0.1	*	*	-	0.1
	6	-	0.1	*	*	-	*	-	*	-	*	-	*
	7	-	0.1	-	*	-	*	-	*	-	*	-	-
	8	-	0.1	-	*	-	*	-	*	-	*	-	-
Total	----	-	0.3	0.5	0.7	0.7	0.1	1.2	0.3	0.8	0.1	-	0.1
62	1 - 2	-	-	-	-	-	-	-	*	-	-	-	-
	3	-	-	-	*	-	*	*	*	-	-	-	-
	4	-	*	-	*	-	*	0.1	*	-	*	-	-
	5	-	*	-	*	-	*	*	*	-	-	-	-
	6	-	-	-	*	-	*	-	*	-	*	-	-
	7	-	*	-	*	-	-	-	*	-	-	-	-
	8	-	-	-	-	-	*	-	-	-	-	-	-
Total	----	-	*	-	*	-	*	0.1	*	-	*	-	-
13 & 23	1 - 2	9.8	3.8	-	*	-	-	-	*	*	*	-	0.4
	3	4.2	2.0	0.1	*	-	-	*	*	*	*	-	0.2
	4	0.2	0.2	-	*	-	-	-	*	-	-	-	*
	5	*	*	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	*	-	-	-	-
Total	----	14.2	6.0	0.1	*	-	-	*	*	*	*	-	0.6
33	1 - 2	0.8	0.2	-	*	-	*	-	*	0.1	*	-	0.5
	3	1.4	0.8	0.3	0.1	0.1	*	0.2	*	1.0	0.1	-	1.2
	4	1.2	0.9	-	*	-	*	0.1	*	0.3	*	-	0.3
	5	1.1	0.6	-	*	-	*	*	*	-	*	-	*
	6	0.1	0.2	-	*	-	-	-	*	-	*	-	-
	7	*	*	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	----	4.6	2.7	0.3	0.1	0.1	*	0.3	0.1	1.3	0.1	-	2.0
43	1 - 2	-	*	-	*	-	*	-	*	*	*	-	-
	3	-	*	0.2	0.1	0.1	*	0.1	*	0.4	0.1	-	*
	4	*	0.3	1.0	0.1	0.4	0.1	0.4	0.1	0.2	0.1	-	*
	5	0.1	0.6	0.1	*	-	*	0.1	*	-	*	-	0.1
	6	*	0.6	-	*	-	*	-	*	-	*	-	*
	7	-	0.3	-	-	-	-	-	*	-	-	-	*
	8	-	0.2	-	-	-	-	-	*	-	-	-	*
Total	----	0.2	2.1	1.4	0.3	0.5	0.1	0.6	0.1	0.6	0.2	-	0.2
53	1 - 2	-	-	-	-	-	-	-	*	-	*	-	-
	3	-	-	-	*	-	*	*	*	*	*	-	-
	4	-	0.1	0.3	*	0.1	*	0.3	*	0.1	*	-	-
	5	-	0.1	*	*	-	*	-	*	*	*	-	-
	6	-	0.3	-	*	0.1	*	-	*	*	*	-	-
	7	-	0.4	-	*	-	-	-	*	-	*	-	-
	8	-	0.3	-	-	-	-	-	*	-	*	-	*
Total	----	-	1.1	0.3	0.1	0.2	*	0.3	*	0.2	*	-	*
63	1 - 2	-	-	-	-	-	*	-	*	-	-	-	-
	3	-	-	-	-	-	*	-	*	-	-	-	-
	4	-	*	-	-	-	*	0.2	*	-	-	-	-
	5	-	*	-	-	-	*	0.1	*	-	*	-	-
	6	-	*	-	-	-	*	-	*	-	-	-	-
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	*	-	-	-	-	-	-
Total	----	-	*	-	-	-	*	0.3	*	-	*	-	-
24 - 54	1 - 8	1.9	2.3	0.3	*	-	*	0.1	*	-	*	-	0.4
25 - 35	1 - 8	-	*	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	1.0	-	*	-	*	-	*	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	*	-	-	-	-	-	-	-	-	-	-
30		-	*	-	-	-	-	-	-	-	-	-	-
31		-	*	-	-	-	*	-	-	-	*	-	-
32		-	0.1	-	*	-	*	-	*	*	0.1	-	-
33		0.2	0.7	-	*	-	*	-	*	0.4	0.4	-	*
34		4.8	4.8	-	0.3	-	0.3	1.1	0.7	5.3	2.6	-	0.3
35		18.8	20.6	-	1.7	2.7	3.1	14.2	3.6	17.5	10.8	-	3.1
36		36.0	38.9	3.5	8.2	16.0	15.3	23.7	11.9	24.7	27.3	-	12.9
37		34.7	29.6	11.5	22.3	62.6	44.0	16.8	27.9	24.2	33.7	-	35.6
38		5.2	4.5	23.4	30.8	16.2	21.5	26.9	33.9	22.0	16.7	-	26.2
39		0.3	0.5	38.3	26.1	2.4	11.5	14.7	19.5	5.5	7.2	-	17.3
40 & Longer		*	0.3	23.3	10.5	0.1	4.3	2.6	2.6	0.5	1.2	-	4.6
Average Staple		36.17	36.09	38.68	38.04	37.00	37.35	37.09	37.60	36.57	36.76	-	37.56
Average Length		1.13	1.12	1.21	1.19	1.16	1.17	1.16	1.18	1.14	1.15	-	1.17

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Feb 06, 2020

Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	37.6	41.5	1.4	6.1	-	4.1	8.4	26.4	-	12.0
	3	14.1	9.1	1.9	8.2	-	2.2	8.7	9.7	-	12.7
	4	0.4	0.2	0.5	0.5	-	0.2	0.6	0.7	-	0.6
	5	-	*	-	*	-	*	-	*	-	*
	6	-	-	-	*	-	-	-	*	-	*
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	52.1	50.8	3.7	14.8	-	6.5	17.6	36.8	-	25.3
31	1 - 2	10.0	7.4	14.2	5.2	-	5.8	9.7	4.5	-	5.4
	3	19.3	17.6	18.9	25.2	-	16.6	13.3	10.0	-	20.2
	4	2.8	5.4	5.5	9.2	-	5.6	2.7	3.5	-	6.1
	5	*	0.7	0.2	0.5	-	0.5	0.4	0.4	-	0.4
	6	*	*	-	*	-	*	*	*	-	*
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	32.2	31.1	38.8	40.2	-	28.5	26.1	18.4	-	32.1
41	1 - 2	0.5	0.1	11.8	2.1	-	3.8	1.7	0.6	-	5.9
	3	1.8	0.9	26.5	18.8	-	21.7	2.5	2.4	-	25.4
	4	2.1	2.0	6.3	13.1	-	21.4	1.5	1.8	-	6.6
	5	0.9	1.4	0.9	1.6	-	7.4	0.7	0.6	-	0.5
	6	0.1	0.5	-	0.1	-	0.9	0.6	0.1	-	*
	7	-	0.2	-	*	-	*	0.2	*	-	-
	8	-	*	-	-	-	*	0.1	*	-	-
Total	----	5.2	5.0	45.5	35.6	-	55.1	7.3	5.4	-	38.4
51	1 - 2	*	*	0.9	0.2	-	0.2	-	0.1	-	0.3
	3	*	*	1.6	1.7	-	1.8	0.1	0.3	-	1.4
	4	*	*	0.4	1.4	-	2.6	0.1	0.2	-	0.6
	5	0.1	*	0.1	0.3	-	1.3	0.1	0.1	-	0.1
	6	*	*	-	*	-	0.3	0.1	*	-	*
	7	*	*	-	*	-	*	0.1	*	-	-
	8	-	*	-	*	-	*	0.7	*	-	-
Total	----	0.2	0.1	3.1	3.6	-	6.1	1.2	0.7	-	2.3
61	1 - 2	-	-	-	*	-	*	-	*	-	-
	3	-	-	-	*	-	-	-	*	-	-
	4	-	-	-	*	-	*	-	*	-	*
	5	-	-	-	*	-	*	-	*	-	-
	6	-	-	-	*	-	-	*	*	-	-
	7	-	-	-	*	-	-	*	*	-	-
	8	-	*	-	*	-	-	*	*	-	-
Total	----	-	*	-	*	-	*	*	0.1	-	*
71	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	-	-	-	-	*	-	-
	5	-	-	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	*	-	-	-	*	-	-
Total	----	-	-	-	*	-	-	-	*	-	-
12 & 22	1 - 2	0.5	1.6	0.2	0.1	-	0.1	2.6	8.5	-	0.1
	3	0.8	1.4	0.5	0.2	-	0.1	1.5	5.2	-	0.1
	4	0.1	0.1	0.2	*	-	*	*	0.6	-	*
	5	-	*	-	-	-	*	*	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	1.3	3.0	1.0	0.4	-	0.2	4.1	14.2	-	0.2
32	1 - 2	0.4	0.5	1.2	0.3	-	0.3	4.5	2.6	-	0.1
	3	1.8	2.9	3.3	1.5	-	0.8	10.8	6.6	-	0.4
	4	0.6	1.7	1.8	0.7	-	0.3	4.0	3.0	-	0.1
	5	*	0.3	-	0.1	-	*	0.3	0.5	-	*
	6	-	*	-	*	-	*	*	0.1	-	*
	7	-	*	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	2.7	5.4	6.2	2.5	-	1.3	19.6	12.7	-	0.6
42	1 - 2	*	*	0.2	0.1	-	0.1	0.2	0.2	-	0.1
	3	0.3	0.3	0.3	1.0	-	0.8	0.9	0.9	-	0.6
	4	1.4	0.7	0.3	0.9	-	0.7	1.4	1.1	-	0.3
	5	0.3	0.7	0.1	0.2	-	0.2	0.9	0.6	-	*
	6	0.1	0.3	-	*	-	*	0.4	0.2	-	*
	7	*	0.1	-	-	-	*	0.2	0.1	-	-
	8	-	*	-	-	-	-	0.2	*	-	-
Total	----	2.1	2.1	0.8	2.2	-	1.8	4.2	3.1	-	1.0

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Feb 06, 2020

Quality Designation	Leaf	OKLAHOMA <i>Week Season</i>		SOUTH CAROLINA <i>Week Season</i>		TENNESSEE <i>Week Season</i>		TEXAS <i>Week Season</i>		VIRGINIA <i>Week Season</i>	
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	*	*	-	*	-	*	-	*	-	*
	3	*	*	*	0.1	-	0.1	-	0.1	-	*
	4	-	*	-	0.1	-	0.1	*	0.1	-	*
	5	*	*	-	*	-	*	0.2	*	-	*
	6	*	*	-	*	-	*	0.4	*	-	*
	7	*	*	-	*	-	*	0.4	*	-	*
	8	*	*	-	*	-	-	0.7	*	-	*
<i>Total</i>	----	<i>0.2</i>	<i>0.1</i>	<i>*</i>	<i>0.2</i>	-	<i>0.1</i>	<i>1.7</i>	<i>0.3</i>	-	<i>0.1</i>
62	1 - 2	-	*	-	-	-	-	-	*	-	*
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	*	-	-	-	*	-	-
	5	-	-	-	*	-	-	-	*	-	-
	6	-	-	-	*	-	-	-	*	-	-
	7	-	-	-	*	-	-	-	*	-	*
	8	-	*	-	-	-	-	*	*	-	-
<i>Total</i>	----	-	<i>*</i>	-	<i>*</i>	-	-	<i>*</i>	<i>*</i>	-	<i>*</i>
13 & 23	1 - 2	0.1	0.1	-	*	-	-	0.2	1.2	-	-
	3	*	0.1	-	*	-	*	0.3	1.1	-	*
	4	-	*	-	*	-	-	*	0.1	-	-
	5	-	*	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
<i>Total</i>	----	<i>0.1</i>	<i>0.2</i>	-	<i>*</i>	-	<i>*</i>	<i>0.4</i>	<i>2.5</i>	-	<i>*</i>
33	1 - 2	0.4	0.2	-	*	-	*	2.6	0.8	-	*
	3	1.7	0.6	0.5	0.1	-	0.1	3.5	2.0	-	*
	4	0.1	0.4	0.2	*	-	*	1.6	1.0	-	*
	5	-	0.1	-	*	-	*	0.2	0.2	-	*
	6	-	*	-	-	-	-	*	*	-	-
	7	-	*	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
<i>Total</i>	----	<i>2.3</i>	<i>1.3</i>	<i>0.6</i>	<i>0.2</i>	-	<i>0.1</i>	<i>7.9</i>	<i>4.0</i>	-	<i>0.1</i>
43	1 - 2	*	*	-	*	-	*	0.8	0.1	-	*
	3	0.4	0.1	*	0.1	-	0.1	2.2	0.3	-	*
	4	0.4	0.2	0.1	0.1	-	0.1	2.0	0.3	-	*
	5	0.1	0.2	0.1	*	-	*	0.9	0.2	-	*
	6	0.1	0.1	-	*	-	*	0.2	0.1	-	-
	7	-	*	-	*	-	-	*	*	-	-
	8	-	*	-	-	-	-	*	*	-	-
<i>Total</i>	----	<i>1.0</i>	<i>0.6</i>	<i>0.3</i>	<i>0.2</i>	-	<i>0.3</i>	<i>6.1</i>	<i>1.0</i>	-	<i>0.1</i>
53	1 - 2	-	-	-	*	-	*	-	*	-	*
	3	-	*	-	*	-	*	*	*	-	*
	4	-	*	-	*	-	*	0.1	*	-	*
	5	-	*	-	*	-	*	0.1	*	-	-
	6	0.1	*	-	*	-	*	0.1	*	-	-
	7	0.1	*	-	-	-	-	0.1	*	-	-
	8	0.1	*	-	-	-	-	*	*	-	-
<i>Total</i>	----	<i>0.2</i>	<i>0.1</i>	-	<i>*</i>	-	<i>*</i>	<i>0.4</i>	<i>0.1</i>	-	<i>*</i>
63	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	*	-	-	-	*	-	-
	5	-	-	-	*	-	-	-	*	-	-
	6	-	-	-	*	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
<i>Total</i>	----	-	-	-	<i>*</i>	-	-	<i>*</i>	<i>*</i>	-	-
24 - 54	1 - 8	0.3	0.2	-	*	-	*	2.8	0.6	-	*
25 - 35	1 - 8	-	*	-	-	-	-	-	*	-	-
81 - 85	1 - 8	*	*	-	*	-	*	0.4	*	-	-
STAPLE											
28 & Shorter		-	*	-	-	-	-	-	*	-	-
29		-	*	-	-	-	-	*	*	-	-
30		-	*	-	-	-	-	*	0.2	-	-
31		0.1	0.2	-	*	-	-	0.4	1.2	-	-
32		0.9	1.3	-	0.3	-	*	2.1	3.8	-	*
33		4.8	4.8	0.5	1.7	-	*	8.6	8.6	-	0.1
34		12.5	9.3	6.4	5.8	-	1.0	18.5	15.0	-	1.0
35		13.4	13.3	15.2	13.1	-	11.8	21.1	20.2	-	4.9
36		15.1	16.5	22.4	20.0	-	36.3	20.8	19.6	-	16.8
37		18.4	23.8	36.0	37.4	-	37.9	18.8	19.1	-	39.8
38		16.7	15.9	16.6	17.1	-	10.4	5.9	8.2	-	23.3
39		14.2	10.2	2.8	4.1	-	2.4	2.7	3.2	-	11.7
40 & Longer		3.7	4.6	0.1	0.4	-	0.2	1.0	0.9	-	2.5
<i>Average Staple</i>		<i>36.52</i>	<i>36.52</i>	<i>36.48</i>	<i>36.54</i>	-	<i>36.53</i>	<i>35.48</i>	<i>35.50</i>	-	<i>37.25</i>
<i>Average Length</i>		<i>1.14</i>	<i>1.14</i>	<i>1.14</i>	<i>1.14</i>	-	<i>1.14</i>	<i>1.11</i>	<i>1.11</i>	-	<i>1.16</i>

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Feb 06, 2020

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	7.4	2.6	0.3	0.9	3.8	1.4	-	3.1	14.7	7.1	8.2	3.3
Bark - Level 2	-	*	-	*	-	-	-	*	-	-	-	*
Grass - Level 1	0.1	0.1	-	0.1	*	*	-	*	-	0.1	0.2	0.1
Grass - Level 2	-	*	-	-	-	-	-	-	-	-	-	*
Prep - Level 1	*	*	-	*	-	*	-	*	0.3	*	0.2	*
Prep - Level 2	-	*	-	-	-	-	-	-	-	-	-	*
Seed Coat - Level 1	0.1	*	-	*	0.2	0.9	-	*	0.7	*	0.1	*
Seed Coat - Level 2	-	*	-	-	-	-	-	-	-	-	-	*
Oil - Level 1	-	*	-	*	*	*	-	-	-	-	-	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	*
Spindle Twist - Level 1	-	-	-	-	-	*	-	*	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	*	0.1	-	*	-	*	-	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	0.1	*	1.0	0.1	-	*	-	*	0.1	*
Plastic - Level 2	-	-	-	*	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	*	*	*	-	*	-	-	-	-	-	*
23	-	*	*	*	-	*	-	-	-	*	0.1	*
24	*	*	0.2	*	*	*	-	*	-	*	0.7	0.2
25	*	0.4	1.3	*	0.1	0.2	-	*	-	0.1	3.2	0.9
26	1.4	1.8	6.1	0.3	0.5	0.5	-	*	0.1	0.8	8.6	3.4
27	18.0	7.7	15.1	1.3	2.0	1.7	-	0.3	1.2	3.6	15.4	8.5
28	27.1	21.0	29.1	6.3	5.1	5.1	-	0.6	18.2	12.4	20.1	15.4
29	26.9	29.7	30.5	19.5	12.6	12.6	-	2.9	41.8	25.5	21.6	21.7
30	16.4	21.4	13.4	30.1	17.0	21.4	-	11.5	17.2	29.2	17.1	22.2
31	6.7	10.8	3.9	24.0	20.7	20.7	-	16.8	18.7	16.5	8.6	14.7
32	3.1	4.6	0.2	12.0	16.1	15.3	-	16.9	2.6	7.1	3.1	7.6
33	0.4	1.7	*	4.4	11.5	10.9	-	12.1	0.1	3.4	1.2	3.5
34	*	0.6	*	1.5	7.4	6.4	-	6.5	0.1	1.0	0.2	1.3
35	*	0.2	-	0.4	4.2	3.1	-	9.1	-	0.3	0.1	0.4
36	*	0.1	-	0.1	1.8	1.2	-	11.7	-	0.1	*	0.1
37	-	*	-	*	0.8	0.5	-	8.4	-	*	-	*
38	-	*	-	*	0.1	0.1	-	2.4	-	-	-	*
39	-	*	-	*	*	*	-	0.5	-	-	-	-
40 & Above	-	-	-	-	*	*	-	0.3	-	-	-	-
Average	29.19	29.69	28.83	30.77	31.71	31.51	-	33.54	29.85	30.26	29.01	29.96
Mike												
2.4 & Below	-	-	-	-	-	*	-	-	-	-	-	-
2.5	-	*	-	-	-	*	-	*	-	*	-	*
2.6	-	*	-	-	*	*	-	*	-	*	-	*
2.7	-	*	-	-	0.1	*	-	0.1	-	*	-	*
2.8	-	*	-	*	0.1	*	-	0.1	-	*	-	*
2.9	-	*	-	*	0.2	*	-	0.2	-	*	*	*
3.0	-	*	-	*	0.3	0.1	-	0.2	-	*	-	*
3.1	-	*	-	*	0.6	0.1	-	0.5	-	*	-	*
3.2	-	*	-	*	0.9	0.2	-	0.5	-	*	*	*
3.3	*	0.1	-	*	0.5	0.2	-	0.5	-	*	0.1	*
3.4	0.4	0.2	-	*	0.7	0.3	-	0.6	-	*	0.1	0.1
3.5	0.7	0.5	*	0.1	1.0	0.5	-	1.0	-	*	0.1	0.1
3.6	0.4	0.9	0.3	0.3	1.5	0.8	-	1.5	-	*	0.5	0.2
3.7	1.2	1.7	1.1	0.6	1.6	1.3	-	1.4	-	*	0.7	0.3
3.8	1.1	2.8	1.4	1.2	1.8	1.8	-	1.9	0.1	0.1	1.2	0.6
3.9	3.1	4.3	3.2	2.0	2.4	2.1	-	2.8	-	0.4	3.7	1.1
4.0	10.5	6.0	1.9	3.3	2.1	2.7	-	4.9	-	1.0	5.2	1.9
4.1	8.3	7.6	1.5	5.1	2.8	3.5	-	7.6	2.2	1.9	6.9	3.2
4.2	9.0	9.3	2.9	7.7	5.5	4.6	-	9.4	17.3	3.5	7.6	5.6
4.3	13.1	10.6	4.7	10.2	6.9	6.0	-	10.3	22.8	6.8	10.2	8.8
4.4	15.7	11.8	6.4	11.8	8.6	8.2	-	12.1	20.1	13.3	14.1	12.4
4.5	14.9	12.3	10.1	13.5	10.4	10.5	-	11.4	28.1	18.7	13.6	14.9
4.6	10.5	11.0	14.2	13.4	12.0	12.1	-	10.9	7.6	18.5	13.7	15.3
4.7	6.1	8.9	15.0	10.8	9.5	11.1	-	8.1	1.8	15.1	9.8	13.1
4.8	3.2	5.7	10.7	8.0	7.7	9.7	-	5.3	-	10.0	5.2	9.7
4.9	1.4	3.4	10.6	5.2	5.9	7.5	-	3.0	0.1	5.6	3.0	6.3
5.0	0.2	1.7	8.5	3.2	5.9	6.0	-	1.6	-	2.8	2.5	3.5
5.1	0.1	0.8	4.6	1.8	4.2	4.2	-	1.1	-	1.6	1.0	1.7
5.2	*	0.3	2.2	1.0	3.1	2.6	-	1.1	-	0.5	0.4	0.6
5.3	-	0.1	0.6	0.5	1.4	1.8	-	0.7	-	0.1	0.3	0.2
5.4	-	*	-	0.2	0.8	1.1	-	0.5	-	*	0.2	0.1
5.5 & Above	-	*	-	0.1	1.6	1.0	-	0.7	-	*	0.2	*
Average	4.33	4.38	4.63	4.50	4.52	4.58	-	4.38	4.38	4.57	4.43	4.54

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Feb 06, 2020

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	20.7	21.0	2.3	1.3	1.2	0.4	0.2	1.1	2.9	2.3	-	1.8
Bark - Level 2	-	-	-	-	-	-	-	*	-	-	-	*
Grass - Level 1	-	*	-	0.1	-	*	-	0.1	0.1	0.3	-	*
Grass - Level 2	-	-	-	-	-	-	-	*	-	-	-	-
Prep - Level 1	-	*	-	*	-	*	-	*	-	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	*	-	*	-	*	-	*	-	*	-	*
Seed Coat - Level 2	-	-	-	-	-	-	-	*	-	-	-	-
Oil - Level 1	-	-	-	*	-	*	-	*	-	*	-	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	*	-	*	-	*	-	*	-	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	0.2	*	-	*	*	*	-	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	*	-	-	-	-
STRENGTH 1/ 22 & Below	-	0.1	-	-	-	*	-	*	-	-	-	-
23	-	0.1	-	-	-	*	-	*	-	*	-	-
24	-	0.4	-	*	0.1	*	-	*	*	*	-	*
25	*	1.0	-	*	0.3	*	0.1	0.1	0.1	0.2	-	0.1
26	0.3	2.3	-	0.2	0.5	0.2	1.4	0.5	1.5	0.7	-	0.3
27	1.9	3.6	*	0.8	5.6	1.8	8.0	2.1	2.0	1.9	-	2.7
28	10.4	6.0	0.2	5.2	36.2	8.6	23.9	6.2	5.9	4.9	-	13.8
29	26.8	18.8	19.7	18.8	48.7	25.2	31.1	15.6	16.9	13.1	-	21.5
30	31.4	25.3	38.4	26.2	7.7	34.2	20.9	29.1	33.6	24.1	-	24.8
31	16.6	19.6	15.3	20.2	0.9	19.9	9.5	27.0	24.7	24.3	-	20.7
32	7.9	11.7	13.2	14.6	-	7.0	4.0	12.4	10.3	17.0	-	11.5
33	4.0	6.7	8.8	8.6	-	2.2	1.0	5.2	4.0	9.1	-	4.1
34	0.4	3.4	2.5	3.6	-	0.6	0.1	1.4	0.5	3.4	-	0.4
35	0.2	0.8	1.3	1.3	-	0.2	-	0.2	0.2	0.9	-	*
36	-	0.1	0.4	0.3	-	*	-	*	0.1	0.2	-	*
37	*	*	0.1	0.1	-	*	-	*	-	0.1	-	*
38	*	*	-	*	-	*	-	*	-	*	-	*
39	-	-	-	-	-	*	-	*	-	-	-	-
40 & Above	-	-	-	-	-	-	-	-	-	-	-	-
Average	30.38	30.67	31.11	31.11	29.04	30.41	29.57	30.83	30.65	31.18	-	30.45
Mike												
2.4 & Below	-	*	-	-	-	-	-	-	-	-	-	-
2.5	*	0.2	-	-	-	-	-	-	-	*	-	-
2.6	0.1	0.2	-	-	-	-	-	-	-	*	-	-
2.7	0.9	0.5	-	-	-	-	-	-	-	*	-	-
2.8	2.8	0.7	-	-	-	-	-	*	-	*	-	*
2.9	1.6	1.0	-	-	-	-	-	*	-	*	-	0.2
3.0	4.0	2.2	-	*	-	*	-	*	-	*	-	0.1
3.1	5.5	3.2	-	*	-	*	-	*	-	*	-	0.1
3.2	5.8	3.8	-	*	-	*	-	*	-	*	-	0.2
3.3	5.4	4.7	-	*	-	*	-	*	-	*	-	0.3
3.4	5.2	5.4	*	*	-	0.1	-	*	-	*	-	0.9
3.5	7.4	6.6	0.1	*	-	0.1	-	*	*	0.1	-	2.0
3.6	7.8	7.2	-	0.1	-	0.2	-	0.1	0.3	0.1	-	2.6
3.7	4.9	6.8	0.1	0.2	-	0.4	-	0.2	1.4	0.3	-	4.7
3.8	7.2	6.9	1.2	0.5	0.1	0.9	-	0.5	1.6	0.6	-	5.7
3.9	6.5	7.5	1.9	1.0	-	1.7	*	1.0	5.1	1.1	-	6.7
4.0	9.4	7.0	4.6	1.4	0.1	2.9	0.2	1.9	5.3	1.5	-	7.5
4.1	8.1	6.7	3.4	2.6	0.4	4.8	2.5	2.8	7.6	2.3	-	7.8
4.2	3.3	5.7	2.7	4.2	0.1	7.6	3.8	4.3	9.7	3.6	-	8.7
4.3	2.2	4.8	2.7	7.5	1.2	9.8	4.3	6.6	9.9	5.4	-	8.8
4.4	2.6	4.6	4.6	11.2	11.9	12.0	6.2	9.9	11.4	8.3	-	9.8
4.5	1.3	4.0	9.8	15.9	15.0	12.9	10.0	13.2	12.1	11.2	-	8.8
4.6	1.3	3.0	35.6	16.8	8.0	12.5	12.2	15.6	9.3	14.1	-	8.3
4.7	0.4	2.4	24.2	16.2	8.8	11.3	15.5	15.7	7.0	15.1	-	5.6
4.8	0.7	2.0	7.3	11.0	10.6	8.6	18.0	12.8	5.1	13.5	-	3.8
4.9	1.9	1.3	0.9	6.1	14.6	6.0	17.1	8.1	4.5	10.5	-	2.0
5.0	2.1	0.9	*	3.0	7.6	3.9	7.6	4.1	6.2	6.5	-	1.4
5.1	1.2	0.6	-	1.3	9.4	2.4	2.1	1.9	2.4	3.3	-	1.5
5.2	0.3	0.1	-	0.5	7.9	1.2	0.4	0.8	0.7	1.5	-	1.4
5.3	0.1	0.1	0.1	0.2	3.9	0.4	0.1	0.4	0.3	0.6	-	0.6
5.4	*	*	0.4	0.1	0.2	0.1	-	0.1	*	0.3	-	0.3
5.5 & Above	-	*	*	*	-	*	-	*	*	0.2	-	*
Average	3.74	3.87	4.54	4.57	4.78	4.52	4.68	4.59	4.44	4.64	-	4.27

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Feb 06, 2020

Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter										
Bark - Level 1	6.5	8.6	0.7	1.6	-	0.3	25.8	9.1	-	0.6
Bark - Level 2	-	-	-	-	-	-	-	*	-	-
Grass - Level 1	-	*	0.4	0.3	-	*	-	0.1	-	0.1
Grass - Level 2	-	-	-	-	-	-	-	*	-	-
Prep - Level 1	-	*	-	*	-	*	*	*	-	*
Prep - Level 2	-	-	-	-	-	-	-	*	-	-
Seed Coat - Level 1	-	*	-	*	-	*	-	0.1	-	*
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	-	-	*	-	*	-	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	-	*	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	-	*	*	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	*	-	*	-	*	*	*	-	-
23	*	*	*	*	-	*	0.1	0.1	-	*
24	0.1	0.1	0.1	0.1	-	*	0.2	0.4	-	*
25	0.3	0.2	1.2	0.5	-	0.1	0.9	1.0	-	0.1
26	0.4	0.6	3.6	2.0	-	0.5	2.7	2.4	-	0.5
27	1.6	1.9	11.0	5.0	-	4.3	6.8	5.4	-	2.0
28	4.3	4.5	21.0	11.8	-	18.7	10.8	10.3	-	4.4
29	11.4	9.2	16.9	24.4	-	31.1	16.1	16.0	-	13.5
30	16.8	14.9	16.6	25.8	-	24.3	17.1	20.0	-	26.7
31	18.0	17.8	15.7	16.4	-	12.2	14.7	18.2	-	25.4
32	14.2	16.2	8.3	8.1	-	5.7	13.6	12.9	-	16.8
33	12.1	13.2	4.0	3.7	-	2.3	8.7	7.3	-	7.2
34	9.1	9.7	1.2	1.5	-	0.6	5.3	3.5	-	2.4
35	6.0	6.1	0.2	0.5	-	0.2	2.1	1.5	-	0.8
36	3.3	3.5	0.1	0.1	-	*	0.7	0.6	-	0.2
37	1.7	1.5	-	*	-	*	0.2	0.2	-	*
38	0.5	0.5	-	*	-	*	*	0.1	-	-
39	0.1	*	-	-	-	*	-	*	-	-
40 & Above	-	-	-	-	-	-	-	*	-	-
Average	32.02	32.12	29.82	30.24	-	29.95	30.75	30.68	-	31.11
Mike										
2.4 & Below	-	*	-	*	-	-	-	*	-	-
2.5	-	*	-	*	-	-	-	0.1	-	-
2.6	-	*	-	*	-	-	*	0.1	-	-
2.7	-	*	-	*	-	-	0.1	0.1	-	-
2.8	-	*	-	*	-	*	0.1	0.2	-	-
2.9	-	0.1	-	*	-	*	0.3	0.3	-	-
3.0	*	0.1	-	*	-	*	0.6	0.4	-	-
3.1	*	0.2	-	*	-	*	1.0	0.5	-	-
3.2	0.1	0.2	0.1	*	-	*	1.0	0.7	-	*
3.3	0.2	0.3	0.2	*	-	*	1.0	0.9	-	*
3.4	0.1	0.5	0.8	*	-	0.1	1.6	1.2	-	*
3.5	0.6	0.9	0.7	0.1	-	0.2	1.6	1.5	-	*
3.6	1.0	1.5	0.5	0.2	-	0.4	1.9	1.9	-	*
3.7	1.9	2.2	0.5	0.3	-	0.7	2.6	2.4	-	0.1
3.8	2.7	3.2	1.1	0.5	-	1.0	2.7	3.0	-	0.1
3.9	3.3	4.0	1.1	0.8	-	1.8	3.8	3.7	-	0.3
4.0	4.3	5.0	2.0	1.5	-	2.7	4.8	4.5	-	0.6
4.1	5.6	5.9	2.3	2.9	-	3.8	5.2	5.5	-	1.2
4.2	5.4	7.1	5.8	5.2	-	5.6	7.2	6.6	-	2.3
4.3	7.3	8.0	10.3	8.4	-	8.2	8.7	7.7	-	4.2
4.4	9.3	9.0	13.4	11.3	-	11.1	9.6	8.9	-	7.1
4.5	13.5	9.8	13.6	13.8	-	13.5	8.9	9.4	-	11.5
4.6	13.2	9.7	13.2	14.9	-	14.3	8.7	9.4	-	16.1
4.7	10.7	9.1	12.7	14.1	-	12.9	7.7	9.0	-	17.9
4.8	9.2	7.6	10.7	11.3	-	10.2	7.2	7.7	-	15.8
4.9	5.2	5.9	8.0	7.3	-	6.7	5.5	5.8	-	10.8
5.0	3.4	4.3	2.6	3.9	-	3.8	4.1	4.0	-	6.6
5.1	1.5	2.7	0.5	1.7	-	1.9	2.4	2.4	-	3.1
5.2	0.5	1.5	*	0.8	-	0.7	1.2	1.2	-	1.3
5.3	0.1	0.7	*	0.5	-	0.2	0.3	0.6	-	0.6
5.4	0.7	0.2	-	0.3	-	*	0.1	0.2	-	0.3
5.5 & Above	0.1	0.1	-	0.1	-	*	0.2	0.1	-	0.1
Average	4.46	4.43	4.51	4.57	-	4.53	4.35	4.38	-	4.68

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Feb 06, 2020

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	-	-	-	-	*	-	-	-	-	-	-
2.5 - 2.6	-	*	-	-	*	*	-	*	-	*	-	*
2.7 - 2.9	-	*	-	*	0.4	0.1	-	0.3	-	*	*	*
3.0 - 3.2	-	0.1	-	*	1.8	0.4	-	1.2	-	*	*	*
3.3 - 3.4	0.5	0.3	-	0.1	1.3	0.6	-	1.1	-	*	0.2	0.1
3.5 - 3.6	1.2	1.3	0.3	0.4	2.5	1.3	-	2.5	-	0.1	0.6	0.4
3.7 - 4.2	33.2	31.6	12.1	19.9	16.2	15.9	-	28.1	19.6	7.0	25.3	12.8
4.3 - 4.9	64.9	63.7	71.7	72.9	61.0	65.0	-	61.1	80.4	87.9	69.5	80.5
5.0 - 5.2	0.4	2.8	15.3	6.0	13.1	12.7	-	3.8	-	4.8	3.9	5.8
5.3 & Above	-	0.2	0.6	0.7	3.7	3.9	-	1.8	-	0.1	0.6	0.4
Average	4.33	4.38	4.63	4.50	4.52	4.58	-	4.38	4.38	4.57	4.43	4.54
Leaf												
1 - 2	6.6	13.6	9.0	9.1	30.0	58.6	-	63.9	0.1	6.3	14.8	16.5
3	42.0	48.4	49.9	37.4	31.7	25.0	-	27.2	17.2	37.7	45.3	48.2
4	32.1	30.5	32.0	35.7	22.0	10.4	-	7.1	57.7	44.1	31.8	29.3
5	12.1	6.5	9.1	15.9	10.9	3.9	-	1.2	23.3	11.1	7.5	5.6
6	7.2	0.9	0.1	1.9	3.6	1.4	-	0.4	1.7	0.7	0.6	0.4
7	-	0.1	*	*	0.7	0.5	-	0.2	-	*	*	*
8	-	*	-	*	1.0	0.2	-	*	-	*	-	*
Average	3.71	3.32	3.41	3.64	3.25	2.47	-	2.27	4.09	3.62	3.33	3.24
HVI Trash 1/												
00	-	*	-	*	*	*	-	0.1	-	-	-	*
01	1.0	2.7	0.2	1.3	11.9	31.6	-	33.8	-	1.0	4.8	3.7
02	9.1	15.0	13.1	9.7	20.7	30.4	-	33.7	0.3	7.6	14.9	17.1
03	21.2	24.6	25.8	16.6	17.9	14.9	-	16.7	6.0	16.7	22.3	24.3
04	22.3	23.3	22.4	18.3	14.3	8.8	-	7.7	15.5	22.7	22.3	22.1
05	17.1	16.1	17.8	17.0	11.6	5.4	-	4.0	25.5	21.3	15.6	15.4
06	9.7	9.2	11.5	14.2	8.2	3.4	-	2.0	24.0	14.9	10.0	9.0
07	5.2	4.7	5.8	10.2	5.8	2.0	-	0.9	15.7	8.4	5.0	4.6
08	3.8	2.3	2.2	6.4	3.8	1.3	-	0.5	7.2	4.1	2.5	2.2
09	4.2	1.1	0.7	3.5	2.3	0.8	-	0.2	2.9	1.9	1.3	1.0
10	3.3	0.6	0.3	1.6	1.2	0.5	-	0.2	1.9	0.8	0.5	0.4
11	2.0	0.3	0.1	0.7	0.8	0.3	-	0.1	0.5	0.4	0.3	0.2
12	0.9	0.1	*	0.3	0.4	0.2	-	0.1	0.4	0.1	0.1	0.1
13	0.3	0.1	-	0.1	0.2	0.1	-	0.1	-	0.1	0.1	*
14	*	*	-	*	0.2	0.1	-	*	0.1	*	*	*
15	-	*	-	*	0.1	0.1	-	*	-	*	*	*
16	-	*	-	*	0.1	*	-	*	-	*	*	*
17	-	*	*	*	0.1	*	-	*	-	*	-	*
18 & Above	-	*	-	*	0.4	0.1	-	*	-	*	-	*
Average	0.49	0.41	0.42	0.50	0.41	0.27	-	0.23	0.58	0.48	0.41	0.40
UNIFORMITY 2/												
74 & Below	-	-	-	-	-	-	-	-	-	-	-	-
75	-	*	-	*	-	*	-	-	-	-	*	*
76	*	*	-	*	*	*	-	*	-	*	0.1	*
77	0.1	0.2	*	0.1	0.2	0.2	-	0.3	-	*	0.4	0.1
78	2.0	2.2	0.4	0.4	1.7	1.7	-	1.1	0.1	0.3	2.2	1.0
79	12.9	11.4	3.4	2.3	8.4	8.2	-	3.8	0.1	2.0	7.5	5.2
80	37.8	30.8	15.4	12.4	28.4	23.1	-	18.0	7.3	13.7	19.2	19.1
81	34.3	35.4	39.6	35.4	34.5	35.3	-	29.7	67.0	41.7	37.3	37.0
82	10.4	16.2	30.7	35.3	22.1	24.7	-	22.0	24.9	32.4	26.3	28.0
83	2.3	3.4	9.9	12.5	4.3	6.0	-	14.2	0.4	8.3	6.2	8.2
84	0.2	0.4	0.5	1.5	0.4	0.6	-	10.5	0.1	1.5	0.7	1.2
85 & Above	*	*	0.1	0.1	*	0.1	-	0.4	-	0.1	0.1	0.1
Average	80.91	81.08	81.74	81.92	81.27	81.38	-	81.98	81.63	81.81	81.43	81.61
Tenderable 3/	84.2	86.0	82.1	89.7	67.9	76.6	-	87.6	76.1	82.9	80.2	84.9
SAMPLES CLASSED	11,770	975,145	9,359	1,435,031	19,434	307,425	-	181,585	1,450	157,550	11,053	2,707,768

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Feb 06, 2020

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	*	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	0.1	0.4	-	-	-	-	-	-	-	*	-	-
2.7 - 2.9	5.3	2.1	-	-	-	-	-	*	-	*	-	0.2
3.0 - 3.2	15.3	9.2	-	*	-	*	-	*	-	*	-	0.5
3.3 - 3.4	10.7	10.1	*	*	-	0.1	-	*	-	*	-	1.2
3.5 - 3.6	15.2	13.8	0.1	0.2	-	0.4	-	0.1	0.4	0.2	-	4.6
3.7 - 4.2	39.3	40.5	14.0	9.9	0.7	18.4	6.6	10.7	30.6	9.3	-	41.1
4.3 - 4.9	10.4	22.2	85.2	84.7	70.2	73.1	83.3	81.7	59.3	78.1	-	47.2
5.0 - 5.2	3.7	1.6	*	4.9	25.0	7.5	10.0	6.9	9.3	11.2	-	4.3
5.3 & Above	0.1	0.1	0.6	0.3	4.1	0.5	0.1	0.5	0.4	1.0	-	0.9
Average	3.74	3.87	4.54	4.57	4.78	4.52	4.68	4.59	4.44	4.64	-	4.27
Leaf												
1 - 2	38.8	38.2	3.7	18.9	18.2	10.3	36.6	17.9	6.5	11.2	-	57.5
3	35.2	31.0	33.6	41.8	48.0	39.6	46.8	40.1	67.6	52.3	-	32.5
4	16.0	16.3	54.1	29.8	29.5	34.8	15.3	31.2	24.2	31.4	-	7.9
5	8.5	7.9	8.4	8.5	4.1	13.7	1.3	9.6	1.6	4.8	-	1.6
6	1.4	3.4	0.3	1.0	0.2	1.5	*	1.2	0.1	0.3	-	0.3
7	0.2	1.9	-	*	-	*	-	0.1	-	*	-	0.1
8	*	1.4	-	*	-	*	-	*	-	*	-	*
Average	2.95	3.14	3.68	3.30	3.20	3.56	2.80	3.35	3.21	3.30	-	2.41
HVI Trash 1/												
00	-	-	-	-	-	*	-	*	-	-	-	*
01	12.1	13.2	0.1	4.0	0.6	1.4	6.2	4.4	0.2	1.4	-	20.8
02	32.1	28.6	3.4	19.1	16.8	9.7	35.0	16.6	9.5	12.2	-	35.3
03	19.2	16.9	11.8	20.1	27.7	17.3	27.6	19.3	32.0	25.1	-	21.6
04	10.8	11.4	22.2	17.9	20.3	18.9	15.5	18.2	30.7	25.8	-	11.0
05	7.6	8.1	27.1	14.7	16.1	17.2	9.5	15.2	16.8	17.9	-	5.6
06	6.0	5.5	19.1	10.4	9.4	13.8	3.9	11.1	6.8	9.9	-	2.7
07	4.8	4.0	10.9	6.5	5.8	9.7	1.7	7.1	2.5	4.6	-	1.4
08	3.3	2.8	3.7	3.7	1.8	6.0	0.4	4.1	0.9	2.0	-	0.7
09	1.8	2.1	1.3	1.9	1.1	3.3	0.1	2.2	0.4	0.8	-	0.3
10	1.1	1.6	0.3	1.0	0.2	1.6	*	1.0	0.1	0.3	-	0.2
11	0.5	1.2	0.1	0.5	0.1	0.7	-	0.5	*	0.1	-	0.1
12	0.4	1.0	*	0.2	0.1	0.3	*	0.2	0.1	*	-	0.1
13	0.2	0.8	*	0.1	0.1	0.1	-	0.1	*	*	-	*
14	0.1	0.6	-	*	-	*	-	*	-	*	-	*
15	*	0.5	-	*	-	*	-	*	-	*	-	*
16	*	0.4	0.1	*	-	*	-	*	-	*	-	-
17	*	0.3	-	*	-	*	-	*	-	*	-	*
18 & Above	*	1.0	*	*	-	*	-	*	-	*	-	*
Average	0.35	0.41	0.50	0.42	0.40	0.49	0.31	0.43	0.39	0.41	-	0.27
UNIFORMITY 2/												
74 & Below	-	*	-	-	-	-	-	-	-	-	-	-
75	*	*	-	-	-	-	-	*	-	*	-	-
76	0.1	0.2	-	-	-	*	*	*	-	*	-	-
77	0.8	0.8	-	*	-	*	0.2	0.1	0.1	0.1	-	*
78	8.8	3.4	-	0.3	-	0.1	2.1	0.9	0.5	0.6	-	0.1
79	22.8	15.9	0.3	2.0	0.2	0.9	10.9	4.7	4.7	4.4	-	1.3
80	38.2	37.4	5.8	13.6	4.6	7.2	31.8	20.7	24.1	19.8	-	10.6
81	26.0	35.5	19.3	36.8	25.3	26.9	37.8	44.6	50.3	38.0	-	29.0
82	3.2	6.5	51.7	33.5	65.4	42.2	15.4	24.7	16.7	29.2	-	45.8
83	0.2	0.3	19.9	11.7	3.9	20.1	1.7	4.0	3.4	6.9	-	12.8
84	*	*	2.8	1.9	0.6	2.4	0.1	0.4	0.2	0.8	-	0.4
85 & Above	-	*	0.2	0.3	-	0.2	-	*	-	0.1	-	*
Average	80.34	80.68	82.41	81.90	82.17	82.26	81.04	81.46	81.36	81.59	-	82.04
Tenderable 3/	44.6	54.7	92.7	89.3	67.6	89.5	86.4	88.4	80.7	83.5	-	85.4
SAMPLES CLASSED	13,012	192,178	2,668	580,742	1,687	827,338	5,247	1,535,904	6,396	1,057,998	-	31,309

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Feb 06, 2020

Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE										
2.4 & Below	-	*	-	*	-	-	-	*	-	-
2.5 - 2.6	-	*	-	*	-	-	*	0.2	-	-
2.7 - 2.9	-	0.1	-	*	-	*	0.5	0.6	-	-
3.0 - 3.2	0.1	0.5	0.1	*	-	0.1	2.5	1.5	-	*
3.3 - 3.4	0.3	0.9	0.9	*	-	0.1	2.6	2.1	-	*
3.5 - 3.6	1.6	2.4	1.2	0.2	-	0.6	3.5	3.4	-	*
3.7 - 4.2	23.2	27.4	12.7	11.1	-	15.5	26.2	25.8	-	4.6
4.3 - 4.9	68.5	59.1	81.8	81.1	-	77.1	56.3	57.9	-	83.3
5.0 - 5.2	5.4	8.6	3.2	6.4	-	6.4	7.7	7.6	-	11.0
5.3 & Above	0.9	1.0	*	1.0	-	0.2	0.6	0.9	-	1.0
Average	4.46	4.43	4.51	4.57	-	4.53	4.35	4.38	-	4.68
Leaf										
1 - 2	49.7	51.4	29.9	14.2	-	14.3	31.1	45.0	-	23.8
3	40.4	32.9	53.5	57.0	-	44.1	45.4	38.9	-	60.8
4	7.9	10.7	15.2	26.0	-	30.9	14.4	12.6	-	14.4
5	1.4	3.4	1.4	2.7	-	9.5	4.0	2.7	-	0.9
6	0.3	1.1	-	0.1	-	1.2	2.1	0.6	-	*
7	0.2	0.4	-	*	-	*	1.2	0.2	-	*
8	0.1	0.2	-	*	-	*	1.7	*	-	*
Average	2.54	2.58	2.87	3.17	-	3.39	3.04	2.67	-	2.92
HVI Trash 1/										
00	-	*	-	*	-	*	0.1	*	-	-
01	16.3	23.1	3.9	1.6	-	2.3	10.8	17.0	-	3.0
02	36.7	31.8	28.0	15.4	-	13.3	24.3	32.0	-	22.8
03	26.6	19.8	32.6	28.6	-	20.8	25.7	22.9	-	33.1
04	10.8	10.7	18.0	25.5	-	20.2	15.4	13.4	-	23.2
05	4.8	5.9	10.0	15.6	-	16.2	8.5	7.2	-	11.1
06	2.0	3.4	4.6	7.7	-	11.4	4.7	3.6	-	4.3
07	1.2	2.0	1.9	3.3	-	7.3	3.0	1.8	-	1.6
08	0.7	1.2	0.5	1.3	-	4.2	1.7	0.9	-	0.5
09	0.2	0.7	0.4	0.5	-	2.2	1.1	0.5	-	0.2
10	0.2	0.5	0.2	0.2	-	1.1	0.8	0.3	-	0.1
11	0.1	0.3	-	0.1	-	0.6	0.8	0.2	-	*
12	0.1	0.2	-	*	-	0.3	0.6	0.1	-	*
13	*	0.1	-	*	-	0.1	0.5	*	-	*
14	0.1	0.1	-	*	-	*	0.5	*	-	*
15	0.1	0.1	-	*	-	*	0.4	*	-	*
16	*	*	-	*	-	*	0.4	*	-	*
17	*	*	-	*	-	*	0.3	*	-	-
18 & Above	0.1	0.1	-	*	-	*	0.5	*	-	-
Average	0.27	0.29	0.33	0.39	-	0.45	0.38	0.29	-	0.34
UNIFORMITY 2/										
74 & Below	*	*	-	-	-	-	*	*	-	-
75	*	*	-	*	-	-	0.1	0.1	-	*
76	0.1	0.2	-	*	-	*	0.3	0.6	-	*
77	0.7	1.0	-	0.3	-	0.1	1.8	2.7	-	0.1
78	3.2	3.8	0.5	1.4	-	0.5	9.1	8.3	-	0.2
79	13.1	12.4	5.4	7.7	-	5.1	22.5	19.7	-	1.3
80	29.7	28.4	30.8	30.5	-	22.4	30.8	30.3	-	9.0
81	33.0	33.3	36.9	40.3	-	36.5	22.8	25.5	-	35.7
82	16.6	16.8	22.3	16.4	-	26.9	9.0	10.6	-	39.4
83	3.4	3.6	3.8	3.1	-	7.8	3.2	1.9	-	12.2
84	0.2	0.5	0.4	0.3	-	0.7	0.5	0.2	-	1.9
85 & Above	-	0.1	-	*	-	0.1	*	*	-	0.2
Average	81.00	81.01	81.34	81.17	-	81.55	80.50	80.51	-	82.03
Tenderable 3/	83.2	77.5	91.0	87.5	-	89.4	50.3	66.0	-	86.2
SAMPLES CLASSED	10,463	492,364	2,425	418,894	-	938,993	19,250	6,279,311	-	225,227

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Feb 06, 2020

Color Grade	Leaf	Arizona		California		New Mexico		Texas	
		Week	Season	Week	Season	Week	Season	Week	Season
01	1	-	53.4	36.9	28.1	-	-	-	11.5
	2	-	7.4	12.0	8.5	-	-	-	15.5
	3	-	1.0	*	*	-	-	-	0.3
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	61.9	49.0	36.5	-	-	-	27.4
02	1	-	20.7	23.0	29.6	-	-	-	14.7
	2	-	11.8	27.3	30.7	-	-	-	43.7
	3	-	2.9	0.5	0.9	-	-	-	5.2
	4	-	0.8	*	*	-	-	-	0.1
	5	-	*	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	36.2	50.7	61.2	-	-	-	63.6
03	1	-	0.2	*	0.3	-	-	-	1.0
	2	-	0.8	0.2	1.4	-	-	-	5.2
	3	-	0.7	0.1	0.4	-	-	-	1.8
	4	-	0.1	*	*	-	-	-	0.1
	5	-	*	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	1.8	0.3	2.1	-	-	-	8.2
04	1	-	*	-	*	-	-	-	-
	2	-	*	-	0.1	-	-	-	0.2
	3	-	0.1	-	*	-	-	-	0.4
	4	-	*	-	*	-	-	-	0.1
	5	-	-	-	*	-	-	-	*
	6	-	-	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-
Total -----		-	0.1	-	0.1	-	-	-	0.7
05	1	-	-	-	-	-	-	-	-
	2	-	-	-	*	-	-	-	*
	3	-	*	-	*	-	-	-	0.1
	4	-	*	-	*	-	-	-	*
	5	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	*	-	-	-	-
Total -----		-	*	-	*	-	-	-	0.1
06	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	-	*	-	-	-	-
07	1	-	-	-	-	-	-	-	-
	2	-	-	-	*	-	-	-	-
	3	-	-	-	*	-	-	-	-
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	-	*	-	-	-	-
STAPLE									
44 & Shorter		-	0.5	1.8	0.7	-	-	-	0.9
46		-	11.9	3.5	6.3	-	-	-	10.2
48		-	65.0	27.2	24.7	-	-	-	62.0
50		-	22.4	65.4	63.9	-	-	-	20.7
52 & Longer		-	0.1	2.1	4.4	-	-	-	6.1
Average Staple		-	48.19	49.25	49.30	-	-	-	48.42
Average Length		-	1.40	1.43	1.43	-	-	-	1.41
EXTRANEIOUS MATTER									
Bark		-	*	-	*	-	-	-	1.2
Grass		-	-	*	0.1	-	-	-	0.8
Spindle Twist		-	*	*	0.2	-	-	-	0.2
Preparation		-	-	-	*	-	-	-	-
All Other		-	0.1	*	*	-	-	-	0.1

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Feb 06, 2020

Quality Designation	Arizona		California		New Mexico		Texas	
	Week	Season	Week	Season	Week	Season	Week	Season
MIKE								
2.4 & Below	-	-	-	*	-	-	-	-
2.5 - 2.6	-	-	-	*	-	-	-	-
2.7 - 2.9	-	*	-	0.1	-	-	-	*
3.0 - 3.2	-	1.3	*	0.5	-	-	-	1.2
3.3 - 3.4	-	8.9	1.5	1.0	-	-	-	2.0
3.5 - 3.6	-	18.8	1.4	2.4	-	-	-	6.6
3.7 - 4.2	-	67.4	50.1	58.7	-	-	-	72.8
4.3 - 4.9	-	3.6	46.9	37.3	-	-	-	17.4
5.0 - 5.2	-	-	*	*	-	-	-	-
5.3 & Above	-	-	*	*	-	-	-	-
Average	-	3.79	4.20	4.14	-	-	-	3.97
ALL RANGE MIKE								
2.4 & Below	-	-	-	*	-	-	-	-
2.5	-	-	-	*	-	-	-	-
2.6	-	-	-	*	-	-	-	-
2.7	-	-	-	*	-	-	-	-
2.8	-	-	-	*	-	-	-	-
2.9	-	*	-	0.1	-	-	-	*
3.0	-	*	*	0.1	-	-	-	*
3.1	-	0.5	*	0.2	-	-	-	0.4
3.2	-	0.8	*	0.2	-	-	-	0.8
3.3	-	3.0	0.6	0.3	-	-	-	0.8
3.4	-	5.9	1.0	0.6	-	-	-	1.2
3.5	-	7.5	0.4	0.8	-	-	-	2.0
3.6	-	11.4	1.1	1.5	-	-	-	4.6
3.7	-	12.5	2.7	2.9	-	-	-	9.9
3.8	-	15.6	5.4	5.8	-	-	-	15.6
3.9	-	16.9	8.3	9.2	-	-	-	14.1
4.0	-	10.5	9.7	12.2	-	-	-	13.2
4.1	-	8.3	11.3	13.8	-	-	-	11.8
4.2	-	3.7	12.6	14.9	-	-	-	8.2
4.3	-	2.6	15.0	14.9	-	-	-	7.6
4.4	-	0.6	13.6	12.4	-	-	-	6.1
4.5	-	0.3	10.7	6.6	-	-	-	3.0
4.6	-	*	4.8	2.4	-	-	-	0.7
4.7	-	-	2.3	0.8	-	-	-	*
4.8	-	-	0.5	0.2	-	-	-	*
4.9	-	-	0.1	*	-	-	-	*
5.0	-	-	*	*	-	-	-	-
5.1	-	-	*	*	-	-	-	-
5.2	-	-	*	*	-	-	-	-
5.3 & Above	-	-	*	*	-	-	-	-
Average	-	3.79	4.20	4.14	-	-	-	3.97
STRENGTH 1/ 36 & Below	-	*	*	0.1	-	-	-	0.2
37	-	*	0.4	0.2	-	-	-	1.5
38	-	0.1	1.8	1.2	-	-	-	1.4
39	-	0.5	3.0	3.2	-	-	-	2.0
40	-	2.1	3.8	3.3	-	-	-	2.5
41	-	7.8	4.3	2.7	-	-	-	9.9
42	-	15.8	8.5	4.6	-	-	-	13.3
43	-	26.9	16.0	9.9	-	-	-	16.6
44	-	25.4	24.9	18.5	-	-	-	21.5
45	-	14.9	24.0	25.5	-	-	-	17.8
46	-	4.9	10.7	18.8	-	-	-	10.1
47	-	0.9	1.9	8.5	-	-	-	2.4
48 & Above	-	0.5	0.7	3.3	-	-	-	0.8
Average	-	43.82	44.10	44.82	-	-	-	43.79
UNIFORMITY								
83 & Below	-	0.9	0.1	0.4	-	-	-	0.7
84	-	8.4	3.9	4.8	-	-	-	3.0
85	-	39.4	11.5	15.2	-	-	-	22.4
86	-	48.1	59.6	54.4	-	-	-	62.0
87	-	3.1	22.5	23.6	-	-	-	11.6
88 & Above	-	0.1	2.4	1.6	-	-	-	0.4
Average	-	85.89	86.54	86.46	-	-	-	86.27
Samples Classed	-	12,610	24,256	553,860	-	-	-	15,020

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.