



Volume 20, No.20

State	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
AL	28	66.8	58.3	57,011	29	64.0	53.2	568,279
AR	22	76.0	54.8	60,803	28	71.1	52.3	1,084,595
AZ	13	71.1	50.5	33,012	13	73.9	51.0	135,365
CA	7	92.9	80.0	14,714	14	90.5	75.1	106,025
FL	3	56.0	45.1	6,092	4	63.1	51.8	51,361
GA	59	69.2	58.4	137,933	59	80.8	66.7	1,251,407
KS	3	45.1	33.5	6,493	3	52.5	43.7	30,205
LA	13	45.3	23.5	17,310	19	57.3	31.9	380,024
MO	17	74.5	50.2	50,298	21	68.5	48.4	683,864
MS	35	72.9	45.7	87,986	38	76.8	49.3	1,165,221
NC	33	82.8	62.4	52,242	33	76.0	58.1	615,089
NM	2	91.6	77.8	3,068	2	92.7	79.1	15,045
OK	11	84.5	72.6	32,957	11	82.4	69.5	183,926
SC	16	83.5	60.8	29,099	16	80.9	67.4	255,694
TN	18	65.4	37.5	42,719	22	46.2	28.5	721,703
TX	155	72.1	58.0	472,148	185	66.6	48.9	4,025,529
VA	4	91.1	61.9	15,156	4	80.9	56.0	149,839
United States	439	72.7	55.9	1,119,041	501	69.6	51.2	11,423,171
AMERICAN PIMA								
AZ	2			877	4			12,333
CA	15			37,272	17			352,909
NM*	-			-	-			-
TX*	-			-	-			-
United States	19			42,352	23			381,927
United States all cotton	456			1,161,393	516			11,805,098

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE													
For The Week Ending Dec 13 2018													
Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	0.3	0.3	*	0.2	10.7	13.7	67.4	59.3	-	-	0.2	1.3
	3	0.1	0.5	*	0.2	2.7	5.3	8.1	12.0	-	*	0.4	2.5
	4	*	*	-	*	*	0.4	0.1	0.1	-	-	*	0.2
	5	-	*	-	-	-	*	-	*	-	-	*	*
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
	Total	----	0.4	0.9	*	0.4	13.4	19.5	75.6	71.4	-	*	0.7
31	1 - 2	1.5	1.6	0.4	0.5	15.5	9.9	11.9	9.7	0.1	0.2	1.3	4.0
	3	7.8	14.2	4.2	4.6	16.8	11.5	9.6	12.2	4.4	5.5	7.4	26.7
	4	3.8	7.2	1.9	3.2	2.1	1.7	0.5	1.7	4.2	3.4	3.0	13.2
	5	0.4	0.5	0.2	0.4	0.1	0.1	-	0.1	*	0.1	0.2	0.8
	6	*	*	-	*	-	*	-	*	-	-	*	*
	7	-	-	-	-	-	*	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
	Total	----	13.5	23.6	6.7	8.7	34.4	23.2	22.0	23.8	8.7	9.2	12.0
41	1 - 2	1.6	0.9	1.4	0.6	6.1	6.8	0.1	*	0.4	0.4	2.5	1.0
	3	18.7	15.3	20.1	15.6	19.6	21.1	0.8	0.3	17.4	16.3	30.1	14.8
	4	28.8	22.5	29.7	30.2	9.4	9.0	0.2	0.1	29.2	36.0	28.8	18.7
	5	11.7	7.4	6.5	11.1	2.4	1.5	*	*	4.8	6.5	4.9	3.8
	6	2.0	1.0	0.2	1.0	0.3	0.2	-	*	0.2	0.1	0.1	0.1
	7	0.1	*	*	*	*	*	-	*	-	-	*	*
	8	-	-	-	*	-	-	-	-	-	-	-	*
	Total	----	62.8	47.2	57.9	58.5	37.8	38.5	1.1	0.5	51.9	59.4	66.5
51	1 - 2	*	*	0.3	0.1	0.2	0.3	-	-	*	*	0.1	*
	3	0.7	0.4	5.1	1.6	0.8	2.3	*	*	1.6	1.4	1.3	0.5
	4	2.6	1.3	10.7	6.2	0.4	2.4	-	-	7.7	5.7	3.2	1.1
	5	3.2	1.4	6.7	5.1	0.1	0.7	-	-	4.8	3.6	1.5	0.6
	6	1.4	0.6	1.0	0.8	0.1	0.1	-	-	0.5	0.3	0.3	0.1
	7	0.3	0.1	*	*	-	*	-	-	-	*	*	*
	8	*	*	*	*	-	*	-	-	-	*	*	*
	Total	----	8.2	3.8	24.0	13.7	1.6	5.8	*	*	14.6	11.1	6.4
61	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	*	-	-	-	*	-	*
	4	-	*	-	*	-	-	-	-	*	0.1	-	-
	5	*	*	-	*	-	-	-	-	0.1	*	*	*
	6	*	*	*	*	-	-	-	-	-	-	*	*
	7	*	*	*	*	-	-	-	-	-	*	-	-
	8	*	*	-	-	-	*	-	-	-	*	-	-
	Total	----	*	*	*	*	-	*	-	-	0.1	0.1	*
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	*
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	*	*
	Total	----	-	-	-	-	-	-	-	-	-	-	*
12 & 22	1 - 2	*	*	-	*	0.2	2.4	0.3	0.7	-	*	*	0.1
	3	*	*	-	*	0.5	1.2	0.3	0.5	-	-	*	0.1
	4	-	*	-	*	*	0.4	*	*	-	-	*	*
	5	-	-	-	-	-	0.1	-	-	-	-	-	*
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
	Total	----	*	*	-	*	0.7	4.1	0.6	1.3	-	*	0.1
32	1 - 2	0.1	0.1	*	*	0.5	0.2	0.2	0.5	-	*	0.2	0.3
	3	0.7	1.6	0.1	0.3	2.4	1.2	0.4	2.0	0.2	0.2	1.4	2.3
	4	0.6	1.4	0.1	0.2	0.3	0.4	0.1	0.3	0.3	0.2	0.6	1.1
	5	0.1	0.2	*	*	*	0.2	*	*	-	*	0.1	0.1
	6	*	*	-	*	-	0.1	-	-	-	-	*	*
	7	-	*	-	-	-	*	-	-	-	-	-	-
	8	-	-	-	-	-	*	-	-	-	-	-	-
	Total	----	1.5	3.4	0.2	0.6	3.3	2.2	0.6	2.9	0.5	0.3	2.3
42	1 - 2	0.2	0.2	*	0.1	0.1	0.2	*	*	*	0.1	0.2	0.1
	3	2.2	4.7	1.5	4.0	2.9	1.7	0.1	0.1	3.2	2.3	3.1	1.5
	4	3.9	8.6	4.1	7.6	2.8	1.9	*	*	7.4	4.4	4.1	2.5
	5	2.4	3.0	1.1	2.2	0.7	0.4	-	*	1.2	1.0	0.9	0.7
	6	0.5	0.4	*	0.2	0.1	0.1	-	-	*	*	*	*
	7	0.1	*	-	*	*	*	-	-	-	-	*	*
	8	-	*	-	-	-	*	-	-	-	-	-	-
	Total	----	9.3	16.9	6.8	14.1	6.6	4.3	0.1	0.1	11.9	7.8	8.3

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 13 2018

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	*	*	*	*	*	*	-	*	-	*	*	*
	3	0.4	0.3	0.2	0.3	0.1	0.2	-	-	1.0	1.2	0.2	0.1
	4	0.6	0.8	1.3	1.3	0.2	0.8	-	-	5.4	5.2	0.5	0.2
	5	0.6	0.6	0.9	1.1	0.2	0.3	-	-	2.3	3.1	0.3	0.1
	6	0.1	0.2	0.1	0.2	*	*	-	-	0.2	0.5	0.1	*
	7	*	*	*	*	-	*	-	-	*	*	*	*
	8	-	*	-	-	-	*	-	-	-	*	-	*
Total	----	1.7	1.9	2.5	2.9	0.4	1.4	-	*	8.9	10.1	1.0	0.4
62	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	*	*	-	*	-	*	-	-	-	*	-	*
	4	-	*	*	*	-	-	-	-	0.1	0.1	*	*
	5	*	*	*	*	-	*	-	-	*	0.1	-	*
	6	*	*	*	*	-	-	-	-	*	*	-	*
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	*	-	-	-	-	-	-
Total	----	*	*	*	*	-	*	-	-	0.1	0.2	*	*
13 & 23	1 - 2	-	*	-	*	*	0.1	-	*	-	-	*	*
	3	*	*	-	*	0.4	0.1	-	*	-	-	*	*
	4	-	-	-	*	0.1	0.1	-	-	-	-	*	*
	5	-	-	-	-	-	*	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	*	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	-	*	0.5	0.3	-	*	-	-	*	*
33	1 - 2	*	*	-	-	-	*	-	-	-	-	0.1	0.1
	3	0.1	0.1	*	*	0.1	0.1	-	*	-	*	0.3	0.3
	4	0.1	0.1	*	*	0.2	0.1	-	*	*	*	0.2	0.1
	5	*	*	-	*	0.1	0.1	-	-	-	-	*	*
	6	*	*	-	-	*	*	-	-	-	-	*	*
	7	-	*	-	-	-	*	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.2	0.2	*	*	0.5	0.3	-	*	*	*	0.5	0.5
43	1 - 2	*	*	-	*	-	-	-	-	-	-	*	*
	3	0.4	0.3	0.2	0.2	*	*	-	*	0.6	0.2	0.6	0.2
	4	0.7	0.8	0.7	0.4	0.3	0.2	-	*	0.7	0.4	0.9	0.3
	5	0.4	0.4	0.2	0.2	0.1	0.1	-	-	0.1	0.1	0.2	0.1
	6	0.1	0.1	*	*	*	*	-	-	-	*	*	*
	7	*	*	-	-	-	*	-	-	-	-	*	*
	8	-	-	-	-	-	*	-	-	-	-	-	-
Total	----	1.6	1.5	1.1	0.8	0.5	0.3	-	*	1.4	0.7	1.8	0.6
53	1 - 2	-	*	*	*	-	-	-	-	-	-	*	*
	3	0.1	0.1	*	*	-	*	*	*	0.1	0.1	*	*
	4	0.2	0.2	0.3	0.1	*	*	-	-	0.9	0.4	0.1	*
	5	0.1	0.1	0.2	0.1	*	*	-	-	0.6	0.4	0.1	*
	6	*	*	*	*	*	*	-	-	*	0.1	*	*
	7	*	*	-	*	-	*	-	-	-	*	*	*
	8	-	*	-	-	-	*	-	-	-	-	*	*
Total	----	0.5	0.4	0.6	0.3	*	*	*	*	1.7	0.9	0.2	0.1
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	*	-	-	-	-	-	-	-	*	-	-
	4	*	*	*	*	-	-	-	-	-	*	*	*
	5	-	*	*	*	-	-	-	-	-	*	*	*
	6	-	*	-	*	-	-	-	-	-	-	-	*
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	*	*	-	-	-	-	-	*	*	*
24 - 54	1 - 8	0.3	0.1	0.2	*	0.2	0.1	-	*	-	*	0.2	0.1
25 - 35	1 - 8	*	*	-	-	-	-	-	-	-	-	*	*
81 - 85	1 - 8	*	*	*	*	-	-	-	-	-	*	*	*
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	*	-	-	-	-	-	-	-	-	*	*
31		*	*	-	-	-	-	-	*	-	-	*	*
32		*	*	-	*	*	*	-	*	-	*	0.1	0.1
33		0.4	0.4	*	*	0.5	0.2	-	0.1	0.4	0.1	1.2	1.0
34		2.3	2.9	0.2	0.4	3.1	2.4	*	0.1	1.4	0.6	6.7	5.3
35		10.8	10.5	3.3	2.9	8.5	8.4	3.7	2.2	4.1	3.0	14.4	13.6
36		23.8	21.4	15.9	11.9	16.8	20.6	14.2	8.2	20.5	11.4	19.0	18.7
37		39.3	37.2	37.8	36.9	26.8	31.7	26.0	26.5	34.1	34.5	28.6	28.7
38		17.4	20.5	23.5	26.7	16.2	17.1	16.9	23.6	22.2	34.2	20.3	22.8
39		5.4	6.1	15.3	15.5	16.2	12.5	20.7	21.5	17.0	15.8	8.3	8.6
40 & Longer		0.6	0.8	4.1	5.7	11.9	7.3	18.4	17.7	0.3	0.4	1.2	1.1
Average Staple		36.76	36.82	37.44	37.56	37.43	37.21	37.95	38.10	37.23	37.48	36.67	36.77
Average Length		1.15	1.15	1.17	1.17	1.17	1.16	1.19	1.19	1.16	1.17	1.14	1.15

1/ Below Grade Color. 2/ Below Grade Leaf. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 13 2018

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	1.8	2.4	0.2	0.7	0.2	0.8	0.2	0.5	*	0.1	16.6	12.7
	3	3.6	3.5	0.3	1.2	0.2	0.8	0.1	0.9	0.1	0.2	6.7	6.0
	4	0.1	0.3	*	0.1	-	*	*	0.1	*	*	0.3	0.1
	5	-	*	-	*	-	*	-	*	-	*	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	5.6	6.2	0.5	2.0	0.3	1.6	0.3	1.5	0.2	0.3	23.5	18.9
31	1 - 2	4.3	5.4	2.3	3.0	0.9	0.9	1.5	1.9	0.8	1.7	23.0	20.4
	3	16.9	21.9	12.4	17.1	5.4	6.8	9.7	14.6	12.9	14.3	16.7	25.4
	4	4.9	7.9	2.8	6.9	1.5	3.3	4.3	7.5	7.9	7.5	1.1	2.9
	5	0.6	1.1	0.1	0.4	0.1	0.3	0.2	0.5	0.6	0.8	-	0.1
	6	*	0.1	-	*	-	*	*	*	*	*	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	*	-	-
Total	----	26.8	36.4	17.7	27.4	7.9	11.4	15.6	24.5	22.2	24.3	40.9	48.8
41	1 - 2	1.3	0.5	2.7	1.8	0.8	0.8	2.9	1.1	1.4	1.6	3.6	2.4
	3	9.3	8.4	24.7	18.0	26.3	20.6	20.9	16.5	25.8	24.0	18.8	15.6
	4	19.3	13.2	16.2	19.4	36.4	33.9	31.1	30.9	27.3	23.8	9.5	9.5
	5	9.5	5.7	1.8	4.5	7.1	9.1	8.5	10.3	7.1	5.1	2.2	3.0
	6	0.8	0.7	0.1	0.3	0.1	0.4	0.4	0.7	0.8	0.3	0.1	0.3
	7	*	*	-	*	-	*	*	*	*	*	-	*
	8	-	-	-	-	-	-	-	*	-	*	-	-
Total	----	40.3	28.5	45.6	44.0	70.7	64.9	63.9	59.5	62.4	54.9	34.3	30.9
51	1 - 2	-	-	1.1	0.2	*	*	*	*	0.1	0.1	-	-
	3	-	*	4.9	1.4	1.3	0.5	0.8	0.3	2.2	1.2	-	*
	4	0.3	0.3	5.0	1.6	6.5	3.6	3.5	1.5	3.1	1.8	0.5	0.3
	5	2.0	0.6	1.4	0.6	4.9	2.9	2.5	1.5	2.2	0.8	0.3	0.2
	6	1.1	0.3	0.1	0.1	0.4	0.3	0.4	0.3	0.3	0.1	-	*
	7	*	*	-	*	*	*	*	*	-	*	-	-
	8	-	-	-	*	-	-	-	*	*	*	-	-
Total	----	3.5	1.2	12.5	3.8	13.0	7.4	7.3	3.7	8.0	4.1	0.7	0.6
61	1 - 2	-	-	-	-	-	-	-	-	-	*	-	-
	3	-	-	*	*	-	-	-	*	0.1	*	-	-
	4	-	-	*	*	-	*	*	*	0.1	*	-	-
	5	-	-	-	*	-	-	*	*	*	*	-	-
	6	-	-	-	*	*	*	*	*	-	-	-	-
	7	-	-	-	-	-	-	*	*	-	-	-	-
	8	-	-	-	*	-	-	-	-	-	-	-	-
Total	----	-	-	*	*	*	*	*	*	0.2	*	-	-
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	-	-	-	-	-
12 & 22	1 - 2	-	*	-	*	*	*	-	*	-	*	-	*
	3	*	1.0	-	*	-	*	*	*	*	*	-	*
	4	-	0.5	-	*	-	*	*	*	*	*	-	-
	5	-	*	-	-	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	1.5	-	0.1	*	*	*	*	*	*	-	*
32	1 - 2	*	*	0.1	0.2	*	*	0.1	0.1	*	0.1	-	-
	3	2.6	1.3	1.0	1.2	0.3	0.4	0.7	0.5	0.5	0.8	-	*
	4	3.4	2.5	0.5	0.7	0.2	0.2	0.7	0.4	0.5	0.5	*	0.1
	5	0.5	1.0	*	*	*	*	0.1	*	*	*	-	*
	6	-	*	-	*	-	-	*	*	*	*	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	6.6	4.9	1.7	2.1	0.5	0.7	1.5	1.0	1.0	1.5	*	0.1
42	1 - 2	-	-	0.5	0.4	0.1	0.1	0.1	0.1	0.1	0.4	-	*
	3	0.1	*	5.2	4.5	1.8	3.7	1.7	1.4	1.5	5.1	0.3	0.3
	4	2.3	1.1	5.1	5.7	3.6	6.5	3.7	3.5	1.7	4.6	0.2	0.1
	5	2.5	1.2	1.0	1.3	0.7	1.7	2.2	2.0	0.3	0.8	-	-
	6	0.2	0.2	*	0.1	*	0.1	0.2	0.2	*	*	-	-
	7	-	*	-	*	-	-	-	*	-	*	-	-
	8	-	-	-	-	-	-	-	-	*	*	-	-
Total	----	5.1	2.5	11.8	12.0	6.3	12.0	7.8	7.1	3.6	10.9	0.5	0.4

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 13 2018

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	0.1	0.1	-	*	*	*	*	0.1	-	-
	3	-	-	1.8	1.6	*	0.1	0.2	0.1	0.4	1.0	-	*
	4	2.9	0.6	2.6	2.3	0.2	0.7	0.5	0.5	0.6	1.3	-	-
	5	5.9	1.5	0.9	0.9	0.2	0.6	0.4	0.8	0.1	0.5	-	-
	6	1.1	0.3	*	0.1	*	0.1	0.2	0.2	*	0.1	-	-
	7	*	*	-	*	-	-	*	*	-	*	-	-
	8	-	-	-	-	-	-	-	-	*	*	-	-
Total	----	9.9	2.5	5.4	5.0	0.5	1.5	1.3	1.6	1.2	2.9	-	*
62	1 - 2	-	-	*	*	-	-	*	*	-	*	-	-
	3	-	-	-	*	*	*	*	*	0.1	*	-	-
	4	-	-	-	*	-	*	*	*	0.2	*	-	-
	5	-	-	-	*	-	-	*	*	*	*	-	-
	6	*	*	-	*	-	-	0.1	*	-	*	-	-
	7	-	-	-	*	-	-	*	*	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	*	-	-
Total	----	*	*	*	0.1	*	*	0.1	*	0.3	0.1	-	-
13 & 23	1 - 2	-	*	-	*	*	*	-	-	-	*	-	0.1
	3	-	1.0	-	-	-	-	-	-	*	*	-	0.1
	4	-	1.2	-	-	-	-	-	-	*	*	-	-
	5	-	*	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	2.2	-	*	*	*	-	-	*	*	-	0.1
33	1 - 2	-	*	*	*	*	*	*	*	*	*	-	*
	3	0.2	0.6	0.1	0.1	*	*	0.1	*	0.1	*	-	0.1
	4	0.4	2.3	0.1	*	0.1	*	0.1	*	*	*	-	-
	5	0.7	1.1	*	*	*	*	*	*	*	*	-	-
	6	0.2	0.1	-	-	-	-	-	-	-	*	-	-
	7	*	*	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	1.4	4.1	0.3	0.1	0.1	*	0.1	0.1	0.1	0.1	-	0.1
43	1 - 2	-	-	0.1	*	*	*	*	*	*	*	-	-
	3	-	*	1.0	0.4	0.2	0.1	0.3	0.1	0.2	0.2	-	*
	4	0.2	0.1	1.6	0.8	0.4	0.2	0.5	0.2	0.3	0.3	-	*
	5	0.2	0.2	0.5	0.3	0.1	0.1	0.3	0.2	0.1	0.1	-	-
	6	0.2	0.1	*	*	*	*	0.1	*	*	*	-	-
	7	-	-	-	-	-	*	-	*	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.5	0.4	3.2	1.5	0.6	0.4	1.3	0.6	0.7	0.6	-	*
53	1 - 2	-	-	*	*	-	-	-	*	-	*	-	-
	3	-	-	0.2	0.3	*	*	*	*	*	0.1	-	-
	4	-	*	0.3	0.6	*	*	0.1	0.1	*	0.1	-	-
	5	-	-	0.3	0.4	*	*	0.1	0.1	*	*	-	*
	6	-	*	*	*	*	*	0.1	*	-	*	-	-
	7	-	*	-	*	-	*	*	*	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-	-	-
Total	----	-	*	0.8	1.4	*	0.1	0.4	0.2	0.1	0.2	-	*
63	1 - 2	-	-	-	*	-	-	-	*	-	*	-	-
	3	-	-	*	0.1	-	-	-	*	-	*	-	-
	4	-	-	*	0.1	-	*	*	*	-	*	-	-
	5	-	-	-	0.1	-	-	-	*	-	*	-	-
	6	*	*	-	*	-	-	-	*	-	*	-	-
	7	-	-	*	*	-	-	*	*	-	-	-	-
	8	-	-	-	-	-	-	-	*	-	-	-	-
Total	----	*	*	*	0.3	-	*	*	*	-	*	-	-
24 - 54	1 - 8	0.1	7.1	0.4	0.2	0.1	*	0.2	0.1	0.1	*	-	*
25 - 35	1 - 8	-	1.1	*	*	-	-	*	*	-	-	-	-
81 - 85	1 - 8	-	1.2	0.1	*	*	*	-	*	*	*	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	*	-	-
30		-	-	-	*	-	-	-	-	-	*	-	-
31		*	*	*	*	-	*	-	*	*	*	-	-
32		*	*	*	*	*	*	*	*	0.2	0.1	-	-
33		*	0.1	0.1	0.3	*	*	0.4	0.3	2.2	0.8	-	0.5
34		2.0	1.5	2.3	2.7	0.1	0.3	2.4	2.4	7.0	5.3	0.9	1.1
35		21.7	15.6	12.0	10.0	2.0	2.6	8.0	7.9	22.0	18.0	4.9	3.9
36		46.1	38.7	17.6	17.7	11.2	11.1	18.0	15.1	23.5	26.3	7.8	8.9
37		27.7	38.2	31.4	27.1	44.4	41.4	31.1	29.2	27.7	27.8	23.2	29.3
38		2.4	4.3	23.5	22.0	26.4	28.5	24.6	27.1	14.1	16.6	28.5	22.3
39		*	0.4	11.7	14.6	12.2	11.8	12.9	15.0	3.0	4.7	16.1	17.3
40 & Longer		-	1.1	1.3	5.5	3.6	4.2	2.6	3.0	0.2	0.4	18.5	16.7
Average Staple		36.07	36.34	37.02	37.21	37.46	37.48	37.15	37.27	36.22	36.45	38.00	37.90
Average Length		1.12	1.13	1.16	1.16	1.17	1.17	1.16	1.16	1.13	1.14	1.19	1.18

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 13 2018

Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	1.2	1.2	0.1	0.2	0.1	0.9	4.6	9.1	0.1	0.1
	3	0.7	2.0	0.6	0.4	0.1	0.7	5.3	6.6	*	0.2
	4	0.1	0.2	0.2	*	-	*	0.7	0.6	*	*
	5	*	*	-	*	-	-	*	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	2.0	3.3	0.8	0.6	0.3	1.6	10.6	16.3	0.1	0.3
31	1 - 2	8.4	5.9	1.3	1.3	1.2	1.7	10.0	7.2	3.3	4.1
	3	24.3	24.6	7.7	11.7	3.6	5.7	27.7	19.2	22.3	24.7
	4	7.6	7.3	5.9	8.9	0.8	1.6	12.0	8.0	6.0	5.1
	5	0.2	0.4	0.5	0.7	0.1	0.1	2.1	1.1	0.1	0.1
	6	-	*	*	*	-	*	0.2	0.1	-	*
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	40.6	38.3	15.3	22.7	5.6	9.1	52.0	35.7	31.7	34.0
41	1 - 2	2.6	2.4	1.4	1.8	5.8	3.7	1.2	1.6	2.4	2.9
	3	23.6	21.8	20.4	18.1	26.1	21.7	7.5	9.2	40.5	34.1
	4	18.7	18.1	27.7	27.3	18.6	15.2	8.1	9.4	18.4	12.6
	5	5.7	4.3	6.9	7.6	3.2	2.3	4.6	3.9	0.8	0.5
	6	0.6	0.5	0.4	0.4	0.1	0.1	1.7	0.9	*	*
	7	*	*	-	*	-	-	0.4	0.2	-	-
	8	-	*	-	*	-	-	0.1	*	-	-
Total	----	51.1	47.2	56.8	55.3	53.8	42.9	23.6	25.1	62.0	50.1
51	1 - 2	*	*	0.5	0.3	0.2	0.1	0.4	0.2	*	*
	3	0.1	0.2	3.7	1.8	7.2	2.2	1.4	0.9	0.4	0.4
	4	0.1	0.4	7.3	2.5	13.0	3.7	0.5	0.7	0.5	0.3
	5	0.2	0.6	4.2	1.7	4.1	1.5	0.2	0.3	0.1	*
	6	0.1	0.2	0.5	0.2	0.2	0.1	0.1	0.2	-	*
	7	*	*	*	*	*	*	0.1	0.1	-	-
	8	*	*	-	-	-	-	0.1	*	-	-
Total	----	0.6	1.5	16.3	6.6	24.7	7.6	2.7	2.3	0.9	0.7
61	1 - 2	-	-	*	*	-	-	*	*	-	-
	3	-	-	0.1	*	-	-	0.2	*	-	-
	4	-	-	0.1	*	*	*	0.1	*	-	*
	5	-	-	*	*	*	*	*	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	-	-	0.2	*	*	*	0.4	0.1	-	*
71	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	-	*	*	-	-
	4	-	-	-	-	-	-	*	*	-	-
	5	-	-	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	*	*	-	-
12 & 22	1 - 2	-	0.1	*	*	*	0.1	0.3	1.9	-	-
	3	*	0.3	*	0.1	-	0.1	0.6	2.0	*	*
	4	-	*	*	*	-	*	0.2	0.4	-	*
	5	-	-	*	*	-	*	*	*	-	*
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	*	0.4	*	0.1	*	0.1	1.1	4.4	*	*
32	1 - 2	*	0.2	0.2	0.3	0.1	0.6	0.4	0.6	0.1	0.2
	3	0.2	1.3	1.0	1.3	0.6	1.8	1.7	2.4	1.1	1.4
	4	0.2	0.9	0.3	0.7	0.1	0.7	1.1	1.7	0.4	0.4
	5	0.1	0.2	*	0.1	*	*	0.3	0.4	-	*
	6	*	*	-	*	-	*	*	*	-	*
	7	-	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	0.5	2.5	1.5	2.3	0.9	3.1	3.6	5.1	1.5	2.1
42	1 - 2	0.5	0.2	0.2	0.6	0.5	1.8	0.1	0.3	0.1	0.5
	3	1.5	1.5	2.2	3.4	4.8	14.4	0.6	1.8	1.9	6.9
	4	1.2	1.5	2.0	3.3	3.6	10.7	0.6	1.8	1.3	3.5
	5	0.4	0.6	0.6	0.9	1.0	1.7	0.4	0.7	0.1	0.2
	6	*	0.2	*	0.1	0.1	0.1	0.2	0.1	-	*
	7	-	*	-	*	-	-	0.1	*	-	-
	8	-	*	-	-	-	-	0.1	*	-	-
Total	----	3.5	3.9	5.0	8.3	9.9	28.6	2.0	4.8	3.3	11.2

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE For The Week Ending Dec 13 2018											
Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	*	*	*	0.1	*	*	0.1	0.1	-	0.1
	3	0.1	0.1	0.6	0.9	0.3	0.8	0.4	0.7	*	0.7
	4	0.2	0.2	1.0	0.9	1.4	2.2	0.4	1.0	*	0.3
	5	0.1	0.2	0.5	0.4	0.7	1.0	0.1	0.4	*	*
	6	*	0.1	0.1	0.1	*	0.1	*	0.1	-	*
	7	-	*	-	*	-	*	*	*	-	-
	8	*	*	-	-	-	-	*	*	-	-
Total	----	0.4	0.6	2.2	2.4	2.5	4.2	0.9	2.3	0.1	1.1
62	1 - 2	-	-	-	*	-	-	*	*	-	-
	3	*	*	*	*	-	*	0.2	0.1	-	-
	4	-	*	*	*	-	*	0.5	0.2	-	-
	5	-	-	*	*	*	*	0.3	0.1	-	-
	6	-	-	*	*	-	*	*	*	-	-
	7	-	-	-	-	-	*	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	*	*	0.1	*	*	*	1.0	0.5	-	-
13 & 23	1 - 2	-	*	-	*	-	*	*	0.2	-	*
	3	-	*	*	*	-	*	0.1	0.2	-	*
	4	-	*	*	*	-	-	*	0.1	-	-
	5	-	*	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	0.1	*	*	-	*	0.2	0.5	-	*
33	1 - 2	-	*	*	*	*	*	*	*	*	*
	3	*	0.3	0.1	0.1	0.1	0.1	0.2	0.2	0.1	*
	4	*	0.2	0.1	0.1	*	*	0.3	0.2	*	*
	5	*	0.1	*	*	-	*	0.1	0.1	-	*
	6	-	*	-	*	-	*	*	*	-	-
	7	-	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	0.1	0.6	0.2	0.2	0.1	0.1	0.6	0.6	0.1	0.1
43	1 - 2	*	*	*	*	0.1	0.1	*	*	-	*
	3	0.2	0.2	0.4	0.3	0.9	1.0	0.1	0.2	0.1	0.2
	4	0.1	0.2	0.5	0.5	0.5	0.8	0.2	0.3	0.1	0.2
	5	0.1	0.2	0.2	0.2	0.1	0.1	0.1	0.1	*	*
	6	*	0.1	*	*	*	*	*	*	-	*
	7	-	*	-	*	-	-	*	*	-	-
	8	-	*	-	-	-	-	*	*	-	-
Total	----	0.5	0.7	1.1	1.0	1.6	2.1	0.4	0.7	0.2	0.4
53	1 - 2	*	*	*	*	*	*	*	*	-	*
	3	0.3	0.1	0.1	*	0.1	0.1	0.1	0.2	-	*
	4	0.2	0.1	0.1	0.1	0.1	0.2	0.1	0.3	-	*
	5	*	*	0.1	0.1	0.1	0.1	0.1	0.2	*	*
	6	-	*	*	*	-	*	*	0.1	-	-
	7	*	*	-	-	-	*	*	*	-	-
	8	-	*	-	-	-	-	-	*	-	-
Total	----	0.6	0.3	0.3	0.3	0.3	0.5	0.3	0.8	*	*
63	1 - 2	-	-	-	-	-	-	*	*	-	-
	3	*	*	-	-	-	*	*	0.1	-	-
	4	*	*	*	*	-	*	0.2	0.2	-	-
	5	-	*	*	*	-	*	0.1	0.2	-	-
	6	-	-	-	-	-	*	*	0.1	-	-
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	*	*	*	*	-	*	0.3	0.5	-	-
24 - 54	1 - 8	0.1	0.5	0.1	*	0.3	0.1	0.2	0.2	*	*
25 - 35	1 - 8	-	*	-	-	-	-	*	*	-	-
81 - 85	1 - 8	*	0.1	*	*	*	*	0.1	0.1	-	-
STAPLE											
28 & Shorter		-	-	-	-	-	-	*	*	-	-
29		-	-	-	-	-	-	*	*	-	-
30		*	*	-	-	-	-	0.1	0.1	-	-
31		*	*	*	*	-	*	0.2	0.4	-	-
32		1.2	0.6	0.4	0.1	-	*	0.7	1.2	-	*
33		2.8	2.3	3.5	1.6	0.3	0.1	2.6	3.6	0.9	0.7
34		7.1	6.7	9.6	5.5	3.3	1.4	9.3	9.8	14.5	9.3
35		11.9	11.6	16.1	10.8	19.4	12.5	20.7	19.2	33.7	26.0
36		22.2	21.2	18.6	16.5	36.0	35.0	25.8	25.1	25.9	30.2
37		30.7	30.3	34.0	30.4	30.2	39.0	27.6	24.7	19.0	22.0
38		14.2	16.4	14.6	26.1	8.9	9.2	9.5	10.5	5.1	9.8
39		8.2	8.8	2.8	8.1	1.5	2.3	3.1	4.5	0.9	1.9
40 & Longer		1.7	2.0	0.5	0.9	0.4	0.4	0.5	0.9	*	0.1
Average Staple		36.51	36.63	36.26	36.83	36.27	36.50	36.06	36.06	35.66	36.01
Average Length		1.14	1.14	1.13	1.15	1.13	1.14	1.12	1.12	1.11	1.12

1/ Below Grade Color. 2/ Below Grade Leaf. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 13 2018

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	15.5	10.2	2.3	1.4	1.0	0.8	-	*	25.4	21.0	18.9	10.5
Bark - Level 2	-	*	-	-	-	-	-	-	-	*	-	*
Grass - Level 1	*	0.1	0.1	0.1	*	*	-	0.1	-	*	*	0.1
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	0.1	*	0.1	*	-	-	*	*	0.1	*	0.1	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	0.2	0.2	*	*	2.4	1.8	-	-	0.3	0.3	0.2	0.1
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	*	*	-	-	-	-	-	-	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	*	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	*	*	-	*	-	-	-	-	-	-	*	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	*	*	*	-	-	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	-	-	*	-	-	-	-	-	-	*	*
23	*	*	-	*	-	-	-	-	*	*	*	*
24	*	0.2	*	*	-	*	-	-	0.1	0.3	0.3	0.3
25	0.5	0.9	0.1	0.2	*	*	-	-	2.0	1.6	1.8	1.9
26	3.1	3.8	1.2	1.3	0.4	0.2	-	*	5.0	6.4	6.9	7.4
27	12.9	14.2	6.3	5.0	1.9	1.6	*	*	18.5	20.3	15.2	16.0
28	26.2	29.6	17.4	17.5	5.2	7.6	0.2	0.4	30.9	38.2	22.1	24.7
29	30.9	29.2	33.5	30.5	13.3	16.8	1.5	1.9	25.8	22.7	24.8	24.6
30	17.1	14.7	23.4	24.3	23.8	23.7	1.6	3.1	15.2	8.0	17.0	15.3
31	6.1	5.4	12.6	13.0	22.1	22.1	3.5	5.9	2.3	2.0	7.4	6.5
32	2.4	1.5	4.0	6.0	15.7	15.9	13.0	14.5	0.2	0.4	2.9	2.3
33	0.6	0.4	1.4	1.8	9.1	7.4	23.5	18.4	*	*	1.0	0.7
34	0.1	0.1	0.2	0.4	4.3	3.1	11.7	10.8	-	*	0.3	0.2
35	*	*	*	0.1	1.9	1.0	10.7	10.3	-	*	0.1	*
36	*	*	*	*	1.1	0.3	15.1	16.6	-	-	*	*
37	-	*	-	-	0.7	0.2	14.1	13.3	-	-	-	*
38	-	-	-	-	0.3	0.1	4.2	4.1	-	-	-	*
39	-	-	-	-	0.1	*	0.4	0.5	-	-	-	-
40 & Above	-	-	-	-	*	*	0.4	0.3	-	-	-	*
Average	29.20	29.03	29.79	29.91	31.37	31.05	34.74	34.59	28.73	28.52	29.09	28.96
Mike												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	-
2.5	-	*	-	-	-	*	*	*	-	-	-	*
2.6	*	*	-	-	-	*	0.2	*	-	-	*	*
2.7	-	*	-	*	-	*	*	0.1	-	-	*	*
2.8	*	*	*	*	*	*	*	0.1	-	-	*	*
2.9	-	*	*	*	-	*	*	0.1	-	-	*	*
3.0	*	*	0.1	*	*	*	*	0.2	-	*	*	*
3.1	0.1	*	0.1	*	*	*	*	0.3	-	-	0.1	0.1
3.2	0.2	0.1	0.2	*	*	0.1	0.1	0.5	-	-	0.2	0.2
3.3	0.4	0.2	0.1	*	0.1	0.1	0.1	0.8	-	*	0.5	0.5
3.4	0.5	0.4	0.1	*	0.1	0.2	*	1.2	-	*	0.8	0.9
3.5	0.8	0.6	0.1	0.1	0.3	0.4	0.7	1.2	-	0.1	1.2	1.4
3.6	1.3	1.1	0.3	0.1	0.3	0.6	1.0	1.9	-	0.2	1.4	1.8
3.7	2.2	2.0	0.4	0.2	0.5	0.8	4.0	2.7	*	0.3	1.8	2.5
3.8	3.8	3.0	0.5	0.4	0.9	1.2	3.1	2.6	0.4	0.9	2.5	3.9
3.9	5.2	4.1	1.0	0.8	1.1	1.8	4.2	3.7	2.9	1.4	4.7	6.3
4.0	6.2	5.9	2.1	1.6	1.5	2.3	2.9	4.1	8.3	3.6	8.2	9.0
4.1	7.8	7.3	3.2	2.8	2.3	3.9	4.5	6.0	5.9	5.8	12.5	12.0
4.2	9.2	9.0	4.6	4.8	4.0	4.7	5.9	7.8	4.8	8.7	15.0	14.3
4.3	11.6	10.7	6.0	6.8	6.0	6.2	9.0	10.0	4.5	12.1	14.9	14.1
4.4	11.0	11.0	8.5	9.9	7.7	7.3	11.1	11.4	7.0	12.7	13.1	12.0
4.5	11.0	10.9	12.4	12.5	9.7	8.5	11.7	10.8	17.8	15.6	9.9	8.8
4.6	10.0	9.8	14.6	13.9	12.2	10.7	13.7	11.1	19.6	14.2	6.1	5.6
4.7	7.8	8.0	14.1	13.2	12.7	12.4	11.1	8.2	14.6	10.5	3.9	3.4
4.8	4.5	6.1	11.5	11.5	11.8	11.4	7.6	6.2	9.5	7.2	1.9	1.7
4.9	2.8	4.2	8.0	8.3	8.7	9.1	2.7	3.3	3.1	4.8	0.7	0.8
5.0	2.0	2.7	6.1	5.6	6.9	7.8	1.2	2.0	0.2	1.4	0.3	0.3
5.1	1.2	1.6	3.6	3.4	6.6	5.9	0.7	1.3	0.8	0.4	0.2	0.1
5.2	0.5	0.9	2.0	2.0	3.9	2.9	1.8	1.4	*	0.1	*	*
5.3	0.2	0.3	0.4	1.0	1.7	1.2	2.2	0.7	0.2	*	*	*
5.4	*	0.1	0.2	0.5	0.5	0.3	0.4	0.2	-	-	*	*
5.5 & Above	*	*	*	0.3	0.4	0.1	-	0.1	-	-	*	*
Average	4.34	4.39	4.60	4.62	4.66	4.61	4.43	4.36	4.48	4.46	4.24	4.21

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 13 2018

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	26.6	23.9	4.9	2.3	1.1	0.7	1.6	0.9	2.2	1.9	0.5	0.6
Bark - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	-	0.1	0.1	0.1	*	0.1	0.1	0.2	*	*	-	-
Grass - Level 2	-	-	-	-	-	-	*	*	-	-	-	-
Prep - Level 1	-	-	-	*	*	*	0.7	0.5	-	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	0.1	0.1	0.1	*	*	0.1	0.1	-	-	-	-
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	*	-	*	-	*	*	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	*	*	-	-	-	*	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	*	*	-	*	*	*	-	-	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	-	0.1	*	*	*	*	*	*	*	*	-	-
Plastic - Level 2	-	-	-	-	-	-	*	*	-	-	-	-
STRENGTH 1/ 22 & Below	-	*	-	*	-	*	*	*	-	-	-	-
23	*	*	-	*	-	*	*	*	0.1	*	-	-
24	*	0.2	-	*	*	*	0.1	0.1	0.3	0.1	-	-
25	0.1	1.1	0.1	0.1	0.1	0.2	0.6	0.4	1.8	0.8	-	-
26	0.2	2.5	0.7	0.7	0.8	1.1	1.6	1.6	4.7	3.0	0.3	0.1
27	3.4	6.6	2.1	3.1	7.1	5.7	5.7	4.9	9.8	7.0	3.5	1.8
28	25.0	23.2	10.6	10.0	19.3	17.4	15.9	13.7	17.3	14.9	6.3	11.7
29	25.3	33.3	30.2	25.9	31.4	28.3	31.5	28.7	21.5	23.5	14.0	22.1
30	30.8	19.9	32.2	28.5	19.7	24.3	28.1	28.4	18.7	21.9	29.6	31.2
31	11.0	8.9	16.3	17.4	11.4	12.7	11.2	14.3	12.3	14.6	27.5	24.0
32	3.9	4.0	5.9	9.1	6.9	6.4	3.8	5.5	6.7	8.3	11.4	7.4
33	0.1	0.2	1.5	3.6	2.6	3.0	1.2	1.9	4.3	4.1	7.1	1.7
34	*	*	0.3	1.1	0.7	0.8	0.2	0.4	1.9	1.4	0.1	*
35	-	*	0.1	0.3	0.1	0.1	*	0.1	0.7	0.2	-	*
36	-	-	*	0.1	*	*	*	*	0.1	*	*	*
37	-	-	*	*	-	*	-	*	*	*	-	-
38	-	-	-	*	-	-	-	-	-	*	*	*
39	-	-	-	-	-	*	-	-	-	-	-	-
40 & Above	-	-	-	-	-	-	-	-	-	-	-	-
Average	29.76	29.46	30.19	30.39	29.86	29.98	29.78	29.99	29.81	30.05	30.79	30.39
Mike												
2.4 & Below	-	*	-	-	-	-	-	-	-	-	-	-
2.5	-	0.2	-	*	-	-	-	-	-	-	-	-
2.6	-	0.5	-	-	-	-	-	-	-	-	-	-
2.7	-	0.7	-	-	-	*	-	-	-	*	0.1	*
2.8	*	1.0	-	-	-	-	-	-	*	*	0.7	0.2
2.9	0.1	0.8	-	-	-	-	-	*	*	*	0.2	0.1
3.0	1.2	1.3	-	*	-	*	-	*	*	*	0.3	0.4
3.1	2.2	2.5	*	*	-	*	-	*	*	*	0.7	0.3
3.2	5.6	3.5	*	*	-	*	-	*	*	*	-	0.3
3.3	3.0	5.9	*	*	-	*	*	*	0.1	0.1	0.3	0.6
3.4	5.3	7.2	*	*	*	*	*	*	0.1	0.1	2.5	1.6
3.5	6.1	6.7	-	*	*	*	0.1	*	0.4	0.2	2.6	2.7
3.6	10.0	7.4	*	*	*	0.1	0.1	0.1	0.7	0.3	5.8	5.0
3.7	8.8	10.4	*	0.1	0.1	0.2	0.3	0.2	0.9	0.5	6.6	3.7
3.8	10.0	9.7	*	0.1	0.1	0.4	0.7	0.4	1.4	0.8	6.9	7.2
3.9	17.0	9.5	*	0.3	0.4	0.7	0.8	0.7	1.8	1.3	6.5	8.0
4.0	9.5	8.0	*	0.5	0.8	1.1	1.2	1.1	2.8	2.1	5.3	9.3
4.1	8.4	8.0	0.5	1.1	2.1	2.1	1.6	1.9	3.2	3.2	4.7	6.1
4.2	5.1	4.7	1.4	1.9	3.5	3.9	2.8	3.0	5.1	4.8	9.1	9.8
4.3	3.3	4.9	2.3	2.8	5.5	6.0	4.1	4.4	7.6	7.0	7.8	8.9
4.4	1.8	4.2	3.1	3.6	8.2	8.3	6.1	6.5	10.4	9.7	6.1	7.6
4.5	2.3	2.0	6.5	6.2	10.8	10.7	8.3	9.2	12.9	13.1	5.6	6.6
4.6	0.4	0.9	6.4	9.4	12.6	11.6	12.5	13.3	14.9	15.1	8.3	6.3
4.7	*	0.1	11.0	13.6	13.5	12.4	16.4	16.2	13.4	14.3	11.5	6.4
4.8	*	*	14.1	16.4	12.8	11.3	15.8	16.4	9.4	11.1	3.1	4.5
4.9	-	*	16.0	15.8	10.3	10.0	13.1	13.1	6.6	7.3	2.2	1.9
5.0	-	*	18.4	12.9	7.7	7.6	9.3	7.3	4.2	4.6	1.4	1.1
5.1	-	*	11.5	8.1	6.2	5.8	4.6	3.4	2.2	2.5	0.5	1.1
5.2	-	-	5.8	4.5	3.2	4.0	1.4	1.6	1.4	1.3	1.0	0.2
5.3	-	-	2.2	1.9	1.4	2.4	0.6	0.8	0.3	0.5	-	-
5.4	-	-	0.6	0.5	0.7	1.0	0.2	0.3	0.1	0.1	-	-
5.5 & Above	-	-	0.1	0.2	0.1	0.4	0.1	*	*	*	-	-
Average	3.79	3.75	4.85	4.79	4.69	4.69	4.69	4.68	4.53	4.57	4.19	4.18

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 13 2018

Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter										
Bark - Level 1	3.9	4.2	2.7	4.1	0.6	0.3	7.4	6.0	0.2	0.3
Bark - Level 2	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	*	*	*	0.1	0.1	*	*	0.3	-	*
Grass - Level 2	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	*	*	*	*	*	*	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	*	-	*	*	*	1.6	1.3	-	-
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	-	-	*	*	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	*	-	-	*	*	-	-
Other - Level 2	-	-	-	-	-	-	-	*	-	-
Plastic - Level 1	*	*	-	*	*	*	*	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	*	*	-	-	-	*	0.1	0.2	-	-
23	*	*	0.3	0.1	*	*	0.2	0.3	*	*
24	0.1	0.1	1.3	0.4	0.1	*	0.4	0.6	0.1	0.3
25	0.1	0.2	5.1	2.6	0.8	0.3	0.9	1.3	1.8	2.1
26	0.6	0.7	11.2	6.7	5.7	2.6	2.2	2.7	5.8	5.3
27	2.8	3.6	17.8	12.4	18.2	11.4	5.0	5.8	13.4	12.2
28	8.2	9.6	22.3	20.7	28.9	25.5	10.5	12.0	24.5	23.9
29	19.6	19.6	19.1	26.3	22.9	27.6	17.2	18.4	22.3	26.3
30	27.2	24.3	11.8	18.6	12.9	17.4	20.1	20.4	15.4	16.2
31	19.0	18.0	6.9	7.8	5.8	9.3	19.7	17.8	9.2	8.6
32	13.2	13.1	2.8	2.9	3.2	4.0	14.4	11.7	4.5	3.4
33	7.3	7.4	0.9	1.2	1.1	1.5	6.4	5.8	2.1	1.3
34	1.5	2.7	0.3	0.3	0.3	0.3	2.2	2.2	0.7	0.4
35	0.3	0.6	0.2	*	0.1	0.1	0.7	0.7	0.1	0.1
36	0.1	0.1	*	*	*	*	0.1	0.2	*	*
37	*	*	*	*	-	*	0.1	*	-	-
38	*	*	-	-	-	-	*	*	-	-
39	-	-	-	-	-	-	*	*	-	-
40 & Above	-	-	-	-	-	-	*	*	-	-
Average	30.72	30.72	28.65	29.16	28.99	29.44	30.56	30.33	29.27	29.22
Mike										
2.4 & Below	-	*	-	-	-	-	0.1	*	-	-
2.5	-	*	-	-	-	-	0.3	0.1	-	-
2.6	*	*	-	*	-	-	0.4	0.1	-	-
2.7	*	*	-	-	-	-	0.4	0.1	-	-
2.8	0.2	0.1	-	-	-	-	0.5	0.1	-	-
2.9	0.1	0.1	-	*	-	-	0.7	0.2	-	-
3.0	0.1	0.1	-	-	-	*	0.9	0.3	-	-
3.1	0.1	0.1	-	*	0.1	*	1.3	0.5	-	-
3.2	0.2	0.2	-	*	0.1	*	1.7	0.7	-	-
3.3	0.3	0.3	*	*	0.1	*	2.3	1.0	-	*
3.4	0.4	0.4	*	0.1	0.1	*	2.7	1.4	-	-
3.5	0.8	0.6	*	0.2	0.4	0.1	3.5	1.8	*	*
3.6	1.4	0.8	0.1	0.4	0.4	0.1	4.2	2.2	-	*
3.7	2.7	1.5	0.5	0.8	0.6	0.2	5.0	2.8	*	0.1
3.8	3.3	2.5	1.0	1.6	0.5	0.3	5.4	3.4	*	*
3.9	5.1	3.7	1.7	3.0	0.7	0.5	6.3	4.1	0.1	0.1
4.0	6.4	5.7	3.2	5.6	1.3	1.0	6.8	4.8	0.3	0.2
4.1	6.5	7.7	7.6	9.5	1.8	1.7	7.2	5.5	0.6	0.5
4.2	7.3	8.6	9.8	12.7	2.8	2.5	7.2	6.2	1.8	1.6
4.3	8.9	9.3	13.5	14.8	4.0	3.7	7.3	7.0	4.1	3.4
4.4	10.2	10.7	17.6	15.2	6.5	5.5	7.0	7.6	6.8	7.2
4.5	11.0	11.6	13.7	12.3	9.7	7.9	6.5	8.2	14.7	14.2
4.6	9.3	9.9	11.2	9.4	10.4	10.0	6.1	8.4	20.6	20.6
4.7	8.6	8.2	8.7	6.6	10.7	11.5	5.1	8.0	20.3	20.5
4.8	6.3	6.7	5.6	4.2	13.1	12.9	4.1	7.1	15.2	15.5
4.9	4.4	4.8	2.9	1.9	14.1	12.2	3.1	5.8	10.0	8.8
5.0	3.1	3.0	1.8	1.1	9.9	11.0	1.9	4.3	3.3	4.3
5.1	2.2	1.8	0.8	0.4	5.0	8.4	1.1	3.2	1.2	1.9
5.2	0.7	1.0	0.2	0.1	3.9	5.5	0.6	2.2	0.6	0.7
5.3	0.2	0.3	*	*	2.5	3.1	0.2	1.4	0.3	0.2
5.4	0.2	0.1	-	*	1.0	1.5	0.1	0.9	0.1	*
5.5 & Above	0.1	0.1	-	*	0.2	0.3	*	0.6	-	*
Average	4.38	4.41	4.43	4.36	4.71	4.76	4.12	4.40	4.65	4.66

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 13 2018

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	*	*	-	-	-	*	0.2	*	-	-	*	*
2.7 - 2.9	*	*	*	*	*	0.1	0.1	0.3	-	-	*	*
3.0 - 3.2	0.3	0.1	0.4	0.1	0.1	0.2	0.1	1.0	-	*	0.4	0.4
3.3 - 3.4	0.9	0.7	0.2	0.1	0.2	0.3	0.1	1.9	-	*	1.3	1.4
3.5 - 3.6	2.1	1.7	0.4	0.2	0.6	0.9	1.7	3.1	-	0.3	2.6	3.2
3.7 - 4.2	34.3	31.3	11.8	10.7	10.4	14.7	24.6	26.9	22.4	20.6	44.7	48.1
4.3 - 4.9	58.6	60.6	75.1	76.1	68.8	65.5	66.9	61.0	76.2	77.2	50.5	46.5
5.0 - 5.2	3.6	5.2	11.6	11.1	17.4	16.7	3.7	4.7	1.1	1.9	0.5	0.5
5.3 & Above	0.2	0.5	0.6	1.8	2.6	1.6	2.5	1.0	0.2	*	*	*
Average	4.34	4.39	4.60	4.62	4.66	4.61	4.43	4.36	4.48	4.46	4.24	4.21
Leaf												
1 - 2	3.7	3.3	2.2	1.5	33.5	33.6	79.9	70.2	0.5	0.7	4.7	6.9
3	31.3	37.5	31.5	27.0	46.3	44.9	19.2	27.2	28.7	27.2	44.8	49.0
4	41.3	43.1	49.0	49.3	15.9	17.3	0.9	2.3	55.9	56.0	41.6	37.5
5	19.0	13.7	15.7	20.1	3.8	3.5	*	0.2	14.0	15.0	8.3	6.3
6	4.2	2.2	1.5	2.1	0.6	0.5	-	*	0.9	1.1	0.5	0.3
7	0.6	0.2	*	*	*	0.1	-	*	*	*	*	*
8	*	*	*	*	-	0.1	-	-	-	*	*	*
Average	3.90	3.75	3.83	3.94	2.87	2.89	2.01	2.16	3.86	3.89	3.55	3.44
HVI Trash 1/												
00	-	-	-	-	-	*	*	*	-	-	-	-
01	0.3	0.2	0.1	0.1	8.9	10.4	39.4	31.7	-	*	0.3	0.6
02	5.2	5.1	3.5	2.3	29.2	28.8	41.5	43.3	1.2	1.4	6.4	8.9
03	15.0	17.8	13.8	10.9	27.5	26.6	14.5	18.5	10.8	10.6	20.1	22.7
04	19.6	24.6	22.7	20.1	16.7	16.5	3.8	4.8	25.8	25.3	26.2	26.0
05	19.1	20.9	22.9	22.4	8.6	9.0	0.7	1.2	28.9	27.4	21.3	19.9
06	15.5	13.9	17.0	18.5	4.3	4.4	0.1	0.4	17.6	18.7	13.2	11.8
07	10.6	8.4	10.5	12.3	2.3	2.1	*	0.1	9.5	9.6	6.8	5.9
08	6.5	4.6	5.2	7.0	1.1	1.0	-	*	3.8	4.3	3.3	2.6
09	3.9	2.4	2.6	3.6	0.6	0.5	-	*	1.5	1.8	1.4	1.0
10	2.0	1.2	1.1	1.6	0.3	0.3	-	*	0.6	0.6	0.6	0.4
11	1.2	0.6	0.4	0.7	0.2	0.2	-	*	0.2	0.2	0.2	0.2
12	0.6	0.2	0.1	0.3	0.1	0.1	-	-	*	0.1	0.1	0.1
13	0.3	0.1	0.1	0.1	*	0.1	-	-	*	*	*	*
14	0.1	*	*	*	*	*	-	-	*	*	*	*
15	*	*	*	*	*	*	-	-	-	-	*	*
16	*	*	*	*	*	*	-	-	-	-	*	*
17	*	*	-	*	-	*	-	-	-	-	*	*
18 & Above	*	*	-	*	-	*	-	-	-	*	*	*
Average	0.53	0.49	0.51	0.54	0.32	0.32	0.19	0.20	0.51	0.51	0.46	0.44
UNIFORMITY 2/												
74 & Below	-	-	-	-	-	-	-	*	-	-	-	-
75	-	*	-	-	*	*	*	*	-	-	-	*
76	*	*	*	*	*	*	-	*	*	*	*	*
77	0.3	0.3	0.1	0.1	0.1	0.1	*	0.1	0.1	0.2	0.2	0.2
78	2.0	1.8	0.9	0.5	1.4	0.9	0.1	0.8	0.8	0.9	1.7	1.8
79	9.9	9.8	5.2	2.9	9.0	6.4	1.8	2.3	10.0	13.6	9.1	9.8
80	35.4	33.1	22.7	15.3	20.9	22.7	4.1	6.8	55.4	56.1	28.5	32.2
81	36.7	38.5	38.5	35.2	34.1	39.0	29.0	21.6	31.9	26.7	38.4	37.3
82	12.9	13.9	24.1	32.8	26.3	24.9	22.1	26.2	1.5	2.2	17.6	15.2
83	2.4	2.3	7.7	12.4	6.7	5.3	6.2	17.6	0.2	0.3	4.0	3.1
84	0.3	0.3	0.6	0.9	1.2	0.6	30.2	21.3	*	*	0.5	0.3
85 & Above	*	*	*	*	0.3	0.1	6.6	3.5	-	-	0.1	*
Average	81.01	81.05	81.50	81.82	81.47	81.44	82.89	82.70	80.70	80.61	81.20	81.09
Tenderables	66.8	64.0	76.0	71.1	71.1	73.9	92.9	90.5	56.0	63.1	69.2	80.8
SAMPLES CLASSED	57,011	568,279	60,803	1,084,595	33,012	135,365	14,714	106,025	6,092	51,361	137,933	1,251,407

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on New York No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 13 2018

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	*	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	-	0.7	-	*	-	-	-	-	-	-	-	-
2.7 - 2.9	0.1	2.4	-	-	-	*	-	*	*	*	1.0	0.4
3.0 - 3.2	8.9	7.3	*	*	-	*	-	*	0.1	*	1.0	0.9
3.3 - 3.4	8.3	13.1	*	*	*	*	*	*	0.2	0.2	2.8	2.2
3.5 - 3.6	16.1	14.0	*	*	*	0.1	0.1	0.1	1.1	0.5	8.4	7.7
3.7 - 4.2	58.9	50.2	1.9	4.0	6.9	8.4	7.4	7.4	15.2	12.7	39.2	44.2
4.3 - 4.9	7.7	12.2	59.3	68.0	73.7	70.3	76.3	79.0	75.3	77.6	44.7	42.2
5.0 - 5.2	-	*	35.8	25.5	17.1	17.4	15.3	12.3	7.8	8.4	2.9	2.4
5.3 & Above	-	-	3.0	2.5	2.3	3.8	0.9	1.1	0.3	0.7	-	-
Average	3.79	3.75	4.85	4.79	4.69	4.69	4.69	4.68	4.53	4.57	4.19	4.18
Leaf												
1 - 2	7.4	8.5	7.1	6.6	1.9	2.6	4.8	3.7	2.5	4.2	43.2	35.7
3	32.9	38.8	51.7	46.0	35.4	33.1	34.6	34.6	44.1	47.0	42.6	47.6
4	34.0	34.6	34.6	38.3	49.0	48.5	44.7	44.8	41.7	40.0	11.6	13.1
5	22.0	15.5	6.3	8.5	13.1	14.8	14.4	15.5	10.5	8.2	2.5	3.3
6	3.6	2.5	0.3	0.6	0.6	0.9	1.4	1.5	1.2	0.6	0.1	0.3
7	0.1	0.1	*	*	*	*	0.1	*	*	*	-	*
8	-	*	-	*	-	-	-	*	*	*	-	-
Average	3.82	3.65	3.41	3.50	3.75	3.78	3.73	3.76	3.64	3.54	2.71	2.82
HVI Trash 1/												
00	-	-	-	-	-	-	-	-	-	-	-	-
01	0.4	1.1	0.5	0.6	0.1	0.1	0.4	0.2	0.1	0.2	8.3	6.1
02	9.3	9.8	9.8	9.3	2.8	3.1	6.8	5.6	4.0	5.9	36.1	30.6
03	17.5	18.9	25.8	22.2	13.9	12.2	16.7	16.4	18.3	20.4	27.7	29.8
04	14.1	19.3	26.5	24.8	22.8	20.6	22.3	22.5	27.2	26.7	14.7	16.6
05	13.6	15.7	18.1	19.5	23.9	22.9	21.4	21.4	21.9	21.1	7.1	8.5
06	14.4	12.9	10.3	12.0	17.5	18.7	15.3	15.8	13.7	13.1	3.6	4.6
07	12.5	9.0	5.3	6.4	10.3	11.8	9.0	9.5	7.5	6.8	1.7	2.2
08	8.5	5.9	2.4	3.0	5.1	6.0	4.6	4.9	4.1	3.3	0.7	1.0
09	5.1	3.5	0.8	1.3	2.3	2.7	2.2	2.2	1.9	1.5	0.2	0.5
10	2.4	1.9	0.3	0.5	0.9	1.1	0.9	0.9	0.9	0.6	0.1	0.2
11	1.5	1.0	0.1	0.2	0.3	0.4	0.4	0.4	0.4	0.2	*	0.1
12	0.5	0.5	*	0.1	0.1	0.1	0.1	0.1	0.1	0.1	-	*
13	0.3	0.2	*	*	*	*	0.1	0.1	*	*	-	-
14	*	0.1	*	*	*	*	*	*	*	*	-	-
15	*	*	*	*	*	*	*	*	*	*	-	-
16	-	*	-	-	*	*	*	*	*	*	-	-
17	-	*	-	-	-	*	*	*	*	*	-	-
18 & Above	-	*	-	-	-	*	*	*	*	*	-	-
Average	0.53	0.49	0.42	0.44	0.51	0.53	0.49	0.49	0.48	0.46	0.30	0.32
UNIFORMITY 2/												
74 & Below	-	*	*	*	-	-	*	*	*	*	-	-
75	*	*	*	*	-	-	*	*	*	*	-	-
76	0.1	0.2	0.1	0.1	*	*	*	*	0.2	0.1	-	-
77	0.3	0.8	0.4	0.6	*	*	0.6	0.3	1.3	0.6	*	*
78	0.6	3.2	2.8	3.3	0.1	0.1	4.1	2.0	5.8	3.5	*	0.2
79	14.6	18.1	14.3	12.7	1.4	0.7	13.4	8.9	18.9	15.2	0.5	1.4
80	60.0	48.4	42.9	30.1	11.2	6.1	33.0	29.9	32.2	33.3	9.1	6.3
81	22.6	24.6	32.2	34.2	32.5	25.1	33.7	38.5	27.0	32.3	22.5	23.8
82	1.7	4.0	6.5	14.5	38.6	41.7	12.8	17.1	12.0	12.6	42.9	48.6
83	*	0.6	0.7	3.6	13.5	23.3	2.1	3.0	2.2	2.1	23.8	18.8
84	-	*	0.1	0.6	2.4	2.8	0.2	0.3	0.3	0.2	1.1	0.8
85 & Above	0.1	*	*	0.1	0.2	0.1	*	*	*	*	0.2	0.1
Average	80.53	80.51	80.72	81.00	82.04	82.34	80.88	81.14	80.69	80.85	82.27	82.22
Tenderables	45.1	52.5	45.3	57.3	74.5	68.5	72.9	76.8	82.8	76.0	91.6	92.7
SAMPLES CLASSED	6,493	30,205	17,310	380,024	50,298	683,864	87,986	1,165,221	52,242	615,089	3068	15045

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on New York No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 13 2018

Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE										
2.4 & Below	-	*	-	-	-	-	0.1	*	-	-
2.5 - 2.6	*	*	-	*	-	-	0.7	0.1	-	-
2.7 - 2.9	0.3	0.2	-	*	-	-	1.6	0.5	-	-
3.0 - 3.2	0.3	0.3	-	*	0.1	*	3.9	1.5	-	-
3.3 - 3.4	0.7	0.7	*	0.1	0.2	*	5.0	2.4	-	*
3.5 - 3.6	2.2	1.4	0.2	0.6	0.8	0.2	7.8	4.0	*	*
3.7 - 4.2	31.3	29.6	23.8	33.3	7.7	6.3	38.0	26.7	2.8	2.6
4.3 - 4.9	58.8	61.4	73.1	64.4	68.5	63.8	39.0	52.1	91.7	90.2
5.0 - 5.2	6.0	5.8	2.9	1.7	18.9	24.8	3.6	9.7	5.1	6.8
5.3 & Above	0.5	0.6	*	0.1	3.8	4.9	0.4	3.0	0.4	0.3
Average	4.38	4.41	4.43	4.36	4.71	4.76	4.12	4.40	4.65	4.66
Leaf										
1 - 2	12.8	10.1	3.7	4.7	8.1	9.0	17.1	21.2	5.9	8.0
3	51.0	52.5	36.9	38.3	43.9	48.5	46.0	43.9	66.4	68.7
4	28.5	29.4	45.3	44.4	38.2	35.2	25.0	25.2	26.6	22.4
5	6.9	6.7	13.0	11.7	9.3	6.8	8.6	7.6	1.1	0.8
6	0.7	1.2	1.0	0.8	0.5	0.4	2.4	1.6	*	*
7	0.1	0.2	*	*	*	*	0.7	0.4	-	-
8	*	*	-	*	-	-	0.2	0.1	-	-
Average	3.32	3.37	3.71	3.66	3.50	3.41	3.35	3.24	3.23	3.16
HVI Trash 1/										
00	-	-	-	-	-	-	-	*	-	-
01	1.7	0.8	0.2	0.3	1.0	0.7	2.5	4.5	0.2	0.4
02	14.3	11.0	5.1	5.8	9.4	10.0	19.1	19.3	8.1	11.0
03	25.8	24.2	16.7	16.4	21.5	22.1	25.5	23.5	30.7	33.1
04	24.2	24.8	23.8	23.7	22.9	24.7	19.8	19.4	33.2	31.7
05	16.1	17.7	22.7	22.4	18.7	19.2	12.9	13.4	18.4	16.0
06	9.0	10.3	15.8	15.5	13.0	11.9	8.0	8.4	6.7	5.5
07	4.8	5.4	8.8	8.7	7.5	6.3	4.7	5.0	1.9	1.6
08	2.3	2.8	4.1	4.2	3.7	3.0	2.8	2.8	0.7	0.5
09	1.0	1.4	1.8	1.8	1.5	1.3	1.7	1.6	0.1	0.1
10	0.5	0.7	0.7	0.8	0.6	0.5	1.1	0.9	*	*
11	0.2	0.4	0.2	0.3	0.2	0.2	0.7	0.5	*	*
12	0.1	0.2	0.1	0.1	0.1	0.1	0.4	0.3	-	*
13	*	0.1	0.1	*	*	*	0.3	0.2	-	*
14	*	0.1	*	*	*	*	0.2	0.1	-	*
15	*	*	*	*	*	*	0.1	0.1	-	*
16	*	*	*	*	-	*	0.1	*	-	*
17	*	*	*	*	-	*	*	*	-	-
18 & Above	*	*	-	*	-	*	0.1	*	-	-
Average	0.41	0.44	0.49	0.48	0.45	0.44	0.41	0.40	0.39	0.38
UNIFORMITY 2/										
74 & Below	*	*	*	*	-	-	*	*	*	*
75	*	*	*	*	-	-	0.1	0.2	*	*
76	0.2	0.1	0.4	0.2	*	*	0.6	0.6	0.1	0.1
77	1.0	0.6	2.0	1.0	0.2	0.1	1.9	1.7	0.8	0.5
78	4.3	2.7	9.9	5.5	1.7	0.6	6.2	4.5	4.8	3.1
79	14.6	12.0	30.7	21.5	11.3	5.3	17.4	12.6	26.0	18.8
80	33.5	30.9	34.7	39.2	34.9	20.7	31.1	26.2	39.8	40.8
81	32.4	34.6	17.3	25.1	28.7	35.2	27.6	29.9	21.1	27.8
82	12.7	15.7	4.1	6.5	17.8	29.2	12.2	18.3	6.4	7.8
83	1.1	3.0	0.7	1.0	4.8	8.1	2.5	5.3	0.9	1.0
84	0.1	0.4	0.1	0.1	0.6	0.8	0.3	0.6	*	0.1
85 & Above	0.1	0.1	*	*	*	*	*	*	-	*
Average	80.81	81.02	80.15	80.50	81.12	81.60	80.67	81.00	80.43	80.65
Tenderables	84.5	82.4	83.5	80.9	65.4	46.2	72.1	66.6	91.1	80.9
SAMPLES CLASSED	32,957	183,926	29,099	255,694	42,719	721,703	472,148	4,025,529	15,156	149,839

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on New York No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 13 2018

Color Grade	Leaf	Arizona		California		New Mexico		Texas	
		Week	Season	Week	Season	Week	Season	Week	Season
01	1	1.4	4.1	15.6	21.0	-	-	-	-
	2	0.8	19.1	22.9	22.4	-	-	-	-
	3	-	2.0	0.6	0.4	-	-	-	-
	4	-	*	*	*	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		2.2	25.2	39.1	43.8	-	-	-	-
02	1	10.4	8.0	4.2	6.0	-	-	-	-
	2	20.9	19.0	40.6	38.7	-	-	-	-
	3	3.3	2.0	11.4	8.2	-	-	-	-
	4	0.1	*	0.3	0.1	-	-	-	-
	5	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		34.7	29.0	56.5	53.0	-	-	-	-
03	1	0.9	2.1	*	*	-	-	-	-
	2	19.3	24.9	1.5	1.3	-	-	-	-
	3	16.1	8.3	2.2	1.5	-	-	-	-
	4	0.3	0.3	0.5	0.2	-	-	-	-
	5	-	-	0.1	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		36.6	35.7	4.3	3.1	-	-	-	-
04	1	0.1	*	-	*	-	-	-	-
	2	13.6	4.4	*	*	-	-	-	-
	3	10.9	4.4	0.1	*	-	-	-	-
	4	0.6	0.3	*	*	-	-	-	-
	5	-	-	*	*	-	-	-	-
	6	-	*	-	*	-	-	-	-
	7	-	*	-	-	-	-	-	-
Total -----		25.2	9.1	0.1	0.1	-	-	-	-
05	1	-	-	-	-	-	-	-	-
	2	0.5	0.2	-	*	-	-	-	-
	3	0.7	0.7	-	*	-	-	-	-
	4	0.2	0.1	-	*	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		1.4	1.0	-	*	-	-	-	-
06	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	*	-	*	-	-	-	-
	4	-	-	-	*	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	*	-	*	-	-	-	-
07	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-
	4	-	-	-	*	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	-	*	-	-	-	-
STAPLE									
44 & Shorter		-	0.1	0.2	0.2	-	-	-	-
46		-	25.4	3.3	4.4	-	-	-	-
48		13.1	27.2	28.7	35.8	-	-	-	-
50		77.3	45.9	56.5	53.8	-	-	-	-
52 & Longer		9.6	1.5	11.4	5.8	-	-	-	-
Average Staple		49.93	48.47	49.51	49.21	-	-	-	-
Average Length		1.45	1.41	1.44	1.43	-	-	-	-
EXTRANEIOUS MATTER									
Bark		-	-	-	*	-	-	-	-
Grass		-	0.2	-	0.2	-	-	-	-
Spindle Twist		-	-	0.1	*	-	-	-	-
Preperation		-	*	*	*	-	-	-	-
All Other		0.1	0.1	*	*	-	-	-	-

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Dec 13 2018

Quality Designation	Arizona		California		New Mexico		Texas	
	Week	Season	Week	Season	Week	Season	Week	Season
MIKE								
2.4 & Below	-	-	-	*	-	-	-	-
2.5 - 2.6	-	-	*	*	-	-	-	-
2.7 - 2.9	-	-	0.2	0.1	-	-	-	-
3.0 - 3.2	-	0.1	1.6	0.5	-	-	-	-
3.3 - 3.4	0.1	0.3	2.3	1.0	-	-	-	-
3.5 - 3.6	2.9	1.4	4.5	3.7	-	-	-	-
3.7 - 4.2	87.0	78.7	52.8	52.1	-	-	-	-
4.3 - 4.9	10.0	19.5	38.4	42.6	-	-	-	-
5.0 - 5.2	-	-	*	*	-	-	-	-
5.3 & Above	-	-	*	*	-	-	-	-
Average	4.02	4.06	4.12	4.16	-	-	-	-
ALL RANGE MIKE								
2.4 & Below	-	-	-	*	-	-	-	-
2.5	-	-	-	*	-	-	-	-
2.6	-	-	*	*	-	-	-	-
2.7	-	-	*	*	-	-	-	-
2.8	-	-	0.1	*	-	-	-	-
2.9	-	-	0.1	0.1	-	-	-	-
3.0	-	-	0.2	0.1	-	-	-	-
3.1	-	-	0.4	0.1	-	-	-	-
3.2	-	0.1	1.0	0.2	-	-	-	-
3.3	0.1	0.1	1.0	0.4	-	-	-	-
3.4	-	0.3	1.3	0.7	-	-	-	-
3.5	0.2	0.1	2.2	1.4	-	-	-	-
3.6	2.6	1.3	2.4	2.3	-	-	-	-
3.7	8.7	3.6	3.2	3.4	-	-	-	-
3.8	12.0	9.4	5.2	5.5	-	-	-	-
3.9	19.7	17.6	7.7	7.7	-	-	-	-
4.0	4.8	19.8	11.0	10.2	-	-	-	-
4.1	15.5	15.4	13.6	11.4	-	-	-	-
4.2	26.3	13.0	12.1	13.9	-	-	-	-
4.3	6.5	11.4	12.8	15.6	-	-	-	-
4.4	1.8	4.4	12.0	13.8	-	-	-	-
4.5	1.7	2.8	7.1	8.3	-	-	-	-
4.6	-	0.7	4.3	3.6	-	-	-	-
4.7	-	0.1	1.6	1.0	-	-	-	-
4.8	-	*	0.5	0.2	-	-	-	-
4.9	-	*	0.1	*	-	-	-	-
5.0	-	-	*	*	-	-	-	-
5.1	-	-	*	*	-	-	-	-
5.2	-	-	*	*	-	-	-	-
5.3 & Above	-	-	*	*	-	-	-	-
Average	4.02	4.06	4.12	4.16	-	-	-	-
STRENGTH 1/ 36 & Below	-	0.1	0.4	0.2	-	-	-	-
37	-	0.2	1.0	0.6	-	-	-	-
38	-	1.3	2.1	2.2	-	-	-	-
39	0.1	8.2	2.7	3.9	-	-	-	-
40	0.2	11.0	2.8	3.9	-	-	-	-
41	0.7	7.2	5.0	4.2	-	-	-	-
42	8.9	10.8	9.6	9.0	-	-	-	-
43	25.4	25.4	17.0	17.1	-	-	-	-
44	35.5	23.0	23.4	24.5	-	-	-	-
45	27.1	9.8	21.9	20.6	-	-	-	-
46	0.7	2.3	9.8	9.2	-	-	-	-
47	1.4	0.5	3.0	3.2	-	-	-	-
48 & Above	-	0.2	1.3	1.4	-	-	-	-
Average	44.34	43.00	44.03	43.98	-	-	-	-
UNIFORMITY								
83 & Below	-	0.1	2.4	0.7	-	-	-	-
84	0.1	3.1	6.0	5.5	-	-	-	-
85	0.3	31.5	19.6	21.3	-	-	-	-
86	56.2	46.4	55.5	54.2	-	-	-	-
87	43.0	18.8	15.0	16.8	-	-	-	-
88 & Above	0.3	0.2	1.5	1.4	-	-	-	-
Average	86.82	86.24	86.24	86.30	-	-	-	-
Samples Classed	877	12,333	37,272	352,909	-	-	-	-