



Volume 21, No.23

State	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
AL	23	78.1	63.5	27,622	29	86.6	74.1	893,033
AR	15	78.7	62.4	38,297	28	90.4	76.3	1,347,712
AZ	12	67.9	48.1	21,714	12	81.0	60.9	199,060
CA	6	85.6	77.1	7,553	15	88.1	75.9	133,730
FL	4	83.4	60.7	7,504	4	83.3	65.5	144,694
GA	55	83.0	67.8	106,685	59	85.3	66.1	2,469,029
KS	3	63.9	40.9	15,110	3	52.7	35.4	106,224
LA	9	86.9	62.6	18,662	19	89.7	70.8	555,520
MO	14	88.4	69.4	37,836	21	89.4	74.0	751,563
MS	24	87.1	69.2	49,487	38	88.4	65.9	1,459,621
NC	22	82.7	61.4	24,885	34	83.3	58.8	999,070
NM	2	81.3	55.7	4,435	2	86.7	72.0	23,602
OK	11	65.9	47.4	33,829	12	80.4	62.9	363,290
SC	13	85.8	57.5	13,238	15	87.4	66.8	388,225
TN	15	79.3	54.5	27,336	22	89.6	71.3	913,480
TX	109	48.0	27.7	128,250	187	67.0	39.9	5,873,246
VA	2	87.6	72.8	4,533	4	85.6	58.7	199,513
United States	339	73.2	54.3	566,976	504	79.8	58.2	16,820,612
AMERICAN PIMA								
AZ	2			913	3			7,634
CA	12			26,744	17			406,679
NM*	-			-	-			-
TX*	-			-	3			13,812
United States	16			27,809	24			437,386
United States all cotton	353			594,785	519			17,257,998

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 02, 2020

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	2.1	9.0	0.7	5.0	33.1	58.0	50.1	56.2	*	3.7	1.8	9.6
	3	2.1	9.6	1.8	4.5	2.7	6.1	2.7	6.0	0.1	3.1	1.0	6.9
	4	0.1	0.8	0.1	0.2	0.1	0.3	-	0.3	*	0.2	0.1	0.3
	5	*	*	-	*	-	*	-	*	-	-	-	*
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	4.3	19.4	2.6	9.7	35.8	64.5	52.9	62.5	0.1	7.0	2.9	16.8
31	1 - 2	0.4	2.3	0.6	3.5	11.2	9.9	10.6	15.3	0.4	1.5	1.2	3.9
	3	5.4	13.2	9.1	18.5	9.5	8.1	11.3	12.8	6.8	8.9	6.6	13.0
	4	4.2	5.8	6.6	8.4	2.3	1.7	1.2	1.9	4.7	3.5	3.8	4.2
	5	0.3	0.5	0.8	0.8	0.2	0.2	0.1	0.1	0.3	0.3	0.3	0.2
	6	*	*	*	*	-	*	-	*	-	*	*	*
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	10.3	21.8	17.1	31.3	23.2	19.9	23.1	30.2	12.1	14.1	11.9	21.3
41	1 - 2	1.6	1.6	0.2	0.7	3.7	1.3	1.8	0.6	2.1	0.7	2.3	2.1
	3	23.1	15.8	12.3	12.7	10.1	2.8	11.0	2.3	24.0	16.7	22.3	17.6
	4	18.9	14.3	28.8	23.1	5.6	1.6	5.2	1.4	33.9	26.0	24.2	15.8
	5	4.5	3.3	16.2	12.4	1.6	0.5	1.2	0.2	5.3	5.2	6.6	3.2
	6	0.4	0.3	2.0	1.4	0.4	0.1	0.1	*	0.2	0.2	0.6	0.2
	7	*	*	-	*	0.1	*	*	*	-	*	*	*
	8	*	*	-	-	-	*	-	-	-	-	-	-
Total	----	48.6	35.3	59.5	50.3	21.5	6.4	19.4	4.6	65.6	48.8	56.1	38.9
51	1 - 2	0.8	0.6	*	0.1	1.0	0.3	*	*	0.4	0.4	0.7	0.9
	3	8.0	5.9	2.3	1.3	1.3	0.6	*	*	6.0	7.5	8.6	7.2
	4	10.4	5.6	9.3	3.3	1.8	0.3	*	*	5.9	11.7	8.3	5.8
	5	3.4	1.5	5.9	2.3	2.5	0.3	0.1	*	1.2	3.8	2.0	1.3
	6	0.3	0.3	0.9	0.4	3.0	0.3	*	*	0.1	0.3	0.2	0.1
	7	0.1	*	*	*	1.3	0.1	-	*	-	*	*	*
	8	0.1	*	-	*	0.2	*	-	-	-	-	-	*
Total	----	23.1	13.9	18.4	7.3	11.1	2.0	0.2	0.1	13.7	23.7	19.9	15.4
61	1 - 2	*	*	-	-	*	*	-	*	-	*	*	*
	3	0.1	0.1	-	*	*	*	-	*	-	0.1	0.1	0.1
	4	0.1	*	-	*	*	*	-	*	-	0.2	*	*
	5	*	*	-	*	-	*	-	-	-	0.1	*	*
	6	*	*	-	*	*	*	-	-	-	*	*	*
	7	*	*	-	-	*	*	-	-	-	-	-	*
	8	*	*	-	-	*	*	-	-	-	-	*	*
Total	----	0.2	0.1	-	*	0.1	*	-	*	-	0.5	0.2	0.2
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	*
	3	-	-	-	*	-	-	-	-	-	-	*	*
	4	-	*	-	-	-	-	-	-	-	-	*	*
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	*
	7	*	*	-	-	-	-	-	-	-	-	-	*
	8	*	*	-	-	-	-	-	-	-	*	-	*
Total	----	*	*	-	*	-	-	-	-	-	*	*	*
12 & 22	1 - 2	0.2	0.2	-	*	0.6	1.7	0.3	0.1	-	*	0.2	0.4
	3	0.4	0.4	-	*	0.4	1.7	0.1	0.1	-	*	0.1	0.2
	4	*	0.1	*	*	*	0.3	-	*	-	*	*	*
	5	-	*	-	-	-	*	-	*	-	-	-	-
	6	-	-	-	-	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.6	0.7	*	0.1	1.0	3.8	0.3	0.2	-	0.1	0.3	0.7
32	1 - 2	0.1	0.1	*	*	1.1	0.4	0.2	0.3	*	0.1	0.1	0.3
	3	1.3	0.9	0.1	0.2	1.9	0.9	0.5	0.6	0.5	0.3	0.5	1.0
	4	0.6	0.7	0.2	0.2	0.5	0.6	0.1	0.3	0.1	0.2	0.2	0.3
	5	*	0.1	*	*	0.1	0.2	*	0.1	-	*	*	*
	6	-	*	-	*	*	*	-	*	-	*	-	*
	7	-	*	-	-	*	*	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	2.0	1.8	0.3	0.4	3.5	2.0	0.8	1.2	0.6	0.6	0.8	1.6
42	1 - 2	0.2	0.2	*	*	0.1	*	*	*	-	0.1	0.2	0.2
	3	3.0	1.6	0.2	0.2	0.8	0.3	1.3	0.3	1.6	0.7	1.8	1.4
	4	2.6	1.7	0.5	0.3	0.9	0.3	1.6	0.6	4.1	1.3	1.4	1.1
	5	0.5	0.6	0.4	0.1	0.2	0.2	0.2	0.1	0.7	0.4	0.3	0.2
	6	0.1	0.1	0.1	*	0.1	0.1	*	*	-	*	*	*
	7	*	*	-	-	*	*	-	-	-	-	*	*
	8	-	*	-	-	*	*	-	-	-	-	-	-
Total	----	6.4	4.2	1.2	0.6	2.1	0.9	3.1	1.0	6.4	2.5	3.7	2.9

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 02, 2020

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	0.1	0.1	*	*	-	-	-	-	*	0.1	0.2	0.1
	3	1.1	0.9	*	*	0.2	0.1	-	*	0.1	0.8	1.5	0.9
	4	1.1	0.9	0.1	*	0.1	*	-	0.1	0.5	1.2	1.1	0.7
	5	0.2	0.2	*	*	-	*	*	0.1	0.1	0.5	0.2	0.2
	6	*	*	*	*	*	*	-	*	*	0.1	0.1	*
	7	0.1	*	-	-	0.1	*	-	*	-	*	*	*
	8	0.1	*	-	-	*	*	-	-	-	*	-	*
Total	----	2.7	2.2	0.1	*	0.5	0.1	*	0.2	0.7	2.6	3.0	2.0
62	1 - 2	*	*	-	*	-	-	-	-	-	*	*	*
	3	*	*	-	*	-	-	-	*	*	*	*	*
	4	*	*	-	*	-	-	-	-	*	0.1	*	*
	5	*	*	-	*	-	-	-	-	-	*	*	*
	6	*	*	-	*	-	-	-	-	-	*	-	*
	7	-	*	-	-	-	-	-	-	-	*	*	*
	8	*	*	-	-	*	*	-	-	-	*	*	*
Total	----	0.1	0.1	-	*	*	*	-	*	*	0.1	0.1	0.1
13 & 23	1 - 2	*	*	-	*	0.1	0.1	*	*	-	-	-	*
	3	*	*	-	*	0.1	*	-	*	-	-	*	*
	4	-	*	-	*	-	*	-	-	-	*	*	*
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	-	*	0.2	0.1	*	*	-	*	*	*
33	1 - 2	-	*	-	*	0.1	*	*	*	-	-	*	*
	3	0.1	*	0.1	*	0.5	0.1	0.1	*	*	*	*	*
	4	0.1	*	*	*	0.1	*	*	*	*	*	*	*
	5	*	*	*	*	*	*	-	-	-	-	*	*
	6	-	*	-	-	-	-	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.2	0.1	0.1	*	0.7	0.2	0.1	*	*	*	0.1	*
43	1 - 2	*	*	-	*	-	*	-	*	-	-	*	*
	3	0.3	0.1	0.1	*	0.1	*	*	*	0.1	*	0.3	0.1
	4	0.4	0.1	0.1	0.1	0.1	*	-	*	0.3	*	0.2	0.1
	5	0.3	0.1	0.1	*	-	*	-	*	0.1	*	0.1	*
	6	*	*	0.1	*	-	*	-	-	-	*	*	*
	7	*	*	-	*	*	*	-	-	-	-	-	*
	8	-	*	-	-	-	*	-	-	-	-	-	-
Total	----	1.1	0.3	0.5	0.1	0.2	0.1	*	*	0.4	0.1	0.5	0.1
53	1 - 2	*	*	-	-	-	-	-	-	-	-	*	*
	3	0.1	*	*	*	*	*	-	-	*	*	0.1	*
	4	0.1	*	*	*	*	*	-	*	0.1	*	0.2	0.1
	5	0.1	*	*	*	-	*	-	-	0.1	*	0.1	*
	6	*	*	*	*	-	*	-	-	-	*	*	*
	7	*	*	-	*	-	*	-	-	-	-	*	*
	8	*	*	-	-	-	*	-	-	-	-	-	-
Total	----	0.3	0.1	*	*	*	*	-	*	0.2	0.1	0.4	0.1
63	1 - 2	-	*	-	-	-	-	-	-	-	-	-	*
	3	*	*	-	*	-	-	-	-	-	-	-	*
	4	*	*	-	*	*	*	-	-	-	-	*	*
	5	*	*	-	-	-	-	-	-	-	-	-	*
	6	-	*	-	-	-	-	-	-	-	*	-	*
	7	-	*	-	*	-	-	-	-	-	*	*	*
	8	*	*	-	-	-	-	-	-	-	*	*	*
Total	----	0.1	*	-	*	*	*	-	-	-	*	*	*
24 - 54	1 - 8	0.1	*	0.1	*	0.1	*	*	*	-	*	0.1	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	*	*	-	-	-	-	-	-	-	-	*	*
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	-	-	-	-	-	-	-	-	-	-	*
31		*	*	-	*	-	-	-	-	-	*	*	*
32		0.4	0.5	-	*	0.1	*	-	-	*	*	0.4	0.4
33		2.2	2.1	-	*	1.0	0.5	-	0.1	0.3	0.7	2.3	2.3
34		9.8	6.8	*	0.1	2.9	2.4	0.8	1.2	2.7	2.7	6.8	7.3
35		12.9	13.1	0.9	1.8	6.5	8.3	5.6	3.4	6.6	5.1	14.9	15.2
36		23.3	22.9	11.3	11.2	17.5	19.2	8.1	11.8	14.6	12.0	22.4	21.0
37		32.4	32.5	42.5	40.1	26.7	30.9	16.8	32.8	25.0	32.3	26.9	29.3
38		13.7	14.8	25.6	25.8	22.2	21.5	30.4	28.5	36.2	34.6	16.1	17.0
39		4.4	6.2	14.5	16.5	16.6	13.1	27.8	18.2	14.3	11.5	8.5	6.5
40 & Longer		0.9	1.1	5.1	4.4	6.5	3.9	10.4	4.0	0.3	1.2	1.6	0.9
Average Staple		36.36	36.50	37.57	37.57	37.33	37.15	37.96	37.55	37.29	37.28	36.54	36.47
Average Length		1.13	1.14	1.17	1.17	1.17	1.16	1.19	1.17	1.16	1.16	1.14	1.14

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 02, 2020

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	22.0	19.8	3.8	15.8	0.7	2.9	11.4	13.4	1.1	4.7	22.5	46.9
	3	6.9	7.1	1.6	14.0	0.2	1.4	9.8	11.7	1.9	5.0	4.1	4.6
	4	0.4	0.3	*	0.8	-	*	1.7	1.3	0.1	0.3	*	*
	5	-	*	-	*	-	*	*	*	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	*	-	-	-	-
Total	----	29.3	27.2	5.4	30.6	0.9	4.3	22.9	26.4	3.2	10.1	26.7	51.6
31	1 - 2	3.6	3.8	1.4	2.4	3.5	5.5	2.7	2.6	2.4	3.7	14.3	14.0
	3	16.0	13.4	12.4	14.5	11.2	19.5	6.6	13.8	15.3	19.6	24.5	15.9
	4	10.3	8.7	3.5	6.7	3.0	7.3	3.7	7.5	4.4	8.7	3.5	2.0
	5	1.1	1.4	0.1	0.5	0.3	0.8	0.4	0.8	0.3	0.8	0.1	0.1
	6	0.1	0.1	-	*	*	*	*	*	*	*	-	-
	7	-	*	-	*	-	-	-	*	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-	-	-
Total	----	31.1	27.4	17.4	24.1	18.0	33.0	13.3	24.7	22.4	32.8	42.4	31.9
41	1 - 2	*	*	0.9	0.5	2.6	1.6	1.1	0.9	7.3	2.7	0.4	0.3
	3	0.1	0.1	17.4	9.0	26.2	17.5	12.6	11.0	39.2	24.9	1.7	2.3
	4	0.7	1.0	26.4	14.1	29.5	25.0	17.5	16.0	17.9	19.7	1.6	2.1
	5	0.8	1.4	7.9	4.6	11.2	11.4	5.3	5.6	2.2	3.2	0.2	0.6
	6	0.1	0.6	0.2	0.5	1.4	1.2	0.7	0.6	0.1	0.2	-	0.1
	7	0.1	0.2	-	*	-	*	*	*	-	*	-	-
	8	*	0.1	-	-	-	-	-	*	-	-	-	-
Total	----	1.9	3.5	52.8	28.7	70.9	56.6	37.3	34.2	66.7	50.7	4.0	5.6
51	1 - 2	-	-	0.2	*	0.1	0.1	0.2	0.2	0.2	0.1	-	-
	3	-	-	3.9	2.3	1.8	0.7	5.8	2.7	1.3	1.1	*	*
	4	-	*	9.6	5.6	5.1	2.4	10.2	5.6	1.4	1.8	-	*
	5	-	0.1	2.9	2.6	2.3	1.8	2.8	2.7	0.3	0.6	-	*
	6	-	*	0.1	0.4	0.2	0.3	0.3	0.5	0.1	0.1	-	*
	7	-	0.1	-	*	-	*	-	*	*	*	-	-
	8	-	0.1	-	*	-	-	-	*	-	*	-	-
Total	----	-	0.4	16.8	11.0	9.3	5.3	19.3	11.7	3.3	3.6	*	*
61	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	*	*	-	*	*	*	-	-	-	-
	4	-	-	0.1	0.1	-	*	*	*	-	*	-	-
	5	-	-	*	0.1	-	*	*	*	-	-	-	-
	6	-	-	-	*	-	*	-	*	-	-	-	-
	7	-	-	-	*	-	-	-	*	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	*	-	-
Total	----	-	-	0.1	0.2	-	*	*	*	-	*	-	-
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	*	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	*	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	*	-	-	-	-
12 & 22	1 - 2	18.8	9.4	*	0.4	-	*	0.1	0.1	*	*	5.1	2.9
	3	5.2	2.8	*	0.5	-	*	0.1	0.2	*	0.1	4.1	1.4
	4	0.2	0.1	-	0.1	-	-	*	0.1	*	*	0.2	0.1
	5	-	*	-	*	-	-	-	*	-	*	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	24.3	12.4	*	1.0	-	*	0.2	0.4	*	0.1	9.3	4.4
32	1 - 2	0.2	0.3	*	0.2	*	*	0.1	0.1	*	0.1	2.1	0.7
	3	2.1	1.8	0.4	0.6	0.1	0.1	0.6	0.3	0.8	0.5	6.2	2.0
	4	2.3	2.7	0.1	0.3	*	0.1	0.6	0.3	0.4	0.3	2.2	0.9
	5	1.3	1.4	*	*	*	*	0.1	0.1	0.1	*	0.4	0.1
	6	0.2	0.2	-	*	-	*	*	*	*	*	-	-
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	6.1	6.5	0.5	1.0	0.1	0.2	1.4	0.7	1.3	0.9	10.9	3.7
42	1 - 2	-	*	0.3	0.1	*	*	0.1	*	0.1	*	*	*
	3	*	*	1.7	0.8	0.1	0.1	1.1	0.2	0.9	0.5	0.2	0.2
	4	0.1	0.4	1.8	1.0	0.2	0.1	1.8	0.6	1.0	0.7	0.2	0.2
	5	0.5	1.4	0.7	0.4	0.1	*	0.8	0.4	0.2	0.2	0.2	0.2
	6	0.6	1.1	*	0.1	*	*	0.1	*	*	*	0.1	*
	7	0.3	0.4	-	*	-	-	-	*	-	*	0.1	*
	8	0.1	0.1	-	-	-	-	-	*	-	-	-	*
Total	----	1.5	3.4	4.5	2.2	0.4	0.3	3.9	1.3	2.3	1.5	0.8	0.7

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 02, 2020

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	0.1	*	-	*	*	*	-	*	-	-
	3	-	-	0.9	0.2	*	*	0.2	*	*	*	-	*
	4	-	*	0.6	0.3	*	*	0.3	0.2	*	*	0.1	*
	5	-	0.1	0.1	0.1	-	*	0.2	0.1	*	*	0.2	0.1
	6	-	0.1	*	*	*	*	*	*	*	*	-	*
	7	-	0.1	-	*	-	-	-	*	-	*	-	-
	8	-	0.1	-	*	-	-	-	*	-	*	-	-
Total		----	- 0.5	1.7 0.7		* *		0.8 0.3		0.1 0.1		0.3 0.1	
62	1 - 2	-	-	-	-	-	-	-	*	-	-	-	-
	3	-	-	-	*	-	*	-	*	-	-	-	-
	4	-	*	-	*	-	*	*	*	-	*	-	-
	5	-	*	-	*	-	*	-	*	-	-	-	-
	6	-	-	-	*	-	*	-	*	-	*	-	-
	7	-	*	-	*	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total		----	- *	- *		- *		* *		- *		- -	
13 & 23	1 - 2	2.8	3.4	-	*	-	-	-	*	-	-	0.6	0.4
	3	1.5	1.7	-	*	-	-	-	*	-	*	0.4	0.2
	4	0.1	0.1	-	*	-	-	-	*	-	-	*	*
	5	*	*	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	*	-	-	-	-
Total		----	4.5 5.2	- *		- -		- *		- *		1.0 0.6	
33	1 - 2	0.1	0.2	-	*	*	*	-	*	*	*	1.5	0.4
	3	0.4	0.6	*	*	0.1	*	0.2	*	0.2	*	1.8	0.6
	4	0.1	0.7	*	*	*	*	0.1	*	*	*	0.4	0.2
	5	0.1	0.7	-	*	*	*	*	*	*	*	*	*
	6	-	0.3	-	*	-	-	-	*	-	*	-	-
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total		----	0.7 2.4	* 0.1		0.1 *		0.3 *		0.2 0.1		3.7 1.2	
43	1 - 2	-	*	*	*	*	*	*	*	*	*	-	-
	3	-	0.1	0.2	0.1	0.1	*	0.2	*	0.3	*	*	*
	4	*	0.5	0.3	0.1	0.1	0.1	0.2	*	0.2	0.1	*	*
	5	*	1.1	0.1	*	*	*	*	*	0.1	*	*	*
	6	*	1.0	-	*	-	*	*	*	*	*	-	-
	7	-	0.5	-	-	-	-	-	*	-	-	-	-
	8	-	0.4	-	-	-	-	-	*	-	-	-	-
Total		----	0.1 3.6	0.5 0.3		0.2 0.1		0.4 0.1		0.5 0.1		0.1 *	
53	1 - 2	-	-	-	-	-	-	*	*	*	*	-	-
	3	-	-	0.1	*	*	*	*	*	*	*	-	-
	4	-	0.1	0.1	*	*	*	*	*	-	*	-	-
	5	-	0.2	0.1	*	*	*	*	*	*	*	-	-
	6	-	0.5	*	*	-	*	*	*	*	*	-	-
	7	-	0.7	-	-	-	-	-	*	*	*	-	-
	8	-	0.5	-	-	-	-	-	*	*	*	-	-
Total		----	- 2.0	0.2 *		* *		0.1 *		0.1 *		- -	
63	1 - 2	-	-	-	-	-	*	-	*	-	-	-	-
	3	-	-	-	-	-	*	-	*	-	-	-	-
	4	-	*	-	-	-	*	-	*	-	-	-	-
	5	-	*	-	-	-	*	-	*	-	*	-	-
	6	-	*	-	-	-	*	-	*	-	-	-	-
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total		----	- *	- -		- *		- *		- *		- -	
24 - 54 25 - 35 81 - 85	1 - 8	0.5	3.7	*	*	*	*	0.1	*	*	*	0.6	0.2
	1 - 8	-	*	-	-	-	-	-	-	-	-	-	-
	1 - 8	*	1.9	-	*	-	-	*	*	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	*	-	-	-	-	-	-	-	-	-	-
30		*	*	-	-	-	-	-	-	-	-	-	-
31		*	*	-	-	-	*	-	-	-	*	-	-
32		0.2	0.1	*	*	-	*	*	*	*	0.1	-	-
33		1.5	0.8	*	*	-	*	*	*	0.3	0.4	*	*
34		3.0	6.1	1.4	0.2	*	0.3	0.8	0.6	3.3	2.5	*	0.4
35		15.6	22.3	2.5	1.6	0.7	3.3	3.9	3.5	10.2	10.8	4.3	3.7
36		32.1	38.6	4.1	8.3	13.9	15.7	12.1	11.5	22.2	27.3	14.2	13.3
37		37.2	28.7	17.0	22.5	41.2	43.5	30.8	27.5	35.0	33.8	46.5	32.6
38		9.6	3.0	34.9	31.3	22.9	21.4	34.5	34.4	22.5	16.8	23.5	26.1
39		0.9	0.4	24.0	26.3	14.7	11.4	14.7	19.9	5.9	7.3	8.2	18.9
40 & Longer		*	0.1	16.0	9.9	6.7	4.4	3.2	2.6	0.6	1.1	3.3	5.0
Average Staple		36.32	35.99	38.19	38.03	37.59	37.35	37.51	37.62	36.82	36.76	37.27	37.58
Average Length		1.13	1.12	1.19	1.19	1.17	1.17	1.17	1.18	1.15	1.15	1.16	1.17

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 02, 2020

Quality Designation	Leaf	OKLAHOMA <i>Week Season</i>		SOUTH CAROLINA <i>Week Season</i>		TENNESSEE <i>Week Season</i>		TEXAS <i>Week Season</i>		VIRGINIA <i>Week Season</i>	
Color 11 & 21	1 - 2	Pct. 24.7	Pct. 46.9	Pct. 2.6	Pct. 6.5	Pct. 0.5	Pct. 4.2	Pct. 10.0	Pct. 27.4	Pct. 1.2	Pct. 12.5
	3	7.1	9.3	0.6	8.6	0.8	2.2	6.0	9.8	1.7	13.7
	4	0.1	0.2	-	0.5	0.4	0.2	0.5	0.6	-	0.7
	5	-	*	-	*	*	*	*	*	-	*
	6	-	-	-	*	-	-	-	*	-	*
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
	<i>Total</i>	<i>-----</i>	<i>31.9 56.5</i>	<i>3.3 15.6</i>		<i>1.8 6.6</i>		<i>16.5 37.9</i>		<i>2.9 26.9</i>	
31	1 - 2	9.3	7.3	3.1	5.2	0.5	5.8	7.0	4.3	1.7	5.3
	3	24.5	16.0	11.7	25.7	5.2	16.7	13.4	9.8	7.0	21.4
	4	6.6	5.3	2.2	9.4	2.4	5.7	3.9	3.5	4.9	6.5
	5	0.6	0.8	*	0.5	0.2	0.5	0.4	0.4	0.1	0.4
	6	*	*	-	*	*	*	*	*	-	*
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
	<i>Total</i>	<i>-----</i>	<i>41.0 29.5</i>	<i>17.1 40.9</i>		<i>8.3 28.7</i>		<i>24.8 18.0</i>		<i>13.7 33.6</i>	
41	1 - 2	0.1	*	5.6	1.9	4.1	3.8	0.7	0.5	5.4	5.1
	3	2.1	0.3	40.1	18.2	32.9	21.8	3.6	2.3	40.9	23.7
	4	4.5	1.1	20.5	12.6	21.3	21.2	3.5	1.7	18.4	6.5
	5	2.3	1.0	1.6	1.5	6.3	7.4	1.2	0.5	2.4	0.5
	6	0.7	0.5	*	0.1	0.5	0.9	0.4	0.1	0.2	*
	7	0.1	0.2	-	*	-	*	0.1	*	-	-
	8	*	*	-	-	-	*	*	*	-	-
	<i>Total</i>	<i>-----</i>	<i>9.9 3.2</i>	<i>67.8 34.3</i>		<i>65.1 55.1</i>		<i>9.5 5.2</i>		<i>67.3 35.8</i>	
51	1 - 2	-	*	0.3	0.1	0.4	0.2	*	0.1	1.3	0.1
	3	-	-	3.3	1.6	7.7	1.7	*	0.3	7.1	1.0
	4	*	*	2.0	1.4	8.3	2.4	0.1	0.2	5.3	0.5
	5	*	*	0.2	0.3	3.1	1.2	*	0.1	0.4	*
	6	0.1	*	-	*	0.4	0.3	*	*	*	*
	7	0.1	*	-	*	-	*	0.1	*	-	-
	8	0.1	*	-	*	-	*	0.1	*	-	-
	<i>Total</i>	<i>-----</i>	<i>0.3 0.1</i>	<i>5.8 3.5</i>		<i>20.0 5.9</i>		<i>0.3 0.7</i>		<i>14.2 1.7</i>	
61	1 - 2	-	-	-	*	-	*	-	*	-	-
	3	-	-	-	*	-	-	-	*	-	-
	4	-	-	-	*	*	*	-	*	-	-
	5	-	-	-	*	-	*	*	*	-	-
	6	-	-	-	*	-	-	*	*	-	-
	7	-	-	*	*	-	-	*	*	-	-
	8	-	*	*	*	-	-	-	*	-	-
	<i>Total</i>	<i>-----</i>	<i>- *</i>	<i>0.1 *</i>		<i>* *</i>		<i>* 0.1</i>		<i>- -</i>	
71	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	-	-	-	-	*	-	-
	5	-	-	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	*	*	-	-	-	*	-	-
	<i>Total</i>	<i>-----</i>	<i>- -</i>	<i>* *</i>		<i>- -</i>		<i>* *</i>		<i>- -</i>	
12 & 22	1 - 2	1.3	1.7	0.1	0.1	*	0.1	2.4	8.8	-	0.1
	3	0.8	1.6	0.2	0.2	*	0.1	2.6	5.3	-	0.1
	4	*	0.1	*	*	*	*	0.6	0.6	-	*
	5	-	*	-	-	-	*	0.1	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	<i>Total</i>	<i>-----</i>	<i>2.1 3.4</i>	<i>0.3 0.4</i>		<i>0.1 0.2</i>		<i>5.6 14.8</i>		<i>- 0.2</i>	
32	1 - 2	0.7	0.4	0.1	0.3	0.1	0.3	4.1	2.5	-	0.1
	3	3.7	2.3	1.0	1.5	0.5	0.8	10.1	6.4	*	0.3
	4	2.2	1.5	0.2	0.7	0.2	0.3	4.6	2.9	-	0.1
	5	0.4	0.3	-	0.1	*	*	0.8	0.5	-	*
	6	*	*	-	*	-	*	0.1	0.1	-	*
	7	-	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
	<i>Total</i>	<i>-----</i>	<i>7.0 4.6</i>	<i>1.3 2.6</i>		<i>0.8 1.3</i>		<i>19.6 12.4</i>		<i>* 0.6</i>	
42	1 - 2	*	*	0.2	0.1	0.1	0.1	0.3	0.2	0.2	0.1
	3	0.5	0.1	2.1	1.0	0.9	0.8	2.2	0.9	0.8	0.6
	4	1.5	0.3	1.1	0.9	1.0	0.7	2.7	1.0	0.2	0.3
	5	1.5	0.4	0.2	0.2	0.7	0.1	1.6	0.5	*	*
	6	0.7	0.2	0.1	*	0.1	*	0.6	0.2	-	*
	7	0.2	0.1	-	-	-	*	0.2	0.1	-	-
	8	*	*	-	-	-	-	0.1	*	-	-
	<i>Total</i>	<i>-----</i>	<i>4.3 1.2</i>	<i>3.6 2.2</i>		<i>2.8 1.7</i>		<i>7.8 2.9</i>		<i>1.2 1.1</i>	

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 02, 2020

Quality Designation	Leaf	OKLAHOMA <i>Week Season</i>		SOUTH CAROLINA <i>Week Season</i>		TENNESSEE <i>Week Season</i>		TEXAS <i>Week Season</i>		VIRGINIA <i>Week Season</i>	
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	*	*	*	*	*	*	*	*
	3	*	*	0.1	0.1	0.1	0.1	0.1	0.1	0.4	*
	4	*	*	*	0.1	*	*	0.1	0.1	0.1	*
	5	*	*	*	*	*	*	*	*	-	*
	6	*	*	-	*	*	*	*	*	-	*
	7	0.1	*	-	*	-	*	0.1	*	-	-
	8	0.1	*	-	-	-	-	0.2	*	-	*
<i>Total</i>	----	<i>0.2</i>	<i>0.1</i>	<i>0.1</i>	<i>0.2</i>	<i>0.2</i>	<i>0.1</i>	<i>0.4</i>	<i>0.3</i>	<i>0.5</i>	<i>0.1</i>
62	1 - 2	-	*	-	-	-	-	-	*	-	*
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	*	-	-	*	*	-	-
	5	-	-	-	*	-	-	*	*	-	-
	6	-	-	-	*	-	-	*	*	-	-
	7	-	-	*	*	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
<i>Total</i>	----	-	*	*	*	-	-	*	*	-	*
13 & 23	1 - 2	0.3	0.1	-	*	-	-	1.1	1.3	-	-
	3	0.1	0.1	-	*	-	*	1.4	1.1	-	*
	4	-	*	-	*	-	-	0.3	0.1	-	-
	5	-	*	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
<i>Total</i>	----	<i>0.4</i>	<i>0.2</i>	-	*	-	*	<i>2.8</i>	<i>2.5</i>	-	*
33	1 - 2	0.1	0.1	-	*	*	*	1.3	0.7	-	*
	3	0.9	0.4	0.1	0.1	0.1	0.1	3.5	1.9	-	*
	4	0.7	0.3	*	*	0.1	*	1.9	0.9	-	*
	5	0.2	0.1	-	*	*	*	0.3	0.2	-	*
	6	*	*	-	-	-	-	*	*	-	-
	7	-	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
<i>Total</i>	----	<i>1.9</i>	<i>0.9</i>	<i>0.1</i>	<i>0.2</i>	<i>0.2</i>	<i>0.1</i>	<i>7.0</i>	<i>3.8</i>	-	<i>0.1</i>
43	1 - 2	*	*	*	*	*	*	0.2	*	-	*
	3	0.1	*	0.2	0.1	0.3	0.1	1.4	0.2	0.1	*
	4	0.3	0.1	0.1	0.1	0.3	0.1	1.2	0.3	*	*
	5	0.4	0.1	*	*	0.1	*	0.8	0.2	-	*
	6	0.1	0.1	-	*	*	*	0.3	0.1	-	-
	7	*	*	-	-	-	-	0.1	*	-	-
	8	-	*	-	-	-	-	*	*	-	-
<i>Total</i>	----	<i>1.0</i>	<i>0.3</i>	<i>0.3</i>	<i>0.2</i>	<i>0.8</i>	<i>0.3</i>	<i>3.9</i>	<i>0.8</i>	<i>0.1</i>	<i>0.1</i>
53	1 - 2	-	-	-	*	*	*	-	*	-	*
	3	-	*	*	*	*	*	*	*	-	*
	4	-	*	*	*	-	*	*	*	-	*
	5	-	*	*	*	-	*	*	*	-	-
	6	-	*	-	*	-	*	0.1	*	-	-
	7	*	*	-	-	-	-	*	*	-	-
	8	*	*	-	-	-	-	*	*	-	-
<i>Total</i>	----	<i>*</i>	<i>*</i>	<i>*</i>	<i>*</i>	<i>*</i>	<i>*</i>	<i>0.2</i>	<i>*</i>	-	<i>*</i>
63	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	*	-	-	-	*	-	-
	5	-	-	-	*	-	-	*	*	-	-
	6	-	-	-	*	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
<i>Total</i>	----	-	-	-	*	-	-	<i>*</i>	<i>*</i>	-	-
24 - 54	1 - 8	*	0.1	0.1	*	*	*	1.5	0.6	-	*
25 - 35	1 - 8	-	*	-	-	-	-	-	*	-	-
81 - 85	1 - 8	*	*	-	*	-	*	*	*	-	-
STAPLE											
28 & Shorter		-	*	-	-	-	-	*	*	-	-
29		*	*	-	-	-	-	*	*	-	-
30		*	*	-	-	-	-	0.1	0.2	-	-
31		0.1	0.2	-	*	-	-	1.1	1.2	-	-
32		1.8	1.2	0.2	0.3	-	*	4.9	3.8	-	*
33		5.7	4.5	2.6	1.7	*	*	11.3	8.5	*	0.1
34		9.1	8.9	12.4	5.9	0.7	1.0	16.7	14.8	0.1	0.7
35		15.0	13.0	14.5	13.1	12.1	11.9	19.6	20.2	7.6	4.8
36		17.0	16.5	14.1	20.0	35.0	36.6	18.5	19.7	19.9	16.6
37		20.8	24.8	33.3	37.4	34.5	37.6	15.3	19.2	38.3	39.1
38		13.8	16.6	16.3	17.1	13.9	10.3	6.4	8.3	25.0	23.4
39		10.1	10.0	5.8	4.1	3.3	2.3	4.7	3.2	8.8	12.6
40 & Longer		6.6	4.3	0.8	0.4	0.5	0.2	1.5	0.9	0.3	2.8
<i>Average Staple</i>		<i>36.48</i>	<i>36.56</i>	<i>36.39</i>	<i>36.54</i>	<i>36.61</i>	<i>36.52</i>	<i>35.36</i>	<i>35.51</i>	<i>37.08</i>	<i>37.29</i>
<i>Average Length</i>		<i>1.14</i>	<i>1.14</i>	<i>1.14</i>	<i>1.14</i>	<i>1.14</i>	<i>1.14</i>	<i>1.10</i>	<i>1.11</i>	<i>1.16</i>	<i>1.16</i>

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 02, 2020

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	6.8	2.1	1.7	0.7	1.9	0.6	3.6	1.0	6.9	6.4	4.6	3.0
Bark - Level 2	0.1	*	-	*	-	-	-	-	-	-	-	*
Grass - Level 1	0.1	0.1	0.2	0.1	*	*	-	0.1	*	0.1	0.1	0.1
Grass - Level 2	-	*	-	-	-	-	-	-	-	-	-	*
Prep - Level 1	0.1	*	*	*	-	*	-	*	*	*	0.1	*
Prep - Level 2	-	*	-	-	-	-	-	-	-	-	-	*
Seed Coat - Level 1	*	*	-	*	2.1	1.3	-	*	-	*	*	*
Seed Coat - Level 2	-	*	-	-	-	-	-	-	-	-	-	*
Oil - Level 1	-	*	-	*	-	-	-	-	-	-	*	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	*
Spindle Twist - Level 1	-	-	-	-	-	*	-	*	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	0.2	0.1	*	*	-	*	*	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	*	-	*	*	*	*	*
Plastic - Level 2	-	-	-	*	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	*	-	*	-	-	-	-	-	-	-	*
23	-	*	-	*	*	*	-	-	-	*	*	*
24	*	*	*	*	0.2	*	-	-	-	*	0.2	0.2
25	0.2	0.4	*	*	0.6	0.1	-	*	0.1	0.1	1.0	0.8
26	1.0	1.8	0.3	0.2	1.0	0.4	-	*	0.2	0.8	3.7	3.2
27	7.2	7.3	1.4	1.1	2.1	1.7	*	0.4	1.7	3.5	8.3	8.4
28	18.2	20.5	6.5	5.8	3.7	5.7	0.6	0.7	7.7	11.8	13.3	15.3
29	22.0	29.8	18.3	18.9	6.9	13.7	3.8	3.2	23.5	24.6	18.3	21.7
30	23.7	21.8	29.7	30.3	18.3	24.0	10.0	10.8	35.0	29.9	20.9	22.4
31	15.7	11.0	21.7	24.7	15.4	21.6	25.9	15.3	18.9	17.0	16.8	14.8
32	8.1	4.7	12.8	12.5	13.9	14.7	11.3	16.4	5.2	7.4	10.0	7.7
33	2.8	1.7	6.4	4.5	17.0	9.3	9.7	10.8	6.7	3.5	4.7	3.5
34	0.7	0.6	2.5	1.5	12.9	4.9	4.0	6.2	0.9	1.0	1.9	1.3
35	0.1	0.2	0.4	0.4	5.2	2.3	8.5	10.0	0.1	0.3	0.7	0.4
36	0.1	0.1	0.1	0.1	2.4	1.0	11.1	13.0	-	0.1	0.2	0.1
37	*	*	*	*	0.3	0.3	12.0	9.8	-	*	*	*
38	-	*	-	*	0.1	0.1	2.5	2.7	-	-	*	*
39	-	*	-	*	*	*	0.4	0.4	-	-	-	-
40 & Above	-	-	-	-	*	*	0.3	0.3	-	-	-	-
Average	30.04	29.72	30.88	30.82	32.07	31.32	33.51	33.68	30.53	30.31	30.17	29.98
Mike												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	-
2.5	-	*	-	-	-	*	-	*	-	*	-	*
2.6	-	*	-	-	-	*	-	-	-	*	-	*
2.7	-	*	-	-	-	*	-	*	-	-	*	*
2.8	-	*	-	*	-	*	-	*	-	*	*	*
2.9	-	*	-	*	*	*	0.3	0.1	-	*	*	*
3.0	*	*	-	*	0.2	*	*	0.2	-	*	*	*
3.1	*	*	-	*	0.2	0.1	0.2	0.4	-	-	*	*
3.2	0.1	*	-	*	0.5	0.1	0.5	0.4	-	-	*	*
3.3	0.1	0.1	0.4	*	0.4	0.2	0.1	0.4	-	*	*	*
3.4	0.2	0.2	0.1	0.1	0.4	0.2	0.2	0.5	-	*	*	0.1
3.5	0.4	0.4	0.2	0.1	0.5	0.4	0.7	0.9	-	*	0.1	0.1
3.6	0.9	0.9	0.5	0.3	0.6	0.6	3.4	1.6	-	*	0.2	0.2
3.7	1.3	1.8	1.3	0.6	1.8	1.1	1.8	1.6	-	*	0.3	0.3
3.8	2.4	2.8	1.7	1.2	2.0	1.8	2.0	2.1	*	0.1	0.7	0.6
3.9	3.9	4.3	2.3	2.0	1.6	2.0	3.1	3.1	0.2	0.4	1.3	1.0
4.0	4.8	6.0	2.8	3.3	2.7	2.7	4.1	5.2	0.2	0.7	2.4	1.7
4.1	5.6	7.6	5.0	5.1	3.7	3.6	5.7	7.6	0.3	1.5	4.0	3.1
4.2	6.3	9.3	6.6	7.8	5.8	4.8	5.9	8.8	1.8	3.1	6.9	5.4
4.3	7.9	10.4	8.4	10.3	6.4	6.4	7.4	9.4	4.4	6.3	10.7	8.7
4.4	11.1	11.7	9.7	11.9	6.8	9.1	18.4	10.8	8.3	13.1	13.9	12.3
4.5	14.6	12.2	12.1	13.7	9.8	11.4	17.3	10.9	9.9	18.4	15.3	14.9
4.6	13.8	11.0	12.1	13.5	9.0	12.8	14.3	11.0	19.4	18.7	14.2	15.4
4.7	10.4	9.0	8.9	10.8	10.5	11.7	4.2	8.8	28.9	15.8	12.3	13.2
4.8	7.7	5.7	6.9	7.9	9.8	9.6	2.3	5.5	16.4	10.6	8.2	9.9
4.9	4.3	3.4	5.3	5.0	7.1	6.8	1.3	3.4	7.8	6.0	4.9	6.4
5.0	2.9	1.8	6.3	2.9	4.2	5.3	0.4	1.9	2.0	3.0	2.8	3.6
5.1	1.0	0.8	4.1	1.6	5.1	3.9	1.2	1.4	0.2	1.7	1.2	1.8
5.2	0.2	0.3	2.4	1.0	4.6	2.4	0.9	1.5	*	0.5	0.4	0.6
5.3	*	0.1	1.9	0.5	3.9	1.7	1.0	0.9	-	0.1	0.2	0.3
5.4	-	*	0.8	0.2	1.5	1.0	2.0	0.7	-	*	0.1	0.1
5.5 & Above	-	*	0.1	0.1	0.8	0.5	1.2	0.9	-	*	*	*
Average	4.44	4.38	4.54	4.49	4.59	4.57	4.39	4.40	4.64	4.59	4.51	4.55

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 02, 2020

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	11.4	23.1	2.2	1.2	0.4	0.3	1.4	1.1	2.3	2.3	1.5	2.2
Bark - Level 2	-	-	-	-	-	-	-	*	-	-	-	*
Grass - Level 1	-	*	*	0.1	*	*	0.1	0.1	0.1	0.3	-	*
Grass - Level 2	-	-	-	-	-	-	-	*	-	-	-	-
Prep - Level 1	-	*	-	*	-	*	*	*	-	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	*	*	-	*	-	*	*	*	-	*	*	*
Seed Coat - Level 2	-	-	-	-	-	-	-	*	-	-	-	-
Oil - Level 1	-	-	-	*	-	*	-	*	-	*	*	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	*	*	-	*	-	*	-	*	-	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	*	*	*	-	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	*	-	-	-	-
STRENGTH 1/ 22 & Below	-	0.2	-	-	-	*	-	*	-	-	-	-
23	*	0.2	-	-	-	*	-	*	*	*	-	-
24	*	0.6	-	-	-	*	*	*	0.1	*	-	*
25	*	1.8	0.2	*	-	*	0.1	*	0.2	0.1	*	*
26	0.1	4.1	1.0	0.2	*	0.2	0.7	0.4	1.2	0.7	0.4	0.1
27	0.6	5.8	1.5	0.9	0.5	1.9	2.6	1.9	2.6	1.8	2.0	1.2
28	3.3	6.9	1.6	5.4	4.8	8.5	8.9	5.7	7.4	4.8	17.7	8.7
29	17.6	16.9	5.4	19.2	23.3	24.3	23.0	15.0	18.3	13.0	21.6	18.4
30	25.7	23.3	22.5	26.5	30.9	34.3	32.0	29.4	27.8	23.9	26.3	26.7
31	20.2	19.1	30.1	19.9	21.2	20.5	18.4	27.7	21.3	24.3	18.5	24.8
32	15.5	11.2	21.1	14.2	10.9	7.3	9.7	12.7	14.0	17.2	9.7	14.5
33	7.7	5.6	9.7	8.5	4.6	2.2	3.8	5.4	5.1	9.3	3.1	5.0
34	6.8	3.3	4.6	3.5	2.4	0.7	0.6	1.5	1.5	3.5	0.5	0.5
35	2.0	0.8	2.0	1.2	0.9	0.2	0.2	0.2	0.3	0.9	*	0.1
36	0.5	0.2	0.4	0.3	0.2	*	0.1	*	0.1	0.2	-	*
37	*	*	0.1	0.1	0.1	*	*	*	*	0.1	*	*
38	*	*	*	*	*	*	*	*	-	*	*	*
39	-	-	-	-	*	*	-	*	-	-	-	-
40 & Above	-	-	-	-	-	-	-	-	-	-	-	-
Average	31.33	30.41	31.60	31.08	30.83	30.43	30.46	30.88	30.70	31.21	30.28	30.77
Mike												
2.4 & Below	-	0.1	-	-	-	-	-	-	-	-	-	-
2.5	*	0.2	-	-	-	-	-	-	-	*	-	-
2.6	*	0.2	-	-	-	-	-	-	-	*	-	-
2.7	0.2	0.5	-	-	-	-	-	-	-	*	-	-
2.8	0.4	0.6	-	-	-	-	-	*	-	*	*	*
2.9	0.6	0.9	-	-	-	-	-	*	-	*	0.7	0.2
3.0	2.4	1.9	-	*	-	*	*	*	-	*	0.4	0.2
3.1	3.9	3.5	-	*	*	*	-	*	-	*	0.7	0.1
3.2	3.1	3.6	-	*	*	*	-	*	-	*	*	0.2
3.3	5.2	4.0	-	*	*	*	-	*	*	*	0.5	0.3
3.4	6.6	4.6	-	*	*	0.1	*	*	0.1	*	0.7	0.6
3.5	6.5	5.2	-	*	0.1	0.1	*	*	0.2	0.1	3.1	2.0
3.6	6.3	5.7	*	0.1	0.2	0.2	0.1	0.1	0.2	0.1	2.0	2.1
3.7	5.3	5.8	-	0.2	0.8	0.4	0.4	0.2	0.5	0.3	4.0	4.2
3.8	5.5	6.2	0.2	0.5	1.3	0.9	0.5	0.5	0.9	0.5	3.7	5.0
3.9	10.1	8.0	0.1	1.0	1.6	1.7	0.7	1.0	2.7	1.0	3.1	6.0
4.0	8.6	7.4	0.8	1.4	2.6	3.0	2.3	1.9	2.6	1.4	7.0	6.8
4.1	6.3	7.4	1.8	2.6	4.2	4.8	3.8	2.9	4.4	2.2	5.9	7.1
4.2	5.9	6.3	1.8	4.3	5.7	7.6	5.1	4.3	5.2	3.4	5.1	8.9
4.3	5.4	5.2	4.3	7.6	8.7	9.8	6.7	6.6	5.7	5.2	7.9	9.1
4.4	5.4	4.9	6.4	11.3	11.1	12.0	9.6	9.9	8.1	8.2	8.9	11.2
4.5	3.2	4.8	16.3	16.0	11.4	12.9	13.4	13.1	10.3	11.1	11.4	9.4
4.6	2.8	3.9	21.1	16.7	12.5	12.4	17.4	15.5	13.2	14.1	12.6	9.1
4.7	2.3	3.1	17.5	16.1	12.7	11.2	19.2	15.6	12.8	15.3	8.1	5.9
4.8	2.1	2.5	16.4	11.0	10.7	8.5	10.5	12.9	12.0	13.8	6.3	3.8
4.9	0.6	1.6	8.7	6.0	7.6	6.1	5.6	8.1	8.9	10.8	2.8	1.9
5.0	0.1	1.0	2.9	3.0	4.7	4.0	3.0	4.2	6.1	6.6	0.9	1.4
5.1	0.3	0.6	0.7	1.3	2.4	2.5	1.2	1.9	3.0	3.4	1.2	1.9
5.2	0.2	0.1	0.4	0.5	1.1	1.2	0.4	0.9	1.5	1.5	0.5	1.6
5.3	0.5	0.1	0.5	0.2	0.6	0.4	0.1	0.4	0.9	0.6	1.8	0.7
5.4	0.1	*	0.2	0.1	0.1	0.1	*	0.1	0.5	0.3	0.5	0.2
5.5 & Above	*	*	*	*	*	*	*	*	0.3	0.1	-	*
Average	3.87	3.93	4.63	4.57	4.55	4.52	4.56	4.59	4.59	4.64	4.33	4.29

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 02, 2020

Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter										
Bark - Level 1	14.3	6.3	2.3	1.6	0.6	0.3	23.3	8.4	2.0	0.6
Bark - Level 2	-	-	-	-	-	-	-	*	-	-
Grass - Level 1	*	*	*	0.3	-	*	0.1	0.1	*	0.1
Grass - Level 2	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	*	*	-	*	-	*	-	*	-	*
Prep - Level 2	-	-	-	-	-	-	-	*	-	-
Seed Coat - Level 1	-	*	-	*	-	*	*	0.1	-	*
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	-	-	*	*	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	-	-	*	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	-	*	-	*	*	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	*	*	-	*	-	*	*	*	-	-
23	*	*	*	*	-	*	*	0.1	-	-
24	*	0.1	0.1	0.1	*	*	0.2	0.4	-	*
25	*	0.2	0.9	0.5	0.1	*	0.7	1.0	*	*
26	0.2	0.6	4.2	1.9	1.0	0.5	2.0	2.5	*	0.4
27	1.3	1.8	9.4	5.0	4.3	4.1	5.5	5.5	1.3	1.5
28	4.7	4.3	19.2	11.3	16.3	18.5	10.8	10.4	5.1	4.3
29	10.3	8.9	20.3	24.0	34.0	31.2	14.8	16.1	32.0	13.3
30	16.4	15.2	23.5	26.1	23.7	24.5	18.5	20.0	35.6	26.4
31	18.1	18.6	11.6	16.7	11.4	12.3	17.7	18.2	20.7	25.6
32	14.2	16.6	6.1	8.3	5.2	5.8	13.6	12.8	4.6	17.6
33	11.3	13.4	3.2	3.8	2.4	2.3	8.1	7.2	0.4	7.4
34	10.1	9.7	1.2	1.6	1.0	0.6	4.3	3.5	0.2	2.4
35	6.1	5.9	0.3	0.5	0.4	0.2	1.9	1.5	*	0.8
36	4.5	3.2	0.1	0.2	0.1	*	1.0	0.6	*	0.2
37	2.4	1.1	*	*	*	*	0.5	0.2	-	0.1
38	0.4	0.3	-	*	*	*	0.2	0.1	-	-
39	*	*	-	-	-	*	*	*	-	-
40 & Above	-	-	-	-	-	-	*	*	-	-
Average	32.19	32.08	29.76	30.27	29.97	29.96	30.86	30.65	30.35	31.16
Mike										
2.4 & Below	-	-	-	*	-	-	*	*	-	-
2.5	-	-	-	*	-	-	0.2	*	-	-
2.6	-	*	-	*	-	-	0.3	0.1	-	-
2.7	-	*	-	*	-	-	0.4	0.1	-	-
2.8	-	*	-	*	*	*	0.5	0.2	-	-
2.9	*	*	-	*	*	*	0.4	0.2	-	-
3.0	0.1	0.1	*	*	-	*	0.6	0.3	-	-
3.1	0.2	0.2	*	*	-	*	0.8	0.5	-	-
3.2	0.5	0.2	*	*	*	*	1.2	0.7	-	*
3.3	0.4	0.3	*	*	*	*	1.6	0.9	-	*
3.4	0.6	0.4	*	*	0.2	0.1	1.7	1.1	-	*
3.5	0.9	0.7	0.1	0.1	0.3	0.2	1.9	1.5	-	*
3.6	1.5	1.4	0.1	0.1	0.9	0.4	2.8	1.8	-	*
3.7	2.1	2.1	0.2	0.2	1.6	0.6	3.0	2.3	0.9	0.1
3.8	3.1	3.1	0.3	0.4	2.9	1.0	3.7	3.0	1.3	0.1
3.9	4.2	4.0	0.4	0.7	3.7	1.7	3.8	3.7	1.3	0.3
4.0	4.5	5.0	1.3	1.3	3.7	2.6	4.7	4.5	2.7	0.6
4.1	4.5	5.9	2.1	2.8	4.2	3.7	5.3	5.5	3.6	1.2
4.2	5.4	7.0	4.5	4.9	5.8	5.5	6.2	6.6	5.4	2.2
4.3	6.5	8.2	6.9	8.2	8.5	8.1	6.6	7.7	3.9	3.9
4.4	8.2	9.3	10.0	11.2	7.2	11.2	7.6	8.9	8.7	6.7
4.5	7.5	9.9	12.7	13.8	8.6	13.6	8.0	9.5	10.9	11.4
4.6	8.9	9.9	12.3	15.2	8.1	14.5	8.1	9.5	15.0	15.8
4.7	9.7	9.3	15.6	14.4	7.4	13.1	7.9	9.1	22.0	18.1
4.8	8.4	7.6	14.5	11.6	8.8	10.3	7.1	7.8	11.1	15.7
4.9	7.5	5.8	10.9	7.5	12.7	6.7	5.8	5.8	3.9	11.4
5.0	6.7	4.3	4.1	4.0	9.4	3.8	4.5	4.0	3.6	6.9
5.1	5.0	2.6	1.3	1.8	4.5	1.9	2.9	2.4	4.3	3.2
5.2	2.0	1.6	0.7	0.8	1.3	0.7	1.4	1.2	1.5	1.4
5.3	1.1	0.8	0.8	0.5	0.2	0.2	0.7	0.5	*	0.6
5.4	0.5	0.2	0.7	0.3	*	*	0.2	0.2	-	0.3
5.5 & Above	0.1	0.1	0.5	0.1	*	*	0.1	0.1	-	0.1
Average	4.49	4.44	4.62	4.58	4.54	4.54	4.32	4.39	4.58	4.69

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 02, 2020

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	-	*	-	-	-	*	-	*	-	*	-	*
2.7 - 2.9	-	*	-	*	*	*	0.3	0.2	-	*	*	*
3.0 - 3.2	0.1	0.1	-	*	0.9	0.2	0.7	1.0	-	*	*	*
3.3 - 3.4	0.3	0.3	0.5	0.1	0.8	0.4	0.3	0.9	-	*	*	0.1
3.5 - 3.6	1.3	1.4	0.7	0.4	1.1	1.0	4.1	2.5	-	*	0.2	0.4
3.7 - 4.2	24.3	31.7	19.8	20.0	17.7	15.9	22.6	28.3	2.6	5.8	15.6	12.2
4.3 - 4.9	70.0	63.5	63.4	73.2	59.6	67.7	65.2	59.8	95.1	88.7	79.4	80.9
5.0 - 5.2	4.1	2.9	12.8	5.6	13.8	11.5	2.5	4.8	2.3	5.3	4.4	6.0
5.3 & Above	*	0.2	2.8	0.7	6.2	3.2	4.2	2.5	-	0.1	0.3	0.4
Average	4.44	4.38	4.54	4.49	4.59	4.57	4.39	4.40	4.64	4.59	4.51	4.55
Leaf												
1 - 2	5.5	14.2	1.6	9.4	51.1	71.8	63.0	72.6	3.0	6.5	6.7	17.4
3	45.0	48.6	26.0	37.5	27.6	20.8	27.0	22.1	39.3	38.3	43.0	48.5
4	38.6	30.1	45.8	35.6	11.5	5.2	8.2	4.7	49.6	44.4	39.5	28.4
5	9.5	6.3	23.4	15.7	4.6	1.4	1.7	0.6	7.8	10.3	9.7	5.3
6	0.9	0.8	3.1	1.8	3.5	0.6	0.1	*	0.4	0.6	1.0	0.3
7	0.2	0.1	*	*	1.5	0.2	*	*	-	*	0.1	*
8	0.2	*	-	*	0.3	0.1	-	-	-	*	*	*
Average	3.57	3.30	4.00	3.63	2.74	2.13	2.33	2.07	3.63	3.60	3.55	3.21
HVI Trash 1/												
00	-	*	*	*	*	*	-	0.1	-	-	-	*
01	0.9	2.9	0.1	1.4	23.9	41.5	29.8	40.9	0.3	1.1	1.1	3.9
02	7.5	15.5	2.1	9.9	29.9	34.1	35.0	34.7	4.5	7.7	8.7	17.9
03	21.1	24.7	8.1	16.6	16.1	12.7	17.1	14.0	17.3	16.9	20.3	24.6
04	26.7	23.1	15.8	18.3	9.9	5.5	9.3	5.5	27.1	23.2	24.4	21.9
05	19.5	15.9	19.8	17.0	6.2	2.6	4.8	2.6	24.9	21.6	19.5	15.0
06	11.2	9.0	18.1	14.1	3.9	1.4	2.4	1.3	14.7	14.7	12.6	8.7
07	6.3	4.6	14.3	10.2	2.6	0.8	1.1	0.5	6.9	8.0	6.8	4.4
08	3.5	2.2	10.2	6.3	2.0	0.4	0.4	0.2	2.6	3.8	3.4	2.1
09	1.6	1.0	5.8	3.4	1.8	0.3	0.1	0.1	1.1	1.7	1.7	0.9
10	0.7	0.5	3.1	1.6	1.3	0.2	*	*	0.4	0.7	0.8	0.4
11	0.3	0.2	1.5	0.7	1.1	0.2	*	*	0.2	0.3	0.4	0.2
12	0.1	0.1	0.6	0.3	0.6	0.1	-	*	*	0.1	0.1	0.1
13	0.1	*	0.2	0.1	0.3	*	*	*	-	*	0.1	*
14	0.1	*	0.1	*	0.2	*	-	*	*	*	*	*
15	0.1	*	*	*	0.1	*	-	*	-	*	*	*
16	0.1	*	*	*	*	*	-	-	-	*	*	*
17	0.1	*	*	*	*	*	-	-	-	*	*	*
18 & Above	0.2	*	-	*	*	*	-	-	*	*	*	*
Average	0.46	0.40	0.59	0.50	0.32	0.21	0.24	0.20	0.47	0.47	0.46	0.39
UNIFORMITY 2/												
74 & Below	-	-	-	-	-	-	-	-	-	-	-	-
75	*	*	-	*	-	*	-	-	-	-	-	*
76	*	*	-	*	*	*	-	*	-	*	*	*
77	0.2	0.2	0.1	0.1	0.1	0.2	*	0.1	*	*	0.1	0.1
78	1.1	2.2	0.5	0.4	1.5	1.8	0.4	0.5	*	0.3	0.7	0.9
79	7.5	11.4	2.3	2.3	7.9	8.7	3.0	2.6	0.6	1.9	4.2	5.2
80	26.2	30.7	11.1	12.3	19.7	21.7	17.7	12.8	6.8	13.4	15.9	19.2
81	37.4	35.2	34.7	35.4	34.0	35.7	31.3	30.4	46.0	41.1	34.9	37.3
82	21.8	16.4	38.2	35.4	26.4	25.6	14.7	26.5	43.3	32.9	30.9	27.9
83	5.3	3.5	11.8	12.6	9.0	5.5	20.0	15.5	3.1	8.7	11.3	8.1
84	0.5	0.4	1.3	1.5	1.0	0.7	12.5	11.1	0.1	1.6	1.9	1.2
85 & Above	*	*	0.1	0.1	0.4	0.2	0.3	0.4	-	0.1	0.1	0.1
Average	81.34	81.08	81.93	81.92	81.54	81.39	82.14	82.18	81.85	81.83	81.78	81.60
Tenderable 3/	78.1	86.6	78.7	90.4	67.9	81.0	85.6	88.1	83.4	83.3	83.0	85.3
SAMPLES CLASSED	27,622	893,033	38,297	1,347,712	21,714	199,060	7,553	133,730	7,504	144,694	106,685	2,469,029

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 02, 2020

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	0.1	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	*	0.4	-	-	-	-	-	-	-	*	-	-
2.7 - 2.9	1.2	2.0	-	-	-	-	-	*	-	*	0.7	0.2
3.0 - 3.2	9.4	9.0	-	*	*	*	*	*	-	*	1.1	0.5
3.3 - 3.4	11.8	8.6	-	*	0.1	0.1	*	*	0.1	*	1.2	0.9
3.5 - 3.6	12.8	10.9	*	0.2	0.3	0.3	0.1	0.1	0.3	0.2	5.1	4.1
3.7 - 4.2	41.8	41.1	4.6	9.9	16.1	18.4	12.8	10.8	16.3	8.7	28.8	37.9
4.3 - 4.9	21.7	26.1	90.6	84.7	74.6	72.9	82.4	81.5	71.0	78.4	58.1	50.4
5.0 - 5.2	0.6	1.7	4.1	4.9	8.3	7.7	4.5	6.9	10.5	11.5	2.6	4.9
5.3 & Above	0.6	0.2	0.7	0.3	0.7	0.5	0.1	0.5	1.7	1.0	2.3	0.9
Average	3.87	3.93	4.63	4.57	4.55	4.52	4.56	4.59	4.59	4.64	4.33	4.29
Leaf												
1 - 2	47.5	36.9	6.8	19.6	6.9	10.1	15.7	17.2	11.2	11.3	46.7	65.8
3	32.6	27.9	38.5	42.1	39.7	39.4	37.3	39.9	59.9	51.7	43.3	27.3
4	14.4	15.4	42.5	29.0	38.0	35.0	36.1	31.7	25.3	31.8	8.5	5.6
5	3.9	9.1	11.9	8.4	13.8	14.0	9.6	9.8	3.3	4.9	1.2	1.0
6	1.0	5.2	0.3	1.0	1.6	1.5	1.2	1.2	0.3	0.3	0.1	0.2
7	0.4	3.0	-	*	-	*	*	0.1	*	*	0.1	*
8	0.1	2.4	-	*	-	-	-	*	*	*	-	*
Average	2.73	3.32	3.60	3.28	3.63	3.57	3.42	3.37	3.22	3.31	2.59	2.26
HVI Trash 1/												
00	-	-	-	-	-	*	-	*	-	-	-	*
01	18.0	13.2	1.4	4.1	0.8	1.3	3.3	4.2	0.6	1.4	11.3	25.7
02	32.7	26.8	7.2	19.8	6.9	9.5	14.4	16.1	12.0	12.2	33.8	39.1
03	17.2	15.3	16.6	20.4	15.5	17.2	16.4	19.1	29.2	24.7	29.4	19.2
04	13.1	10.3	20.6	17.8	18.9	18.8	17.9	18.3	26.9	25.7	14.8	8.4
05	8.1	7.4	19.4	14.3	18.3	17.2	17.4	15.4	16.4	18.0	6.3	3.9
06	4.5	5.2	16.0	10.1	15.0	13.9	13.6	11.3	8.7	10.0	2.8	1.8
07	2.6	4.1	10.3	6.3	10.4	9.8	8.5	7.3	3.5	4.7	0.9	0.8
08	1.6	3.2	5.2	3.6	6.6	6.1	4.4	4.2	1.6	2.0	0.4	0.4
09	0.9	2.7	2.2	1.8	3.6	3.3	2.2	2.2	0.7	0.8	0.2	0.2
10	0.5	2.3	0.8	1.0	2.0	1.6	1.1	1.1	0.3	0.3	0.1	0.1
11	0.3	1.9	0.3	0.5	1.0	0.7	0.5	0.5	0.1	0.1	*	0.1
12	0.2	1.6	0.1	0.2	0.4	0.3	0.2	0.2	0.1	*	0.1	0.1
13	0.1	1.3	*	0.1	0.2	0.1	*	0.1	*	*	0.1	*
14	0.1	1.1	*	*	0.1	*	*	*	*	*	-	*
15	*	0.8	-	*	*	*	*	*	*	*	-	-
16	*	0.7	*	*	*	*	*	*	*	*	-	-
17	-	0.5	-	*	*	*	-	*	*	*	-	-
18 & Above	*	1.7	-	*	-	*	*	*	*	*	-	*
Average	0.31	0.46	0.49	0.42	0.52	0.49	0.46	0.44	0.40	0.41	0.29	0.24
UNIFORMITY 2/												
74 & Below	*	*	-	-	-	-	-	-	-	-	-	-
75	*	*	-	-	-	-	*	*	*	*	-	-
76	0.1	0.2	-	-	*	*	*	*	*	*	-	-
77	0.6	0.9	0.1	*	*	*	0.1	0.1	*	0.1	-	*
78	3.2	2.4	0.3	0.3	0.2	0.1	1.0	0.8	0.4	0.6	*	0.1
79	16.0	14.3	3.0	2.1	1.0	0.9	4.3	4.4	2.6	4.4	1.5	1.4
80	39.1	38.2	10.0	13.9	10.3	6.6	19.3	20.1	15.4	19.8	6.2	11.7
81	36.0	36.4	33.5	37.4	33.4	26.2	47.3	44.8	40.2	37.9	36.9	26.7
82	4.8	7.2	36.1	33.1	39.0	42.7	24.5	25.3	32.9	29.3	48.4	45.3
83	0.2	0.4	13.8	11.2	14.0	20.8	3.1	4.1	7.7	6.9	6.8	14.4
84	*	*	2.1	1.8	1.9	2.5	0.3	0.4	0.8	0.8	0.1	0.3
85 & Above	*	*	1.0	0.3	0.2	0.2	*	*	*	0.1	-	*
Average	80.67	80.74	82.01	81.88	82.05	82.29	81.44	81.48	81.74	81.60	81.98	82.04
Tenderable 3/	63.9	52.7	86.9	89.7	88.4	89.4	87.1	88.4	82.7	83.3	81.3	86.7
SAMPLES CLASSED	15,110	106,224	18,662	555,520	37,836	751,563	49,487	1,459,621	24,885	999,070	4,435	23,602

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 02, 2020

Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE										
2.4 & Below	-	-	-	*	-	-	*	*	-	-
2.5 - 2.6	-	*	-	*	-	-	0.5	0.1	-	-
2.7 - 2.9	*	0.1	-	*	*	*	1.3	0.6	-	-
3.0 - 3.2	0.7	0.5	0.1	*	*	0.1	2.6	1.5	-	*
3.3 - 3.4	1.1	0.7	0.1	*	0.3	0.1	3.4	2.0	-	*
3.5 - 3.6	2.4	2.2	0.2	0.2	1.2	0.5	4.7	3.3	-	*
3.7 - 4.2	23.8	27.0	8.8	10.3	21.9	15.1	26.7	25.7	15.2	4.4
4.3 - 4.9	56.6	59.9	82.9	81.8	61.2	77.6	51.1	58.3	75.5	83.0
5.0 - 5.2	13.7	8.5	6.0	6.6	15.1	6.4	8.8	7.6	9.3	11.6
5.3 & Above	1.7	1.1	2.0	1.0	0.2	0.2	1.0	0.9	*	1.0
Average	4.49	4.44	4.62	4.58	4.54	4.54	4.32	4.39	4.58	4.69
Leaf										
1 - 2	36.5	56.6	12.1	14.3	5.9	14.5	27.4	46.1	9.8	23.3
3	39.7	30.2	59.4	57.1	48.6	44.3	44.9	38.5	58.1	61.0
4	16.0	9.1	26.3	25.8	34.0	30.6	19.8	12.2	28.9	14.7
5	5.4	2.8	2.1	2.7	10.5	9.4	5.4	2.5	3.0	1.0
6	1.6	0.9	0.1	0.1	1.0	1.2	1.6	0.5	0.2	*
7	0.5	0.3	*	*	-	*	0.5	0.1	-	-
8	0.2	0.1	0.1	*	-	*	0.3	*	-	*
Average	2.91	2.46	3.18	3.17	3.52	3.38	3.09	2.64	3.26	2.93
HVI Trash 1/										
00	*	*	-	*	-	*	-	*	-	-
01	12.4	27.4	1.4	1.7	0.6	2.3	7.1	17.6	0.3	3.0
02	28.1	32.9	13.3	15.6	6.4	13.4	24.8	32.5	10.4	22.4
03	22.6	18.5	28.9	28.8	20.0	20.9	25.3	22.7	26.3	33.1
04	15.2	9.4	27.3	25.5	24.1	20.2	17.7	13.1	28.1	23.4
05	8.3	4.9	16.4	15.5	19.0	16.1	10.9	7.0	18.1	11.3
06	5.0	2.8	7.7	7.6	12.8	11.3	6.0	3.5	10.2	4.4
07	3.1	1.6	3.0	3.3	8.0	7.2	3.3	1.7	4.3	1.6
08	1.9	0.9	1.1	1.2	4.7	4.2	1.9	0.9	1.3	0.6
09	1.3	0.6	0.5	0.5	2.4	2.2	1.1	0.4	0.7	0.2
10	0.7	0.4	0.1	0.2	1.2	1.1	0.6	0.2	0.3	0.1
11	0.5	0.3	0.1	0.1	0.5	0.6	0.4	0.1	0.1	*
12	0.3	0.2	*	*	0.2	0.3	0.2	0.1	-	*
13	0.2	0.1	*	*	0.1	0.1	0.1	*	-	*
14	0.1	0.1	-	*	*	*	0.1	*	-	*
15	0.1	*	*	*	*	*	0.1	*	-	*
16	*	*	*	*	-	*	0.1	*	-	*
17	*	*	*	*	*	*	*	*	-	-
18 & Above	0.1	*	*	*	-	*	0.2	*	-	-
Average	0.34	0.26	0.39	0.39	0.48	0.45	0.37	0.29	0.41	0.34
UNIFORMITY 2/										
74 & Below	*	*	-	-	-	-	*	*	-	-
75	*	*	-	*	-	-	0.1	0.1	-	*
76	0.1	0.2	-	*	-	*	0.7	0.6	-	*
77	0.3	1.0	0.1	0.3	*	0.1	3.6	2.5	-	0.1
78	2.8	3.7	0.4	1.4	0.6	0.5	12.4	8.0	0.1	0.2
79	13.9	11.8	4.0	7.7	7.5	5.0	24.9	19.5	0.3	1.3
80	32.8	27.5	23.2	30.3	29.6	22.4	30.4	30.3	1.8	8.8
81	32.8	34.1	45.4	40.4	42.7	36.5	20.3	25.9	44.4	34.8
82	14.3	17.6	20.9	16.4	15.8	26.9	6.4	10.8	43.9	39.3
83	2.6	3.5	5.3	3.1	3.1	7.9	1.0	1.9	9.2	13.2
84	0.4	0.5	0.7	0.3	0.6	0.7	0.1	0.2	0.3	2.2
85 & Above	0.1	0.1	0.1	*	*	0.1	*	*	-	0.2
Average	80.96	81.04	81.47	81.17	81.22	81.56	80.17	80.53	82.04	82.06
Tenderable 3/	65.9	80.4	85.8	87.4	79.3	89.6	48.0	67.0	87.6	85.6
SAMPLES CLASSED	33,829	363,290	13,238	388,225	27,336	913,480	128,250	5,873,246	4,533	199,513

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 02, 2020

Color Grade	Leaf	Arizona		California		New Mexico		Texas	
		Week	Season	Week	Season	Week	Season	Week	Season
01	1	60.6	54.5	28.9	26.6	-	-	-	10.9
	2	5.8	6.9	8.7	8.0	-	-	-	15.4
	3	-	1.7	*	*	-	-	-	0.3
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		66.4	63.1	37.6	34.6	-	-	-	26.6
02	1	21.4	24.6	28.4	30.8	-	-	-	14.9
	2	10.7	7.5	28.7	31.4	-	-	-	44.9
	3	0.3	2.8	0.8	1.0	-	-	-	5.0
	4	-	1.2	-	*	-	-	-	0.1
	5	-	*	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		32.4	36.0	58.0	63.1	-	-	-	64.8
03	1	0.5	0.1	0.6	0.3	-	-	-	1.1
	2	0.5	0.4	2.7	1.5	-	-	-	5.4
	3	-	0.1	0.7	0.4	-	-	-	1.5
	4	-	0.2	*	*	-	-	-	0.1
	5	-	*	*	*	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		1.1	0.8	4.1	2.2	-	-	-	8.1
04	1	-	*	-	*	-	-	-	-
	2	-	-	0.1	*	-	-	-	0.1
	3	0.1	*	0.2	*	-	-	-	0.3
	4	-	0.1	*	*	-	-	-	0.1
	5	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		0.1	0.1	0.3	0.1	-	-	-	0.4
05	1	-	-	-	-	-	-	-	-
	2	-	-	*	*	-	-	-	*
	3	-	-	-	*	-	-	-	0.1
	4	-	-	-	*	-	-	-	-
	5	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	*	-	-	-	-
Total -----		-	-	*	*	-	-	-	0.1
06	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	*
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	-	-	-	-	-	*
07	1	-	-	-	-	-	-	-	-
	2	-	-	*	*	-	-	-	-
	3	-	-	*	*	-	-	-	-
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	*	*	-	-	-	-
STAPLE									
44 & Shorter		0.2	0.9	*	0.5	-	-	-	0.8
46		10.7	18.0	0.5	7.1	-	-	-	9.2
48		78.9	60.7	20.1	25.1	-	-	-	63.5
50		10.2	20.3	73.6	62.4	-	-	-	20.9
52 & Longer		-	0.1	5.9	4.8	-	-	-	5.6
Average Staple		47.98	48.01	49.70	49.28	-	-	-	48.42
Average Length		1.40	1.40	1.44	1.43	-	-	-	1.41
EXTRANEIOUS MATTER									
Bark		-	-	*	*	-	-	-	1.0
Grass		-	-	0.1	0.1	-	-	-	0.9
Spindle Twist		0.1	*	1.1	0.2	-	-	-	0.1
Preparation		-	-	*	*	-	-	-	-
All Other		0.1	0.1	*	*	-	-	-	0.1

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 02, 2020

Quality Designation	Arizona		California		New Mexico		Texas	
	Week	Season	Week	Season	Week	Season	Week	Season
MIKE								
2.4 & Below	-	-	-	*	-	-	-	-
2.5 - 2.6	-	-	-	*	-	-	-	-
2.7 - 2.9	-	*	0.2	0.1	-	-	-	*
3.0 - 3.2	-	1.6	0.7	0.3	-	-	-	0.4
3.3 - 3.4	7.0	9.3	1.8	0.8	-	-	-	1.4
3.5 - 3.6	16.0	18.1	3.2	2.4	-	-	-	6.6
3.7 - 4.2	76.1	68.2	55.8	60.5	-	-	-	74.6
4.3 - 4.9	0.9	2.7	38.1	35.8	-	-	-	16.9
5.0 - 5.2	-	-	0.1	*	-	-	-	-
5.3 & Above	-	-	*	*	-	-	-	-
Average	3.83	3.77	4.14	4.14	-	-	-	3.97
ALL RANGE MIKE								
2.4 & Below	-	-	-	*	-	-	-	-
2.5	-	-	-	*	-	-	-	-
2.6	-	-	-	*	-	-	-	-
2.7	-	-	*	*	-	-	-	-
2.8	-	-	0.1	*	-	-	-	-
2.9	-	*	0.1	*	-	-	-	*
3.0	-	*	0.1	0.1	-	-	-	*
3.1	-	0.8	0.4	0.1	-	-	-	0.2
3.2	-	0.8	0.2	0.1	-	-	-	0.2
3.3	3.2	3.3	0.7	0.2	-	-	-	0.5
3.4	3.8	6.0	1.2	0.5	-	-	-	0.9
3.5	3.0	7.0	1.1	0.8	-	-	-	1.9
3.6	13.0	11.1	2.1	1.7	-	-	-	4.7
3.7	8.2	14.6	2.0	3.0	-	-	-	10.5
3.8	16.6	16.3	4.6	6.4	-	-	-	16.3
3.9	22.6	18.6	9.4	10.0	-	-	-	14.5
4.0	15.2	10.0	12.4	12.7	-	-	-	13.1
4.1	11.9	6.9	14.4	13.8	-	-	-	12.0
4.2	1.5	1.9	12.9	14.6	-	-	-	8.2
4.3	0.8	2.2	14.1	14.0	-	-	-	7.5
4.4	-	0.2	13.1	12.1	-	-	-	5.9
4.5	0.1	0.4	5.6	6.5	-	-	-	2.7
4.6	-	-	2.7	2.4	-	-	-	0.8
4.7	-	-	1.7	0.8	-	-	-	*
4.8	-	-	0.7	0.2	-	-	-	*
4.9	-	-	0.2	*	-	-	-	-
5.0	-	-	*	*	-	-	-	-
5.1	-	-	*	*	-	-	-	-
5.2	-	-	-	*	-	-	-	-
5.3 & Above	-	-	*	*	-	-	-	-
Average	3.83	3.77	4.14	4.14	-	-	-	3.97
STRENGTH 1/ 36 & Below	-	*	*	*	-	-	-	0.1
37	-	0.1	0.1	0.1	-	-	-	0.6
38	0.4	0.2	0.1	1.2	-	-	-	1.0
39	0.2	0.6	0.3	3.4	-	-	-	1.4
40	0.2	2.3	0.5	3.6	-	-	-	2.2
41	0.5	9.5	1.5	2.7	-	-	-	10.3
42	5.1	17.1	3.6	4.6	-	-	-	13.6
43	17.6	26.9	8.4	9.6	-	-	-	17.1
44	41.1	23.7	16.4	18.3	-	-	-	21.9
45	26.4	13.4	24.3	25.4	-	-	-	18.4
46	5.3	4.5	23.7	18.9	-	-	-	10.2
47	1.9	1.1	14.8	8.8	-	-	-	2.6
48 & Above	1.2	0.6	6.3	3.4	-	-	-	0.8
Average	44.59	43.72	45.63	44.83	-	-	-	43.92
UNIFORMITY								
83 & Below	0.3	1.3	0.2	0.3	-	-	-	0.7
84	9.4	10.2	1.8	5.1	-	-	-	2.1
85	56.5	38.7	16.0	15.7	-	-	-	22.1
86	32.5	45.9	59.2	54.0	-	-	-	63.3
87	1.1	3.9	21.9	23.3	-	-	-	11.5
88 & Above	0.1	0.1	0.9	1.5	-	-	-	0.4
Average	85.73	85.86	86.49	86.44	-	-	-	86.29
Samples Classed	913	7,634	26,744	406,679	-	-	-	13,812

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.