



Volume 21, No.13

State	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
AL	29	91.7	80.3	78,571	29	92.8	79.0	222,427
AR	28	90.6	78.3	105,594	28	93.9	84.7	327,796
AZ	2	70.2	39.0	3,748	2	82.7	47.7	23,456
CA	8	89.4	76.7	9,279	8	90.2	79.5	16,570
FL	4	89.4	76.3	9,055	4	90.9	78.5	20,222
GA	57	90.5	71.7	198,632	57	91.2	69.8	563,034
KS*	-	-	-	-	2	2.90	2.40	17,195
LA	19	92.3	74.2	53,404	19	95.4	82.8	178,777
MO	19	93.3	80.3	57,417	19	92.1	77.8	144,309
MS	35	85.6	57.1	122,265	36	91.7	70.9	347,827
NC	34	80.8	52.1	106,909	34	80.6	50.7	223,262
NM	-	-	-	-	-	-	-	-
OK	10	87.5	73.7	19,410	10	87.7	72.8	23,124
SC	14	88.2	64.9	32,641	14	88.1	66.5	87,081
TN	22	91.3	77.9	82,284	22	92.1	76.7	224,105
TX	139	73.1	45.3	268,910	146	82.0	55.4	1,679,184
VA	4	81.0	49.0	19,487	4	81.2	50.5	41,485
United States	425	85.1	63.9	1,167,730	434	86.9	65.4	4,139,854
AMERICAN PIMA								
AZ	-			-	-			-
CA	9			13,263	9			15,858
NM	-			-	-			-
TX	-			-	-			-
United States	9			13,263	9			15,858
United States all cotton	433			1,180,993	442			4,155,712

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Oct 24, 2019

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	20.2	23.8	7.5	11.5	39.8	38.5	69.0	79.0	18.1	17.0	22.8	24.3
	3	18.1	25.2	6.1	10.6	10.5	19.2	9.4	8.2	13.9	14.5	16.3	18.4
	4	1.3	1.9	0.2	0.5	1.5	2.0	0.6	0.4	0.9	0.8	0.8	0.7
	5	*	*	-	*	0.2	0.1	-	-	-	-	*	*
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	39.6	50.9	13.8	22.6	52.0	59.8	79.0	87.6	32.8	32.4	39.9	43.4
31	1 - 2	5.2	3.8	6.6	6.3	4.4	1.5	7.8	4.8	7.4	7.0	12.3	8.1
	3	23.1	20.7	27.8	27.0	9.6	4.3	9.2	5.3	32.7	33.0	27.8	27.7
	4	9.8	9.5	12.8	13.9	7.5	3.4	3.8	2.1	10.8	11.2	6.6	7.5
	5	0.7	1.0	1.1	1.8	1.3	0.6	0.2	0.1	1.6	0.8	0.3	0.3
	6	*	0.1	*	*	-	*	-	-	0.1	*	*	*
	7	*	*	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	38.8	35.1	48.4	49.0	22.7	9.7	21.0	12.3	52.5	52.2	47.0	43.6
41	1 - 2	0.4	0.2	0.3	0.2	0.1	*	-	-	0.3	0.2	1.1	0.5
	3	6.4	2.9	4.6	3.1	0.3	0.1	-	-	4.9	4.5	4.4	2.4
	4	7.7	3.7	17.2	12.6	0.8	0.2	*	*	5.6	6.0	2.9	2.3
	5	2.2	1.2	12.7	10.4	0.1	*	-	-	1.2	0.8	0.6	0.5
	6	0.2	0.2	1.5	1.0	-	*	-	-	0.1	0.1	0.1	*
	7	*	*	*	*	-	-	-	-	*	*	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	16.9	8.1	36.3	27.4	1.3	0.4	*	*	12.2	11.6	9.0	5.6
51	1 - 2	*	*	-	*	-	-	-	-	-	-	*	*
	3	0.1	*	*	*	-	-	-	-	0.6	0.3	0.1	*
	4	0.1	0.1	0.1	*	-	-	-	-	0.9	0.4	*	*
	5	0.1	*	0.2	0.1	-	-	-	-	0.1	0.1	*	*
	6	*	*	0.1	*	-	-	-	-	-	-	*	*
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	*	-	-	-	-	-	-	-	-
Total	----	0.3	0.1	0.3	0.2	-	-	-	-	1.7	0.7	0.2	0.1
61	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	-	*	*
	4	-	-	-	*	-	-	-	-	-	-	-	*
	5	-	-	*	*	-	-	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	*	*
Total	----	-	-	*	*	-	-	-	-	-	-	*	*
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	-	-	-	-	-
12 & 22	1 - 2	0.4	0.5	0.1	0.1	3.8	11.2	-	-	-	0.2	0.5	1.1
	3	0.5	0.9	0.1	*	6.3	12.0	-	-	-	0.2	0.4	0.7
	4	*	0.2	*	*	2.4	2.2	-	-	-	0.1	*	*
	5	-	*	-	-	0.5	0.2	-	-	-	-	-	-
	6	-	-	-	-	*	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.9	1.7	0.2	0.1	13.0	25.6	-	-	-	0.5	0.9	1.7
32	1 - 2	0.1	0.2	0.1	*	0.3	0.2	-	*	0.1	0.2	0.3	0.7
	3	0.8	1.4	0.4	0.3	3.5	1.1	-	-	0.2	0.9	1.4	2.9
	4	0.5	1.0	0.2	0.1	2.8	1.6	-	-	*	1.1	0.4	0.8
	5	*	0.2	*	*	1.2	0.7	-	-	-	0.1	*	*
	6	*	*	-	*	0.2	0.1	-	-	*	*	-	*
	7	*	*	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	1.5	2.8	0.7	0.5	8.0	3.6	-	*	0.3	2.3	2.2	4.5
42	1 - 2	*	*	*	*	-	*	-	-	*	*	0.1	*
	3	0.4	0.3	0.1	0.1	0.1	*	-	-	0.1	0.1	0.4	0.4
	4	0.6	0.4	0.2	0.2	0.6	0.1	-	-	0.2	0.2	0.3	0.5
	5	0.3	0.2	0.1	0.1	0.5	0.1	-	-	0.1	*	*	0.1
	6	0.1	0.1	*	*	-	-	-	-	-	-	*	*
	7	*	*	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	1.5	1.0	0.4	0.3	1.1	0.3	-	-	0.4	0.3	0.8	1.0

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Oct 24, 2019

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	-	*	-	-	-	-	-	-	*	*
	3	*	*	*	*	-	-	-	-	*	*	*	*
	4	0.1	0.1	*	*	-	-	-	-	*	*	*	*
	5	0.1	*	*	*	-	-	-	-	*	*	-	*
	6	*	*	*	*	-	-	-	-	-	-	*	*
	7	*	*	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total		----	0.30.1	**		-	-	-	-	0.1*		**	
62	1 - 2	-	-	-	*	-	-	-	-	*	*	-	-
	3	-	-	*	*	-	-	-	-	-	-	-	-
	4	-	*	-	-	-	-	-	-	-	-	-	*
	5	-	*	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total		----	-*	**		-	-	-	-	**		-*	
13 & 23	1 - 2	-	-	-	-	0.1	0.2	-	-	-	-	*	*
	3	-	*	-	-	1.1	0.2	-	-	-	-	*	*
	4	-	*	-	-	0.1	*	-	-	-	-	*	*
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total		----	-*	-	-	1.30.5		-	-	-	-	**	
33	1 - 2	*	*	*	*	-	*	-	-	-	-	*	*
	3	*	*	*	*	-	*	-	-	-	-	*	*
	4	*	*	*	*	0.1	*	-	-	-	-	*	*
	5	*	*	-	*	0.2	*	-	-	-	-	*	*
	6	-	*	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total		----	0.1*	**		0.30.1		-	-	-	-	**	
43	1 - 2	*	*	-	-	-	-	-	-	-	-	*	*
	3	*	*	*	*	0.1	*	-	-	-	-	*	*
	4	*	*	*	*	*	*	-	-	*	*	*	*
	5	*	*	-	*	-	*	-	-	*	*	*	*
	6	-	-	-	*	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total		----	0.1*	**		0.1*		-	-	**		**	
53	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	*	-	-	-	-	-	-	-	-	-	-
	4	*	*	-	-	-	-	-	-	-	-	*	*
	5	-	*	*	*	-	-	-	-	-	-	-	-
	6	*	*	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total		----	**	**		-	-	-	-	-	-	**	
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	-	-	-
	4	-	*	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	*	*
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	*	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total		----	-*	-	*	-	-	-	-	-	-	**	
24 - 54	1 - 8	*	*	*	*	0.3	*	-	-	-	-	*	*
	25 - 35	-	-	-	-	-	-	-	-	-	-	-	-
	81 - 85	*	*	-	-	-	-	-	-	-	-	*	*
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	-	-	-	-	-	-	-	-	-	-	*
31		*	0.1	-	-	-	-	-	-	-	-	0.1	0.1
32		0.5	0.9	-	*	-	-	-	-	0.2	0.1	0.5	0.7
33		2.0	3.0	*	*	-	*	*	*	2.6	1.6	2.8	3.7
34		6.8	8.1	*	0.1	*	0.7	0.6	0.3	4.8	4.4	7.7	10.0
35		14.0	15.5	2.1	2.5	13.6	7.5	3.5	2.8	3.9	5.5	15.2	17.1
36		22.3	24.5	14.2	14.5	37.8	30.7	18.3	15.6	7.2	12.2	20.9	21.8
37		31.8	30.7	44.4	44.6	29.7	30.9	47.5	41.8	41.6	44.0	34.0	32.5
38		15.7	12.2	24.0	22.2	11.4	21.7	22.5	22.3	32.6	27.6	15.6	11.9
39		5.9	4.3	12.6	13.7	7.0	8.4	7.4	15.8	7.1	4.6	2.9	2.1
40 & Longer		0.9	0.6	2.7	2.4	0.4	0.2	0.2	1.3	0.1	0.1	0.3	0.2
Average Staple		36.49	36.26	37.39	37.37	36.62	36.91	37.11	37.36	37.06	36.94	36.34	36.12
Average Length		1.14	1.13	1.17	1.17	1.14	1.15	1.16	1.17	1.16	1.15	1.13	1.13

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Oct 24, 2019

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	-	*	18.5	25.9	5.7	10.0	23.3	30.0	11.2	12.8	-	-
	3	-	0.1	18.4	25.7	2.7	4.6	19.6	25.3	9.7	13.0	-	-
	4	-	*	1.1	1.7	*	0.1	2.2	3.3	0.6	0.8	-	-
	5	-	*	*	*	-	-	*	0.1	*	*	-	-
	6	-	-	-	-	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	*	-	-	-	-
Total	----	-	0.2	37.9	53.2	8.4	14.7	45.1	58.7	21.6	26.6	-	-
31	1 - 2	-	-	2.4	2.2	9.5	10.9	4.8	3.0	4.9	4.5	-	-
	3	-	0.2	21.4	16.7	27.1	31.4	22.2	18.0	31.3	31.1	-	-
	4	-	0.7	9.9	9.5	14.3	14.4	13.0	11.6	17.9	17.1	-	-
	5	-	0.6	1.1	1.0	2.1	1.7	1.7	1.7	1.7	1.6	-	-
	6	-	0.1	*	*	0.1	*	*	*	*	*	-	-
	7	-	*	*	*	-	-	-	*	*	*	-	-
	8	-	-	-	-	-	-	-	*	-	-	-	-
Total	----	-	1.5	34.8	29.4	53.0	58.5	41.7	34.3	55.8	54.3	-	-
41	1 - 2	-	-	0.1	0.1	0.9	0.4	0.2	0.1	0.2	0.1	-	-
	3	-	0.1	5.9	3.8	8.7	5.1	2.9	1.5	5.9	4.6	-	-
	4	-	0.8	13.3	7.3	17.9	13.1	5.1	2.5	10.5	8.4	-	-
	5	-	1.8	4.6	2.7	9.7	7.1	2.8	1.4	3.3	2.4	-	-
	6	-	1.0	1.0	0.4	0.9	0.6	0.6	0.3	0.3	0.2	-	-
	7	-	0.3	*	*	*	*	*	*	*	*	-	-
	8	-	0.1	-	-	-	-	-	-	-	-	-	-
Total	----	-	4.1	24.9	14.4	38.2	26.3	11.6	5.7	20.3	15.8	-	-
51	1 - 2	-	-	-	-	-	-	*	*	-	*	-	-
	3	-	-	*	*	-	*	*	*	*	*	-	-
	4	-	0.1	0.1	0.1	*	*	0.1	*	0.1	0.1	-	-
	5	-	0.5	0.2	0.1	*	*	0.2	0.1	0.2	0.1	-	-
	6	-	0.2	0.2	0.1	*	*	0.1	*	*	*	-	-
	7	-	*	*	*	-	-	*	*	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	0.9	0.6	0.3	0.1	*	0.4	0.2	0.3	0.2	-	-
61	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	*	*	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	*	*	-	-	-	-
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	-	-	-	-	-
12 & 22	1 - 2	-	-	0.2	0.5	*	*	0.1	0.2	0.1	0.1	-	-
	3	-	*	0.3	0.6	-	*	0.2	0.3	0.1	0.2	-	-
	4	-	0.1	*	0.1	-	-	0.1	0.1	*	*	-	-
	5	-	*	-	*	-	-	-	*	*	*	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	0.1	0.6	1.3	*	*	0.4	0.5	0.2	0.4	-	-
32	1 - 2	-	-	*	0.1	*	*	0.1	*	0.1	0.1	-	-
	3	-	0.2	0.3	0.3	*	0.2	0.3	0.2	0.6	0.7	-	-
	4	-	1.0	0.2	0.2	*	*	0.2	0.2	0.3	0.5	-	-
	5	-	1.7	*	*	*	*	0.1	*	*	0.1	-	-
	6	-	0.6	-	-	-	-	-	*	-	*	-	-
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	3.5	0.5	0.7	0.1	0.2	0.6	0.5	1.0	1.4	-	-
42	1 - 2	-	-	*	*	*	*	*	*	*	*	-	-
	3	-	0.2	0.1	0.2	0.1	0.1	0.1	*	0.2	0.3	-	-
	4	-	1.6	0.4	0.3	0.1	0.1	0.1	*	0.4	0.7	-	-
	5	-	5.7	0.1	0.1	*	*	*	*	0.1	0.3	-	-
	6	-	5.0	*	*	*	*	*	*	*	*	-	-
	7	-	1.7	*	*	-	-	-	-	-	-	-	-
	8	-	0.6	-	-	-	-	-	-	-	-	-	-
Total	----	-	14.8	0.6	0.7	0.2	0.2	0.2	0.1	0.8	1.3	-	-

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Oct 24, 2019

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	-	-	-	*	-	*	-	-	-	-
	3	-	-	*	*	-	0.1	-	*	-	*	-	-
	4	-	0.1	*	*	*	*	*	*	*	*	-	-
	5	-	0.5	*	*	-	*	*	*	*	*	-	-
	6	-	0.8	*	*	-	*	*	*	-	*	-	-
	7	-	0.5	*	*	-	-	-	-	-	-	-	-
	8	-	0.6	-	-	-	-	-	-	-	-	-	-
Total		----	- 2.6	0.1	*	*	0.1	*	*	*	*	-	-
62	1 - 2	-	-	-	-	-	-	*	*	-	-	-	-
	3	-	-	-	-	-	*	-	-	-	-	-	-
	4	-	*	-	-	-	*	-	*	-	-	-	-
	5	-	*	-	-	-	*	*	*	-	-	-	-
	6	-	-	-	-	-	*	-	-	-	-	-	-
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total		----	- *	- -	- -	- *	- *	*	*	- -	- -	- -	- -
13 & 23	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	*	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	*	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total		----	- *	- -	- -	- -	- -	- -	- -	- -	- -	- -	- -
33	1 - 2	-	-	*	*	-	*	*	*	*	*	-	-
	3	-	0.2	*	*	-	*	*	*	*	*	-	-
	4	-	1.0	*	*	-	*	*	*	*	*	-	-
	5	-	3.0	-	-	-	-	-	-	*	*	-	-
	6	-	1.6	-	-	-	-	-	-	-	-	-	-
	7	-	0.3	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total		----	- 6.1	*	*	- *	- *	*	*	*	*	-	-
43	1 - 2	-	*	-	-	-	*	*	*	-	-	-	-
	3	-	0.4	*	*	*	*	*	*	*	*	-	-
	4	-	2.8	*	*	*	*	*	*	*	*	-	-
	5	-	6.4	*	*	-	-	*	*	*	*	-	-
	6	-	6.1	-	*	-	-	*	*	-	-	-	-
	7	-	2.9	-	-	-	-	-	-	-	-	-	-
	8	-	2.6	-	-	-	-	-	-	-	-	-	-
Total		----	- 21.3	*	*	*	*	*	*	*	*	-	-
53	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	*	-	-	-	*	-	-
	4	-	0.6	*	*	-	*	*	*	*	*	-	-
	5	-	1.5	-	-	-	*	-	*	-	-	-	-
	6	-	3.1	-	-	-	-	-	-	-	-	-	-
	7	-	4.2	-	-	-	-	-	-	-	-	-	-
	8	-	3.0	-	-	-	-	-	-	-	-	-	-
Total		----	- 12.4	*	*	- *	- *	*	*	*	*	-	-
63	1 - 2	-	-	-	-	-	*	-	*	-	-	-	-
	3	-	-	-	-	-	*	-	*	-	-	-	-
	4	-	*	-	-	-	*	-	*	-	-	-	-
	5	-	*	-	-	-	*	*	*	-	*	-	-
	6	-	0.1	-	-	-	*	-	*	-	-	-	-
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total		----	- 0.2	- -	- -	- *	- *	*	*	- *	- *	-	-
24 - 54	1 - 8	-	21.0	-	*	-	-	-	*	*	*	-	-
25 - 35	1 - 8	-	*	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	11.3	-	-	-	-	-	*	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	-	-	-	-	-	-	-	-	-	-	-
31		-	*	-	-	-	-	-	-	*	*	-	-
32		-	*	-	-	-	-	*	*	0.1	0.1	-	-
33		-	1.2	-	*	*	*	0.1	0.1	0.8	0.6	-	-
34		-	13.5	*	0.1	0.2	0.4	1.3	0.7	3.6	3.4	-	-
35		-	43.2	0.3	0.7	6.1	7.4	3.9	3.0	11.3	11.5	-	-
36		-	31.4	6.4	8.6	19.7	23.3	12.2	10.8	27.9	28.4	-	-
37		-	10.1	19.3	24.1	45.7	45.9	27.7	26.3	33.4	34.1	-	-
38		-	0.5	33.1	32.5	17.8	14.5	34.6	36.0	14.6	14.8	-	-
39		-	*	30.8	28.2	9.1	7.2	18.6	21.2	6.9	6.3	-	-
40 & Longer		-	-	10.0	5.8	1.3	1.2	1.6	1.9	1.3	0.8	-	-
Average Staple		-	35.37	38.19	37.97	37.07	36.93	37.52	37.65	36.67	36.66	-	-
Average Length		-	1.10	1.19	1.19	1.16	1.15	1.17	1.18	1.14	1.14	-	-

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Oct 24, 2019

Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	68.0	63.6	14.9	14.7	6.6	13.6	36.2	32.3	23.6	21.1
	3	7.2	8.6	17.4	21.2	3.2	7.4	11.1	15.4	28.9	31.6
	4	0.3	0.3	1.1	1.5	0.3	0.5	0.7	1.2	1.7	2.0
	5	-	-	-	*	*	*	*	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	75.5	72.5	33.3	37.5	10.1	21.5	48.1	48.9	54.2	54.7
31	1 - 2	6.5	6.8	8.9	6.0	8.2	9.4	3.1	4.3	3.9	3.0
	3	8.8	10.4	35.4	31.9	25.7	26.9	6.9	10.2	27.0	26.3
	4	1.7	1.9	11.4	13.6	8.5	10.4	2.2	3.6	12.6	14.0
	5	0.1	0.1	0.5	1.0	0.7	1.2	0.2	0.3	0.8	0.8
	6	-	-	*	*	*	*	*	*	-	-
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	17.1	19.1	56.2	52.5	43.1	47.9	12.4	18.5	44.3	44.0
41	1 - 2	*	*	0.5	0.2	1.2	0.7	0.6	1.1	*	*
	3	*	*	2.4	1.4	12.3	6.8	2.8	4.0	0.4	0.3
	4	*	*	2.2	1.9	19.3	11.6	1.9	2.4	0.4	0.3
	5	-	-	0.6	0.7	9.1	6.1	0.4	0.4	0.1	0.1
	6	-	-	0.1	0.1	1.6	1.2	*	*	-	-
	7	-	-	-	-	0.1	0.1	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	*	0.1	5.8	4.3	43.6	26.3	5.7	7.9	1.0	0.7
51	1 - 2	-	-	-	-	-	*	0.1	0.1	-	-
	3	-	-	*	*	*	*	0.8	0.6	-	*
	4	*	*	-	*	0.1	*	0.6	0.5	-	*
	5	-	-	*	*	0.1	*	0.1	0.1	-	-
	6	-	-	-	-	0.1	0.1	*	*	-	-
	7	-	-	-	-	*	*	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	*	*	0.4	0.2	1.7	1.4	-	*
61	1 - 2	-	-	-	*	-	*	*	*	-	-
	3	-	-	-	*	-	-	*	0.1	-	-
	4	-	-	-	*	-	-	*	0.1	-	-
	5	-	-	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	-	-	-	*	-	*	0.1	0.2	-	-
71	1 - 2	-	-	-	-	-	-	*	*	-	-
	3	-	-	-	-	-	-	*	*	-	-
	4	-	-	-	-	-	-	*	*	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	-	-	-	-	-	-	*	*	-	-
12 & 22	1 - 2	0.9	1.5	0.2	0.3	*	0.3	12.0	8.1	*	*
	3	1.8	1.9	0.3	0.5	0.1	0.1	5.8	5.1	0.1	0.2
	4	0.2	0.3	*	*	*	*	0.9	0.9	-	*
	5	-	-	-	-	-	*	0.1	0.1	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	2.9	3.6	0.6	0.8	0.1	0.4	18.6	14.1	0.1	0.2
32	1 - 2	0.1	0.2	0.2	0.3	0.2	0.5	2.7	1.1	*	*
	3	1.2	1.2	1.4	2.1	0.8	1.3	3.0	2.4	0.2	0.1
	4	2.0	1.8	0.9	1.2	0.3	0.5	1.5	1.1	0.1	0.1
	5	0.2	0.2	0.1	0.2	*	*	0.3	0.2	*	*
	6	-	*	*	*	-	-	0.1	*	*	*
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	3.5	3.5	2.6	3.8	1.2	2.4	7.5	4.9	0.3	0.3
42	1 - 2	-	*	*	*	*	*	0.2	0.3	-	-
	3	*	*	0.6	0.3	0.6	0.5	0.8	0.9	*	*
	4	0.1	0.1	0.6	0.4	0.6	0.6	0.8	0.7	*	*
	5	*	*	0.1	0.1	0.1	0.1	0.2	0.2	*	*
	6	-	*	*	*	*	*	*	*	-	-
	7	-	-	-	-	*	*	*	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	0.1	0.1	1.4	0.9	1.4	1.3	2.1	2.1	0.1	0.1

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE											
For The Week Ending Oct 24, 2019											
Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	-	*	-	-	*	*	-	-
	3	-	-	*	*	*	*	0.2	0.2	-	-
	4	-	-	-	*	*	*	0.3	0.2	*	*
	5	*	*	-	*	*	*	*	0.1	-	-
	6	-	-	-	*	*	*	*	*	-	-
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	*	*	*	*	*	*	0.6	0.5	*	*
62	1 - 2	-	-	-	-	-	-	*	*	-	-
	3	-	-	-	-	-	-	*	*	-	-
	4	-	-	-	*	-	-	*	*	-	-
	5	-	-	-	*	-	-	*	*	-	-
	6	-	-	-	*	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	-	-	*	0.1	-	-
13 & 23	1 - 2	*	*	-	-	-	-	0.4	0.2	-	-
	3	0.1	0.1	-	*	-	-	0.3	0.2	-	-
	4	*	*	-	-	-	-	0.1	*	-	-
	5	-	-	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	0.1	0.1	-	*	-	-	0.7	0.5	-	-
33	1 - 2	-	*	-	*	*	*	0.8	0.2	-	-
	3	0.1	0.2	*	0.1	*	*	0.6	0.3	-	-
	4	0.4	0.6	*	*	*	*	0.2	0.1	-	-
	5	0.1	0.1	*	*	-	-	0.1	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	0.6	0.9	0.1	0.1	*	*	1.7	0.7	-	-
43	1 - 2	-	-	-	-	-	*	0.1	*	-	-
	3	-	-	*	*	*	*	0.3	0.1	-	-
	4	0.1	*	*	*	*	*	0.1	0.1	-	-
	5	*	*	-	-	*	*	*	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	0.1	0.1	*	*	*	*	0.6	0.2	-	-
53	1 - 2	-	-	-	-	-	-	*	*	-	-
	3	*	*	-	*	*	*	*	*	-	-
	4	-	-	-	*	-	*	*	*	-	-
	5	*	*	-	*	-	-	*	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	*	*	-	*	*	*	0.1	0.1	-	-
63	1 - 2	-	-	-	-	-	-	*	*	-	-
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	*	-	-	*	*	-	-
	5	-	-	-	*	-	-	*	*	-	-
	6	-	-	-	*	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	-	-	*	*	-	-
24 - 54	1 - 8	*	*	*	*	*	*	0.1	*	-	-
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	-	-	*	-	-	*	*	-	-
STAPLE											
28 & Shorter		-	-	-	-	-	-	*	*	-	-
29		-	*	-	-	-	-	*	*	-	-
30		0.1	0.2	-	-	-	-	0.6	0.2	-	-
31		0.5	0.7	0.2	0.1	-	-	2.7	0.9	-	-
32		1.7	1.8	0.5	0.3	-	-	6.6	2.8	-	-
33		7.2	7.5	2.6	1.8	*	*	10.8	6.0	*	0.1
34		6.9	7.7	6.7	6.5	0.7	1.3	15.3	11.2	0.9	1.5
35		11.6	12.2	12.6	13.1	11.4	15.6	17.3	18.0	3.0	4.1
36		17.8	19.2	20.7	20.4	35.8	40.4	15.5	21.1	14.3	14.4
37		29.3	28.3	42.1	41.6	37.9	31.5	18.1	24.3	37.6	36.8
38		18.9	17.0	11.9	14.0	11.1	9.3	8.9	11.2	24.4	24.2
39		5.5	4.9	2.6	2.2	2.8	1.8	3.6	3.7	15.1	14.9
40 & Longer		0.6	0.5	0.1	0.1	0.2	0.1	0.6	0.6	4.7	4.0
Average Staple		36.29	36.17	36.38	36.44	36.56	36.37	35.25	35.85	37.46	37.39
Average Length		1.13	1.13	1.13	1.14	1.14	1.13	1.10	1.12	1.17	1.17

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Oct 24, 2019

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	1.3	1.0	0.5	0.7	-	-	-	-	3.3	3.3	1.5	1.4
Bark - Level 2	-	-	-	*	-	-	-	-	-	-	*	*
Grass - Level 1	0.3	0.2	0.2	0.2	-	*	-	0.1	0.4	0.2	0.2	0.2
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	*	*	-	*	-	-	-	*	-	-	*	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	*	*
Seed Coat - Level 1	*	*	*	*	-	*	-	-	*	*	*	*
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	*	-	-	-	-	-	-	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	-	-	-	-	-	-	*	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	*	*	*	*	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	*	-	*	-	-	-	-	-	-	-	*
23	*	*	-	*	-	-	-	-	-	*	*	0.1
24	*	0.1	*	*	-	-	-	-	*	*	0.1	0.3
25	0.2	0.9	*	*	*	*	*	*	0.2	0.5	0.7	1.7
26	1.4	3.5	0.1	0.2	*	0.1	-	-	1.5	3.3	3.1	6.0
27	6.3	11.6	1.0	1.5	2.3	3.2	4.6	2.6	4.3	10.1	8.1	13.0
28	19.6	25.3	6.7	8.7	19.2	8.4	4.5	2.6	15.5	21.1	16.2	21.2
29	30.3	29.1	19.7	24.5	30.1	21.6	3.4	6.4	28.7	31.4	25.0	24.4
30	23.1	17.6	29.4	31.1	15.7	26.4	8.4	18.7	30.6	21.2	23.3	17.8
31	11.2	7.3	25.9	21.4	11.8	20.3	17.7	20.0	14.1	8.8	13.8	9.3
32	5.6	3.2	11.7	9.0	13.9	14.2	17.7	15.7	4.0	2.5	6.0	3.9
33	1.7	1.1	3.6	2.5	6.2	5.2	5.9	4.6	0.8	0.7	2.3	1.5
34	0.5	0.3	1.3	0.7	0.8	0.5	2.0	1.1	0.2	0.2	0.9	0.5
35	0.1	*	0.3	0.2	-	*	6.8	4.1	0.1	0.1	0.3	0.2
36	*	*	0.2	0.1	-	*	11.1	10.2	-	*	0.1	0.1
37	*	*	*	*	-	-	13.4	10.5	-	-	*	*
38	-	-	-	-	-	-	4.0	3.1	-	-	*	*
39	-	-	-	-	-	-	0.5	0.3	-	-	-	-
40 & Above	-	-	-	-	-	-	0.1	*	-	-	-	-
Average	29.80	29.29	30.76	30.48	30.32	30.63	33.29	32.76	29.91	29.42	29.85	29.29
Mike												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	-
2.5	-	-	-	-	-	-	-	-	-	-	-	-
2.6	-	-	-	-	-	-	-	-	-	-	*	*
2.7	-	-	-	-	-	-	-	-	-	-	-	*
2.8	-	*	*	*	-	-	-	-	-	-	*	*
2.9	-	-	*	*	-	-	-	*	*	*	*	*
3.0	*	*	-	*	-	-	-	0.9	-	-	*	*
3.1	*	*	*	*	-	-	-	0.8	-	-	*	*
3.2	*	*	-	*	-	-	-	0.5	-	-	*	*
3.3	0.1	0.1	*	*	*	*	-	0.7	-	-	*	*
3.4	0.3	0.3	*	0.1	0.3	*	-	0.7	-	-	*	0.1
3.5	0.5	0.5	*	0.1	1.2	0.2	-	1.3	-	-	0.1	0.1
3.6	0.9	1.0	0.2	0.2	0.1	*	0.6	2.2	0.1	*	0.2	0.2
3.7	1.4	1.7	0.3	0.5	0.1	0.1	2.5	2.7	*	*	0.2	0.5
3.8	2.7	3.0	0.9	1.1	0.4	0.5	3.7	3.5	*	0.1	0.4	0.8
3.9	4.7	4.9	1.9	1.8	2.9	1.0	4.1	4.8	0.3	0.4	0.9	1.3
4.0	5.9	6.4	3.0	2.9	4.3	1.6	8.9	6.8	2.1	1.8	1.7	2.4
4.1	7.9	8.6	5.6	5.1	5.3	3.9	6.4	9.6	3.3	3.4	3.0	4.2
4.2	10.5	10.3	8.4	8.3	6.2	6.0	5.2	8.9	6.3	6.4	5.5	7.1
4.3	12.3	12.2	10.3	12.0	4.3	8.8	6.3	9.3	7.8	10.0	8.7	10.6
4.4	13.1	12.3	12.3	14.0	5.5	12.3	8.5	8.3	11.2	16.4	13.3	14.1
4.5	11.7	11.6	12.5	15.5	7.8	13.4	9.0	8.7	20.3	21.4	15.9	15.6
4.6	9.2	9.9	12.6	14.1	7.9	12.0	13.5	10.2	17.0	16.7	15.9	14.4
4.7	7.2	7.8	11.8	10.8	6.0	8.9	8.5	6.8	12.5	11.0	13.0	11.1
4.8	4.6	4.5	8.1	6.3	13.5	11.1	6.7	3.8	8.0	5.6	9.2	8.0
4.9	3.4	2.7	5.0	3.3	12.9	7.5	5.5	3.4	4.8	3.0	5.8	5.0
5.0	1.8	1.2	3.3	1.8	6.8	5.2	4.1	2.5	3.2	2.0	3.4	2.6
5.1	0.8	0.4	1.9	1.0	9.8	4.1	1.6	0.9	2.2	1.4	1.7	1.2
5.2	0.5	0.2	1.2	0.7	1.4	1.9	2.4	1.3	0.8	0.4	0.6	0.4
5.3	0.3	0.1	0.3	0.2	1.0	0.8	2.1	1.2	0.1	*	0.3	0.2
5.4	0.1	0.1	0.1	*	2.1	0.3	0.3	0.2	*	*	0.1	0.1
5.5 & Above	*	*	*	*	0.3	0.1	*	*	-	-	0.1	0.1
Average	4.36	4.34	4.50	4.46	4.63	4.58	4.46	4.31	4.55	4.51	4.55	4.50

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Oct 24, 2019

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	-	75.5	0.5	0.2	0.2	0.2	0.4	0.2	2.2	1.6	-	-
Bark - Level 2	-	-	-	-	-	-	-	*	-	-	-	-
Grass - Level 1	-	-	0.1	0.1	*	*	0.2	0.2	0.4	0.4	-	-
Grass - Level 2	-	-	-	-	-	-	-	*	-	-	-	-
Prep - Level 1	-	-	-	-	*	*	*	*	-	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	-	-	*	-	*	*	*	-	*	-	-
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	*	-	-	-	*	-	-	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	-	-	*	*	*	-	-	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	-	0.1	*	*	*	*	*	*	*	*	-	-
Plastic - Level 2	-	-	-	-	-	-	-	*	-	-	-	-
STRENGTH 1/ 22 & Below	-	1.0	-	-	-	*	-	-	-	-	-	-
23	-	1.2	-	-	-	*	-	-	-	*	-	-
24	-	3.9	-	-	-	*	*	*	*	*	-	-
25	-	11.4	-	*	*	*	*	*	0.2	0.1	-	-
26	-	24.5	0.1	0.1	0.2	0.3	0.5	0.5	1.1	0.9	-	-
27	-	30.5	1.4	1.4	1.7	3.5	1.5	1.9	1.7	2.1	-	-
28	-	18.8	8.6	9.2	9.8	14.7	4.3	4.7	4.0	5.0	-	-
29	-	6.8	23.5	26.6	26.2	29.1	11.4	14.0	11.4	13.6	-	-
30	-	1.5	28.4	27.2	34.9	31.4	30.5	33.6	22.6	23.3	-	-
31	-	0.3	18.8	16.8	19.4	15.2	32.0	29.0	23.9	22.4	-	-
32	-	*	11.8	12.5	6.4	4.6	13.7	11.0	18.4	17.4	-	-
33	-	*	5.1	4.8	1.3	0.9	4.4	4.0	11.2	10.3	-	-
34	-	-	2.1	1.2	0.1	0.2	1.5	1.0	4.1	3.7	-	-
35	-	-	0.3	0.2	*	*	0.2	0.1	1.1	0.9	-	-
36	-	-	*	*	-	*	*	*	0.3	0.2	-	-
37	-	-	*	*	-	-	-	-	*	*	-	-
38	-	-	-	-	-	-	-	-	-	-	-	-
39	-	-	-	-	-	-	-	-	-	-	-	-
40 & Above	-	-	-	-	-	-	-	-	-	-	-	-
Average	-	27.13	30.67	30.57	30.30	30.03	30.97	30.81	31.34	31.19	-	-
Mike												
2.4 & Below	-	0.4	-	-	-	-	-	-	-	-	-	-
2.5	-	1.2	-	-	-	-	-	-	-	-	-	-
2.6	-	1.0	-	-	-	-	-	-	-	-	-	-
2.7	-	1.5	-	-	-	-	-	-	-	*	-	-
2.8	-	1.6	-	-	-	-	-	-	-	*	-	-
2.9	-	1.9	-	-	-	-	-	*	-	*	-	-
3.0	-	1.8	-	*	-	*	-	-	*	*	-	-
3.1	-	3.2	*	*	-	*	-	*	*	*	-	-
3.2	-	3.0	-	*	-	*	*	*	*	*	-	-
3.3	-	1.6	-	*	-	*	*	*	*	*	-	-
3.4	-	2.3	0.1	*	*	*	*	*	*	*	-	-
3.5	-	3.1	0.1	*	0.1	*	*	*	*	*	-	-
3.6	-	5.1	0.2	0.2	0.1	0.1	0.1	0.1	*	*	-	-
3.7	-	7.3	0.3	0.2	0.2	0.2	0.1	0.3	0.1	0.1	-	-
3.8	-	7.4	0.6	0.6	0.4	0.6	0.3	0.6	0.2	0.2	-	-
3.9	-	8.5	1.5	1.8	1.4	1.6	0.8	1.5	0.3	0.3	-	-
4.0	-	6.3	2.0	2.3	3.8	3.3	1.1	2.6	0.8	0.7	-	-
4.1	-	7.4	2.6	4.0	7.0	5.8	2.0	3.6	1.1	1.1	-	-
4.2	-	7.4	3.0	5.8	9.8	8.4	2.9	4.5	2.2	2.1	-	-
4.3	-	6.2	7.1	12.1	11.6	10.4	4.8	6.7	3.8	3.7	-	-
4.4	-	6.2	9.9	14.8	11.4	12.0	7.1	10.3	6.7	6.4	-	-
4.5	-	5.2	14.7	16.1	11.7	12.6	10.5	13.4	10.3	9.8	-	-
4.6	-	3.5	16.0	13.8	12.3	12.4	13.1	14.6	13.6	13.1	-	-
4.7	-	3.6	18.5	13.8	11.4	11.3	16.0	14.4	15.8	15.9	-	-
4.8	-	1.8	11.8	8.0	8.3	8.2	16.3	12.4	16.3	16.9	-	-
4.9	-	0.9	6.8	3.6	5.2	6.2	11.9	7.8	12.8	13.4	-	-
5.0	-	0.3	3.9	2.0	2.9	3.9	6.7	3.6	7.9	8.4	-	-
5.1	-	0.1	0.8	0.5	1.6	1.9	3.2	1.8	4.5	4.5	-	-
5.2	-	*	0.2	0.2	0.8	0.9	2.0	1.1	2.0	2.1	-	-
5.3	-	*	*	0.1	0.1	0.1	0.7	0.5	1.0	0.8	-	-
5.4	-	-	*	*	*	*	0.2	0.2	0.3	0.3	-	-
5.5 & Above	-	-	-	*	0.1	*	*	*	0.2	0.1	-	-
Average	-	3.89	4.57	4.49	4.49	4.51	4.67	4.57	4.70	4.71	-	-

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Oct 24, 2019

Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter										
Bark - Level 1	1.8	1.6	1.5	1.1	0.3	0.3	2.1	0.9	0.8	0.7
Bark - Level 2	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	-	-	0.4	0.3	*	*	0.1	0.3	0.2	0.1
Grass - Level 2	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	-	-	*	-	*	*	*	*	*
Prep - Level 2	-	-	-	-	-	-	-	*	-	-
Seed Coat - Level 1	0.3	0.3	-	0.1	-	*	0.2	0.1	*	*
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	-	-	-	*	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	*	*	-	-	-	*	*	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	*	*	0.1	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	0.2	-	*	-	-	0.1	0.1	-	-
23	*	0.2	*	0.1	-	-	0.5	0.2	-	-
24	*	0.4	0.1	0.1	*	*	1.3	0.5	-	*
25	0.2	0.9	0.5	0.5	*	0.1	2.5	1.1	-	0.1
26	0.8	1.6	2.1	2.1	0.2	0.7	4.5	2.7	0.2	0.4
27	2.7	2.9	5.4	5.5	2.9	6.4	7.4	5.7	2.1	2.5
28	7.4	6.7	11.4	14.3	16.2	23.8	11.1	10.9	5.3	5.8
29	14.2	12.9	30.1	30.8	31.4	33.4	14.7	17.4	13.2	13.8
30	17.9	16.7	25.4	23.7	27.4	21.7	18.6	22.1	22.8	26.0
31	13.7	14.3	13.8	12.7	14.2	9.1	16.2	18.4	23.6	22.5
32	15.6	15.8	6.4	6.1	5.6	3.5	10.9	11.0	19.8	17.6
33	15.5	15.3	3.0	2.6	1.7	1.0	6.3	5.5	9.4	7.5
34	7.0	7.1	1.2	1.1	0.3	0.2	3.4	2.8	2.7	2.7
35	3.4	3.5	0.4	0.3	0.1	*	1.6	1.2	0.9	0.9
36	1.1	1.1	0.1	0.1	*	*	0.6	0.4	0.2	0.2
37	0.4	0.4	*	*	*	*	0.2	0.1	*	*
38	0.1	0.1	-	-	-	-	*	*	-	-
39	*	*	-	-	-	-	*	*	-	-
40 & Above	-	-	-	-	-	-	-	-	-	-
Average	31.50	31.40	30.08	29.97	30.04	29.61	30.27	30.45	31.22	31.07
Mike										
2.4 & Below	-	-	-	-	-	-	-	*	-	-
2.5	-	-	-	-	-	-	*	*	-	-
2.6	-	-	-	-	-	-	-	*	-	-
2.7	-	-	-	-	-	-	-	*	-	-
2.8	*	*	-	-	-	-	*	*	-	-
2.9	*	*	-	*	*	*	*	*	-	-
3.0	*	*	-	-	*	*	*	0.1	-	-
3.1	*	*	-	-	0.1	*	0.1	0.1	-	-
3.2	*	*	-	-	0.1	*	0.2	0.2	-	-
3.3	0.1	0.1	-	*	*	*	0.5	0.4	-	-
3.4	0.3	0.3	*	*	*	*	0.6	0.7	-	-
3.5	0.5	0.4	*	*	0.1	0.1	0.9	1.1	-	-
3.6	1.6	1.3	0.2	0.2	0.3	0.2	1.1	1.5	-	-
3.7	1.9	1.6	0.4	0.3	0.7	0.5	1.7	2.3	-	-
3.8	1.7	1.6	0.5	0.5	1.0	0.8	2.3	3.3	*	*
3.9	3.5	3.2	0.9	0.9	1.6	1.6	3.0	4.2	*	0.1
4.0	5.4	5.4	1.0	1.3	2.3	2.5	4.0	5.1	0.1	0.2
4.1	6.0	6.6	2.1	2.5	4.0	3.7	5.2	6.5	0.4	0.4
4.2	8.8	9.9	4.1	4.4	5.1	5.2	6.8	7.7	1.4	1.3
4.3	10.1	11.9	6.8	7.8	7.6	7.4	8.4	9.1	2.2	2.6
4.4	11.8	12.2	9.6	10.8	12.7	11.7	10.3	10.3	4.3	5.0
4.5	11.4	11.0	14.5	14.3	16.4	16.3	11.6	10.4	8.3	9.4
4.6	11.5	10.5	15.3	15.2	15.9	17.1	11.3	9.8	15.7	14.9
4.7	8.4	8.0	15.2	14.1	13.3	13.2	10.5	9.1	17.4	17.7
4.8	7.0	7.1	13.1	11.6	8.7	9.1	7.7	7.0	17.3	17.0
4.9	3.8	3.8	8.7	7.8	5.2	5.6	5.8	4.7	14.8	13.7
5.0	2.7	2.4	4.0	4.2	2.8	2.7	3.7	3.2	9.8	9.5
5.1	1.5	1.3	2.1	1.9	1.5	1.3	2.2	1.7	4.8	4.6
5.2	1.4	1.1	0.7	0.8	0.5	0.5	1.2	0.8	2.4	2.3
5.3	0.2	0.1	0.4	0.6	0.1	0.1	0.4	0.4	0.8	0.7
5.4	0.1	0.1	0.3	0.5	*	*	0.2	0.2	0.2	0.4
5.5 & Above	*	*	0.2	0.2	*	*	0.1	0.2	0.1	0.3
Average	4.41	4.41	4.60	4.59	4.52	4.52	4.45	4.39	4.75	4.74

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Oct 24, 2019

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	-	-	-	-	-	-	-	-	-	-	*	*
2.7 - 2.9	-	*	*	*	-	-	-	*	*	*	*	*
3.0 - 3.2	*	*	*	0.1	-	-	-	2.2	-	-	*	*
3.3 - 3.4	0.4	0.4	*	0.1	0.3	*	-	1.4	-	-	0.1	0.1
3.5 - 3.6	1.5	1.6	0.3	0.3	1.3	0.2	0.6	3.5	0.1	*	0.2	0.4
3.7 - 4.2	33.2	34.9	20.2	19.8	19.3	13.2	30.8	36.4	12.1	12.0	11.8	16.2
4.3 - 4.9	61.5	61.0	72.6	76.0	57.8	74.1	58.1	50.4	81.5	84.1	81.8	78.7
5.0 - 5.2	3.0	1.9	6.4	3.4	18.0	11.2	8.1	4.7	6.2	3.8	5.7	4.2
5.3 & Above	0.4	0.2	0.5	0.2	3.4	1.2	2.5	1.4	0.1	*	0.4	0.3
Average	4.36	4.34	4.50	4.46	4.63	4.58	4.46	4.31	4.55	4.51	4.55	4.50
Leaf												
1 - 2	26.3	28.5	14.6	18.1	48.5	51.6	76.8	83.9	25.8	24.6	37.1	34.7
3	49.5	51.4	39.1	41.2	31.5	37.0	18.6	13.6	52.4	53.5	50.8	52.6
4	20.3	16.9	30.7	27.3	16.0	9.5	4.4	2.5	18.5	19.9	10.9	11.8
5	3.5	2.7	14.1	12.3	3.8	1.8	0.2	0.1	3.0	1.9	1.0	0.9
6	0.4	0.3	1.5	1.1	0.2	0.1	-	-	0.3	0.1	0.1	*
7	0.1	*	*	*	-	-	-	-	*	*	*	*
8	-	-	-	*	-	-	-	-	-	-	*	*
Average	3.01	2.93	3.48	3.36	2.62	2.56	2.03	1.86	2.98	2.98	2.73	2.77
HVI Trash 1/												
00	-	*	-	*	-	-	0.1	0.2	-	-	*	*
01	6.2	6.7	2.3	3.0	27.7	18.6	43.3	51.1	5.8	5.1	9.4	8.3
02	26.0	28.7	15.2	18.4	29.3	45.1	35.9	34.7	27.8	26.0	34.6	33.6
03	26.9	29.4	19.6	21.6	17.7	21.3	10.2	7.8	29.1	29.4	29.3	30.4
04	18.6	18.0	16.9	17.1	13.0	8.9	5.3	3.3	16.7	19.4	15.3	16.3
05	11.1	9.1	14.5	13.4	6.4	3.6	2.6	1.5	10.0	11.5	6.8	7.0
06	5.7	4.2	12.2	10.8	3.5	1.6	1.4	0.8	5.5	5.3	2.7	2.7
07	2.8	2.0	8.9	7.6	1.5	0.6	0.6	0.4	2.5	2.1	1.1	1.0
08	1.5	1.0	5.5	4.4	0.7	0.2	0.4	0.2	1.0	0.7	0.5	0.4
09	0.6	0.5	2.9	2.2	0.2	0.1	0.1	*	0.6	0.3	0.2	0.2
10	0.3	0.2	1.3	0.9	-	*	*	*	0.4	0.2	0.1	0.1
11	0.1	0.1	0.5	0.4	-	*	*	*	0.3	0.1	*	*
12	0.1	*	0.2	0.1	-	-	-	-	0.1	*	*	*
13	*	*	0.1	*	-	-	-	-	0.1	*	*	*
14	*	*	*	*	-	-	-	-	*	*	*	*
15	*	*	*	*	-	-	-	-	-	-	*	*
16	-	*	*	*	-	-	-	-	-	-	-	*
17	-	*	-	*	-	-	-	-	*	*	*	*
18 & Above	-	*	*	*	-	-	-	-	-	-	*	*
Average	0.35	0.33	0.46	0.43	0.26	0.24	0.20	0.17	0.34	0.34	0.29	0.30
UNIFORMITY 2/												
74 & Below	-	-	-	-	-	-	-	-	-	-	-	-
75	-	-	-	-	-	-	-	-	-	-	*	*
76	0.1	*	*	*	-	-	-	-	*	*	*	*
77	0.4	0.4	0.1	0.1	-	-	-	-	0.1	0.1	0.2	0.3
78	2.6	3.4	0.4	0.4	*	*	0.3	0.2	0.6	1.1	1.1	1.9
79	14.8	16.0	2.6	2.5	14.6	5.1	1.6	1.3	4.7	6.7	6.3	9.0
80	33.1	35.8	13.8	14.6	32.8	26.9	11.0	24.9	26.7	29.6	22.5	27.4
81	31.6	31.3	36.3	39.0	37.0	44.2	39.0	37.9	39.8	38.6	39.3	37.8
82	13.7	10.7	33.8	32.6	15.4	23.1	36.9	28.0	20.6	18.0	24.0	18.9
83	3.5	2.1	11.5	9.8	0.1	0.7	6.8	5.2	6.7	5.3	5.7	4.1
84	0.4	0.2	1.3	1.0	-	*	4.4	2.5	0.8	0.6	0.8	0.6
85 & Above	*	*	0.2	0.1	-	-	*	*	0.1	*	0.1	0.1
Average	80.95	80.81	81.86	81.79	80.96	81.32	81.93	81.63	81.43	81.28	81.44	81.22
Tenderable 3/	91.7	92.8	90.6	93.9	70.2	82.7	89.4	90.2	89.4	90.9	90.5	91.2
SAMPLES CLASSED	78,571	222,427	105,594	327,796	3,748	23,456	9,279	16,570	9,055	20,222	198,632	563,034

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Oct 24, 2019

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	0.4	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	-	2.2	-	-	-	-	-	-	-	-	-	-
2.7 - 2.9	-	5.0	-	-	-	-	-	*	-	*	-	-
3.0 - 3.2	-	8.0	*	*	-	*	*	*	*	*	-	-
3.3 - 3.4	-	3.9	0.1	0.1	*	*	*	*	*	*	-	-
3.5 - 3.6	-	8.2	0.2	0.2	0.2	0.1	0.2	0.2	*	*	-	-
3.7 - 4.2	-	44.5	10.0	14.7	22.6	19.8	7.2	13.1	4.7	4.5	-	-
4.3 - 4.9	-	27.4	84.7	82.1	71.8	73.1	79.7	79.6	79.4	79.2	-	-
5.0 - 5.2	-	0.4	5.0	2.8	5.2	6.7	11.9	6.5	14.4	15.0	-	-
5.3 & Above	-	*	*	0.1	0.1	0.2	1.0	0.7	1.5	1.2	-	-
Average	-	3.89	4.57	4.49	4.49	4.51	4.67	4.57	4.70	4.71	-	-
Leaf												
1 - 2	-	*	21.2	28.8	16.2	21.4	28.5	33.4	16.6	17.6	-	-
3	-	1.7	46.4	47.4	38.6	41.3	45.3	45.3	47.8	49.9	-	-
4	-	12.9	25.0	19.2	32.3	27.8	20.6	17.7	29.8	27.7	-	-
5	-	29.9	6.0	4.0	11.9	8.9	4.9	3.3	5.4	4.5	-	-
6	-	26.0	1.3	0.6	1.0	0.7	0.7	0.4	0.4	0.2	-	-
7	-	16.0	0.1	*	*	*	*	*	*	*	-	-
8	-	13.4	-	-	-	-	-	*	-	-	-	-
Average	-	5.82	3.19	2.99	3.42	3.25	3.02	2.88	3.24	3.19	-	-
HVI Trash 1/												
00	-	-	-	-	-	-	-	*	-	-	-	-
01	-	*	4.4	6.5	2.3	3.7	7.3	9.8	3.5	3.3	-	-
02	-	*	21.9	28.8	14.8	19.3	26.2	29.2	15.6	17.0	-	-
03	-	0.3	23.9	25.4	19.3	22.1	24.6	25.4	23.5	24.7	-	-
04	-	1.1	18.7	17.0	17.9	17.9	17.2	16.7	22.7	23.1	-	-
05	-	2.7	13.0	10.5	15.6	14.0	10.9	9.5	16.4	15.9	-	-
06	-	5.0	8.0	5.8	12.7	10.4	6.4	4.9	9.7	8.9	-	-
07	-	8.6	4.5	3.0	8.4	6.4	3.6	2.4	4.9	4.2	-	-
08	-	9.5	2.5	1.5	4.9	3.5	2.0	1.1	2.3	1.9	-	-
09	-	10.6	1.4	0.7	2.4	1.7	1.0	0.5	0.9	0.7	-	-
10	-	10.7	0.8	0.4	1.1	0.7	0.5	0.2	0.3	0.3	-	-
11	-	9.6	0.5	0.2	0.4	0.3	0.2	0.1	0.1	0.1	-	-
12	-	8.7	0.2	0.1	0.2	0.1	0.1	*	0.1	*	-	-
13	-	6.9	0.1	*	0.1	*	*	*	*	*	-	-
14	-	5.8	*	*	*	*	*	*	*	*	-	-
15	-	4.4	-	-	*	*	*	*	*	*	-	-
16	-	3.7	-	-	-	-	*	*	-	*	-	-
17	-	2.8	-	-	*	*	*	*	*	*	-	-
18 & Above	-	9.5	-	-	*	*	-	*	-	-	-	-
Average	-	1.15	0.39	0.34	0.45	0.41	0.35	0.32	0.40	0.39	-	-
UNIFORMITY 2/												
74 & Below	-	*	-	-	-	-	-	-	-	-	-	-
75	-	0.1	-	-	-	-	-	-	*	*	-	-
76	-	0.3	-	-	-	*	*	*	*	*	-	-
77	-	0.8	*	*	0.1	*	0.1	0.1	0.1	0.1	-	-
78	-	2.2	0.2	0.3	0.3	0.2	0.8	0.6	0.8	0.6	-	-
79	-	14.0	2.3	1.6	0.9	0.9	4.4	3.5	5.2	4.8	-	-
80	-	42.7	11.0	15.5	6.9	6.9	20.6	20.3	18.4	19.5	-	-
81	-	36.2	36.8	43.6	31.2	30.6	45.4	46.7	34.7	36.3	-	-
82	-	3.7	35.1	29.4	42.0	42.8	24.2	24.7	31.2	30.9	-	-
83	-	0.1	12.0	8.3	17.0	17.1	4.1	3.8	8.4	7.0	-	-
84	-	*	2.4	1.1	1.5	1.3	0.4	0.3	1.0	0.7	-	-
85 & Above	-	-	0.2	0.1	0.1	0.1	*	*	0.1	*	-	-
Average	-	80.65	81.95	81.75	82.16	82.17	81.46	81.49	81.65	81.61	-	-
Tenderable 3/	-	2.90	92.3	95.4	93.3	92.1	85.6	91.7	80.8	80.6	-	-
SAMPLES CLASSED	-	17,195	53,404	178,777	57,417	144,309	122,265	347,827	106,909	223,262	-	-

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Oct 24, 2019

Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE										
2.4 & Below	-	-	-	-	-	-	-	*	-	-
2.5 - 2.6	-	-	-	-	-	-	*	*	-	-
2.7 - 2.9	0.1	0.1	-	*	*	*	*	*	-	-
3.0 - 3.2	0.1	0.1	-	-	0.2	0.1	0.3	0.4	-	-
3.3 - 3.4	0.4	0.3	*	*	0.1	*	1.2	1.1	-	-
3.5 - 3.6	2.1	1.8	0.3	0.3	0.4	0.3	2.1	2.6	-	-
3.7 - 4.2	27.4	28.2	8.9	9.9	14.7	14.5	23.0	29.0	1.9	1.9
4.3 - 4.9	64.1	64.4	83.2	81.6	79.8	80.4	65.6	60.3	80.0	80.3
5.0 - 5.2	5.5	4.8	6.7	6.9	4.8	4.6	7.2	5.7	17.0	16.4
5.3 & Above	0.3	0.3	0.9	1.3	0.1	0.1	0.7	0.7	1.1	1.4
Average	4.41	4.41	4.60	4.59	4.52	4.52	4.45	4.39	4.75	4.74
Leaf										
1 - 2	75.5	72.1	24.6	21.5	16.2	24.5	56.2	47.7	27.6	24.2
3	19.2	22.4	57.5	57.5	42.8	43.0	32.8	39.6	56.7	58.4
4	4.8	5.0	16.3	18.8	29.1	23.6	9.3	10.9	14.7	16.4
5	0.4	0.5	1.4	2.1	10.1	7.5	1.5	1.6	1.0	0.9
6	-	*	0.1	0.1	1.7	1.3	0.2	0.2	*	*
7	-	-	-	-	0.1	0.1	*	*	-	-
8	-	-	-	-	-	-	*	*	-	-
Average	2.01	2.08	2.94	3.01	3.37	3.16	2.43	2.58	2.88	2.93
HVI Trash 1/										
00	*	*	-	-	*	*	*	*	-	-
01	44.9	40.9	3.7	3.0	3.8	5.9	24.2	16.6	5.0	3.5
02	33.4	34.5	24.7	21.7	13.7	21.3	34.9	33.3	25.2	23.9
03	11.6	13.6	31.9	30.9	20.4	22.9	19.4	23.5	31.3	31.9
04	4.7	5.3	21.1	22.7	19.2	17.8	10.4	13.5	21.3	22.6
05	2.6	2.8	10.6	12.1	15.0	12.3	5.6	7.0	10.2	11.1
06	1.6	1.6	4.7	5.7	11.1	8.3	2.9	3.4	4.4	4.6
07	0.6	0.7	2.1	2.4	7.3	5.2	1.4	1.5	1.6	1.6
08	0.3	0.3	0.7	0.9	4.4	3.0	0.6	0.7	0.5	0.4
09	0.1	0.1	0.3	0.3	2.4	1.6	0.3	0.3	0.2	0.2
10	0.1	0.1	0.1	0.2	1.3	0.8	0.1	0.1	0.1	0.1
11	*	*	*	*	0.7	0.5	0.1	0.1	*	*
12	*	*	*	*	0.4	0.3	*	*	*	*
13	-	*	*	*	0.2	0.1	*	*	*	*
14	-	*	*	*	0.1	0.1	*	*	-	-
15	-	-	*	*	*	*	*	*	-	-
16	-	-	*	*	*	*	*	*	-	-
17	-	*	-	-	*	*	*	*	-	-
18 & Above	-	-	-	-	*	*	*	*	-	-
Average	0.20	0.21	0.34	0.35	0.45	0.39	0.26	0.28	0.33	0.34
UNIFORMITY 2/										
74 & Below	*	*	-	-	-	-	*	*	-	-
75	*	0.1	*	*	-	-	0.2	0.1	-	-
76	0.3	0.4	0.1	*	*	*	1.1	0.4	*	*
77	1.9	2.2	0.7	0.4	0.1	0.1	4.0	1.7	*	*
78	7.0	7.3	2.7	2.1	0.6	0.6	10.7	5.4	0.1	0.2
79	20.7	19.3	10.5	9.9	6.2	6.6	21.3	14.3	1.1	1.4
80	34.4	33.3	34.2	36.2	23.7	26.3	28.0	27.4	7.7	8.7
81	26.8	26.8	38.2	39.3	37.4	35.9	23.7	31.6	28.4	29.7
82	7.9	9.1	11.9	10.5	24.6	24.2	9.2	15.8	40.3	40.5
83	0.9	1.3	1.6	1.4	6.8	5.7	1.6	2.9	17.9	15.9
84	*	0.1	0.1	0.2	0.6	0.5	0.2	0.3	3.9	3.3
85 & Above	0.1	*	-	*	*	*	*	*	0.5	0.4
Average	80.49	80.52	80.94	80.94	81.47	81.41	80.32	80.86	82.24	82.16
Tenderable 3/	87.5	87.7	88.2	88.1	91.3	92.1	73.1	82.0	81.0	81.2
SAMPLES CLASSED	19,410	23,124	32,641	87,081	82,284	224,105	268,910	1,679,184	19,487	41,485

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Oct 24, 2019

Color Grade	Leaf	Arizona		California		New Mexico		Texas	
		Week	Season	Week	Season	Week	Season	Week	Season
01	1	-	-	28.0	32.5	-	-	-	-
	2	-	-	6.2	6.0	-	-	-	-
	3	-	-	*	*	-	-	-	-
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	34.3	38.5	-	-	-	-
02	1	-	-	35.9	35.6	-	-	-	-
	2	-	-	27.0	23.5	-	-	-	-
	3	-	-	0.4	0.3	-	-	-	-
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	63.2	59.4	-	-	-	-
03	1	-	-	0.1	0.1	-	-	-	-
	2	-	-	1.8	1.5	-	-	-	-
	3	-	-	0.6	0.5	-	-	-	-
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	2.5	2.1	-	-	-	-
04	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	*	*	-	-	-	-
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	*	*	-	-	-	-
05	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	-	-	-	-	-	-
06	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	-	-	-	-	-	-
07	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	-	-	-	-	-	-
STAPLE									
44 & Shorter		-	-	2.0	3.2	-	-	-	-
46		-	-	18.3	30.0	-	-	-	-
48		-	-	41.3	34.8	-	-	-	-
50		-	-	37.4	31.3	-	-	-	-
52 & Longer		-	-	0.9	0.8	-	-	-	-
Average Staple		-	-	48.34	47.93	-	-	-	-
Average Length		-	-	1.40	1.39	-	-	-	-
EXTRANEIOUS MATTER									
Bark		-	-	-	-	-	-	-	-
Grass		-	-	-	-	-	-	-	-
Spindle Twist		-	-	-	-	-	-	-	-
Preparation		-	-	*	*	-	-	-	-
All Other		-	-	*	*	-	-	-	-

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Oct 24, 2019

Quality Designation	Arizona		California		New Mexico		Texas	
	Week	Season	Week	Season	Week	Season	Week	Season
MIKE								
2.4 & Below	-	-	-	-	-	-	-	-
2.5 - 2.6	-	-	-	-	-	-	-	-
2.7 - 2.9	-	-	-	-	-	-	-	-
3.0 - 3.2	-	-	-	-	-	-	-	-
3.3 - 3.4	-	-	1.6	1.3	-	-	-	-
3.5 - 3.6	-	-	4.4	3.8	-	-	-	-
3.7 - 4.2	-	-	58.3	65.0	-	-	-	-
4.3 - 4.9	-	-	35.7	29.9	-	-	-	-
5.0 - 5.2	-	-	-	-	-	-	-	-
5.3 & Above	-	-	-	-	-	-	-	-
Average	-	-	4.13	4.10	-	-	-	-
ALL RANGE MIKE								
2.4 & Below	-	-	-	-	-	-	-	-
2.5	-	-	-	-	-	-	-	-
2.6	-	-	-	-	-	-	-	-
2.7	-	-	-	-	-	-	-	-
2.8	-	-	-	-	-	-	-	-
2.9	-	-	-	-	-	-	-	-
3.0	-	-	-	-	-	-	-	-
3.1	-	-	-	-	-	-	-	-
3.2	-	-	-	-	-	-	-	-
3.3	-	-	0.1	0.1	-	-	-	-
3.4	-	-	1.5	1.2	-	-	-	-
3.5	-	-	1.9	1.6	-	-	-	-
3.6	-	-	2.5	2.2	-	-	-	-
3.7	-	-	5.0	4.5	-	-	-	-
3.8	-	-	5.2	6.0	-	-	-	-
3.9	-	-	9.1	12.0	-	-	-	-
4.0	-	-	15.6	18.5	-	-	-	-
4.1	-	-	13.6	14.9	-	-	-	-
4.2	-	-	9.7	9.1	-	-	-	-
4.3	-	-	9.2	7.7	-	-	-	-
4.4	-	-	10.2	8.5	-	-	-	-
4.5	-	-	9.2	7.7	-	-	-	-
4.6	-	-	4.9	4.1	-	-	-	-
4.7	-	-	1.8	1.5	-	-	-	-
4.8	-	-	0.5	0.4	-	-	-	-
4.9	-	-	0.1	*	-	-	-	-
5.0	-	-	-	-	-	-	-	-
5.1	-	-	-	-	-	-	-	-
5.2	-	-	-	-	-	-	-	-
5.3 & Above	-	-	-	-	-	-	-	-
Average	-	-	4.13	4.10	-	-	-	-
STRENGTH 1/ 36 & Below	-	-	-	-	-	-	-	-
37	-	-	0.1	0.1	-	-	-	-
38	-	-	6.7	8.1	-	-	-	-
39	-	-	10.9	14.1	-	-	-	-
40	-	-	5.0	10.9	-	-	-	-
41	-	-	4.7	5.9	-	-	-	-
42	-	-	9.1	7.6	-	-	-	-
43	-	-	14.0	11.7	-	-	-	-
44	-	-	18.7	15.6	-	-	-	-
45	-	-	18.5	15.5	-	-	-	-
46	-	-	9.6	8.0	-	-	-	-
47	-	-	2.3	1.9	-	-	-	-
48 & Above	-	-	0.5	0.4	-	-	-	-
Average	-	-	43.30	42.76	-	-	-	-
UNIFORMITY								
83 & Below	-	-	*	*	-	-	-	-
84	-	-	7.9	9.0	-	-	-	-
85	-	-	22.3	32.6	-	-	-	-
86	-	-	50.8	42.5	-	-	-	-
87	-	-	17.5	14.6	-	-	-	-
88 & Above	-	-	1.5	1.3	-	-	-	-
Average	-	-	86.28	86.12	-	-	-	-
Samples Classed	-	-	13,263	15,858	-	-	-	-

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.