



Volume 25, No.25

State	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
AL	11	87.6	73.1	16,441	26	86.8	73.3	680,475
AR	2	76.8	48.8	10,393	28	78.5	55.9	1,436,907
AZ	7	88.2	69.9	16,962	9	88.7	71.1	157,301
CA	2	95.7	91.7	5,066	11	91.1	80.8	48,260
FL	3	70.5	47.7	1,097	4	67.8	43.6	92,246
GA	54	82.0	68.2	100,378	58	90.8	78.0	1,991,405
KS	3	25.3	23.3	7,863	3	41.5	28.9	117,004
LA	-	-	-	-	17	63.8	37.8	207,195
MO	5	97.9	84.1	11,684	19	92.4	74.7	777,871
MS	3	80.8	66.4	1,582	35	61.0	35.5	833,008
NC	11	76.4	63.5	8,406	32	62.4	41.1	742,218
NM*	-	-	-	-	3	80.4	65.6	15,070
OK	5	83.2	77.8	1,672	11	79.6	61.3	138,813
SC	8	84.1	76.6	12,474	12	85.5	71.1	301,645
TN	3	98.2	93.2	9,687	18	97.5	90.3	657,268
TX	34	53.1	37.1	23,515	159	72.4	44.4	2,699,629
VA	2	95.2	73.7	7,172	4	90.0	72.5	185,264
United States	154	79.9	65.9	234,899	449	79.3	59.3	11,081,579
AMERICAN PIMA								
AZ	2			1,571	3			10,345
CA	3			7,197	13			208,790
NM*	-			-	3			28,199
TX	2			1,676	3			18,538
United States	8			12,996	22			265,872
United States all cotton	161			247,895	462			11,347,451

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 11, 2024

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	14.8	11.3	3.9	6.8	63.7	72.6	82.3	55.4	-	1.1	0.4	1.6
	3	18.2	10.6	2.1	2.7	10.5	8.2	6.4	10.4	-	1.2	0.4	1.5
	4	2.2	0.9	0.1	0.1	0.2	0.3	*	0.9	-	0.1	*	0.1
	5	0.1	*	-	*	-	*	-	*	-	-	-	*
	6	-	-	-	-	-	-	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	35.3	22.8	6.1	9.6	74.3	81.1	88.7	66.7	-	2.4	0.9	3.2
31	1 - 2	8.3	7.7	19.1	13.8	8.7	5.9	6.0	10.6	0.1	6.7	2.7	7.5
	3	21.0	30.3	43.9	38.8	11.6	6.8	4.2	11.4	6.4	26.9	9.1	27.3
	4	6.0	12.2	8.4	12.2	3.4	1.9	0.1	7.0	3.2	10.1	3.1	9.7
	5	0.6	1.5	0.5	1.0	0.3	0.1	-	1.5	0.5	1.0	0.4	1.0
	6	*	0.1	-	*	-	*	-	0.1	-	*	*	*
	7	*	*	-	*	-	-	-	-	-	*	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	35.8	51.8	71.9	65.7	24.0	14.7	10.3	30.5	10.2	44.6	15.3	45.6
41	1 - 2	0.6	0.9	0.6	0.5	0.1	*	*	0.1	0.5	1.1	2.3	1.6
	3	5.3	7.1	12.5	7.9	0.4	0.1	0.1	0.2	10.1	13.5	23.1	18.9
	4	5.1	7.4	8.1	11.6	0.6	0.1	0.5	0.6	8.0	14.5	21.5	17.5
	5	0.8	2.3	0.6	3.7	0.2	*	0.1	0.3	3.9	3.9	6.1	4.8
	6	0.1	0.4	*	0.3	0.1	*	-	0.1	0.1	0.5	0.9	0.7
	7	-	*	-	*	*	*	-	-	-	0.1	0.1	0.1
	8	-	*	-	-	-	*	-	-	-	*	*	*
Total	----	11.8	18.1	21.8	24.0	1.4	0.3	0.7	1.2	22.7	33.5	54.0	43.6
51	1 - 2	0.4	0.1	-	*	-	-	-	-	0.7	0.2	1.0	0.1
	3	5.7	1.6	*	*	*	*	-	-	28.8	3.4	8.1	1.5
	4	5.3	1.8	*	0.1	*	*	-	-	25.1	3.6	9.2	1.8
	5	1.1	0.5	-	0.1	*	*	-	-	3.9	1.0	3.3	0.7
	6	0.2	0.1	*	*	-	-	-	-	-	0.1	0.6	0.2
	7	*	*	-	*	-	*	-	-	-	*	0.1	*
	8	-	*	-	*	-	*	-	-	-	-	*	*
Total	----	12.7	4.2	*	0.3	*	*	-	-	58.5	8.3	22.5	4.4
61	1 - 2	0.1	*	-	*	-	-	-	-	-	*	-	*
	3	0.2	*	-	-	-	-	-	-	0.1	0.1	*	*
	4	*	*	-	*	-	-	-	-	0.1	*	*	*
	5	*	*	-	*	-	-	-	-	-	*	*	*
	6	-	*	-	*	-	-	-	-	-	*	-	*
	7	-	*	-	*	-	-	-	-	-	*	-	*
	8	-	*	-	-	-	-	-	-	-	-	-	*
Total	----	0.2	0.1	-	*	-	-	-	-	0.2	0.1	0.1	*
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	*
	6	-	-	-	-	-	-	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	-	-	-	-	*
12 & 22	1 - 2	-	*	-	*	*	2.3	-	*	-	*	-	*
	3	-	*	-	*	*	0.8	0.1	0.1	-	*	*	*
	4	-	*	-	*	*	*	-	*	-	-	*	*
	5	-	*	-	*	-	-	-	-	-	-	-	*
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	*	0.1	3.1	0.1	0.2	-	*	*	*
32	1 - 2	-	0.1	-	*	*	0.1	-	*	-	0.2	*	*
	3	*	0.4	0.1	0.1	*	0.3	-	0.2	-	1.6	0.3	0.3
	4	0.1	0.2	*	*	*	0.2	-	0.4	-	0.7	0.2	0.2
	5	*	*	-	*	*	*	-	0.3	-	0.1	0.1	*
	6	-	*	-	*	-	*	-	*	-	*	-	*
	7	-	*	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.1	0.7	0.1	0.1	0.1	0.7	-	1.0	-	2.6	0.5	0.6
42	1 - 2	*	*	-	*	-	*	-	*	-	0.1	0.1	*
	3	0.4	0.4	*	0.1	*	*	*	*	0.3	2.5	1.1	0.6
	4	0.5	0.6	*	0.1	-	*	0.1	*	0.3	2.2	1.5	0.8
	5	0.1	0.3	-	0.1	-	*	*	0.1	0.1	0.5	0.6	0.3
	6	*	0.1	-	*	-	*	-	0.1	-	0.1	0.2	0.1
	7	-	*	-	*	-	-	-	-	-	*	*	*
	8	-	*	-	-	-	-	-	-	-	-	-	*
Total	----	1.0	1.3	*	0.3	*	*	0.2	0.2	0.6	5.5	3.5	1.8

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 11, 2024

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	*	*	-	*	-	-	-	-	0.2	*	*	*
	3	1.0	0.2	-	*	-	-	-	-	3.7	0.7	0.7	0.1
	4	1.0	0.3	-	*	-	-	-	-	2.2	1.0	1.2	0.2
	5	0.4	0.1	-	*	-	-	-	-	0.4	0.4	0.6	0.1
	6	*	*	-	*	-	-	-	-	-	0.1	0.1	*
	7	-	*	-	*	-	-	-	-	-	*	*	*
	8	-	*	-	*	-	*	-	-	-	-	*	*
Total	----	2.4	0.7	-	*	-	*	-	-	6.5	2.2	2.7	0.5
62	1 - 2	-	*	-	-	-	-	-	-	-	*	-	-
	3	*	*	-	-	-	-	-	-	-	*	*	*
	4	*	*	-	-	-	-	-	-	-	*	*	*
	5	-	*	-	-	-	-	-	-	-	*	*	*
	6	-	*	-	-	-	-	-	-	-	*	-	*
	7	*	*	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	*	*
Total	----	*	*	-	-	-	-	-	-	-	0.1	*	*
13 & 23	1 - 2	-	*	-	-	-	0.1	-	-	-	-	-	*
	3	-	*	-	-	-	*	-	-	-	-	*	*
	4	-	-	-	-	-	-	-	-	-	-	-	*
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	-	-	0.1	-	-	-	-	*	*
33	1 - 2	-	*	-	*	*	*	-	*	-	*	-	*
	3	-	*	-	*	*	*	*	*	-	*	*	*
	4	*	*	-	*	*	*	-	*	-	*	*	*
	5	-	*	-	*	-	-	-	-	-	-	-	*
	6	-	*	-	*	-	-	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	-	*	*	*	*	*	-	0.1	*	*
43	1 - 2	-	*	-	*	-	-	-	-	-	*	*	*
	3	*	*	-	*	*	*	-	-	-	0.1	0.1	*
	4	0.1	*	-	*	-	*	-	*	-	0.1	0.1	*
	5	*	*	-	*	-	*	-	*	-	*	0.1	*
	6	-	*	-	*	-	-	-	*	-	-	*	*
	7	-	*	-	-	-	-	-	-	-	-	*	*
	8	-	-	-	-	-	-	-	-	-	-	*	*
Total	----	0.2	0.1	-	*	*	*	-	0.1	-	0.2	0.3	0.1
53	1 - 2	-	-	-	-	-	-	-	-	-	*	*	*
	3	0.1	*	-	-	-	-	-	-	1.1	0.1	0.1	*
	4	0.1	*	-	*	-	-	-	-	0.1	0.1	0.1	*
	5	*	*	-	*	-	-	-	-	0.1	*	0.1	*
	6	*	*	-	-	-	-	-	-	-	*	*	*
	7	-	*	-	-	-	-	-	-	-	*	*	*
	8	-	-	-	-	-	-	-	-	-	*	-	*
Total	----	0.3	0.1	-	*	-	-	-	-	1.3	0.2	0.3	*
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	*	*	-	-	-	-	-	-	-	*	*	*
	4	*	*	-	-	-	-	-	-	-	*	*	*
	5	-	*	-	-	-	-	-	-	-	*	-	*
	6	-	*	-	-	-	-	-	-	-	*	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	-	-	-	-	-	-	-	*	*	*
24 - 54	1 - 8	-	*	-	*	-	-	-	-	-	*	*	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	-	-	-	-	-	-	-	-	-	*	*
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	*	-	-	-	-	-	-	-	-	*	*
31		-	0.1	-	*	-	-	-	-	-	*	*	*
32		*	0.4	-	*	*	*	-	-	0.1	0.3	0.4	0.2
33		1.1	1.7	-	0.1	0.6	0.2	-	*	2.0	2.5	1.3	1.3
34		2.0	5.7	*	0.5	1.9	1.0	0.3	0.7	10.9	9.8	5.6	6.3
35		8.0	13.9	5.2	5.9	5.8	6.5	7.9	5.3	14.1	22.4	14.7	16.6
36		33.0	23.6	29.0	20.6	16.1	18.0	24.7	13.1	12.9	25.2	22.7	28.0
37		43.3	36.4	38.1	50.1	35.0	34.1	47.7	38.0	23.5	25.8	36.2	33.9
38		12.3	13.8	14.7	18.6	26.9	23.5	19.4	19.6	29.3	9.5	14.8	10.7
39		0.3	3.6	12.2	3.8	10.5	12.5	0.1	15.8	7.0	3.8	3.8	2.6
40 & Longer		*	0.7	0.7	0.4	3.3	4.3	-	7.5	0.1	0.6	0.4	0.4
Average Staple		36.54	36.45	37.02	36.93	37.22	37.28	36.78	37.48	36.61	36.08	36.47	36.31
Average Length		1.14	1.14	1.15	1.15	1.16	1.16	1.15	1.17	1.14	1.12	1.14	1.13

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 11, 2024

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	1.1	7.5	-	3.2	5.8	7.4	34.2	5.9	2.6	3.9	-	57.6
	3	0.4	11.0	-	1.5	2.1	2.1	12.1	4.6	1.4	2.7	-	5.6
	4	*	2.7	-	*	-	*	0.1	0.2	*	0.1	-	*
	5	-	0.2	-	-	-	*	-	*	-	*	-	-
	6	-	*	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	1.5	21.3	-	4.8	7.9	9.5	46.3	10.7	4.0	6.7	-	63.2
31	1 - 2	0.2	0.6	-	7.6	23.0	22.8	13.5	9.5	5.8	10.4	-	10.2
	3	3.7	7.4	-	24.1	46.0	43.3	23.4	38.6	28.6	43.4	-	14.6
	4	3.8	9.9	-	6.8	4.0	7.0	3.1	12.2	13.3	14.2	-	3.6
	5	0.6	3.6	-	0.3	0.1	0.2	-	0.9	2.2	0.9	-	0.3
	6	*	0.4	-	*	-	*	-	*	0.1	*	-	-
	7	-	*	-	-	-	*	-	*	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	8.2	22.0	-	38.9	73.0	73.4	40.0	61.1	50.0	68.9	-	28.7
41	1 - 2	-	*	-	1.2	1.1	0.9	1.0	0.4	0.6	0.4	-	0.1
	3	2.0	0.8	-	16.6	10.9	9.1	5.4	8.2	11.6	8.4	-	1.0
	4	16.6	4.9	-	17.8	6.6	6.1	2.3	12.4	14.1	11.2	-	2.2
	5	23.4	7.9	-	4.4	0.3	0.9	0.1	4.5	5.6	2.8	-	1.0
	6	9.0	4.6	-	0.3	-	*	-	0.7	0.5	0.3	-	0.3
	7	0.9	0.9	-	*	-	*	-	*	*	*	-	-
	8	0.1	0.1	-	*	-	-	-	*	-	-	-	-
Total	----	52.0	19.2	-	40.4	19.0	17.0	8.8	26.1	32.6	23.1	-	4.4
51	1 - 2	-	-	-	*	-	*	-	*	*	*	-	-
	3	-	-	-	0.2	-	*	-	*	2.8	0.1	-	-
	4	0.2	*	-	0.6	*	*	-	*	4.8	0.1	-	-
	5	3.4	0.5	-	0.7	-	*	-	0.1	0.9	0.1	-	*
	6	5.7	1.4	-	0.1	-	*	-	*	0.3	*	-	*
	7	2.0	1.1	-	*	-	*	-	*	0.1	*	-	-
	8	0.5	0.4	-	-	-	-	-	*	-	-	-	-
Total	----	11.7	3.4	-	1.7	*	*	-	0.2	8.9	0.3	-	*
61	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	*	-	-	-	-
	4	-	-	-	*	-	-	-	-	-	-	-	-
	5	-	-	-	*	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	*	-	-	-	*	-	-	-	-
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	-	-	-	-	-
12 & 22	1 - 2	*	2.7	-	1.8	-	*	-	*	*	*	-	0.3
	3	0.1	5.7	-	0.7	-	*	-	*	0.1	*	-	0.1
	4	-	2.1	-	*	-	*	-	*	*	*	-	-
	5	-	0.1	-	-	-	-	-	*	-	*	-	-
	6	-	*	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.1	10.7	-	2.6	-	*	-	*	0.1	*	-	0.4
32	1 - 2	0.1	0.1	-	0.9	-	*	-	0.1	*	*	-	0.7
	3	0.6	1.5	-	2.6	0.1	*	-	0.6	0.3	0.3	-	1.6
	4	1.7	3.8	-	0.6	*	*	-	0.2	0.1	0.1	-	0.4
	5	0.6	1.7	-	*	-	*	-	*	*	*	-	*
	6	*	0.3	-	-	-	-	-	*	-	*	-	-
	7	-	*	-	*	-	-	-	*	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	3.0	7.4	-	4.1	0.1	*	-	0.9	0.4	0.4	-	2.7
42	1 - 2	-	*	-	0.4	-	*	-	*	-	*	-	-
	3	0.3	0.2	-	3.4	*	*	1.8	0.3	0.5	0.1	-	0.1
	4	4.7	2.5	-	2.3	*	*	2.3	0.4	0.7	0.2	-	0.1
	5	7.6	4.9	-	0.6	-	*	0.3	0.1	0.4	*	-	0.1
	6	2.8	3.6	-	0.1	-	*	-	*	*	*	-	*
	7	0.4	1.2	-	*	-	-	-	*	-	*	-	-
	8	0.1	*	-	-	-	-	-	*	-	-	-	-
Total	----	16.0	12.4	-	6.7	*	*	4.4	0.9	1.6	0.4	-	0.3

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 11, 2024

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	-	*	-	-	-	-	*	*	-	-
	3	-	-	-	0.2	-	*	-	*	0.7	*	-	-
	4	0.1	*	-	0.3	-	-	0.3	*	0.4	*	-	-
	5	0.5	0.1	-	0.2	-	*	0.1	*	0.1	*	-	-
	6	0.5	0.3	-	0.1	-	*	-	*	-	*	-	-
	7	0.4	0.5	-	*	-	-	-	*	-	*	-	-
	8	0.8	0.2	-	-	-	-	-	*	-	-	-	-
Total	----	2.3	1.2	-	0.7	-	*	0.3	*	1.2	*	-	-
62	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	-	-	-
	4	-	-	-	*	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	-	-	-	-	-	-	-	-
13 & 23	1 - 2	-	0.1	-	*	-	-	-	-	-	*	-	-
	3	0.4	0.2	-	*	-	-	-	-	-	*	-	-
	4	0.1	0.1	-	-	-	-	-	*	-	*	-	-
	5	-	*	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.5	0.4	-	0.1	-	-	-	*	-	*	-	-
33	1 - 2	*	*	-	*	-	*	-	*	-	*	-	-
	3	1.1	0.2	-	*	-	*	-	*	*	*	-	*
	4	0.7	0.4	-	*	-	*	-	*	0.1	*	-	0.1
	5	0.1	0.3	-	-	-	*	-	*	*	*	-	*
	6	*	*	-	-	-	-	-	-	-	-	-	-
	7	*	*	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	1.9	0.9	-	*	-	*	-	*	0.1	*	-	0.1
43	1 - 2	-	-	-	*	-	*	-	*	-	*	-	-
	3	*	*	-	*	-	*	0.1	*	0.1	*	-	*
	4	0.4	0.2	-	*	-	*	0.1	*	0.1	*	-	0.1
	5	0.7	0.4	-	*	-	*	-	*	*	*	-	0.1
	6	0.5	0.2	-	*	-	-	-	*	-	*	-	-
	7	0.3	0.1	-	-	-	-	-	*	-	*	-	-
	8	0.1	*	-	-	-	-	-	*	-	-	-	-
Total	----	1.9	0.9	-	0.1	-	*	0.1	*	0.3	*	-	0.2
53	1 - 2	-	-	-	-	-	*	-	-	-	-	-	-
	3	-	-	-	*	-	*	-	-	0.3	*	-	-
	4	-	*	-	*	-	-	-	*	0.2	*	-	-
	5	0.1	*	-	*	-	-	-	*	*	*	-	-
	6	0.1	*	-	*	-	-	-	*	-	*	-	-
	7	0.1	*	-	*	-	-	-	-	-	*	-	-
	8	0.1	*	-	-	-	-	-	-	-	-	-	-
Total	----	0.5	0.1	-	*	-	*	-	*	0.6	*	-	-
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	*	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	-	-	-	-	-	-	-	-
24 - 54	1 - 8	0.3	0.1	-	*	-	-	-	*	0.2	*	-	-
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	*	-	-	-	*	-	-	-	*	-	-
31		0.3	0.3	-	*	-	-	-	*	-	*	-	-
32		1.2	1.6	-	0.1	-	*	-	0.1	*	0.2	-	-
33		8.6	5.3	-	1.2	-	*	-	0.6	0.8	2.1	-	*
34		10.4	12.2	-	5.4	-	0.1	0.3	4.1	4.7	10.1	-	3.8
35		14.5	19.6	-	14.5	3.2	2.5	30.2	12.5	13.0	24.1	-	7.7
36		22.5	22.8	-	26.9	9.4	15.8	39.5	25.0	19.5	31.5	-	19.1
37		21.8	23.4	-	32.5	44.2	47.2	27.9	37.6	38.9	26.3	-	32.1
38		11.9	9.2	-	13.2	25.9	26.9	2.1	14.7	18.8	4.8	-	14.6
39		7.8	5.2	-	5.3	13.0	6.6	0.1	4.7	4.3	0.8	-	15.0
40 & Longer		0.9	0.4	-	0.9	4.3	1.0	-	0.8	0.1	0.1	-	7.7
Average Staple		36.05	35.91	-	36.49	37.49	37.22	36.02	36.62	36.65	35.87	-	37.25
Average Length		1.12	1.12	-	1.14	1.17	1.16	1.12	1.14	1.14	1.12	-	1.16

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE											
For The Week Ending Jan 11, 2024											
Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	0.5	25.1	1.2	3.1	28.3	16.9	26.2	31.6	6.9	11.1
	3	0.4	4.5	1.7	2.9	17.2	6.7	5.7	12.7	4.7	8.3
	4	-	0.1	0.3	0.2	0.2	0.1	0.2	0.9	0.1	0.4
	5	-	*	*	*	-	*	*	*	-	*
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	0.9	29.8	3.3	6.2	45.7	23.7	32.1	45.3	11.6	19.7
31	1 - 2	9.8	11.8	1.7	4.8	16.6	25.0	3.7	6.8	12.2	18.0
	3	35.7	22.4	18.7	30.8	23.6	35.4	12.9	14.3	27.6	47.6
	4	4.7	4.0	14.1	15.9	4.2	6.4	4.3	4.0	3.2	7.5
	5	0.2	0.3	1.6	1.7	0.3	0.3	0.4	0.4	0.1	0.5
	6	-	*	*	0.1	*	*	*	*	*	*
	7	-	-	-	*	*	*	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	50.5	38.5	36.2	53.3	44.8	67.1	21.3	25.5	43.2	73.6
41	1 - 2	0.8	0.7	0.2	0.4	0.7	0.6	0.1	0.2	10.5	0.7
	3	17.0	5.6	12.4	10.9	4.2	4.0	1.8	1.6	29.9	3.7
	4	16.5	3.3	23.7	19.8	3.0	3.5	2.9	1.8	3.8	1.6
	5	1.8	1.1	9.1	6.5	0.5	0.8	2.2	0.8	0.1	0.2
	6	0.3	0.3	1.2	0.7	*	0.1	1.0	0.3	*	*
	7	-	*	0.1	*	*	*	0.1	0.1	-	-
	8	-	*	-	-	-	-	*	*	-	-
Total	----	36.4	11.0	46.8	38.4	8.4	8.9	8.2	4.8	44.3	6.2
51	1 - 2	-	*	0.1	*	-	*	-	*	0.1	*
	3	-	*	2.6	0.2	*	*	*	0.1	0.1	*
	4	0.1	*	3.7	0.4	*	*	*	0.1	*	*
	5	0.8	0.1	1.9	0.3	*	*	0.3	0.1	-	*
	6	0.1	0.1	0.4	0.1	-	*	0.7	*	-	*
	7	-	*	0.1	*	-	*	0.4	*	-	-
	8	-	*	-	-	-	-	0.2	*	-	-
Total	----	1.0	0.3	8.7	1.0	0.1	*	1.6	0.4	0.3	*
61	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	*	*	-	*	-	-
	4	-	-	*	*	-	-	-	*	-	*
	5	-	-	-	*	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	*	*	*	*	-	*	-	*
71	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	-	-	-	-	*	-	-
	5	-	-	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	*	-	-
12 & 22	1 - 2	-	4.3	-	*	-	*	3.6	8.9	-	*
	3	-	2.3	*	*	0.1	*	2.1	4.8	*	*
	4	-	0.2	*	*	0.1	*	0.2	0.6	*	*
	5	-	*	*	*	-	-	*	*	-	*
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	6.8	*	*	0.2	*	5.8	14.3	*	0.1
32	1 - 2	0.1	1.4	-	*	*	*	2.5	0.9	-	*
	3	2.0	3.9	0.1	0.1	0.1	*	7.4	2.8	0.2	0.1
	4	0.6	1.9	0.3	0.1	0.1	*	3.3	1.3	0.1	0.1
	5	0.1	0.3	0.1	0.1	*	*	0.3	0.2	-	*
	6	-	*	-	*	-	*	*	*	-	*
	7	-	*	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	2.8	7.5	0.5	0.3	0.2	0.1	13.5	5.3	0.3	0.2
42	1 - 2	-	*	-	*	-	*	0.1	0.1	-	*
	3	3.5	0.8	0.1	*	0.1	*	0.5	0.5	*	*
	4	3.1	1.2	1.2	0.2	*	*	1.1	0.6	0.3	0.1
	5	0.4	0.7	1.5	0.2	-	*	1.1	0.4	*	*
	6	0.5	0.2	0.1	0.1	-	*	0.6	0.2	-	-
	7	0.1	0.1	*	*	-	*	0.1	0.1	-	-
	8	-	*	-	-	-	-	0.1	*	-	-
Total	----	7.6	3.1	3.0	0.6	0.1	*	3.6	1.8	0.3	0.2

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE											
For The Week Ending Jan 11, 2024											
Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	*	-	-	-	-	*	*	-	-
	3	-	*	*	*	*	*	0.1	0.1	-	*
	4	0.1	*	0.4	*	*	*	0.1	0.1	-	-
	5	0.1	0.1	0.5	*	-	*	0.1	*	-	-
	6	0.1	0.1	0.2	*	-	*	0.1	*	-	-
	7	-	0.1	*	*	-	-	0.1	*	-	-
	8	-	*	-	-	-	-	0.1	*	-	-
	Total	----	0.2	0.3	1.1	0.1	*	*	0.6	0.2	-
62	1 - 2	-	-	-	-	-	-	*	*	-	-
	3	-	-	-	-	0.1	*	0.1	*	-	-
	4	-	-	-	*	*	*	0.1	*	-	-
	5	-	-	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
	Total	----	-	-	-	*	0.1	*	0.2	*	-
13 & 23	1 - 2	-	0.5	-	-	-	-	0.9	0.5	-	*
	3	-	0.5	-	-	-	-	0.3	0.5	-	*
	4	-	0.1	-	*	-	-	0.1	0.1	-	*
	5	-	*	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	-	1.1	-	*	-	-	1.3	1.1	-
33	1 - 2	0.1	0.1	-	-	-	*	1.5	0.1	-	*
	3	0.1	0.6	-	*	*	*	3.2	0.4	*	*
	4	-	0.4	-	*	0.2	*	1.3	0.3	*	*
	5	-	0.1	-	*	-	*	0.2	0.1	-	*
	6	-	*	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
	Total	----	0.2	1.2	-	*	0.2	*	6.1	0.9	0.1
43	1 - 2	-	*	-	*	-	-	*	*	-	-
	3	-	*	0.1	*	*	*	0.4	*	-	*
	4	0.4	0.1	0.2	*	0.1	*	0.9	0.1	-	*
	5	-	0.1	*	*	*	*	0.3	0.1	-	*
	6	-	*	-	*	-	-	0.1	0.1	-	*
	7	-	*	-	*	-	-	*	*	-	-
	8	-	*	-	-	-	-	-	*	-	-
	Total	----	0.4	0.3	0.4	0.1	0.1	*	1.7	0.3	-
53	1 - 2	-	-	-	-	-	-	*	*	-	-
	3	-	-	-	-	-	-	*	*	-	-
	4	-	-	*	*	*	*	*	*	-	-
	5	0.1	*	0.1	*	-	-	*	*	-	-
	6	-	*	*	*	-	-	0.1	*	-	-
	7	-	*	-	-	-	-	0.1	*	-	-
	8	-	*	-	-	-	-	*	*	-	-
	Total	----	0.1	*	0.1	*	*	*	0.2	*	-
63	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	-	*	*	-	-
	4	-	-	-	-	0.1	*	*	*	-	-
	5	-	-	-	-	*	*	*	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
	Total	----	-	-	-	-	0.1	*	*	*	-
24 - 54	1 - 8	0.1	0.1	*	*	-	-	3.3	0.1	-	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	*	-	-	-	-	0.4	*	-	-
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		-	*	-	-	-	-	*	*	-	-
30		-	*	-	-	-	-	-	0.1	-	-
31		-	0.5	-	*	-	-	0.4	0.4	-	*
32		0.1	2.4	-	*	-	*	1.8	1.9	*	*
33		4.4	4.6	0.2	0.5	-	*	6.2	6.0	0.3	1.0
34		14.7	8.3	2.6	3.7	-	0.2	14.4	14.7	1.4	5.9
35		13.3	12.5	16.1	13.6	0.9	2.5	21.0	22.7	9.5	19.8
36		5.6	18.9	25.4	26.3	8.3	15.8	19.8	22.8	44.0	42.4
37		18.0	29.5	36.1	38.1	63.4	57.6	25.2	19.8	40.7	26.9
38		15.2	13.8	15.3	13.0	23.3	20.1	7.8	7.4	4.1	3.4
39		23.9	6.1	4.0	4.0	4.0	3.4	2.9	3.2	0.1	0.5
40 & Longer		4.8	3.4	0.3	0.8	0.1	0.2	0.5	0.9	*	0.1
Average Staple		36.84	36.34	36.58	36.57	37.21	37.06	35.74	35.68	36.36	36.00
Average Length		1.15	1.13	1.14	1.14	1.16	1.16	1.11	1.11	1.13	1.12

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 11, 2024

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	0.8	0.2	0.3	*	0.2	0.2	0.1	0.1	4.2	0.5	4.5	1.2
Bark - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	*	0.1	0.1	0.1	-	*	1.0	0.4	-	0.1	0.1	0.1
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	*	-	*	-	-	-	*	-	*	*	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	0.1	0.1	-	*	0.3	0.8	-	*	0.1	*	0.3	0.1
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	*	-	-	-	-	-	-	-	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	-	*	-	-	-	*	-	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	0.1	*	*	-	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	*	-	*	-	-	-	-	-	*	-	*
23	-	*	-	*	-	*	-	-	0.4	*	*	*
24	-	*	-	*	*	0.1	-	-	0.2	*	*	*
25	*	0.1	*	*	*	0.3	-	0.2	0.4	0.1	0.1	0.1
26	0.1	0.3	0.1	*	0.2	1.3	0.6	0.6	1.3	0.4	0.7	0.4
27	1.5	1.3	0.2	0.5	0.2	2.6	2.0	0.9	3.9	1.2	3.5	2.1
28	2.8	5.0	5.2	4.0	1.8	5.4	6.0	3.2	8.9	3.5	11.7	7.9
29	16.5	16.1	44.2	19.1	2.9	9.4	25.3	11.1	13.2	7.5	20.9	18.4
30	29.5	29.1	39.8	35.0	6.7	13.0	19.9	16.0	17.3	14.2	23.4	26.4
31	27.4	24.9	9.0	26.1	16.7	16.4	29.2	12.5	20.5	19.2	18.9	23.0
32	15.5	14.7	1.3	11.0	24.4	19.3	14.8	6.7	21.3	18.8	12.9	13.2
33	5.1	6.2	0.1	3.2	22.5	14.7	2.3	7.7	9.4	14.6	5.5	5.6
34	1.5	1.8	-	0.8	10.4	8.1	*	10.8	2.3	9.7	1.8	2.0
35	0.2	0.5	-	0.2	5.5	5.0	-	8.9	0.8	6.3	0.4	0.6
36	0.1	0.1	-	0.1	4.1	2.5	-	6.6	-	3.4	0.1	0.2
37	*	*	-	*	2.7	1.1	-	7.8	0.1	0.9	*	*
38	-	*	-	-	1.3	0.5	-	5.5	-	0.1	*	*
39	-	-	-	-	0.5	0.2	-	1.2	-	*	-	*
40 & Above	-	-	-	-	0.2	0.1	-	0.3	-	*	-	*
Average	30.99	30.97	30.02	30.79	32.99	31.95	30.66	33.11	30.96	32.23	30.58	30.82
Mike												
2.4 & Below	-	*	-	-	-	-	-	-	-	-	*	*
2.5	-	*	-	*	-	*	-	-	-	-	*	*
2.6	-	*	-	*	*	*	-	*	-	-	*	*
2.7	-	*	-	*	*	*	-	*	-	-	*	*
2.8	*	*	-	*	0.1	0.1	-	*	-	-	0.1	*
2.9	*	*	-	*	*	0.1	-	*	-	-	0.1	*
3.0	0.1	*	-	*	0.1	0.2	*	*	-	*	0.1	*
3.1	0.2	0.1	-	*	0.2	0.2	*	0.2	-	*	0.2	*
3.2	0.3	0.3	-	*	0.1	0.4	*	0.1	-	*	0.3	0.1
3.3	0.3	0.3	*	*	0.5	0.6	0.1	0.3	-	*	0.4	0.1
3.4	0.7	0.5	*	*	1.2	0.7	*	0.3	-	0.1	0.5	0.2
3.5	1.7	0.7	*	0.1	1.0	0.9	0.6	0.3	0.3	0.1	0.8	0.4
3.6	1.9	1.1	0.1	0.1	1.6	1.3	1.1	0.7	2.0	0.2	1.3	0.6
3.7	3.7	1.9	-	0.1	2.3	2.1	4.0	2.6	5.7	0.3	2.2	1.1
3.8	4.2	2.8	*	0.2	4.1	3.3	14.6	6.6	7.1	0.5	3.3	1.9
3.9	5.6	4.0	0.1	0.3	6.2	4.1	24.8	10.6	6.7	0.8	4.4	3.1
4.0	5.0	5.8	0.4	0.7	5.6	5.2	24.9	11.8	2.7	1.4	5.1	4.8
4.1	6.7	7.3	3.1	1.4	6.3	6.8	16.5	9.0	2.4	2.4	7.2	6.7
4.2	9.2	8.3	4.6	2.8	6.1	7.8	6.4	8.4	2.0	3.7	8.9	8.9
4.3	7.5	9.6	4.9	4.9	7.9	8.6	1.2	8.5	3.6	4.7	10.4	10.8
4.4	7.8	10.0	9.4	8.3	6.7	9.9	0.3	7.3	6.0	6.4	10.2	12.1
4.5	8.4	9.8	6.0	11.1	7.9	10.5	0.3	6.8	4.8	7.8	10.0	12.2
4.6	9.4	8.9	8.6	12.9	9.8	10.1	0.4	6.2	8.2	10.1	9.5	11.5
4.7	9.5	7.9	11.8	13.5	7.3	8.0	0.2	5.5	12.3	12.5	9.0	9.5
4.8	6.0	6.7	12.0	12.4	9.4	6.6	0.4	4.1	9.2	13.2	7.0	7.2
4.9	5.7	5.2	16.1	10.3	6.5	5.0	1.3	4.3	8.8	11.9	4.4	4.7
5.0	3.6	3.6	13.4	8.0	3.6	3.1	2.7	4.4	10.5	10.5	2.4	2.4
5.1	2.1	2.3	5.9	5.9	2.5	1.6	*	1.1	6.4	6.6	1.3	1.1
5.2	0.4	1.3	2.2	3.5	0.6	1.2	-	0.6	0.8	3.2	0.5	0.3
5.3	0.2	0.7	0.8	1.8	0.5	0.8	-	0.2	0.4	2.0	0.1	0.1
5.4	*	0.3	0.3	0.9	1.0	0.6	-	0.1	-	1.1	0.1	*
5.5 & Above	*	0.2	0.2	0.6	0.7	0.3	-	*	-	0.7	0.1	*
Average	4.36	4.41	4.71	4.71	4.41	4.40	4.01	4.29	4.50	4.71	4.37	4.43

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 11, 2024

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	47.6	20.6	-	0.1	*	*	-	*	4.6	1.1	-	9.0
Bark - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	-	1.1	-	*	*	0.1	-	*	1.7	0.3	-	0.2
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	-	-	*	-	*	-	-	-	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	*	-	*	-	*	-	*	-	*	-	0.6
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	*	-	*	-	*	-	*	-	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	-	-	-	*	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	-	*	-	*	-	*	*	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	*	*	-	-	-	-	-	*	-	-	-	-
23	0.1	0.1	-	-	-	*	-	*	-	-	-	-
24	0.3	0.1	-	*	-	*	-	*	-	*	-	-
25	1.4	0.6	-	*	*	*	0.1	*	*	*	-	*
26	2.6	1.2	-	0.5	*	0.1	0.2	0.2	*	0.1	-	*
27	2.7	2.5	-	2.1	0.7	0.6	6.1	1.0	1.9	0.9	-	0.5
28	2.3	3.9	-	4.6	10.9	5.8	39.7	4.1	5.5	4.8	-	3.3
29	7.9	7.9	-	10.3	56.3	27.3	39.3	13.1	17.7	15.4	-	15.5
30	17.0	13.2	-	22.4	27.9	40.5	12.9	25.6	26.2	26.3	-	26.4
31	16.3	19.6	-	29.6	3.2	19.3	1.6	28.9	23.8	26.5	-	21.0
32	15.8	20.0	-	19.6	0.8	5.1	0.2	16.8	15.4	16.2	-	18.6
33	15.1	15.1	-	7.8	0.3	1.1	-	6.9	7.5	7.0	-	11.4
34	12.8	10.2	-	1.9	*	0.3	-	2.4	1.8	2.2	-	2.2
35	5.1	4.6	-	0.8	*	0.1	-	0.7	0.2	0.5	-	0.3
36	0.3	0.7	-	0.3	-	*	-	0.2	*	0.1	-	0.2
37	0.1	0.1	-	*	-	*	-	*	-	*	-	0.1
38	-	*	-	*	-	-	-	-	-	-	-	0.2
39	-	*	-	-	-	-	-	-	-	-	-	0.1
40 & Above	-	-	-	-	-	-	-	-	-	-	-	*
Average	31.76	31.87	-	31.22	29.69	30.38	29.10	31.17	30.98	31.09	-	31.27
Mike												
2.4 & Below	-	0.1	-	-	-	-	-	-	-	-	-	-
2.5	-	0.5	-	-	-	-	-	-	-	*	-	-
2.6	-	0.5	-	-	-	-	-	*	-	*	-	-
2.7	0.3	1.1	-	-	-	*	-	*	-	*	-	*
2.8	1.1	1.4	-	-	-	*	-	*	-	*	-	*
2.9	0.5	1.9	-	-	-	*	-	*	-	*	-	*
3.0	1.1	3.0	-	*	-	*	-	*	-	*	-	-
3.1	1.4	3.6	-	*	*	*	-	*	-	*	-	0.1
3.2	1.9	4.4	-	*	-	*	-	*	*	*	-	0.3
3.3	2.3	4.6	-	*	-	*	0.1	*	0.1	*	-	0.2
3.4	3.9	6.2	-	*	*	*	0.1	*	0.2	0.1	-	1.2
3.5	4.1	7.5	-	*	0.6	0.1	-	0.1	0.3	0.1	-	1.6
3.6	10.0	7.5	-	*	0.8	0.1	0.8	0.1	1.3	0.2	-	2.0
3.7	8.3	8.2	-	0.1	0.2	0.2	2.3	0.2	2.8	0.3	-	1.5
3.8	11.8	8.3	-	0.2	0.9	0.5	3.4	0.3	3.4	0.6	-	2.0
3.9	10.8	8.6	-	0.5	0.8	1.0	7.8	0.5	4.0	1.0	-	2.5
4.0	7.0	7.7	-	1.0	1.1	1.9	5.9	0.7	4.5	1.5	-	4.9
4.1	4.2	6.1	-	1.9	3.4	3.2	7.0	1.1	6.5	2.2	-	5.9
4.2	3.0	4.9	-	3.3	5.9	5.1	5.2	1.9	7.5	3.0	-	5.2
4.3	7.7	4.8	-	4.8	9.1	8.0	5.2	2.9	9.6	4.0	-	9.7
4.4	7.7	3.5	-	6.2	16.4	11.5	4.7	4.2	8.6	5.2	-	11.7
4.5	5.7	2.7	-	8.0	16.7	14.0	12.9	6.2	9.4	6.9	-	7.7
4.6	2.5	1.2	-	10.8	17.0	15.3	12.3	8.5	8.2	8.0	-	10.9
4.7	1.9	0.9	-	12.0	12.7	13.9	4.7	10.2	7.3	9.5	-	11.1
4.8	1.1	0.4	-	12.7	8.4	10.6	3.0	12.2	8.2	10.4	-	7.2
4.9	1.6	0.2	-	9.9	3.9	6.9	10.3	13.6	4.8	11.0	-	4.8
5.0	*	*	-	9.0	1.5	4.0	8.9	12.2	4.5	11.0	-	4.6
5.1	-	*	-	6.7	0.4	1.9	4.0	9.5	3.3	9.5	-	2.8
5.2	-	-	-	5.2	0.1	0.9	1.1	6.9	3.2	7.2	-	1.5
5.3	-	-	-	3.4	*	0.3	-	4.4	1.2	4.4	-	0.6
5.4	-	-	-	2.4	-	0.1	-	2.5	0.8	2.2	-	0.1
5.5 & Above	-	-	-	2.0	-	0.1	0.1	1.9	0.1	1.6	-	-
Average	3.92	3.72	-	4.76	4.50	4.57	4.46	4.83	4.46	4.78	-	4.44

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE										
For The Week Ending Jan 11, 2024										
Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter										
Bark - Level 1	9.3	6.0	6.8	3.4	*	*	32.0	8.1	0.8	0.3
Bark - Level 2	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	-	0.3	1.0	0.5	-	*	0.4	0.2	0.2	0.1
Grass - Level 2	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	-	-	*	-	-	-	*	-	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	*	-	*	-	-	*	0.3	-	*
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	-	-	-	*	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	*	-	-	*	*	-	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	-	*	0.1	*	*	*	*	0.1	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/										
22 & Below	-	0.1	-	-	-	-	*	0.2	-	-
23	-	0.3	-	-	-	*	0.1	0.3	-	-
24	0.2	0.6	-	*	-	*	0.4	0.6	-	*
25	1.4	1.3	0.1	*	-	*	1.2	1.4	*	*
26	1.6	2.0	0.6	0.1	*	0.1	3.5	3.2	0.2	0.2
27	4.8	3.5	3.5	0.7	1.0	1.1	7.2	6.1	7.2	2.2
28	4.1	6.5	11.6	3.8	12.4	8.2	13.1	10.2	53.1	15.1
29	10.2	9.5	27.8	16.0	32.5	28.9	13.4	14.4	32.0	33.5
30	7.4	12.9	32.3	32.4	33.5	39.5	13.3	16.5	5.1	27.9
31	11.4	12.8	15.0	26.9	17.9	18.2	20.2	15.6	2.0	15.4
32	27.2	11.8	5.9	13.3	2.4	3.5	14.5	12.8	0.3	4.4
33	23.8	15.3	2.2	5.5	0.3	0.5	6.5	9.3	0.1	1.0
34	5.3	15.3	0.8	1.0	*	0.1	3.5	5.4	*	0.3
35	2.3	6.8	0.1	0.2	-	*	1.8	2.7	-	0.1
36	0.2	1.2	*	*	-	*	1.1	1.0	-	*
37	0.1	0.2	-	*	-	*	0.3	0.3	-	-
38	-	*	-	-	-	-	*	*	-	-
39	-	*	-	-	-	-	*	*	-	-
40 & Above	-	-	-	-	-	-	-	*	-	-
Average	31.72	31.76	30.19	30.94	30.07	30.23	30.60	30.77	28.85	30.03
Mike										
2.4 & Below	-	*	-	-	-	-	0.1	*	-	-
2.5	-	*	-	-	-	-	0.2	*	-	-
2.6	-	*	-	-	-	*	0.3	0.1	-	*
2.7	-	*	-	*	-	*	0.2	0.1	-	*
2.8	-	*	-	*	-	*	0.1	0.1	-	*
2.9	-	0.1	-	*	-	*	*	0.2	-	*
3.0	-	0.2	*	*	-	*	0.2	0.2	-	*
3.1	0.4	0.3	*	*	*	0.1	0.3	0.3	*	*
3.2	0.1	0.4	0.1	0.1	*	0.1	0.3	0.5	*	*
3.3	0.1	0.7	0.3	0.2	0.2	0.2	0.3	0.7	0.1	0.1
3.4	0.1	1.1	0.7	0.3	0.1	0.3	0.3	0.9	*	0.2
3.5	2.0	1.5	1.0	0.4	1.0	0.5	0.6	1.2	0.1	0.4
3.6	4.5	1.9	1.5	0.6	0.9	1.0	1.2	1.5	0.4	0.5
3.7	3.0	2.7	2.5	1.1	2.5	1.6	1.9	2.0	0.1	0.9
3.8	2.7	3.5	2.7	1.7	3.2	2.4	2.5	2.6	0.2	1.5
3.9	16.1	5.7	5.7	2.6	10.6	3.7	3.7	3.3	0.4	2.2
4.0	15.8	7.6	7.5	3.9	11.1	5.7	4.2	4.1	0.7	3.2
4.1	11.3	8.7	8.7	5.7	9.8	7.9	6.6	5.2	1.1	4.9
4.2	10.9	9.7	9.2	7.9	10.8	10.8	7.7	6.6	4.7	6.8
4.3	14.4	10.7	11.0	10.0	9.3	14.1	10.6	7.9	5.9	8.6
4.4	8.0	9.6	11.4	10.7	13.0	15.1	12.3	8.9	9.6	10.2
4.5	3.6	10.0	13.5	10.7	11.3	12.8	12.6	9.6	16.7	11.2
4.6	2.1	8.1	10.3	11.2	5.8	10.0	12.9	9.7	18.2	12.4
4.7	2.0	5.5	7.2	10.0	6.7	6.7	8.5	9.2	17.6	11.5
4.8	1.7	4.7	3.0	8.2	2.5	3.9	4.9	8.0	14.8	9.8
4.9	0.2	3.3	2.1	6.0	0.6	1.6	3.1	6.2	6.1	6.6
5.0	1.1	2.3	1.0	4.1	0.4	1.0	2.5	4.3	2.0	4.5
5.1	-	1.1	0.3	2.5	0.2	0.4	1.7	2.8	0.5	2.3
5.2	-	0.4	0.2	1.3	*	0.1	0.4	1.7	0.5	1.2
5.3	-	0.1	-	0.6	-	*	0.1	1.0	*	0.6
5.4	-	*	*	0.2	-	*	*	0.6	0.1	0.2
5.5 & Above	-	*	-	0.1	-	*	*	0.5	*	0.2
Average	4.12	4.29	4.31	4.48	4.25	4.34	4.38	4.44	4.59	4.52

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE												
For The Week Ending Jan 11, 2024												
Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	*	-	-	-	-	-	-	-	-	*	*
2.5 - 2.6	-	*	-	*	*	*	-	*	-	-	*	*
2.7 - 2.9	*	0.1	-	*	0.1	0.1	-	*	-	-	0.2	*
3.0 - 3.2	0.5	0.5	-	*	0.3	0.8	0.1	0.2	-	*	0.6	0.1
3.3 - 3.4	0.9	0.8	*	*	1.7	1.3	0.1	0.6	-	0.1	0.9	0.3
3.5 - 3.6	3.5	1.8	0.1	0.1	2.7	2.1	1.7	1.1	2.3	0.3	2.1	1.0
3.7 - 4.2	34.5	30.2	8.3	5.7	30.7	29.3	91.2	49.0	26.6	9.0	31.2	26.5
4.3 - 4.9	54.1	58.1	68.7	73.3	55.5	58.7	4.1	42.7	53.1	66.4	60.5	68.0
5.0 - 5.2	6.1	7.2	21.5	17.4	6.7	6.0	2.8	6.1	17.7	20.3	4.2	3.9
5.3 & Above	0.2	1.3	1.3	3.4	2.3	1.7	-	0.3	0.4	3.8	0.3	0.2
Average	4.36	4.41	4.71	4.71	4.41	4.40	4.01	4.29	4.50	4.71	4.37	4.43
Leaf												
1 - 2	24.2	20.2	23.6	21.1	72.5	81.0	88.3	66.2	1.5	9.4	6.6	11.0
3	52.0	50.8	58.6	49.6	22.7	16.2	10.8	22.4	50.5	50.2	43.2	50.4
4	20.5	23.4	16.6	24.1	4.2	2.5	0.7	8.9	38.9	32.4	36.9	30.4
5	3.0	4.8	1.1	4.8	0.5	0.2	0.1	2.3	8.9	7.0	11.2	7.0
6	0.3	0.7	*	0.4	0.1	*	-	0.3	0.1	0.8	1.8	1.0
7	*	0.1	-	*	*	*	-	-	-	0.1	0.3	0.1
8	-	*	-	*	-	*	-	-	-	*	*	*
Average	3.03	3.14	2.94	3.13	2.13	1.90	1.76	2.26	3.56	3.40	3.59	3.37
HVI Trash 1/												
00	-	-	-	*	*	0.1	*	*	-	-	-	*
01	3.1	4.0	3.4	3.7	32.0	47.1	50.4	33.3	-	0.9	0.6	1.3
02	28.1	21.7	23.7	21.3	42.4	36.1	36.5	34.6	2.0	12.1	8.5	14.0
03	29.7	28.3	32.2	26.5	16.1	10.9	9.6	14.7	20.5	25.3	21.0	26.4
04	19.4	21.5	22.1	20.6	5.7	3.8	2.6	7.0	31.3	25.3	24.0	24.2
05	11.0	12.6	11.0	13.2	2.5	1.4	0.7	4.6	23.2	17.5	19.1	16.1
06	4.9	6.4	4.8	7.5	0.9	0.5	0.1	2.8	12.9	10.0	12.1	9.0
07	2.2	3.0	2.0	3.8	0.3	0.1	*	1.5	7.1	5.0	7.2	4.6
08	0.9	1.4	0.6	1.8	0.1	0.1	-	0.7	1.7	2.2	3.7	2.3
09	0.3	0.7	0.1	0.8	*	*	-	0.3	0.8	1.0	1.9	1.1
10	0.2	0.3	*	0.4	*	*	-	0.2	0.4	0.4	0.9	0.5
11	0.1	0.1	*	0.2	*	*	-	0.1	-	0.2	0.5	0.2
12	*	0.1	-	0.1	*	*	-	*	-	0.1	0.2	0.1
13	-	*	-	*	-	*	-	*	-	*	0.1	0.1
14	*	*	*	*	*	*	-	*	-	*	*	*
15	-	*	-	*	-	*	-	-	-	*	*	*
16	-	*	-	*	-	*	-	-	-	*	*	*
17	*	*	-	*	-	*	-	-	-	-	*	*
18 & Above	-	*	-	*	-	*	-	-	-	*	*	*
Average	0.34	0.36	0.34	0.38	0.21	0.18	0.17	0.24	0.46	0.42	0.46	0.41
UNIFORMITY 2/												
74 & Below	-	*	-	-	-	-	-	-	-	*	-	*
75	-	*	-	*	-	*	-	-	-	-	-	*
76	-	*	*	*	*	*	-	-	-	*	*	*
77	*	0.1	*	*	0.1	0.2	*	*	-	0.1	0.1	0.2
78	0.1	0.7	0.2	0.1	1.2	2.1	0.3	0.4	0.3	0.7	0.8	1.2
79	1.4	4.6	2.2	1.1	6.1	9.2	8.4	4.1	6.4	3.9	4.6	7.3
80	8.6	17.2	16.8	8.5	18.1	23.2	62.3	26.8	15.3	16.1	20.0	24.5
81	32.4	33.4	38.3	20.9	35.1	32.3	27.9	25.2	33.5	33.7	38.2	36.8
82	41.8	32.1	31.5	33.7	31.0	24.4	0.6	16.5	31.4	32.4	27.9	22.6
83	15.1	10.6	9.6	28.3	7.6	7.8	0.5	14.5	12.3	11.8	7.3	6.3
84	0.6	1.1	1.2	6.4	0.9	0.8	-	11.3	0.7	1.3	1.1	0.9
85 & Above	*	0.1	0.2	0.9	*	*	-	1.2	-	*	0.1	0.1
Average	82.06	81.73	81.78	82.47	81.61	81.39	80.67	81.93	81.75	81.78	81.59	81.40
Tenderable 3/	87.6	86.8	76.8	78.5	88.2	88.7	95.7	91.1	70.5	67.8	82.0	90.8
SAMPLES CLASSED	16,441	680,475	10,393	1,436,907	16,962	157,301	5,066	48,260	1,097	92,246	100,378	1,991,405

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 11, 2024

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	0.1	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	-	1.0	-	-	-	-	-	*	-	*	-	-
2.7 - 2.9	1.9	4.4	-	-	-	*	-	*	-	*	-	*
3.0 - 3.2	4.4	11.0	-	*	*	*	-	0.1	*	*	-	0.3
3.3 - 3.4	6.3	10.8	-	*	*	0.1	0.2	0.1	0.3	0.1	-	1.5
3.5 - 3.6	14.1	15.1	-	*	1.4	0.2	0.8	0.2	1.6	0.3	-	3.6
3.7 - 4.2	45.2	43.7	-	6.9	12.3	12.0	31.6	4.6	28.8	8.6	-	21.9
4.3 - 4.9	28.2	13.9	-	64.3	84.3	80.4	53.2	57.6	56.2	55.1	-	63.1
5.0 - 5.2	*	*	-	20.9	1.9	6.8	14.1	28.6	11.0	27.7	-	9.0
5.3 & Above	-	-	-	7.8	*	0.6	0.1	8.9	2.1	8.2	-	0.7
Average	3.92	3.72	-	4.76	4.50	4.57	4.46	4.83	4.46	4.78	-	4.44
Leaf												
1 - 2	1.4	11.1	-	15.2	29.9	31.1	48.7	15.9	9.0	14.8	-	68.8
3	8.6	27.1	-	49.4	59.1	54.5	42.7	52.3	46.5	55.0	-	23.0
4	28.3	26.5	-	28.4	10.6	13.2	8.1	25.4	34.1	26.0	-	6.5
5	37.1	19.7	-	6.3	0.5	1.1	0.4	5.6	9.3	3.9	-	1.4
6	18.8	11.0	-	0.6	-	*	-	0.7	1.0	0.3	-	0.3
7	4.1	3.9	-	0.1	-	*	-	0.1	0.1	*	-	-
8	1.8	0.7	-	*	-	-	-	*	-	-	-	-
Average	4.83	4.06	-	3.27	2.81	2.83	2.56	3.23	3.46	3.20	-	2.14
HVI Trash 1/												
00	-	-	-	-	-	*	-	*	-	*	-	0.1
01	0.4	3.6	-	2.6	3.9	5.3	10.6	2.0	2.3	1.8	-	36.5
02	1.5	10.9	-	16.3	32.0	28.9	38.0	18.8	8.9	15.6	-	32.8
03	2.9	14.1	-	25.5	33.2	31.4	29.9	28.2	20.0	27.1	-	15.4
04	7.4	13.5	-	22.6	18.8	19.2	10.7	22.3	24.0	24.6	-	7.1
05	12.1	12.0	-	15.5	7.5	9.2	6.0	13.7	18.6	15.8	-	3.8
06	13.9	10.1	-	9.0	3.0	3.7	2.8	7.5	11.8	8.3	-	2.2
07	15.4	8.8	-	4.6	1.2	1.4	1.3	3.9	7.1	3.9	-	1.1
08	14.3	7.2	-	2.2	0.4	0.5	0.4	1.9	4.0	1.7	-	0.5
09	11.3	5.7	-	1.0	0.1	0.2	0.1	0.9	1.8	0.7	-	0.2
10	7.6	4.4	-	0.5	*	0.1	0.2	0.4	0.8	0.3	-	0.2
11	5.2	3.3	-	0.2	*	*	-	0.2	0.4	0.1	-	0.1
12	2.9	2.4	-	0.1	-	*	-	0.1	0.2	0.1	-	*
13	1.7	1.6	-	*	-	*	-	*	*	*	-	-
14	1.2	1.0	-	*	-	*	-	*	*	*	-	-
15	0.8	0.6	-	-	-	*	-	*	-	*	-	-
16	0.4	0.3	-	-	-	*	-	*	-	*	-	-
17	0.4	0.2	-	-	-	*	-	*	-	*	-	-
18 & Above	0.8	0.3	-	-	-	*	-	*	-	*	-	-
Average	0.76	0.58	-	0.40	0.31	0.32	0.28	0.39	0.45	0.39	-	0.23
UNIFORMITY 2/												
74 & Below	0.3	*	-	-	-	-	-	-	-	-	-	-
75	0.2	0.1	-	-	-	*	-	-	-	*	-	-
76	1.6	1.0	-	-	-	*	-	*	-	*	-	-
77	5.4	5.1	-	*	*	*	-	*	-	*	-	0.1
78	13.6	16.7	-	0.5	0.1	0.1	-	0.3	0.2	0.2	-	1.1
79	24.5	28.4	-	3.1	1.7	0.9	0.3	1.7	1.6	1.9	-	4.6
80	22.8	24.7	-	10.8	8.1	9.1	12.2	7.9	10.1	11.7	-	17.3
81	17.8	16.4	-	30.7	30.2	23.5	48.5	22.3	22.2	29.9	-	44.7
82	9.4	7.0	-	35.2	46.7	36.0	33.4	37.7	37.3	36.5	-	27.5
83	4.2	0.6	-	17.8	11.6	25.6	5.1	23.9	25.5	17.6	-	4.4
84	0.2	*	-	1.9	1.3	4.4	0.4	5.7	2.9	2.1	-	0.2
85 & Above	-	-	-	0.1	0.3	0.4	-	0.4	0.2	0.1	-	-
Average	80.17	79.95	-	82.03	82.07	82.36	81.78	82.37	82.29	82.07	-	81.52
Tenderable 3/	25.3	41.5	-	63.8	97.9	92.4	80.8	61.0	76.4	62.4	-	80.4
SAMPLES CLASSED	7,863	117,004	-	207,195	11,684	777,871	1,582	833,008	8,406	742,218	-	15,070

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE For The Week Ending Jan 11, 2024										
Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE										
2.4 & Below	-	*	-	-	-	-	0.1	*	-	-
2.5 - 2.6	-	*	-	-	-	*	0.5	0.1	-	*
2.7 - 2.9	-	0.2	-	*	-	*	0.3	0.4	-	*
3.0 - 3.2	0.5	0.9	0.1	0.1	*	0.2	0.7	1.1	0.1	0.1
3.3 - 3.4	0.1	1.8	1.1	0.4	0.2	0.5	0.6	1.6	0.1	0.3
3.5 - 3.6	6.5	3.4	2.5	1.1	1.9	1.5	1.7	2.7	0.5	0.9
3.7 - 4.2	59.9	37.9	36.2	22.8	48.0	32.0	26.5	23.7	7.3	19.5
4.3 - 4.9	31.9	51.9	58.5	66.9	49.2	64.2	64.9	59.4	88.9	70.3
5.0 - 5.2	1.1	3.8	1.5	7.9	0.6	1.6	4.6	8.8	3.0	7.9
5.3 & Above	-	0.2	*	0.9	-	*	0.1	2.1	0.2	1.0
Average	4.12	4.29	4.31	4.48	4.25	4.34	4.38	4.44	4.59	4.52
Leaf										
1 - 2	11.3	44.0	3.2	8.3	45.6	42.5	39.1	49.3	29.7	29.8
3	58.7	40.8	35.8	45.0	45.4	46.2	36.2	37.8	62.6	59.8
4	25.4	11.5	44.0	36.8	8.0	10.2	15.6	9.9	7.5	9.7
5	3.4	2.7	14.8	8.9	0.9	1.1	5.3	2.2	0.3	0.6
6	1.0	0.8	1.9	1.0	0.1	0.1	2.6	0.6	*	*
7	0.1	0.2	0.3	0.1	*	*	0.8	0.2	-	-
8	-	*	-	-	-	-	0.4	0.1	-	-
Average	3.24	2.67	3.77	3.49	2.63	2.66	2.82	2.58	2.78	2.80
HVI Trash 1/										
00	-	0.1	-	-	-	*	1.4	0.1	-	-
01	0.5	15.7	0.1	0.9	7.5	11.1	20.4	18.0	3.0	3.3
02	11.4	31.0	4.3	9.4	41.1	34.6	20.5	34.5	29.7	29.0
03	28.9	24.1	15.1	20.2	27.3	27.6	20.1	23.2	39.4	35.9
04	25.5	13.9	23.9	24.0	12.8	14.8	13.8	12.2	18.0	19.8
05	15.6	7.0	22.5	19.4	6.9	7.0	8.4	5.9	6.8	7.9
06	10.1	3.6	15.7	12.6	2.8	3.0	4.8	2.8	2.1	2.8
07	3.5	1.9	9.4	7.0	0.9	1.2	3.0	1.4	0.7	0.9
08	2.3	1.0	5.0	3.6	0.4	0.5	1.9	0.8	0.2	0.2
09	0.9	0.7	2.1	1.6	0.2	0.2	1.4	0.4	*	0.1
10	0.7	0.4	1.1	0.7	*	0.1	1.2	0.3	*	*
11	0.3	0.2	0.5	0.3	0.1	*	0.9	0.2	-	*
12	0.1	0.2	0.2	0.1	*	*	0.6	0.1	-	*
13	0.2	0.1	0.1	0.1	-	*	0.5	0.1	-	*
14	-	0.1	*	*	-	*	0.3	*	-	-
15	0.1	*	-	*	*	*	0.2	*	-	-
16	-	*	-	*	-	*	0.2	*	-	-
17	-	*	-	*	-	*	0.1	*	-	-
18 & Above	-	*	-	*	-	-	0.1	*	-	-
Average	0.42	0.30	0.50	0.46	0.29	0.29	0.35	0.28	0.31	0.31
UNIFORMITY 2/										
74 & Below	-	*	-	-	-	-	*	*	-	-
75	0.5	0.1	-	-	-	*	0.2	0.1	-	-
76	0.7	0.6	-	*	-	*	1.3	0.7	-	-
77	2.5	2.5	0.1	*	-	*	4.7	2.6	-	*
78	6.9	8.0	0.6	0.2	0.1	0.1	13.3	7.6	0.1	0.2
79	7.9	14.8	4.0	1.9	0.5	1.0	19.8	16.9	0.7	2.0
80	11.7	21.7	20.3	13.7	6.6	6.6	22.5	27.1	3.2	13.2
81	26.4	25.2	40.5	37.8	32.6	24.1	23.3	28.1	26.0	33.2
82	26.3	22.3	25.2	32.3	47.1	44.4	13.3	13.8	48.0	35.4
83	15.8	4.8	8.5	12.6	11.8	22.1	1.5	2.6	21.1	14.5
84	1.3	0.1	0.7	1.4	1.3	1.7	0.1	0.3	0.9	1.4
85 & Above	-	*	*	0.1	*	0.1	-	*	*	0.1
Average	81.42	80.88	81.59	81.89	82.12	82.30	80.33	80.66	82.32	81.96
Tenderable 3/	83.2	79.6	84.1	85.5	98.2	97.5	53.1	72.4	95.2	90.0
SAMPLES CLASSED	1,672	138,813	12,474	301,645	9,687	657,268	23,515	2,699,629	7,172	185,264

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE									
For The Week Ending Jan 11, 2024									
Color Grade	Leaf	Arizona		California		New Mexico		Texas	
		Week	Season	Week	Season	Week	Season	Week	Season
01	1	78.1	72.9	0.9	6.0	-	29.2	6.0	10.9
	2	16.1	15.7	6.5	12.2	-	30.3	16.2	16.0
	3	0.1	1.1	0.1	0.5	-	1.0	0.6	0.9
	4	-	*	-	-	-	*	-	*
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		94.3	89.8	7.5	18.6	-	60.4	22.7	27.9
02	1	3.2	4.4	3.2	7.4	-	6.1	7.5	9.2
	2	2.2	4.4	70.9	49.0	-	22.5	47.0	43.5
	3	0.2	1.1	8.2	11.8	-	6.3	13.9	9.2
	4	-	0.2	0.1	0.7	-	0.2	0.7	0.3
	5	-	-	*	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	*	-	-	-	*
Total -----		5.6	10.0	82.4	68.9	-	35.1	69.0	62.2
03	1	-	*	0.1	0.1	-	*	-	*
	2	0.1	0.1	4.7	3.3	-	1.2	1.6	3.3
	3	-	*	3.7	5.2	-	2.7	5.4	4.7
	4	-	*	0.5	1.7	-	0.4	1.1	0.7
	5	-	-	*	0.1	-	-	-	*
	6	-	-	-	*	-	-	-	-
	7	-	-	-	*	-	-	-	-
Total -----		0.1	0.1	9.0	10.5	-	4.3	8.2	8.7
04	1	-	-	-	*	-	-	-	-
	2	-	*	0.2	0.1	-	*	-	0.1
	3	0.1	*	0.6	0.5	-	*	-	0.5
	4	-	-	0.1	0.6	-	*	0.1	0.5
	5	-	-	-	0.2	-	-	-	*
	6	-	-	-	0.1	-	-	-	-
	7	-	-	-	*	-	-	-	-
Total -----		0.1	*	0.8	1.5	-	0.1	0.1	1.1
05	1	-	-	-	-	-	-	-	-
	2	-	*	*	*	-	-	-	-
	3	-	*	*	*	-	-	-	*
	4	-	-	*	0.1	-	*	-	0.1
	5	-	-	-	*	-	-	-	-
	6	-	-	-	0.1	-	-	-	-
	7	-	-	-	0.2	-	-	-	-
Total -----		-	0.1	0.1	0.5	-	*	-	0.1
06	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	*	*	-	-	-	-
	4	-	-	0.1	*	-	-	-	*
	5	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	0.1	-	-	-	-
Total -----		-	-	0.1	0.1	-	-	-	*
07	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-
	4	-	-	*	*	-	-	-	-
	5	-	-	*	*	-	-	-	-
	6	-	-	*	*	-	-	-	-
	7	-	-	-	*	-	-	-	-
Total -----		-	-	0.1	*	-	-	-	-
STAPLE									
44 & Shorter		-	*	-	0.5	-	0.7	-	6.9
46		0.4	1.4	0.7	6.4	-	9.3	1.8	29.1
48		45.2	62.1	30.4	28.1	-	64.9	42.7	42.8
50		53.9	35.2	40.5	50.8	-	23.6	55.1	21.1
52 & Longer		0.5	1.2	28.4	14.3	-	1.6	0.4	0.1
Average Staple		49.09	48.72	49.93	49.44	-	48.32	49.08	47.56
Average Length		1.43	1.42	1.45	1.43	-	1.40	1.43	1.38
EXTRANEIOUS MATTER									
Bark		-	-	-	*	-	0.3	0.1	0.2
Grass		-	-	-	0.1	-	0.2	0.3	0.1
Spindle Twist		-	*	0.5	0.3	-	*	-	*
Preparation		-	*	*	*	-	-	-	*
All Other		-	*	-	*	-	*	0.1	0.2

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE For The Week Ending Jan 11, 2024								
Quality Designation	Arizona		California		New Mexico		Texas	
	Week	Season	Week	Season	Week	Season	Week	Season
MIKE								
2.4 & Below	-	-	*	*	-	-	-	-
2.5 - 2.6	-	*	1.7	0.2	-	-	-	-
2.7 - 2.9	0.1	0.1	5.9	0.8	-	0.1	-	*
3.0 - 3.2	-	*	2.0	2.0	-	0.2	-	*
3.3 - 3.4	1.6	0.7	1.7	4.1	-	3.6	-	1.1
3.5 - 3.6	4.4	4.9	0.6	12.5	-	10.4	-	7.8
3.7 - 4.2	93.7	93.6	77.7	75.4	-	75.4	40.8	74.4
4.3 - 4.9	0.3	0.7	10.3	5.0	-	10.3	59.2	16.6
5.0 - 5.2	-	-	-	*	-	-	-	-
5.3 & Above	-	-	-	*	-	-	-	-
Average	3.88	3.91	3.93	3.86	-	3.94	4.25	4.00
ALL RANGE MIKE								
2.4 & Below	-	-	*	*	-	-	-	-
2.5	-	-	0.2	*	-	-	-	-
2.6	-	*	1.5	0.2	-	-	-	-
2.7	-	*	2.3	0.2	-	*	-	-
2.8	0.1	0.1	2.0	0.3	-	*	-	*
2.9	-	*	1.5	0.3	-	*	-	-
3.0	-	-	0.7	0.4	-	*	-	*
3.1	-	*	0.4	0.6	-	*	-	-
3.2	-	*	0.8	1.0	-	0.2	-	*
3.3	0.2	*	0.8	1.5	-	0.9	-	0.4
3.4	1.4	0.6	0.9	2.6	-	2.6	-	0.7
3.5	2.0	1.9	0.1	4.6	-	4.3	-	3.9
3.6	2.4	3.0	0.5	7.9	-	6.1	-	4.0
3.7	10.4	8.7	2.3	10.4	-	8.0	-	6.4
3.8	22.6	17.0	6.1	13.6	-	11.3	2.0	10.1
3.9	24.9	26.4	11.7	15.6	-	15.7	-	16.1
4.0	25.8	27.0	20.5	15.8	-	15.3	0.2	12.5
4.1	8.0	11.7	23.4	12.6	-	13.7	14.0	14.4
4.2	2.0	2.9	13.9	7.4	-	11.3	24.6	14.9
4.3	0.1	0.6	4.1	3.3	-	6.1	48.6	12.3
4.4	-	*	4.8	1.3	-	2.9	7.5	3.0
4.5	0.1	*	1.5	0.3	-	1.0	3.1	1.2
4.6	-	*	*	0.1	-	0.3	-	0.1
4.7	-	-	-	*	-	*	0.1	*
4.8	-	-	-	*	-	*	-	-
4.9	-	-	-	*	-	*	-	-
5.0	-	-	-	*	-	-	-	-
5.1	-	-	-	*	-	-	-	-
5.2	-	-	-	*	-	-	-	-
5.3 & Above	-	-	-	*	-	-	-	-
Average	3.88	3.91	3.93	3.86	-	3.94	4.25	4.00
STRENGTH 1/								
36 & Below	0.1	0.1	5.6	2.6	-	12.6	-	3.5
37	0.1	0.9	1.3	4.0	-	11.9	1.1	9.4
38	0.1	5.4	1.1	6.0	-	7.8	0.1	14.6
39	2.4	5.2	2.0	5.9	-	3.4	1.0	19.3
40	10.2	11.1	5.7	7.5	-	2.8	2.6	8.9
41	31.6	29.9	12.1	11.8	-	7.2	12.9	5.9
42	23.7	28.4	18.4	16.9	-	15.7	26.3	12.5
43	22.2	12.9	17.4	16.6	-	19.1	22.5	12.4
44	8.0	4.3	14.6	13.7	-	12.4	12.4	6.7
45	1.5	1.5	11.3	9.7	-	5.3	16.8	4.5
46	-	0.2	7.7	3.8	-	1.4	3.9	1.4
47	-	0.1	2.1	1.1	-	0.1	0.2	0.6
48 & Above	-	*	0.6	0.3	-	0.1	0.4	0.2
Average	42.30	41.80	42.93	42.35	-	41.21	43.34	40.82
UNIFORMITY								
83 & Below	-	*	1.4	0.7	-	0.1	-	0.1
84	0.2	0.5	6.4	4.1	-	3.1	-	4.9
85	6.3	15.0	11.7	18.2	-	32.6	11.0	36.4
86	68.8	58.1	41.0	49.6	-	44.5	35.7	39.8
87	24.2	26.1	29.7	26.1	-	19.6	49.9	18.5
88 & Above	0.5	0.3	9.8	1.5	-	0.2	3.3	0.4
Average	86.62	86.55	86.68	86.46	-	86.27	86.94	86.17
Samples Classed	1,571	10,345	7,197	208,790	-	28,199	1,676	18,538

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
 * Less than 0.05 percent.