



Volume 25, No.26

State	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
AL	6	90.0	80.5	10,495	26	86.9	73.4	690,970
AR	2	86.8	60.1	2,118	28	78.5	55.9	1,439,025
AZ	7	92.8	80.0	10,692	9	89.0	71.7	167,989
CA*	-	-	-	-	11	91.5	81.1	51,463
FL*	-	-	-	-	4	67.7	43.5	92,319
GA	45	80.2	67.3	65,042	58	90.4	77.7	2,056,429
KS*	-	-	-	-	3	41.5	28.9	117,236
LA	-	-	-	-	17	63.8	37.8	207,195
MO	2	99.9	99.6	2,345	19	92.4	74.7	780,216
MS	-	-	-	-	35	61.0	35.5	833,008
NC	12	85.5	69.4	4,829	32	62.5	41.3	747,047
NM*	-	-	-	-	3	81.0	66.6	15,543
OK	-	-	-	-	11	79.6	61.3	138,813
SC	8	91.4	85.0	14,089	12	85.8	71.7	315,734
TN	-	-	-	-	18	97.5	90.3	657,268
TX	18	49.7	22.3	12,062	159	72.3	44.3	2,711,603
VA	2	66.7	38.2	1,037	4	89.8	72.3	186,301
United States	108	81.4	68.0	126,690	449	79.3	59.4	11,208,159
AMERICAN PIMA								
AZ	2			1,445	3			11,790
CA	2			5,246	13			214,036
NM*	-			-	3			28,672
TX	2			1,301	3			19,839
United States	7			8,465	22			274,337
United States all cotton	115			135,155	462			11,482,496

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 18, 2024

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	13.0	11.4	6.2	6.8	54.9	71.5	-	57.5	-	1.1	0.5	1.6
	3	11.1	10.6	2.6	2.7	13.2	8.6	-	9.9	-	1.2	0.5	1.4
	4	0.6	0.9	-	0.1	0.4	0.3	-	0.8	-	0.1	*	0.1
	5	-	*	-	*	-	*	-	*	-	-	-	*
	6	-	-	-	-	-	-	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	24.7	22.9	8.8	9.6	68.5	80.3	-	68.3	-	2.4	1.1	3.2
31	1 - 2	10.2	7.8	27.8	13.8	8.6	6.1	-	10.3	-	6.6	2.4	7.4
	3	33.4	30.3	48.4	38.8	16.0	7.4	-	10.8	-	26.8	9.9	26.8
	4	7.1	12.1	12.0	12.2	2.8	1.9	-	6.5	-	10.1	3.6	9.5
	5	0.3	1.5	0.3	1.0	0.4	0.2	-	1.4	-	1.0	0.5	1.0
	6	*	0.1	-	*	-	*	-	0.1	-	*	*	*
	7	-	*	-	*	-	-	-	-	-	*	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	51.1	51.8	88.4	65.8	27.9	15.6	-	29.1	-	44.6	16.4	44.7
41	1 - 2	0.2	0.9	0.2	0.5	0.1	*	-	0.1	-	1.1	2.3	1.6
	3	5.1	7.1	1.3	7.9	0.7	0.1	-	0.2	-	13.5	25.1	19.1
	4	3.0	7.3	1.0	11.6	1.3	0.2	-	0.5	-	14.5	23.3	17.6
	5	0.3	2.3	*	3.6	0.6	0.1	-	0.3	-	3.9	5.9	4.8
	6	*	0.4	-	0.3	0.1	*	-	0.1	-	0.5	0.8	0.7
	7	-	*	-	*	*	*	-	-	-	0.1	0.1	0.1
	8	-	*	-	-	-	*	-	-	-	*	-	*
Total	----	8.6	18.0	2.6	23.9	2.7	0.5	-	1.2	-	33.4	57.4	44.1
51	1 - 2	1.0	0.2	-	*	-	-	-	-	-	0.2	0.6	0.2
	3	5.2	1.7	-	*	-	*	-	-	-	3.4	7.4	1.7
	4	2.7	1.8	-	0.1	-	*	-	-	-	3.6	7.3	2.0
	5	0.8	0.5	-	0.1	-	*	-	-	-	1.0	2.8	0.8
	6	0.1	0.1	-	*	*	*	-	-	-	0.1	0.6	0.2
	7	*	*	-	*	*	*	-	-	-	*	0.1	*
	8	-	*	-	*	*	*	-	-	-	-	-	*
Total	----	9.8	4.2	-	0.3	0.1	*	-	-	-	8.3	18.9	4.9
61	1 - 2	0.1	*	-	*	-	-	-	-	-	*	-	*
	3	0.4	*	-	-	-	-	-	-	-	0.1	*	*
	4	0.1	*	-	*	-	-	-	-	-	*	*	*
	5	*	*	-	*	-	-	-	-	-	*	*	*
	6	-	*	-	*	-	-	-	-	-	*	*	*
	7	-	*	-	*	-	-	-	-	-	*	-	*
	8	-	*	-	-	-	-	-	-	-	-	-	*
Total	----	0.7	0.1	-	*	-	-	-	-	-	0.1	*	*
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	*
	6	-	-	-	-	-	-	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	-	-	-	-	*
12 & 22	1 - 2	-	*	-	*	0.1	2.1	-	*	-	*	*	*
	3	-	*	-	*	0.1	0.7	-	0.1	-	*	*	*
	4	-	*	-	*	-	*	-	*	-	-	-	*
	5	-	*	-	*	-	-	-	-	-	-	-	*
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	*	0.1	2.9	-	0.2	-	*	*	*
32	1 - 2	-	0.1	-	*	0.2	0.1	-	*	-	0.2	*	*
	3	-	0.4	-	0.1	0.2	0.3	-	0.2	-	1.6	0.2	0.3
	4	*	0.2	-	*	*	0.2	-	0.4	-	0.7	0.1	0.2
	5	-	*	-	*	-	*	-	0.3	-	0.1	*	*
	6	-	*	-	*	-	*	-	*	-	*	-	*
	7	-	*	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	0.7	-	0.1	0.5	0.6	-	0.9	-	2.6	0.4	0.6
42	1 - 2	*	*	-	*	-	*	-	*	-	0.1	*	*
	3	0.1	0.4	-	0.1	*	*	-	*	-	2.5	0.8	0.6
	4	0.1	0.5	-	0.1	-	*	-	*	-	2.2	1.5	0.8
	5	*	0.2	-	0.1	*	*	-	0.1	-	0.5	0.8	0.3
	6	-	0.1	-	*	*	*	-	0.1	-	0.1	0.1	0.1
	7	-	*	-	*	-	-	-	-	-	*	*	*
	8	-	*	-	-	-	-	-	-	-	-	-	*
Total	----	0.2	1.3	-	0.3	0.1	*	-	0.2	-	5.5	3.3	1.8

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 18, 2024

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	*	*	-	*	-	-	-	-	-	*	*	*
	3	1.1	0.3	-	*	-	-	-	-	-	0.7	0.4	0.1
	4	1.6	0.3	-	*	-	-	-	-	-	1.0	0.6	0.2
	5	0.4	0.1	-	*	0.1	*	-	-	-	0.4	0.4	0.1
	6	0.2	*	-	*	0.1	*	-	-	-	0.1	0.2	*
	7	*	*	-	*	-	-	-	-	-	*	*	*
	8	-	*	-	*	-	*	-	-	-	-	-	*
Total	----	3.3	0.8	-	*	0.1	*	-	-	-	2.3	1.7	0.5
62	1 - 2	-	*	-	-	-	-	-	-	-	*	-	-
	3	0.1	*	0.1	*	-	-	-	-	-	*	-	*
	4	0.3	*	-	-	-	-	-	-	-	*	*	*
	5	0.2	*	-	-	-	-	-	-	-	*	*	*
	6	0.1	*	-	-	-	-	-	-	-	*	*	*
	7	-	*	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	*
Total	----	0.6	*	0.1	*	-	-	-	-	-	0.1	*	*
13 & 23	1 - 2	-	*	-	-	-	0.1	-	-	-	-	-	*
	3	-	*	-	-	-	*	-	-	-	-	-	*
	4	-	-	-	-	-	-	-	-	-	-	-	*
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	-	-	0.1	-	-	-	-	-	*
33	1 - 2	-	*	-	*	-	*	-	*	-	*	*	*
	3	-	*	-	*	*	*	-	*	-	*	*	*
	4	-	*	-	*	-	*	-	*	-	*	*	*
	5	-	*	-	*	-	-	-	-	-	-	*	*
	6	-	*	-	*	-	-	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	*	*	*	-	*	-	0.1	0.1	*
43	1 - 2	-	*	-	*	-	-	-	-	-	*	*	*
	3	-	*	-	*	*	*	-	-	-	0.1	0.1	*
	4	*	*	-	*	*	*	-	*	-	0.1	0.2	*
	5	*	*	-	*	-	*	-	*	-	*	0.1	*
	6	-	*	-	*	-	-	-	*	-	-	*	*
	7	-	*	-	-	-	-	-	-	-	-	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	*
Total	----	0.1	0.1	-	*	*	*	-	0.1	-	0.2	0.4	0.1
53	1 - 2	-	-	-	-	-	-	-	-	-	*	*	*
	3	0.1	*	-	-	-	-	-	-	-	0.1	*	*
	4	0.2	*	-	*	-	-	-	-	-	0.1	0.1	*
	5	0.1	*	-	*	-	-	-	-	-	*	0.1	*
	6	-	*	-	-	-	-	-	-	-	*	0.1	*
	7	-	*	-	-	-	-	-	-	-	*	*	*
	8	-	-	-	-	-	-	-	-	-	*	-	*
Total	----	0.3	0.1	-	*	-	-	-	-	-	0.2	0.3	*
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	*	-	-	-	-	-	-	-	*	-	*
	4	0.3	*	-	-	-	-	-	-	-	*	-	*
	5	0.2	*	-	-	-	-	-	-	-	*	-	*
	6	0.1	*	-	-	-	-	-	-	-	*	-	*
	7	*	*	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.6	*	-	-	-	-	-	-	-	*	-	*
24 - 54	1 - 8	*	*	-	*	-	-	-	-	-	*	*	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	-	-	-	-	-	-	-	-	-	-	*
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	*	-	-	-	-	-	-	-	-	-	*
31		*	0.1	-	*	-	-	-	-	-	*	*	*
32		0.3	0.4	-	*	0.2	*	-	-	-	0.3	0.2	0.2
33		0.3	1.7	-	0.1	0.3	0.2	-	*	-	2.5	1.3	1.3
34		3.4	5.7	0.1	0.5	1.0	1.0	-	0.7	-	9.8	4.9	6.3
35		10.3	13.8	8.7	5.9	3.9	6.3	-	6.1	-	22.4	14.3	16.6
36		26.7	23.7	22.0	20.6	6.8	17.3	-	14.4	-	25.2	22.1	27.8
37		57.6	36.8	60.2	50.1	24.3	33.5	-	38.4	-	25.8	36.2	34.0
38		1.4	13.6	4.9	18.6	32.2	24.1	-	18.5	-	9.5	16.3	10.8
39		-	3.5	3.9	3.8	21.0	13.0	-	14.9	-	3.8	4.2	2.7
40 & Longer		*	0.7	0.1	0.4	10.2	4.7	-	7.0	-	0.6	0.4	0.4
Average Staple		36.41	36.45	36.73	36.93	37.90	37.32	-	37.41	-	36.08	36.54	36.32
Average Length		1.13	1.14	1.15	1.15	1.18	1.17	-	1.17	-	1.12	1.14	1.13

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 18, 2024

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	-	7.5	-	3.2	5.7	7.4	-	5.9	6.8	3.9	-	57.8
	3	-	11.0	-	1.5	4.5	2.1	-	4.6	6.8	2.7	-	5.4
	4	-	2.7	-	*	-	*	-	0.2	0.1	0.1	-	*
	5	-	0.2	-	-	-	*	-	*	-	*	-	-
	6	-	*	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	21.3	-	4.8	10.2	9.5	-	10.7	13.7	6.7	-	63.3
31	1 - 2	-	0.6	-	7.6	15.4	22.8	-	9.5	1.9	10.4	-	10.5
	3	-	7.4	-	24.1	56.8	43.3	-	38.6	12.8	43.2	-	14.5
	4	-	9.9	-	6.8	4.2	7.0	-	12.2	14.4	14.2	-	3.5
	5	-	3.6	-	0.3	0.1	0.2	-	0.9	2.1	0.9	-	0.3
	6	-	0.4	-	*	-	*	-	*	*	*	-	-
	7	-	*	-	-	-	*	-	*	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	22.0	-	38.9	76.5	73.4	-	61.1	31.2	68.7	-	28.8
41	1 - 2	-	*	-	1.2	0.3	0.9	-	0.4	0.5	0.4	-	0.1
	3	-	0.8	-	16.6	2.7	9.0	-	8.2	16.3	8.5	-	0.9
	4	-	5.0	-	17.8	8.6	6.2	-	12.4	18.6	11.3	-	2.1
	5	-	7.9	-	4.4	1.4	0.9	-	4.5	5.9	2.8	-	0.9
	6	-	4.6	-	0.3	-	*	-	0.7	0.6	0.3	-	0.2
	7	-	0.9	-	*	-	*	-	*	-	*	-	-
	8	-	0.1	-	*	-	-	-	*	-	-	-	-
Total	----	-	19.3	-	40.4	13.0	17.0	-	26.1	42.0	23.3	-	4.3
51	1 - 2	-	-	-	*	-	*	-	*	*	*	-	-
	3	-	-	-	0.2	-	*	-	*	3.0	0.1	-	-
	4	-	*	-	0.6	0.3	*	-	*	6.3	0.2	-	-
	5	-	0.5	-	0.7	*	*	-	0.1	1.2	0.1	-	*
	6	-	1.4	-	0.1	-	*	-	*	0.1	*	-	*
	7	-	1.1	-	*	-	*	-	*	*	*	-	-
	8	-	0.4	-	-	-	-	-	*	-	-	-	-
Total	----	-	3.4	-	1.7	0.3	*	-	0.2	10.6	0.4	-	*
61	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	*	-	-	-	-
	4	-	-	-	*	-	-	-	-	-	-	-	-
	5	-	-	-	*	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	*	-	-	-	*	-	-	-	-
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	-	-	-	-	-
12 & 22	1 - 2	-	2.7	-	1.8	-	*	-	*	-	*	-	0.3
	3	-	5.7	-	0.7	-	*	-	*	-	*	-	0.1
	4	-	2.1	-	*	-	*	-	*	-	*	-	-
	5	-	0.1	-	-	-	-	-	*	-	*	-	-
	6	-	*	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	10.6	-	2.6	-	*	-	*	-	*	-	0.4
32	1 - 2	-	0.1	-	0.9	-	*	-	0.1	-	*	-	0.7
	3	-	1.5	-	2.6	-	*	-	0.6	0.5	0.3	-	1.5
	4	-	3.8	-	0.6	-	*	-	0.2	0.4	0.1	-	0.4
	5	-	1.7	-	*	-	*	-	*	*	*	-	*
	6	-	0.3	-	-	-	-	-	*	-	*	-	-
	7	-	*	-	*	-	-	-	*	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	7.4	-	4.1	-	*	-	0.9	0.9	0.4	-	2.6
42	1 - 2	-	*	-	0.4	-	*	-	*	-	*	-	-
	3	-	0.2	-	3.4	*	*	-	0.3	0.2	0.1	-	0.1
	4	-	2.5	-	2.3	-	*	-	0.4	0.3	0.2	-	0.1
	5	-	4.9	-	0.6	-	*	-	0.1	0.2	0.1	-	0.1
	6	-	3.6	-	0.1	-	*	-	*	*	*	-	*
	7	-	1.2	-	*	-	-	-	*	-	*	-	-
	8	-	*	-	-	-	-	-	*	-	-	-	-
Total	----	-	12.4	-	6.7	*	*	-	0.9	0.7	0.4	-	0.3

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 18, 2024

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	-	*	-	-	-	-	-	*	-	-
	3	-	-	-	0.2	-	*	-	*	-	*	-	-
	4	-	*	-	0.3	-	-	-	*	0.5	*	-	-
	5	-	0.1	-	0.2	-	*	-	*	*	*	-	-
	6	-	0.3	-	0.1	-	*	-	*	-	*	-	-
	7	-	0.5	-	*	-	-	-	*	-	*	-	-
	8	-	0.2	-	-	-	-	-	*	-	-	-	-
Total	----	-	1.2	-	0.7	-	*	-	*	0.5	*	-	-
62	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	-	-	-
	4	-	-	-	*	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	-	-	-	-	-	-	-	-
13 & 23	1 - 2	-	0.1	-	*	-	-	-	-	-	*	-	-
	3	-	0.2	-	*	-	-	-	-	-	*	-	-
	4	-	0.1	-	-	-	-	-	*	-	*	-	-
	5	-	*	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	0.4	-	0.1	-	-	-	*	-	*	-	-
33	1 - 2	-	*	-	*	-	*	-	*	-	*	-	-
	3	-	0.2	-	*	-	*	-	*	0.2	*	-	*
	4	-	0.4	-	*	-	*	-	*	0.2	*	-	0.1
	5	-	0.3	-	-	-	*	-	*	-	*	-	*
	6	-	*	-	-	-	-	-	-	-	-	-	-
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	0.9	-	*	-	*	-	*	0.3	*	-	0.1
43	1 - 2	-	-	-	*	-	*	-	*	-	*	-	-
	3	-	*	-	*	-	*	-	*	-	*	-	*
	4	-	0.2	-	*	-	*	-	*	-	*	-	0.1
	5	-	0.4	-	*	-	*	-	*	*	*	-	0.1
	6	-	0.2	-	*	-	-	-	*	-	*	-	-
	7	-	0.1	-	-	-	-	-	*	-	*	-	-
	8	-	*	-	-	-	-	-	*	-	-	-	-
Total	----	-	0.9	-	0.1	-	*	-	*	*	*	-	0.2
53	1 - 2	-	-	-	-	-	*	-	-	-	-	-	-
	3	-	-	-	*	-	*	-	-	-	*	-	-
	4	-	*	-	*	-	-	-	*	-	*	-	-
	5	-	*	-	*	-	-	-	*	-	*	-	-
	6	-	*	-	*	-	-	-	*	-	*	-	-
	7	-	*	-	*	-	-	-	-	-	*	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	----	-	0.1	-	*	-	*	-	*	-	*	-	-
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	*	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	-	-	-	-	-	-	-	-
24 - 54	1 - 8	-	0.1	-	*	-	-	-	*	-	*	-	-
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	*	-	-	-	*	-	-	-	*	-	-
31		-	0.3	-	*	-	-	-	*	-	*	-	-
32		-	1.6	-	0.1	-	*	-	0.1	-	0.2	-	-
33		-	5.3	-	1.2	-	*	-	0.6	0.1	2.1	-	*
34		-	12.2	-	5.4	0.1	0.1	-	4.1	1.7	10.1	-	3.8
35		-	19.7	-	14.5	1.4	2.5	-	12.5	17.8	24.0	-	7.8
36		-	22.8	-	26.9	3.5	15.8	-	25.0	33.7	31.5	-	20.2
37		-	23.4	-	32.5	72.7	47.3	-	37.6	35.6	26.4	-	31.7
38		-	9.2	-	13.2	11.8	26.9	-	14.7	7.8	4.8	-	14.3
39		-	5.2	-	5.3	8.1	6.6	-	4.7	3.4	0.8	-	14.6
40 & Longer		-	0.4	-	0.9	2.5	1.0	-	0.8	0.1	0.1	-	7.5
Average Staple		-	35.91	-	36.49	37.29	37.22	-	36.62	36.40	35.87	-	37.22
Average Length		-	1.12	-	1.14	1.17	1.16	-	1.14	1.13	1.12	-	1.16

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE											
For The Week Ending Jan 18, 2024											
Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	-	25.1	0.3	3.0	-	16.9	19.5	31.6	3.0	11.0
	3	-	4.5	1.1	2.8	-	6.7	3.3	12.7	3.7	8.2
	4	-	0.1	0.1	0.2	-	0.1	0.1	0.9	-	0.4
	5	-	*	-	*	-	*	-	*	-	*
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	29.8	1.6	6.0	-	23.7	22.9	45.2	6.7	19.7
31	1 - 2	-	11.8	1.9	4.7	-	25.0	8.5	6.8	19.6	18.0
	3	-	22.4	21.7	30.4	-	35.4	8.3	14.2	25.4	47.5
	4	-	4.0	14.6	15.9	-	6.4	2.4	4.0	8.6	7.5
	5	-	0.3	1.3	1.7	-	0.3	0.2	0.4	0.5	0.5
	6	-	*	0.1	0.1	-	*	*	*	-	*
	7	-	-	-	*	-	*	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	38.5	39.6	52.7	-	67.1	19.4	25.4	54.0	73.5
41	1 - 2	-	0.7	0.3	0.4	-	0.6	0.2	0.2	9.5	0.7
	3	-	5.6	12.6	11.0	-	4.0	3.7	1.6	19.8	3.8
	4	-	3.3	29.8	20.2	-	3.5	2.7	1.8	0.9	1.6
	5	-	1.1	10.4	6.7	-	0.8	1.8	0.8	-	0.2
	6	-	0.3	1.0	0.7	-	0.1	1.3	0.3	-	*
	7	-	*	*	*	-	*	0.1	0.1	-	-
	8	-	*	-	-	-	-	-	*	-	-
Total	----	-	11.0	54.0	39.1	-	8.9	9.8	4.8	30.2	6.3
51	1 - 2	-	*	*	*	-	*	-	*	-	*
	3	-	*	1.0	0.2	-	*	-	0.1	0.3	*
	4	-	*	1.6	0.5	-	*	*	0.1	0.1	*
	5	-	0.1	0.6	0.3	-	*	0.4	0.1	-	*
	6	-	0.1	0.1	0.1	-	*	0.9	*	-	*
	7	-	*	-	*	-	*	0.3	*	-	-
	8	-	*	-	-	-	-	*	*	-	-
Total	----	-	0.3	3.3	1.1	-	*	1.8	0.4	0.4	*
61	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	*	-	*	-	-
	4	-	-	-	*	-	-	-	*	-	*
	5	-	-	-	*	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	-	*	-	*	-	*
71	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	-	-	-	-	*	-	-
	5	-	-	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	*	-	-	
12 & 22	1 - 2	-	4.3	-	*	-	*	6.7	8.9	-	*
	3	-	2.3	-	*	-	*	5.6	4.8	-	*
	4	-	0.2	-	*	-	*	0.3	0.6	-	*
	5	-	*	-	*	-	-	-	*	-	*
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	6.8	-	*	-	*	12.7	14.3	-	0.1
32	1 - 2	-	1.4	-	*	-	*	3.5	0.9	0.2	*
	3	-	3.9	*	0.1	-	*	9.6	2.8	0.4	0.1
	4	-	1.9	0.1	0.1	-	*	3.4	1.3	0.5	0.1
	5	-	0.3	0.1	0.1	-	*	0.6	0.2	0.1	*
	6	-	*	-	*	-	*	0.1	*	-	*
	7	-	*	-	-	-	-	0.1	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	-	7.5	0.2	0.3	-	0.1	17.3	5.3	1.2	0.2
42	1 - 2	-	*	-	*	-	*	0.1	0.1	0.4	*
	3	-	0.8	*	*	-	*	0.5	0.5	1.5	0.1
	4	-	1.2	0.1	0.2	-	*	0.9	0.6	2.9	0.1
	5	-	0.7	0.2	0.2	-	*	0.7	0.4	0.8	*
	6	-	0.2	0.1	0.1	-	*	0.3	0.2	-	-
	7	-	0.1	-	*	-	*	0.2	0.1	-	-
	8	-	*	-	-	-	-	-	*	-	-
Total	----	-	3.1	0.4	0.6	-	*	2.7	1.8	5.6	0.2

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE											
For The Week Ending Jan 18, 2024											
Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	*	-	-	-	-	-	*	-	-
	3	-	*	0.1	*	-	*	-	0.1	0.3	*
	4	-	*	0.6	*	-	*	-	0.1	0.2	*
	5	-	0.1	0.1	*	-	*	0.1	*	-	-
	6	-	0.1	-	*	-	*	*	*	-	-
	7	-	0.1	*	*	-	-	*	*	-	-
	8	-	*	-	-	-	-	*	*	-	-
Total	----	-	0.3	0.8	0.1	-	*	0.2	0.2	0.5	*
62	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	*	-	*	-	-
	4	-	-	-	*	-	*	-	*	-	-
	5	-	-	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	-	-	-	*	-	*	-	*	-	-
13 & 23	1 - 2	-	0.5	-	-	-	-	2.5	0.5	-	*
	3	-	0.5	-	-	-	-	1.1	0.5	-	*
	4	-	0.1	-	*	-	-	0.1	0.1	-	*
	5	-	*	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	1.1	-	*	-	-	3.6	1.2	-	*
33	1 - 2	-	0.1	-	-	-	*	1.4	0.1	0.1	*
	3	-	0.6	-	*	-	*	2.5	0.4	0.8	*
	4	-	0.4	*	*	-	*	1.0	0.3	-	*
	5	-	0.1	*	*	-	*	0.2	0.1	-	*
	6	-	*	-	-	-	-	0.1	*	-	-
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	-	1.2	*	*	-	*	5.2	0.9	0.9	*
43	1 - 2	-	*	-	*	-	-	0.1	*	-	-
	3	-	*	-	*	-	*	0.6	*	0.4	*
	4	-	0.1	*	*	-	*	0.4	0.1	-	*
	5	-	0.1	*	*	-	*	0.1	0.1	0.2	*
	6	-	*	*	*	-	-	0.2	0.1	-	*
	7	-	*	-	*	-	-	0.1	*	-	-
	8	-	*	-	-	-	-	-	*	-	-
Total	----	-	0.3	*	0.1	-	*	1.5	0.3	0.6	*
53	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	-	*	*	-	-
	4	-	-	*	*	-	*	*	*	-	-
	5	-	*	-	*	-	-	*	*	-	-
	6	-	*	-	*	-	-	-	*	-	-
	7	-	*	*	*	-	-	*	*	-	-
	8	-	*	-	-	-	-	-	*	-	-
Total	----	-	*	*	*	*	*	*	-	-	
63	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	-	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	-	-	-	-	-	*	-	*	-	-
24 - 54	1 - 8	-	0.1	*	*	-	-	2.7	0.1	0.1	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	*	-	-	-	-	0.2	*	-	-
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		-	*	-	-	-	-	-	*	-	-
30		-	*	-	-	-	-	-	0.1	-	-
31		-	0.5	-	*	-	-	0.2	0.4	-	*
32		-	2.4	*	*	-	*	1.0	1.9	-	*
33		-	4.6	0.1	0.5	-	*	6.6	6.0	-	1.0
34		-	8.3	2.8	3.6	-	0.2	13.8	14.7	2.3	5.9
35		-	12.5	11.9	13.5	-	2.5	27.0	22.7	28.3	19.9
36		-	18.9	22.0	26.1	-	15.8	23.7	22.8	40.8	42.4
37		-	29.5	33.7	37.9	-	57.6	21.9	19.8	28.3	26.9
38		-	13.8	16.5	13.2	-	20.1	3.8	7.4	0.3	3.4
39		-	6.1	9.2	4.2	-	3.4	1.8	3.2	0.1	0.5
40 & Longer		-	3.4	3.8	0.9	-	0.2	*	0.9	-	0.1
Average Staple		-	36.34	36.93	36.58	-	37.06	35.56	35.68	35.96	36.00
Average Length		-	1.13	1.15	1.14	-	1.16	1.11	1.11	1.12	1.12

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 18, 2024

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	2.1	0.3	-	*	0.2	0.2	-	0.1	-	0.5	8.7	1.4
Bark - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	*	*	-	0.1	*	*	-	0.4	-	0.1	0.2	0.1
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	*	-	*	-	-	-	*	-	*	*	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	*	0.1	-	*	0.2	0.8	-	*	-	*	0.2	0.1
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	*	-	-	-	-	-	-	-	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	-	*	-	-	-	*	-	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	-	*	-	*	-	*	-	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	*	-	*	-	-	-	-	-	*	*	*
23	-	*	-	*	-	*	-	-	-	*	*	*
24	-	*	-	*	0.2	0.1	-	-	-	*	*	*
25	-	0.1	*	*	0.3	0.3	-	0.2	-	0.1	0.1	0.1
26	*	0.2	-	*	0.2	1.3	-	0.8	-	0.4	0.9	0.4
27	1.4	1.3	0.1	0.5	1.4	2.5	-	1.1	-	1.2	3.9	2.2
28	2.1	5.0	36.7	4.0	2.7	5.3	-	3.9	-	3.5	11.1	8.0
29	4.9	15.9	28.6	19.1	5.0	9.1	-	13.0	-	7.5	22.3	18.6
30	16.9	28.9	24.1	35.0	10.8	12.8	-	15.9	-	14.2	24.1	26.3
31	33.3	25.0	7.9	26.1	20.3	16.7	-	12.8	-	19.2	18.9	22.8
32	30.6	14.9	2.5	11.0	18.0	19.2	-	6.5	-	18.8	11.8	13.2
33	9.9	6.3	-	3.2	16.1	14.8	-	7.2	-	14.6	4.6	5.6
34	0.7	1.8	*	0.8	11.4	8.3	-	10.1	-	9.7	1.6	2.0
35	*	0.5	-	0.2	7.6	5.2	-	8.3	-	6.3	0.4	0.6
36	0.1	0.1	-	0.1	3.6	2.6	-	6.2	-	3.4	0.1	0.2
37	*	*	-	*	1.5	1.1	-	7.3	-	0.9	*	*
38	-	*	-	-	0.6	0.5	-	5.2	-	0.1	*	*
39	-	-	-	-	0.2	0.2	-	1.2	-	*	-	*
40 & Above	-	-	-	-	0.1	0.1	-	0.3	-	*	-	*
Average	31.60	30.98	29.54	30.79	32.55	31.99	-	32.90	-	32.23	30.51	30.81
Mike												
2.4 & Below	-	*	-	-	-	-	-	-	-	-	-	*
2.5	-	*	-	*	-	*	-	-	-	-	*	*
2.6	-	*	-	*	-	*	-	*	-	-	*	*
2.7	-	*	-	*	*	*	-	*	-	-	0.1	*
2.8	-	*	-	*	0.3	0.1	-	*	-	-	0.1	*
2.9	0.1	*	-	*	0.3	0.1	-	*	-	-	0.1	*
3.0	*	*	-	*	0.8	0.2	-	*	-	*	0.1	*
3.1	*	0.1	-	*	0.7	0.3	-	0.1	-	*	0.1	*
3.2	*	0.3	-	*	0.6	0.4	-	*	-	*	0.4	0.1
3.3	0.2	0.3	-	*	0.8	0.6	-	0.3	-	*	0.5	0.1
3.4	*	0.4	-	*	1.3	0.8	-	0.3	-	0.1	0.8	0.2
3.5	0.2	0.7	-	0.1	2.2	0.9	-	0.5	-	0.1	1.6	0.4
3.6	0.4	1.1	-	0.1	3.1	1.4	-	1.1	-	0.2	1.5	0.6
3.7	0.3	1.9	-	0.1	3.7	2.2	-	2.9	-	0.3	2.1	1.1
3.8	2.2	2.8	-	0.2	5.3	3.4	-	6.9	-	0.5	3.1	1.9
3.9	3.7	4.0	-	0.3	5.8	4.2	-	11.0	-	0.8	4.5	3.1
4.0	5.4	5.8	-	0.7	7.5	5.4	-	12.2	-	1.4	6.5	4.8
4.1	6.1	7.3	-	1.4	8.8	6.9	-	9.5	-	2.4	9.0	6.8
4.2	7.5	8.3	2.4	2.8	11.5	8.1	-	8.5	-	3.7	9.7	8.9
4.3	6.5	9.5	0.3	4.9	10.4	8.7	-	8.3	-	4.7	9.5	10.8
4.4	8.6	9.9	1.6	8.2	8.7	9.8	-	6.9	-	6.4	10.0	12.1
4.5	11.5	9.8	2.5	11.0	7.0	10.3	-	6.4	-	7.8	9.8	12.1
4.6	17.5	9.0	21.9	12.9	6.9	9.9	-	5.8	-	10.1	9.2	11.4
4.7	17.3	8.0	31.5	13.5	5.2	7.9	-	5.2	-	12.5	7.7	9.4
4.8	6.5	6.7	18.9	12.4	5.0	6.5	-	3.9	-	13.1	6.2	7.2
4.9	2.6	5.2	7.8	10.3	2.1	4.8	-	4.1	-	11.9	3.6	4.7
5.0	0.9	3.6	12.7	8.0	1.2	3.0	-	4.1	-	10.5	2.1	2.4
5.1	0.7	2.3	0.3	5.8	0.4	1.6	-	1.1	-	6.7	1.1	1.1
5.2	0.7	1.3	-	3.5	0.2	1.2	-	0.6	-	3.2	0.4	0.3
5.3	0.3	0.7	*	1.8	*	0.8	-	0.2	-	1.9	0.2	0.1
5.4	0.5	0.3	-	0.9	-	0.5	-	0.1	-	1.1	0.1	*
5.5 & Above	-	0.2	*	0.6	0.1	0.3	-	*	-	0.7	*	*
Average	4.46	4.41	4.73	4.71	4.20	4.39	-	4.27	-	4.71	4.33	4.42

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 18, 2024

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	-	20.7	-	0.1	-	*	-	*	3.4	1.1	-	8.7
Bark - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	-	1.1	-	*	-	0.1	-	*	3.4	0.3	-	0.2
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	-	-	*	-	*	-	-	-	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	*	-	*	-	*	-	*	*	*	-	0.6
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	*	-	*	-	*	-	*	-	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	-	-	-	*	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	-	*	-	*	-	*	-	*	*	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	*	-	-	-	-	-	*	-	-	-	-
23	-	0.1	-	-	-	*	-	*	-	-	-	-
24	-	0.1	-	*	-	*	-	*	-	*	-	-
25	-	0.6	-	*	*	*	-	*	0.1	*	-	*
26	-	1.2	-	0.5	0.1	0.1	-	0.2	0.6	0.1	-	*
27	-	2.5	-	2.1	0.9	0.6	-	1.0	0.1	0.9	-	0.5
28	-	3.9	-	4.6	7.2	5.8	-	4.1	2.9	4.7	-	3.2
29	-	7.9	-	10.3	69.2	27.4	-	13.1	15.4	15.4	-	16.5
30	-	13.2	-	22.4	21.7	40.4	-	25.6	27.3	26.3	-	26.3
31	-	19.6	-	29.6	0.9	19.3	-	28.9	23.3	26.5	-	21.1
32	-	20.0	-	19.6	*	5.1	-	16.8	17.4	16.2	-	18.3
33	-	15.1	-	7.8	-	1.1	-	6.9	9.3	7.0	-	11.0
34	-	10.2	-	1.9	-	0.3	-	2.4	2.6	2.2	-	2.1
35	-	4.6	-	0.8	-	0.1	-	0.7	0.7	0.5	-	0.3
36	-	0.7	-	0.3	-	*	-	0.2	0.1	0.1	-	0.2
37	-	0.1	-	*	-	*	-	*	-	*	-	0.1
38	-	*	-	*	-	-	-	-	-	-	-	0.2
39	-	*	-	-	-	-	-	-	-	-	-	0.1
40 & Above	-	-	-	-	-	-	-	-	-	-	-	*
Average	-	31.87	-	31.22	29.61	30.38	-	31.17	31.20	31.09	-	31.25
Mike												
2.4 & Below	-	0.1	-	-	-	-	-	-	-	-	-	-
2.5	-	0.5	-	-	-	-	-	-	-	*	-	-
2.6	-	0.5	-	-	-	-	-	*	-	*	-	-
2.7	-	1.1	-	-	-	*	-	*	-	*	-	*
2.8	-	1.4	-	-	-	*	-	*	-	*	-	*
2.9	-	1.9	-	-	-	*	-	*	-	*	-	*
3.0	-	3.0	-	*	-	*	-	*	-	*	-	-
3.1	-	3.5	-	*	-	*	-	*	-	*	-	0.1
3.2	-	4.4	-	*	-	*	-	*	*	*	-	0.2
3.3	-	4.6	-	*	-	*	-	*	*	*	-	0.2
3.4	-	6.2	-	*	-	*	-	*	0.3	0.1	-	1.2
3.5	-	7.5	-	*	-	0.1	-	0.1	0.3	0.1	-	1.6
3.6	-	7.5	-	*	-	0.1	-	0.1	0.9	0.2	-	1.9
3.7	-	8.2	-	0.1	*	0.2	-	0.2	1.8	0.3	-	1.5
3.8	-	8.2	-	0.2	0.1	0.5	-	0.3	1.8	0.6	-	2.0
3.9	-	8.7	-	0.5	*	1.0	-	0.5	4.1	1.0	-	2.4
4.0	-	7.6	-	1.0	3.4	1.9	-	0.7	4.8	1.6	-	4.8
4.1	-	6.1	-	1.9	9.3	3.2	-	1.1	3.7	2.2	-	6.2
4.2	-	4.9	-	3.3	7.0	5.2	-	1.9	4.8	3.0	-	5.9
4.3	-	4.8	-	4.8	10.9	8.0	-	2.9	7.4	4.1	-	9.9
4.4	-	3.6	-	6.2	17.8	11.5	-	4.2	12.4	5.3	-	11.6
4.5	-	2.8	-	8.0	26.4	14.1	-	6.2	15.2	7.0	-	8.1
4.6	-	1.3	-	10.8	15.8	15.3	-	8.5	11.9	8.0	-	10.7
4.7	-	0.9	-	12.0	9.0	13.9	-	10.2	9.5	9.5	-	10.8
4.8	-	0.4	-	12.7	*	10.6	-	12.2	8.4	10.4	-	7.0
4.9	-	0.2	-	9.9	0.1	6.9	-	13.6	6.8	11.0	-	4.6
5.0	-	*	-	9.0	*	4.0	-	12.2	2.8	10.9	-	4.5
5.1	-	*	-	6.7	-	1.9	-	9.5	1.0	9.5	-	2.7
5.2	-	-	-	5.2	-	0.9	-	6.9	1.2	7.2	-	1.5
5.3	-	-	-	3.4	-	0.3	-	4.4	0.7	4.4	-	0.6
5.4	-	-	-	2.4	-	0.1	-	2.5	0.1	2.2	-	0.1
5.5 & Above	-	-	-	2.0	-	0.1	-	1.9	0.1	1.6	-	-
Average	-	3.73	-	4.76	4.42	4.57	-	4.83	4.47	4.78	-	4.44

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE										
For The Week Ending Jan 18, 2024										
Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter										
Bark - Level 1	-	6.0	4.0	3.4	-	*	28.9	8.2	0.2	0.3
Bark - Level 2	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	-	0.3	0.6	0.5	-	*	0.1	0.2	-	0.1
Grass - Level 2	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	-	*	*	-	-	-	*	-	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	*	-	*	-	-	*	0.3	-	*
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	-	-	-	-	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	*	-	-	-	*	-	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	-	*	*	*	-	*	*	0.1	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/										
22 & Below	-	0.1	-	-	-	-	-	0.2	-	-
23	-	0.3	-	-	-	*	0.3	0.3	-	-
24	-	0.6	*	*	-	*	0.3	0.6	-	*
25	-	1.3	0.1	*	-	*	0.6	1.4	-	*
26	-	2.0	0.1	0.1	-	0.1	2.2	3.2	-	0.2
27	-	3.5	1.2	0.7	-	1.1	10.7	6.1	0.1	2.2
28	-	6.5	6.7	4.0	-	8.2	11.3	10.2	5.3	15.0
29	-	9.5	26.5	16.4	-	28.9	10.9	14.4	20.0	33.5
30	-	12.9	30.3	32.3	-	39.5	15.3	16.4	58.9	28.1
31	-	12.8	18.9	26.6	-	18.2	15.5	15.6	15.3	15.4
32	-	11.8	10.6	13.2	-	3.5	13.9	12.8	0.3	4.4
33	-	15.3	4.4	5.5	-	0.5	9.1	9.3	-	1.0
34	-	15.3	0.8	1.0	-	0.1	7.2	5.4	-	0.3
35	-	6.8	0.3	0.2	-	*	2.2	2.7	0.1	0.1
36	-	1.2	*	*	-	*	0.4	1.0	-	*
37	-	0.2	-	*	-	*	*	0.3	-	-
38	-	*	-	-	-	-	*	*	-	-
39	-	*	-	-	-	-	-	*	-	-
40 & Above	-	-	-	-	-	-	-	*	-	-
Average	-	31.76	30.58	30.93	-	30.23	30.77	30.77	30.27	30.03
Mike										
2.4 & Below	-	*	-	-	-	-	-	*	-	-
2.5	-	*	-	-	-	-	-	*	-	-
2.6	-	*	-	-	-	*	-	0.1	-	*
2.7	-	*	*	*	-	*	-	0.1	-	*
2.8	-	*	-	*	-	*	-	0.1	-	*
2.9	-	0.1	-	*	-	*	*	0.2	-	*
3.0	-	0.2	*	*	-	*	*	0.2	-	*
3.1	-	0.3	-	*	-	0.1	0.2	0.3	-	*
3.2	-	0.4	0.4	0.1	-	0.1	0.4	0.5	-	*
3.3	-	0.7	0.5	0.2	-	0.2	0.5	0.7	-	0.1
3.4	-	1.1	0.3	0.3	-	0.3	0.7	0.9	1.4	0.2
3.5	-	1.5	0.3	0.4	-	0.5	0.9	1.2	1.8	0.4
3.6	-	1.9	0.9	0.7	-	1.0	1.7	1.5	0.4	0.5
3.7	-	2.7	2.1	1.1	-	1.6	2.6	2.0	-	0.9
3.8	-	3.5	3.6	1.8	-	2.4	3.5	2.6	-	1.5
3.9	-	5.7	5.3	2.7	-	3.7	3.7	3.3	-	2.2
4.0	-	7.6	6.6	4.0	-	5.7	4.8	4.1	-	3.2
4.1	-	8.7	8.0	5.8	-	7.9	6.9	5.2	0.2	4.9
4.2	-	9.7	10.8	8.0	-	10.8	6.5	6.6	0.8	6.8
4.3	-	10.7	10.0	10.0	-	14.1	7.6	7.9	1.4	8.6
4.4	-	9.6	13.3	10.8	-	15.1	7.8	8.9	3.6	10.2
4.5	-	10.0	12.9	10.8	-	12.8	8.8	9.6	10.8	11.2
4.6	-	8.1	11.1	11.2	-	10.0	9.7	9.7	11.1	12.3
4.7	-	5.5	7.3	9.9	-	6.7	9.6	9.2	16.0	11.5
4.8	-	4.7	4.2	8.0	-	3.9	8.4	8.0	18.7	9.9
4.9	-	3.3	1.4	5.8	-	1.6	6.2	6.2	8.8	6.6
5.0	-	2.3	0.6	3.9	-	1.0	2.9	4.3	6.3	4.5
5.1	-	1.1	0.4	2.4	-	0.4	2.4	2.8	7.5	2.3
5.2	-	0.4	0.1	1.3	-	0.1	1.5	1.7	8.4	1.2
5.3	-	0.1	*	0.6	-	*	0.5	1.0	2.8	0.6
5.4	-	*	*	0.2	-	*	0.2	0.6	-	0.2
5.5 & Above	-	*	-	0.1	-	*	2.1	0.5	0.1	0.2
Average	-	4.29	4.32	4.48	-	4.34	4.44	4.44	4.75	4.52

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
 * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE												
For The Week Ending Jan 18, 2024												
Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	*	-	-	-	-	-	-	-	-	-	*
2.5 - 2.6	-	*	-	*	-	*	-	*	-	-	*	*
2.7 - 2.9	0.1	0.1	-	*	0.7	0.2	-	*	-	-	0.3	*
3.0 - 3.2	0.1	0.5	-	*	2.1	0.8	-	0.2	-	*	0.6	0.2
3.3 - 3.4	0.3	0.8	-	*	2.2	1.3	-	0.6	-	0.1	1.3	0.4
3.5 - 3.6	0.6	1.8	-	0.1	5.3	2.3	-	1.6	-	0.3	3.1	1.0
3.7 - 4.2	25.2	30.1	2.4	5.7	42.6	30.2	-	51.0	-	9.0	34.9	26.7
4.3 - 4.9	70.6	58.3	84.5	73.4	45.2	57.8	-	40.5	-	66.4	55.9	67.7
5.0 - 5.2	2.3	7.2	13.0	17.4	1.8	5.7	-	5.7	-	20.4	3.6	3.9
5.3 & Above	0.8	1.3	0.1	3.4	0.2	1.6	-	0.3	-	3.8	0.3	0.2
Average	4.46	4.41	4.73	4.71	4.20	4.39	-	4.27	-	4.71	4.33	4.42
Leaf												
1 - 2	24.6	20.3	34.2	21.1	63.8	79.9	-	68.0	-	9.4	5.9	10.8
3	56.7	50.9	52.4	49.6	30.3	17.1	-	21.3	-	50.2	44.5	50.2
4	15.9	23.3	13.0	24.1	4.5	2.6	-	8.4	-	32.4	36.8	30.6
5	2.4	4.8	0.3	4.8	1.1	0.3	-	2.1	-	7.0	10.7	7.1
6	0.4	0.7	-	0.4	0.2	*	-	0.3	-	0.8	1.8	1.1
7	0.1	0.1	-	*	*	*	-	-	-	0.1	0.3	0.2
8	-	*	-	*	*	*	-	-	-	*	-	*
Average	2.97	3.14	2.79	3.13	2.30	1.93	-	2.22	-	3.40	3.59	3.38
HVI Trash 1/												
00	-	-	-	*	-	*	-	*	-	-	-	*
01	3.2	3.9	3.6	3.7	27.4	45.8	-	35.0	-	0.9	0.3	1.2
02	29.9	21.8	31.5	21.3	41.8	36.5	-	34.6	-	12.1	8.2	13.9
03	32.9	28.3	32.2	26.5	19.4	11.4	-	14.1	-	25.3	21.3	26.3
04	18.4	21.4	21.7	20.6	6.6	3.9	-	6.6	-	25.3	24.0	24.2
05	9.0	12.5	8.3	13.2	2.1	1.4	-	4.3	-	17.5	19.0	16.2
06	4.0	6.3	2.2	7.5	1.2	0.5	-	2.6	-	10.0	12.1	9.1
07	1.5	3.0	0.4	3.8	0.7	0.2	-	1.4	-	5.0	7.2	4.7
08	0.6	1.4	*	1.8	0.4	0.1	-	0.6	-	2.2	3.8	2.3
09	0.2	0.7	0.1	0.8	0.2	*	-	0.3	-	1.0	2.0	1.1
10	0.1	0.3	-	0.4	0.1	*	-	0.2	-	0.4	1.1	0.5
11	0.1	0.1	-	0.2	*	*	-	0.1	-	0.2	0.4	0.2
12	*	0.1	-	0.1	-	*	-	*	-	0.1	0.3	0.1
13	-	*	-	*	*	*	-	*	-	*	0.1	0.1
14	*	*	-	*	*	*	-	*	-	*	0.1	*
15	-	*	-	*	*	*	-	-	-	*	*	*
16	-	*	-	*	-	*	-	-	-	*	*	*
17	-	*	-	*	-	*	-	-	-	-	*	*
18 & Above	-	*	-	*	*	*	-	-	-	*	*	*
Average	0.32	0.36	0.31	0.38	0.23	0.18	-	0.23	-	0.42	0.46	0.41
UNIFORMITY 2/												
74 & Below	-	*	-	-	-	-	-	-	-	*	-	*
75	-	*	-	*	-	*	-	-	-	-	-	*
76	-	*	-	*	*	*	-	-	-	*	*	*
77	*	0.1	-	*	0.6	0.2	-	*	-	0.1	0.1	0.2
78	*	0.7	0.2	0.1	1.9	2.1	-	0.6	-	0.7	1.0	1.2
79	0.6	4.5	3.0	1.1	6.6	9.0	-	6.3	-	3.9	4.9	7.2
80	6.1	17.1	23.1	8.5	17.0	22.8	-	28.5	-	16.1	18.4	24.3
81	23.3	33.3	43.6	20.9	35.6	32.5	-	23.7	-	33.7	36.1	36.8
82	49.8	32.4	16.7	33.7	29.0	24.7	-	15.5	-	32.4	29.0	22.8
83	20.0	10.8	12.7	28.3	8.0	7.8	-	13.6	-	11.7	8.9	6.4
84	0.2	1.1	0.2	6.4	1.1	0.8	-	10.6	-	1.3	1.4	0.9
85 & Above	*	0.1	0.4	0.9	0.1	*	-	1.2	-	*	0.2	0.1
Average	82.29	81.74	81.58	82.47	81.55	81.40	-	81.81	-	81.78	81.65	81.40
Tenderable 3/	90.0	86.9	86.8	78.5	92.8	89.0	-	91.5	-	67.7	80.2	90.4
SAMPLES CLASSED	10,495	690,970	2,118	1,439,025	10,692	167,989	-	51,463	-	92,319	65,042	2,056,429

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 18, 2024

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	0.1	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	-	1.0	-	-	-	-	-	*	-	*	-	-
2.7 - 2.9	-	4.4	-	-	-	*	-	*	-	*	-	*
3.0 - 3.2	-	11.0	-	*	-	*	-	0.1	*	*	-	0.3
3.3 - 3.4	-	10.8	-	*	-	0.1	-	0.1	0.3	0.1	-	1.4
3.5 - 3.6	-	15.0	-	*	-	0.2	-	0.2	1.2	0.3	-	3.5
3.7 - 4.2	-	43.7	-	6.9	19.9	12.0	-	4.6	21.1	8.6	-	22.7
4.3 - 4.9	-	14.0	-	64.3	80.1	80.4	-	57.6	71.7	55.2	-	62.7
5.0 - 5.2	-	*	-	20.9	*	6.8	-	28.6	4.9	27.6	-	8.7
5.3 & Above	-	-	-	7.8	-	0.6	-	8.9	0.8	8.1	-	0.7
Average	-	3.73	-	4.76	4.42	4.57	-	4.83	4.47	4.78	-	4.44
Leaf												
1 - 2	-	11.0	-	15.2	21.3	31.1	-	15.9	9.3	14.7	-	69.4
3	-	27.1	-	49.4	64.1	54.5	-	52.3	39.6	54.9	-	22.7
4	-	26.5	-	28.4	13.0	13.2	-	25.4	40.8	26.1	-	6.3
5	-	19.7	-	6.3	1.6	1.1	-	5.6	9.6	3.9	-	1.4
6	-	11.0	-	0.6	-	*	-	0.7	0.7	0.3	-	0.3
7	-	3.9	-	0.1	-	*	-	0.1	*	*	-	-
8	-	0.7	-	*	-	-	-	*	-	-	-	-
Average	-	4.06	-	3.27	2.95	2.83	-	3.23	3.52	3.20	-	2.13
HVI Trash 1/												
00	-	-	-	-	-	*	-	*	-	*	-	0.1
01	-	3.6	-	2.6	1.9	5.3	-	2.0	1.3	1.8	-	37.1
02	-	10.9	-	16.3	28.1	28.9	-	18.8	10.4	15.6	-	32.7
03	-	14.1	-	25.5	37.7	31.4	-	28.2	16.5	27.0	-	15.2
04	-	13.5	-	22.6	18.4	19.2	-	22.3	21.2	24.5	-	7.0
05	-	12.1	-	15.5	7.7	9.2	-	13.7	19.3	15.8	-	3.7
06	-	10.2	-	9.0	3.6	3.7	-	7.5	13.6	8.4	-	2.1
07	-	8.8	-	4.6	1.8	1.4	-	3.9	9.2	3.9	-	1.0
08	-	7.2	-	2.2	0.4	0.5	-	1.9	4.8	1.7	-	0.5
09	-	5.7	-	1.0	0.3	0.2	-	0.9	2.3	0.7	-	0.2
10	-	4.4	-	0.5	0.1	0.1	-	0.4	0.9	0.3	-	0.2
11	-	3.3	-	0.2	-	*	-	0.2	0.3	0.1	-	0.1
12	-	2.4	-	0.1	-	*	-	0.1	0.2	0.1	-	*
13	-	1.6	-	*	-	*	-	*	0.1	*	-	-
14	-	1.0	-	*	-	*	-	*	*	*	-	-
15	-	0.6	-	-	-	*	-	*	*	*	-	-
16	-	0.3	-	-	-	*	-	*	-	*	-	-
17	-	0.2	-	-	-	*	-	*	-	*	-	-
18 & Above	-	0.3	-	-	-	*	-	*	-	*	-	-
Average	-	0.58	-	0.40	0.32	0.32	-	0.39	0.47	0.39	-	0.22
UNIFORMITY 2/												
74 & Below	-	*	-	-	-	-	-	-	-	-	-	-
75	-	0.1	-	-	-	*	-	-	-	*	-	-
76	-	1.0	-	-	-	*	-	*	-	*	-	-
77	-	5.1	-	*	-	*	-	*	*	*	-	0.1
78	-	16.7	-	0.5	0.2	0.1	-	0.3	*	0.2	-	1.1
79	-	28.4	-	3.1	2.7	0.9	-	1.7	0.4	1.8	-	5.0
80	-	24.7	-	10.8	6.7	9.1	-	7.9	12.2	11.7	-	18.8
81	-	16.4	-	30.7	22.3	23.5	-	22.3	33.3	30.0	-	43.9
82	-	6.9	-	35.2	43.2	36.1	-	37.7	36.9	36.5	-	26.7
83	-	0.6	-	17.8	24.5	25.6	-	23.9	14.3	17.6	-	4.3
84	-	*	-	1.9	0.1	4.4	-	5.7	2.7	2.1	-	0.2
85 & Above	-	-	-	0.1	0.2	0.4	-	0.4	0.2	0.1	-	-
Average	-	79.95	-	82.03	82.27	82.36	-	82.37	82.07	82.07	-	81.48
Tenderable 3/	-	41.5	-	63.8	99.9	92.4	-	61.0	85.5	62.5	-	81.0
SAMPLES CLASSED	-	117,236	-	207,195	2,345	780,216	-	833,008	4,829	747,047	-	15,543

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE										
For The Week Ending Jan 18, 2024										
Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE										
2.4 & Below	-	*	-	-	-	-	-	*	-	-
2.5 - 2.6	-	*	-	-	-	*	-	0.1	-	*
2.7 - 2.9	-	0.2	*	*	-	*	*	0.4	-	*
3.0 - 3.2	-	0.9	0.4	0.1	-	0.2	0.6	1.1	-	0.1
3.3 - 3.4	-	1.8	0.8	0.5	-	0.5	1.2	1.6	1.4	0.4
3.5 - 3.6	-	3.4	1.2	1.1	-	1.5	2.6	2.7	2.2	0.9
3.7 - 4.2	-	37.9	36.4	23.4	-	32.0	28.0	23.8	1.0	19.4
4.3 - 4.9	-	51.9	60.2	66.6	-	64.2	58.1	59.4	70.4	70.3
5.0 - 5.2	-	3.8	1.1	7.6	-	1.6	6.8	8.8	22.2	8.0
5.3 & Above	-	0.2	0.1	0.9	-	*	2.7	2.1	2.9	1.0
Average	-	4.29	4.32	4.48	-	4.34	4.44	4.44	4.75	4.52
Leaf										
1 - 2	-	44.0	2.6	8.0	-	42.5	43.7	49.2	32.8	29.8
3	-	40.8	36.5	44.6	-	46.2	36.3	37.8	52.5	59.8
4	-	11.5	47.0	37.3	-	10.2	11.8	9.9	13.2	9.7
5	-	2.7	12.7	9.0	-	1.1	4.2	2.2	1.5	0.7
6	-	0.8	1.2	1.0	-	0.1	3.1	0.6	-	*
7	-	0.2	*	0.1	-	*	0.9	0.2	-	-
8	-	*	-	-	-	-	0.1	0.1	-	-
Average	-	2.67	3.74	3.50	-	2.66	2.78	2.58	2.83	2.80
HVI Trash 1/										
00	-	0.1	-	-	-	*	0.1	0.1	-	-
01	-	15.7	0.1	0.9	-	11.1	19.3	18.0	4.0	3.4
02	-	31.0	4.0	9.1	-	34.6	30.7	34.5	29.9	29.0
03	-	24.1	15.1	20.0	-	27.6	20.7	23.2	35.9	35.9
04	-	13.9	24.0	24.0	-	14.8	11.8	12.2	16.3	19.8
05	-	7.0	22.3	19.6	-	7.0	6.2	5.9	8.6	7.9
06	-	3.6	16.2	12.8	-	3.0	3.1	2.8	3.5	2.8
07	-	1.9	9.3	7.1	-	1.2	2.0	1.4	1.2	0.9
08	-	1.0	5.1	3.6	-	0.5	1.6	0.8	0.7	0.3
09	-	0.7	2.2	1.6	-	0.2	1.3	0.4	-	0.1
10	-	0.4	1.0	0.8	-	0.1	1.0	0.3	-	*
11	-	0.2	0.4	0.3	-	*	0.8	0.2	0.1	*
12	-	0.2	0.1	0.1	-	*	0.6	0.1	-	*
13	-	0.1	*	0.1	-	*	0.4	0.1	-	*
14	-	0.1	*	*	-	*	0.3	*	-	-
15	-	*	*	*	-	*	0.1	*	-	-
16	-	*	*	*	-	*	0.1	*	-	-
17	-	*	-	*	-	*	*	*	-	-
18 & Above	-	*	-	*	-	-	*	*	-	-
Average	-	0.30	0.50	0.46	-	0.29	0.32	0.28	0.31	0.31
UNIFORMITY 2/										
74 & Below	-	*	-	-	-	-	-	*	-	-
75	-	0.1	-	-	-	*	0.1	0.1	-	-
76	-	0.6	-	*	-	*	1.0	0.7	-	-
77	-	2.5	*	*	-	*	4.9	2.6	-	*
78	-	8.0	0.1	0.2	-	0.1	16.4	7.7	-	0.2
79	-	14.8	2.9	2.0	-	1.0	30.3	17.0	-	2.0
80	-	21.7	17.0	13.9	-	6.6	25.9	27.1	0.1	13.2
81	-	25.2	36.9	37.7	-	24.1	16.8	28.0	28.8	33.1
82	-	22.3	31.4	32.2	-	44.4	4.4	13.8	50.1	35.5
83	-	4.8	10.3	12.5	-	22.1	0.3	2.6	20.7	14.5
84	-	0.1	1.2	1.4	-	1.7	*	0.3	0.2	1.4
85 & Above	-	*	*	0.1	-	0.1	-	*	-	0.1
Average	-	80.88	81.77	81.88	-	82.30	79.91	80.66	82.34	81.96
Tenderable 3/	-	79.6	91.4	85.8	-	97.5	49.7	72.3	66.7	89.8
SAMPLES CLASSED	-	138,813	14,089	315,734	-	657,268	12,062	2,711,603	1,037	186,301

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE									
For The Week Ending Jan 18, 2024									
Color Grade	Leaf	Arizona		California		New Mexico		Texas	
		Week	Season	Week	Season	Week	Season	Week	Season
01	1	87.5	74.7	5.8	6.0	-	28.9	13.1	11.1
	2	10.5	15.1	19.3	12.3	-	30.3	19.4	16.2
	3	-	1.0	0.1	0.5	-	1.1	0.5	0.9
	4	-	*	-	-	-	*	-	*
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		98.1	90.8	25.2	18.8	-	60.3	33.0	28.2
02	1	1.2	4.0	6.5	7.4	-	6.1	4.4	8.9
	2	0.6	3.9	57.2	49.2	-	22.6	43.7	43.5
	3	-	0.9	3.9	11.6	-	6.4	14.4	9.6
	4	-	0.2	-	0.7	-	0.3	0.2	0.3
	5	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	*	-	-	-	*
Total -----		1.9	9.0	67.5	68.9	-	35.4	62.7	62.3
03	1	0.1	*	*	0.1	-	*	0.1	*
	2	-	0.1	2.4	3.3	-	1.2	2.0	3.3
	3	-	*	3.2	5.2	-	2.7	1.3	4.5
	4	-	*	0.2	1.6	-	0.4	0.5	0.6
	5	-	-	-	0.1	-	-	-	*
	6	-	-	-	*	-	-	-	-
	7	-	-	-	*	-	-	-	-
Total -----		0.1	0.1	5.9	10.3	-	4.3	3.8	8.4
04	1	-	-	-	*	-	-	-	-
	2	-	*	0.1	0.1	-	*	-	0.1
	3	-	*	0.6	0.5	-	*	0.1	0.5
	4	-	-	0.4	0.6	-	*	0.2	0.5
	5	-	-	*	0.2	-	-	-	*
	6	-	-	-	0.1	-	-	-	-
	7	-	-	-	*	-	-	-	-
Total -----		-	*	1.1	1.5	-	0.1	0.3	1.1
05	1	-	-	-	-	-	-	-	-
	2	-	*	-	*	-	-	-	-
	3	-	*	*	*	-	-	-	*
	4	-	-	0.1	0.1	-	*	0.1	0.1
	5	-	-	0.1	*	-	-	0.1	*
	6	-	-	-	0.1	-	-	-	-
	7	-	-	-	0.2	-	-	-	-
Total -----		-	0.1	0.2	0.5	-	*	0.2	0.1
06	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-
	4	-	-	-	*	-	-	-	*
	5	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	0.1	-	-	-	-
Total -----		-	-	-	0.1	-	-	-	*
07	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-
	4	-	-	-	*	-	-	-	-
	5	-	-	-	*	-	-	-	-
	6	-	-	*	*	-	-	-	-
	7	-	-	-	*	-	-	-	-
Total -----		-	-	*	*	-	-	-	-
STAPLE									
44 & Shorter		-	*	-	0.5	-	0.6	6.8	6.9
46		0.1	1.3	*	6.2	-	9.3	0.2	27.2
48		58.5	61.7	6.1	27.5	-	65.0	36.0	42.3
50		41.0	35.9	64.1	51.1	-	23.4	55.5	23.4
52 & Longer		0.4	1.1	29.8	14.7	-	1.6	1.5	0.2
Average Staple		48.84	48.74	50.47	49.47	-	48.32	48.76	47.64
Average Length		1.42	1.42	1.46	1.44	-	1.40	1.42	1.38
EXTRANEIOUS MATTER									
Bark		-	-	-	*	-	0.3	1.5	0.3
Grass		-	-	*	0.1	-	0.2	0.5	0.1
Spindle Twist		-	*	0.5	0.3	-	*	-	*
Preparation		-	*	-	*	-	-	-	*
All Other		-	*	-	*	-	*	-	0.2

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 18, 2024

Quality Designation	Arizona		California		New Mexico		Texas	
	Week	Season	Week	Season	Week	Season	Week	Season
MIKE								
2.4 & Below	-	-	-	*	-	-	-	-
2.5 - 2.6	-	*	*	0.2	-	-	-	-
2.7 - 2.9	-	0.1	1.6	0.8	-	0.1	-	*
3.0 - 3.2	-	*	0.6	2.0	-	0.2	-	*
3.3 - 3.4	-	0.6	0.8	4.0	-	3.5	-	1.0
3.5 - 3.6	7.1	5.2	2.3	12.2	-	10.2	-	7.3
3.7 - 4.2	91.0	93.3	91.2	75.8	-	75.5	56.3	73.2
4.3 - 4.9	1.9	0.8	3.5	5.0	-	10.5	43.7	18.4
5.0 - 5.2	-	-	*	*	-	-	-	-
5.3 & Above	-	-	-	*	-	-	-	-
Average	3.94	3.91	3.94	3.86	-	3.94	4.23	4.02
ALL RANGE MIKE								
2.4 & Below	-	-	-	*	-	-	-	-
2.5	-	-	*	*	-	-	-	-
2.6	-	*	-	0.2	-	-	-	-
2.7	-	*	0.5	0.2	-	*	-	-
2.8	-	0.1	0.6	0.3	-	*	-	*
2.9	-	*	0.5	0.3	-	*	-	-
3.0	-	-	0.4	0.4	-	*	-	*
3.1	-	*	-	0.6	-	*	-	-
3.2	-	*	0.2	1.0	-	0.2	-	*
3.3	-	*	0.5	1.5	-	0.9	-	0.4
3.4	-	0.5	0.3	2.5	-	2.6	-	0.6
3.5	1.1	1.8	0.5	4.5	-	4.2	-	3.6
3.6	6.0	3.4	1.8	7.7	-	6.0	-	3.7
3.7	5.6	8.3	5.3	10.3	-	8.1	-	6.0
3.8	14.1	16.6	13.1	13.6	-	11.5	1.4	9.5
3.9	29.1	26.7	22.4	15.7	-	15.8	1.0	15.1
4.0	15.8	25.6	24.7	16.0	-	15.3	5.2	12.0
4.1	15.3	12.1	17.8	12.7	-	13.6	26.9	15.2
4.2	11.1	3.9	7.8	7.4	-	11.2	21.8	15.3
4.3	1.4	0.7	2.5	3.3	-	6.1	20.5	12.8
4.4	0.5	0.1	0.7	1.3	-	3.1	17.1	4.0
4.5	-	*	0.2	0.3	-	1.0	3.2	1.4
4.6	-	*	0.1	0.1	-	0.3	2.9	0.3
4.7	-	-	*	*	-	*	-	*
4.8	-	-	-	*	-	*	-	-
4.9	-	-	-	*	-	*	-	-
5.0	-	-	*	*	-	-	-	-
5.1	-	-	-	*	-	-	-	-
5.2	-	-	-	*	-	-	-	-
5.3 & Above	-	-	-	*	-	-	-	-
Average	3.94	3.91	3.94	3.86	-	3.94	4.23	4.02
STRENGTH 1/								
36 & Below	-	0.1	1.4	2.6	-	12.4	6.8	3.8
37	-	0.8	0.3	3.9	-	11.8	-	8.8
38	-	4.7	0.6	5.9	-	7.9	0.1	13.6
39	0.5	4.6	2.3	5.8	-	3.9	0.1	18.1
40	4.1	10.2	5.5	7.5	-	2.8	3.3	8.5
41	12.5	27.8	13.2	11.8	-	7.3	11.1	6.3
42	28.4	28.4	22.0	17.0	-	15.6	7.1	12.1
43	30.4	15.0	22.6	16.8	-	19.0	9.2	12.2
44	15.7	5.7	17.6	13.8	-	12.4	29.5	8.2
45	6.1	2.1	9.4	9.7	-	5.3	15.9	5.2
46	1.6	0.3	3.7	3.8	-	1.3	11.3	2.1
47	0.7	0.2	1.2	1.1	-	0.2	5.5	0.9
48 & Above	0.1	*	0.4	0.3	-	0.1	0.1	0.2
Average	43.12	41.97	43.10	42.37	-	41.21	43.41	40.99
UNIFORMITY								
83 & Below	-	*	0.3	0.6	-	0.1	0.2	0.1
84	-	0.5	2.6	4.1	-	3.1	4.4	4.8
85	9.3	14.3	14.2	18.1	-	32.8	4.6	34.3
86	53.1	57.5	41.8	49.4	-	44.5	38.8	39.7
87	37.5	27.5	34.0	26.3	-	19.4	51.5	20.6
88 & Above	0.1	0.3	7.0	1.6	-	0.2	0.5	0.4
Average	86.67	86.56	86.73	86.47	-	86.27	86.88	86.22
Samples Classed	1,445	11,790	5,246	214,036	-	28,672	1,301	19,839

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.