



Volume 26, No.21

State	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
AL	17	83.3	69.6	55,640	23	80.1	67.5	495,533
AR	26	88.5	70.3	143,915	26	85.4	67.9	1,443,468
AZ	9	88.9	74.4	22,559	9	86.3	68.6	75,097
CA	4	68.1	52.2	2,540	8	79.9	55.5	28,640
FL	4	64.9	40.6	13,773	4	78.2	58.6	78,774
GA	55	76.4	56.6	188,483	55	79.1	59.9	1,082,253
KS	3	51.5	31.9	17,606	3	68.8	43.4	86,675
LA	9	66.2	50.2	4,857	15	78.3	56.3	309,370
MO	19	95.4	82.0	74,568	19	90.9	77.7	693,440
MS	29	77.6	54.3	72,471	33	78.2	56.7	1,077,391
NC	31	93.0	79.3	110,887	31	93.0	80.4	554,275
NM	2	99.0	90.1	1,743	4	97.8	86.6	10,419
OK	10	67.1	51.4	13,374	10	84.8	70.3	107,721
SC	11	87.6	69.4	35,046	11	87.5	70.3	208,347
TN	13	94.3	80.3	40,957	18	86.0	77.7	507,232
TX	111	72.4	51.1	275,254	152	78.8	59.2	2,827,924
VA	4	97.4	87.8	29,229	4	97.6	89.9	129,711
United States	357	81.5	63.3	1,102,902	425	82.3	64.8	9,716,270
AMERICAN PIMA								
AZ	2			1,303	2			4,186
CA	11			33,385	11			172,335
NM*	-			-	3			11,072
TX	3			3,036	3			12,580
United States	17			40,848	19			200,173
United States all cotton	372			1,143,750	437			9,916,443

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 05, 2024

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	2.3	2.5	1.5	1.0	90.5	81.7	89.7	61.5	0.2	0.7	1.9	2.8
	3	2.9	1.9	1.4	0.7	2.6	7.6	5.8	14.9	0.1	0.4	1.3	1.5
	4	0.1	0.1	*	*	*	0.1	*	2.4	-	*	*	*
	5	-	*	-	*	-	-	-	*	-	-	-	*
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	5.3	4.5	3.0	1.7	93.1	89.5	95.6	78.9	0.3	1.1	3.2	4.4
31	1 - 2	4.8	5.9	7.1	4.0	4.8	3.3	2.1	5.4	2.1	3.6	5.2	8.9
	3	20.7	24.8	20.7	16.2	1.3	2.3	1.0	2.4	11.8	21.7	13.0	27.7
	4	6.1	5.8	3.6	4.4	0.1	0.5	0.1	2.6	1.5	6.0	1.9	4.4
	5	0.2	0.2	0.1	0.2	*	0.1	-	0.7	*	0.2	*	0.1
	6	-	*	*	*	-	*	-	0.1	-	-	*	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	31.7	36.8	31.5	24.7	6.2	6.2	3.2	11.2	15.4	31.5	20.2	41.2
41	1 - 2	2.1	1.5	4.9	2.8	0.1	*	0.1	0.1	0.7	0.9	2.4	1.6
	3	20.9	19.2	33.9	32.6	*	*	-	*	11.7	18.7	23.9	20.9
	4	14.2	15.8	15.7	22.0	-	*	-	*	10.2	22.6	15.2	13.4
	5	1.6	2.5	2.2	3.5	*	*	-	*	1.1	3.9	1.7	1.5
	6	0.1	0.1	0.4	0.4	*	*	-	*	*	0.2	*	*
	7	-	*	-	*	-	*	-	-	-	*	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	38.9	39.1	57.1	61.2	0.1	0.1	0.1	0.2	23.7	46.3	43.2	37.4
51	1 - 2	0.6	0.1	*	0.1	-	-	-	-	0.2	0.1	0.8	0.2
	3	6.6	1.6	1.9	2.1	-	-	-	-	7.0	1.9	9.4	2.6
	4	5.4	1.6	2.1	2.2	-	*	-	-	24.1	6.1	9.1	2.8
	5	1.3	0.5	0.5	0.6	-	-	-	-	7.3	1.8	2.2	0.7
	6	0.1	0.1	0.1	0.2	-	-	-	-	0.3	0.1	0.2	0.1
	7	*	*	-	*	-	-	-	-	-	*	*	*
	8	-	-	-	-	-	-	-	-	-	-	*	*
Total	----	14.0	3.9	4.7	5.1	-	*	-	-	38.9	10.0	21.7	6.4
61	1 - 2	*	*	-	-	-	-	-	-	-	-	*	*
	3	*	*	*	*	-	-	-	-	*	*	*	*
	4	0.1	*	*	*	-	-	-	-	0.6	0.1	*	*
	5	*	*	*	*	-	-	-	-	0.5	0.1	*	*
	6	-	*	*	*	-	-	-	-	0.1	*	*	*
	7	-	*	-	*	-	-	-	-	-	-	-	*
	8	*	*	-	-	-	-	-	-	-	-	-	-
Total	----	0.1	*	*	*	-	-	-	-	1.2	0.2	*	*
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	*	-	-	-	-	-	-	-	-	-	-
	6	*	*	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	-	*	-	-	-	-	-	-	-	-
12 & 22	1 - 2	-	*	*	*	0.5	2.5	0.3	3.9	-	*	*	*
	3	*	*	-	*	*	1.0	0.1	2.7	-	*	*	*
	4	-	*	-	*	-	*	-	0.7	-	-	-	*
	5	-	-	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	0.1	*	*	0.5	3.5	0.4	7.4	-	*	*	*
32	1 - 2	0.4	0.2	*	*	*	0.1	*	*	-	*	*	0.1
	3	1.3	1.3	0.1	0.2	*	0.1	0.6	0.4	*	0.5	0.4	0.8
	4	0.3	0.5	*	0.1	-	0.1	-	0.7	*	0.2	0.1	0.3
	5	*	*	*	*	-	*	-	0.5	-	*	*	*
	6	-	*	*	*	-	*	-	0.1	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	2.0	2.0	0.2	0.2	*	0.3	0.7	1.7	*	0.8	0.5	1.1
42	1 - 2	0.2	0.3	*	0.1	-	*	*	*	*	*	0.1	0.2
	3	2.4	4.4	1.3	2.9	-	*	*	*	0.5	1.1	2.0	3.0
	4	2.3	4.8	1.2	2.3	-	*	-	*	0.4	2.5	2.5	3.1
	5	0.7	1.4	0.3	0.3	-	*	-	*	0.1	0.7	0.4	0.5
	6	0.1	0.1	0.1	*	-	-	-	-	*	0.1	*	*
	7	*	*	-	*	-	-	-	-	-	*	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	5.7	11.0	2.8	5.5	-	*	0.1	*	1.1	4.4	4.9	6.7

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 05, 2024

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	*	*	*	*	-	-	-	-	*	*	*	*
	3	0.5	0.6	0.1	0.6	-	-	-	-	2.4	0.7	1.4	0.5
	4	0.8	1.0	0.2	0.6	-	-	-	-	9.7	2.8	3.1	1.2
	5	0.4	0.5	0.1	0.1	-	-	-	-	4.7	1.2	1.1	0.5
	6	*	0.1	*	*	-	-	-	-	0.3	0.1	0.1	0.1
	7	-	*	-	-	-	-	-	-	*	*	*	*
	8	-	-	-	-	-	-	-	-	-	-	*	*
Total	----	1.7	2.2	0.5	1.3	-	-	-	-	17.1	4.8	5.8	2.3
62	1 - 2	-	-	-	*	-	-	-	-	-	-	*	*
	3	*	*	-	*	-	-	-	-	*	*	*	*
	4	*	*	-	*	-	-	-	-	0.2	0.1	*	*
	5	*	*	*	*	-	-	-	-	0.3	0.1	*	*
	6	*	*	-	*	-	-	-	-	*	*	*	*
	7	-	*	-	-	-	-	-	-	-	-	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	*	*	-	-	-	-	0.5	0.1	*	*
13 & 23	1 - 2	-	-	-	-	*	0.3	-	0.1	-	*	-	*
	3	-	*	-	-	-	*	-	0.2	-	*	*	*
	4	-	-	-	-	-	*	-	0.1	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	-	*	0.3	-	0.3	-	*	*	*
33	1 - 2	*	*	-	-	-	*	-	*	-	*	*	*
	3	*	*	-	-	-	*	-	*	-	*	*	*
	4	-	*	-	-	-	*	-	0.1	-	*	*	*
	5	-	*	-	-	-	*	-	0.2	-	-	-	*
	6	-	-	-	-	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	*	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	-	-	-	0.1	-	0.3	-	*	*	*
43	1 - 2	*	*	*	*	-	-	-	-	*	*	*	*
	3	0.1	0.1	0.1	*	-	*	-	-	0.1	*	*	0.1
	4	0.2	0.2	0.1	*	-	*	-	-	0.2	0.1	0.1	0.1
	5	0.1	0.1	*	*	-	*	-	-	*	*	*	*
	6	-	*	*	*	-	*	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	*	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.4	0.4	0.2	0.1	-	*	-	*	0.3	0.2	0.2	0.3
53	1 - 2	-	-	-	*	-	-	-	-	-	-	-	*
	3	*	*	*	*	-	-	-	-	0.1	*	*	*
	4	*	*	*	*	-	-	-	-	0.7	0.2	0.1	0.1
	5	0.1	*	-	*	-	-	-	-	0.5	0.1	0.1	*
	6	*	*	-	*	-	-	-	-	0.1	*	*	*
	7	-	*	-	-	-	-	-	-	-	-	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.1	0.1	*	*	-	-	-	-	1.3	0.4	0.2	0.1
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	*	-	-	-	-	-	-	*	*	*	*
	5	-	*	-	-	-	-	-	-	*	*	-	*
	6	-	*	-	-	-	-	-	-	-	*	-	*
	7	-	*	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	-	-	-	-	-	*	*	*	*
24 - 54	1 - 8	*	*	*	*	-	*	-	-	0.2	*	*	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	-	-	-	-	-	-	-	-	*	*	*
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	-	-	-	-	-	-	-	-	-	-	-
31		-	*	-	*	-	-	-	-	-	-	*	*
32		*	0.2	*	*	-	-	-	-	*	*	0.2	0.1
33		0.9	1.8	0.2	0.1	*	*	-	-	0.3	0.2	1.0	0.7
34		5.4	7.6	1.4	0.7	0.5	0.7	7.9	0.7	4.5	3.2	5.0	5.1
35		14.4	16.4	9.2	6.7	3.0	3.1	19.8	3.2	11.5	11.0	15.4	18.1
36		24.6	25.2	24.9	22.2	9.4	13.5	31.0	9.5	22.3	23.9	28.5	29.9
37		37.3	35.7	58.2	59.3	40.2	38.9	11.1	16.9	28.0	33.6	34.5	33.6
38		11.9	10.1	5.7	10.1	27.1	25.5	15.3	25.3	20.4	18.6	11.8	10.0
39		4.5	2.6	0.3	0.9	14.9	12.8	3.3	23.1	9.9	7.6	3.3	2.4
40 & Longer		0.9	0.4	*	*	4.9	5.7	11.6	21.4	3.1	2.0	0.2	0.2
Average Staple		36.50	36.28	36.58	36.74	37.56	37.47	36.63	38.24	36.90	36.84	36.40	36.31
Average Length		1.14	1.13	1.14	1.15	1.17	1.17	1.14	1.19	1.15	1.15	1.13	1.13

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE													
For The Week Ending Dec 05, 2024													
Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	17.2	24.5	20.9	12.0	7.2	2.4	2.5	1.7	0.6	0.7	57.4	69.0
	3	19.2	21.8	11.6	5.4	2.4	1.0	1.6	1.1	0.5	0.6	7.5	16.1
	4	0.8	2.3	0.2	0.2	*	*	0.1	*	*	*	0.9	1.1
	5	*	*	-	*	-	-	-	*	-	*	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	37.3	48.6	32.6	17.5	9.7	3.4	4.1	2.9	1.2	1.2	65.8	86.2
31	1 - 2	0.5	0.4	10.7	7.5	20.7	13.4	5.2	4.0	2.9	5.6	19.3	5.2
	3	4.8	5.2	26.9	25.2	35.7	29.3	20.8	18.8	14.5	21.7	11.6	4.7
	4	1.6	4.5	5.8	6.5	3.9	3.9	5.3	7.1	5.2	7.1	0.5	1.3
	5	0.1	1.1	0.5	0.3	0.1	0.1	0.3	0.4	0.5	0.5	-	0.2
	6	-	0.1	0.1	*	*	*	*	*	*	*	-	*
	7	-	*	*	*	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	*	-	-
Total	----	7.0	11.2	44.1	39.5	60.4	46.7	31.6	30.3	23.2	35.1	31.4	11.4
41	1 - 2	-	*	0.4	0.4	4.3	5.7	0.9	0.9	2.4	2.1	0.5	0.1
	3	0.5	0.1	4.4	13.7	17.6	28.9	15.6	19.1	28.7	25.9	1.8	0.3
	4	0.2	0.1	6.9	19.7	6.0	9.7	20.2	26.0	29.1	25.7	0.1	*
	5	0.1	0.2	1.0	4.5	0.4	0.7	3.9	6.4	6.9	5.2	-	-
	6	*	0.1	0.1	0.2	*	*	0.2	0.5	0.5	0.4	-	-
	7	-	*	0.1	*	-	-	*	*	*	0.1	-	-
	8	-	*	0.1	*	-	-	-	-	-	*	-	-
Total	----	0.9	0.6	13.1	38.7	28.3	45.0	40.9	53.0	67.5	59.3	2.4	0.4
51	1 - 2	*	*	-	*	*	*	0.4	*	*	*	-	-
	3	0.7	0.1	0.4	0.2	0.4	0.4	2.4	0.8	1.1	0.4	-	-
	4	0.2	*	2.5	0.6	0.2	0.2	7.4	2.6	3.5	1.6	-	-
	5	0.4	0.1	0.5	0.2	*	*	2.6	1.3	1.9	0.9	-	-
	6	0.1	*	-	*	*	*	0.3	0.2	0.3	0.1	-	-
	7	*	*	-	*	-	-	*	*	*	*	-	-
	8	*	*	-	*	-	-	-	-	*	*	-	-
Total	----	1.5	0.3	3.4	1.1	0.7	0.7	13.1	5.0	6.8	3.0	-	-
61	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	*	*	*	*	-	-	-	-
	4	-	-	-	*	*	*	*	*	-	-	-	-
	5	-	-	-	-	-	*	*	*	-	*	-	-
	6	-	-	-	*	-	*	*	*	-	-	-	-
	7	-	-	-	-	-	-	-	*	-	*	-	-
	8	-	-	-	-	-	-	-	-	*	*	-	-
Total	----	-	-	-	*	*	*	0.1	*	*	*	-	-
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	*	*	-	-	-	-
	5	-	-	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	*	*	-	-
Total	----	-	-	-	-	-	-	*	*	*	*	-	-
12 & 22	1 - 2	2.6	7.7	0.3	*	*	*	*	*	-	*	-	0.4
	3	6.0	10.5	0.3	0.1	*	*	0.1	*	*	*	0.2	1.0
	4	0.5	1.7	0.1	*	*	*	*	*	*	*	0.1	0.2
	5	-	0.1	-	*	-	-	*	*	-	*	-	*
	6	-	*	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	9.1	19.9	0.6	0.1	*	*	0.1	0.1	*	*	0.3	1.6
32	1 - 2	0.2	0.1	0.1	*	*	*	*	0.1	*	*	-	-
	3	2.7	2.2	1.3	0.3	0.1	0.2	0.2	0.3	0.1	0.1	0.1	0.1
	4	1.4	2.4	0.2	0.1	0.1	0.1	0.1	0.2	0.1	0.1	-	0.1
	5	0.1	0.7	-	*	*	*	*	*	*	*	-	*
	6	-	0.3	-	*	-	-	*	*	*	*	-	-
	7	-	0.1	-	-	-	-	-	-	-	*	-	-
	8	-	*	-	-	-	-	-	-	-	*	-	-
Total	----	4.5	5.8	1.6	0.5	0.2	0.3	0.3	0.6	0.2	0.2	0.1	0.2
42	1 - 2	*	*	-	*	*	0.2	0.1	0.1	*	*	-	*
	3	1.6	0.4	0.9	0.7	0.4	2.2	0.7	1.9	0.2	0.2	-	-
	4	3.6	1.0	1.2	1.0	0.1	0.9	2.2	2.8	0.5	0.4	-	-
	5	2.2	1.0	0.6	0.4	*	0.1	0.6	0.8	0.1	0.1	-	-
	6	0.7	0.3	0.1	0.1	*	*	0.1	0.1	*	*	-	-
	7	0.1	0.1	0.1	*	-	-	-	*	-	*	-	-
	8	*	*	*	*	-	-	-	-	-	*	-	-
Total	----	8.3	2.8	3.0	2.1	0.6	3.5	3.7	5.8	0.9	0.8	-	*

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 05, 2024

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	*	*	-	*	*	*	*	*	-	-	-	-
	3	0.4	0.1	*	0.1	*	0.2	0.4	0.4	*	*	-	-
	4	1.2	0.3	0.5	0.2	*	0.1	3.0	1.1	0.1	0.1	-	-
	5	3.0	0.9	0.5	0.1	*	*	2.0	0.6	0.1	0.1	-	-
	6	4.8	1.2	0.1	*	-	*	0.2	0.1	*	*	-	-
	7	2.7	0.6	*	*	-	-	*	*	*	*	-	-
	8	0.4	0.1	-	*	-	-	-	-	-	*	-	-
Total	----	12.5	3.2	1.1	0.4	0.1	0.4	5.7	2.2	0.2	0.2	-	-
62	1 - 2	-	-	-	-	-	-	-	*	-	-	-	-
	3	-	-	-	*	-	*	*	*	-	-	-	-
	4	-	-	-	-	-	*	0.1	*	-	-	-	-
	5	-	-	-	-	*	*	0.1	*	-	-	-	-
	6	-	-	-	*	-	-	*	*	-	-	-	-
	7	-	-	-	-	-	-	*	*	-	-	-	-
	8	-	-	-	-	-	-	-	-	*	*	-	-
Total	----	-	-	-	*	*	*	0.2	*	*	*	-	-
13 & 23	1 - 2	0.1	0.1	*	*	-	-	-	-	-	-	-	0.1
	3	0.1	0.3	*	*	-	-	*	*	-	-	-	*
	4	*	0.2	-	*	-	-	*	*	-	-	-	-
	5	-	*	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.2	0.6	*	*	-	-	*	*	-	-	-	0.1
33	1 - 2	*	*	-	*	-	-	-	*	*	*	-	*
	3	0.2	0.2	0.1	*	-	-	*	*	*	*	-	-
	4	0.2	0.4	0.1	*	-	-	*	*	*	*	-	-
	5	0.1	0.1	-	*	-	-	-	*	-	*	-	-
	6	-	*	-	-	-	-	-	-	-	*	-	-
	7	-	*	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	*	-	-
Total	----	0.5	0.7	0.2	0.1	-	-	*	*	*	*	-	*
43	1 - 2	-	*	-	*	-	*	*	*	*	*	-	-
	3	0.9	0.2	0.1	*	*	*	*	*	*	*	-	-
	4	2.7	0.6	0.2	*	*	*	0.1	*	*	*	-	-
	5	1.0	0.3	-	*	*	*	*	*	*	*	-	*
	6	0.1	0.1	-	*	*	*	*	*	*	*	-	-
	7	*	*	-	*	-	-	-	-	-	*	-	-
	8	-	*	-	-	-	-	-	-	-	*	-	-
Total	----	4.8	1.2	0.2	*	*	*	0.2	0.1	*	*	-	*
53	1 - 2	-	-	-	-	-	-	-	*	-	-	-	-
	3	0.1	*	*	*	-	-	*	*	-	*	-	-
	4	2.0	0.7	-	*	-	-	0.1	*	*	*	-	-
	5	4.0	1.6	*	*	-	-	*	*	*	*	-	-
	6	4.5	1.5	-	-	-	-	*	*	-	*	-	-
	7	1.7	0.5	-	-	-	-	-	*	-	*	-	-
	8	0.1	*	*	*	-	-	-	-	-	*	-	-
Total	----	12.6	4.5	0.1	*	-	-	0.2	0.1	*	*	-	-
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	*	*	-	-	-	-
	5	-	-	-	-	-	-	*	*	-	-	-	-
	6	-	-	-	-	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	*	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	*	*	-	-	-	-
24 - 54	1 - 8	1.0	0.6	*	*	-	-	*	*	*	*	-	-
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	*	*	-	-	-	-	-	-	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	*	-	-	-	-	-	-	-	-	-	-
30		*	*	-	-	-	-	-	-	-	-	-	-
31		0.1	0.5	-	-	-	-	-	*	-	-	-	-
32		0.7	1.8	-	*	*	*	*	*	-	-	-	*
33		4.2	5.7	0.1	0.1	0.1	0.1	0.4	0.3	0.3	0.2	-	*
34		12.5	11.9	1.0	0.7	1.9	0.9	4.4	2.9	3.7	4.7	3.0	1.6
35		20.8	23.3	7.9	7.0	11.2	7.3	20.6	13.9	18.6	19.9	10.8	9.4
36		26.2	25.9	21.6	22.3	21.6	25.1	27.4	28.9	40.9	39.6	30.8	18.7
37		28.9	24.1	34.8	40.9	55.4	56.3	36.6	40.9	31.6	30.9	27.1	34.4
38		6.3	6.3	22.1	18.5	9.0	9.7	9.3	10.6	4.2	4.0	15.9	26.2
39		0.2	0.6	12.2	8.3	0.6	0.5	1.2	2.2	0.7	0.7	12.3	7.2
40 & Longer		-	*	0.3	2.3	*	*	0.1	0.2	0.1	0.1	0.1	2.6
Average Staple		35.81	35.65	37.07	37.04	36.60	36.68	36.28	36.49	36.15	36.11	36.79	37.08
Average Length		1.12	1.11	1.16	1.16	1.14	1.14	1.13	1.14	1.13	1.12	1.15	1.16

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE For The Week Ending Dec 05, 2024											
Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	41.2	65.1	0.7	1.3	2.4	3.6	24.7	30.0	0.3	0.2
	3	7.3	11.4	1.4	1.4	2.4	1.8	9.9	9.4	0.6	0.5
	4	0.1	0.2	0.1	0.1	0.1	*	0.9	0.7	*	*
	5	*	*	-	-	-	*	*	*	-	*
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	48.7	76.8	2.3	2.8	4.8	5.5	35.5	40.1	0.9	0.7
31	1 - 2	1.1	1.5	2.6	5.3	13.2	13.1	4.6	2.2	8.7	7.3
	3	1.2	2.4	20.6	29.8	30.0	22.2	15.7	13.0	33.3	31.1
	4	0.2	0.4	8.2	11.4	4.6	3.0	8.1	5.8	9.0	7.3
	5	*	*	0.5	0.7	0.2	0.1	1.7	0.7	0.8	0.4
	6	-	-	*	*	*	*	0.1	0.1	*	*
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	2.6	4.3	31.9	47.2	48.1	38.4	30.3	21.8	51.9	46.0
41	1 - 2	0.3	0.1	0.8	0.6	2.8	8.3	0.1	0.5	2.9	3.8
	3	7.9	1.4	16.9	15.0	16.4	24.1	1.6	6.9	21.7	27.9
	4	3.0	0.6	21.7	21.4	7.4	6.7	3.3	7.4	16.2	17.9
	5	0.6	0.1	4.5	5.5	0.7	0.5	3.1	1.7	3.9	2.5
	6	-	*	0.1	0.4	*	*	1.5	0.3	0.3	0.1
	7	-	-	-	*	-	-	0.5	0.1	*	*
	8	-	-	-	*	-	-	0.1	*	*	*
Total	----	11.8	2.2	43.9	42.9	27.2	39.6	10.2	17.0	45.1	52.1
51	1 - 2	-	-	0.1	*	1.7	0.4	*	*	*	*
	3	0.1	*	4.5	1.1	11.0	2.1	0.1	0.4	0.1	0.2
	4	0.2	*	10.9	2.9	2.8	0.7	*	0.8	0.4	0.2
	5	0.1	*	3.2	1.1	0.3	0.1	*	0.3	0.2	0.1
	6	-	-	0.2	0.1	*	*	*	*	*	*
	7	-	-	-	*	-	-	*	*	*	*
	8	-	-	-	*	-	-	0.3	*	-	-
Total	----	0.4	*	18.9	5.2	15.8	3.4	0.5	1.7	0.8	0.4
61	1 - 2	-	-	-	-	-	*	-	-	-	-
	3	-	-	*	*	*	*	-	*	-	-
	4	-	-	*	*	-	*	-	*	-	-
	5	-	-	-	-	*	*	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	*	-	-	*	*	-	-
Total	----	-	-	*	*	*	*	*	*	-	-
71	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	-	-	-
12 & 22	1 - 2	3.3	4.5	-	*	*	*	4.6	4.8	-	*
	3	0.7	2.2	*	*	*	*	3.1	2.7	*	*
	4	0.1	0.3	-	*	*	*	0.3	0.3	-	-
	5	*	*	-	-	-	*	*	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	4.0	7.0	*	*	0.1	*	8.0	7.9	*	*
32	1 - 2	1.4	0.4	-	*	0.1	0.2	1.5	0.4	*	*
	3	2.6	0.8	0.1	0.1	0.8	0.6	4.4	1.8	0.5	0.2
	4	0.9	0.3	0.1	0.1	0.2	0.1	2.5	1.1	0.3	0.1
	5	*	*	-	*	*	*	0.6	0.3	*	*
	6	-	*	-	*	-	*	0.1	*	-	-
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	4.9	1.5	0.3	0.3	1.1	0.9	9.0	3.6	0.8	0.3
42	1 - 2	0.7	0.1	*	*	0.3	2.0	*	*	0.1	*
	3	9.7	2.2	0.3	0.2	1.2	6.6	0.5	1.1	0.1	0.1
	4	6.6	2.2	0.6	0.5	0.5	1.5	0.9	2.3	*	0.1
	5	1.2	0.4	0.2	0.3	0.1	0.1	0.6	0.9	*	*
	6	*	*	*	*	*	*	0.2	0.1	-	*
	7	-	-	-	*	-	-	0.1	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	18.2	5.0	1.1	1.0	2.0	10.2	2.3	4.5	0.2	0.2

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE											
For The Week Ending Dec 05, 2024											
Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	*	*	*	0.2	-	*	*	*
	3	0.3	*	0.4	0.1	0.3	0.9	*	0.1	*	*
	4	1.2	0.2	0.7	0.2	0.3	0.6	*	0.5	*	*
	5	0.3	*	0.4	0.2	0.1	0.1	*	0.4	-	*
	6	0.1	*	*	*	*	*	*	0.1	-	-
	7	-	*	-	*	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	1.8	0.3	1.5	0.5	0.7	1.9	0.1	1.2	*	*
62	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	*	*	-	*	-	-
	4	-	-	-	-	*	*	-	*	-	-
	5	-	-	*	*	-	-	-	*	-	-
	6	-	-	-	*	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	-	-	*	*	*	*	-	*	-	-
13 & 23	1 - 2	0.4	0.3	*	*	-	-	0.4	0.3	-	-
	3	0.5	0.3	*	*	-	-	0.3	0.3	-	-
	4	0.1	0.1	-	*	-	-	*	0.1	-	*
	5	-	-	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	1.0	0.7	*	*	-	-	0.8	0.7	-	*
33	1 - 2	0.6	0.2	-	-	-	-	0.4	0.1	*	*
	3	1.3	0.4	*	*	-	-	1.0	0.3	0.2	*
	4	0.2	0.1	-	*	-	-	0.4	0.2	0.1	*
	5	*	*	-	*	-	-	0.1	*	*	*
	6	-	*	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	2.2	0.8	*	*	-	-	1.9	0.7	0.3	0.1
43	1 - 2	0.1	*	-	-	*	*	*	*	*	*
	3	1.5	0.4	*	*	*	0.1	0.1	0.1	*	*
	4	0.7	0.3	0.1	*	*	*	0.1	0.1	*	*
	5	0.2	0.1	*	*	*	*	0.1	0.1	*	*
	6	*	*	*	*	-	-	*	*	-	*
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	2.5	0.8	0.1	*	0.1	0.2	0.4	0.3	0.1	*
53	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	0.1	*	*	*	-	-	*	*	-	-
	4	0.1	*	*	*	-	-	-	0.1	-	-
	5	0.1	*	*	*	-	-	*	0.2	-	-
	6	0.1	*	-	-	-	-	*	*	-	-
	7	*	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	0.4	0.1	0.1	*	-	-	*	0.3	-	-
63	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	-	-	-	-	*	-	-
	5	-	-	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	-	-	-	-	-	-	-	*	-	-
24 - 54	1 - 8	1.4	0.5	*	*	*	*	0.9	0.2	-	-
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	*	0.1	-	-	-	-	0.1	*	-	-
STAPLE											
28 & Shorter		-	*	-	-	-	-	*	*	-	-
29		0.2	0.1	-	-	-	-	*	*	-	-
30		0.4	0.3	-	-	-	-	0.1	0.1	-	-
31		0.1	0.8	-	-	-	*	0.6	0.4	-	-
32		0.7	1.4	-	-	-	*	1.9	1.6	-	-
33		2.3	2.9	0.1	0.1	*	0.2	5.5	4.4	0.1	0.1
34		9.3	7.9	2.1	1.5	1.7	2.1	12.4	11.0	1.4	2.5
35		17.8	17.6	13.1	11.7	15.1	13.4	20.9	18.7	15.4	15.4
36		23.4	25.1	31.9	33.1	28.4	35.4	25.3	21.2	46.8	45.6
37		32.7	28.9	38.3	40.1	46.9	42.0	24.5	26.2	34.7	34.6
38		9.7	9.7	10.4	10.7	7.7	6.0	6.5	11.6	1.5	1.7
39		3.3	4.8	3.2	2.6	0.2	0.8	2.0	4.3	0.1	0.1
40 & Longer		0.2	0.5	0.9	0.3	*	0.1	0.3	0.5	*	*
Average Staple		36.13	36.11	36.54	36.55	36.44	36.38	35.71	36.01	36.20	36.18
Average Length		1.13	1.13	1.14	1.14	1.14	1.13	1.11	1.12	1.13	1.13

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 05, 2024

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	0.5	0.2	*	*	-	*	-	*	2.4	0.9	1.3	0.8
Bark - Level 2	-	-	-	*	-	-	-	-	-	-	-	-
Grass - Level 1	*	0.1	0.1	*	-	*	-	*	0.2	0.1	*	0.1
Grass - Level 2	*	*	-	-	-	-	-	-	-	-	-	*
Prep - Level 1	-	*	-	*	-	-	-	-	-	-	*	*
Prep - Level 2	-	-	-	*	-	-	-	-	-	-	*	*
Seed Coat - Level 1	0.8	1.2	*	0.2	*	0.1	-	-	6.5	2.3	2.6	1.6
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	*	-	*	-	-	-	-	-	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	-	-	-	-	-	-	-	-	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	0.1	0.1	-	*	-	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	-	-	-	-	-	-	-	-	-	-	-
23	*	*	-	-	-	-	-	-	-	-	*	*
24	-	*	-	*	*	*	-	-	-	-	*	*
25	*	0.1	*	*	0.1	0.1	-	*	-	*	0.1	0.1
26	0.2	0.8	0.2	0.2	0.3	0.3	-	*	*	0.1	0.4	0.4
27	1.7	4.3	1.8	2.3	1.4	1.2	*	0.1	0.3	0.6	1.8	2.6
28	7.5	15.2	24.2	20.4	6.5	4.5	0.3	0.3	1.8	3.1	7.9	9.4
29	27.5	29.5	41.7	41.2	10.2	10.6	2.1	3.3	11.7	12.7	21.9	22.8
30	32.1	26.1	22.7	24.2	16.8	19.1	7.2	15.3	25.7	25.0	28.4	28.6
31	19.9	15.0	6.8	8.8	20.9	21.0	4.0	16.9	26.9	24.5	21.4	20.5
32	8.4	6.2	2.0	2.3	19.4	16.3	20.9	13.8	17.3	18.1	11.5	9.9
33	2.3	1.9	0.5	0.5	11.5	10.8	10.9	10.2	8.1	8.3	4.6	3.9
34	0.4	0.6	*	0.1	5.7	7.5	28.3	13.8	6.2	5.1	1.4	1.3
35	*	0.1	*	*	4.4	5.4	20.8	10.7	1.8	1.9	0.5	0.4
36	*	*	*	*	2.3	2.4	4.5	8.1	0.3	0.5	0.2	0.1
37	-	*	-	*	0.3	0.6	1.0	5.4	*	0.1	*	*
38	-	*	-	-	*	0.1	*	2.1	*	*	*	*
39	-	-	-	-	*	*	-	0.1	-	*	-	*
40 & Above	-	*	-	-	-	*	-	*	-	-	-	*
Average	30.42	30.05	29.62	29.71	31.71	31.83	33.73	33.28	31.50	31.43	30.67	30.53
Mike												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	*
2.5	-	-	-	*	-	-	-	-	-	-	-	-
2.6	-	-	-	*	-	-	0.7	0.1	-	-	-	*
2.7	*	*	-	*	*	*	-	0.1	-	-	-	-
2.8	-	*	*	*	-	*	-	0.1	-	-	-	*
2.9	*	*	*	*	-	*	-	*	-	-	-	*
3.0	0.1	*	*	*	*	*	-	0.4	-	-	-	*
3.1	*	*	*	*	0.1	0.1	0.1	0.7	-	-	*	*
3.2	*	0.1	0.1	*	0.5	0.4	0.1	1.1	-	*	*	*
3.3	*	0.1	0.1	*	1.2	0.5	-	1.2	-	*	*	*
3.4	0.1	0.2	0.2	0.1	1.3	0.5	0.4	2.5	-	*	*	*
3.5	0.3	0.4	0.3	0.1	1.6	0.6	0.3	1.8	-	*	*	*
3.6	0.5	0.8	0.6	0.2	1.5	0.7	0.5	2.8	0.1	0.1	0.1	0.1
3.7	1.1	1.5	0.8	0.4	2.9	1.5	3.5	3.3	0.1	0.2	0.3	0.2
3.8	2.9	2.7	1.2	0.7	4.9	2.9	5.8	3.3	0.2	0.5	0.5	0.4
3.9	3.8	4.0	1.9	1.3	5.8	3.7	0.1	3.3	0.3	0.7	0.8	0.9
4.0	5.3	5.6	3.1	2.3	7.1	4.5	1.8	4.8	0.6	1.0	1.6	1.7
4.1	8.4	7.9	3.6	3.5	8.1	5.7	0.9	5.2	1.4	2.1	3.0	3.0
4.2	9.6	9.7	5.2	5.3	9.2	7.7	3.1	5.8	2.9	3.4	5.8	5.0
4.3	10.5	10.6	7.1	7.6	9.5	8.4	5.5	8.7	4.0	5.0	7.9	7.6
4.4	10.3	11.1	8.3	10.2	10.2	10.6	8.4	7.3	8.5	9.6	10.4	10.3
4.5	8.9	10.4	12.2	13.0	8.0	9.2	8.4	6.8	10.2	12.4	12.0	12.4
4.6	8.3	10.0	15.2	15.4	4.1	8.8	7.5	7.5	15.7	16.8	12.3	13.8
4.7	8.7	8.6	15.1	14.5	5.1	8.5	8.3	7.5	14.8	16.5	12.5	13.8
4.8	7.6	6.6	11.0	10.9	6.0	8.2	9.8	7.1	13.3	12.3	12.3	11.9
4.9	5.2	4.6	6.8	7.3	4.7	5.9	4.3	6.9	13.6	8.2	9.2	8.4
5.0	3.2	2.6	3.9	4.0	3.2	4.1	3.9	5.0	8.0	5.4	5.7	5.3
5.1	2.9	1.4	1.7	1.9	3.5	3.2	2.6	3.3	4.5	3.0	3.5	3.0
5.2	1.3	0.6	0.8	0.8	0.9	1.3	8.5	1.8	1.4	1.8	1.4	1.3
5.3	0.8	0.3	0.5	0.3	0.1	1.3	15.6	1.7	0.6	0.6	0.5	0.6
5.4	0.1	0.1	0.1	0.1	0.1	1.1	-	0.1	*	0.1	0.1	0.2
5.5 & Above	0.1	*	0.1	0.1	0.1	0.6	-	*	-	*	*	*
Average	4.44	4.40	4.54	4.56	4.31	4.47	4.65	4.37	4.68	4.63	4.60	4.60

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 05, 2024

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	20.6	7.3	-	*	*	*	0.4	0.1	2.2	2.1	0.1	*
Bark - Level 2	-	-	-	*	-	-	-	*	-	-	-	-
Grass - Level 1	-	0.2	-	0.1	*	*	*	*	0.1	0.3	-	0.6
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	-	-	-	-	*	*	*	-	-	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	0.1	0.1	-	0.2	*	*	0.2	0.9	*	*	-	-
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	-	-	*	-	*	-	-	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	*	-	-	-	*	-	*	-	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	-	*	*	*	*	*	*	*	0.1	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	-	-	-	-	-	-	-	-	-	-	-
23	-	*	-	-	-	-	-	-	-	-	-	-
24	*	0.1	-	*	*	*	*	*	-	-	-	-
25	*	0.1	-	*	*	*	0.1	0.1	0.2	0.1	0.1	*
26	0.1	0.5	*	*	0.3	0.1	0.9	0.5	2.7	2.0	0.2	0.1
27	0.5	1.4	0.2	0.3	1.6	1.7	4.2	3.3	17.9	15.2	0.7	0.9
28	5.1	3.1	7.3	3.0	13.8	16.7	15.5	14.3	34.9	36.2	18.8	7.9
29	14.7	8.8	28.7	18.5	35.3	40.2	36.7	30.9	28.1	28.7	35.1	22.1
30	20.9	15.3	33.4	33.4	32.7	28.1	27.1	30.2	12.1	12.2	20.0	18.6
31	17.3	19.5	18.9	29.5	11.6	9.5	10.7	14.6	3.1	4.2	4.9	17.8
32	20.6	21.2	8.4	10.7	4.1	2.8	3.9	4.5	0.7	1.1	5.4	14.7
33	15.9	19.9	3.0	3.1	0.6	0.6	0.9	1.3	0.2	0.2	11.8	10.1
34	3.7	8.8	*	1.2	0.1	0.2	0.1	0.4	*	*	3.1	5.8
35	0.5	1.0	-	0.3	*	*	*	0.1	*	*	-	1.4
36	0.6	0.4	-	*	*	*	*	*	-	-	-	0.5
37	*	0.1	-	*	-	*	-	*	-	-	-	-
38	*	*	-	*	-	-	-	-	-	-	-	*
39	*	*	-	-	-	-	-	-	-	-	-	-
40 & Above	-	-	-	-	-	-	-	-	-	-	-	-
Average	31.45	31.87	30.45	30.86	29.99	29.84	29.82	30.03	28.87	28.96	30.28	31.12
Mike												
2.4 & Below	-	*	-	-	-	-	-	*	-	-	-	-
2.5	-	*	-	-	-	-	-	*	-	-	-	-
2.6	*	*	-	-	-	-	*	*	-	-	-	-
2.7	*	0.1	-	*	-	*	*	*	*	*	-	-
2.8	0.4	0.4	-	*	-	*	-	*	*	*	-	*
2.9	0.2	0.6	-	*	-	*	-	*	*	*	-	*
3.0	0.4	1.0	-	*	*	*	*	*	*	*	-	*
3.1	0.9	1.7	-	*	*	*	*	*	*	*	-	*
3.2	0.8	2.0	-	*	0.1	0.1	*	*	0.1	0.1	0.2	0.1
3.3	1.6	2.2	1.4	0.1	0.1	0.1	*	*	0.2	0.1	0.2	0.1
3.4	2.6	1.7	0.3	*	0.3	0.2	0.1	*	0.3	0.2	0.4	0.4
3.5	2.1	2.8	*	0.1	0.6	0.3	0.1	0.1	0.4	0.3	2.9	2.5
3.6	4.3	3.5	1.0	0.1	0.9	0.5	0.2	0.1	0.5	0.4	1.5	2.3
3.7	6.5	5.2	0.4	0.2	1.4	0.8	0.3	0.3	0.8	0.8	5.9	4.6
3.8	7.4	6.5	1.2	0.4	2.2	1.5	0.7	0.6	1.5	1.5	9.6	5.4
3.9	9.4	8.4	1.6	0.9	3.0	2.2	1.0	0.9	2.8	2.6	6.5	7.3
4.0	7.6	7.6	3.0	1.6	4.8	3.2	1.9	1.7	4.0	4.1	5.3	7.7
4.1	8.2	9.0	2.4	2.4	5.7	4.8	2.6	2.7	5.8	6.5	14.2	8.5
4.2	9.1	9.1	4.3	4.3	8.4	7.4	3.8	4.1	8.3	8.6	12.7	11.3
4.3	7.3	8.5	4.5	6.7	10.2	10.2	6.6	6.5	11.3	11.1	11.2	8.4
4.4	6.0	6.9	8.6	8.8	11.1	12.3	9.1	8.7	13.3	13.5	7.4	7.1
4.5	4.6	5.0	13.2	9.7	13.4	13.8	10.4	10.9	14.9	14.5	6.5	11.0
4.6	5.7	4.9	6.3	10.6	12.4	13.8	12.3	13.4	13.6	13.2	7.1	9.5
4.7	4.9	4.2	9.8	12.4	10.5	11.0	14.8	14.1	10.2	9.9	4.4	8.1
4.8	3.7	3.5	9.3	12.9	6.5	7.9	12.4	12.7	6.1	6.5	2.5	3.1
4.9	3.0	2.6	5.0	9.2	5.1	4.9	11.5	9.7	3.5	3.6	1.5	2.1
5.0	1.9	1.7	9.3	6.4	2.2	2.9	7.1	6.8	1.6	1.7	0.1	0.3
5.1	1.1	0.7	9.1	5.0	0.7	1.3	3.2	3.7	0.5	0.6	-	0.1
5.2	0.4	0.2	4.0	3.5	0.3	0.5	1.3	1.8	0.1	0.2	-	-
5.3	*	0.1	3.7	2.5	*	0.2	0.4	0.8	*	*	-	-
5.4	*	*	1.3	1.3	*	0.1	0.1	0.3	*	*	-	-
5.5 & Above	-	-	0.2	0.8	-	*	0.1	0.1	-	*	-	-
Average	4.13	4.10	4.64	4.67	4.42	4.48	4.62	4.63	4.42	4.43	4.17	4.24

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE										
For The Week Ending Dec 05, 2024										
Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter										
Bark - Level 1	1.8	0.8	3.5	2.3	*	*	6.6	2.6	0.6	1.4
Bark - Level 2	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	*	*	0.3	0.3	-	*	0.1	0.8	*	*
Grass - Level 2	-	-	-	-	-	-	-	*	-	-
Prep - Level 1	*	*	*	*	-	-	*	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	*	*	*	0.1	-	*	*	0.1	*	*
Seed Coat - Level 2	-	-	-	-	-	-	-	*	-	-
Oil - Level 1	-	*	-	-	-	-	*	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	-	-	-	*	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	*	*	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/										
22 & Below	*	0.1	-	-	-	-	0.1	0.1	-	-
23	0.1	0.2	-	-	-	-	0.1	0.2	-	-
24	0.7	0.4	-	-	-	*	0.4	0.4	-	-
25	0.6	0.6	*	*	*	0.1	0.8	0.8	0.3	0.3
26	1.3	1.4	0.3	0.2	0.2	1.1	1.9	1.9	6.4	4.6
27	3.8	3.4	3.2	1.8	2.3	8.4	5.0	4.4	30.5	27.0
28	5.8	6.8	17.1	10.8	19.8	29.9	10.9	9.0	37.0	40.9
29	7.1	11.7	30.0	27.4	46.1	36.0	17.9	15.1	18.2	20.4
30	11.5	13.1	26.4	29.5	25.5	18.3	22.1	20.3	6.3	5.7
31	13.1	12.4	13.6	17.7	4.8	4.8	19.9	19.7	1.0	0.9
32	17.1	16.3	6.3	8.7	1.1	1.2	11.9	13.3	0.2	0.1
33	21.0	18.9	2.1	3.1	0.1	0.3	5.4	7.8	*	*
34	14.9	10.6	0.7	0.7	*	*	2.4	4.1	*	*
35	2.5	2.9	0.2	0.1	-	*	0.9	1.9	-	*
36	0.3	0.8	*	*	-	*	0.3	0.7	-	-
37	*	0.3	-	-	-	-	0.1	0.2	-	-
38	*	*	-	-	-	-	*	0.1	-	-
39	-	*	-	-	-	-	*	*	-	-
40 & Above	-	-	-	-	-	-	-	*	-	-
Average	31.87	31.63	30.07	30.38	29.58	29.27	30.51	30.85	28.35	28.43
Mike										
2.4 & Below	-	-	-	-	-	-	*	*	-	-
2.5	-	*	-	-	-	-	0.1	*	-	-
2.6	-	*	-	-	-	-	0.1	*	-	-
2.7	*	*	-	-	-	*	0.2	0.1	-	-
2.8	-	*	-	-	-	*	0.3	0.1	-	-
2.9	*	*	-	-	*	*	0.5	0.2	*	*
3.0	0.3	0.1	*	*	*	*	0.6	0.3	-	-
3.1	0.3	0.2	*	*	0.1	*	1.0	0.4	-	*
3.2	0.3	0.4	*	*	0.1	0.1	1.5	0.6	*	*
3.3	0.2	0.5	*	*	0.3	0.2	1.8	0.7	0.2	0.1
3.4	0.4	0.6	*	*	0.4	0.3	2.1	1.0	0.5	0.2
3.5	1.1	0.9	*	0.1	0.5	0.3	2.8	1.4	0.7	0.5
3.6	4.5	2.7	0.3	0.1	1.3	0.7	3.6	1.9	1.6	1.1
3.7	3.9	3.4	0.8	0.3	2.2	1.3	4.0	2.4	3.1	2.7
3.8	3.3	4.4	1.0	0.7	2.7	2.3	4.9	3.2	4.4	4.9
3.9	3.6	6.9	1.4	1.0	3.5	3.7	5.5	4.2	7.5	7.1
4.0	5.3	8.1	3.2	2.2	5.0	5.8	5.7	5.1	9.0	9.2
4.1	7.8	9.8	4.1	3.6	6.4	8.4	6.7	6.5	11.7	10.4
4.2	9.5	10.6	7.2	6.6	8.7	11.0	7.3	7.8	15.3	13.1
4.3	13.0	10.5	8.6	10.0	9.3	13.1	7.9	9.2	16.2	16.2
4.4	10.9	10.0	10.5	12.2	12.3	13.6	8.6	10.1	16.5	14.9
4.5	10.6	9.0	13.7	12.9	13.8	12.6	8.5	10.1	7.9	10.7
4.6	8.2	7.0	14.0	13.4	9.7	11.1	7.6	9.6	3.4	5.1
4.7	6.4	5.9	12.2	11.6	9.7	7.8	6.2	8.7	1.6	2.4
4.8	4.0	3.6	10.1	10.2	8.0	4.6	5.0	7.0	0.2	0.9
4.9	3.1	2.6	6.5	7.0	3.9	1.8	3.4	4.6	0.1	0.3
5.0	2.7	1.7	3.9	4.4	1.6	0.8	2.2	2.6	*	*
5.1	0.5	0.7	1.4	2.3	0.2	0.3	1.2	1.3	-	-
5.2	*	0.2	0.7	0.9	0.1	0.1	0.4	0.6	-	-
5.3	-	0.1	0.2	0.4	-	*	0.2	0.3	-	-
5.4	-	*	0.1	0.1	-	*	0.1	0.1	-	-
5.5 & Above	-	*	*	*	-	*	*	*	-	-
Average	4.29	4.26	4.52	4.55	4.39	4.35	4.20	4.35	4.19	4.22

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE												
For The Week Ending Dec 05, 2024												
Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	*
2.5 - 2.6	-	-	-	*	-	-	0.7	0.1	-	-	-	*
2.7 - 2.9	*	*	*	*	*	*	-	0.2	-	-	-	*
3.0 - 3.2	0.1	0.1	0.1	*	0.6	0.5	0.2	2.1	-	*	*	*
3.3 - 3.4	0.2	0.3	0.3	0.1	2.5	0.9	0.4	3.6	-	*	*	*
3.5 - 3.6	0.8	1.2	0.9	0.3	3.1	1.3	0.7	4.6	0.1	0.2	0.1	0.1
3.7 - 4.2	31.1	31.4	15.9	13.6	38.1	26.0	15.2	25.7	5.5	8.0	11.9	11.2
4.3 - 4.9	59.5	62.0	75.7	78.9	47.7	59.6	52.2	51.8	80.1	80.9	76.6	78.2
5.0 - 5.2	7.4	4.6	6.3	6.7	7.6	8.6	15.0	10.1	13.8	10.3	10.7	9.6
5.3 & Above	1.0	0.4	0.8	0.4	0.3	3.0	15.6	1.9	0.6	0.7	0.6	0.8
Average	4.44	4.40	4.54	4.56	4.31	4.47	4.65	4.37	4.68	4.63	4.60	4.60
Leaf												
1 - 2	10.5	10.6	13.7	8.0	95.9	87.9	92.2	71.1	3.1	5.5	10.4	13.8
3	55.5	53.9	59.5	55.3	3.9	11.1	7.6	20.7	33.8	45.2	51.4	57.2
4	29.4	29.9	22.9	31.5	0.1	0.8	0.1	6.5	47.7	40.8	32.3	25.4
5	4.2	5.2	3.2	4.7	*	0.2	-	1.5	14.5	8.1	5.5	3.4
6	0.3	0.4	0.6	0.6	*	*	-	0.2	0.8	0.4	0.4	0.2
7	*	*	-	*	-	*	-	*	*	*	*	*
8	*	*	-	-	-	-	-	-	-	-	*	*
Average	3.28	3.31	3.17	3.35	1.52	1.75	1.69	2.19	3.76	3.53	3.34	3.19
HVI Trash 1/												
00	-	-	-	-	0.4	0.2	0.1	*	-	-	-	-
01	1.0	1.0	1.4	0.6	68.4	54.5	58.9	34.6	0.1	0.4	1.1	1.3
02	14.5	14.3	19.2	11.2	27.5	36.1	33.9	38.5	4.5	7.4	13.0	16.3
03	29.1	28.5	33.4	27.6	3.1	7.0	5.7	13.2	15.0	21.1	25.5	29.6
04	26.5	25.7	24.0	26.8	0.4	1.4	1.3	5.7	20.6	26.3	25.2	25.1
05	15.8	15.8	12.4	17.2	0.1	0.4	0.1	3.6	22.1	21.1	17.3	14.8
06	7.4	8.1	5.3	9.0	*	0.2	*	2.2	17.9	12.8	9.5	7.2
07	3.1	3.7	2.2	4.2	*	0.1	-	1.0	10.5	6.3	4.7	3.2
08	1.4	1.6	1.0	1.9	*	0.1	-	0.5	5.4	2.8	2.2	1.4
09	0.6	0.7	0.5	0.8	*	*	-	0.3	2.4	1.1	0.9	0.6
10	0.3	0.3	0.3	0.4	*	*	-	0.2	0.8	0.4	0.4	0.3
11	0.2	0.1	0.1	0.2	-	*	-	0.1	0.3	0.1	0.2	0.1
12	0.1	0.1	0.1	0.1	-	*	-	*	0.1	0.1	0.1	0.1
13	*	*	*	*	-	-	-	*	*	*	*	*
14	*	*	*	*	-	-	-	*	*	*	*	*
15	*	*	*	*	-	-	-	*	*	*	*	*
16	*	*	*	*	-	-	-	-	*	*	*	*
17	*	*	-	*	-	-	-	-	*	*	*	*
18 & Above	*	*	-	*	-	-	-	-	*	*	*	*
Average	0.39	0.40	0.36	0.41	0.14	0.16	0.15	0.22	0.51	0.45	0.41	0.38
UNIFORMITY 2/												
74 & Below	-	-	-	-	-	-	-	-	-	-	-	-
75	-	-	-	-	-	-	-	-	-	-	*	*
76	*	*	*	*	-	*	-	-	*	*	*	*
77	0.1	0.2	*	*	*	0.1	-	-	*	*	0.1	0.1
78	0.7	1.3	0.2	0.2	0.4	0.5	0.7	0.1	*	0.2	0.5	0.5
79	4.1	7.5	2.2	1.5	3.1	2.3	*	0.5	0.6	1.6	2.7	3.1
80	15.3	23.2	16.3	12.0	23.2	18.6	0.2	9.6	5.9	13.1	13.1	14.6
81	37.0	36.6	37.0	31.9	40.4	39.6	41.7	29.9	25.5	35.0	30.7	32.0
82	32.8	24.6	33.5	38.4	25.7	30.4	35.3	29.3	41.6	31.4	29.6	30.1
83	9.1	6.1	9.8	14.2	7.0	7.9	10.9	16.7	23.4	14.8	18.8	15.5
84	0.8	0.7	0.8	1.6	0.2	0.6	10.4	12.0	2.8	3.6	4.2	3.8
85 & Above	*	*	0.1	0.2	*	*	0.8	2.0	0.1	0.3	0.3	0.4
Average	81.73	81.41	81.80	82.02	81.55	81.69	82.33	82.40	82.34	82.02	82.05	81.97
Tenderable 3/	83.3	80.1	88.5	85.4	88.9	86.3	68.1	79.9	64.9	78.2	76.4	79.1
SAMPLES CLASSED	55,640	495,533	143,915	1,443,468	22,559	75,097	2,540	28,640	13,773	78,774	188,483	1,082,253

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 05, 2024

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	*	-	-	-	-	-	*	-	-	-	-
2.5 - 2.6	*	*	-	-	-	-	*	*	-	-	-	-
2.7 - 2.9	0.6	1.1	-	*	-	*	*	*	0.1	*	-	*
3.0 - 3.2	2.1	4.7	-	*	0.2	0.1	*	*	0.2	0.1	0.2	0.1
3.3 - 3.4	4.2	4.0	1.7	0.1	0.4	0.3	0.2	0.1	0.5	0.3	0.6	0.5
3.5 - 3.6	6.4	6.3	1.0	0.2	1.6	0.7	0.3	0.2	0.9	0.7	4.4	4.9
3.7 - 4.2	48.1	45.7	13.0	9.9	25.4	19.9	10.4	10.4	23.2	24.1	54.2	44.9
4.3 - 4.9	35.1	35.5	56.7	70.3	69.2	73.9	76.9	75.9	73.0	72.2	40.6	49.2
5.0 - 5.2	3.3	2.6	22.4	14.9	3.2	4.7	11.6	12.3	2.2	2.5	0.1	0.5
5.3 & Above	0.1	0.1	5.2	4.6	0.1	0.3	0.6	1.1	*	*	-	-
Average	4.13	4.10	4.64	4.67	4.42	4.48	4.62	4.63	4.42	4.43	4.17	4.24
Leaf												
1 - 2	20.7	32.8	32.4	20.0	32.4	21.8	9.1	7.0	5.9	8.4	77.2	74.8
3	37.4	41.2	46.2	45.7	56.6	62.3	41.8	42.4	45.2	48.9	21.2	22.2
4	14.5	14.4	17.6	28.4	10.4	14.9	38.7	40.0	38.6	35.0	1.6	2.7
5	11.3	6.3	3.0	5.6	0.5	0.9	9.6	9.7	9.5	6.9	-	0.3
6	10.8	3.8	0.4	0.4	*	*	0.8	0.8	0.8	0.6	-	*
7	4.8	1.4	0.3	*	-	-	*	*	*	0.1	-	-
8	0.5	0.2	0.1	*	-	-	-	-	*	*	-	-
Average	3.70	3.07	2.92	3.20	2.77	2.95	3.51	3.55	3.54	3.43	1.93	1.95
HVI Trash 1/												
00	-	-	-	-	-	-	-	*	-	-	-	0.2
01	4.9	11.4	5.6	4.1	6.2	2.6	1.2	0.8	0.3	0.7	43.5	43.4
02	22.8	27.5	30.0	19.1	34.6	24.7	11.9	8.6	7.6	10.5	36.5	33.3
03	21.8	24.1	27.4	23.6	33.7	35.2	22.4	20.2	20.7	23.6	14.2	14.2
04	11.0	13.8	15.9	21.4	16.4	21.9	23.8	24.4	24.4	25.0	4.8	5.6
05	6.5	7.2	9.7	15.2	6.1	10.0	19.0	20.2	19.9	18.8	1.0	2.1
06	4.9	4.1	6.3	8.9	1.9	3.7	11.2	13.0	13.4	11.3	0.1	0.7
07	4.0	2.8	2.7	4.5	0.6	1.2	5.8	7.0	7.5	5.7	-	0.2
08	3.9	2.1	1.2	2.0	0.2	0.4	2.6	3.3	3.5	2.6	-	0.2
09	3.7	1.8	0.7	0.8	0.1	0.2	1.2	1.4	1.6	1.1	-	0.1
10	3.9	1.4	0.3	0.3	*	0.1	0.5	0.6	0.7	0.4	-	*
11	3.6	1.2	0.2	0.1	*	*	0.2	0.2	0.3	0.2	-	*
12	3.2	0.9	*	*	*	*	0.1	0.1	0.1	0.1	-	-
13	2.3	0.6	0.1	*	*	*	*	*	*	0.1	-	-
14	1.7	0.4	-	*	*	*	*	*	*	*	-	-
15	1.0	0.3	-	*	*	*	*	*	*	*	-	-
16	0.5	0.1	*	*	-	-	*	*	*	*	-	-
17	0.3	0.1	-	*	-	-	*	*	*	*	-	-
18 & Above	0.2	0.1	*	*	-	-	*	*	*	*	-	-
Average	0.51	0.37	0.34	0.39	0.29	0.33	0.43	0.45	0.46	0.43	0.18	0.19
UNIFORMITY 2/												
74 & Below	-	*	-	-	-	-	-	-	-	-	-	-
75	*	*	-	*	-	-	-	*	-	-	-	-
76	0.2	0.4	*	*	*	*	-	*	-	-	0.2	*
77	0.7	1.4	*	*	*	*	*	0.1	*	*	0.5	0.1
78	7.4	5.9	0.4	0.1	0.2	0.3	0.4	0.5	0.1	0.2	1.5	0.3
79	29.6	18.1	4.4	1.8	2.8	1.9	3.7	3.7	1.8	3.1	27.1	7.0
80	28.6	31.3	13.3	13.8	12.7	10.4	21.2	19.9	12.6	19.3	35.9	23.7
81	27.2	32.6	40.3	33.8	32.2	31.8	42.6	37.6	35.7	38.8	21.6	33.1
82	6.0	9.8	36.2	33.8	40.1	40.7	24.5	27.5	36.0	30.2	11.0	31.9
83	0.2	0.5	4.4	14.2	10.7	13.9	6.9	9.5	12.7	7.7	2.4	3.8
84	*	*	0.8	2.3	1.2	1.0	0.7	1.1	1.2	0.7	-	*
85 & Above	-	-	*	0.2	0.1	0.1	*	0.2	*	*	-	-
Average	80.36	80.62	81.65	81.97	81.91	82.01	81.56	81.67	81.93	81.66	80.67	81.46
Tenderable 3/	51.5	68.8	66.2	78.3	95.4	90.9	77.6	78.2	93.0	93.0	99.0	97.8
SAMPLES CLASSED	17,606	86,675	4,857	309,370	74,568	693,440	72,471	1,077,391	110,887	554,275	1,743	10,419

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE For The Week Ending Dec 05, 2024										
Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE										
2.4 & Below	-	-	-	-	-	-	*	*	-	-
2.5 - 2.6	-	*	-	-	-	-	0.1	*	-	-
2.7 - 2.9	*	0.1	-	-	*	*	0.9	0.4	*	*
3.0 - 3.2	1.0	0.7	*	*	0.2	0.2	3.2	1.3	*	*
3.3 - 3.4	0.6	1.1	*	*	0.7	0.5	4.0	1.7	0.7	0.3
3.5 - 3.6	5.6	3.6	0.3	0.2	1.8	1.0	6.4	3.2	2.3	1.6
3.7 - 4.2	33.3	43.1	17.7	14.4	28.5	32.4	34.0	29.2	51.0	47.4
4.3 - 4.9	56.4	48.6	75.7	77.3	66.8	64.6	47.3	59.2	46.0	50.7
5.0 - 5.2	3.2	2.7	6.0	7.6	1.9	1.3	3.8	4.5	*	*
5.3 & Above	-	0.1	0.3	0.4	-	*	0.3	0.5	-	-
Average	4.29	4.26	4.52	4.55	4.39	4.35	4.20	4.35	4.19	4.22
Leaf										
1 - 2	49.4	72.3	4.2	7.3	20.6	27.8	36.7	38.5	12.1	11.4
3	33.9	22.0	44.2	47.7	62.2	58.5	37.2	36.2	56.4	60.0
4	13.7	4.9	42.5	36.7	15.8	12.8	16.7	19.6	26.1	25.5
5	2.6	0.8	8.8	7.7	1.4	0.9	6.2	4.7	4.9	2.9
6	0.3	0.1	0.4	0.6	0.1	*	2.0	0.8	0.4	0.2
7	0.1	*	-	*	-	-	0.6	0.1	*	*
8	*	*	-	*	-	-	0.5	0.1	*	*
Average	2.56	2.08	3.57	3.47	2.98	2.86	2.95	2.83	3.25	3.21
HVI Trash 1/										
00	0.1	0.3	-	-	-	-	0.2	0.1	-	-
01	24.3	38.9	0.2	0.6	2.3	4.7	14.9	18.0	0.6	0.6
02	27.5	35.4	6.4	9.6	26.4	29.1	26.1	22.9	14.1	13.5
03	17.1	13.6	20.8	23.3	35.7	33.8	21.0	18.6	29.6	30.9
04	13.1	5.7	25.2	25.4	20.8	19.4	14.1	15.8	24.5	26.4
05	8.8	3.0	21.4	19.1	9.0	8.2	8.8	10.9	15.7	15.8
06	4.3	1.6	14.2	11.6	3.4	3.1	5.4	6.4	8.8	7.7
07	2.2	0.8	7.1	5.9	1.4	1.1	3.4	3.5	4.3	3.3
08	1.2	0.4	3.0	2.7	0.5	0.4	2.2	1.8	1.4	1.1
09	0.7	0.2	1.1	1.1	0.2	0.2	1.4	0.9	0.6	0.4
10	0.2	0.1	0.4	0.4	0.1	0.1	0.9	0.5	0.2	0.2
11	0.1	*	0.2	0.2	0.1	*	0.5	0.2	0.1	0.1
12	0.1	*	*	0.1	*	*	0.3	0.1	*	*
13	0.1	*	*	*	*	*	0.2	0.1	*	*
14	*	*	*	*	*	*	0.1	*	*	*
15	*	*	*	*	*	*	0.1	*	-	-
16	*	*	-	*	-	-	0.1	*	-	*
17	*	*	-	-	-	-	0.1	*	-	*
18 & Above	*	*	-	*	-	-	0.2	*	-	*
Average	0.29	0.21	0.46	0.44	0.33	0.31	0.35	0.33	0.40	0.39
UNIFORMITY 2/										
74 & Below	*	*	-	-	-	-	0.1	*	-	-
75	0.1	0.2	-	-	-	-	0.2	0.2	-	-
76	0.7	0.5	-	-	*	*	0.9	0.6	-	-
77	0.7	1.3	-	-	*	0.1	3.2	1.9	-	-
78	3.7	3.7	*	0.1	0.1	0.5	9.5	5.4	0.1	0.3
79	11.7	10.6	0.7	1.1	1.3	4.3	22.2	13.0	1.4	3.3
80	17.0	19.0	9.9	11.8	12.0	18.9	31.5	24.7	14.6	24.1
81	28.0	27.9	41.1	37.3	39.0	38.7	22.6	30.9	38.5	34.8
82	29.4	25.9	38.4	37.0	40.6	30.4	8.1	18.3	31.3	28.9
83	8.6	10.1	9.4	11.9	6.9	6.7	1.6	4.5	12.6	7.9
84	0.1	0.9	0.4	0.8	0.1	0.4	0.2	0.5	1.5	0.7
85 & Above	-	*	*	*	*	*	*	*	0.1	*
Average	81.35	81.34	81.92	81.94	81.84	81.61	80.34	80.95	81.88	81.60
Tenderable 3/	67.1	84.8	87.6	87.5	94.3	86.0	72.4	78.8	97.4	97.6
SAMPLES CLASSED	13,374	107,721	35,046	208,347	40,957	507,232	275,254	2,827,924	29,229	129,711

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE									
For The Week Ending Dec 05, 2024									
Color Grade	Leaf	Arizona		California		New Mexico		Texas	
		Week	Season	Week	Season	Week	Season	Week	Season
01	1	76.6	75.3	18.5	17.9	-	35.8	13.1	18.7
	2	5.0	3.4	16.4	12.7	-	18.7	42.0	37.4
	3	-	-	0.2	0.1	-	0.3	5.7	6.7
	4	-	-	-	-	-	-	0.1	0.4
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		81.6	78.8	35.1	30.7	-	54.9	60.9	63.2
02	1	16.0	19.1	14.1	19.4	-	19.3	9.4	9.2
	2	2.1	1.9	40.5	41.3	-	24.1	24.7	24.7
	3	-	-	3.8	3.1	-	1.5	2.7	2.1
	4	-	-	*	*	-	-	0.3	0.1
	5	-	-	-	-	-	-	0.1	*
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		18.2	21.0	58.4	63.9	-	44.9	37.1	36.1
03	1	-	*	0.2	0.5	-	*	-	*
	2	0.2	0.1	3.2	3.4	-	0.2	0.6	0.3
	3	-	-	2.3	1.1	-	*	0.9	0.3
	4	-	-	0.1	0.1	-	-	0.3	0.1
	5	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		0.2	0.2	5.8	5.1	-	0.3	1.8	0.6
04	1	-	-	*	*	-	-	-	-
	2	-	-	0.3	0.2	-	-	*	*
	3	-	-	0.3	0.1	-	-	0.1	*
	4	-	-	*	*	-	-	0.1	*
	5	-	-	*	*	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	0.6	0.3	-	-	0.2	*
05	1	-	-	-	*	-	-	-	-
	2	-	*	*	*	-	-	-	-
	3	-	-	*	*	-	-	-	-
	4	-	-	*	*	-	-	-	-
	5	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	*	0.1	*	-	-	-	-
06	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	-	-	-	-	-	-
07	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	-	-	-	-	-	-
STAPLE									
44 & Shorter		-	-	*	0.1	-	1.7	10.4	18.8
46		1.2	3.8	3.0	5.2	-	16.9	47.2	53.6
48		63.9	66.9	14.2	21.9	-	62.4	42.1	25.8
50		34.4	28.6	57.8	54.2	-	18.8	0.3	1.7
52 & Longer		0.5	0.8	24.9	18.6	-	0.2	*	*
Average Staple		48.69	48.53	50.09	49.72	-	47.98	46.64	46.21
Average Length		1.42	1.41	1.45	1.44	-	1.39	1.36	1.35
EXTRANEIOUS MATTER									
Bark		-	-	-	*	-	0.1	-	-
Grass		-	-	*	*	-	-	0.1	*
Spindle Twist		-	-	0.1	0.1	-	-	0.3	0.1
Preparation		-	-	-	*	-	-	-	*
All Other		-	-	*	*	-	*	0.1	0.1

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE For The Week Ending Dec 05, 2024								
Quality Designation	Arizona		California		New Mexico		Texas	
	Week	Season	Week	Season	Week	Season	Week	Season
MIKE								
2.4 & Below	-	-	-	-	-	-	-	-
2.5 - 2.6	-	-	*	*	-	-	-	-
2.7 - 2.9	-	*	0.6	0.3	-	0.1	*	*
3.0 - 3.2	1.2	0.4	2.5	1.8	-	5.2	0.1	0.7
3.3 - 3.4	0.1	0.1	6.9	5.0	-	11.5	6.3	5.0
3.5 - 3.6	14.0	4.4	21.0	16.8	-	19.9	23.3	16.1
3.7 - 4.2	82.5	91.9	68.8	75.3	-	57.3	69.0	77.8
4.3 - 4.9	2.2	3.2	0.2	0.7	-	6.1	1.2	0.4
5.0 - 5.2	-	-	*	*	-	-	-	-
5.3 & Above	-	-	-	*	-	-	-	-
Average	3.90	3.93	3.74	3.78	-	3.76	3.76	3.79
ALL RANGE MIKE								
2.4 & Below	-	-	-	-	-	-	-	-
2.5	-	-	-	-	-	-	-	-
2.6	-	-	*	*	-	-	-	-
2.7	-	-	0.1	*	-	*	*	*
2.8	-	-	0.2	0.1	-	*	-	-
2.9	-	*	0.3	0.2	-	*	-	-
3.0	-	-	0.6	0.3	-	0.1	-	0.1
3.1	0.1	*	0.8	0.6	-	1.1	0.1	*
3.2	1.2	0.4	1.1	0.9	-	4.0	*	0.5
3.3	0.1	*	2.1	1.7	-	3.9	0.2	1.6
3.4	-	*	4.8	3.3	-	7.6	6.2	3.4
3.5	3.5	1.1	8.2	6.3	-	8.1	6.7	4.6
3.6	10.4	3.3	12.8	10.6	-	11.7	16.6	11.5
3.7	9.2	5.4	17.7	17.3	-	11.1	22.8	14.3
3.8	8.5	13.2	17.2	19.3	-	11.3	13.5	24.4
3.9	18.6	30.1	14.9	17.5	-	10.7	15.1	21.6
4.0	26.5	28.7	12.3	11.8	-	13.5	12.4	11.3
4.1	17.5	12.0	5.3	7.1	-	6.4	1.3	3.8
4.2	2.2	2.4	1.3	2.3	-	4.3	3.9	2.3
4.3	0.8	0.9	0.1	0.6	-	5.7	1.2	0.4
4.4	1.4	2.1	*	0.1	-	0.4	*	*
4.5	-	0.2	*	*	-	*	-	*
4.6	-	-	*	*	-	*	-	*
4.7	-	-	*	*	-	-	-	-
4.8	-	-	*	*	-	-	-	-
4.9	-	-	-	-	-	-	-	-
5.0	-	-	*	*	-	-	-	-
5.1	-	-	-	-	-	-	-	-
5.2	-	-	-	-	-	-	-	-
5.3 & Above	-	-	-	*	-	-	*	*
Average	3.90	3.93	3.74	3.78	-	3.76	3.76	3.79
STRENGTH 1/								
36 & Below	0.1	*	0.7	1.0	-	16.3	26.8	29.7
37	-	-	1.5	2.7	-	14.6	17.8	20.2
38	-	*	3.0	5.2	-	3.2	16.4	26.8
39	-	*	2.8	4.6	-	1.7	2.6	4.0
40	-	0.2	2.1	3.1	-	0.1	0.1	0.2
41	9.4	3.3	4.1	5.6	-	2.5	0.8	0.3
42	8.0	14.9	10.1	11.6	-	10.3	2.6	0.7
43	32.5	33.9	18.3	18.8	-	14.4	5.5	2.4
44	29.9	25.9	23.4	21.3	-	14.2	7.2	3.3
45	14.3	14.3	22.9	17.1	-	16.2	7.2	4.9
46	4.4	5.3	6.7	6.6	-	5.2	7.0	3.6
47	1.1	1.9	3.1	1.8	-	1.0	5.5	3.5
48 & Above	0.5	0.3	1.2	0.5	-	0.3	0.5	0.6
Average	44.00	44.02	43.88	43.29	-	41.70	39.69	38.68
UNIFORMITY								
83 & Below	-	-	0.3	0.3	-	*	13.2	10.9
84	-	0.2	6.5	5.7	-	10.8	29.4	36.4
85	21.8	12.9	19.6	21.5	-	39.2	32.3	41.9
86	49.3	59.7	61.4	54.6	-	44.1	24.2	10.3
87	28.8	26.9	11.3	16.8	-	5.8	0.8	0.4
88 & Above	0.2	0.3	0.9	1.1	-	0.1	0.1	*
Average	86.51	86.58	86.25	86.30	-	85.92	85.05	84.92
Samples Classed	1,303	4,186	33,385	172,335	-	11,072	3,036	12,580

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
 * Less than 0.05 percent.