



Volume 65, No.21

Classing Office	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
Abilene	33	64.8	47.3	55,276	33	70.2	52.3	333,983
Corpus Christi	5	88.1	67.6	2,864	48	82.1	45.4	991,389
Dumas	13	50.8	26.0	22,676	37	59.1	33.3	964,113
Florence	41	74.3	56.3	109,843	48	71.0	51.3	1,032,562
Lamesa	23	65.7	41.6	39,072	28	74.1	50.3	215,333
Lubbock	52	55.3	32.8	139,942	56	67.5	43.6	1,132,958
Macon	74	87.1	74.3	259,740	77	89.7	75.9	1,872,639
Memphis	59	89.5	74.1	190,853	73	89.1	72.7	2,713,941
Rayville	5	67.1	36.3	2,255	20	62.8	37.0	249,035
Visalia	15	88.5	74.7	26,973	24	87.6	69.7	147,623
United States	320	77.3	60.4	849,494	444	79.4	58.7	9,653,576
AMERICAN PIMA								
Visalia	15			23,881	20			195,534
United States	15			23,881	20			195,534
United States all cotton	333			873,375	458			9,849,110

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Dec 14, 2023

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	11.7	25.0	-	28.1	3.8	4.3	5.2	4.8	23.6	44.8
	3	6.3	8.5	0.1	18.7	4.2	3.6	3.6	3.4	5.4	7.3
	4	0.3	1.1	-	1.7	0.2	0.1	0.2	0.2	0.2	0.3
	5	*	0.1	-	*	-	*	*	*	-	*
	6	-	*	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	18.3 34.6	0.1 48.6	8.1 8.0	8.9 8.4	29.2 52.4	29.2 52.4	29.2 52.4	29.2 52.4	29.2 52.4
31	1 - 2	10.2	7.7	0.2	2.6	2.2	7.9	9.0	10.8	9.3	7.2
	3	22.1	16.3	6.2	6.0	26.2	35.5	37.0	42.9	22.3	14.5
	4	6.5	5.6	7.0	1.8	16.5	13.0	11.9	14.0	7.5	4.6
	5	0.8	1.2	1.6	0.1	1.3	0.9	0.9	1.0	1.1	0.7
	6	*	0.1	-	*	*	*	*	*	0.1	0.1
	7	-	*	-	*	-	-	*	*	*	*
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	39.7 31.0	15.1 10.5	46.2 57.2	58.8 68.7	40.3 26.9	40.3 26.9	40.3 26.9	40.3 26.9	40.3 26.9
41	1 - 2	0.7	0.5	4.7	0.4	0.2	0.3	0.6	0.3	0.2	0.1
	3	4.8	3.7	13.9	2.0	11.3	9.4	11.1	7.2	2.2	1.1
	4	4.8	3.7	26.8	1.2	25.7	17.2	15.2	11.0	3.5	2.0
	5	3.0	2.2	7.2	0.2	6.8	5.8	3.5	3.2	2.0	1.5
	6	1.5	0.9	0.1	*	0.2	0.6	0.4	0.3	0.7	0.7
	7	0.4	0.2	-	*	*	*	0.1	*	0.2	0.3
	8	*	*	-	*	-	*	-	-	*	*
	Total	----	15.3 11.2	52.7 3.7	44.2 33.3	30.9 22.0	8.8 5.7	8.8 5.7	8.8 5.7	8.8 5.7	8.8 5.7
51	1 - 2	-	*	-	*	-	*	*	*	-	*
	3	*	*	0.7	0.3	*	*	0.2	*	*	*
	4	*	*	15.1	0.3	0.2	0.1	0.2	0.1	*	*
	5	0.1	0.1	6.9	0.1	0.1	*	0.2	*	*	*
	6	0.1	0.1	1.7	*	-	*	0.1	*	*	*
	7	0.1	0.1	0.1	*	-	*	*	*	*	0.1
	8	0.1	0.1	-	-	-	*	-	-	*	*
	Total	----	0.5 0.4	24.5 0.8	0.3 0.2	0.7 0.2	0.1 0.1	0.1 0.1	0.1 0.1	0.1 0.1	0.1 0.1
61	1 - 2	-	-	-	*	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	-
	4	-	-	-	*	-	-	-	*	-	-
	5	-	-	-	*	-	*	-	-	-	-
	6	-	-	0.1	*	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	- *	0.1 *	- *	- *	- *	- *	- *	- *	- *
71	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	-
	4	-	-	-	*	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	- -	- *	- -	- -	- -	- -	- -	- -	- -
12 & 22	1 - 2	1.8	4.0	-	17.9	-	*	*	*	4.4	5.3
	3	1.8	3.7	-	8.7	-	*	*	*	3.3	2.2
	4	0.2	0.9	-	1.0	-	*	*	*	0.3	0.2
	5	*	*	-	0.1	-	*	-	*	*	*
	6	-	*	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	3.8 8.6	- 27.7	- *	* *	8.0 7.6	8.0 7.6	8.0 7.6	8.0 7.6	8.0 7.6
32	1 - 2	1.4	0.8	-	0.8	-	*	*	*	1.7	1.1
	3	5.4	2.9	0.1	2.0	0.1	0.4	0.1	0.2	4.6	2.6
	4	3.3	2.3	1.0	0.9	*	0.1	0.1	0.1	2.3	1.2
	5	0.4	0.7	0.6	0.2	-	*	*	*	0.4	0.2
	6	*	0.1	-	*	-	*	*	*	0.1	*
	7	-	*	-	*	-	*	-	-	*	*
	8	-	-	-	*	-	-	-	-	-	-
	Total	----	10.5 6.9	1.7 3.8	0.1 0.6	0.2 0.4	9.1 5.2	9.1 5.2	9.1 5.2	9.1 5.2	9.1 5.2
42	1 - 2	0.1	*	-	0.2	-	*	-	*	*	*
	3	0.6	0.4	0.5	0.8	0.2	0.2	*	0.1	0.2	0.1
	4	2.5	1.2	1.2	0.4	0.4	0.3	0.2	0.1	0.4	0.2
	5	2.8	1.5	1.0	0.1	0.2	0.1	0.1	0.1	0.4	0.2
	6	1.7	1.1	0.4	*	*	*	*	*	0.2	0.1
	7	0.7	0.4	*	*	-	*	*	*	0.2	*
	8	0.1	0.1	-	*	-	*	-	-	*	*
	Total	----	8.6 4.7	3.1 1.6	0.8 0.6	0.3 0.3	1.4 0.6	1.4 0.6	1.4 0.6	1.4 0.6	1.4 0.6

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Dec 14, 2023

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	*	*	-	*	-	-	-	-	-	-
	3	*	*	*	0.2	*	*	-	*	*	*
	4	*	*	0.3	0.1	0.1	*	*	*	*	*
	5	0.1	*	0.7	*	*	*	*	*	*	*
	6	0.2	0.1	0.4	*	-	*	-	*	*	*
	7	0.3	0.1	0.1	*	*	*	-	*	*	*
	8	0.2	0.1	-	-	-	*	-	-	-	*
Total	----	0.8	0.3	1.5	0.4	0.1	*	*	*	*	*
62	1 - 2	-	-	-	*	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	-
	4	-	-	-	*	-	-	-	*	-	-
	5	-	-	-	*	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-
	7	-	-	-	*	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	-	-	-	*	-	-
13 & 23	1 - 2	0.2	0.3	-	1.1	-	-	-	*	0.5	0.3
	3	0.1	0.4	-	0.8	-	-	-	*	0.6	0.2
	4	0.1	0.1	-	0.2	-	*	*	*	0.1	*
	5	*	*	-	*	-	*	-	-	*	*
	6	-	-	-	*	-	*	-	-	-	-
	7	-	-	-	*	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	0.4	0.8	-	2.1	-	*	*	*	1.2	0.5
33	1 - 2	0.2	0.1	-	0.1	-	*	-	*	0.4	0.2
	3	0.7	0.4	*	0.2	-	*	*	*	0.8	0.4
	4	0.4	0.3	-	0.2	-	*	*	*	0.3	0.2
	5	0.1	0.1	*	0.1	-	*	*	*	0.1	*
	6	*	*	-	*	-	*	-	-	*	*
	7	-	*	-	*	-	-	-	-	*	*
	8	-	-	-	-	-	-	-	-	-	-
Total	----	1.3	0.9	0.1	0.6	-	*	*	*	1.7	0.8
43	1 - 2	*	*	-	*	-	*	-	*	*	*
	3	0.1	*	0.1	*	-	*	*	*	*	*
	4	0.2	0.1	0.3	*	-	*	*	*	0.1	*
	5	0.2	0.2	0.1	*	*	*	*	*	*	*
	6	0.1	0.1	*	*	-	*	*	*	*	*
	7	0.1	*	-	*	-	-	-	*	*	*
	8	*	*	-	*	-	*	-	-	-	-
Total	----	0.7	0.4	0.5	0.2	*	*	0.1	*	0.2	0.1
53	1 - 2	-	-	-	*	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	-
	4	*	*	0.3	*	*	*	-	*	-	-
	5	*	*	*	*	*	*	-	*	-	-
	6	*	*	-	*	-	-	*	*	-	-
	7	*	*	-	*	-	-	-	*	-	-
	8	*	*	-	*	-	-	-	-	-	-
Total	----	*	*	0.3	*	*	*	*	*	-	-
63	1 - 2	-	-	-	*	-	-	-	-	-	*
	3	-	-	-	*	-	-	-	-	-	-
	4	-	-	0.2	*	-	-	-	-	-	-
	5	-	-	0.1	*	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	0.2	*	-	-	-	-	-	*
24 - 54	1 - 8	0.1	0.1	-	*	-	*	*	*	*	0.1
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	*	*	-	*	-	-	-	-	-	*
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		-	*	0.1	*	-	-	-	-	-	-
30		*	*	0.3	*	-	-	-	*	*	*
31		0.1	0.3	0.2	0.3	-	-	*	*	0.6	0.4
32		1.8	1.7	0.3	1.7	*	*	0.1	0.1	1.9	1.8
33		4.9	3.8	1.2	6.5	0.1	0.4	1.0	1.7	6.1	6.0
34		9.2	8.3	1.5	19.0	1.4	3.1	7.0	8.3	16.9	14.9
35		16.9	14.5	5.2	27.6	5.2	9.4	20.6	21.3	28.9	24.7
36		21.3	20.9	17.2	22.2	18.3	21.8	30.9	31.9	24.5	25.0
37		27.1	28.2	22.6	14.6	46.4	44.3	31.2	29.0	15.4	20.4
38		9.8	13.5	25.6	5.4	21.4	16.4	6.7	6.1	3.3	5.2
39		6.2	6.5	24.9	2.3	5.9	4.1	1.9	1.4	2.1	1.4
40 & Longer		2.7	2.3	0.8	0.3	1.3	0.5	0.6	0.2	0.3	0.3
Average Staple		36.18	36.34	37.35	35.40	37.04	36.75	36.15	36.03	35.38	35.54
Average Length		1.13	1.13	1.17	1.10	1.16	1.15	1.13	1.12	1.10	1.11

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Dec 14, 2023

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	20.9	35.0	1.9	2.5	10.3	11.1	-	3.2	67.1	68.7
	3	7.0	10.3	2.1	2.3	7.0	4.9	0.1	2.1	7.7	7.2
	4	0.2	0.4	0.3	0.2	0.4	0.2	-	*	0.1	0.4
	5	*	*	*	*	*	*	-	*	-	*
	6	-	*	*	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	28.1 45.8	4.2 5.0	17.7 16.3	0.1 5.3	74.9 76.3				
31	1 - 2	13.4	10.3	5.0	9.0	16.4	18.9	3.0	7.0	11.1	7.1
	3	25.8	20.4	19.3	32.8	39.0	39.7	5.1	22.2	11.2	7.3
	4	6.1	5.3	7.7	11.7	7.8	9.7	1.2	6.1	1.8	3.2
	5	0.4	0.4	1.0	1.2	0.7	0.7	*	0.3	0.1	0.6
	6	*	*	0.1	0.1	0.1	*	-	*	-	*
	7	-	*	*	*	*	*	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	45.7 36.5	33.0 54.7	64.0 69.1	9.3 35.6	24.2 18.2				
41	1 - 2	0.1	0.1	2.1	1.3	1.1	0.6	1.5	1.2	0.1	0.1
	3	1.5	0.9	21.9	15.2	9.1	6.1	13.6	15.8	0.1	0.1
	4	2.7	1.6	21.3	14.6	6.0	5.8	17.4	16.1	0.1	0.2
	5	1.3	0.8	6.5	4.2	1.2	1.7	5.8	3.9	0.1	0.2
	6	0.3	0.3	1.1	0.6	0.2	0.2	1.1	0.3	*	0.1
	7	0.1	0.1	0.2	0.1	*	*	*	*	-	-
	8	*	*	*	*	-	-	-	*	-	-
	Total	----	6.0 3.7	53.1 35.9	17.6 14.4	39.3 37.5	0.5 0.6				
51	1 - 2	-	*	0.1	*	*	*	-	*	-	-
	3	*	*	1.9	0.4	0.1	*	1.6	0.2	-	-
	4	-	*	2.4	0.5	0.1	*	11.1	0.6	-	-
	5	*	*	1.0	0.2	*	*	6.9	0.7	-	*
	6	*	*	0.3	0.1	*	*	1.8	0.1	-	*
	7	*	*	*	*	*	*	0.1	*	-	-
	8	*	*	*	*	-	-	-	-	-	-
	Total	----	* *	5.7 1.3	0.2 0.1	21.6 1.6	- *				
61	1 - 2	-	*	*	*	-	*	-	-	-	-
	3	-	-	*	*	-	*	-	-	-	-
	4	-	-	*	*	-	*	0.2	*	-	-
	5	-	-	*	*	-	*	0.3	*	-	-
	6	-	-	*	*	-	*	-	*	-	-
	7	-	-	*	*	-	*	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	- *	* *	- *	0.4 *	- -				
71	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	*	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	- *	- -	- -	- -	- -				
12 & 22	1 - 2	3.0	3.3	*	*	*	*	-	1.7	*	2.4
	3	2.1	2.6	*	*	*	*	0.2	1.2	*	0.9
	4	0.2	0.4	*	*	*	*	0.1	0.1	-	*
	5	*	*	*	*	-	-	*	*	-	-
	6	*	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	5.3 6.3	* *	* *	0.4 3.0	* 3.4				
32	1 - 2	1.7	0.8	*	0.1	*	*	-	0.9	0.1	0.2
	3	4.9	2.7	0.3	0.5	0.1	*	1.9	3.7	0.1	0.5
	4	2.0	1.3	0.2	0.3	0.1	*	2.9	1.4	0.1	0.3
	5	0.3	0.3	0.1	*	*	*	0.3	0.2	-	0.1
	6	*	*	*	*	*	*	-	*	-	*
	7	*	*	*	*	-	-	-	*	-	-
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	9.0 5.1	0.7 0.9	0.1 0.1	5.1 6.3	0.3 1.2				
42	1 - 2	*	*	*	*	*	*	*	0.4	-	*
	3	0.3	0.1	0.5	0.6	*	*	2.3	3.8	*	*
	4	0.9	0.3	0.8	0.8	0.1	*	5.5	3.8	*	*
	5	0.9	0.4	0.5	0.3	0.1	*	5.3	1.3	*	*
	6	0.5	0.2	0.2	0.1	*	*	5.2	0.3	-	*
	7	0.2	0.1	0.1	*	*	*	0.7	*	-	-
	8	0.1	*	*	*	-	-	-	-	-	-
	Total	----	2.9 1.2	2.1 1.8	0.3 0.1	18.9 9.5	* 0.1				

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Dec 14, 2023

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	*	*	-	*	-	*	-	-
	3	*	*	0.2	0.1	*	*	0.2	0.1	-	-
	4	*	*	0.4	0.1	*	*	0.8	0.2	-	-
	5	*	*	0.2	*	*	*	0.7	0.2	-	-
	6	*	*	0.1	*	*	*	1.4	0.1	-	-
	7	*	*	*	*	*	*	1.3	*	-	-
	8	0.1	*	*	*	-	-	-	-	-	-
Total	----	0.1	0.1	1.0	0.2	*	*	4.4	0.7	-	-
62	1 - 2	-	-	*	*	-	-	-	-	-	-
	3	-	-	*	*	-	-	-	*	-	-
	4	-	-	*	*	-	-	-	*	-	-
	5	-	-	*	*	-	-	-	-	-	-
	6	-	-	*	*	-	-	*	*	-	-
	7	-	*	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
Total	----	-	*	*	*	-	-	*	*	-	-
13 & 23	1 - 2	0.2	0.1	*	*	-	-	-	*	*	0.1
	3	0.3	0.2	-	-	-	-	-	0.1	-	*
	4	*	0.1	-	-	-	-	-	*	-	-
	5	-	*	-	-	-	-	-	*	-	-
	6	-	*	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	0.5	0.4	*	*	-	-	-	0.2	*	0.1
33	1 - 2	0.3	0.1	*	*	*	*	-	*	-	*
	3	0.9	0.3	*	*	*	*	-	*	*	*
	4	0.4	0.2	*	*	*	*	*	*	-	*
	5	0.1	0.1	*	*	*	*	*	*	-	-
	6	*	*	*	*	-	-	-	*	-	-
	7	-	*	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
Total	----	1.7	0.7	*	*	*	*	0.1	0.1	*	0.1
43	1 - 2	*	*	*	*	-	*	-	*	-	-
	3	*	*	*	*	*	*	-	*	-	*
	4	0.2	0.1	0.1	*	*	*	-	0.1	-	*
	5	0.2	0.1	*	*	*	*	*	0.1	-	*
	6	0.1	0.1	*	*	*	*	0.1	0.1	-	-
	7	*	*	*	*	-	-	-	*	-	-
	8	*	*	*	*	-	-	-	-	-	-
Total	----	0.5	0.3	0.1	*	*	*	0.1	0.2	-	*
53	1 - 2	-	-	*	*	-	*	-	-	-	-
	3	-	*	*	*	*	*	-	*	-	-
	4	*	*	*	*	-	*	-	*	-	-
	5	-	*	*	*	*	*	0.1	*	-	-
	6	*	*	*	*	*	*	0.1	*	-	-
	7	-	*	*	*	*	*	-	*	-	-
	8	*	*	-	-	-	-	-	-	-	-
Total	----	*	*	*	*	*	*	0.2	*	-	-
63	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	*	*	*	*	-	-	-	*	-	-
	5	-	*	*	*	-	-	-	-	-	-
	6	-	-	*	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
Total	----	*	*	*	*	-	-	-	*	-	-
24 - 54	1 - 8	0.1	0.1	*	*	-	-	-	*	-	-
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	*	*	-	*	-	-	-	-	-	-
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		*	*	-	-	-	-	-	-	-	-
30		0.1	0.1	-	*	-	*	-	-	-	-
31		1.0	0.6	*	*	-	*	-	*	-	-
32		3.4	2.1	0.3	0.3	*	*	1.0	0.4	*	*
33		8.3	5.6	1.7	1.7	0.2	0.1	3.3	2.4	0.1	0.1
34		15.9	11.9	7.1	7.2	1.0	0.4	16.3	7.4	0.6	1.1
35		23.0	19.3	16.6	18.0	4.8	5.0	20.4	16.4	4.3	7.5
36		23.5	23.2	25.6	28.1	15.9	19.5	14.8	26.8	12.9	18.2
37		17.5	23.0	33.7	32.7	49.1	48.8	27.1	29.8	32.3	33.7
38		5.3	8.9	10.9	9.4	23.1	20.8	12.5	11.5	27.9	20.8
39		1.8	3.8	3.4	2.3	5.3	4.7	1.2	4.5	16.8	13.4
40 & Longer		0.2	1.4	0.7	0.4	0.7	0.7	3.2	0.7	5.1	5.1
Average Staple		35.36	35.86	36.31	36.21	37.07	37.01	36.03	36.29	37.55	37.27
Average Length		1.10	1.12	1.13	1.13	1.16	1.16	1.12	1.13	1.17	1.16

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Dec 14, 2023

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	11.9	9.2	1.3	0.1	*	*	2.1	1.3	7.7	4.1
Bark - Level 2	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	*	0.6	*	0.4	*	*	0.3	0.3	0.1	0.2
Grass - Level 2	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	*	-	*	-	-	*	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	*	*	*	0.6	-	*	-	*	*	0.2
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	*	-	*	-	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	-	*	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	0.1	*	*	*	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/22 & Below	*	0.1	0.6	0.5	-	-	-	-	*	*
23	0.1	0.2	*	0.6	-	-	-	-	*	*
24	0.1	0.3	*	1.4	-	*	*	*	0.3	0.2
25	0.4	0.8	0.4	2.7	*	*	*	*	1.1	0.7
26	1.0	1.5	0.4	5.0	*	0.1	0.1	0.1	3.7	2.5
27	3.5	3.3	1.6	8.2	0.1	0.8	1.3	0.9	7.7	5.6
28	7.3	6.2	1.1	11.3	0.8	3.5	7.2	5.3	14.4	11.0
29	12.8	10.0	8.7	14.1	7.4	11.4	24.5	17.2	20.8	16.1
30	16.8	14.3	23.8	14.8	18.1	23.6	30.5	28.0	21.2	19.9
31	19.8	16.5	15.6	12.6	28.7	29.8	20.7	25.9	14.5	18.1
32	12.9	14.9	15.7	10.6	25.7	19.3	11.1	14.4	7.5	12.0
33	11.2	14.0	14.5	8.7	12.4	7.7	3.4	6.1	5.0	7.6
34	8.3	11.3	9.1	5.4	5.1	2.6	0.9	1.7	2.5	4.0
35	4.4	5.2	5.2	2.8	1.5	0.8	0.2	0.4	0.9	1.6
36	1.0	1.2	2.0	1.1	0.2	0.2	*	0.1	0.3	0.6
37	0.4	0.3	0.9	0.2	*	*	-	*	0.1	0.1
38	*	*	0.2	*	-	-	-	-	*	*
39	*	*	0.1	*	-	-	-	-	-	*
40 & Above	*	*	-	-	-	-	-	-	-	*
Average	31.43	31.68	31.93	30.36	31.81	31.31	30.60	30.97	30.11	30.69
Mike										
2.4 & Below	0.1	*	-	*	-	-	-	-	-	*
2.5	0.2	0.1	-	*	-	*	-	*	*	*
2.6	0.3	0.2	-	0.1	-	*	-	*	0.1	*
2.7	0.8	0.3	-	0.1	*	*	*	*	0.2	*
2.8	0.4	0.4	-	0.1	-	*	*	*	*	*
2.9	0.3	0.6	-	0.2	-	*	*	*	0.1	*
3.0	0.8	1.0	-	0.2	-	*	*	*	0.1	0.1
3.1	0.7	1.2	-	0.4	-	*	*	*	*	0.1
3.2	1.0	1.4	-	0.6	-	*	*	*	0.3	0.2
3.3	1.0	1.6	-	0.8	-	*	0.1	0.1	0.5	0.4
3.4	1.5	2.2	-	1.1	*	*	0.2	0.1	0.7	0.5
3.5	2.1	2.7	-	1.3	*	*	0.3	0.2	0.7	0.6
3.6	2.6	3.0	0.5	1.7	*	*	0.4	0.3	1.2	1.0
3.7	3.9	3.8	1.0	2.2	*	0.1	0.6	0.5	2.4	1.6
3.8	4.6	4.5	1.7	3.0	0.1	0.1	1.1	0.8	2.9	2.3
3.9	6.2	5.4	0.4	3.9	0.1	0.2	1.8	1.2	2.8	3.2
4.0	5.8	6.0	3.5	5.2	0.1	0.5	2.7	2.0	3.2	3.5
4.1	6.2	6.7	4.0	6.8	0.2	0.8	4.1	3.1	4.6	4.4
4.2	7.1	7.3	4.0	8.7	0.3	1.5	5.3	4.5	5.9	5.9
4.3	7.6	8.1	5.6	10.2	0.8	2.5	7.2	5.8	7.0	7.1
4.4	8.3	8.1	12.4	10.8	1.9	3.9	7.7	7.0	8.0	7.5
4.5	8.5	8.8	15.6	10.7	4.6	5.8	9.0	8.2	8.1	8.6
4.6	8.7	7.8	17.4	9.5	8.0	8.1	9.5	9.4	9.2	10.0
4.7	6.9	6.1	16.5	7.6	10.2	10.3	9.7	10.1	9.6	10.7
4.8	5.4	4.6	11.4	5.7	11.6	12.4	9.2	10.1	7.7	9.4
4.9	3.7	3.3	4.2	3.8	13.5	13.9	8.5	9.5	6.6	7.2
5.0	2.4	2.2	1.4	2.4	13.6	12.9	7.6	8.8	6.4	5.6
5.1	1.5	1.3	0.2	1.6	12.9	10.5	6.8	7.1	5.5	4.1
5.2	0.7	0.7	0.2	0.8	8.8	7.8	4.2	5.2	3.2	2.6
5.3	0.3	0.4	-	0.4	6.4	4.6	2.2	3.1	2.1	1.9
5.4	0.3	0.2	-	0.1	3.9	2.4	1.1	1.5	0.8	1.0
5.5 & Above	0.1	*	-	0.1	3.1	1.5	0.5	1.1	0.2	0.6
Average	4.24	4.20	4.52	4.34	4.93	4.86	4.63	4.69	4.52	4.53

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Dec 14, 2023

Quality Designation	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	23.0	12.1	0.9	0.5	*	*	7.0	0.7	1.2	0.8
Bark - Level 2	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	*	0.1	0.2	0.1	*	*	-	*	0.1	0.1
Grass - Level 2	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	*	*	*	*	*	*	-	*	-	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	*	*	0.1	0.1	0.1	*	-	*	0.8	0.7
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	*	*	-	*	-	*	-	*	-	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	*	*	-	-	-	*	-	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	*	-	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/22 & Below	*	*	*	*	-	*	-	-	-	-
23	*	*	*	*	-	*	-	-	-	*
24	0.2	0.1	*	*	*	*	-	0.1	-	0.1
25	0.9	0.5	0.1	0.1	*	*	4.8	0.4	*	0.3
26	3.0	1.8	0.3	0.3	*	0.1	9.0	1.3	0.4	1.4
27	6.5	4.5	1.8	1.7	0.3	0.7	6.8	3.3	0.6	2.5
28	11.1	9.0	7.1	6.5	4.2	5.5	4.4	6.3	3.1	5.6
29	16.6	14.1	18.2	16.3	26.3	23.9	18.2	11.9	8.9	10.3
30	18.3	16.9	24.6	25.6	42.0	38.8	14.4	22.0	15.8	13.7
31	16.2	17.4	22.5	24.1	20.7	22.4	15.6	27.1	16.6	14.8
32	11.7	15.2	14.3	14.7	5.4	6.7	9.7	17.5	18.3	15.2
33	7.9	10.5	7.0	6.7	0.9	1.5	8.6	7.1	17.1	11.9
34	4.2	5.8	2.7	2.6	0.1	0.3	8.2	1.9	7.9	8.7
35	2.0	2.8	1.0	1.0	*	0.1	0.1	0.7	5.6	6.2
36	0.8	1.0	0.3	0.3	*	*	0.1	0.3	2.3	3.6
37	0.3	0.3	0.1	0.1	-	*	*	*	2.0	3.1
38	*	*	*	*	-	-	-	*	1.1	2.0
39	-	-	-	*	-	-	-	-	0.3	0.5
40 & Above	-	-	*	*	-	-	-	-	0.1	0.1
Average	30.66	31.14	30.96	31.01	30.44	30.50	30.31	30.99	32.29	32.21
Mike										
2.4 & Below	*	*	-	*	-	-	-	-	-	-
2.5	*	0.1	*	*	-	-	-	-	*	*
2.6	0.1	0.1	*	*	-	-	-	-	*	*
2.7	0.2	0.1	*	*	*	*	-	*	*	*
2.8	0.3	0.2	*	*	*	*	-	*	*	*
2.9	0.4	0.2	*	*	*	*	-	*	0.1	*
3.0	0.4	0.3	*	*	*	*	-	*	0.4	0.1
3.1	0.4	0.4	*	*	0.2	*	-	0.1	0.4	0.2
3.2	0.4	0.5	*	*	0.4	0.1	0.1	0.1	0.5	0.2
3.3	0.6	0.7	0.1	0.1	0.3	0.1	0.9	0.2	1.3	0.4
3.4	0.8	0.9	0.2	0.1	0.3	0.1	2.0	0.3	1.0	0.5
3.5	1.0	1.2	0.4	0.2	0.5	0.2	0.2	0.5	1.4	0.7
3.6	1.3	1.5	0.7	0.4	0.8	0.4	1.6	0.5	1.6	1.0
3.7	1.7	1.9	1.2	0.7	1.3	0.7	2.0	0.6	2.2	1.5
3.8	1.9	2.2	2.1	1.4	1.8	1.2	0.3	0.9	3.9	2.8
3.9	2.6	2.7	3.0	2.4	2.2	1.8	0.3	1.2	4.2	3.5
4.0	3.4	3.3	4.8	4.1	3.2	2.8	2.2	1.6	6.2	5.2
4.1	4.1	4.0	6.7	6.0	4.7	4.2	4.7	2.7	9.5	6.8
4.2	5.1	5.0	8.1	8.3	7.2	6.0	5.3	4.0	7.5	7.9
4.3	5.8	6.0	10.0	10.4	8.5	8.5	6.2	5.5	7.3	8.8
4.4	7.1	7.4	11.9	11.9	11.2	11.1	8.7	6.7	8.9	9.9
4.5	8.4	8.6	11.5	12.3	12.0	12.4	12.3	8.2	9.2	10.6
4.6	9.6	9.6	10.8	11.7	11.7	12.8	20.3	10.4	9.5	10.4
4.7	10.7	10.4	9.3	10.1	10.8	11.6	11.6	11.2	8.2	8.9
4.8	9.8	9.9	7.2	8.0	8.5	9.3	11.8	11.5	6.1	6.6
4.9	8.3	8.1	5.3	5.6	5.7	6.6	7.7	9.0	4.9	5.4
5.0	6.0	5.7	3.4	3.3	3.9	4.5	0.9	7.9	2.9	3.8
5.1	4.5	3.7	1.9	1.7	2.6	2.7	0.1	5.7	2.0	1.7
5.2	2.6	2.3	0.8	0.7	1.3	1.4	*	4.4	0.7	1.4
5.3	1.4	1.5	0.4	0.3	0.4	0.7	0.7	2.9	0.1	1.0
5.4	0.7	0.9	0.1	0.2	0.1	0.4	-	2.1	0.1	0.5
5.5 & Above	0.4	0.9	*	0.1	0.1	0.4	-	1.7	0.1	0.3
Average	4.51	4.51	4.45	4.48	4.48	4.54	4.48	4.68	4.34	4.43

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Dec 14, 2023

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
2.4 & Below	0.1	*	-	*	-	-	-	-	-	*
2.5 - 2.6	0.5	0.3	-	0.1	-	*	-	*	0.1	*
2.7 - 2.9	1.5	1.3	-	0.4	*	*	*	*	0.3	0.1
3.0 - 3.2	2.4	3.6	-	1.2	-	*	0.1	*	0.4	0.4
3.3 - 3.4	2.6	3.8	-	1.9	*	*	0.3	0.2	1.1	0.8
3.5 - 3.6	4.7	5.7	0.5	3.0	*	0.1	0.8	0.5	2.0	1.6
3.7 - 4.2	33.7	33.7	14.6	29.9	0.8	3.2	15.5	12.2	21.7	20.9
4.3 - 4.9	49.1	46.7	83.1	58.2	50.6	56.8	60.9	60.3	56.1	60.4
5.0 - 5.2	4.7	4.3	1.8	4.7	35.3	31.3	18.6	21.1	15.1	12.3
5.3 & Above	0.7	0.6	-	0.6	13.3	8.5	3.9	5.7	3.2	3.5
Average	4.24	4.20	4.52	4.34	4.93	4.86	4.63	4.69	4.52	4.53
Leaf										
1 - 2	26.4	38.3	4.9	51.2	6.3	12.5	14.7	15.9	40.2	58.9
3	41.9	36.4	21.6	39.7	42.0	49.0	52.1	53.8	39.4	28.3
4	18.3	15.4	52.2	8.0	43.1	30.9	27.8	25.5	14.8	8.8
5	7.5	6.2	18.4	1.0	8.4	6.9	4.7	4.3	4.0	2.6
6	3.7	2.5	2.7	0.2	0.2	0.6	0.6	0.4	1.1	1.0
7	1.6	0.9	0.2	*	*	*	0.1	*	0.5	0.4
8	0.5	0.3	-	*	-	*	-	-	*	*
Average	3.25	2.94	3.93	2.51	3.54	3.34	3.24	3.19	2.76	2.38
HVI Trash 1/										
00	-	*	-	*	-	*	-	*	0.1	0.4
01	6.4	14.3	0.2	15.4	0.4	1.4	1.7	1.8	19.4	33.0
02	24.5	27.4	6.5	36.6	9.2	15.3	15.9	16.5	27.5	30.3
03	24.7	21.3	8.4	25.7	20.7	25.6	25.9	27.0	22.9	16.7
04	16.1	13.4	11.7	12.9	24.4	22.8	23.6	23.6	14.2	8.9
05	9.4	8.2	20.9	5.5	20.3	15.7	16.2	15.3	7.2	4.5
06	5.7	5.1	21.8	2.1	13.3	9.4	8.8	8.3	3.9	2.4
07	3.8	3.3	15.3	0.9	6.9	5.1	4.2	4.1	2.1	1.4
08	2.6	2.2	7.8	0.4	3.0	2.5	1.9	1.8	1.2	0.8
09	1.9	1.6	3.5	0.2	1.2	1.2	0.8	0.8	0.7	0.5
10	1.5	1.1	1.8	0.1	0.4	0.5	0.4	0.3	0.4	0.4
11	1.1	0.7	0.9	0.1	0.1	0.2	0.2	0.1	0.2	0.2
12	0.8	0.5	0.5	*	*	0.1	0.1	0.1	0.1	0.1
13	0.6	0.3	0.2	*	*	*	*	*	*	0.1
14	0.4	0.2	0.2	*	-	*	*	*	*	*
15	0.2	0.1	0.1	*	-	*	*	*	*	*
16	0.1	0.1	0.1	*	-	*	*	*	*	*
17	0.1	*	*	*	-	*	-	*	*	*
18 & Above	0.1	0.1	*	*	-	*	*	*	-	*
Average	0.40	0.35	0.57	0.27	0.45	0.41	0.40	0.39	0.30	0.25
UNIFORMITY 2/										
74 & Below	-	*	*	*	-	-	-	-	-	*
75	0.1	0.1	-	0.1	-	-	-	*	*	0.1
76	0.6	0.5	0.2	0.4	-	-	-	*	0.7	0.6
77	2.9	2.6	0.2	1.5	*	*	*	*	4.2	2.9
78	10.1	9.7	2.1	4.0	0.1	0.3	0.1	0.2	13.3	10.1
79	20.9	19.6	4.7	10.3	0.4	1.5	1.8	1.9	27.1	23.4
80	28.3	25.5	29.6	24.2	3.1	6.9	12.8	12.4	30.3	32.4
81	24.5	24.4	35.2	36.4	13.4	18.8	33.2	32.2	20.2	23.4
82	10.7	14.6	22.2	20.0	31.9	33.7	34.8	35.5	3.8	6.5
83	1.8	2.8	5.3	3.0	34.4	27.6	15.9	15.8	0.2	0.7
84	0.1	0.2	0.3	0.2	14.7	9.8	1.3	1.8	*	*
85 & Above	-	*	-	*	2.0	1.4	*	0.1	-	*
Average	80.44	80.58	81.32	81.07	82.94	82.58	81.99	82.01	80.04	80.29
Tenderable 3/	64.8	70.2	88.1	82.1	50.8	59.1	74.3	71.0	65.7	74.1
SAMPLES CLASSED										
Week	55,276		2,864		22,676		109,843		39,072	
Season	333,983		991,389		964,113		1,032,562		215,333	

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Dec 14, 2023

Quality MIKE	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
2.4 & Below	*	*	-	*	-	-	-	-	-	-
2.5 - 2.6	0.1	0.1	*	*	-	-	-	-	*	*
2.7 - 2.9	0.8	0.5	*	*	*	*	-	0.1	0.1	0.1
3.0 - 3.2	1.2	1.1	0.1	0.1	0.6	0.1	0.1	0.3	1.3	0.5
3.3 - 3.4	1.4	1.6	0.3	0.1	0.7	0.2	2.9	0.5	2.3	0.9
3.5 - 3.6	2.3	2.7	1.1	0.5	1.3	0.7	1.8	1.0	2.9	1.6
3.7 - 4.2	18.8	18.9	25.9	22.9	20.5	16.7	14.8	10.9	33.4	27.7
4.3 - 4.9	59.8	60.0	66.0	70.0	68.4	72.3	78.6	62.6	54.1	60.5
5.0 - 5.2	13.1	11.7	6.1	5.7	7.8	8.6	1.1	18.1	5.7	7.0
5.3 & Above	2.6	3.3	0.5	0.6	0.6	1.5	0.7	6.6	0.3	1.8
Average	4.51	4.51	4.45	4.48	4.48	4.54	4.48	4.68	4.34	4.43
Leaf										
1 - 2	39.7	49.7	9.1	12.9	27.9	30.6	4.5	14.4	78.4	78.5
3	43.0	37.5	46.4	51.9	55.2	50.8	24.9	49.3	19.2	16.1
4	12.6	9.8	33.2	28.2	14.4	15.8	39.3	28.6	2.2	4.3
5	3.3	2.1	9.2	6.0	2.1	2.5	19.5	6.7	0.2	0.9
6	0.9	0.6	1.7	0.8	0.4	0.3	9.7	0.9	*	0.1
7	0.3	0.2	0.3	0.1	*	*	2.1	0.1	-	-
8	0.1	0.1	0.1	*	-	-	-	*	-	-
Average	2.79	2.58	3.49	3.30	2.91	2.89	4.11	3.30	2.00	1.96
HVI Trash 1/										
00	*	*	-	*	*	*	-	-	*	0.1
01	11.8	18.8	1.0	1.6	4.4	6.4	0.3	2.3	38.5	47.4
02	34.0	35.9	12.0	16.1	27.4	28.0	4.4	16.0	41.5	33.4
03	25.5	22.4	23.9	27.7	32.0	28.7	9.5	25.9	13.5	10.4
04	13.6	11.5	23.5	23.8	19.5	18.5	16.6	22.7	4.4	4.3
05	6.9	5.6	17.0	15.1	9.5	9.8	15.7	15.2	1.4	2.2
06	3.6	2.7	10.5	8.1	3.9	4.7	15.5	8.8	0.5	1.2
07	1.9	1.4	5.8	4.0	1.7	2.2	12.5	4.6	0.2	0.6
08	1.0	0.7	3.1	1.9	0.8	1.0	7.5	2.3	0.1	0.3
09	0.6	0.4	1.5	0.9	0.4	0.4	5.1	1.1	*	0.1
10	0.4	0.3	0.8	0.4	0.2	0.2	5.0	0.6	*	0.1
11	0.2	0.2	0.4	0.2	0.1	0.1	3.4	0.3	*	*
12	0.2	0.1	0.2	0.1	*	*	2.4	0.2	-	*
13	0.1	0.1	0.1	*	*	*	1.2	0.1	-	*
14	0.1	*	0.1	*	*	*	0.8	*	-	*
15	0.1	*	*	*	*	*	-	-	-	-
16	*	*	*	*	*	*	-	-	-	-
17	*	*	*	*	*	*	-	-	-	-
18 & Above	*	*	*	*	*	*	-	-	-	-
Average	0.31	0.28	0.44	0.40	0.33	0.33	0.61	0.40	0.19	0.19
UNIFORMITY 2/										
74 & Below	0.1	0.1	*	*	-	-	-	-	-	-
75	0.4	0.2	-	*	*	*	-	-	-	*
76	1.3	0.9	*	*	*	*	-	-	*	*
77	4.9	3.3	0.1	0.2	*	*	3.4	0.1	0.1	0.2
78	12.6	9.6	0.7	1.3	0.3	0.1	3.1	1.3	0.8	1.9
79	23.8	20.3	5.1	7.6	1.4	1.1	14.7	5.6	7.1	8.5
80	28.9	28.1	21.3	24.8	7.7	8.5	24.4	15.1	23.0	22.6
81	19.3	22.9	37.9	36.1	24.6	24.1	30.3	29.7	29.1	29.4
82	7.1	11.0	26.3	22.9	42.0	38.0	20.3	31.4	28.5	22.9
83	1.4	2.9	7.6	6.2	21.3	25.0	2.7	15.1	8.3	10.0
84	0.1	0.5	0.9	0.8	2.5	3.1	1.0	1.6	3.1	4.1
85 & Above	*	0.1	0.1	*	0.2	0.2	-	0.1	0.1	0.4
Average	80.12	80.46	81.55	81.38	82.27	82.32	80.97	81.80	81.60	81.56
Tenderable 3/	55.3	67.5	87.1	89.7	89.5	89.1	67.1	62.8	88.5	87.6
SAMPLES CLASSED										
Week	139,942		259,740		190,853		2,255		26,973	
Season		1,132,958		1,872,639		2,713,941		249,035		147,623

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Dec 14, 2023

Color Grade	Leaf	VISALIA			Quality Designation	VISALIA	
		Week	Season			Week	Season
01	1	7.3	10.9		MIKE	-	-
	2	12.7	14.5		2.4 & Below	-	-
	3	0.7	0.6		2.5 - 2.6	0.3	0.1
	4	*	*		2.7 - 2.9	1.5	0.5
	5	-	-		3.0 - 3.2	3.0	1.7
	6	-	-		3.3 - 3.4	5.0	3.7
	7	-	-		3.5 - 3.6	8.7	10.9
Total -----		20.7	26.0		3.7 - 4.2	73.5	77.5
02	1	4.3	7.6		4.3 - 4.9	8.1	5.6
	2	43.8	43.9		5.0 - 5.2	-	*
	3	12.8	10.4		5.3 & Above	-	*
	4	0.7	0.6		Average	3.87	3.88
	5	*	*		ALL RANGE MIKE		
	6	-	*		2.4 & Below	-	-
	7	-	*		2.5	*	*
Total -----		61.6	62.6		2.6	0.3	0.1
03	1	0.1	0.1		2.7	0.4	0.1
	2	4.1	3.2		2.8	0.4	0.1
	3	6.6	5.0		2.9	0.7	0.2
	4	1.8	1.3		3.0	0.8	0.3
	5	0.1	0.1		3.1	1.0	0.5
	6	*	*		3.2	1.2	0.9
	7	-	*		3.3	2.0	1.4
Total -----		12.8	9.6		3.4	2.9	2.3
04	1	-	*		3.5	3.1	4.2
	2	0.1	0.1		3.6	5.6	6.7
	3	0.9	0.4		3.7	9.1	9.7
	4	1.0	0.6		3.8	12.2	13.7
	5	0.3	0.2		3.9	14.1	17.1
	6	0.2	0.1		4.0	17.1	16.4
	7	0.1	*		4.1	12.2	12.9
Total -----		2.5	1.3		4.2	8.8	7.8
05	1	-	-		4.3	6.3	3.7
	2	-	*		4.4	1.4	1.4
	3	*	*		4.5	0.3	0.3
	4	0.2	*		4.6	0.1	0.1
	5	0.2	*		4.7	*	*
	6	0.6	0.1		4.8	*	*
	7	1.2	0.2		4.9	*	*
Total -----		2.1	0.4		5.0	-	*
06	1	-	-		5.1	-	*
	2	-	-		5.2	-	*
	3	-	-		5.3 & Above	-	*
	4	*	*		Average	3.87	3.88
	5	-	*		STRENGTH 1/		
	6	-	*		36 & Below	3.6	3.1
	7	0.3	0.1		37	4.2	5.0
Total -----		0.3	0.1		38	4.2	7.1
07	1	-	-		39	6.5	6.8
	2	-	-		40	6.3	6.6
	3	-	-		41	9.9	10.3
	4	-	-		42	14.6	15.8
	5	-	-		43	17.2	16.8
	6	-	-		44	17.1	13.7
	7	*	*		45	11.6	9.6
Total -----		*	*		46	2.8	3.7
STAPLE					47	1.5	1.1
44 & Shorter		1.9	1.2		48 & Above	0.5	0.3
46		8.3	8.9		Average	42.49	42.22
48		18.6	34.4		UNIFORMITY		
50		49.6	45.2		83 & Below	0.9	0.5
52 & Longer		21.5	10.3		84	4.3	4.0
Average Staple		49.61	49.09		85	17.3	21.1
Average Length		1.44	1.43		86	43.9	47.8
EXTRANEEOUS MATTER					87	32.6	25.7
Bark		*	*		88 & Above	1.0	0.8
Grass		*	0.1		Average	86.50	86.42
Spindle Twist		0.3	0.2		Samples Classed		
Preparation		*	*		Week	23,881	
All Other		*	*		Season		195,534

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.