



Quality of Cotton Classed by Classing Office for the week ending - 1/13/2022

Agricultural Marketing Service
Cotton Market News

January 14, 2022

Volume 63, No.22

Classing Office	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
Abilene	38	79.2	64.9	155,475	38	73.0	56.7	1,055,947
Corpus Christi	6	78.1	73.7	4,547	53	86.2	74.3	1,737,698
Dumas	6	91.3	75.9	1,194	39	89.5	72.3	1,001,381
Florence	19	93.4	88.2	35,144	50	95.9	88.2	1,251,754
Lamesa	27	73.5	55.9	103,633	33	78.5	61.7	1,194,327
Lubbock	62	64.4	46.7	243,338	65	66.6	46.7	2,626,939
Macon	77	89.1	80.2	249,329	79	89.2	80.8	2,432,346
Memphis	53	92.1	84.3	164,813	79	95.3	87.1	2,470,492
Rayville	2	94.5	93.0	3,131	19	88.1	70.5	271,735
Visalia	12	82.8	68.4	23,184	26	83.6	66.8	319,001
United States	302	80.2	67.7	983,788	481	84.1	71.0	14,361,620
AMERICAN PIMA								
Visalia	8			9,480	20			289,959
United States	8			9,480	21			289,959
United States all cotton	310			993,268	494			14,651,592

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed.

MP_CN100

Source: USDA AMS Cotton and Tobacco Market News

Memphis, Tennessee | 901-384-3016 | cottonmn@ams.usda.gov

<https://www.ams.usda.gov/market-news/cotton>

<https://mymarketnews.ams.usda.govcottonmn@ams.usda.gov>

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 13, 2022

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	54.1	44.2	9.0	17.9	-	0.4	1.6	0.9	79.8	76.9
	3	13.5	15.6	2.0	13.9	-	0.4	2.9	0.9	12.6	13.1
	4	1.1	1.4	*	0.9	-	*	0.1	0.1	0.9	1.4
	5	*	*	-	*	-	*	-	*	*	0.1
	6	-	*	-	*	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	68.7 61.2	11.0 32.8	0.9	4.6 1.8	93.2 91.4				
31	1 - 2	7.1	5.0	4.7	6.0	0.8	3.8	3.4	7.6	1.4	0.6
	3	11.7	12.4	18.2	26.5	6.4	21.4	31.6	30.4	1.3	1.0
	4	5.1	7.5	2.5	10.8	1.3	8.6	21.0	10.9	0.9	1.0
	5	0.9	1.6	*	0.8	0.1	0.4	2.2	0.7	0.3	0.3
	6	0.1	0.1	-	*	-	*	0.1	*	*	0.1
	7	*	*	-	*	-	-	-	*	*	*
	8	-	-	-	*	-	-	-	-	-	-
	Total	----	24.9 26.6	25.4 44.2	8.6 34.2	58.2 49.8	4.0 3.0				
41	1 - 2	0.1	0.1	3.3	0.6	8.7	1.8	0.4	1.6	*	*
	3	0.6	0.3	36.1	6.1	70.5	26.2	10.2	19.8	*	*
	4	1.0	0.9	12.3	7.1	5.0	30.0	18.3	20.6	*	*
	5	0.7	0.9	0.7	1.7	0.5	4.8	5.5	4.4	*	*
	6	0.2	0.3	*	0.2	-	0.1	0.5	0.3	*	*
	7	*	0.1	-	*	-	*	*	*	*	*
	8	*	*	-	*	-	-	-	-	-	-
	Total	----	2.6 2.6	52.4 15.8	84.8 63.0	34.9 46.7	0.1 *				
51	1 - 2	-	*	0.2	*	-	*	-	*	-	*
	3	*	*	2.0	0.2	0.3	0.2	0.1	0.1	*	*
	4	*	*	1.3	0.3	-	0.3	0.5	0.2	-	*
	5	-	*	0.3	0.1	0.1	0.1	0.4	0.2	-	*
	6	*	*	-	*	-	*	0.1	*	-	-
	7	*	*	-	*	-	*	-	*	-	-
	8	*	*	-	*	-	-	*	*	-	-
	Total	----	* *	3.8 0.7	0.4 0.7	1.0 0.5	* *				
61	1 - 2	-	-	-	*	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	*	*
	4	-	-	-	*	-	*	-	*	-	-
	5	-	-	-	-	-	-	-	*	-	-
	6	*	*	-	*	-	*	-	*	-	-
	7	-	-	-	*	-	-	-	-	-	-
	8	-	-	-	*	-	-	*	*	-	-
	Total	----	* *	- *	- *	* *	* *				
71	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	- -	- -	- -	- -	- -				
12 & 22	1 - 2	1.1	2.9	-	0.5	-	*	-	*	1.2	2.8
	3	1.0	2.4	*	0.8	-	*	*	*	0.7	1.4
	4	0.2	0.6	-	0.1	-	*	*	*	0.1	0.3
	5	*	*	-	*	-	-	-	-	*	*
	6	-	*	-	-	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	2.3 5.9	* 1.3	- *	* *	2.0 4.5				
32	1 - 2	0.1	0.2	0.1	0.1	0.1	*	-	*	*	*
	3	0.3	0.7	0.5	1.0	1.8	0.1	0.1	0.2	0.1	0.1
	4	0.3	0.9	0.3	0.7	-	0.1	0.2	0.1	0.1	0.1
	5	0.1	0.5	*	0.1	-	*	*	*	*	*
	6	*	0.1	-	*	-	*	-	*	*	*
	7	*	*	-	-	-	-	-	-	*	*
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	0.7 2.3	1.0 1.9	1.9 0.2	0.3 0.3	0.2 0.2				
42	1 - 2	*	*	-	*	0.2	0.1	-	*	*	*
	3	*	*	1.6	0.5	3.5	0.4	0.1	0.2	*	*
	4	*	*	2.7	1.3	0.2	0.4	0.2	0.3	-	*
	5	*	0.1	0.2	0.4	-	0.1	0.1	0.1	*	*
	6	*	0.1	-	*	-	*	*	*	*	*
	7	*	*	-	*	-	-	*	*	-	*
	8	-	*	-	*	-	-	-	-	-	-
	Total	----	0.1 0.3	4.6 2.3	3.9 1.0	0.4 0.6	* *				

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 13, 2022

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	*	*	-	*	-	*	-	-	-	*
	3	-	-	0.2	*	-	*	*	*	-	*
	4	-	*	0.2	0.2	-	*	0.1	0.1	-	*
	5	*	*	-	0.1	-	*	0.2	0.1	-	-
	6	*	*	-	*	-	*	*	*	-	*
	7	-	*	-	*	-	-	-	*	-	-
	8	-	*	-	*	-	-	-	*	-	-
Total	----	*	*	0.3	0.4	-	0.1	0.3	0.2	-	*
62	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	*	-	-	-	-
	4	-	-	-	*	-	-	-	*	-	-
	5	-	-	-	*	-	-	-	*	-	-
	6	-	-	-	*	-	-	-	*	-	-
	7	-	-	-	*	-	-	-	-	-	-
	8	-	-	-	*	-	-	-	-	-	-
Total	----	-	-	-	*	-	*	-	*	-	-
13 & 23	1 - 2	0.1	0.2	-	*	-	-	*	*	0.1	0.2
	3	0.1	0.3	-	*	-	-	*	*	0.2	0.3
	4	*	0.1	-	*	-	-	-	*	*	*
	5	-	*	-	*	-	-	-	-	-	*
	6	-	*	-	-	-	-	-	*	-	*
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	0.2	0.5	-	0.1	-	-	*	*	0.3	0.5
33	1 - 2	*	*	*	*	-	*	-	*	*	*
	3	0.1	0.1	0.4	0.1	0.3	*	*	*	0.1	0.1
	4	0.1	0.1	0.1	0.1	-	*	0.1	*	0.1	0.1
	5	*	0.1	-	*	-	*	*	*	*	*
	6	*	*	-	*	-	-	*	*	*	*
	7	-	*	-	-	-	-	-	-	-	*
	8	*	*	-	-	-	-	-	-	-	*
Total	----	0.2	0.4	0.6	0.2	0.3	*	0.1	*	0.2	0.2
43	1 - 2	-	*	*	*	-	*	-	*	-	*
	3	*	*	0.2	*	0.1	*	*	*	*	*
	4	*	*	0.4	0.1	0.1	*	*	*	*	*
	5	*	*	-	0.1	-	*	*	*	*	*
	6	*	*	*	*	-	-	*	*	-	*
	7	*	*	-	*	-	-	-	*	-	*
	8	-	*	-	-	-	-	-	-	-	*
Total	----	0.1	0.1	0.6	0.2	0.2	*	0.1	*	*	*
53	1 - 2	-	*	-	*	-	-	-	-	-	*
	3	-	*	*	*	-	*	*	*	-	-
	4	-	*	0.2	*	-	*	*	*	-	-
	5	-	-	*	*	-	*	*	*	-	-
	6	-	*	-	*	-	*	*	*	-	-
	7	-	*	-	*	-	*	-	-	-	-
	8	-	*	-	*	-	*	-	-	-	-
Total	----	-	*	0.2	0.1	-	*	*	*	-	*
63	1 - 2	-	-	-	-	-	-	-	-	-	*
	3	-	-	-	*	-	*	-	-	-	*
	4	-	-	-	*	-	-	-	-	-	*
	5	-	-	-	*	-	-	-	-	-	-
	6	-	-	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	-	*	-	-	-	*
24 - 54	1 - 8	0.1	0.1	*	*	-	*	*	*	*	0.1
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	*	*	-	*	-	-	-	*	*	*
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		*	*	-	*	-	-	-	-	*	*
30		*	*	-	*	-	-	-	*	0.3	0.1
31		0.3	0.4	-	*	-	-	-	*	0.8	0.4
32		1.7	2.0	*	*	-	*	*	*	1.5	1.2
33		5.9	5.8	0.9	0.3	-	*	0.2	0.4	6.7	5.6
34		12.4	12.6	5.8	1.9	0.1	0.3	2.2	3.1	18.5	15.8
35		20.8	20.3	18.4	7.7	1.3	2.1	12.4	10.9	28.6	24.7
36		21.2	19.8	24.9	21.3	11.2	6.3	19.0	23.8	24.4	24.1
37		19.7	20.5	31.6	42.4	43.9	22.5	37.8	37.4	14.6	20.5
38		10.1	10.7	16.3	19.4	35.4	27.4	21.2	18.5	3.6	6.0
39		5.4	5.8	2.1	6.2	7.5	28.6	6.5	5.2	0.9	1.5
40 & Longer		2.5	2.1	*	0.7	0.6	12.8	0.7	0.7	0.1	0.2
Average Staple		35.95	35.94	36.38	36.90	37.39	38.13	36.85	36.75	35.28	35.57
Average Length		1.12	1.12	1.13	1.15	1.17	1.19	1.15	1.15	1.10	1.11

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 13, 2022

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	71.0	62.3	5.0	2.6	0.4	0.4	1.3	1.3	41.0	54.7
	3	17.6	21.8	8.0	3.1	0.7	0.6	1.0	1.1	13.9	10.7
	4	1.6	2.8	1.0	0.3	0.2	0.1	0.1	*	0.4	0.3
	5	0.1	0.2	*	*	*	*	-	-	*	*
	6	*	*	*	*	*	*	-	-	-	-
	7	-	*	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	90.2	87.0	14.1	6.0	1.3	1.1	2.4	2.4	55.4	65.7
31	1 - 2	1.3	0.4	3.7	4.5	3.8	6.9	9.3	4.9	8.1	10.3
	3	2.4	1.1	23.4	22.6	25.1	28.0	44.4	33.1	21.1	13.0
	4	1.4	1.3	9.3	7.5	13.2	10.2	16.6	13.2	7.3	3.2
	5	0.4	0.5	0.8	0.5	2.8	0.9	1.3	0.5	0.8	0.4
	6	0.1	0.1	*	*	0.2	*	0.1	*	*	*
	7	*	*	*	*	*	*	-	-	*	*
	8	-	*	-	-	-	-	-	-	-	*
Total	----	5.6	3.4	37.2	35.2	45.1	46.1	71.8	51.7	37.3	26.9
41	1 - 2	*	*	1.1	0.9	0.8	1.2	0.1	0.6	0.2	0.7
	3	*	*	15.7	19.3	19.6	21.6	10.4	15.9	0.4	0.9
	4	*	*	16.7	22.9	24.3	24.1	10.6	23.1	2.2	0.9
	5	0.1	*	4.1	5.4	5.6	4.3	3.2	3.6	1.0	0.4
	6	*	*	0.4	0.4	1.0	0.3	1.0	0.1	0.1	0.1
	7	*	*	*	*	0.1	*	-	-	*	*
	8	*	*	*	*	*	*	-	-	*	*
Total	----	0.1	0.1	38.0	48.9	51.5	51.5	25.4	43.3	4.0	3.1
51	1 - 2	-	-	0.3	*	-	*	-	*	-	*
	3	-	*	2.7	0.8	*	*	-	0.1	-	0.1
	4	*	*	2.7	1.9	0.2	0.1	0.1	0.2	*	0.1
	5	-	-	1.0	1.1	0.2	0.1	0.1	0.1	*	*
	6	-	*	0.2	0.2	0.1	*	-	*	-	*
	7	-	*	*	*	*	*	-	-	-	*
	8	-	*	*	*	-	*	-	-	-	*
Total	----	*	*	6.9	4.1	0.5	0.2	0.2	0.3	*	0.3
61	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	*	*	-	-	-	-	-	*
	4	-	-	*	*	-	-	-	*	-	*
	5	-	-	*	*	-	-	-	-	-	-
	6	-	-	*	*	-	*	-	-	-	-
	7	-	-	*	*	-	-	-	-	-	-
	8	-	-	*	*	-	-	-	-	-	-
Total	----	-	-	*	*	-	*	-	*	-	*
71	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	*	-	-	-	-	-	-
	8	-	-	-	*	-	-	-	-	-	-
Total	----	-	-	-	*	-	-	-	-	-	-
12 & 22	1 - 2	1.5	4.1	*	*	*	*	-	*	0.1	0.8
	3	1.3	3.3	*	*	*	*	0.1	0.1	0.4	0.9
	4	0.2	0.7	*	*	*	*	-	*	0.1	0.2
	5	*	0.1	*	*	*	*	-	-	-	*
	6	*	*	-	*	-	-	-	-	-	-
	7	-	*	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	3.0	8.2	*	*	0.1	*	0.1	0.1	0.5	1.8
32	1 - 2	*	*	*	*	*	*	-	*	0.1	0.1
	3	0.2	0.1	0.2	0.1	0.2	0.1	*	0.2	0.9	0.6
	4	0.1	0.1	0.1	0.1	0.2	0.1	0.1	0.4	1.0	0.5
	5	*	0.1	*	*	0.2	*	-	0.1	0.1	0.1
	6	*	*	*	*	0.1	*	-	*	*	*
	7	*	*	-	-	*	*	-	-	-	*
	8	-	*	-	-	*	*	-	-	-	-
Total	----	0.4	0.4	0.4	0.2	0.6	0.3	0.1	0.7	2.2	1.4
42	1 - 2	*	*	*	*	-	*	-	*	*	*
	3	-	*	0.7	0.8	0.1	0.2	-	0.2	*	0.1
	4	*	*	1.1	1.7	0.3	0.4	-	0.7	0.1	0.1
	5	*	*	0.5	0.6	0.1	0.1	-	0.2	0.2	0.2
	6	*	*	0.1	0.1	0.1	*	-	*	0.2	0.1
	7	*	*	*	*	0.1	*	-	-	*	*
	8	*	*	-	*	*	*	-	-	-	*
Total	----	*	*	2.4	3.2	0.6	0.7	-	1.1	0.5	0.6

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 13, 2022

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color 52	1 - 2	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
	3	-	-	*	*	-	-	-	*	-	-
	4	-	-	0.1	0.2	*	*	-	0.1	-	*
	5	-	*	0.2	1.0	*	*	-	0.1	-	*
	6	-	-	0.2	0.6	*	*	-	*	-	*
	7	-	-	0.1	0.1	*	*	-	*	-	*
	8	-	-	*	*	*	*	-	-	-	*
	Total	----	-	0.6	2.0	*	*	-	0.2	-	*
62	1 - 2	-	*	-	-	-	-	-	-	-	-
	3	-	-	*	*	-	-	-	*	-	*
	4	-	-	-	*	-	-	-	*	-	*
	5	-	-	*	*	-	-	-	*	-	-
	6	-	-	*	*	-	-	-	-	-	-
	7	-	-	*	*	-	-	-	-	-	-
	8	-	-	*	*	-	*	-	-	-	-
	Total	----	-	*	*	-	*	-	*	-	*
13 & 23	1 - 2	0.2	0.2	*	*	-	*	-	-	-	*
	3	0.3	0.3	*	*	*	*	-	*	*	*
	4	*	0.1	*	*	*	*	-	-	*	*
	5	*	*	*	*	*	*	-	-	-	-
	6	-	*	-	-	-	-	-	-	-	-
	7	-	*	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	0.5	0.7	*	*	*	-	*	*	*
33	1 - 2	*	*	*	*	*	*	-	*	-	*
	3	*	0.1	*	*	*	*	-	*	*	*
	4	*	0.1	*	*	*	*	-	*	*	*
	5	*	*	*	*	*	*	-	*	*	*
	6	*	*	*	*	*	*	-	*	*	*
	7	-	*	-	*	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	0.1	0.2	0.1	*	0.1	-	*	0.1	0.1
43	1 - 2	-	*	*	*	-	*	-	-	-	*
	3	*	*	0.1	*	*	*	-	*	*	*
	4	*	*	0.1	0.1	*	*	-	*	*	*
	5	*	*	*	*	*	*	-	*	*	*
	6	*	*	*	*	*	*	-	*	*	*
	7	*	*	*	*	*	*	-	-	*	*
	8	*	*	*	*	*	*	-	-	*	*
	Total	----	*	*	0.3	0.2	0.1	-	0.1	0.1	0.1
53	1 - 2	-	-	*	*	-	-	-	-	-	-
	3	-	*	*	*	-	*	-	-	-	*
	4	-	-	*	0.1	-	*	-	*	-	*
	5	-	-	*	0.1	-	*	-	*	*	*
	6	-	-	*	*	-	*	-	*	-	*
	7	-	*	*	*	-	-	-	-	-	-
	8	*	*	-	*	-	-	-	-	-	*
	Total	----	*	*	*	0.2	*	-	*	*	*
63	1 - 2	-	*	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	*
	4	-	-	-	*	-	-	-	-	-	*
	5	-	-	-	*	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-
	7	-	*	-	*	-	-	-	-	-	-
	8	-	-	-	*	-	-	-	-	-	-
	Total	----	-	*	-	*	-	-	-	-	*
24 - 54	1 - 8	*	0.1	*	*	*	*	-	*	-	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	*	*	*	*	-	-	-	-	-	-
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		*	*	-	-	-	-	-	-	-	-
30		0.1	*	-	*	-	-	-	-	-	-
31		0.6	0.3	*	*	-	-	-	-	-	-
32		2.1	1.2	*	0.1	-	*	-	*	-	*
33		6.4	4.1	0.4	0.8	*	*	*	*	*	*
34		14.1	10.6	3.0	4.7	0.3	0.3	0.5	0.4	0.2	0.5
35		20.0	18.3	9.6	11.4	1.6	3.1	1.8	3.8	3.0	4.8
36		22.2	23.0	19.0	19.1	8.1	12.5	18.8	11.0	7.3	13.9
37		22.4	26.3	40.2	38.1	26.8	27.9	68.3	22.4	32.6	35.0
38		8.5	10.5	20.7	18.6	32.2	29.9	10.3	25.1	30.1	24.5
39		2.8	4.3	6.1	6.0	24.2	20.8	0.2	23.5	20.0	15.7
40 & Longer		0.8	1.3	0.9	1.2	6.8	5.6	-	13.8	6.9	5.6
Average Staple		35.72	36.07	36.87	36.74	37.89	37.69	36.87	37.96	37.77	37.48
Average Length		1.11	1.12	1.15	1.15	1.18	1.18	1.15	1.19	1.18	1.17

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 13, 2022

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	6.9	10.4	14.4	2.8	0.3	1.2	1.9	0.6	3.3	3.3
Bark - Level 2	-	*	-	-	-	-	-	-	-	-
Grass - Level 1	0.1	0.1	0.1	0.8	-	0.2	0.1	0.1	0.2	0.2
Grass - Level 2	-	-	-	-	-	-	-	*	-	-
Prep - Level 1	*	*	-	*	0.1	*	*	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	0.1	0.1	0.2	2.1	-	*	*	*	0.5	0.5
Seed Coat - Level 2	-	*	-	-	-	-	-	-	-	-
Oil - Level 1	*	*	-	*	-	*	-	-	-	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	*	*	*	*	-	*	-	*	*	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	0.3	0.1	-	*	*	*	*	*
Plastic - Level 2	-	-	-	*	-	-	-	-	-	-
STRENGTH 1/22 & Below	*	*	-	*	-	-	-	-	*	*
23	0.1	*	-	*	-	-	-	*	0.1	*
24	0.2	0.1	0.1	*	-	*	0.1	*	0.2	0.1
25	0.6	0.5	0.2	0.1	-	*	0.4	0.1	0.6	0.5
26	2.8	1.9	1.1	0.8	0.1	0.1	1.5	0.4	2.3	1.8
27	7.1	6.0	5.0	2.9	1.3	0.6	5.8	1.8	7.1	6.0
28	13.5	12.3	13.3	8.9	7.0	3.2	12.6	7.1	15.5	14.1
29	18.3	16.9	22.2	18.2	21.9	11.7	22.7	19.9	22.4	20.8
30	18.7	18.7	26.7	22.9	32.2	25.5	25.6	29.2	20.6	20.8
31	15.5	16.4	17.9	19.3	20.9	29.0	16.1	23.2	14.6	15.8
32	10.7	12.8	8.7	14.3	9.9	18.1	9.5	11.8	9.2	10.7
33	7.3	8.3	3.6	8.2	4.5	7.7	4.0	4.8	4.7	5.9
34	3.8	4.3	0.9	3.1	1.8	3.0	1.2	1.5	1.7	2.5
35	1.1	1.4	0.2	1.1	0.3	0.9	0.4	0.4	0.6	0.7
36	0.3	0.3	0.1	0.1	-	0.1	*	*	0.3	0.2
37	*	0.1	-	*	0.1	*	-	*	0.1	*
38	*	*	-	*	-	-	-	-	0.1	*
39	*	*	-	-	-	-	-	-	*	*
40 & Above	-	*	-	-	-	-	-	-	*	*
Average	30.45	30.69	30.28	30.88	30.69	31.30	30.26	30.73	30.16	30.37
Mike										
2.4 & Below	*	*	-	*	-	*	-	-	0.3	0.1
2.5	0.1	*	-	*	-	*	-	*	0.4	0.2
2.6	0.1	0.1	-	*	-	*	-	*	0.5	0.2
2.7	0.2	0.2	-	*	-	*	-	*	0.9	0.4
2.8	0.3	0.3	-	*	-	*	*	*	1.2	0.7
2.9	0.5	0.6	-	*	-	*	0.1	*	1.5	0.9
3.0	0.9	1.0	-	*	-	*	0.1	*	1.9	1.3
3.1	1.7	1.6	*	*	-	*	0.2	*	2.5	1.8
3.2	2.0	2.3	*	0.1	-	*	0.4	0.1	3.0	2.6
3.3	2.4	3.2	0.2	0.2	-	*	0.6	0.1	4.1	3.5
3.4	3.2	4.3	0.4	0.3	-	*	0.8	0.2	5.4	4.4
3.5	4.1	5.1	0.8	0.4	-	0.1	0.9	0.3	6.7	5.4
3.6	5.7	6.2	1.1	0.8	0.1	0.1	1.0	0.5	8.5	6.2
3.7	7.8	7.3	1.7	1.3	0.4	0.4	2.9	1.0	7.7	7.1
3.8	9.6	8.5	2.7	2.0	0.4	0.6	4.3	1.7	8.8	8.4
3.9	10.9	9.7	4.7	3.0	0.2	1.0	6.6	2.9	8.9	9.0
4.0	10.3	10.0	6.1	4.4	0.2	1.7	7.7	5.1	8.0	9.4
4.1	9.3	9.3	8.6	6.9	0.6	2.8	12.0	7.8	8.2	9.4
4.2	8.4	8.1	12.0	9.1	0.7	4.6	13.2	10.9	7.0	8.2
4.3	7.0	6.6	18.2	11.0	5.4	7.8	14.7	13.6	6.0	6.7
4.4	5.2	4.9	17.4	12.1	16.5	11.8	12.1	14.7	4.1	5.0
4.5	3.7	3.6	12.6	12.9	28.2	14.7	9.4	14.1	2.1	3.5
4.6	2.5	2.6	7.4	12.1	15.7	15.2	6.8	11.1	1.1	2.3
4.7	1.8	1.9	4.0	9.5	10.6	13.7	3.2	7.6	0.7	1.4
4.8	0.9	1.1	1.5	6.1	11.1	10.5	1.4	4.4	0.3	0.9
4.9	0.6	0.7	0.5	3.3	5.4	6.7	0.8	2.1	0.2	0.5
5.0	0.5	0.4	0.1	1.9	2.8	3.9	0.5	1.1	*	0.2
5.1	0.3	0.2	-	1.2	1.0	2.1	0.3	0.4	*	0.1
5.2	0.1	0.1	-	0.8	0.3	1.1	0.1	0.2	*	0.1
5.3	*	*	-	0.4	0.3	0.6	*	0.1	-	0.1
5.4	*	*	-	0.1	-	0.2	-	*	-	*
5.5 & Above	-	*	-	0.1	-	0.1	-	*	-	*
Average	3.95	3.93	4.28	4.42	4.58	4.57	4.22	4.38	3.78	3.89

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 13, 2022

Quality Designation	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	2.6	4.8	1.5	0.7	0.6	0.4	4.3	1.8	0.3	0.2
Bark - Level 2	-	*	-	*	-	-	-	-	-	-
Grass - Level 1	0.2	0.2	*	*	0.1	*	-	*	*	0.2
Grass - Level 2	-	*	-	-	-	-	-	-	-	-
Prep - Level 1	*	*	*	*	0.1	*	-	*	-	*
Prep - Level 2	-	*	-	-	-	-	-	-	-	-
Seed Coat - Level 1	0.6	0.2	2.4	1.5	0.7	0.1	-	0.2	0.6	0.4
Seed Coat - Level 2	-	-	-	*	-	-	-	-	-	-
Oil - Level 1	*	*	-	*	-	*	-	-	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	*	*
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	*	*	*	*	-	*	-	*	-	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	*	-	*	*	*
Plastic - Level 2	-	*	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	*	*	*	*	-	-	-	*	-	*
23	0.1	*	*	*	-	-	0.1	*	-	*
24	0.2	0.1	*	0.1	-	*	0.1	*	-	*
25	0.9	0.6	0.4	0.3	*	*	0.6	*	*	*
26	3.0	1.9	1.6	1.5	*	*	0.6	0.2	0.1	0.1
27	7.2	5.5	5.6	5.1	0.2	0.2	0.3	0.6	0.8	0.8
28	13.9	11.6	15.7	14.1	2.2	2.6	0.3	4.1	3.3	3.2
29	19.3	17.6	25.2	26.5	15.1	14.0	3.8	12.8	6.3	8.1
30	19.7	20.1	27.0	27.7	31.5	30.7	19.3	31.3	10.3	15.2
31	15.9	18.1	15.8	15.3	33.1	31.4	53.1	27.4	21.5	22.1
32	10.5	12.7	6.0	6.2	13.9	15.0	12.1	11.7	23.3	18.3
33	5.6	7.0	2.0	2.3	3.4	4.8	9.5	7.7	11.9	11.3
34	2.5	3.1	0.5	0.7	0.6	1.1	0.2	3.0	11.2	8.1
35	0.9	1.1	0.1	0.2	0.1	0.2	-	0.7	8.2	5.1
36	0.3	0.3	*	*	*	*	*	0.5	2.6	2.9
37	0.1	0.1	*	*	-	*	-	*	0.4	2.6
38	*	*	*	*	-	*	-	*	0.1	1.7
39	*	*	-	*	-	-	-	-	*	0.5
40 & Above	-	*	-	-	-	-	-	-	*	0.1
Average	30.28	30.61	30.00	30.06	30.99	31.06	31.40	31.13	32.38	32.32
Mike										
2.4 & Below	0.2	0.1	-	-	*	*	-	-	-	*
2.5	0.6	0.3	*	*	*	*	-	*	0.1	*
2.6	1.0	0.6	*	*	*	*	0.1	*	0.1	0.1
2.7	1.3	0.9	*	*	*	*	0.1	*	0.1	0.1
2.8	1.6	1.3	*	*	*	*	0.4	*	0.3	0.2
2.9	2.0	1.8	*	*	*	*	0.4	*	0.6	0.4
3.0	2.6	2.6	0.1	0.1	0.1	0.1	1.2	*	0.5	0.3
3.1	3.9	3.5	0.2	0.1	0.2	0.1	0.4	*	0.6	0.4
3.2	4.7	4.5	0.5	0.2	0.4	0.2	*	*	2.3	0.7
3.3	5.9	5.6	0.9	0.4	0.9	0.3	-	0.1	2.5	0.9
3.4	6.9	6.4	1.5	0.6	1.4	0.5	0.1	0.2	2.6	1.3
3.5	7.1	7.0	2.0	0.9	2.2	0.8	0.1	0.2	4.0	1.7
3.6	7.6	7.6	3.2	1.4	3.0	1.4	0.7	0.4	3.8	1.9
3.7	7.8	8.1	4.3	2.1	3.8	2.0	0.9	0.6	4.5	2.2
3.8	7.7	8.1	5.4	3.0	4.7	3.0	1.4	0.8	6.8	3.5
3.9	7.6	7.9	7.4	4.5	5.4	4.2	2.1	1.2	8.0	4.2
4.0	7.2	7.3	9.0	6.1	7.5	6.1	8.0	1.9	7.3	4.7
4.1	6.6	6.6	10.8	8.3	9.3	8.8	14.0	2.5	8.4	5.7
4.2	5.7	5.7	11.3	10.3	11.1	11.3	17.3	4.5	7.6	6.9
4.3	4.1	4.6	11.2	12.5	12.1	12.8	25.4	7.8	7.9	8.1
4.4	2.8	3.4	10.4	13.4	11.4	12.9	15.2	10.0	6.1	9.1
4.5	2.0	2.5	8.6	12.3	10.0	11.7	9.5	12.8	5.5	9.8
4.6	1.4	1.6	6.4	10.0	7.0	9.2	2.2	15.8	5.6	8.5
4.7	0.8	1.0	3.6	6.6	4.4	6.5	0.2	15.4	4.1	7.3
4.8	0.5	0.6	1.7	3.7	2.3	4.1	0.1	10.8	3.0	6.8
4.9	0.2	0.3	0.9	1.9	1.1	2.2	0.2	6.8	2.7	5.6
5.0	0.1	0.2	0.3	0.9	0.8	1.0	-	4.4	1.9	3.8
5.1	0.1	0.1	0.2	0.4	0.5	0.4	-	2.6	0.8	2.9
5.2	*	*	*	0.1	0.2	0.2	-	0.7	0.9	1.6
5.3	*	*	*	0.1	*	0.1	-	0.3	1.0	0.9
5.4	*	*	*	*	*	*	-	0.1	0.4	0.4
5.5 & Above	-	*	-	*	*	*	-	*	0.1	0.3
Average	3.69	3.74	4.16	4.31	4.21	4.31	4.21	4.57	4.12	4.38

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 13, 2022

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
2.4 & Below	*	*	-	*	-	*	-	-	0.3	0.1
2.5 - 2.6	0.2	0.1	-	*	-	*	-	*	0.9	0.4
2.7 - 2.9	1.0	1.1	-	*	-	*	0.1	*	3.6	1.9
3.0 - 3.2	4.6	4.9	0.1	0.1	-	*	0.6	0.1	7.4	5.7
3.3 - 3.4	5.7	7.5	0.5	0.5	-	0.1	1.4	0.3	9.5	7.9
3.5 - 3.6	9.8	11.3	2.0	1.2	0.1	0.2	1.9	0.8	15.2	11.7
3.7 - 4.2	56.3	52.9	35.7	26.7	2.4	11.0	46.7	29.4	48.5	51.5
4.3 - 4.9	21.6	21.4	61.6	67.0	93.0	80.5	48.4	67.6	14.5	20.2
5.0 - 5.2	0.9	0.7	0.1	3.9	4.2	7.1	0.9	1.6	0.1	0.5
5.3 & Above	*	*	-	0.6	0.3	1.0	*	0.1	-	0.1
Average	3.95	3.93	4.28	4.42	4.58	4.57	4.22	4.38	3.78	3.89
Leaf										
1 - 2	62.5	52.6	17.2	25.2	9.8	6.1	5.3	10.1	82.6	80.6
3	27.3	31.8	61.4	49.3	83.0	48.8	45.1	51.6	15.0	15.9
4	7.9	11.5	19.9	21.8	6.5	39.5	40.5	32.3	2.1	2.9
5	1.9	3.2	1.4	3.4	0.7	5.4	8.3	5.6	0.3	0.5
6	0.3	0.7	*	0.3	-	0.1	0.7	0.4	0.1	0.1
7	*	0.2	-	*	-	*	*	*	*	*
8	*	*	-	*	-	*	*	*	-	*
Average	2.30	2.53	3.03	3.02	2.98	3.45	3.54	3.34	1.88	1.87
HVI Trash 1/										
00	0.1	0.1	-	*	-	-	-	-	0.1	0.3
01	31.6	23.4	4.3	5.6	0.2	0.3	0.3	0.8	53.3	53.3
02	33.8	30.9	14.3	21.3	20.8	6.8	6.4	10.7	34.9	31.3
03	17.5	19.4	28.5	25.3	47.8	19.5	19.4	22.9	8.1	9.5
04	8.5	11.3	27.6	20.8	22.9	25.7	25.0	25.1	2.3	3.3
05	4.2	6.4	14.2	13.4	5.4	21.9	21.3	18.9	0.8	1.3
06	2.1	3.6	6.6	7.2	1.8	13.8	13.7	11.2	0.3	0.5
07	1.1	2.1	2.6	3.5	0.8	7.0	7.3	5.7	0.1	0.2
08	0.5	1.2	1.1	1.6	0.3	3.1	3.7	2.7	*	0.1
09	0.3	0.7	0.5	0.7	-	1.2	1.7	1.2	*	0.1
10	0.1	0.4	0.2	0.3	-	0.5	0.7	0.5	*	*
11	0.1	0.2	*	0.1	-	0.2	0.4	0.2	*	*
12	*	0.1	*	0.1	-	*	0.1	0.1	*	*
13	*	0.1	-	*	-	*	*	*	*	*
14	*	*	*	*	-	*	*	*	*	*
15	*	*	-	*	-	*	*	*	-	*
16	*	*	-	*	-	*	*	*	-	*
17	*	*	-	*	-	*	-	*	-	*
18 & Above	*	*	-	*	-	*	*	*	-	*
Average	0.24	0.28	0.37	0.37	0.32	0.46	0.47	0.43	0.16	0.17
UNIFORMITY 2/										
74 & Below	*	*	-	-	-	-	*	*	0.1	*
75	0.1	0.1	-	*	-	-	*	*	0.3	0.4
76	0.6	0.5	0.1	*	-	-	0.1	*	2.1	1.9
77	3.0	2.6	1.1	0.2	0.1	*	0.3	0.1	7.0	6.3
78	9.7	10.2	5.3	1.2	0.4	0.3	1.2	0.7	17.2	16.2
79	23.7	24.7	18.5	6.1	2.8	2.1	5.6	4.4	31.9	29.1
80	33.0	31.6	33.0	21.2	16.8	9.6	20.2	16.8	29.7	29.8
81	22.3	22.2	30.1	36.9	37.3	29.6	34.7	31.9	10.1	13.4
82	6.6	7.0	10.8	27.3	32.7	37.5	25.7	30.8	1.4	2.6
83	1.0	1.0	1.2	6.4	8.6	17.3	9.5	13.2	0.2	0.3
84	0.1	0.1	-	0.7	1.3	3.3	2.3	1.9	*	*
85 & Above	-	*	-	*	-	0.2	0.3	0.2	-	-
Average	80.29	80.29	80.68	81.49	81.74	82.13	81.61	81.80	79.60	79.74
Tenderable 3/	79.2	73.0	78.1	86.2	91.3	89.5	93.4	95.9	73.5	78.5
SAMPLES CLASSED										
Week	155,475		4,547		1,194		35,144		103,633	
Season		1,055,947		1,737,698		1,001,381		1,251,754		1,194,327

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 13, 2022

Quality MIKE	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
2.4 & Below	0.2	0.1	-	-	*	*	-	-	-	*
2.5 - 2.6	1.6	0.9	*	*	*	*	0.1	*	0.2	0.1
2.7 - 2.9	4.9	3.9	0.1	*	0.1	0.1	0.9	*	1.0	0.7
3.0 - 3.2	11.2	10.6	0.9	0.4	0.8	0.4	1.7	*	3.4	1.4
3.3 - 3.4	12.8	11.9	2.4	1.0	2.4	0.8	0.1	0.2	5.1	2.2
3.5 - 3.6	14.7	14.6	5.2	2.4	5.2	2.2	0.8	0.6	7.7	3.6
3.7 - 4.2	42.6	43.6	48.1	34.3	41.8	35.5	43.8	11.5	42.5	27.0
4.3 - 4.9	11.8	14.1	42.8	60.3	48.1	59.3	52.7	79.3	34.9	55.2
5.0 - 5.2	0.2	0.3	0.5	1.5	1.5	1.6	-	7.8	3.6	8.2
5.3 & Above	*	*	*	0.1	0.1	0.1	-	0.5	1.5	1.5
Average	3.69	3.74	4.16	4.31	4.21	4.31	4.21	4.57	4.12	4.38
Leaf										
1 - 2	74.0	67.1	10.1	8.1	5.0	8.5	10.8	6.8	49.5	66.6
3	21.8	26.7	51.1	47.1	45.8	50.6	56.0	50.7	36.7	26.5
4	3.5	5.0	31.3	35.5	38.4	35.0	27.6	37.7	11.1	5.3
5	0.6	1.0	6.7	8.4	8.9	5.5	4.7	4.6	2.2	1.2
6	0.1	0.2	0.7	0.9	1.5	0.4	1.0	0.2	0.3	0.3
7	*	*	0.1	0.1	0.2	*	-	-	0.1	0.1
8	*	*	*	*	0.1	*	-	-	0.1	*
Average	2.09	2.24	3.37	3.47	3.57	3.39	3.29	3.40	2.57	2.25
HVI Trash 1/										
00	0.1	*	-	*	-	*	-	-	*	*
01	40.3	31.7	1.2	1.0	0.2	0.7	0.6	0.4	20.0	30.7
02	39.8	41.5	12.6	10.9	5.4	8.4	10.3	8.5	36.3	40.6
03	13.3	16.5	25.4	23.7	17.6	20.5	22.9	21.8	22.9	16.8
04	4.2	6.1	25.1	25.1	23.4	24.8	26.6	26.4	10.8	6.3
05	1.4	2.4	16.9	18.3	21.2	20.4	19.2	20.7	5.2	2.6
06	0.5	1.0	9.6	10.7	14.7	12.9	9.9	12.2	2.4	1.3
07	0.3	0.4	4.9	5.6	8.4	6.8	4.4	5.9	1.1	0.7
08	0.1	0.2	2.4	2.6	4.5	3.1	2.3	2.5	0.5	0.4
09	*	0.1	1.1	1.2	2.3	1.3	1.1	1.0	0.3	0.2
10	*	*	0.5	0.5	1.2	0.6	0.8	0.4	0.2	0.1
11	*	*	0.2	0.2	0.6	0.2	1.0	0.2	0.1	0.1
12	*	*	0.1	0.1	0.3	0.1	0.6	0.1	*	*
13	*	*	*	*	0.1	*	0.2	*	*	*
14	-	*	*	*	0.1	*	0.1	*	*	*
15	*	*	*	*	*	*	-	-	*	*
16	*	*	*	*	*	*	-	-	*	*
17	*	*	-	*	*	*	-	-	*	*
18 & Above	*	*	*	*	*	*	-	-	*	*
Average	0.19	0.21	0.42	0.43	0.49	0.45	0.44	0.44	0.26	0.22
UNIFORMITY 2/										
74 & Below	0.1	*	-	-	-	-	-	-	-	-
75	0.3	0.2	*	*	-	-	-	*	-	-
76	1.8	1.2	*	0.1	*	*	0.1	*	*	*
77	6.1	4.4	0.1	0.4	*	*	0.1	*	0.2	0.2
78	16.0	12.0	1.0	2.4	0.1	0.1	0.5	0.1	2.3	1.2
79	27.7	23.7	5.8	11.2	0.9	1.2	0.9	1.0	9.3	8.6
80	27.4	29.6	23.0	30.8	8.7	9.6	1.6	7.6	24.5	28.7
81	15.0	20.0	37.7	34.0	30.1	30.6	8.6	25.4	37.0	36.3
82	4.6	7.3	24.6	16.5	40.3	38.5	24.5	41.4	22.2	17.8
83	0.8	1.5	6.7	4.0	18.2	17.9	55.4	20.8	4.2	4.9
84	0.1	0.2	1.0	0.5	1.5	2.0	8.2	3.5	0.3	2.2
85 & Above	*	*	0.1	*	0.1	0.1	0.2	0.1	*	0.1
Average	79.84	80.18	81.48	81.09	82.16	82.13	82.98	82.29	81.25	81.29
Tenderable 3/	64.4	66.6	89.1	89.2	92.1	95.3	94.5	88.1	82.8	83.6
SAMPLES CLASSED										
Week	243,338		249,329		164,813		3,131		23,184	
Season		2,626,939		2,432,346		2,470,492		271,735		319,001

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 13, 2022

Color Grade	Leaf	VISALIA			Quality Designation	VISALIA	
		Week	Season			Week	Season
01	1	49.0	47.5		MIKE	-	*
	2	9.2	14.8		2.4 & Below	0.1	*
	3	0.1	0.1		2.5 - 2.6	2.9	0.5
	4	-	-		2.7 - 2.9	5.3	1.4
	5	-	-		3.0 - 3.2	4.9	1.6
	6	-	-		3.3 - 3.4	1.1	2.8
	7	-	-		3.5 - 3.6	56.9	55.3
Total -----		58.3	62.4		3.7 - 4.2	28.8	38.2
02	1	19.8	15.7		4.3 - 4.9	*	*
	2	12.6	16.8		5.0 - 5.2	-	*
	3	2.5	1.4		5.3 & Above	-	*
	4	0.1	*		Average	4.02	4.13
	5	-	*		ALL RANGE MIKE		
	6	-	*		2.4 & Below	-	*
	7	-	-		2.5	-	*
Total -----		35.0	33.9		2.6	0.1	*
03	1	0.1	0.2		2.7	0.5	0.1
	2	0.9	1.6		2.8	0.9	0.2
	3	0.6	0.7		2.9	1.4	0.3
	4	0.2	0.1		3.0	1.0	0.4
	5	*	*		3.1	1.6	0.4
	6	-	-		3.2	2.7	0.7
	7	-	-		3.3	2.1	0.7
Total -----		1.8	2.6		3.4	2.8	0.9
04	1	-	*		3.5	0.4	1.1
	2	0.1	0.3		3.6	0.8	1.8
	3	0.4	0.2		3.7	2.2	2.9
	4	0.1	*		3.8	2.1	4.1
	5	-	*		3.9	6.5	6.9
	6	-	*		4.0	9.6	10.9
	7	-	-		4.1	16.3	14.3
Total -----		0.6	0.6		4.2	20.2	16.2
05	1	-	*		4.3	16.1	15.6
	2	0.2	0.1		4.4	10.3	12.6
	3	1.1	0.1		4.5	2.0	6.4
	4	0.9	0.1		4.6	0.3	2.6
	5	0.2	*		4.7	*	0.8
	6	*	*		4.8	*	0.2
	7	*	*		4.9	*	*
Total -----		2.5	0.3		5.0	*	*
06	1	-	-		5.1	-	*
	2	-	*		5.2	-	*
	3	0.4	*		5.3 & Above	-	*
	4	0.7	*		Average	4.02	4.13
	5	0.4	*		STRENGTH 1/		
	6	0.2	*		36 & Below	4.8	1.4
	7	*	*		37	2.4	1.4
Total -----		1.7	0.1		38	4.3	2.7
07	1	-	-		39	3.5	4.9
	2	-	*		40	1.8	5.9
	3	*	*		41	1.8	3.3
	4	0.1	*		42	2.5	3.6
	5	-	*		43	7.1	7.7
	6	0.1	*		44	14.7	16.0
	7	*	*		45	19.7	19.8
Total -----		0.2	*		46	14.8	16.0
STAPLE					47	11.1	10.6
44 & Shorter		3.0	1.2		48 & Above	11.3	6.6
46		10.0	12.0		Average	44.55	44.47
48		22.2	26.9		UNIFORMITY		
50		52.4	49.0		83 & Below	2.8	0.4
52 & Longer		12.5	11.0		84	7.6	4.4
Average Staple		49.23	49.13		85	12.6	18.7
Average Length		1.43	1.43		86	28.7	38.7
EXTRANEEOUS MATTER					87	41.0	35.4
Bark		0.4	0.1		88 & Above	7.2	2.4
Grass		0.1	0.4		Average	86.63	86.56
Spindle Twist		4.3	0.6		Samples Classed		
Preparation		*	*		Week	9,480	
All Other		*	0.1		Season		289,959

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.