



Quality of Cotton Classed by Classing Office for the week ending - 4/4/2019

Agricultural Marketing Service
Cotton Market News

** Report Correction on 4/9/2019 **

April 09, 2019

Volume 60, No.36

Classing Office	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
Abilene	12	24.0	18.4	18,822	40	64.8	53.0	1,311,862
Corpus Christi*	-	-	-	-	56	53.8	31.4	1,804,924
Dumas*	-	-	-	-	40	77.3	49.8	1,393,267
Florence	-	-	-	-	53	77.5	58.8	1,251,460
Lamesa*	-	-	-	-	36	66.6	52.7	885,442
Lubbock*	-	-	-	-	72	69.1	54.6	3,401,668
Macon	-	-	-	-	79	71.3	57.6	2,546,067
Memphis	-	-	-	-	81	62.0	44.1	3,056,346
Rayville	2	16.2	13.8	2,064	21	52.6	29.9	545,712
Visalia*	-	-	-	-	34	79.1	61.4	648,788
United States	21	23.2	16.9	28,364	512	67.2	49.8	16,845,536
AMERICAN PIMA								
Visalia	-			-	26			781,205
United States	1			1,189	26			781,205
United States all cotton	22			29,553	527			17,626,741

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed.

MP_CN100

Source: USDA AMS Cotton and Tobacco Market News

Memphis, Tennessee | 901-384-3016 | cottonmn@ams.usda.gov

<https://www.ams.usda.gov/market-news/cotton>

<https://mymarketnews.ams.usda.govcottonmn@ams.usda.gov>

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Apr 04, 2019

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	1.6	3.3	-	16.3	-	0.4	-	0.1	-	5.7
	3	4.3	3.0	-	10.2	-	0.7	-	0.2	-	4.2
	4	1.6	0.3	-	0.7	-	0.1	-	*	-	0.4
	5	0.1	*	-	*	-	*	-	*	-	*
	6	-	*	-	*	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	*	-	-	-	-	-	-
	Total	----	7.6	6.6	-	27.3	-	1.2	-	0.4	-
31	1 - 2	1.0	9.1	-	5.5	-	1.7	-	1.8	-	10.0
	3	9.5	22.5	-	11.2	-	13.2	-	13.7	-	25.6
	4	9.1	7.3	-	3.3	-	6.5	-	6.9	-	10.7
	5	2.6	0.9	-	0.2	-	0.4	-	0.6	-	1.6
	6	0.4	0.1	-	*	-	*	-	*	-	0.1
	7	-	*	-	*	-	-	-	-	-	*
	8	-	*	-	*	-	-	-	*	-	-
	Total	----	22.5	39.9	-	20.1	-	21.9	-	23.1	-
41	1 - 2	0.4	2.3	-	1.7	-	0.9	-	1.9	-	0.9
	3	3.5	13.0	-	5.4	-	17.4	-	23.7	-	6.9
	4	9.2	11.5	-	2.7	-	33.0	-	23.3	-	8.7
	5	11.2	4.9	-	0.4	-	10.7	-	5.3	-	4.2
	6	3.9	1.1	-	*	-	0.7	-	0.4	-	1.2
	7	0.8	0.1	-	*	-	*	-	*	-	0.3
	8	0.1	*	-	*	-	*	-	*	-	-
	Total	----	29.2	32.9	-	10.2	-	62.8	-	54.5	-
51	1 - 2	*	*	-	0.4	-	*	-	0.2	-	*
	3	0.1	0.3	-	2.1	-	0.5	-	1.9	-	*
	4	0.3	0.6	-	1.7	-	2.0	-	2.4	-	0.1
	5	1.1	0.7	-	0.3	-	1.8	-	1.3	-	0.1
	6	1.1	0.4	-	*	-	0.3	-	0.2	-	0.2
	7	0.8	0.1	-	*	-	*	-	*	-	0.2
	8	0.3	*	-	*	-	*	-	*	-	-
	Total	----	3.6	2.2	-	4.6	-	4.6	-	6.1	-
61	1 - 2	-	-	-	*	-	-	-	*	-	-
	3	-	*	-	0.1	-	*	-	0.1	-	-
	4	-	*	-	0.1	-	*	-	0.1	-	-
	5	-	*	-	*	-	*	-	*	-	-
	6	-	*	-	*	-	*	-	*	-	*
	7	-	*	-	*	-	-	-	*	-	-
	8	-	*	-	*	-	-	-	*	-	-
	Total	----	-	*	-	0.3	-	*	-	0.1	-
71	1 - 2	-	-	-	*	-	*	-	*	-	-
	3	-	-	-	*	-	-	-	*	-	-
	4	-	-	-	*	-	-	-	*	-	-
	5	-	-	-	*	-	-	-	*	-	-
	6	-	-	-	*	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	-	-	-	*	-	*	-	*	-
12 & 22	1 - 2	0.1	0.2	-	4.0	-	*	-	*	-	0.5
	3	0.1	0.5	-	3.9	-	*	-	*	-	1.1
	4	*	0.1	-	0.7	-	*	-	*	-	0.2
	5	*	*	-	*	-	-	-	*	-	*
	6	-	-	-	*	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	*	-	-	-	-	-	-
	Total	----	0.3	0.8	-	8.6	-	*	-	*	-
32	1 - 2	0.1	0.5	-	1.0	-	*	-	0.1	-	0.5
	3	0.8	2.3	-	3.1	-	0.4	-	1.0	-	3.7
	4	2.3	1.6	-	1.5	-	0.4	-	0.6	-	3.3
	5	1.8	0.5	-	0.2	-	*	-	0.1	-	0.9
	6	0.5	0.1	-	*	-	*	-	*	-	0.1
	7	0.2	*	-	*	-	-	-	-	-	*
	8	*	*	-	*	-	-	-	-	-	-
	Total	----	5.8	4.9	-	5.8	-	0.9	-	1.8	-
42	1 - 2	*	0.3	-	0.5	-	*	-	0.4	-	0.1
	3	0.9	1.7	-	2.8	-	1.1	-	4.5	-	0.7
	4	4.2	2.3	-	2.4	-	3.3	-	4.0	-	1.1
	5	8.0	1.5	-	0.6	-	1.4	-	0.8	-	0.9
	6	2.7	0.5	-	0.1	-	0.1	-	0.1	-	0.4
	7	0.6	0.1	-	*	-	*	-	*	-	0.1
	8	0.2	*	-	*	-	-	-	*	-	-
	Total	----	16.5	6.5	-	6.3	-	6.0	-	9.8	-

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Apr 04, 2019

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	*	-	0.2	-	*	-	0.1	-	*
	3	*	0.2	-	1.8	-	0.1	-	0.9	-	*
	4	0.1	0.3	-	3.1	-	0.6	-	1.1	-	*
	5	0.5	0.3	-	1.2	-	0.7	-	0.4	-	*
	6	0.5	0.2	-	0.2	-	0.2	-	0.1	-	*
	7	0.5	0.1	-	*	-	*	-	*	-	*
	8	0.6	*	-	*	-	*	-	*	-	-
Total	----	2.3	1.1	-	6.5	-	1.6	-	2.6	-	0.1
62	1 - 2	-	*	-	*	-	*	-	*	-	*
	3	-	*	-	0.4	-	*	-	*	-	*
	4	-	*	-	0.9	-	*	-	*	-	*
	5	-	*	-	0.4	-	*	-	*	-	*
	6	-	*	-	0.1	-	*	-	*	-	*
	7	-	*	-	*	-	*	-	*	-	-
	8	-	*	-	*	-	*	-	*	-	-
Total	----	-	0.1	-	1.8	-	*	-	0.1	-	*
13 & 23	1 - 2	0.2	*	-	0.3	-	-	-	*	-	*
	3	0.1	0.1	-	0.5	-	*	-	*	-	0.1
	4	*	0.1	-	0.2	-	*	-	*	-	0.1
	5	-	*	-	*	-	-	-	-	-	*
	6	-	-	-	*	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	0.3	0.2	-	1.1	-	*	-	*	-	0.3
33	1 - 2	0.6	0.1	-	0.1	-	*	-	*	-	0.1
	3	1.5	0.5	-	0.4	-	*	-	0.1	-	0.8
	4	1.3	0.6	-	0.3	-	*	-	0.1	-	1.2
	5	0.2	0.2	-	0.1	-	*	-	*	-	0.6
	6	*	*	-	*	-	-	-	*	-	0.1
	7	*	*	-	*	-	-	-	*	-	*
	8	-	*	-	*	-	-	-	*	-	-
Total	----	3.6	1.5	-	0.9	-	0.1	-	0.2	-	2.9
43	1 - 2	-	*	-	*	-	*	-	*	-	*
	3	0.4	0.3	-	0.4	-	0.1	-	0.3	-	0.1
	4	2.0	0.7	-	0.5	-	0.3	-	0.4	-	0.3
	5	1.5	0.6	-	0.2	-	0.2	-	0.2	-	0.4
	6	0.6	0.2	-	0.1	-	*	-	*	-	0.2
	7	0.1	0.1	-	*	-	*	-	*	-	0.1
	8	*	*	-	*	-	-	-	*	-	-
Total	----	4.6	1.9	-	1.3	-	0.6	-	0.9	-	1.1
53	1 - 2	-	*	-	*	-	*	-	*	-	*
	3	*	0.1	-	0.4	-	*	-	0.1	-	*
	4	0.5	0.1	-	1.0	-	0.1	-	0.1	-	*
	5	1.1	0.1	-	0.8	-	0.1	-	0.1	-	*
	6	0.6	0.1	-	0.2	-	*	-	*	-	*
	7	0.1	*	-	*	-	*	-	*	-	*
	8	0.1	*	-	*	-	*	-	*	-	-
Total	----	2.4	0.5	-	2.4	-	0.3	-	0.3	-	0.1
63	1 - 2	-	*	-	*	-	-	-	*	-	-
	3	-	*	-	0.2	-	*	-	*	-	-
	4	-	*	-	0.7	-	*	-	*	-	-
	5	*	*	-	0.7	-	*	-	*	-	-
	6	-	*	-	0.2	-	*	-	*	-	-
	7	-	*	-	*	-	*	-	*	-	-
	8	*	*	-	*	-	-	-	*	-	-
Total	----	*	*	-	1.8	-	*	-	*	-	-
24 - 54	1 - 8	1.3	0.7	-	0.4	-	0.1	-	0.1	-	0.7
25 - 35	1 - 8	-	*	-	*	-	-	-	-	-	-
81 - 85	1 - 8	0.1	0.1	-	0.5	-	-	-	*	-	*
STAPLE											
28 & Shorter		-	*	-	-	-	-	-	-	-	-
29		-	*	-	*	-	-	-	*	-	-
30		*	*	-	0.2	-	-	-	*	-	*
31		0.3	0.2	-	0.8	-	-	-	*	-	*
32		0.8	1.1	-	2.2	-	*	-	0.1	-	0.4
33		3.2	4.0	-	5.7	-	0.2	-	1.3	-	2.9
34		14.0	10.1	-	12.5	-	1.9	-	6.6	-	12.2
35		29.9	19.5	-	18.4	-	6.7	-	17.8	-	25.2
36		29.8	26.1	-	22.2	-	13.7	-	24.3	-	25.6
37		20.9	25.0	-	22.0	-	28.7	-	28.2	-	21.8
38		1.0	9.6	-	10.7	-	27.3	-	16.8	-	8.4
39		0.1	3.7	-	4.7	-	17.5	-	4.6	-	2.8
40 & Longer		*	0.7	-	0.7	-	3.9	-	0.4	-	0.6
Average Staple		35.51	36.01	-	35.85	-	37.41	-	36.42	-	35.89
Average Length		1.11	1.12	-	1.12	-	1.17	-	1.14	-	1.12

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Apr 04, 2019

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	-	4.2	-	0.7	-	0.5	-	0.6	-	21.8
	3	-	5.5	-	1.4	-	0.5	-	1.1	-	6.3
	4	-	0.9	-	0.1	-	*	-	0.1	-	0.3
	5	-	*	-	*	-	*	-	*	-	*
	6	-	*	-	-	-	-	-	*	-	*
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	10.7	-	2.2	-	1.0	-	1.7	-	28.4
31	1 - 2	-	9.1	-	2.5	-	0.9	-	2.4	-	12.1
	3	-	25.6	-	17.4	-	5.5	0.2	13.7	-	17.6
	4	-	12.6	-	8.5	-	3.1	0.8	5.7	-	3.6
	5	-	2.3	-	0.5	-	0.3	-	0.6	-	0.5
	6	-	0.2	-	*	-	*	-	*	-	0.1
	7	-	*	-	*	-	-	*	*	-	*
	8	-	*	-	-	-	-	-	-	-	*
	Total	----	49.8	-	28.9	-	9.8	1.1	22.5	-	33.9
41	1 - 2	-	1.1	-	1.3	-	1.6	0.8	1.8	-	3.6
	3	-	8.4	-	16.5	-	17.9	5.0	17.3	-	12.8
	4	-	10.7	-	20.0	-	26.0	3.0	17.3	-	7.4
	5	-	5.5	-	4.3	-	7.9	1.5	4.1	-	1.9
	6	-	1.6	-	0.2	-	0.6	0.7	0.5	-	0.4
	7	-	0.4	-	*	-	*	0.7	0.1	-	0.1
	8	-	0.1	-	*	-	*	0.4	*	-	*
	Total	----	27.7	-	42.4	-	54.0	12.0	41.1	-	26.1
51	1 - 2	-	*	-	0.3	-	0.1	1.2	0.5	-	0.1
	3	-	*	-	3.1	-	1.5	7.6	2.6	-	1.0
	4	-	0.1	-	4.5	-	4.7	3.6	2.0	-	1.1
	5	-	0.2	-	1.8	-	3.5	2.4	0.6	-	0.5
	6	-	0.1	-	0.3	-	0.5	1.0	0.2	-	0.2
	7	-	0.1	-	*	-	*	0.4	0.1	-	0.1
	8	-	*	-	*	-	*	1.2	0.1	-	*
	Total	----	0.5	-	10.0	-	10.3	17.2	6.1	-	2.9
61	1 - 2	-	-	-	*	-	-	0.3	*	-	*
	3	-	-	-	0.1	-	*	7.0	0.1	-	*
	4	-	*	-	0.3	-	*	11.8	0.1	-	*
	5	-	-	-	0.2	-	*	1.5	0.1	-	*
	6	-	-	-	*	-	*	-	*	-	*
	7	-	*	-	*	-	*	-	-	-	*
	8	-	*	-	*	-	-	-	*	-	*
	Total	----	*	-	0.6	-	*	20.5	0.4	-	*
71	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	*	-	-	0.7	*	-	-
	4	-	-	-	*	-	-	0.7	*	-	-
	5	-	-	-	*	-	-	0.7	*	-	-
	6	-	-	-	*	-	-	0.1	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	*	-	-	-	-	-	*
	Total	----	-	-	*	-	-	2.3	0.1	-	*
12 & 22	1 - 2	-	0.3	-	*	-	*	-	0.1	-	0.7
	3	-	0.7	-	0.1	-	*	-	0.2	-	0.5
	4	-	0.2	-	*	-	*	-	*	-	0.1
	5	-	*	-	*	-	*	-	*	-	*
	6	-	*	-	-	-	-	-	*	-	*
	7	-	*	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	1.3	-	0.1	-	0.1	-	0.4	-	1.3
32	1 - 2	-	0.6	-	0.2	-	0.2	-	0.2	-	0.2
	3	-	2.5	-	1.6	-	0.9	-	1.2	-	1.1
	4	-	2.0	-	0.9	-	0.5	-	0.8	-	0.4
	5	-	0.6	-	0.1	-	0.1	-	0.2	-	0.1
	6	-	0.1	-	*	-	*	-	*	-	*
	7	-	*	-	-	-	*	*	*	-	*
	8	-	*	-	-	-	-	-	-	-	*
	Total	----	5.7	-	2.9	-	1.7	*	2.4	-	1.9
42	1 - 2	-	0.1	-	0.2	-	0.5	-	0.4	-	0.1
	3	-	0.7	-	2.3	-	6.5	3.3	4.8	-	0.8
	4	-	0.9	-	3.4	-	8.8	0.9	5.7	-	1.3
	5	-	0.5	-	1.0	-	2.6	0.8	1.8	-	0.7
	6	-	0.2	-	0.1	-	0.2	0.2	0.3	-	0.2
	7	-	0.1	-	*	-	*	0.3	0.1	-	0.1
	8	-	*	-	*	-	*	0.9	*	-	*
	Total	----	2.5	-	7.0	-	18.7	6.4	13.1	-	3.3

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Apr 04, 2019

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	*	-	*	-	*	*	0.2	-	*
	3	-	*	-	0.5	-	0.3	3.9	2.0	-	0.1
	4	-	*	-	1.3	-	1.3	4.3	2.8	-	0.3
	5	-	*	-	0.8	-	0.9	3.4	1.2	-	0.3
	6	-	*	-	0.1	-	0.2	1.6	0.3	-	0.2
	7	-	*	-	*	-	*	-	0.1	-	0.2
	8	-	*	-	*	-	*	0.2	0.1	-	0.1
Total	----	-	0.1	-	2.8	-	2.7	13.5	6.7	-	1.2
62	1 - 2	-	*	-	*	-	*	-	*	-	*
	3	-	*	-	*	-	*	2.7	0.4	-	*
	4	-	*	-	0.2	-	*	6.7	0.4	-	*
	5	-	*	-	0.2	-	*	4.3	0.2	-	*
	6	-	*	-	0.1	-	*	1.4	*	-	*
	7	-	*	-	*	-	*	0.1	*	-	*
	8	-	-	-	*	-	*	-	*	-	*
Total	----	-	*	-	0.5	-	*	15.3	1.1	-	0.1
13 & 23	1 - 2	-	*	-	*	-	*	-	*	-	*
	3	-	0.1	-	*	-	*	-	*	-	*
	4	-	*	-	*	-	*	-	*	-	*
	5	-	*	-	-	-	-	-	-	-	*
	6	-	*	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	0.2	-	*	-	*	-	*	-	0.1
33	1 - 2	-	0.1	-	*	-	*	-	*	-	*
	3	-	0.4	-	0.2	-	*	-	0.1	-	*
	4	-	0.4	-	0.1	-	*	0.1	0.1	-	0.1
	5	-	0.1	-	*	-	*	0.2	*	-	*
	6	-	*	-	*	-	*	-	*	-	*
	7	-	*	-	-	-	*	-	*	-	*
	8	-	*	-	-	-	-	-	-	-	*
Total	----	-	0.9	-	0.4	-	0.1	0.4	0.2	-	0.1
43	1 - 2	-	*	-	*	-	*	-	0.1	-	*
	3	-	*	-	0.4	-	0.4	1.2	0.5	-	*
	4	-	0.1	-	0.6	-	0.6	0.3	0.8	-	0.1
	5	-	0.1	-	0.2	-	0.2	0.2	0.3	-	0.1
	6	-	*	-	*	-	*	-	0.1	-	0.1
	7	-	*	-	*	-	*	0.1	*	-	*
	8	-	*	-	-	-	*	0.1	*	-	*
Total	----	-	0.3	-	1.2	-	1.3	1.9	1.7	-	0.4
53	1 - 2	-	*	-	*	-	*	-	*	-	-
	3	-	*	-	0.1	-	*	1.2	0.4	-	*
	4	-	*	-	0.2	-	0.1	2.4	0.7	-	0.1
	5	-	*	-	0.2	-	0.1	1.1	0.5	-	0.1
	6	-	*	-	*	-	*	0.5	0.1	-	0.1
	7	-	*	-	*	-	*	-	*	-	0.1
	8	-	*	-	*	-	*	*	*	-	*
Total	----	-	*	-	0.5	-	0.3	5.1	1.8	-	0.3
63	1 - 2	-	-	-	*	-	-	-	*	-	-
	3	-	-	-	*	-	*	-	0.1	-	-
	4	-	*	-	*	-	*	0.5	0.2	-	*
	5	-	*	-	*	-	*	0.7	0.1	-	*
	6	-	-	-	*	-	*	0.1	*	-	*
	7	-	*	-	*	-	*	-	*	-	*
	8	-	*	-	*	-	*	-	*	-	*
Total	----	-	*	-	0.1	-	*	1.3	0.5	-	0.1
24 - 54	1 - 8	-	0.1	-	0.2	-	0.1	1.2	0.3	-	0.1
25 - 35	1 - 8	-	*	-	*	-	*	-	*	-	-
81 - 85	1 - 8	-	*	-	*	-	*	1.7	0.1	-	*
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		-	*	-	-	-	-	-	-	-	-
30		-	*	-	*	-	*	-	*	-	-
31		-	*	-	*	-	*	0.2	0.1	-	*
32		-	0.3	-	0.2	-	*	6.2	0.5	-	*
33		-	2.0	-	1.6	-	0.1	19.5	2.1	-	0.3
34		-	8.7	-	6.8	-	0.9	9.2	4.9	-	1.7
35		-	21.5	-	14.4	-	6.3	25.5	13.6	-	6.0
36		-	27.6	-	19.0	-	19.7	24.6	19.4	-	15.3
37		-	26.6	-	29.5	-	39.9	11.2	25.0	-	28.3
38		-	9.1	-	20.6	-	21.2	3.1	18.4	-	21.2
39		-	3.4	-	7.0	-	8.9	0.4	11.5	-	16.1
40 & Longer		-	0.8	-	0.8	-	3.1	*	4.4	-	11.2
Average Staple		-	36.12	-	36.61	-	37.13	34.91	36.82	-	37.56
Average Length		-	1.13	-	1.14	-	1.16	1.09	1.15	-	1.17

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Apr 04, 2019

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	55.1	20.6	-	1.5	-	1.4	-	2.4	-	13.9
Bark - Level 2	-	*	-	-	-	-	-	-	-	-
Grass - Level 1	-	*	-	0.6	-	0.2	-	0.1	-	*
Grass - Level 2	-	*	-	-	-	*	-	-	-	-
Prep - Level 1	*	*	-	*	-	0.8	-	*	-	*
Prep - Level 2	-	-	-	-	-	*	-	-	-	-
Seed Coat - Level 1	-	*	-	4.0	-	0.1	-	*	-	*
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	*	-	*	-	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	*	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	-	*	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	-	0.1	-	*	-	*	-	*
Plastic - Level 2	-	-	-	-	-	*	-	-	-	-
STRENGTH 1/22 & Below	*	*	-	0.4	-	-	-	*	-	*
23	0.2	0.1	-	0.8	-	-	-	0.1	-	*
24	0.6	0.3	-	1.6	-	*	-	0.5	-	0.1
25	2.0	1.0	-	3.3	-	0.2	-	2.1	-	0.5
26	10.3	3.3	-	5.9	-	1.0	-	5.4	-	2.3
27	22.5	9.7	-	9.6	-	4.1	-	10.7	-	7.1
28	28.6	19.2	-	15.9	-	12.9	-	18.6	-	15.6
29	17.3	22.8	-	20.9	-	28.5	-	23.5	-	20.9
30	11.2	19.0	-	19.1	-	29.4	-	18.8	-	21.4
31	6.3	12.8	-	12.4	-	15.2	-	11.1	-	17.0
32	0.9	7.5	-	5.9	-	5.8	-	5.6	-	9.1
33	*	3.1	-	2.6	-	2.1	-	2.6	-	3.7
34	*	0.9	-	1.1	-	0.6	-	0.9	-	1.5
35	*	0.2	-	0.4	-	0.1	-	0.1	-	0.5
36	-	0.1	-	0.1	-	*	-	*	-	0.1
37	-	*	-	*	-	-	-	*	-	*
38	-	*	-	*	-	-	-	*	-	*
39	-	*	-	-	-	-	-	-	-	-
40 & Above	-	-	-	-	-	-	-	-	-	-
Average	28.55	29.76	-	29.45	-	30.10	-	29.51	-	30.14
Mike										
2.4 & Below	0.2	*	-	*	-	-	-	*	-	0.2
2.5	2.5	0.3	-	*	-	*	-	-	-	0.7
2.6	1.8	0.3	-	*	-	*	-	*	-	0.9
2.7	1.3	0.3	-	*	-	*	-	*	-	1.1
2.8	1.4	0.4	-	*	-	*	-	*	-	1.2
2.9	1.2	0.5	-	*	-	*	-	*	-	1.4
3.0	1.0	0.6	-	0.1	-	*	-	*	-	1.6
3.1	1.9	0.8	-	0.1	-	*	-	*	-	1.9
3.2	3.1	1.3	-	0.1	-	*	-	*	-	2.3
3.3	3.5	1.6	-	0.2	-	*	-	*	-	2.7
3.4	4.4	2.0	-	0.3	-	*	-	0.1	-	3.1
3.5	3.6	2.3	-	0.3	-	*	-	0.2	-	3.8
3.6	4.4	2.8	-	0.4	-	0.1	-	0.3	-	4.5
3.7	4.8	3.7	-	0.6	-	0.1	-	0.6	-	5.1
3.8	5.0	4.4	-	1.0	-	0.3	-	1.0	-	5.5
3.9	6.3	5.3	-	1.3	-	0.5	-	1.7	-	6.2
4.0	8.7	6.6	-	1.8	-	0.9	-	2.9	-	6.9
4.1	7.0	7.9	-	2.6	-	1.7	-	4.5	-	7.4
4.2	7.6	8.4	-	3.9	-	2.8	-	6.5	-	7.5
4.3	5.9	8.6	-	5.4	-	4.3	-	8.7	-	7.7
4.4	6.2	8.9	-	7.3	-	6.4	-	11.0	-	6.8
4.5	6.7	8.9	-	9.2	-	9.3	-	13.2	-	6.3
4.6	5.4	7.8	-	11.0	-	13.4	-	14.3	-	5.1
4.7	3.7	6.0	-	11.6	-	16.6	-	12.9	-	3.7
4.8	1.4	4.2	-	11.0	-	16.7	-	9.7	-	2.6
4.9	0.1	2.7	-	9.1	-	13.1	-	6.0	-	1.8
5.0	0.2	1.6	-	7.1	-	7.4	-	3.5	-	1.0
5.1	0.1	0.9	-	5.5	-	3.5	-	1.8	-	0.5
5.2	*	0.5	-	4.0	-	1.6	-	0.9	-	0.2
5.3	0.2	0.2	-	2.8	-	0.8	-	0.3	-	*
5.4	0.2	0.1	-	1.9	-	0.3	-	0.1	-	*
5.5 & Above	*	*	-	1.3	-	*	-	*	-	*
Average	3.90	4.20	-	4.66	-	4.69	-	4.52	-	3.99

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE

For The Week Ending Apr 04, 2019

Quality Designation	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	-	11.0	-	13.3	-	1.1	21.4	7.4	-	3.1
Bark - Level 2	-	-	-	*	-	-	0.5	0.1	-	-
Grass - Level 1	-	*	-	*	-	0.1	-	0.1	-	*
Grass - Level 2	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	*	-	0.1	-	*	-	*	-	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	*	-	2.4	-	0.1	2.2	0.1	-	0.5
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	*	-	*	-	*	-	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	*	-	*	-	*
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	-	*	-	*	-	-
Other - Level 2	-	*	-	-	-	-	-	-	-	-
Plastic - Level 1	-	*	-	*	-	*	*	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/22 & Below	-	*	-	*	-	*	0.1	*	-	*
23	-	*	-	0.1	-	*	1.6	0.1	-	*
24	-	0.1	-	0.7	-	*	7.8	0.4	-	*
25	-	0.3	-	2.8	-	0.3	5.1	1.0	-	0.1
26	-	1.1	-	8.4	-	1.9	10.4	2.7	-	0.3
27	-	3.8	-	16.8	-	8.3	19.1	6.1	-	1.3
28	-	9.5	-	24.9	-	21.7	26.6	12.8	-	4.5
29	-	16.4	-	23.7	-	29.3	16.3	24.8	-	10.9
30	-	21.0	-	13.7	-	20.7	6.3	24.8	-	16.5
31	-	21.1	-	5.8	-	10.7	2.4	15.0	-	17.1
32	-	15.2	-	2.1	-	4.9	2.6	7.8	-	15.6
33	-	7.6	-	0.7	-	1.7	1.5	3.0	-	11.7
34	-	2.8	-	0.2	-	0.4	0.1	1.0	-	7.7
35	-	0.8	-	0.1	-	0.1	-	0.2	-	5.2
36	-	0.2	-	*	-	*	-	0.1	-	4.5
37	-	*	-	*	-	*	-	*	-	3.4
38	-	*	-	*	-	-	-	*	-	1.1
39	-	*	-	*	-	*	-	-	-	0.1
40 & Above	-	*	-	*	-	*	-	-	-	0.1
Average	-	30.83	-	28.82	-	29.66	28.05	30.02	-	32.20
Mike										
2.4 & Below	-	0.2	-	-	-	-	-	-	-	*
2.5	-	0.4	-	*	-	*	-	*	-	*
2.6	-	0.5	-	*	-	*	-	*	-	0.1
2.7	-	0.6	-	*	-	*	0.1	*	-	0.1
2.8	-	0.7	-	*	-	*	-	*	-	0.1
2.9	-	1.0	-	*	-	*	0.5	*	-	0.1
3.0	-	1.2	-	*	-	*	0.2	*	-	0.2
3.1	-	1.6	-	0.1	-	*	*	*	-	0.3
3.2	-	2.1	-	0.2	-	*	0.3	0.1	-	0.4
3.3	-	2.6	-	0.4	-	*	1.9	0.1	-	0.5
3.4	-	3.2	-	0.7	-	0.1	0.8	0.1	-	0.8
3.5	-	3.9	-	1.0	-	0.1	0.2	0.1	-	1.0
3.6	-	4.4	-	1.4	-	0.2	0.6	0.2	-	1.3
3.7	-	5.0	-	2.2	-	0.4	2.0	0.3	-	1.6
3.8	-	5.7	-	3.4	-	0.7	1.0	0.4	-	2.0
3.9	-	6.3	-	5.2	-	1.1	1.0	0.7	-	2.8
4.0	-	6.8	-	7.6	-	1.7	4.4	1.1	-	3.7
4.1	-	7.0	-	10.1	-	2.8	3.2	1.7	-	5.1
4.2	-	7.0	-	12.5	-	4.5	2.5	2.7	-	6.5
4.3	-	6.8	-	13.3	-	6.3	3.1	3.8	-	8.0
4.4	-	6.4	-	12.3	-	8.6	6.7	4.7	-	9.0
4.5	-	6.0	-	10.3	-	10.6	8.1	6.9	-	9.7
4.6	-	5.4	-	7.8	-	11.7	8.3	9.5	-	10.4
4.7	-	4.6	-	5.3	-	11.7	8.5	12.9	-	9.7
4.8	-	3.6	-	3.2	-	11.0	13.8	15.2	-	8.6
4.9	-	2.7	-	1.8	-	9.3	10.2	14.5	-	6.5
5.0	-	1.9	-	0.8	-	7.3	18.3	11.7	-	4.8
5.1	-	1.2	-	0.3	-	5.3	2.8	7.2	-	3.4
5.2	-	0.7	-	0.1	-	3.4	1.2	3.8	-	1.8
5.3	-	0.4	-	*	-	1.9	0.2	1.7	-	0.9
5.4	-	0.1	-	*	-	0.8	*	0.4	-	0.4
5.5 & Above	-	0.1	-	*	-	0.3	*	0.2	-	0.3
Average	-	4.07	-	4.28	-	4.65	4.59	4.74	-	4.47

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Apr 04, 2019

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
2.4 & Below	0.2	*	-	*	-	-	-	*	-	0.2
2.5 - 2.6	4.3	0.6	-	*	-	*	-	*	-	1.6
2.7 - 2.9	3.9	1.2	-	0.1	-	*	-	*	-	3.6
3.0 - 3.2	5.9	2.7	-	0.3	-	*	-	*	-	5.8
3.3 - 3.4	7.9	3.6	-	0.4	-	*	-	0.1	-	5.8
3.5 - 3.6	8.1	5.2	-	0.8	-	0.1	-	0.5	-	8.3
3.7 - 4.2	39.5	36.3	-	11.3	-	6.4	-	17.1	-	38.8
4.3 - 4.9	29.4	47.2	-	64.6	-	79.8	-	75.7	-	34.1
5.0 - 5.2	0.4	3.0	-	16.5	-	12.6	-	6.1	-	1.8
5.3 & Above	0.5	0.3	-	6.0	-	1.1	-	0.4	-	*
Average	3.90	4.20	-	4.66	-	4.69	-	4.52	-	3.99
Leaf										
1 - 2	4.0	15.9	-	30.2	-	3.1	-	4.8	-	18.0
3	21.3	44.7	-	43.1	-	33.7	-	46.5	-	43.6
4	30.7	25.8	-	20.0	-	46.4	-	39.0	-	26.4
5	28.6	10.1	-	5.5	-	15.4	-	8.8	-	8.8
6	10.7	2.8	-	1.0	-	1.4	-	0.8	-	2.4
7	3.3	0.6	-	0.2	-	0.1	-	*	-	0.7
8	1.4	0.1	-	*	-	*	-	*	-	-
Average	4.36	3.41	-	3.01	-	3.79	-	3.54	-	3.35
HVI Trash 1/										
00	-	*	-	*	-	-	-	-	-	*
01	0.3	2.6	-	7.5	-	0.2	-	0.3	-	4.0
02	5.2	16.7	-	25.0	-	4.8	-	6.4	-	18.3
03	9.8	23.4	-	24.2	-	15.7	-	20.7	-	23.9
04	11.0	19.1	-	17.4	-	22.9	-	26.1	-	19.5
05	11.7	13.3	-	11.1	-	22.0	-	20.8	-	13.2
06	12.4	8.8	-	6.7	-	16.2	-	12.9	-	8.3
07	12.1	5.8	-	3.7	-	9.7	-	6.9	-	5.1
08	10.5	3.9	-	2.0	-	4.9	-	3.3	-	3.1
09	8.2	2.5	-	1.1	-	2.2	-	1.5	-	1.8
10	5.8	1.5	-	0.6	-	0.9	-	0.7	-	1.1
11	4.1	0.9	-	0.3	-	0.3	-	0.3	-	0.8
12	2.6	0.6	-	0.2	-	0.1	-	0.1	-	0.5
13	1.9	0.4	-	0.1	-	0.1	-	*	-	0.3
14	1.3	0.2	-	0.1	-	*	-	*	-	0.1
15	1.0	0.1	-	*	-	*	-	*	-	0.1
16	0.6	0.1	-	*	-	*	-	*	-	*
17	0.5	*	-	*	-	*	-	*	-	*
18 & Above	1.0	0.1	-	*	-	*	-	*	-	*
Average	0.69	0.44	-	0.36	-	0.50	-	0.46	-	0.42
UNIFORMITY 2/										
74 & Below	*	*	-	0.1	-	-	-	*	-	*
75	0.1	0.1	-	0.5	-	-	-	*	-	0.1
76	0.8	0.5	-	1.3	-	-	-	0.2	-	0.6
77	2.2	2.5	-	3.3	-	0.2	-	0.9	-	2.2
78	9.5	9.6	-	7.0	-	1.6	-	4.9	-	7.5
79	19.8	24.4	-	13.2	-	8.3	-	19.0	-	21.0
80	32.2	33.9	-	21.6	-	29.7	-	35.7	-	34.3
81	32.5	22.5	-	25.4	-	39.1	-	28.1	-	24.6
82	2.7	5.6	-	19.8	-	17.4	-	9.5	-	8.3
83	0.1	0.8	-	6.9	-	3.3	-	1.5	-	1.4
84	*	0.1	-	0.9	-	0.4	-	0.2	-	0.1
85 & Above	-	*	-	*	-	*	-	*	-	*
Average	80.33	80.28	-	80.89	-	81.18	-	80.65	-	80.46
Tenderable 3/	24.0	64.8	-	53.8	-	77.3	-	77.5	-	66.6
SAMPLES CLASSED										
Week	18,822		-		-		-		-	
Season		1,311,862		1,804,924		1,393,267		1,251,460		885,442

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Apr 04, 2019

Quality MIKE	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
2.4 & Below	-	0.2	-	-	-	-	-	-	-	*
2.5 - 2.6	-	0.8	-	*	-	*	-	*	-	0.1
2.7 - 2.9	-	2.3	-	*	-	*	0.6	0.1	-	0.3
3.0 - 3.2	-	5.0	-	0.3	-	*	0.6	0.2	-	0.9
3.3 - 3.4	-	5.8	-	1.0	-	0.1	2.7	0.2	-	1.3
3.5 - 3.6	-	8.3	-	2.5	-	0.4	0.8	0.3	-	2.3
3.7 - 4.2	-	37.7	-	40.8	-	11.3	14.0	6.9	-	21.8
4.3 - 4.9	-	35.5	-	54.1	-	69.2	58.7	67.4	-	61.8
5.0 - 5.2	-	3.9	-	1.3	-	16.0	22.3	22.7	-	10.0
5.3 & Above	-	0.6	-	*	-	3.0	0.3	2.3	-	1.6
Average	-	4.07	-	4.28	-	4.65	4.59	4.74	-	4.47
Leaf										
1 - 2	-	15.5	-	5.4	-	3.7	2.4	6.4	-	38.6
3	-	44.0	-	43.8	-	33.6	33.8	44.6	-	40.3
4	-	28.0	-	40.4	-	45.4	35.8	37.0	-	14.8
5	-	9.5	-	9.4	-	15.6	17.2	9.8	-	4.2
6	-	2.3	-	1.0	-	1.6	6.2	1.6	-	1.3
7	-	0.6	-	0.1	-	*	1.8	0.4	-	0.5
8	-	0.1	-	*	-	*	2.9	0.2	-	0.2
Average	-	3.41	-	3.57	-	3.78	4.08	3.58	-	2.86
HVI Trash 1/										
00	-	*	-	-	-	-	-	-	-	*
01	-	2.3	-	0.4	-	0.3	-	0.5	-	12.4
02	-	16.5	-	7.2	-	4.5	3.3	9.0	-	30.3
03	-	23.6	-	20.1	-	13.9	14.6	21.7	-	24.4
04	-	20.3	-	25.0	-	21.4	20.4	23.9	-	14.5
05	-	14.4	-	20.6	-	21.8	16.5	18.4	-	8.0
06	-	9.3	-	13.1	-	16.9	13.0	11.6	-	4.3
07	-	5.6	-	7.2	-	10.6	8.2	6.6	-	2.3
08	-	3.3	-	3.5	-	5.7	6.7	3.5	-	1.3
09	-	1.9	-	1.6	-	2.8	4.8	1.9	-	0.8
10	-	1.1	-	0.7	-	1.3	3.1	1.0	-	0.5
11	-	0.7	-	0.3	-	0.5	2.0	0.6	-	0.4
12	-	0.4	-	0.1	-	0.2	1.8	0.4	-	0.3
13	-	0.2	-	0.1	-	0.1	0.7	0.2	-	0.2
14	-	0.1	-	*	-	*	0.8	0.2	-	0.1
15	-	0.1	-	*	-	*	0.3	0.1	-	0.1
16	-	*	-	*	-	*	0.4	0.1	-	0.1
17	-	*	-	*	-	*	0.5	0.1	-	*
18 & Above	-	*	-	*	-	*	2.7	0.2	-	0.1
Average	-	0.43	-	0.46	-	0.51	0.62	0.47	-	0.32
UNIFORMITY 2/										
74 & Below	-	*	-	-	-	-	0.3	0.1	-	*
75	-	*	-	*	-	-	1.5	0.2	-	*
76	-	0.2	-	*	-	*	3.0	0.4	-	0.1
77	-	1.0	-	0.4	-	0.1	4.0	1.5	-	0.4
78	-	4.1	-	2.4	-	0.5	18.1	5.4	-	1.6
79	-	13.6	-	11.6	-	3.4	22.5	15.5	-	5.8
80	-	29.6	-	33.6	-	16.1	28.6	29.7	-	17.4
81	-	32.3	-	35.7	-	33.9	17.0	31.6	-	33.1
82	-	15.5	-	13.4	-	32.3	4.7	12.3	-	25.4
83	-	3.3	-	2.5	-	12.5	0.2	3.0	-	9.3
84	-	0.4	-	0.3	-	1.2	*	0.5	-	6.0
85 & Above	-	*	-	*	-	*	-	0.1	-	1.0
Average	-	80.94	-	80.98	-	81.81	79.80	80.79	-	81.75
Tenderable 3/	-	69.1	-	71.3	-	62.0	16.2	52.6	-	79.1
SAMPLES CLASSED										
Week	-		-		-		2,064		-	
Season		3,401,668		2,546,067		3,056,346		545,712		648,788

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Apr 04, 2019

Color Grade	Leaf	VISALIA			Quality Designation	VISALIA	
		Week	Season			Week	Season
01	1	-	20.9		MIKE	-	*
	2	-	21.7		2.4 & Below	-	*
	3	-	0.4		2.5 - 2.6	-	0.1
	4	-	*		2.7 - 2.9	-	0.4
	5	-	-		3.0 - 3.2	-	1.0
	6	-	-		3.3 - 3.4	-	2.0
	7	-	-		3.5 - 3.6	-	5.0
Total -----		-	43.0		3.7 - 4.2	-	52.7
02	1	-	6.7		4.3 - 4.9	-	38.7
	2	-	37.7		5.0 - 5.2	-	*
	3	-	6.7		5.3 & Above	-	*
	4	-	0.1		Average	-	4.12
	5	-	*		ALL RANGE MIKE		
	6	-	-		2.4 & Below	-	*
	7	-	-		2.5	-	*
Total -----		-	51.2		2.6	-	*
03	1	-	0.1		2.7	-	0.1
	2	-	2.5		2.8	-	0.1
	3	-	2.1		2.9	-	0.2
	4	-	0.3		3.0	-	0.2
	5	-	*		3.1	-	0.3
	6	-	*		3.2	-	0.5
	7	-	-		3.3	-	0.7
Total -----		-	5.0		3.4	-	1.3
04	1	-	*		3.5	-	2.0
	2	-	0.2		3.6	-	3.0
	3	-	0.3		3.7	-	4.3
	4	-	0.1		3.8	-	6.1
	5	-	*		3.9	-	8.4
	6	-	*		4.0	-	10.4
	7	-	*		4.1	-	11.1
Total -----		-	0.6		4.2	-	12.4
05	1	-	*		4.3	-	13.3
	2	-	*		4.4	-	11.8
	3	-	0.1		4.5	-	7.9
	4	-	*		4.6	-	4.0
	5	-	*		4.7	-	1.4
	6	-	*		4.8	-	0.4
	7	-	*		4.9	-	0.1
Total -----		-	0.1		5.0	-	*
06	1	-	-		5.1	-	*
	2	-	*		5.2	-	*
	3	-	*		5.3 & Above	-	*
	4	-	*		Average	-	4.12
	5	-	-		STRENGTH 1/		
	6	-	*		36 & Below	-	0.4
	7	-	*		37	-	1.0
Total -----		-	*		38	-	2.8
07	1	-	-		39	-	4.2
	2	-	-		40	-	4.3
	3	-	*		41	-	4.8
	4	-	*		42	-	9.7
	5	-	*		43	-	17.0
	6	-	*		44	-	22.4
	7	-	*		45	-	18.7
Total -----		-	*		46	-	9.4
STAPLE	44 & Shorter	-	0.2		47	-	3.6
	46	-	5.1		48 & Above	-	1.7
	48	-	36.1		Average	-	43.85
	50	-	52.7		UNIFORMITY		
	52 & Longer	-	5.9		83 & Below	-	1.1
Average Staple		-	49.18		84	-	6.9
Average Length		-	1.43		85	-	25.0
EXTRANEEOUS MATTER	Bark	-	0.1		86	-	50.4
	Grass	-	0.1		87	-	15.2
	Spindle Twist	-	0.2		88 & Above	-	1.4
	Preparation	-	*		Average	-	86.21
	All Other	-	*		Samples Classed		
					Week	-	
					Season		781,205

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.