



Volume 65, No.29

Classing Office	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
Abilene	4	12.5	4.2	969	35	64.8	48.3	436,792
Corpus Christi*	-	-	-	-	49	82.0	45.3	994,175
Dumas	-	-	-	-	37	58.8	32.9	992,725
Florence*	-	-	-	-	48	72.6	53.8	1,264,841
Lamesa	-	-	-	-	28	71.8	47.5	277,758
Lubbock*	-	-	-	-	56	65.1	41.8	1,239,286
Macon	23	79.6	67.2	17,396	77	88.1	74.3	2,643,313
Memphis	2	87.2	74.3	15,709	73	89.5	73.2	3,012,684
Rayville	-	-	-	-	20	62.3	36.7	252,671
Visalia	8	89.4	74.5	2,932	26	87.8	72.7	270,087
United States	47	80.8	68.3	37,877	449	79.3	59.5	11,384,332
AMERICAN PIMA								
Visalia	5			2,303	22			291,673
United States	5			2,303	23			291,673
United States all cotton	52			40,180	462			11,676,017

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 08, 2024

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color 11 & 21	1 - 2	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
	3	0.5	20.6	-	28.0	-	4.2	-	4.7	-	41.7
	4	0.4	7.7	-	18.6	-	3.6	-	3.5	-	6.9
	5	-	0.9	-	1.7	-	0.1	-	0.2	-	0.3
	6	-	0.1	-	*	-	*	-	*	-	*
	7	-	*	-	*	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	0.9 29.3	-	48.4	-	7.9	-	8.4	-	48.9
31	1 - 2	0.3	7.0	-	2.6	-	7.7	-	10.0	-	6.9
	3	0.9	16.2	-	6.0	-	35.1	-	40.3	-	14.8
	4	0.6	5.9	-	1.8	-	13.0	-	13.6	-	4.9
	5	-	1.2	-	0.1	-	0.9	-	1.1	-	0.7
	6	-	0.1	-	*	-	*	-	*	-	0.1
	7	-	*	-	*	-	-	-	*	-	*
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	1.9 30.4	-	10.5	-	56.8	-	65.0	-	27.4
41	1 - 2	-	0.4	-	0.4	-	0.3	-	0.4	-	0.1
	3	2.0	3.7	-	2.0	-	9.5	-	8.4	-	1.1
	4	7.3	4.5	-	1.2	-	17.5	-	12.2	-	1.9
	5	3.7	3.5	-	0.2	-	5.8	-	3.5	-	1.3
	6	0.8	1.6	-	*	-	0.6	-	0.4	-	0.6
	7	1.3	0.3	-	*	-	*	-	*	-	0.2
	8	0.1	*	-	*	-	*	-	-	-	*
	Total	----	15.3 14.0	-	3.7	-	33.8	-	25.0	-	5.4
51	1 - 2	-	*	-	*	-	*	-	*	-	*
	3	0.2	*	-	0.3	-	*	-	0.2	-	*
	4	2.6	0.1	-	0.3	-	0.1	-	0.3	-	*
	5	9.3	0.4	-	0.1	-	0.1	-	0.1	-	*
	6	17.4	0.8	-	*	-	*	-	*	-	*
	7	12.5	0.5	-	*	-	*	-	*	-	0.1
	8	3.1	0.1	-	-	-	*	-	-	-	*
	Total	----	45.1 1.9	-	0.9	-	0.2	-	0.6	-	0.1
61	1 - 2	-	-	-	*	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	*	-	-
	4	-	-	-	*	-	-	-	*	-	-
	5	-	-	-	*	-	*	-	*	-	-
	6	-	-	-	*	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	- *	- *	*	- *	*	- *	*	-	-
71	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	-
	4	-	-	-	*	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	- -	- *	*	- -	-	- -	-	-	-
12 & 22	1 - 2	0.4	3.3	-	17.8	-	*	-	*	-	5.4
	3	6.7	3.2	-	8.7	-	*	-	*	-	2.5
	4	0.4	0.7	-	1.0	-	*	-	*	-	0.2
	5	-	*	-	0.1	-	*	-	*	-	*
	6	-	*	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	7.5 7.3	-	27.6	-	*	-	*	-	8.1
32	1 - 2	0.4	0.8	-	0.8	-	*	-	*	-	1.4
	3	2.7	3.3	-	2.0	-	0.4	-	0.2	-	3.5
	4	1.1	2.5	-	0.9	-	0.1	-	0.1	-	1.6
	5	-	0.7	-	0.2	-	*	-	*	-	0.3
	6	-	0.1	-	*	-	*	-	*	-	0.1
	7	-	*	-	*	-	*	-	-	-	*
	8	-	-	-	*	-	-	-	-	-	-
	Total	----	4.2 7.4	-	3.8	-	0.6	-	0.4	-	6.8
42	1 - 2	-	*	-	0.2	-	*	-	*	-	*
	3	0.4	0.5	-	0.8	-	0.2	-	0.1	-	0.1
	4	4.9	1.6	-	0.5	-	0.3	-	0.2	-	0.3
	5	2.8	2.0	-	0.1	-	0.1	-	0.1	-	0.3
	6	0.8	1.3	-	*	-	*	-	*	-	0.2
	7	1.9	0.4	-	*	-	*	-	*	-	0.1
	8	0.1	*	-	*	-	*	-	-	-	*
	Total	----	10.8 5.9	-	1.6	-	0.7	-	0.4	-	1.0

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 08, 2024

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	*	-	*	-	-	-	*	-	-
	3	-	*	-	0.2	-	*	-	*	-	*
	4	1.1	*	-	0.2	-	*	-	*	-	*
	5	1.7	0.1	-	*	-	*	-	*	-	*
	6	1.7	0.2	-	*	-	*	-	*	-	*
	7	3.5	0.2	-	*	-	*	-	*	-	*
	8	1.9	0.1	-	-	-	*	-	-	-	*
Total	----	9.8	0.6	-	0.4	-	*	-	0.1	-	*
62	1 - 2	-	-	-	*	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	-
	4	-	-	-	*	-	-	-	*	-	-
	5	-	-	-	*	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	*
	7	-	-	-	*	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	-	-	-	*	-	*
13 & 23	1 - 2	-	0.3	-	1.1	-	-	-	*	-	0.5
	3	1.1	0.4	-	0.8	-	-	-	*	-	0.4
	4	0.2	0.1	-	0.2	-	*	-	*	-	0.1
	5	0.1	*	-	*	-	*	-	-	-	*
	6	-	-	-	*	-	*	-	-	-	-
	7	-	-	-	*	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	1.4	0.8	-	2.1	-	*	-	*	-	0.9
33	1 - 2	-	0.1	-	0.1	-	*	-	*	-	0.2
	3	-	0.7	-	0.2	-	*	-	*	-	0.6
	4	-	0.5	-	0.2	-	*	-	*	-	0.2
	5	-	0.1	-	0.1	-	*	-	*	-	0.1
	6	-	*	-	*	-	*	-	-	-	*
	7	-	*	-	*	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	1.4	-	0.6	-	*	-	*	-	1.1
43	1 - 2	-	*	-	*	-	*	-	*	-	*
	3	0.1	0.1	-	*	-	*	-	*	-	*
	4	0.3	0.3	-	0.1	-	*	-	*	-	*
	5	0.1	0.2	-	*	-	*	-	*	-	*
	6	-	0.1	-	*	-	*	-	*	-	*
	7	0.1	*	-	*	-	-	-	*	-	*
	8	0.1	*	-	*	-	*	-	-	-	-
Total	----	0.7	0.7	-	0.2	-	*	-	*	-	0.1
53	1 - 2	-	-	-	*	-	-	-	*	-	-
	3	-	*	-	*	-	-	-	*	-	-
	4	0.4	*	-	*	-	*	-	*	-	*
	5	0.4	*	-	*	-	*	-	*	-	*
	6	0.1	*	-	*	-	*	-	*	-	-
	7	0.2	*	-	*	-	-	-	*	-	*
	8	-	*	-	*	-	-	-	-	-	-
Total	----	1.1	0.1	-	*	-	*	-	*	-	*
63	1 - 2	-	-	-	*	-	-	-	-	-	*
	3	-	-	-	*	-	-	-	-	-	-
	4	-	-	-	*	-	-	-	*	-	-
	5	-	-	-	*	-	-	-	*	-	-
	6	-	-	-	*	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	-	-	-	*	-	*
24 - 54	1 - 8	1.1	0.3	-	*	-	*	-	*	-	0.1
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	*	-	*	-	-	-	-	-	*
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		-	*	-	*	-	-	-	-	-	-
30		-	*	-	*	-	-	-	*	-	*
31		-	0.3	-	0.3	-	-	-	*	-	0.3
32		2.2	1.6	-	1.7	-	*	-	0.1	-	1.8
33		2.1	4.0	-	6.5	-	0.4	-	1.5	-	6.3
34		9.9	8.9	-	19.0	-	3.0	-	7.8	-	15.3
35		22.2	15.4	-	27.5	-	9.2	-	20.6	-	24.4
36		12.8	21.2	-	22.2	-	21.5	-	31.7	-	24.4
37		48.4	27.4	-	14.7	-	44.5	-	29.6	-	20.9
38		2.2	12.7	-	5.4	-	16.7	-	6.8	-	4.8
39		0.2	6.4	-	2.3	-	4.1	-	1.7	-	1.5
40 & Longer		0.1	2.3	-	0.3	-	0.5	-	0.3	-	0.3
Average Staple		35.97	36.29	-	35.40	-	36.76	-	36.08	-	35.53
Average Length		1.12	1.13	-	1.10	-	1.15	-	1.12	-	1.11

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 08, 2024

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	-	33.3	0.3	2.2	8.3	11.1	-	3.1	64.8	66.0
	3	-	9.9	0.8	2.1	2.0	5.0	-	2.1	9.5	8.7
	4	-	0.4	0.1	0.2	*	0.2	-	*	-	0.3
	5	-	*	-	*	-	*	-	*	-	*
	6	-	*	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	43.6	1.1	4.5	10.3	16.3	-	5.3	74.3	75.1
31	1 - 2	-	10.1	3.2	7.3	19.3	18.9	-	6.9	13.1	7.7
	3	-	20.4	17.4	26.9	45.0	39.8	-	21.9	7.2	9.1
	4	-	5.4	4.3	9.6	6.4	9.4	-	6.0	2.0	3.1
	5	-	0.4	0.4	1.0	0.1	0.7	-	0.3	0.3	0.4
	6	-	*	-	*	-	*	-	*	-	*
	7	-	*	-	*	-	*	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	36.3	25.2	44.8	70.7	69.0	-	35.1	22.6	20.3
41	1 - 2	-	0.1	2.2	1.6	0.4	0.6	-	1.2	0.1	0.1
	3	-	1.0	17.2	17.8	10.7	6.2	-	15.8	0.2	0.2
	4	-	1.8	16.7	16.5	7.1	5.8	-	16.2	0.6	0.4
	5	-	1.0	3.3	4.5	0.5	1.6	-	4.0	1.0	0.2
	6	-	0.3	0.5	0.6	*	0.2	-	0.3	0.3	0.1
	7	-	0.1	0.1	0.1	-	*	-	*	-	*
	8	-	*	-	*	-	-	-	*	-	*
	Total	----	4.2	39.9	41.1	18.7	14.4	-	37.6	2.3	1.0
51	1 - 2	-	*	2.7	0.2	-	*	-	*	-	*
	3	-	*	10.6	2.1	*	*	-	0.2	-	*
	4	-	*	8.6	2.4	*	*	-	0.6	-	*
	5	-	*	2.4	0.8	-	*	-	0.7	-	*
	6	-	0.1	0.4	0.2	-	*	-	0.2	-	*
	7	-	*	0.1	*	-	*	-	*	-	*
	8	-	*	-	*	-	-	-	*	-	*
	Total	----	0.2	24.7	5.7	0.1	0.1	-	1.7	-	*
61	1 - 2	-	*	0.3	*	-	*	-	-	-	-
	3	-	-	0.3	*	-	*	-	-	-	-
	4	-	-	*	*	-	*	-	*	-	-
	5	-	-	*	*	-	*	-	*	-	-
	6	-	-	-	*	-	*	-	*	-	-
	7	-	-	-	*	-	*	-	-	-	-
	8	-	-	-	*	-	-	-	-	-	-
	Total	----	*	0.7	*	-	*	-	*	-	-
71	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	*	-	*	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	*	-	*	-	-	-	-	-	-
12 & 22	1 - 2	-	3.4	-	*	-	*	-	1.6	0.1	1.5
	3	-	2.6	0.1	*	-	*	-	1.2	-	0.5
	4	-	0.4	*	*	-	*	-	0.1	-	*
	5	-	*	-	*	-	-	-	*	-	-
	6	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	6.4	0.1	*	-	*	-	3.0	0.1	2.0
32	1 - 2	-	0.9	*	*	*	*	-	0.9	0.1	0.2
	3	-	3.0	0.2	0.4	0.2	*	-	3.7	0.1	0.5
	4	-	1.4	0.1	0.2	*	*	-	1.5	-	0.3
	5	-	0.3	-	*	-	*	-	0.2	*	0.1
	6	-	*	-	*	-	*	-	*	-	*
	7	-	*	-	*	-	-	-	*	-	*
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	5.6	0.3	0.8	0.2	0.1	-	6.3	0.2	1.0
42	1 - 2	-	*	0.1	*	-	*	-	0.3	-	*
	3	-	0.2	0.8	0.7	*	*	-	3.8	-	*
	4	-	0.5	1.7	0.9	*	*	-	3.8	*	*
	5	-	0.4	0.5	0.3	-	*	-	1.4	0.1	0.1
	6	-	0.2	0.1	0.1	-	*	-	0.4	0.3	*
	7	-	0.1	*	*	-	*	-	0.1	-	*
	8	-	*	-	*	-	-	-	*	-	*
	Total	----	1.5	3.3	2.0	*	0.1	-	9.8	0.5	0.2

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 08, 2024

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color 52	1 - 2	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
	3	-	*	0.2	*	-	*	-	*	-	-
	4	-	*	1.4	0.2	-	*	-	0.1	-	-
	5	-	*	1.0	0.3	-	*	-	0.2	-	-
	6	-	*	0.5	0.2	-	*	-	0.2	-	*
	7	-	*	0.1	0.1	-	*	-	0.1	*	*
	8	-	*	-	*	-	*	-	0.1	-	*
	8	-	*	*	*	-	-	-	*	-	*
Total	----	-	0.1	3.2	0.8	-	*	-	0.8	*	*
62	1 - 2	-	-	0.1	*	-	-	-	-	-	-
	3	-	-	0.1	*	-	*	-	*	-	-
	4	-	-	*	*	-	*	-	*	-	-
	5	-	-	*	*	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	*	-	-
	7	-	*	-	*	-	-	-	-	-	-
	8	-	*	-	*	-	-	-	-	-	-
	8	-	*	-	*	-	-	-	-	-	-
Total	----	-	*	0.2	*	-	*	-	*	-	-
13 & 23	1 - 2	-	0.2	-	*	-	-	-	*	-	0.1
	3	-	0.2	-	*	-	-	-	0.1	-	*
	4	-	0.1	-	*	-	-	-	*	-	*
	5	-	*	-	-	-	-	-	*	-	-
	6	-	*	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	0.5	-	*	-	-	-	0.2	-	0.1
33	1 - 2	-	0.1	-	*	-	*	-	*	0.1	0.1
	3	-	0.5	-	*	*	*	-	*	-	0.1
	4	-	0.3	*	*	-	*	-	*	-	*
	5	-	0.1	-	*	-	*	-	*	-	*
	6	-	*	-	*	-	-	-	*	-	-
	7	-	*	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
Total	----	-	1.0	*	*	*	*	-	0.1	0.1	0.2
43	1 - 2	-	*	*	*	-	*	-	*	-	*
	3	-	*	0.2	*	-	*	-	*	-	*
	4	-	0.1	0.2	*	-	*	-	0.1	-	*
	5	-	0.1	0.1	*	-	*	-	0.1	-	*
	6	-	0.1	0.1	*	-	*	-	0.1	-	*
	7	-	*	*	*	-	-	-	*	-	-
	8	-	*	-	*	-	-	-	-	-	-
	8	-	*	-	*	-	-	-	-	-	-
Total	----	-	0.4	0.5	0.1	-	*	-	0.2	-	*
53	1 - 2	-	*	*	*	-	*	-	-	-	-
	3	-	*	0.4	*	-	*	-	*	-	-
	4	-	*	0.2	*	-	*	-	*	-	-
	5	-	*	0.1	*	-	*	-	*	-	-
	6	-	*	*	*	-	*	-	*	-	-
	7	-	*	-	*	-	*	-	*	-	-
	8	-	*	-	*	-	-	-	-	-	-
	8	-	*	-	*	-	-	-	-	-	-
Total	----	-	*	0.6	0.1	-	*	-	*	-	-
63	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	-
	4	-	*	-	*	-	*	-	*	-	-
	5	-	*	-	*	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-
	7	-	*	-	*	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
Total	----	-	*	-	*	-	*	-	*	-	-
24 - 54	1 - 8	-	0.2	0.1	*	-	-	-	*	-	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	*	-	*	-	-	-	-	-	-
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		-	*	-	-	-	-	-	-	-	-
30		-	0.1	-	*	-	*	-	*	-	-
31		-	0.6	-	*	-	*	-	*	-	-
32		-	2.3	0.1	0.2	*	*	-	0.6	-	*
33		-	5.9	1.3	1.6	*	0.1	-	2.5	-	0.2
34		-	12.3	6.5	6.8	0.1	0.4	-	7.5	1.3	1.5
35		-	19.6	14.9	17.1	7.2	4.9	-	16.7	13.0	6.9
36		-	23.1	25.8	27.5	19.5	19.2	-	26.7	22.6	17.3
37		-	22.6	39.9	33.6	48.1	49.0	-	29.6	39.6	34.5
38		-	8.6	8.1	10.4	18.2	20.9	-	11.3	18.2	22.1
39		-	3.6	2.6	2.5	6.8	4.9	-	4.4	4.3	12.6
40 & Longer		-	1.3	0.8	0.4	0.1	0.7	-	0.7	0.9	5.0
Average Staple		-	35.81	36.35	36.27	36.98	37.02	-	36.27	36.78	37.27
Average Length		-	1.12	1.13	1.13	1.16	1.16	-	1.13	1.15	1.16

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 08, 2024

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	73.4	13.8	-	0.1	-	*	-	1.6	-	6.4
Bark - Level 2	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	-	0.5	-	0.4	-	*	-	0.3	-	0.2
Grass - Level 2	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	*	-	*	-	-	-	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	*	-	0.6	-	*	-	*	-	0.1
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	*	-	*	-	*	-	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	-	*	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	-	*	-	0.1	-	*	-	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/22 & Below	-	0.1	-	0.5	-	-	-	-	-	*
23	-	0.1	-	0.6	-	-	-	-	-	0.1
24	0.2	0.3	-	1.4	-	*	-	*	-	0.2
25	0.4	0.8	-	2.7	-	*	-	*	-	0.6
26	2.2	1.6	-	5.0	-	0.1	-	0.1	-	2.4
27	7.7	3.3	-	8.2	-	0.8	-	1.0	-	5.8
28	5.8	6.3	-	11.3	-	3.4	-	6.1	-	11.4
29	8.4	10.3	-	14.1	-	11.3	-	18.4	-	16.8
30	18.3	14.8	-	14.8	-	23.5	-	28.1	-	19.7
31	39.1	16.8	-	12.6	-	29.9	-	24.9	-	17.8
32	10.0	15.1	-	10.6	-	19.4	-	13.7	-	11.7
33	6.6	13.5	-	8.7	-	7.9	-	5.7	-	7.2
34	0.2	10.6	-	5.4	-	2.7	-	1.6	-	3.9
35	1.1	4.9	-	2.9	-	0.8	-	0.4	-	1.6
36	-	1.2	-	1.1	-	0.2	-	0.1	-	0.6
37	-	0.3	-	0.2	-	*	-	*	-	0.1
38	-	*	-	*	-	-	-	-	-	*
39	-	*	-	*	-	-	-	-	-	*
40 & Above	-	*	-	-	-	-	-	-	-	*
Average	30.78	31.63	-	30.37	-	31.33	-	30.88	-	30.65
Mike										
2.4 & Below	3.1	0.1	-	*	-	-	-	-	-	*
2.5	3.6	0.2	-	*	-	*	-	*	-	*
2.6	0.1	0.2	-	0.1	-	*	-	*	-	*
2.7	0.6	0.4	-	0.1	-	*	-	*	-	*
2.8	2.0	0.5	-	0.1	-	*	-	*	-	*
2.9	2.3	0.6	-	0.2	-	*	-	*	-	*
3.0	1.4	1.0	-	0.2	-	*	-	*	-	0.1
3.1	17.3	1.2	-	0.4	-	*	-	*	-	0.1
3.2	3.6	1.5	-	0.6	-	*	-	*	-	0.2
3.3	14.1	1.7	-	0.8	-	*	-	0.1	-	0.4
3.4	5.1	2.4	-	1.1	-	*	-	0.2	-	0.5
3.5	3.1	3.0	-	1.3	-	*	-	0.2	-	0.7
3.6	4.4	3.4	-	1.7	-	*	-	0.4	-	1.1
3.7	4.6	4.1	-	2.2	-	0.1	-	0.6	-	1.6
3.8	6.5	4.8	-	3.0	-	0.1	-	1.1	-	2.3
3.9	7.2	6.0	-	3.9	-	0.2	-	1.6	-	3.0
4.0	1.1	6.4	-	5.2	-	0.4	-	2.5	-	3.5
4.1	4.3	6.6	-	6.8	-	0.8	-	3.6	-	4.5
4.2	4.2	7.1	-	8.6	-	1.5	-	4.9	-	5.8
4.3	4.4	8.0	-	10.2	-	2.5	-	6.3	-	7.2
4.4	2.6	8.0	-	10.8	-	3.8	-	7.5	-	8.0
4.5	4.0	8.3	-	10.7	-	5.7	-	8.6	-	9.0
4.6	0.1	7.3	-	9.5	-	8.0	-	9.4	-	10.1
4.7	-	5.7	-	7.6	-	10.2	-	9.8	-	10.5
4.8	-	4.2	-	5.7	-	12.4	-	9.6	-	9.2
4.9	-	3.0	-	3.8	-	13.9	-	9.0	-	7.0
5.0	-	2.1	-	2.4	-	13.0	-	8.1	-	5.4
5.1	-	1.2	-	1.6	-	10.6	-	6.5	-	3.9
5.2	-	0.6	-	0.8	-	7.9	-	4.7	-	2.5
5.3	-	0.4	-	0.4	-	4.7	-	2.8	-	1.8
5.4	-	0.1	-	0.1	-	2.5	-	1.4	-	1.0
5.5 & Above	-	*	-	0.1	-	1.5	-	1.0	-	0.5
Average	3.50	4.17	-	4.34	-	4.86	-	4.66	-	4.53

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 08, 2024

Quality Designation	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	-	14.7	6.0	1.4	*	*	-	1.0	3.9	1.3
Bark - Level 2	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	-	0.1	-	0.1	*	*	-	*	0.1	0.3
Grass - Level 2	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	*	*	*	-	*	-	*	-	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	*	0.7	0.1	*	*	-	*	0.6	0.5
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	*	-	*	-	*	-	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	-	-	-	*	-	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	-	*	*	*	*	*	-	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/22 & Below	-	*	-	*	-	*	-	-	-	-
23	-	*	-	*	-	*	-	-	-	*
24	-	0.2	*	*	-	*	-	0.1	-	*
25	-	0.7	0.2	0.1	-	*	-	0.4	-	0.2
26	-	2.0	1.6	0.4	*	0.1	-	1.4	1.3	1.0
27	-	4.9	9.1	2.2	0.1	0.7	-	3.3	2.0	1.9
28	-	9.5	20.4	7.7	8.9	5.7	-	6.4	10.8	5.1
29	-	14.3	20.2	17.3	41.6	24.9	-	12.0	28.3	11.2
30	-	16.9	22.5	25.2	40.4	39.0	-	22.0	32.3	15.3
31	-	17.1	16.3	23.1	8.7	21.6	-	27.0	19.1	16.6
32	-	14.7	6.0	14.1	0.3	6.4	-	17.4	4.0	16.6
33	-	10.1	2.4	6.3	*	1.4	-	7.1	0.9	12.5
34	-	5.6	0.9	2.4	*	0.3	-	1.9	0.6	7.7
35	-	2.7	0.3	0.8	-	0.1	-	0.7	0.4	5.0
36	-	0.9	0.1	0.3	-	*	-	0.3	*	2.9
37	-	0.3	*	0.1	-	*	-	*	-	2.1
38	-	*	-	*	-	-	-	*	-	1.3
39	-	-	-	*	-	-	-	-	*	0.3
40 & Above	-	-	-	*	-	-	-	-	0.1	0.1
Average	-	31.04	29.91	30.90	29.96	30.46	-	30.97	30.18	32.02
Mike										
2.4 & Below	-	*	-	*	-	-	-	-	-	-
2.5	-	*	-	*	-	*	-	-	0.1	*
2.6	-	0.1	*	*	-	*	-	-	-	*
2.7	-	0.1	-	*	-	*	-	*	0.1	*
2.8	-	0.2	*	*	-	*	-	*	0.1	0.1
2.9	-	0.2	*	*	-	*	-	*	0.3	0.1
3.0	-	0.3	0.2	*	-	*	-	0.1	0.1	0.2
3.1	-	0.4	0.1	0.1	-	*	-	0.1	0.5	0.3
3.2	-	0.5	1.0	0.1	-	0.1	-	0.1	-	0.4
3.3	-	0.7	0.9	0.2	-	0.1	-	0.2	0.5	0.6
3.4	-	0.9	0.7	0.2	-	0.2	-	0.4	1.7	0.8
3.5	-	1.2	1.1	0.4	*	0.3	-	0.5	1.0	1.0
3.6	-	1.5	1.8	0.6	*	0.5	-	0.5	3.4	1.5
3.7	-	1.9	3.0	1.1	*	0.8	-	0.6	5.2	2.5
3.8	-	2.2	3.2	1.8	*	1.3	-	0.9	8.6	4.2
3.9	-	2.7	4.5	2.9	0.9	1.9	-	1.2	18.1	6.0
4.0	-	3.4	5.1	4.6	1.0	2.9	-	1.6	12.4	7.3
4.1	-	4.1	9.0	6.4	3.4	4.3	-	2.6	12.3	7.9
4.2	-	5.1	9.3	8.4	8.3	6.1	-	4.0	5.7	7.9
4.3	-	6.1	8.1	10.2	11.0	8.6	-	5.6	2.2	8.2
4.4	-	7.5	10.0	11.4	14.6	11.1	-	6.8	2.6	8.6
4.5	-	8.6	9.6	11.7	14.2	12.4	-	8.3	4.2	8.9
4.6	-	9.6	11.0	11.2	11.1	12.7	-	10.4	2.5	8.7
4.7	-	10.3	8.3	9.7	9.9	11.5	-	11.1	4.2	7.4
4.8	-	9.8	5.5	7.6	6.3	9.2	-	11.4	6.1	5.8
4.9	-	8.1	3.8	5.3	6.6	6.4	-	9.0	5.0	4.3
5.0	-	5.6	2.3	3.1	8.9	4.4	-	7.9	2.9	3.2
5.1	-	3.6	1.3	1.6	3.2	2.6	-	5.7	-	1.6
5.2	-	2.3	0.2	0.7	0.5	1.3	-	4.4	0.1	1.1
5.3	-	1.4	0.1	0.3	*	0.7	-	2.8	-	0.7
5.4	-	0.9	*	0.1	0.1	0.4	-	2.0	-	0.4
5.5 & Above	-	0.9	*	0.1	*	0.4	-	1.7	-	0.3
Average	-	4.50	4.33	4.45	4.56	4.53	-	4.68	4.14	4.35

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 08, 2024

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
2.4 & Below	3.1	0.1	-	*	-	-	-	-	-	*
2.5 - 2.6	3.7	0.4	-	0.1	-	*	-	*	-	*
2.7 - 2.9	4.9	1.5	-	0.3	-	*	-	*	-	0.1
3.0 - 3.2	22.4	3.6	-	1.2	-	*	-	0.1	-	0.4
3.3 - 3.4	19.2	4.1	-	1.9	-	*	-	0.3	-	0.9
3.5 - 3.6	7.5	6.4	-	3.0	-	0.1	-	0.6	-	1.8
3.7 - 4.2	28.1	35.0	-	29.8	-	3.2	-	14.3	-	20.5
4.3 - 4.9	11.1	44.5	-	58.2	-	56.6	-	60.3	-	61.1
5.0 - 5.2	-	4.0	-	4.8	-	31.4	-	19.4	-	11.9
5.3 & Above	-	0.5	-	0.6	-	8.7	-	5.2	-	3.2
Average	3.50	4.17	-	4.34	-	4.86	-	4.66	-	4.53
Leaf										
1 - 2	1.7	32.6	-	51.0	-	12.2	-	15.1	-	56.2
3	14.9	35.9	-	39.7	-	48.9	-	52.7	-	30.0
4	19.7	17.1	-	8.0	-	31.3	-	26.7	-	9.6
5	18.2	8.4	-	1.1	-	7.0	-	4.9	-	2.8
6	20.8	4.2	-	0.2	-	0.6	-	0.5	-	1.0
7	19.5	1.5	-	*	-	*	-	*	-	0.4
8	5.3	0.3	-	*	-	*	-	-	-	*
Average	5.21	3.15	-	2.51	-	3.35	-	3.23	-	2.42
HVI Trash 1/										
00	-	*	-	*	-	*	-	*	-	0.5
01	-	11.6	-	15.4	-	1.4	-	1.8	-	31.3
02	3.8	24.3	-	36.6	-	15.1	-	15.8	-	29.7
03	8.8	20.7	-	25.7	-	25.5	-	26.3	-	17.7
04	6.7	13.8	-	12.9	-	22.9	-	23.6	-	9.6
05	9.1	8.8	-	5.5	-	15.9	-	15.7	-	4.9
06	9.8	5.9	-	2.2	-	9.5	-	8.8	-	2.6
07	6.5	4.2	-	0.9	-	5.2	-	4.4	-	1.5
08	5.4	3.0	-	0.4	-	2.5	-	2.0	-	0.9
09	6.9	2.3	-	0.2	-	1.2	-	0.9	-	0.6
10	6.3	1.7	-	0.1	-	0.5	-	0.4	-	0.4
11	7.8	1.2	-	0.1	-	0.2	-	0.2	-	0.2
12	7.4	0.9	-	*	-	0.1	-	0.1	-	0.1
13	6.6	0.6	-	*	-	*	-	*	-	0.1
14	5.7	0.4	-	*	-	*	-	*	-	*
15	4.1	0.2	-	*	-	*	-	*	-	*
16	3.0	0.1	-	*	-	*	-	*	-	*
17	1.5	0.1	-	*	-	*	-	*	-	*
18 & Above	0.5	0.1	-	*	-	*	-	*	-	*
Average	0.87	0.39	-	0.27	-	0.41	-	0.40	-	0.25
UNIFORMITY 2/										
74 & Below	0.1	*	-	*	-	-	-	-	-	*
75	0.3	0.1	-	*	-	-	-	*	-	0.1
76	2.8	0.6	-	0.4	-	-	-	*	-	0.7
77	6.2	2.8	-	1.5	-	*	-	*	-	3.2
78	27.6	10.1	-	4.0	-	0.2	-	0.2	-	10.6
79	48.2	20.5	-	10.3	-	1.5	-	1.9	-	23.0
80	11.8	25.8	-	24.2	-	6.8	-	12.4	-	31.3
81	2.7	23.6	-	36.4	-	18.5	-	32.5	-	23.2
82	0.4	13.7	-	20.0	-	33.4	-	35.2	-	7.2
83	-	2.6	-	3.0	-	27.9	-	15.8	-	0.6
84	-	0.1	-	0.2	-	10.1	-	1.8	-	*
85 & Above	-	*	-	*	-	1.5	-	0.1	-	*
Average	79.08	80.52	-	81.07	-	82.60	-	82.01	-	80.28
Tenderable 3/	12.5	64.8	-	82.0	-	58.8	-	72.6	-	71.8
SAMPLES CLASSED										
Week	969		-		-		-		-	
Season		436,792		994,175		992,725		1,264,841		277,758

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 08, 2024

Quality MIKE	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
2.4 & Below	-	*	-	*	-	-	-	-	-	-
2.5 - 2.6	-	0.1	*	*	-	*	-	-	0.1	*
2.7 - 2.9	-	0.5	0.1	*	-	*	-	0.1	0.4	0.2
3.0 - 3.2	-	1.1	1.3	0.2	-	0.1	-	0.3	0.6	0.9
3.3 - 3.4	-	1.5	1.6	0.4	-	0.3	-	0.6	2.2	1.3
3.5 - 3.6	-	2.7	3.0	1.1	*	0.7	-	1.0	4.4	2.5
3.7 - 4.2	-	19.4	34.0	25.2	13.6	17.2	-	10.9	62.3	35.9
4.3 - 4.9	-	59.9	56.2	67.2	73.7	72.0	-	62.6	26.9	51.9
5.0 - 5.2	-	11.5	3.8	5.4	12.6	8.3	-	18.0	3.0	6.0
5.3 & Above	-	3.2	0.1	0.5	0.1	1.4	-	6.5	-	1.3
Average	-	4.50	4.33	4.45	4.56	4.53	-	4.68	4.14	4.35
Leaf										
1 - 2	-	48.2	9.0	11.4	28.0	30.6	-	14.2	78.2	75.5
3	-	37.9	49.4	50.3	57.9	51.2	-	48.9	17.0	19.2
4	-	10.3	32.9	30.2	13.5	15.5	-	28.7	2.7	4.3
5	-	2.4	7.3	6.9	0.6	2.4	-	6.8	1.5	0.8
6	-	0.8	1.2	1.0	*	0.3	-	1.1	0.7	0.1
7	-	0.3	0.2	0.1	-	*	-	0.2	-	*
8	-	0.1	*	*	-	-	-	*	-	*
Average	-	2.62	3.43	3.36	2.86	2.88	-	3.32	2.04	2.04
HVI Trash 1/										
00	-	*	-	*	-	*	-	-	-	*
01	-	17.8	0.7	1.4	2.6	6.2	-	2.3	38.5	41.3
02	-	35.1	10.8	14.5	25.9	28.1	-	15.8	39.1	36.3
03	-	22.5	25.1	26.5	32.7	29.0	-	25.7	13.6	12.8
04	-	11.8	24.7	24.0	22.7	18.5	-	22.6	3.4	5.0
05	-	5.9	18.2	16.0	10.5	9.7	-	15.2	1.6	2.3
06	-	2.9	10.3	8.9	3.8	4.6	-	8.9	1.1	1.1
07	-	1.5	5.4	4.6	1.2	2.1	-	4.6	0.9	0.6
08	-	0.9	2.6	2.2	0.4	0.9	-	2.3	0.8	0.3
09	-	0.5	1.3	1.1	0.1	0.4	-	1.2	0.3	0.1
10	-	0.3	0.5	0.5	*	0.2	-	0.6	0.2	0.1
11	-	0.2	0.2	0.2	-	0.1	-	0.4	0.2	*
12	-	0.1	0.1	0.1	*	*	-	0.2	0.1	*
13	-	0.1	0.1	0.1	-	*	-	0.1	0.1	*
14	-	0.1	*	*	-	*	-	0.1	*	*
15	-	*	-	*	-	*	-	*	-	*
16	-	*	-	*	*	*	-	*	-	*
17	-	*	-	*	-	*	-	*	-	*
18 & Above	-	*	*	*	-	*	-	*	-	*
Average	-	0.28	0.43	0.41	0.33	0.33	-	0.41	0.21	0.20
UNIFORMITY 2/										
74 & Below	-	0.1	-	*	-	-	-	*	-	-
75	-	0.3	-	*	*	*	-	*	-	*
76	-	1.0	-	*	*	*	-	*	-	*
77	-	3.6	0.1	0.1	0.1	*	-	0.2	-	0.2
78	-	10.1	0.6	1.2	0.2	0.1	-	1.5	0.2	1.7
79	-	20.8	5.4	6.9	1.3	1.1	-	5.8	9.4	8.4
80	-	28.0	26.6	23.7	19.5	8.6	-	15.4	35.5	25.1
81	-	22.4	37.3	36.8	19.9	24.0	-	29.5	44.5	32.0
82	-	10.5	23.2	24.0	40.9	38.6	-	31.0	10.1	21.8
83	-	2.8	6.4	6.4	13.8	24.3	-	14.9	0.3	8.0
84	-	0.5	0.4	0.8	4.2	3.1	-	1.6	-	2.7
85 & Above	-	0.1	*	*	0.1	0.2	-	0.1	-	0.2
Average	-	80.41	81.44	81.43	82.02	82.31	-	81.78	80.96	81.44
Tenderable 3/	-	65.1	79.6	88.1	87.2	89.5	-	62.3	89.4	87.8
SAMPLES CLASSED										
Week	-		17,396		15,709		-		2,932	
Season		1,239,286		2,643,313		3,012,684		252,671		270,087

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 08, 2024

Color Grade	Leaf	VISALIA		Quality Designation	VISALIA	
		Week	Season		Week	Season
01	1	59.0	12.7	MIKE	-	*
	2	11.5	14.7	2.4 & Below	*	0.1
	3	0.1	0.6	2.5 - 2.6	-	0.6
	4	-	*	2.7 - 2.9	-	1.5
	5	-	-	3.0 - 3.2	1.0	3.4
	6	-	-	3.3 - 3.4	9.0	11.1
	7	-	-	3.5 - 3.6	82.9	76.5
Total -----		70.5	27.9	3.7 - 4.2	7.0	6.7
02	1	6.0	7.2	4.3 - 4.9	-	*
	2	20.6	44.0	5.0 - 5.2	-	*
	3	0.6	10.1	5.3 & Above	-	*
	4	-	0.5	Average	3.93	3.89
	5	-	*	ALL RANGE MIKE	-	*
	6	-	*	2.4 & Below	*	*
	7	-	*	2.5	-	0.1
Total -----		27.2	61.8	2.6	-	0.2
03	1	-	0.1	2.7	-	0.2
	2	1.8	2.8	2.8	-	0.3
	3	0.5	4.4	2.9	-	0.3
	4	-	1.3	3.0	-	0.4
	5	-	0.1	3.1	-	0.8
	6	-	*	3.2	0.6	1.2
	7	-	*	3.3	0.5	2.2
Total -----		2.3	8.7	3.4	3.4	4.2
04	1	-	*	3.5	5.6	6.9
	2	-	0.1	3.6	15.4	9.8
	3	-	0.4	3.7	13.4	13.5
	4	-	0.5	3.8	11.6	16.2
	5	-	0.1	3.9	15.8	15.9
	6	-	0.1	4.0	19.3	12.8
	7	-	*	4.1	7.5	8.3
Total -----		-	1.2	4.2	5.0	4.3
05	1	-	-	4.3	2.0	1.8
	2	-	*	4.4	-	0.5
	3	-	*	4.5	-	0.1
	4	-	0.1	4.6	-	*
	5	-	*	4.7	-	*
	6	-	0.1	4.8	-	*
	7	-	0.1	4.9	-	*
Total -----		-	0.3	5.0	-	*
06	1	-	-	5.1	-	*
	2	-	-	5.2	-	*
	3	-	*	5.3 & Above	-	*
	4	-	*	Average	3.93	3.89
	5	-	*	STRENGTH 1/	-	3.3
	6	-	*	36 & Below	-	4.8
	7	-	*	37	*	6.3
Total -----		-	0.1	38	0.2	6.3
07	1	-	-	39	7.2	7.3
	2	-	-	40	18.5	12.0
	3	-	-	41	22.6	17.4
	4	-	*	42	18.6	16.9
	5	-	*	43	14.9	12.8
	6	-	*	44	11.3	8.4
	7	-	*	45	5.2	3.2
Total -----		-	*	46	1.5	0.9
STAPLE				47	0.1	0.3
44 & Shorter		-	0.9	48 & Above	43.26	42.16
46		0.2	7.7	Average		
48		52.4	33.8	UNIFORMITY	0.1	0.5
50		45.1	45.9	83 & Below	0.2	3.8
52 & Longer		2.3	11.7	84	11.9	20.5
Average Staple		48.99	49.20	85	44.1	48.5
Average Length		1.43	1.43	86	41.3	25.4
EXTRANEEOUS MATTER				87	2.4	1.4
Bark		0.3	0.1	88 & Above	86.74	86.44
Grass		-	0.1	Average		
Spindle Twist		-	0.2	Samples Classed	2,303	291,673
Preparation		-	*	Week		
All Other		0.2	*	Season		

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.