



Quality of Cotton Classed by Classing Office for the week ending - 1/16/2020

Agricultural Marketing Service
Cotton Market News

January 17, 2020

Volume 61, No.25

Classing Office	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
Abilene	33	61.7	42.7	84,021	40	71.9	53.1	1,170,505
Corpus Christi	6	93.1	75.0	13,649	53	83.6	57.6	2,099,443
Dumas	13	88.2	63.9	12,093	41	86.5	61.5	1,534,375
Florence	30	89.3	68.7	31,256	53	84.7	61.2	1,658,381
Lamesa	16	47.5	18.9	8,023	36	55.8	28.1	1,002,413
Lubbock	27	43.2	25.3	33,643	71	53.9	24.8	2,375,446
Macon	63	78.4	63.3	87,023	79	84.6	66.2	3,360,011
Memphis	33	86.3	69.3	53,441	81	90.7	76.9	3,454,045
Rayville	7	54.6	36.1	8,962	21	87.5	67.4	686,004
Visalia	17	74.1	53.2	29,684	31	82.6	65.4	435,139
United States	245	72.6	54.3	361,795	506	79.3	57.9	17,775,762
AMERICAN PIMA								
Visalia	16			30,051	23			506,440
United States	16			30,051	24			506,440
United States all cotton	258			391,846	520			18,282,204

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed.

MP_CN100

Source: USDA AMS Cotton and Tobacco Market News

Memphis, Tennessee | 901-384-3016 | cottonmn@ams.usda.gov

<https://www.ams.usda.gov/market-news/cotton>

<https://mymarketnews.ams.usda.govcottonmn@ams.usda.gov>

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 16, 2020

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	21.1	40.5	33.6	29.6	15.8	13.4	2.9	6.0	14.0	33.0
	3	8.5	9.4	25.4	15.0	9.9	10.8	3.7	6.8	1.8	5.9
	4	0.4	0.4	1.0	1.2	0.2	1.0	0.1	0.4	-	0.3
	5	-	*	*	*	-	*	*	*	-	*
	6	-	-	-	*	-	*	-	*	-	-
	7	-	-	-	*	-	-	-	-	-	-
	8	-	-	-	-	-	*	-	-	-	-
	Total	----	30.1 50.3	59.9 45.9	25.9 25.3	6.7 13.2	15.8 39.2	15.8 39.2	15.8 39.2	15.8 39.2	15.8 39.2
31	1 - 2	6.1	5.8	3.8	4.9	8.5	2.9	3.3	4.2	3.5	4.5
	3	18.6	13.0	9.8	10.8	22.8	17.1	17.0	21.1	10.0	8.1
	4	6.3	5.0	4.6	3.5	5.7	8.5	6.2	8.5	3.7	3.3
	5	0.8	0.7	0.5	0.3	0.1	0.9	0.4	0.7	0.3	0.5
	6	*	*	*	*	-	*	-	*	*	*
	7	-	*	-	*	-	*	-	*	*	*
	8	-	-	-	-	-	*	-	-	-	-
	Total	----	31.8 24.6	18.7 19.4	37.1 29.4	26.8 34.5	17.5 16.5	17.5 16.5	17.5 16.5	17.5 16.5	17.5 16.5
41	1 - 2	0.3	0.2	0.4	1.3	1.1	0.8	4.8	2.9	0.2	0.1
	3	2.2	0.9	4.8	5.1	9.2	10.9	34.7	23.7	1.5	0.6
	4	2.9	1.5	1.7	3.0	10.9	15.9	16.8	16.3	2.2	0.8
	5	1.6	1.0	1.2	0.5	3.8	5.7	1.8	2.4	1.2	0.5
	6	0.5	0.4	0.2	*	0.3	0.6	0.1	0.1	0.4	0.3
	7	0.1	0.1	-	*	-	*	-	*	0.6	0.1
	8	*	*	-	-	-	*	-	-	-	-
	Total	----	7.6 4.1	8.3 10.0	25.3 34.0	58.3 45.5	6.2 2.4	6.2 2.4	6.2 2.4	6.2 2.4	6.2 2.4
51	1 - 2	*	*	-	0.1	0.2	0.2	0.2	0.1	-	*
	3	-	*	-	0.8	3.0	2.3	2.0	1.3	-	*
	4	*	*	*	0.6	3.3	4.4	1.2	1.5	-	*
	5	*	*	*	0.1	0.5	2.2	0.1	0.4	*	*
	6	*	*	-	*	*	0.4	*	0.1	*	*
	7	*	*	-	*	*	*	-	*	0.2	*
	8	0.1	*	-	-	-	*	-	*	-	-
	Total	----	0.2 0.1	0.1 1.8	7.0 9.5	3.6 3.4	0.2 *	0.2 *	0.2 *	0.2 *	0.2 *
61	1 - 2	-	-	-	*	-	-	-	*	-	-
	3	-	-	-	0.1	-	*	-	*	-	-
	4	-	-	-	0.1	-	*	*	*	-	-
	5	-	-	-	*	-	*	-	*	-	-
	6	-	-	-	*	-	*	-	*	-	-
	7	-	-	-	*	-	*	-	*	-	-
	8	*	*	-	*	-	*	-	*	-	-
	Total	----	* *	- 0.2	- *	* *	* *	* *	* *	- -	- -
71	1 - 2	-	-	-	*	-	-	-	-	-	-
	3	-	-	-	*	-	*	-	-	-	-
	4	-	-	-	*	-	-	-	-	-	-
	5	-	-	-	*	-	-	-	-	-	-
	6	-	-	-	*	-	*	-	-	-	-
	7	-	-	-	*	-	*	-	-	-	-
	8	-	-	-	*	-	-	-	*	-	-
	Total	----	- -	- *	- *	- *	- *	- *	- *	- -	- -
12 & 22	1 - 2	3.3	3.7	5.1	7.3	0.4	0.1	0.1	0.1	11.3	7.5
	3	2.2	1.8	2.8	5.0	0.4	0.1	0.1	0.1	2.4	4.0
	4	0.1	0.1	0.1	0.8	*	*	*	*	*	0.3
	5	*	*	-	0.1	-	*	-	*	-	*
	6	-	*	-	*	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	5.6 5.7	8.0 13.2	0.8 0.2	0.2 0.2	13.7 11.8	13.7 11.8	13.7 11.8	13.7 11.8	13.7 11.8
32	1 - 2	1.3	1.5	0.1	0.8	0.2	*	0.1	0.1	4.4	3.1
	3	5.5	3.3	1.0	2.2	0.8	0.3	0.9	0.7	10.1	9.0
	4	3.1	1.7	0.3	1.1	0.3	0.2	0.4	0.4	4.4	4.4
	5	0.9	0.4	*	0.2	*	*	*	*	1.7	0.9
	6	0.1	*	-	*	-	*	*	*	0.2	0.1
	7	-	*	-	*	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	10.8 6.9	1.4 4.3	1.3 0.5	1.4 1.3	20.8 17.4	20.8 17.4	20.8 17.4	20.8 17.4	20.8 17.4
42	1 - 2	0.1	0.1	*	0.4	*	*	0.1	*	0.2	0.1
	3	1.3	0.6	1.3	1.5	0.4	0.2	1.1	0.7	1.0	0.7
	4	2.1	0.9	1.2	1.2	0.6	0.3	0.6	0.7	1.0	1.0
	5	1.5	0.7	0.1	0.3	0.1	0.2	0.1	0.2	1.0	0.8
	6	0.6	0.3	-	*	*	*	*	*	0.4	0.4
	7	0.2	0.1	-	*	-	*	-	*	0.1	0.2
	8	*	*	-	*	-	*	-	-	-	-
	Total	----	5.8 2.8	2.6 3.4	1.2 0.7	1.9 1.6	3.7 3.2	3.7 3.2	3.7 3.2	3.7 3.2	3.7 3.2

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 16, 2020

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	*	-	*	-	*	-	*	-	*
	3	*	*	-	0.3	0.2	*	*	*	-	*
	4	*	*	-	0.4	0.4	0.1	*	*	-	*
	5	*	*	*	0.1	0.1	*	*	*	-	*
	6	0.1	*	*	*	-	*	*	*	-	*
	7	0.1	*	-	*	-	*	*	*	-	*
	8	0.1	0.1	-	*	-	*	-	*	-	-
Total	----	0.3	0.1	*	0.8	0.6	0.1	0.1	0.1	-	*
62	1 - 2	-	*	-	*	-	*	-	*	-	-
	3	-	-	-	*	-	*	-	-	-	-
	4	-	*	-	*	-	*	-	*	-	-
	5	-	*	-	*	-	*	-	*	-	-
	6	-	-	-	*	-	*	-	*	-	-
	7	-	*	-	*	-	*	*	*	-	-
	8	*	*	-	-	-	-	-	-	-	-
Total	----	*	*	-	0.1	-	*	*	*	-	-
13 & 23	1 - 2	0.9	0.6	*	0.2	*	*	-	*	0.3	0.8
	3	0.5	0.3	0.2	0.2	0.1	*	*	*	0.3	0.7
	4	*	*	*	*	-	*	-	*	*	0.1
	5	-	*	-	*	-	-	-	-	-	*
	6	-	-	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	*	-	-	-	-
Total	----	1.5	1.0	0.2	0.4	0.1	*	*	*	0.6	1.6
33	1 - 2	0.3	0.4	-	*	*	*	*	*	3.0	0.8
	3	1.6	0.9	0.1	0.1	0.1	*	0.2	0.1	7.3	2.7
	4	0.9	0.4	*	0.1	0.1	*	0.2	*	3.6	1.7
	5	0.2	0.2	-	*	-	*	*	*	1.8	0.4
	6	*	*	-	*	-	*	-	*	0.3	0.1
	7	-	*	-	*	-	-	-	-	*	*
	8	-	*	-	-	-	-	-	-	-	-
Total	----	3.0	2.0	0.1	0.2	0.2	*	0.5	0.1	16.1	5.7
43	1 - 2	0.1	0.1	-	*	-	*	*	*	0.7	0.1
	3	0.9	0.4	0.2	0.1	*	*	0.2	0.1	1.4	0.5
	4	0.9	0.4	0.3	0.1	0.1	*	0.2	0.1	0.9	0.5
	5	0.6	0.3	*	*	0.1	*	*	*	0.5	0.4
	6	0.2	0.2	-	*	-	*	-	*	0.4	0.2
	7	*	0.1	-	*	-	*	-	*	*	0.1
	8	*	*	-	*	-	*	-	-	-	-
Total	----	2.7	1.5	0.6	0.2	0.2	0.1	0.4	0.2	3.9	1.7
53	1 - 2	-	*	-	*	*	*	-	*	-	-
	3	*	*	-	*	*	*	*	*	-	*
	4	*	*	*	*	-	*	*	*	-	*
	5	*	*	-	*	*	*	*	*	-	*
	6	0.1	0.1	-	*	-	*	*	*	-	*
	7	*	0.1	-	*	-	*	-	*	-	*
	8	*	0.1	-	*	-	*	-	*	-	-
Total	----	0.2	0.2	*	0.1	*	*	0.1	*	-	*
63	1 - 2	-	-	-	*	-	*	-	-	-	-
	3	-	-	-	*	-	*	-	-	-	-
	4	*	*	-	*	-	*	-	*	-	-
	5	-	*	-	*	-	*	-	*	-	-
	6	-	*	-	*	-	*	-	*	-	-
	7	-	*	-	*	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
Total	----	*	*	-	*	-	*	-	*	-	-
24 - 54	1 - 8	0.3	0.6	*	0.1	0.1	*	*	*	1.5	0.5
25 - 35	1 - 8	-	*	-	-	-	-	-	-	-	-
81 - 85	1 - 8	*	0.2	-	*	-	*	-	*	-	*
STAPLE											
28 & Shorter		-	*	-	*	-	-	-	-	-	-
29		*	*	-	*	-	-	-	-	-	*
30		*	0.1	-	0.1	-	-	-	-	0.1	0.6
31		0.6	0.8	*	0.4	-	-	-	*	0.9	2.9
32		2.1	2.9	0.2	1.5	*	*	*	0.1	2.0	7.9
33		5.4	6.8	1.4	4.3	0.4	*	0.3	0.7	10.7	15.0
34		11.0	11.2	2.4	10.2	5.3	0.5	1.9	3.1	28.7	21.3
35		18.1	16.7	5.2	18.8	4.8	2.8	8.5	10.6	21.8	21.1
36		23.5	19.4	11.9	20.9	20.0	10.5	21.0	24.1	16.7	15.9
37		21.5	21.1	23.3	25.3	36.4	27.1	41.4	35.4	14.5	10.4
38		9.9	11.5	31.3	12.9	20.4	34.2	18.9	17.7	2.9	2.9
39		4.9	6.4	19.1	4.6	11.0	21.5	6.0	7.1	1.3	1.4
40 & Longer		2.8	2.9	5.2	0.8	1.5	3.4	2.2	1.2	0.4	0.7
Average Staple		36.00	36.00	37.50	36.07	37.00	37.70	36.93	36.77	35.02	34.65
Average Length		1.12	1.12	1.17	1.13	1.16	1.18	1.15	1.15	1.09	1.08

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 16, 2020

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	8.9	18.1	1.5	9.0	2.1	4.3	0.4	13.7	17.6	50.9
	3	5.8	6.6	2.5	7.0	0.5	3.8	0.3	12.1	1.5	5.3
	4	0.8	0.3	0.4	0.3	0.3	0.3	*	0.7	*	0.2
	5	*	*	*	*	*	*	-	*	-	*
	6	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	15.5 25.1	4.4 16.3	3.0 8.5	0.7 26.5	19.1 56.5	19.1 56.5	19.1 56.5	19.1 56.5	19.1 56.5
31	1 - 2	9.7	3.7	1.1	3.4	4.1	4.2	0.8	3.1	10.7	12.1
	3	16.2	9.8	6.7	12.3	12.5	16.2	4.3	15.0	10.3	10.2
	4	4.6	3.6	5.4	4.2	4.3	6.8	3.0	6.4	1.7	1.7
	5	0.9	0.4	0.6	0.3	0.5	0.7	0.2	0.5	0.1	0.1
	6	*	*	*	*	*	*	-	*	-	*
	7	-	*	-	*	-	*	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	31.5 17.5	13.7 20.2	21.4 27.9	8.4 25.0	22.7 24.1	22.7 24.1	22.7 24.1	22.7 24.1	22.7 24.1
41	1 - 2	0.5	0.1	2.0	2.0	2.1	1.9	0.5	0.9	7.9	2.0
	3	1.2	0.4	21.9	17.7	16.8	16.7	15.9	11.1	17.7	5.0
	4	1.4	0.8	22.0	16.0	21.6	22.7	24.3	13.7	8.1	2.5
	5	1.4	0.5	5.4	3.3	8.3	10.0	6.5	4.2	1.7	0.6
	6	1.1	0.2	0.4	0.2	0.6	1.1	0.6	0.4	0.2	0.1
	7	0.4	*	*	*	-	*	*	*	*	*
	8	0.1	*	-	*	-	*	-	-	-	*
	Total	----	5.9 2.0	51.8 39.2	49.3 52.3	47.8 30.4	35.6 10.2	35.6 10.2	35.6 10.2	35.6 10.2	35.6 10.2
51	1 - 2	-	*	1.0	0.9	0.1	0.1	-	0.1	0.5	0.2
	3	-	*	8.5	7.3	3.4	1.8	1.0	2.3	3.1	0.6
	4	-	*	7.6	6.2	9.7	3.7	5.5	5.0	3.9	0.7
	5	-	*	2.1	1.5	6.7	2.2	5.5	2.3	2.8	0.5
	6	-	*	0.2	0.1	1.8	0.4	2.3	0.4	1.1	0.3
	7	*	*	*	*	*	*	0.6	*	0.2	0.1
	8	0.2	*	-	*	-	*	0.3	*	*	*
	Total	----	0.2 *	19.4 16.0	21.7 8.2	15.3 10.1	11.7 2.4	11.7 2.4	11.7 2.4	11.7 2.4	11.7 2.4
61	1 - 2	-	-	*	*	-	*	-	-	-	*
	3	-	-	0.1	0.1	-	*	-	*	-	*
	4	-	-	0.1	0.1	-	*	-	0.1	*	*
	5	-	-	*	*	-	*	-	0.1	0.1	*
	6	-	-	*	*	-	*	-	*	0.1	*
	7	-	-	*	*	-	-	*	*	*	*
	8	-	-	-	*	-	-	-	-	-	*
	Total	----	- -	0.2 0.2	- *	* 0.1	0.2 *	0.2 *	0.2 *	0.2 *	0.2 *
71	1 - 2	-	-	-	*	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	-
	4	-	-	-	*	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-
	7	-	-	-	*	-	-	-	-	-	-
	8	-	-	*	*	-	-	-	-	-	-
	Total	----	- -	* *	- -	- -	- -	- -	- -	- -	- -
12 & 22	1 - 2	2.5	11.5	0.1	0.4	0.2	0.1	0.1	0.6	0.5	1.2
	3	4.0	6.9	0.1	0.2	0.1	0.1	0.8	0.7	0.2	1.0
	4	0.8	0.6	*	*	*	*	0.1	0.1	*	0.1
	5	*	*	-	*	*	*	-	*	-	*
	6	-	*	-	-	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	7.3 19.0	0.2 0.6	0.2 0.2	1.0 1.4	0.7 2.3	0.7 2.3	0.7 2.3	0.7 2.3	0.7 2.3
32	1 - 2	4.0	4.1	*	0.2	0.1	0.1	0.1	0.3	0.8	0.5
	3	7.9	10.0	0.5	0.9	0.5	0.4	1.9	1.1	2.7	1.1
	4	3.0	4.4	0.3	0.3	0.3	0.3	2.3	0.6	1.0	0.6
	5	0.4	0.8	0.1	*	*	*	0.4	0.1	0.1	0.1
	6	*	0.1	-	*	-	*	-	*	*	*
	7	-	*	-	*	-	*	-	*	-	*
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	15.2 19.4	1.0 1.5	1.0 0.8	4.7 2.1	4.6 2.3	4.6 2.3	4.6 2.3	4.6 2.3	4.6 2.3
42	1 - 2	0.5	0.1	0.2	0.2	*	*	0.1	0.1	0.1	*
	3	0.7	0.5	2.3	1.5	0.6	0.4	2.6	1.1	1.2	0.4
	4	1.7	0.9	2.2	1.3	0.8	0.6	4.9	1.2	1.6	0.6
	5	1.3	0.7	0.8	0.3	0.4	0.3	3.6	0.4	0.5	0.2
	6	0.4	0.3	0.1	*	0.1	*	0.8	0.1	*	*
	7	0.1	0.1	*	*	*	*	*	*	*	*
	8	*	*	-	*	-	-	-	-	-	*
	Total	----	4.6 2.5	5.5 3.3	2.0 1.4	12.1 2.8	3.3 1.4	3.3 1.4	3.3 1.4	3.3 1.4	3.3 1.4

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 16, 2020

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	*	0.1	0.1	-	*	-	*	-	-
	3	-	*	0.7	0.9	*	0.1	0.1	0.2	*	*
	4	*	*	0.9	0.8	0.1	0.1	0.4	0.3	0.1	0.1
	5	*	*	0.3	0.2	0.2	0.1	0.8	0.1	*	*
	6	*	*	*	*	0.1	*	0.8	0.1	*	*
	7	*	*	*	*	*	*	0.3	*	*	*
	8	*	*	*	*	*	*	0.2	*	-	*
Total	----	0.1	*	2.0	2.1	0.5	0.3	2.6	0.7	0.2	0.2
62	1 - 2	-	-	-	*	-	*	-	-	-	-
	3	-	-	*	*	-	*	-	*	*	*
	4	-	-	*	*	-	*	-	*	*	*
	5	-	-	*	*	-	*	-	*	-	-
	6	-	*	*	*	-	*	-	*	-	*
	7	-	-	*	*	-	-	-	*	-	-
	8	-	*	-	*	-	-	*	*	-	*
Total	----	-	*	*	0.1	-	*	*	*	*	*
13 & 23	1 - 2	0.6	2.7	*	*	*	*	-	*	*	0.1
	3	4.0	2.3	*	*	-	*	0.1	*	*	*
	4	0.7	0.3	-	*	-	*	-	*	*	*
	5	*	*	*	*	-	-	-	-	-	-
	6	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	*	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	5.3	5.3	*	*	*	*	0.1	*	*	0.1
33	1 - 2	1.2	1.4	*	*	*	*	-	*	0.2	0.1
	3	3.9	3.6	0.1	*	0.2	*	0.3	0.1	0.7	0.2
	4	1.6	1.6	0.1	*	0.1	*	0.4	0.1	0.1	0.1
	5	0.4	0.3	*	*	*	*	-	*	*	*
	6	*	*	*	*	-	*	-	*	-	*
	7	*	*	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	7.1	7.0	0.2	0.1	0.3	0.1	0.7	0.2	1.0	0.3
43	1 - 2	0.5	0.1	*	*	-	*	*	*	*	*
	3	0.9	0.3	0.4	0.1	0.1	0.1	0.5	0.2	0.1	*
	4	0.6	0.3	0.5	0.1	0.3	0.1	1.6	0.2	0.2	*
	5	0.3	0.2	0.1	*	0.1	*	2.1	0.1	*	*
	6	0.1	0.1	*	*	*	*	0.7	*	*	*
	7	*	*	*	*	-	-	*	*	-	*
	8	-	*	-	*	-	-	-	-	-	*
Total	----	2.4	1.0	1.1	0.2	0.5	0.2	5.0	0.5	0.4	0.1
53	1 - 2	-	*	*	*	-	*	-	-	-	-
	3	-	*	0.1	*	*	*	*	*	*	*
	4	*	*	0.2	0.1	*	*	0.1	*	*	*
	5	-	*	0.1	*	*	*	0.4	*	-	*
	6	-	*	*	*	*	*	0.5	*	-	*
	7	-	*	-	*	-	-	0.1	*	-	*
	8	*	*	-	*	-	-	*	*	-	*
Total	----	*	*	0.3	0.1	0.1	*	1.3	0.1	*	*
63	1 - 2	-	-	-	*	-	*	-	-	-	-
	3	-	-	-	*	-	*	-	-	*	*
	4	-	-	*	*	-	*	-	-	-	*
	5	-	*	*	*	-	*	-	-	-	-
	6	-	*	*	*	-	*	-	-	-	-
	7	-	-	-	*	-	*	-	-	-	-
	8	-	*	-	*	-	-	-	-	-	-
Total	----	-	*	*	*	-	*	-	-	*	*
24 - 54	1 - 8	4.1	1.2	0.2	*	*	*	0.4	0.1	0.4	0.1
25 - 35	1 - 8	0.7	*	-	-	-	-	-	-	-	-
81 - 85	1 - 8	0.2	*	*	*	*	*	-	*	*	*
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		*	*	-	-	-	-	-	-	-	-
30		0.4	0.2	-	*	-	-	-	*	-	-
31		1.8	1.2	0.1	*	-	*	0.1	*	-	-
32		6.6	4.1	0.8	0.5	*	*	0.2	*	0.2	*
33		12.2	9.7	2.8	2.4	*	*	2.6	0.3	0.3	0.3
34		16.2	16.9	7.1	7.7	0.4	0.6	5.4	1.6	2.6	1.9
35		22.3	21.9	15.9	15.2	1.9	5.6	11.2	3.3	8.6	6.3
36		21.7	20.8	23.9	21.2	12.2	20.6	14.5	9.5	20.0	16.4
37		15.4	17.3	28.4	29.4	47.6	40.4	12.7	23.8	26.2	31.2
38		2.7	5.5	14.3	16.7	21.1	19.9	18.9	28.9	21.5	23.9
39		0.7	1.8	5.7	6.2	12.7	10.1	12.7	23.4	16.7	15.9
40 & Longer		0.1	0.6	1.0	0.8	4.1	2.8	21.7	9.2	3.8	4.0
Average Staple		34.94	35.28	36.36	36.44	37.42	37.15	37.54	37.83	37.19	37.32
Average Length		1.09	1.10	1.13	1.14	1.17	1.16	1.17	1.18	1.16	1.17

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 16, 2020

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	16.3	11.2	0.1	0.4	4.8	1.3	1.1	1.9	13.5	9.3
Bark - Level 2	-	*	-	-	-	*	-	-	-	-
Grass - Level 1	*	*	0.3	0.3	0.1	0.2	*	0.3	-	*
Grass - Level 2	*	*	-	-	-	*	-	-	-	-
Prep - Level 1	-	*	*	*	*	*	*	*	-	*
Prep - Level 2	-	-	-	*	-	-	-	-	-	-
Seed Coat - Level 1	-	0.2	*	0.1	-	*	-	*	0.3	0.2
Seed Coat - Level 2	-	-	-	-	-	*	-	-	-	-
Oil - Level 1	-	*	-	*	-	*	-	*	-	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	*	*	-	*	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	0.1	0.1	*	*	-	*	*	*
Plastic - Level 2	-	-	-	-	-	*	-	-	-	-
STRENGTH 1/22 & Below	*	*	*	*	-	-	-	*	*	0.1
23	*	*	*	*	-	-	*	*	*	0.2
24	0.1	0.2	*	0.1	*	*	*	*	0.1	0.6
25	0.3	0.7	*	0.5	0.2	*	0.2	0.2	0.2	1.5
26	0.9	1.8	0.1	1.6	3.6	0.3	1.0	1.0	0.9	3.5
27	3.3	4.3	0.5	4.1	9.2	1.4	3.5	2.6	2.5	6.4
28	6.9	8.2	1.9	8.8	22.6	5.1	8.6	6.6	8.4	11.9
29	14.0	13.0	6.2	15.5	32.7	14.6	18.3	15.9	18.9	17.4
30	18.4	16.5	18.4	21.9	17.4	28.9	25.3	24.8	22.9	19.4
31	17.0	17.1	18.6	19.9	10.3	28.5	23.4	22.5	20.4	16.9
32	13.9	14.1	14.7	13.2	3.2	13.4	11.7	14.9	15.2	12.1
33	10.0	10.3	16.4	7.7	0.4	5.5	5.5	7.6	6.6	6.0
34	6.9	6.9	13.3	4.0	0.2	1.9	1.8	2.8	2.0	2.1
35	3.9	3.8	6.3	1.8	0.1	0.4	0.5	0.8	0.5	0.9
36	2.4	1.9	3.0	0.6	*	*	0.1	0.2	0.2	0.5
37	1.4	0.8	0.3	0.2	-	*	0.1	0.1	0.7	0.4
38	0.6	0.3	*	*	-	*	*	*	0.3	0.1
39	*	*	*	*	-	-	-	-	*	*
40 & Above	-	-	-	-	-	-	-	-	*	*
Average	31.52	31.32	32.36	30.89	29.42	30.96	30.68	30.95	30.86	30.36
Mike										
2.4 & Below	*	*	-	*	-	-	-	*	*	*
2.5	0.1	*	-	-	-	-	-	*	0.1	*
2.6	0.2	*	-	*	-	-	-	*	0.1	0.1
2.7	0.1	0.1	-	*	-	-	-	*	0.2	0.1
2.8	0.3	0.1	-	*	-	*	-	*	0.5	0.2
2.9	0.4	0.2	-	*	-	*	-	*	0.7	0.2
3.0	0.6	0.3	-	0.1	-	*	-	*	0.6	0.3
3.1	0.8	0.5	-	0.2	-	*	*	*	1.1	0.4
3.2	1.3	0.7	*	0.2	-	*	*	*	0.7	0.5
3.3	2.1	1.0	*	0.4	*	*	0.1	*	1.4	0.6
3.4	2.8	1.2	0.1	0.7	*	*	*	*	2.3	0.8
3.5	3.1	1.6	0.3	1.1	*	*	0.1	0.1	2.8	1.2
3.6	3.7	2.2	0.8	1.6	*	*	0.3	0.1	2.3	1.6
3.7	4.5	2.8	1.4	2.4	0.2	0.1	0.5	0.3	3.3	1.9
3.8	4.8	3.4	2.0	3.3	*	0.2	0.8	0.5	3.6	2.4
3.9	4.7	4.3	3.3	4.3	0.1	0.4	1.7	0.8	4.2	2.9
4.0	5.0	5.1	4.8	5.2	0.5	1.0	3.3	1.3	6.1	3.8
4.1	5.0	6.1	6.7	6.6	1.4	1.5	5.0	2.3	4.0	4.6
4.2	5.7	7.3	12.7	7.9	2.9	2.7	6.8	3.7	3.3	5.5
4.3	6.3	8.5	15.3	9.4	8.3	5.0	6.9	5.9	4.4	6.4
4.4	7.8	9.7	13.0	10.6	8.6	8.3	9.9	8.8	9.2	7.6
4.5	8.5	10.0	8.9	10.5	12.1	12.5	11.6	11.9	8.2	8.7
4.6	8.0	9.3	9.2	9.7	19.1	16.2	14.0	14.6	7.6	9.7
4.7	7.4	8.2	7.5	8.9	19.6	17.3	13.2	15.3	8.9	9.9
4.8	6.1	6.4	6.3	6.8	14.5	14.8	12.2	13.4	5.7	9.1
4.9	4.0	4.5	3.5	4.4	8.0	9.7	7.4	9.9	4.9	7.6
5.0	2.9	3.1	0.7	2.8	2.1	5.2	3.3	5.9	3.4	5.7
5.1	2.0	1.8	0.3	1.5	1.3	2.7	1.5	2.9	2.9	3.8
5.2	0.9	0.9	0.4	0.6	0.9	1.4	0.5	1.3	2.4	2.3
5.3	0.6	0.4	1.0	0.3	0.1	0.6	0.3	0.6	2.0	1.2
5.4	0.2	0.1	1.1	0.1	*	0.2	0.3	0.3	1.6	0.6
5.5 & Above	0.1	0.1	0.6	0.2	*	0.1	0.3	0.1	1.2	0.3
Average	4.24	4.34	4.40	4.38	4.62	4.65	4.54	4.63	4.35	4.48

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE

For The Week Ending Jan 16, 2020

Quality Designation	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	17.1	15.5	7.7	3.4	2.8	0.5	28.3	2.9	1.1	1.1
Bark - Level 2	-	-	-	*	-	-	-	-	-	*
Grass - Level 1	*	*	0.1	0.1	*	*	0.1	0.2	-	*
Grass - Level 2	-	-	-	*	-	-	-	-	-	-
Prep - Level 1	-	*	0.1	*	-	*	-	*	-	*
Prep - Level 2	-	-	-	*	-	-	-	-	-	-
Seed Coat - Level 1	0.1	*	*	*	-	*	0.1	*	*	0.6
Seed Coat - Level 2	-	-	-	*	-	-	-	-	-	-
Oil - Level 1	*	*	-	*	-	*	*	*	-	*
Oil - Level 2	-	-	-	*	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	*
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	*	*	-	*	-	*	-	0.1
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	*	*	*	*	*
Plastic - Level 2	-	-	-	-	-	*	-	-	-	-
STRENGTH 1/22 & Below	*	*	*	*	*	*	-	-	-	-
23	*	0.2	*	*	*	*	-	-	-	*
24	0.1	0.5	0.3	0.1	*	*	-	*	*	*
25	0.5	1.1	0.9	0.8	0.3	*	*	0.1	0.3	0.1
26	1.6	2.8	3.4	3.0	1.0	0.4	0.2	0.8	0.5	0.3
27	4.3	6.1	8.8	8.2	5.0	2.8	1.1	2.8	0.7	1.3
28	9.7	11.0	15.5	15.8	18.0	12.1	2.2	6.9	2.8	3.9
29	15.8	16.3	23.1	22.6	31.7	25.9	8.4	18.1	6.5	9.5
30	19.3	19.4	20.6	22.5	27.6	29.1	13.9	25.0	14.1	18.2
31	18.8	17.7	13.4	14.5	11.6	18.0	19.0	19.6	17.9	19.4
32	13.9	12.7	7.8	7.4	3.6	8.0	26.4	14.2	16.5	15.5
33	8.7	7.2	4.1	3.3	0.9	2.9	15.7	7.8	15.4	10.3
34	4.2	3.2	1.5	1.2	0.1	0.8	6.9	3.3	10.3	5.6
35	1.8	1.2	0.6	0.4	0.1	0.2	4.2	1.1	7.0	5.2
36	0.8	0.4	0.2	0.1	*	*	1.4	0.3	4.8	5.4
37	0.3	0.2	*	*	*	*	0.5	0.1	2.4	3.7
38	0.1	0.1	-	*	-	*	*	*	0.6	1.1
39	0.1	*	-	-	-	*	-	-	0.2	0.2
40 & Above	*	*	-	-	-	-	-	-	0.1	0.1
Average	30.93	30.55	29.96	29.96	29.80	30.32	32.06	30.94	32.53	32.21
Mike										
2.4 & Below	0.1	*	-	-	-	-	-	-	-	*
2.5	0.6	0.1	-	*	-	-	-	-	*	*
2.6	1.3	0.2	*	*	-	-	-	*	0.1	*
2.7	1.8	0.3	-	*	-	-	-	*	*	*
2.8	1.6	0.4	-	*	-	*	-	*	*	*
2.9	1.2	0.6	*	*	-	*	-	*	*	0.1
3.0	1.3	0.7	*	*	*	*	-	*	*	0.1
3.1	2.2	0.9	*	*	*	*	*	*	0.1	0.2
3.2	2.2	1.2	*	*	0.1	*	*	*	0.3	0.2
3.3	2.3	1.5	0.1	*	0.1	*	0.2	*	0.1	0.3
3.4	2.6	1.8	0.2	0.1	0.3	0.1	1.6	0.1	0.5	0.4
3.5	2.9	2.0	0.4	0.2	0.6	0.2	1.5	0.1	0.9	0.7
3.6	3.2	2.3	0.5	0.3	1.1	0.5	1.3	0.2	1.0	1.1
3.7	4.0	2.7	0.6	0.4	1.3	0.9	1.7	0.3	1.5	1.5
3.8	4.4	3.2	0.9	0.7	2.2	1.7	1.3	0.6	1.3	2.1
3.9	4.4	3.7	1.7	1.2	3.1	2.7	1.1	1.2	1.7	2.6
4.0	4.6	4.2	2.6	2.0	4.2	4.2	2.4	1.7	2.0	3.9
4.1	4.7	4.9	4.8	3.3	7.0	6.0	3.6	2.9	4.0	5.3
4.2	4.9	5.6	7.4	5.7	9.4	8.4	4.5	4.6	6.7	6.6
4.3	5.6	6.4	10.0	8.7	12.2	10.6	5.7	7.8	8.3	7.7
4.4	6.2	7.3	12.9	12.3	12.2	12.3	7.8	11.3	8.6	9.9
4.5	6.6	8.3	14.2	15.0	11.8	13.1	12.3	15.2	7.8	10.7
4.6	7.0	8.8	14.8	15.4	10.5	12.3	11.1	15.8	9.8	11.6
4.7	6.4	8.7	11.9	13.1	9.1	10.0	14.0	15.5	10.4	10.0
4.8	5.5	7.9	8.0	9.6	6.2	7.2	14.6	11.1	10.3	7.8
4.9	4.5	6.4	4.9	6.1	3.7	4.6	7.9	6.4	6.9	5.3
5.0	3.5	4.7	2.3	3.3	2.5	2.7	4.8	3.1	6.6	4.0
5.1	2.3	2.8	1.2	1.7	1.8	1.4	1.5	1.3	4.7	3.0
5.2	1.1	1.4	0.4	0.6	0.6	0.6	1.1	0.5	2.6	2.0
5.3	0.5	0.6	0.2	0.2	0.1	0.2	*	0.2	1.7	1.4
5.4	0.2	0.2	0.1	0.1	*	0.1	-	0.1	0.6	0.9
5.5 & Above	0.3	0.1	*	*	*	*	*	*	1.3	0.7
Average	4.13	4.34	4.48	4.54	4.41	4.45	4.52	4.56	4.57	4.49

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 16, 2020

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
2.4 & Below	*	*	-	*	-	-	-	*	*	*
2.5 - 2.6	0.3	0.1	-	*	-	-	-	*	0.2	0.1
2.7 - 2.9	0.7	0.3	-	*	-	*	-	*	1.4	0.4
3.0 - 3.2	2.7	1.6	*	0.5	-	*	*	*	2.4	1.3
3.3 - 3.4	4.9	2.2	0.2	1.2	*	*	0.1	*	3.7	1.5
3.5 - 3.6	6.8	3.8	1.1	2.8	*	*	0.4	0.2	5.1	2.7
3.7 - 4.2	29.7	29.0	30.8	29.8	5.2	6.0	18.0	8.9	24.5	21.1
4.3 - 4.9	48.2	56.6	63.7	60.3	90.3	83.7	75.2	79.7	48.9	59.0
5.0 - 5.2	5.8	5.7	1.5	5.0	4.3	9.3	5.3	10.1	8.7	11.9
5.3 & Above	0.9	0.6	2.7	0.6	0.2	1.0	1.0	1.0	4.9	2.1
Average	4.24	4.34	4.40	4.38	4.62	4.65	4.54	4.63	4.35	4.48
Leaf										
1 - 2	33.7	52.9	42.9	44.7	26.4	17.4	11.5	13.4	37.9	50.2
3	41.6	30.9	45.6	41.3	46.9	41.7	59.9	54.5	36.6	32.1
4	16.9	10.6	9.3	12.1	21.7	30.5	25.9	28.0	16.2	12.4
5	5.6	3.5	1.9	1.7	4.8	9.1	2.6	3.8	6.6	3.7
6	1.5	1.2	0.3	0.2	0.3	1.1	0.2	0.2	1.8	1.1
7	0.4	0.5	-	*	*	0.1	*	*	1.0	0.4
8	0.3	0.3	-	*	-	*	-	*	-	-
Average	2.97	2.57	2.69	2.64	3.03	3.34	3.20	3.23	2.93	2.59
HVI Trash 1/										
00	-	*	-	*	-	*	-	*	-	0.1
01	10.8	24.8	9.0	14.3	6.1	4.2	0.8	1.7	14.6	26.3
02	26.4	31.8	41.4	32.6	23.1	16.0	12.8	14.2	27.3	29.2
03	23.7	18.4	24.5	24.2	25.5	19.5	29.2	26.9	22.6	18.8
04	15.5	10.1	12.8	14.5	18.4	18.7	26.9	25.4	14.1	11.1
05	9.1	5.7	6.3	7.7	12.4	15.3	16.7	16.6	9.1	6.3
06	5.5	3.3	2.8	3.7	7.2	11.0	7.8	8.7	5.7	3.5
07	3.4	2.0	1.3	1.7	4.3	7.1	3.4	3.9	3.2	2.0
08	2.1	1.2	0.8	0.7	1.7	4.1	1.3	1.6	1.6	1.1
09	1.3	0.8	0.6	0.3	0.9	2.2	0.5	0.6	0.6	0.7
10	0.7	0.6	0.3	0.1	0.3	1.0	0.2	0.2	0.3	0.4
11	0.5	0.4	0.1	0.1	0.1	0.5	0.1	0.1	0.2	0.3
12	0.3	0.3	0.1	*	*	0.2	0.1	*	0.3	0.1
13	0.2	0.2	*	*	*	0.1	*	*	0.4	0.1
14	0.2	0.2	*	*	*	*	*	*	*	*
15	0.1	0.1	-	*	-	*	*	*	-	*
16	0.1	0.1	-	*	-	*	*	*	-	*
17	*	0.1	-	*	-	*	-	*	-	*
18 & Above	0.1	0.2	-	*	-	*	-	*	-	*
Average	0.35	0.29	0.29	0.29	0.36	0.43	0.40	0.40	0.33	0.28
UNIFORMITY 2/										
74 & Below	*	*	-	*	-	-	-	-	0.1	*
75	0.1	0.1	*	0.1	*	*	-	*	1.3	0.4
76	0.2	0.3	0.1	0.3	*	*	*	*	2.7	1.9
77	1.3	2.0	0.4	1.2	0.2	0.1	*	0.1	5.8	6.9
78	6.2	7.4	2.3	4.1	1.4	0.9	0.4	0.8	13.9	16.9
79	18.3	18.9	10.3	13.0	10.7	4.6	3.1	4.8	32.7	28.8
80	31.5	30.5	36.3	29.0	39.1	20.0	15.1	21.1	29.8	28.7
81	27.8	27.2	36.6	33.0	38.9	43.5	41.6	38.2	11.7	13.1
82	10.9	11.0	11.7	16.3	8.4	25.5	30.7	27.3	1.8	2.9
83	3.1	2.3	2.1	2.9	1.1	4.7	8.4	6.7	0.1	0.4
84	0.5	0.3	0.2	0.2	0.2	0.6	0.7	0.8	*	*
85 & Above	0.1	*	*	*	-	*	*	0.1	-	*
Average	80.70	80.61	80.96	80.94	80.92	81.49	81.72	81.55	79.65	79.72
Tenderable 3/	61.7	71.9	93.1	83.6	88.2	86.5	89.3	84.7	47.5	55.8
SAMPLES CLASSED										
Week	84,021		13,649		12,093		31,256		8,023	
Season		1,170,505		2,099,443		1,534,375		1,658,381		1,002,413

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 16, 2020

Quality MIKE	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
2.4 & Below	0.1	*	-	-	-	-	-	-	-	*
2.5 - 2.6	1.9	0.4	*	*	-	-	-	*	0.1	*
2.7 - 2.9	4.6	1.3	*	*	-	*	-	*	0.1	0.1
3.0 - 3.2	5.7	2.8	*	*	0.1	*	*	*	0.4	0.5
3.3 - 3.4	4.9	3.2	0.3	0.1	0.4	0.1	1.8	0.1	0.7	0.7
3.5 - 3.6	6.1	4.3	0.9	0.4	1.7	0.7	2.8	0.2	1.9	1.8
3.7 - 4.2	27.0	24.2	18.0	13.3	27.2	24.0	14.7	11.2	17.2	21.9
4.3 - 4.9	41.7	53.8	76.7	80.2	65.7	70.1	73.3	83.1	62.1	62.9
5.0 - 5.2	7.0	8.9	3.8	5.6	4.9	4.8	7.4	5.0	14.0	9.0
5.3 & Above	1.0	0.9	0.3	0.4	0.1	0.3	*	0.3	3.5	3.0
Average	4.13	4.34	4.48	4.54	4.41	4.45	4.52	4.56	4.57	4.49
Leaf										
1 - 2	30.1	42.0	6.1	16.2	8.6	10.7	2.0	18.8	38.3	67.1
3	47.2	41.1	43.9	48.1	34.7	39.6	28.0	44.0	37.5	24.0
4	15.4	13.1	39.6	29.5	37.6	34.8	42.9	28.4	17.0	6.7
5	4.7	3.0	9.5	5.7	16.4	13.3	19.6	7.8	5.3	1.6
6	1.7	0.6	0.8	0.4	2.7	1.6	5.8	1.0	1.5	0.5
7	0.5	0.2	*	*	*	*	1.2	0.1	0.3	0.1
8	0.3	*	*	*	*	*	0.5	*	*	*
Average	3.01	2.73	3.55	3.25	3.70	3.55	4.05	3.28	2.87	2.22
HVI Trash 1/										
00	-	*	-	*	-	*	-	-	*	*
01	6.7	13.6	0.8	3.5	1.3	1.7	0.2	3.7	14.6	36.4
02	29.9	33.5	8.0	16.9	8.5	10.7	2.2	19.5	27.0	33.9
03	28.4	24.5	20.8	24.3	15.0	18.1	8.7	21.6	21.7	14.8
04	15.7	13.7	24.3	22.2	18.5	19.3	17.1	18.5	14.9	7.0
05	7.9	7.2	19.7	15.5	17.8	17.0	19.3	14.2	9.5	3.6
06	4.4	3.6	12.6	9.0	14.5	13.2	16.5	9.7	5.6	2.0
07	2.6	1.8	7.1	4.6	10.5	9.1	12.8	6.0	3.3	1.0
08	1.6	0.9	3.6	2.2	6.9	5.5	8.7	3.3	1.7	0.5
09	1.0	0.5	1.7	1.0	3.8	2.9	5.7	1.7	0.9	0.3
10	0.7	0.3	0.8	0.4	2.0	1.4	3.6	0.9	0.4	0.2
11	0.4	0.1	0.3	0.2	0.8	0.6	2.5	0.5	0.2	0.1
12	0.2	0.1	0.1	0.1	0.3	0.3	1.2	0.2	0.1	0.1
13	0.2	*	0.1	*	0.1	0.1	0.4	0.1	*	*
14	0.1	*	*	*	*	*	0.3	*	*	*
15	0.1	*	*	*	*	*	0.3	*	*	*
16	0.1	*	*	*	*	*	0.2	*	-	*
17	*	*	*	*	*	*	0.2	*	*	*
18 & Above	0.1	*	*	*	*	*	0.1	*	-	*
Average	0.34	0.30	0.46	0.40	0.51	0.48	0.61	0.41	0.33	0.23
UNIFORMITY 2/										
74 & Below	0.1	*	-	-	-	-	-	-	-	-
75	0.5	0.1	-	*	-	-	-	-	-	*
76	2.2	0.5	*	*	*	*	-	-	*	*
77	6.7	2.2	0.1	0.1	*	0.1	0.1	0.1	0.2	0.1
78	15.1	7.9	0.7	1.2	0.4	0.5	1.0	0.5	0.9	1.1
79	25.9	20.9	5.0	6.2	3.0	3.3	3.9	3.8	5.2	5.8
80	28.1	32.4	17.3	20.5	16.8	15.7	8.4	16.1	26.6	19.1
81	15.9	25.1	34.5	36.8	36.6	34.5	19.9	36.4	28.1	32.7
82	4.6	9.1	30.3	26.5	34.6	32.6	37.1	31.1	23.5	26.2
83	0.6	1.6	10.4	7.5	7.9	11.9	20.0	10.2	11.9	10.0
84	0.1	0.2	1.6	1.1	0.7	1.3	7.8	1.6	3.5	4.7
85 & Above	-	*	0.1	0.1	0.1	0.1	1.8	0.2	0.1	0.2
Average	79.83	80.48	81.71	81.53	81.74	81.82	82.33	81.77	81.62	81.72
Tenderable 3/	43.2	53.9	78.4	84.6	86.3	90.7	54.6	87.5	74.1	82.6
SAMPLES CLASSED										
Week	33,643		87,023		53,441		8,962		29,684	
Season		2,375,446		3,360,011		3,454,045		686,004		435,139

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 16, 2020

Color Grade	Leaf	VISALIA			Quality Designation	VISALIA	
		Week	Season			Week	Season
01	1	29.6	27.3		MIKE		
	2	9.3	8.4		2.4 & Below	*	*
	3	*	0.1		2.5 - 2.6	*	*
	4	-	-		2.7 - 2.9	0.6	0.1
	5	-	-		3.0 - 3.2	1.4	0.5
	6	-	-		3.3 - 3.4	1.6	1.1
	7	-	-		3.5 - 3.6	3.4	3.0
Total -----		38.9	35.8		3.7 - 4.2	57.8	60.4
02	1	28.0	29.7		4.3 - 4.9	35.1	34.8
	2	29.1	30.9		5.0 - 5.2	*	*
	3	0.9	1.1		5.3 & Above	-	*
	4	*	*		Average	4.10	4.12
	5	*	*		ALL RANGE MIKE		
	6	-	-		2.4 & Below	*	*
	7	-	-		2.5	*	*
Total -----		58.0	61.7		2.6	*	*
03	1	0.5	0.3		2.7	0.1	*
	2	1.6	1.6		2.8	0.2	*
	3	0.3	0.5		2.9	0.3	0.1
	4	*	*		3.0	0.3	0.1
	5	*	*		3.1	0.5	0.2
	6	-	-		3.2	0.6	0.2
	7	-	-		3.3	0.9	0.4
Total -----		2.4	2.4		3.4	0.8	0.7
04	1	*	*		3.5	1.1	1.0
	2	0.3	0.1		3.6	2.3	2.0
	3	0.1	*		3.7	3.6	3.5
	4	*	*		3.8	5.8	6.6
	5	-	*		3.9	8.7	9.9
	6	-	*		4.0	9.9	12.3
	7	-	-		4.1	14.0	13.7
Total -----		0.4	0.1		4.2	15.9	14.4
05	1	-	-		4.3	16.6	14.1
	2	0.1	*		4.4	10.8	11.7
	3	0.1	*		4.5	5.6	6.1
	4	*	*		4.6	1.8	2.1
	5	-	*		4.7	0.4	0.7
	6	-	*		4.8	0.1	0.1
	7	-	*		4.9	*	*
Total -----		0.1	*		5.0	*	*
06	1	-	-		5.1	*	*
	2	-	-		5.2	*	*
	3	*	*		5.3 & Above	-	*
	4	-	-		Average	4.10	4.12
	5	-	-		STRENGTH 1/		
	6	-	-		36 & Below	0.1	0.1
	7	-	-		37	0.2	0.2
Total -----		*	*		38	0.3	1.1
07	1	-	-		39	0.8	2.9
	2	-	*		40	1.3	3.2
	3	-	*		41	2.0	3.0
	4	-	-		42	3.6	5.1
	5	-	-		43	10.0	10.1
	6	-	-		44	20.6	18.3
	7	-	-		45	25.5	25.1
Total -----		-	*		46	20.0	18.8
STAPLE					47	10.8	8.7
44 & Shorter		*	0.4		48 & Above	4.8	3.4
46		1.3	6.6		Average	45.27	44.83
48		19.3	27.3		UNIFORMITY		
50		75.0	61.2		83 & Below	0.6	0.4
52 & Longer		4.4	4.5		84	2.4	4.7
Average Staple		49.65	49.25		85	11.8	16.1
Average Length		1.44	1.43		86	59.3	55.0
EXTRANEEOUS MATTER					87	23.5	22.3
Bark		-	0.1		88 & Above	2.3	1.5
Grass		-	0.1		Average	86.56	86.44
Spindle Twist		0.1	0.2		Samples Classed		
Preparation		-	*		Week	30,051	
All Other		*	*		Season		506,440

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.